
This is an electronic reprint of the original article.
This reprint may differ from the original in pagination and typographic detail.

Author(s): Motohashi, T. & Ono, T. & Katsumata, Y. & Kanno, R. & Karppinen, Maarit & Yamauchi, H.

Title: Electrochemical synthesis and properties of CoO_{2} , the $x=0$ phase of the A_xCoO_{2} systems ($\text{A}=\text{Li}, \text{Na}$)

Year: 2008

Version: Final published version

Please cite the original version:

Motohashi, T. & Ono, T. & Katsumata, Y. & Kanno, R. & Karppinen, Maarit & Yamauchi, H. 2008. Electrochemical synthesis and properties of CoO_{2} , the $x=0$ phase of the A_xCoO_{2} systems ($\text{A}=\text{Li}, \text{Na}$). *Journal of Applied Physics*. Volume 103, Issue 7. 07C902/1-3. ISSN 0021-8979 (printed). DOI: 10.1063/1.2828525.

Rights: © 2008 AIP Publishing. This is the accepted version of the following article: Motohashi, T. & Ono, T. & Katsumata, Y. & Kanno, R. & Karppinen, Maarit & Yamauchi, H. 2008. Electrochemical synthesis and properties of CoO_{2} , the $x=0$ phase of the A_xCoO_{2} systems ($\text{A}=\text{Li}, \text{Na}$). *Journal of Applied Physics*. Volume 103, Issue 7. 07C902/1-3. ISSN 0021-8979 (printed). DOI: 10.1063/1.2828525, which has been published in final form at <http://scitation.aip.org/content/aip/journal/jap/103/7/10.1063/1.2828525>.

All material supplied via Aaltodoc is protected by copyright and other intellectual property rights, and duplication or sale of all or part of any of the repository collections is not permitted, except that material may be duplicated by you for your research use or educational purposes in electronic or print form. You must obtain permission for any other use. Electronic or print copies may not be offered, whether for sale or otherwise to anyone who is not an authorised user.

Electrochemical synthesis and properties of CoO_2 , the $x = 0$ phase of the A_xCoO_2 systems ($\text{A} = \text{Li}, \text{Na}$)

T. Motohashi, T. Ono, Y. Katsumata, R. Kanno, M. Karppinen, and H. Yamauchi

Citation: *Journal of Applied Physics* **103**, 07C902 (2008); doi: 10.1063/1.2828525

View online: <http://dx.doi.org/10.1063/1.2828525>

View Table of Contents: <http://scitation.aip.org/content/aip/journal/jap/103/7?ver=pdfcov>

Published by the [AIP Publishing](#)

Articles you may be interested in

Microstructures and the corresponding magnetic properties of half-doped $\text{Nd}_{0.5}\text{Sr}_{0.5}\text{MnO}_3$ films
J. Appl. Phys. **104**, 103901 (2008); 10.1063/1.3020529

Crystal Structure and Magnetic Properties of $\text{YNi}_{5-x}\text{Al}_x$ Compounds
AIP Conf. Proc. **899**, 782 (2007); 10.1063/1.2733523

Relation between the magnetic properties and the crystal and electronic structures of manganese spinels $\text{LiNi}_{0.5}\text{Mn}_{1.5}\text{O}_4$ and $\text{LiCu}_{0.5}\text{Mn}_{1.5}\text{O}_4 - \delta$ ($0 \leq \delta \leq 0.125$)
J. Appl. Phys. **100**, 093908 (2006); 10.1063/1.2364045

Synthesis and Magnetic Properties of Na_xCoO_2 ($x = 0.4$ & 0.5)
AIP Conf. Proc. **850**, 1211 (2006); 10.1063/1.2355139

Structural and magnetic properties of transition metal substituted ZnO
J. Appl. Phys. **95**, 2582 (2004); 10.1063/1.1644638

The new SR865 **2 MHz Lock-In Amplifier ... \$7950**





Chart recording



FFT displays



Trend analysis

Features

- Intuitive front-panel operation
- Touchscreen data display
- Save data & screen shots to USB flash drive
- Embedded web server and iOS app
- Synch multiple SR865s via 10 MHz timebase I/O
- View results on a TV or monitor (HDMI output)

Specs

- 1 mHz to 2 MHz
- 2.5 nV/ $\sqrt{\text{Hz}}$ input noise
- 1 μs to 30 ks time constants
- 1.25 MHz data streaming rate
- Sine out with DC offset
- GPIB, RS-232, Ethernet & USB

SRS Stanford Research Systems
www.thinksrs.com · Tel: (408)744-9040

Electrochemical synthesis and properties of CoO_2 , the $x=0$ phase of the $A_x\text{CoO}_2$ systems ($A=\text{Li}, \text{Na}$)

T. Motohashi^{a)}

Materials and Structures Laboratory, Tokyo Institute of Technology, Yokohama 226-8503, Japan

T. Ono and Y. Katsumata

Materials and Structures Laboratory, Tokyo Institute of Technology, Yokohama 226-8503, Japan and Interdisciplinary Graduate School of Science and Engineering, Tokyo Institute of Technology, Yokohama 226-8502, Japan

R. Kanno

Interdisciplinary Graduate School of Science and Engineering, Tokyo Institute of Technology, Yokohama 226-8502, Japan

M. Karppinen

Materials and Structures Laboratory, Tokyo Institute of Technology, Yokohama 226-8503, Japan and Laboratory of Inorganic and Analytical Chemistry, Helsinki University of Technology, P.O. Box 6100, FI-02015 TKK, Finland

H. Yamauchi

Materials and Structures Laboratory, Tokyo Institute of Technology, Yokohama 226-8503, Japan, Interdisciplinary Graduate School of Science and Engineering, Tokyo Institute of Technology, Yokohama 226-8502, Japan, and Laboratory of Inorganic and Analytical Chemistry, Helsinki University of Technology, P. O. Box 6100, FI-02015 TKK, Finland

(Presented on 7 November 2007; received 5 November 2007; accepted 17 September 2007; published online 16 January 2008)

Single-phase bulk samples of the “exotic” CoO_2 , the $x=0$ phase of the $A_x\text{CoO}_2$ systems ($A=\text{Li}, \text{Na}$), were successfully synthesized through electrochemical deintercalation of Li from pristine LiCoO_2 samples. The samples of pure CoO_2 were found to be essentially oxygen stoichiometric and possess a hexagonal structure consisting of stacked triangular-lattice CoO_2 layers only. The magnetism of CoO_2 is featured with a temperature-independent susceptibility of the magnitude of 10^{-3} emu/mol Oe, being essentially identical to that of a Li-doped phase, $\text{Li}_{0.12}\text{CoO}_2$. It is most likely that the CoO_2 phase is a Pauli-paramagnetic metal with itinerant electrons. © 2008 American Institute of Physics. [DOI: 10.1063/1.2828525]

The layered cobalt oxide systems, $A_x\text{CoO}_2$ ($A=\text{Li}, \text{Na}$), have attracted increased attention due to recent discoveries of various unconventional transport and magnetic properties. Namely, among the members of the systems, Na_xCoO_2 exhibits a superb thermoelectric property about $x=0.7$,^{1,2} a spin-density-wave excitation at $x=0.75$,³ a charge ordering at $x=0.50$,⁴ and superconductivity about $x=0.35$ with a hydrated form.⁵ The crystals of $A_x\text{CoO}_2$ consist of alternate stacking of a CoO_2 layer and a single atomic layer of A ions. The CoO_2 layer contains a two-dimensional triangular cobalt lattice with possible magnetic frustrations (due to the geometry) that may be underlying aforementioned unconventional electronic states.

As mentioned above, the physical properties sensitively depend on the concentration of A ions. It is thus important to establish the electronic phase diagrams for the $A_x\text{CoO}_2$ systems with respect to x . Nevertheless, properties have remained unclear in the low x regime, i.e., $x < 0.25$, due to the difficulty in sample syntheses. In particular, it is worth synthesizing the $x=0$ phase of the $A_x\text{CoO}_2$ systems, i.e., pure CoO_2 , since it can be regarded as the parent of these systems.

Synthesis of CoO_2 samples was previously reported,^{6,7} but the sample purity was insufficient for the accurate determination of physical properties. Here we report the synthesis and the properties of pure CoO_2 bulk samples.

Bulk samples of pure CoO_2 phase were synthesized through electrochemical deintercalation of Li from pristine LiCoO_2 samples. The LiCoO_2 samples were prepared by a conventional solid-state reaction technique. A mixture of Li_2CO_3 and Co_3O_4 with the ratio of $\text{Li}/\text{Co}=1:1$ was calcined (600 °C) and then sintered (900 °C) in flowing O_2 gas. Electrochemical oxidation was carried out with a constant current (i.e., galvanometric) setup utilizing an airtight flat cell filled with a nonaqueous electrolyte. The electrochemical cell consisted of an as-synthesized LiCoO_2 pellet and an aluminum metal disk as the cathode and anode, respectively. No auxiliary agents (e.g., acetylene black and Teflon powder) were added to the bulk pellet to avoid any magnetic noise sources. Since high-valent cobalt oxides tend to experience chemical instability when exposed to atmospheric moisture, sample handling and characterization were carefully made in an inert gas atmosphere. Details of experimental procedures are given elsewhere.⁸

^{a)}Electronic mail: t-mot@msl.titech.ac.jp.




FIG. 1. (Color online) Change in voltage for the $\text{Li}_x\text{CoO}_2/\text{Al}$ electrochemical cell as Li is deintercalated from LiCoO_2 . The Li content (x) of Li_xCoO_2 is calculated based on Faraday's law.

Single-phase CoO_2 samples were successfully obtained through the aforementioned electrochemical synthesis technique. Figure 1 shows a typical voltage versus x plot for the $\text{Li}_x\text{CoO}_2/\text{Al}$ cell. The x values were estimated through theoretical calculations based on Faraday's law with an assumption that the full amount of electricity was used for the Li deintercalation reaction. The cell voltage gradually increased with decreasing x in Li_xCoO_2 and finally reached +4.78 V at $x=0.0$. As x decreased below ≈ 0.1 , the cell voltage increased rapidly to indicate the completion of lithium extraction.⁶ The actual Li content (x) of the resultant CoO_2 sample was determined by means of inductively coupled plasma atomic emission spectroscopy to be below the detection limit of the apparatus, i.e., smaller than 0.01. This ensures that our CoO_2 samples are indeed the $x=0$ end member of the Li_xCoO_2 system.

In Fig. 2, x-ray powder diffraction patterns for the pristine LiCoO_2 and the CoO_2 samples are shown. The pattern for LiCoO_2 was readily refined based on space group $R\bar{3}m$ with the lattice parameters $a=2.814 \text{ \AA}$ and $c=14.05 \text{ \AA}$, being in good agreement with those previously reported.^{6,9} For CoO_2 , on the other hand, diffraction peaks were indexed based on space group $P\bar{3}m1$ with the lattice parameters $a=2.820 \text{ \AA}$ and $c=4.238 \text{ \AA}$.




FIG. 2. (Color online) X-ray powder diffraction patterns for (a) CoO_2 , (b) $\text{Li}_{0.12}\text{CoO}_2$, and (c) LiCoO_2 samples.




FIG. 3. (Color online) Temperature dependence of magnetic susceptibility (χ) for the samples of CoO_2 (red circles), $\text{Li}_{0.12}\text{CoO}_2$ (blue triangles), and LiCoO_2 (black squares).

$=2.820 \text{ \AA}$ and $c=4.238 \text{ \AA}$. The LiCoO_2 phase crystallizes in the so-called $O3$ -type structure, in which Li ions occupy the octahedral site with three CoO_2 layers per unit cell, while the CoO_2 phase possesses an $O1$ -type structure consisting of a single CoO_2 layer only per unit cell. Oxygen-content analysis was performed based on hydrogen reduction experiments in a 5% H_2/Ar gas flow with a thermobalance. The oxygen content of the sample was determined to be $\text{CoO}_{1.98\pm 0.02}$. Thus, the resultant CoO_2 sample is essentially oxygen stoichiometric, implying that the highest formal valence of cobalt is realized, i.e., $V_{\text{Co}} \approx +4.0$.

In the cell voltage versus x curve shown in Fig. 1, one may notice that there appears a narrow plateau at about $x=0.12$ prior to the rapid increase in voltage, suggesting the existence of another stable phase neighboring on the $x=0$ end member. We thus synthesized a Li_xCoO_2 sample precisely controlling the electric charge setting at $x=0.12$. It is found that the $x=0.12$ sample is indeed of single phase possessing a hexagonal structure with the lattice parameters $a=2.821 \text{ \AA}$ and $c=27.13 \text{ \AA}$ (Fig. 2). The crystal of the $x=0.12$ phase is reported to consist of alternate stacking of a Li-intercalated $O3$ -type block (as in LiCoO_2) and a Li-free $O1$ -type block (as in CoO_2), leading to a six- CoO_2 -layer unit cell that is called “ H1-3 .”^{10,11} Note that $\text{Li}_{0.12}\text{CoO}_2$ ($V_{\text{Co}} = +3.88$) may correspond to an electron-doped phase of CoO_2 ($V_{\text{Co}} = +4$).

Magnetic susceptibility (χ) measurements were performed with a superconducting quantum interference device magnetometer (MPMS-XL, Quantum Design). The χ vs T plots for the LiCoO_2 (pristine), $\text{Li}_{0.12}\text{CoO}_2$, and CoO_2 samples are given in Fig. 3. The χ value for the LiCoO_2 sample is small in magnitude and little dependent on temperature due to the nonmagnetic nature of low-spin Co^{III} . Surprisingly, the CoO_2 and $\text{Li}_{0.12}\text{CoO}_2$ samples also exhibit temperature-independent susceptibility in the temperature range between 50 and 300 K. The susceptibility data for CoO_2 are in good agreement with those reported by de Vaulx *et al.*,⁷ although their sample contains a large amount of secondary phases. The χ vs T plots were fitted with the following formula: $\chi = \chi_0 + C/(T - \Theta)$, where χ_0 , C , and Θ denote the constant susceptibility, the Curie constant, and the Weiss temperature, respectively. Fitted values for χ_0 , C , and Θ are

TABLE I. The χ_0 , C , and Θ values for the LiCoO_2 , $\text{Li}_{0.12}\text{CoO}_2$, and CoO_2 samples. These values were determined based on least-squares calculations for the χ vs T plots (Fig. 3).

x in Li_xCoO_2	χ_0 (10^{-4} emu/mol Oe)	C (10^{-3} emu K/mol Oe)	Θ (K)
0.0	5.68	4.01	-3.3
0.12	6.00	5.48	-3.1
1.0	1.34	0.89	-1.6

summarized in Table I. The C value for the CoO_2 sample yields an effective magnetic moment (μ_{eff}) of $0.18\mu_{\text{B}}/\text{Co}$ site, being much smaller than the theoretical spin-only value of low-spin Co^{IV} ($S=1/2$), i.e., $1.73\mu_{\text{B}}/\text{Co}$ site. Thus, any localized spin model is unlikely.

We conclude that (1) the magnetism of CoO_2 is featured with a temperature-independent susceptibility with a relatively large value for χ_0 and that (2) the upturn behavior at low temperatures likely originates from an extrinsic cause, e.g., lattice defects. A possible (and the most conservative) explanation for this is that the CoO_2 phase is a Pauli-paramagnetic metal with itinerant electrons. Assuming that the difference in magnitude of χ_0 between CoO_2 and LiCoO_2 corresponds to the Pauli-paramagnetic contribution, the density of states at the Fermi level, $D(\epsilon_F)$, is calculated at 13 electrons/eV. This value is three times larger than the theoretical value: $D(\epsilon_F) \approx 4$ electrons/eV for nonmagnetic CoO_2 according to local density approximation calculations.¹²

It is worthwhile to compare the magnetic property of “electron-doped” $\text{Li}_{0.12}\text{CoO}_2$ to that of the parent phase, CoO_2 . Our magnetic data (Fig. 3) demonstrate that the χ - T curve for $\text{Li}_{0.12}\text{CoO}_2$ is essentially identical to that for CoO_2 , indicating that $\text{Li}_{0.12}\text{CoO}_2$ is also a Pauli paramagnet of the same magnetic origin as CoO_2 . Thus, the $x=0$ composition is *not* a singular point in the electronic phase diagram of the $A_x\text{CoO}_2$ systems. The situation is in sharp contrast to the case of high- T_c superconductive copper oxides in which the parent material is a Mott insulator. The present study implies that any theoretical approaches starting from a Mott insulator

may not be appropriate for discussion of the metallic state in $A_x\text{CoO}_2$.

In summary, synthesis and properties of CoO_2 , the $x=0$ phase of the $A_x\text{CoO}_2$ systems ($A=\text{Li,Na}$), were reported. Single-phase bulk samples of CoO_2 were successfully obtained through electrochemical deintercalation of Li from pristine LiCoO_2 . The magnetism of CoO_2 is featured with a temperature-independent susceptibility with a relatively large value, being essentially identical to that of a Li-doped phase, $\text{Li}_{0.12}\text{CoO}_2$. This suggests that the CoO_2 phase is a Pauli-paramagnetic metal with itinerant electrons.

The present work was supported by Grants-in-Aid for Scientific Research (Contract Nos. 16740194 and 19740201) from the Japan Society for the Promotion of Science. M.K. acknowledges financial support from the Academy of Finland (Decision No. 110433).

- ¹I. Terasaki, Y. Sasago, and K. Uchinokura, *Phys. Rev. B* **56**, R12685 (1997).
- ²T. Motohashi, E. Naujalis, R. Ueda, K. Isawa, M. Karppinen, and H. Yamauchi, *Appl. Phys. Lett.* **79**, 1480 (2001); T. Motohashi, M. Karppinen, and H. Yamauchi, *Oxide Thermoelectrics* (Research Signpost, Trivandrum, India, 2002), pp. 73–81.
- ³T. Motohashi, R. Ueda, E. Naujalis, T. Tojo, I. Terasaki, T. Atake, M. Karppinen, and H. Yamauchi, *Phys. Rev. B* **67**, 064406 (2003).
- ⁴M. L. Foo, Y. Wang, S. Watauchi, H. W. Zandbergen, T. He, R. J. Cava, and N. P. Ong, *Phys. Rev. Lett.* **92**, 247001 (2004).
- ⁵K. Takada, H. Sakurai, E. Takayama-Muromachi, F. Izumi, R. A. Dilanian, and T. Sasaki, *Nature (London)* **422**, 53 (2003).
- ⁶G. G. Amatucci, J. M. Tarascon, and L. C. Klein, *J. Electrochem. Soc.* **143**, 1114 (1996).
- ⁷C. de Vaulx, M.-H. Julien, C. Berthier, S. Hébert, V. Pralong, and A. Maignan, *Phys. Rev. Lett.* **98**, 246402 (2007).
- ⁸T. Motohashi, Y. Katsumata, T. Ono, R. Kanno, M. Karppinen, and H. Yamauchi, *Chem. Mater.* **19**, 5063 (2007).
- ⁹M. Ménétrier, I. Saadoune, S. Levasseur, and C. Delmas, *J. Mater. Chem.* **9**, 1135 (1999); S. Levasseur, M. Ménétrier, E. Suard, and C. Delmas, *Solid State Ionics* **128**, 11 (2000).
- ¹⁰Z. Chen, Z. Lu, and J. R. Dahn, *J. Electrochem. Soc.* **149**, A1604 (2002).
- ¹¹A. Van der Ven, M. K. Aydinol, and G. Ceder, *J. Electrochem. Soc.* **145**, 2149 (1998).
- ¹²K.-W. Lee and W. E. Pickett, *Phys. Rev. B* **72**, 115110 (2005).