Designing High Performance All-Cellulose Composites by Dissolution/Swelling of Macro- and Nano-scale Cellulose Fibers

Feng Chen

Designing High Performance All-Cellulose Composites by Dissolution/Swelling of Macro- and Nano-scale Cellulose Fibers

Feng Chen

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Chemical Engineering, at a public examination held at the meeting room Halko (Bio2) of the school on 05 February 2021 at 14:00.

Aalto University
School of Chemical Engineering
Department of Bioproducts and Biosystems
Biorefineries group, ALL-CELL project

Supervising professors

FiDiPro Professor Tatiana Budtova, Aalto University, Finland
(Mines ParisTech, Centre de Mise en Forme des Matériaux, France)

Thesis advisors

FiDiPro Professor Tatiana Budtova, Aalto University, Finland
Professor Herbert Sixta, Aalto University, Finland
Associate Professor Michael Hummel, Aalto University, Finland

Preliminary examiners

Professor Jun Zhang, The Chinese Academy of Science, China
Professor Johannes Ganster, Fraunhofer Institute for Applied Polymer Research, Germany

Opponent

Professor Mohamed Naceur Belgacem, Université Grenoble Alpes, Grenoble INP, France

Aalto University publication series

DOCTORAL DISSERTATIONS 6/2021

© 2021 Feng Chen

ISBN 978-952-64-0235-2 (printed)

ISBN 978-952-64-0236-9 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-64-0236-9>

Painosalama Oy

Turku 2021

Finland

Author
Feng Chen

Name of the doctoral dissertation

Designing High Performance All-Cellulose Composites by Dissolution/Swelling of Macro- and Nano-scale Cellulose Fibers

Publisher School of Chemical Engineering

Unit Department of Bioproducts and Biosystems

Series Aalto University publication series DOCTORAL DISSERTATIONS 6/2021

Field of research Bioproduct Technology

Manuscript submitted 4 November 2020

Date of the defence 5 February 2021

Permission for public defence granted (date) 16 December 2020

Language English

☐ **Monograph**

☒ **Article dissertation**

☐ **Essay dissertation**

Abstract

All-cellulose composites (ACCs) is a new generation of biocomposites with both the matrix and reinforcing fibers being based on cellulose. This thesis explores various designs of ACCs using either macro- or nano-scale cellulose fibers as raw materials and ionic liquids (ILs) as cellulose solvents. Prior to ACCs fabrication, the swelling and dissolution kinetics of different cellulose fibers (natural fiber flax, viscose-type Cordenka and two Ioncell fibers with one containing lignin and hemicelluloses) in solvent power tuned ILs (1-ethyl-3-methylimidazolium acetate, [EMIM][OAc] and N-methyl-1,5-diazabicyclo[4.3.0]non-5-enium dimethyl phosphate, [mDBN][DMP]) was studied. High performance unidirectional flax-based ACCs, isotropic filter paper-based ACCs and nanopaper were then produced involving controlled dissolution and/or swelling of cellulose fibers.

The fundamental investigation on fibers swelling and dissolution kinetics revealed that the rate of fiber dissolution in [EMIM][OAc] depended on fiber accessibility and solvent viscosity. The fastest dissolution (in [EMIM][OAc] and [EMIM][OAc]-5% water) or swelling (in [EMIM][OAc]-15% water) was recorded for Ioncell fibers and the slowest for Cordenka. An anomalous two-step dissolution-swelling behavior of flax was observed in [mDBN][DMP] and [mDBN][DMP]-water.

ACCs from either unidirectional flax or isotropic filter paper were produced via selective dissolution strategy. For flax-based ACCs, it was shown that the mechanical properties were controlled by the sufficient amount of matrix and the non-dissolution of the inner, mechanically strong cell walls in the fiber. The interface between the matrix and the fibers was further artfully re-modelled by utilizing two-step dissolution-swelling phenomenon in [mDBN][DMP], resulting in increased tensile strength in both transverse direction and fiber direction. For isotropic paper-based ACCs, a digital image correlation technique was explored for accuracy enhanced analysis of mechanical properties. A 30-60 min impregnation allowed increasing tensile strength, Young's modulus and toughness of a filter paper in almost 10 times, 5 times and 25 times, respectively.

Isotropic ACC constructed from highly disordered and entangled cellulose nanofibrils (CNFs) through their self-binding exhibited an exceptional ductility (up to 35%) while combining high strength (up to 260 MPa) and toughness (up to 51 MJ/m³). This was realized by swelling of hemicelluloses in-between the nanofibrils in [EMIM][OAc]-water below the dissolution limit of cellulose and hemicellulose, thus allowing delamination of thick CNF bundles into thinner ones without influencing the length.

The results obtained demonstrate that a fundamental understanding of cellulose swelling and dissolution promotes various possibilities to design ACCs with engineered performance. The findings bring new perspectives to the design of macroscale and nanoscale cellulosic materials.

Keywords Cellulose, nanocellulose, ionic liquid, all-cellulose composite, mechanical properties

ISBN (printed) 978-952-64-0235-2

ISBN (pdf) 978-952-64-0236-9

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Helsinki

Location of printing Turku **Year** 2021

Pages 180

urn <http://urn.fi/URN:ISBN:978-952-64-0236-9>

Preface

This doctoral dissertation was completed in the frame of the FiDiPro-project ALL-CELL (From ultralight to ultra-strong all-cellulose composites via “green” processing) which was enabled by the financial support from Business Finland (former TEKES, Finnish Funding Agency for Innovation), Stora Enso Oyj, UPM-Kymmene Oyj and the collaboration with Fibertus Oy and Separation Research Ab Oy as well. The work was carried out from Autumn 2016 to Spring 2020 mainly at Aalto University in Finland and partly at Mines ParisTech-Center of Materials Forming (CEMEF) in Sophia Antipolis, France. The grants or scholarships from Foundation for Aalto University Science and Technology, Aalto CHEM school's funding (FinnCERES), Walter Ahlströmin Foundation and Finnish Forest Products Engineers' Association supported the finalization of the thesis. All funding over the years is gratefully acknowledged.

First, I wish to express my deepest appreciation to my supervisor and advisor Prof. Tatiana Budtova for giving me the opportunity to pursue PhD abroad after achieving my master's degree in China, for guiding me consistently throughout my PhD journey in Finland and France, for supporting my participation in conferences over the world and for supporting me whenever your help is needed. Your encouragement-dominated attitude as a supervisor and rigorous attitude as a scientist will be a standard example in my future academic career. I also wish to show my gratitude to my thesis advisors Prof. Herbert Sixta and Prof. Michael Hummel. Thank you, Herbert, for your support and advises during my PhD study in Biorefineries group since the first day I came Bio2 department. Thank you, Michael, for helping me solve all the issues and your valuable discussions concerning experimental results and writing. I feel extremely lucky to spend my doctoral time with you all.

My deep gratitude also goes to all the co-authors: Dr. Daisuke Sawada, Dr. Wenchao Xiang, Dr. Long Bai, Dr. Christophe Pradille (Mat Xper) and Prof. Jean-Luc Bouvard (CEMEF). It was my great pleasure to work with and learn from you. All the achievements on the research work are inseparable from your contribution. I warmly thank Prof. Jun Zhang, Prof. Johannes Ganster and Prof. Mohamed Naceur Belgacem for carefully examining this thesis. I also thank all the project partners from Business Finland and industry for insightful discussions and the encouragement during every half-year project meeting. In addition, I wish to thank the colleagues from both Aalto and CEMEF: Marja Risänen, Hatakka Rita, Leena Nolvi, Leena Pitkänen, Tuyen Nguyen, Phan Nguyen, Seppo Jääskeläinen, Guillaume Corvec, Gilbert Fiorucci, Gabriel Monge

and Suzanne Jacomet, for the provision of experimental convenience and technical support. Seperate thank also goes to Prof. Alistair King (University of Helsinki) for the help of providing novel ionic liquids.

I am deeply grateful to Yibo and Xiang for our wonderful “meet” and friendship in Finland. I will never forget the day when I arrived Helsinki alone from China with two big luggages; it was you that contacted, picked up and drove me to my current home and then Ikea to buy living necessities. Special thank also goes to Oona for being such a nice project partner and friend; it was your help that eased me to settle down in Finland and in Aalto.

I would wish to thank all the colleagues and friends I met in Biorefineries group, in Bio2, in Aalto and in Finland over past years, in particular: Guodong, Jiaqi, Siqi, Wenwen, Guang, Xuhai, Wenyang, Xue, Ling, Jinze, Weixin, Ya, Xun, Xuetong, Tao, Yingying, Yujiao, Bin, Xiao, Yang, Gonghua, Zhuojun, Liang, Zhenzi, Shaozuo, Simone, Kaniz, Leena, Hilda, Chamseddine, Sanna, Joanna, Sherif, Quang, Sara, Inge, Yingfeng, Xueyao, Yuhang, Dandan, Sanni, Sirje, Mika, Mikko, Farooq, Jue, Hang, Qing, Huiting and all those that I do not list here but in my memory, for helping me along the way. Special thanks to Wenchao, Xue, Wenyang, Weixin, Long, Siqi, Ya, Xun, Tao, Ling and Yingfeng for lunch and entertainment accompanying, thus making my life in Finland more interesting and “sunny”. I also thank my friends and colleagues at CEMEF: Lucile, Sophie, Loan, Shaojie, Meng, Feng, Fangxin, Beini (Deakin University) and Prof. Yancheng Zhang, for making my every stay in France so happy and memorable.

Besides above-mentioned colleagues and friends in Finland and France, I appreciate my old friends Yazhu, Steven, Dannin, Haiyan, Qian Mou and Sara Pu², for always being there for me through the years since our meet in middle school, high school and the universities in Wuhan and Chengdu. It is fortunate to have you and it is your spirit accompanying and/or motivation that has kept me moving on still. Let's hope we will get together soon in China. How lucky I am that you are there still, I wish to give my warm hug to you, Yazhu! I will keep the promise to you and as well me and will be there soon. My sincere thank also goes to Prof. Xueqing Liu (Jiangnan University), it was you that guided me to the right road to science when I was an undergraduate student and that inspired me all the way along.

At last, the biggest thanks go to my family, especially my parents, for your endless love and support that enabled my decision of pursuing PhD abroad. Here I must thank my younger brother Yun who has taken most of the family responsibility, which is the strong backing that ensure my wholehearted full-time PhD study here.

Helsinki, Finland, Christmas 2020

Feng Chen

Contents

Preface	I
Contents	III
List of Abbreviations and Symbols.....	VI
List of Publications.....	VIII
Author's Contribution	IX
1 Introduction.....	1
2 Thesis objectives	3
3 Background.....	5
3.1 Cellulose and its hierarchical structure	5
3.2 Cellulose fibers.....	7
3.2.1 Cellulose nanofibrils	7
3.2.2 Natural fibers.....	9
3.2.3 Man-made cellulose fibers	10
3.3 Ionic liquid as cellulose solvent.....	12
3.4 Swelling and dissolution of cellulose (macro) fibers in ILs	13
3.5 All-cellulose composites (ACCs).....	14
3.5.1 Manufacturing ACCs via selective dissolution strategy	16
3.5.2 Manufacturing ACCs via self-binding.....	18
3.6 Comments on the tensile testing of ACCs	20
3.7 Concluding remarks	21
4 Experimental	22
4.1 Materials.....	22
4.1.1 Cellulose macroscale fibers	22
4.1.2 Cellulose nanofibrils (CNF)	22
4.1.3 Cellulose filter paper	23
4.1.4 Ionic liquids (ILs).....	23
4.1.5 Other materials	24
4.2 Preparation of all-cellulose composites	24

4.2.1	Fabricating unidirectional flax-based ACCs via selective dissolution.....	24
4.2.2	Fabricating unidirectional flax-based ACCs via selective swelling.....	25
4.2.3	Fabricating isotropic macroscale paper-based ACCs.....	25
4.2.4	Fabricating cellulose nanopaper	26
4.3	Characterization methods.....	27
4.3.1	Optical microscopy observations of fiber swelling and dissolution.....	27
4.3.2	Methods for matter characterisation in the solid state.....	27
4.3.3	Methods for matter characterisation in the liquid state ...	30
5	Results and Discussion	32
5.1	Characterization of macroscale cellulose fibers	32
5.2	Characterization of ILs and ILs-water mixtures.....	34
5.2.1	Thermal properties of ILs	34
5.2.2	Kamlet–Taft parameters	35
5.2.3	Rheological properties of ILs and ILs-water mixtures	35
5.3	Kinetics of various cellulose fibers swelling and dissolution.....	37
5.3.1	Solvents: [EMIM][OAc] and [EMIM][OAc]-water mixtures.....	37
5.3.2	Solvents: [mDBN][DMP] and [mDBN][DMP]-water mixtures.....	39
5.4	Unidirectional flax-based ACCs: Selective dissolution <i>vs</i> Selective swelling	40
5.4.1	Selective dissolution strategy.....	40
5.4.2	Selective swelling strategy.....	43
5.5	Isotropic macroscale paper-based ACCs: Exploring DIC analysis of mechanical properties	45
5.5.1	Evolution of the basic characteristics of paper-based ACCs.....	45
5.5.2	Mechanical properties.....	48
5.6	Isotropic cellulose nanopaper: Toward large ductility combining high strength and toughness	50
5.6.1	Swelling induced delamination of CNF (bundles)	50
5.6.2	Performance of nanopaper from CNF-IL-water suspension.....	52
6	Conclusions and Perspectives.....	56
6.1	Main findings of this thesis.....	56
6.1.1	Swelling and dissolution of cellulose fibers	56

6.1.2 Unidirectional flax-based ACCs via selective dissolution and selective swelling	57
6.1.3 Isotropic macroscopic paper-based ACCs	57
6.1.4 Isotropic cellulose nanopaper.....	58
6.2 Research perspectives	58
References.....	60

List of Abbreviations and Symbols

[EMIM][OAc]	1-ethyl-3-methylimidazolium acetate
[mDBN][DMP]	N-methyl-1,5-diazabicyclo[4.3.0]non-5-enium dimethyl phosphate
α	hydrogen bond acidity
β	hydrogen bond basicity
β - α	net basicity
ACCs	all-cellulose composites
AFM	atomic force microscopy
Cell-I-IV	cellulose I-IV crystalline structure
CNF	cellulose nanofibrils
Cryo-TEM	cryogenic transmission electron microscopy
DIC	digital image correlation
DP	degree of polymerization
DVS	dynamic vapor sorption
G'	storage modulus
G''	loss modulus
H-bond (ing)	hydrogen bond (ing)
IL	ionic liquid
K-T Parameters	Kamlet–Taft Parameters
Mn	number-average molecular weights
Mw	weight-average molecular weights
MMCF	man-made cellulose fibers
RH	relative humidity
SD	selective dissolution
SEM	scanning electron microscopy

SW	selective swelling
XRD	X-ray diffraction

List of Publications

This doctoral dissertation consists of a summary and of the following publications which are referred to in the text by their numerals

- I** **Feng Chen**, Daisuke Sawada, Michael Hummel, Herbert Sixta, Tatiana Budtova (2020) Swelling and dissolution kinetics of natural and man-made cellulose fibers in solvent power tuned ionic liquid. *Cellulose* 23: 7399–7415. DOI: 10.1007/s10570-020-03312-5
- II** **Feng Chen**, Daisuke Sawada, Michael Hummel, Herbert Sixta, Tatiana Budtova (2020) Unidirectional all-cellulose composites from flax via controlled impregnation with ionic liquid. *Polymers* 12: 1010. DOI: 10.3390/polym12051010
- III** **Feng Chen**, Jean-Luc Bouvard, Daisuke Sawada, Christophe Pradille, Michael Hummel, Herbert Sixta, Tatiana Budtova (2020) Exploring digital image correlation technique for the analysis of the tensile properties of all-cellulose composites. Submitted to *Cellulose* (under revision).
- IV** **Feng Chen**, Xiang Wenchao, Daisuke Sawada, Bai Long, Michael Hummel, Herbert Sixta, Tatiana Budtova (2020) Exploring large ductility in cellulose nanopaper combining high toughness and strength. *ACS Nano*, 14: 11150–11159. DOI: 10.1021/acsnano.0c02302

Author's Contribution

Paper I: Swelling and dissolution kinetics of natural and man-made cellulose fibers in solvent power tuned ionic liquid

FC had the main responsibility for the experimental design under the supervision of TB, and carried out the analysis of the raw materials including chemical compositions, molar mass distribution, dynamic vapour sorption (DVS), rheology of ionic liquid (IL) and IL-water mixtures and Kamlet–Taft parameters of IL and IL-water mixtures. DS contributed to the analysis of the XRD results. FC also complemented the observation of fiber swelling/dissolution in IL and IL-water mixtures using optical microscope. FC, MH and TB contributed to writing of the article and the interpretation of the results. TB, MH and HS critically reviewed the results and discussion.

Paper II: Unidirectional all-cellulose composites from flax via controlled impregnation with ionic liquid

FC had the main responsibility for the experimental design and ACCs fabrication under the supervision of TB, and carried out the analysis of the initial flax and flax-based ACCs, including density calculation, scanning electron microscopy (SEM) imaging and tensile testing. DS contributed to the analysis of the XRD results. FC and TB contributed to the draft of the article and the interpretation of the results. TB, MH and HS critically reviewed the results and discussion.

Paper III: Exploring digital image correlation technique for the analysis of the tensile properties of all-cellulose composites

FC had the main responsibility for the experimental design and ACCs fabrication under the supervision of TB, and carried out analysis of the initial filter paper and paper-based ACCs, including density calculation, scanning electron microscopy (SEM) imaging, optical and mechanical properties. DS provided the assistance with XRD measurements and contributed to the analysis of the XRD results. The tensile testing was conducted in CEMEF, MINES ParisTech with the assistance from JLB and CP. FC, JLB and TB contributed to the draft of the article and the interpretation of the results. TB, JLB, CP, MH and HS critically reviewed the results and discussion.

Paper IV: Exploring large ductility in cellulose nanopaper combining high toughness and strength

FC had the main responsibility for the experimental design and cellulose nanopaper fabrication under the supervision of TB. FC also carried out the analysis of the cellulose nanofibrils (CNF)-water and CNF-IL-water suspensions including CNF compositions and viscoelastic properties, and of the prepared nanopapers including density (porosity) calculation, tensile testing, SEM imaging and optical properties of transmittance and haze. WX and LB provided the assistance with the Cryo-TEM imaging and AFM measurements. DS contributed to the analysis and interpretation of XRD measurement. FC, MH and TB contributed to the draft of the article and the interpretation of the results. TB, MH and HS critically reviewed the results and discussion.

1. Introduction

Within the past decades significant growing concerns on environmental issues and awareness caused by the accumulation of non-biodegradable petroleum-based products have motivated the desire to create more eco-friendly and sustainable materials. This has also been acknowledged by governments worldwide. For example, the European Union has introduced regulations for vehicles that must be made of at least 95 % recyclable materials within the next decade (Kanari et al. 2003). The US Department of Energy supported a research project aimed at finding ways to ensure that at least 10% of the basic chemical building blocks can be obtained from renewable resources by 2020, with an incentive to increase this share to 50% by 2050 (Mohanty et al. 2002). In China, the government has insisted on environmentally sound economic advances, such as regulations for single-use plastic packaging, which has promoted companies to invest in biodegradable materials. As a result, biocomposites, especially natural fiber-reinforced polymer composites, have attracted increasing interest in various branches of industry due to their lower dependence on petroleum-based materials, their light weight and better recyclability.

Cellulose fibers featuring high specific mechanical properties (specific strength and specific modulus) are renewable and globally available and are excellent reinforcement for polymers (including both oil- and bio-based). However, due to the inherent chemical incompatibility between the cellulose fibers and classical polymer matrices and thus a weak interfacial strength and an inefficient stress transfer under load, the mechanical strength and stiffness of these biocomposites are not high enough (Bledzki and Gassan 1999, Romhány et al. 2003). This can of course be improved by a chemical treatment of the cellulose fibers or matrix or using compatibilisers (Jacob et al. 2005, Hua et al. 2016), or by applying nanosized cellulose fibers such as bacterial cellulose and nanofibrillated cellulose that provide an increased surface area (Nakagaito et al. 2005, Lee et al. 2014). The latter results in significant improvements in mechanical properties but entails additional costs and complexity in the formulation of biocomposites.

One way to overcome the problem of adhesion between the matrix and the fibers is to produce an all-polymer (or single polymer) composites. In this type of composites, the reinforcing and matrix phases are based on the same matter, thus showing perfect adhesion. This concept was first illustrated by Capiati and Porter (Capiati and Porter 1975) who produced the high-density all-

polyethylene composites with improved interfacial shear strength by partially melting the crystals in a lower melting temperature matrix; crystals played the role of reinforcement. More cases of the self-reinforced or all-polymer composites can be found in ref. (Gao et al. 2012). Inspired by the development of the self-reinforced polymer composites, Nishino et al. proposed the concept of cellulose self-reinforced composite or all-cellulose composites (ACCs), which proved to be a high-performance newly developed 100% biocomposites (Nishino et al. 2003, Nishino et al. 2004). In the case of ACC, the reinforcement and the matrix have the same chemical composition but differ in the crystalline phases. Due to their recognised advantages over traditional cellulose fibre reinforced composites, such as biodegradability, non-toxicity and renewability of raw materials and easier recycling, ACCs have become increasingly popular in recent years.

The general strategy of manufacturing ACCs is through partial/selective dissolution of the cellulose fibers which are in the shape of either individual fibers, fabric or paper using cellulose solvent or cellulose solution. Consequently, the dissolved cellulose is converted into the matrix of the ACCs and the remained undissolved fibers serve as the reinforcement (Huber et al. 2012a, Li et al. 2018b, Baghaei and Skrifvars 2020). The solvent is then washed out and the material is dried. This ACCs strategy also benefits, above all, from the possibility of producing a composite material with a high reinforcement content (undissolved cellulose fibers), which contributes to the excellent mechanical properties. For example, the mechanically strong Bocell fibers were converted into ACCs with volume fractions of up to 90% of fiber and only 10% of “newly” regenerated cellulose matrix. The average tensile strength was as high as 910 MPa and a Young’s modulus 23 GPa with 8% elongation at break, which are significantly higher values and far exceeding the reported traditional unidirectional natural fiber reinforced composites (Soykeabkaew et al. 2009). Although both long and short single cellulose fibers have been successfully converted into ACCs to date, most work has been done with ACCs based on fibers that make the main phase in the composite precursor, such as woven fabric or filter paper or oriented long fibers. This is probably due to a simpler manufacturing process with more structural design options.

Despite continuous research efforts of produce ACCs from various cellulose sources using different cellulose solvents, a deeper understanding is needed to correlate the structure of the fibers, their behavior when a solvent is added, the processing parameters (dissolution times, temperatures and pressures during drying) and the properties of the ACCs. To answer some of these questions and design ACC from various cellulose fibers is the focus of this thesis. Macroscopic natural and artificial cellulose fibers and nanoscale cellulose fibers obtained from commercial pulp will be used and studied from the basics to the final application. The objectives and questions of the thesis are discussed in detail in the following chapter and it is expected that the ongoing work will bring new perspectives for the design of the ACCs.

2. Thesis objectives

It is known that both the dissolution and swelling of cellulose fibers are influenced by fiber type, supramolecular structure, morphology and composition, as well as solvent type and dissolution conditions (Le Moigne and Navard 2010). Therefore, the understanding of the dissolution and swelling kinetics of a given fiber in a certain cellulose solvent and correlation with fiber morphology are important in order to select optimal processing conditions for making ACCs with the best possible mechanical properties. Additionally, it would be interesting to use the swelling phenomena of cellulose fiber for the design of ACCs. This topic has not been addressed by the researchers so far.

As well as the ACCs produced by above-mentioned dissolution involved strategy, it is also possible to manufacture ACCs without solvent utilizing the inherent property of cellulose to form hydrogen bonds (H-bonds). Indeed, this has already received attention from the researchers in recent years. For example, ACCs have been successfully produced from macroscopic ramie fibers and microfibrillated flax-based pulp without the use of cellulose solvents or binders (Arévalo and Peijs 2016, Yang and Berglund 2018). Another type of material belonging to the category of ACCs is called “cellulose nanopaper” in which cellulose nanofibers (CNFs) are “glued” together by interfibrillar H-bonds (Nogi et al. 2009).

The aim of the work was therefore to tune the properties of ACCs on the basis of a fundamental understanding of the behaviour of cellulose fibers with respect to their swelling and dissolution. The solvent selected was ionic liquid (IL) and its mixtures with water. Various composite materials, from unidirectional to isotropic, and from macro- to nanoscale, were produced. In addition, a digital image correlation technique was explored for a more accurate “capturing” of mechanical properties of cellulosic materials, herein ACCs as an example. Figure 2.1 illustrates and summaries the scope of the thesis. The research questions to answer were as follows:

1. What is the effect of fiber structure and solvent power on the dissolution and swelling kinetics of natural and man-made cellulose fiber (**Paper I & unpublished results**)?
2. How to use the knowledge of fiber swelling and dissolution kinetics to select the optimal processing conditions to obtain the best mechanical properties of ACCs (**Paper II & unpublished results**)?

3. How to improve the analysis of the mechanical properties of ACCs (**Paper III**)?
4. How to make ductile cellulose nanopaper with high toughness and strength? (**Paper IV**)?

Figure 2.1. A tree “map” illustrating the approach taken in the thesis.

3. Background

This chapter will provide the background knowledge on the topics which are closely related to the work performed in the thesis. For example, polymer composites reinforced with natural fibers is a huge area in itself and will not be addressed.

In the first section of this chapter, the basic knowledge on cellulose and its hierarchical structure is introduced from the point of view of macro- and micro-level. In the second section, a general description of various cellulose fibers, natural and man-made, including cellulose nanofibers, are presented. The following two sections deal with cellulose dissolution: an introduction of IL as cellulose solvent and a brief discussion of the mechanisms of cellulose dissolution and swelling. The next section deals with ACCs produced via either conventional selective dissolution strategy using cellulose solvent, in particular, IL, or self-binding method (cellulose nanopaper). Then various approaches used for the analysis of tensile testing are briefly discussed from the point of assessment of the mechanical properties of ACCs. Finally, the chapter ends with some concluding remarks focusing on the perspectives and research questions to be solved.

3.1 Cellulose and its hierarchical structure

Cellulose is a fascinating biopolymer present on the Earth in almost inexhaustible quantity. It was discovered in 1838 by the French chemist Anselme Payen (Payen 1838). On the macro-level, as shown in Figure 3.1 a, cellulose is present in biomass like trees, in plant fibers as cotton or flax, in tunicate-class marine resources (Šturcová et al. 2005) and as a metabolic product of some bacteria (Iguchi et al. 2000). Note that chemical synthesis of low molecular weight cellulose (DP around 100) has been explored and is also possible now (Egusa et al. 2007). In nature cellulose very often coexists with hemicellulose and lignin organized in a complex composite structure, the cell walls (Figure 3.1 b). Here hemicellulose refers to a collective term of an extremely heterogeneous group of nonlinear polysaccharides with a low degree of polymerization and linked with cellulose by H-bond (Deblois and Wiegel 1990), while lignin is a complex heteropolymer formed from phenolpropane units (Sarkanen and Ludwig 1971). In most cases cellulose is isolated from wood or other lignocellulose plants via

pulping process, during which the lignin and hemicelluloses can be selectively removed (Sixta 2006).

Figure 3.1. (a) Examples of cellulose sources on the Earth, (b) Schematic illustration of the hierarchical structure of cellulose in a wood tissue, (c) Supramolecular structure of cellulose and (d) Semicrystalline structure of cellulose (adapted and reproduced with permission from Postek et al. 2010, Moon et al. 2011 and French 2017).

On the micro-level, cellulose is a biosynthesized linear polymer of variable length consisting of 1-4-linked β -D-anhydroglucopyranose units linked by carbon atoms of C1 and C4 (Henrissat and Davies 1997, Brown Jr et al. 2000). The supramolecular structure of cellulose is illustrated in Figure 3.1 c, and the repeating unit in a cellulose chain is anhydroglucose, around 0.5 nm in length (French 2017). Three kinds of H-bonds are formed due to the presence of the hydroxyl groups. The cellulose chains are stiffened by the intramolecular H-bonds (O2H2-O6 and O3H3-O5) and bound together into cellulose sheets by the intermolecular bonds (O6H6-O3). These sheets are further stacked together by Van der Waals forces (Cross and Chu 2010), thus finally allowing the formation of the semicrystalline structures in a thin long fibrillar shape, known as elementary fibril with a diameter ranging from 1.5 to 3.5 nm and containing about 40 cellulose chains, as illustrated in Figure 3.1 b and d (Klemm et al. 2005, Postek et al. 2010, Moon et al. 2011). Then the much higher-level cellulosic fibrillar structures, including cellulose nanofibrils (CNF, also called cellulose microfibrils in the early reports) and cellulose macroscale fibers or so-called natural cellulose fibers in dimensions spanning several orders of magnitude (Figure 3.1 b) are built by bottom-up assembly of the elementary fibrils.

Opposite to the crystallization of the traditional polymers (Strobl 2007, Cheng 2008), the supermolecular organization of cellulose chains in the semicrystalline structure is still not precisely known. Various models including fringed-fibrillar model, uniform elementary fibril model and single crystalline model, have been proposed in early reports (Orr et al. 1959, Hearle 1958, Fink et al. 1995). To date, cellulose as a polymorph, was identified as several allomorphs: Cellulose I (Cell-I), II, III and IV (O'Sullivan 1997, Malcolm and Saxena 2007). Naturally occurring Cell-I is the form in which the cellulose chains are organized parallel to each other, which has been characterized as two crystal forms: I_α and I_β (Atalla and Vanderhart 1984). Bacterial cellulose and algae cellulose are rich in I_α allomorph whereas the cellulose extracted from lignocellulosic plants contains mostly I_β allomorph (Atalla and Vanderhart 1984). It has been further reported that I_α can be converted irreversibly to more stable I_β allomorph upon heating (O'Sullivan 1997, Langan et al. 2005).

The other crystalline allomorphs can be produced from the native cellulose (Cell-I) via various treatments. The most known "artificial" allomorph is thermodynamically more stable Cell-II, which is irreversibly produced from Cell-I by dissolution and regeneration or by mercerisation through alkaline treatment. Cellulose chains in Cell-II are arranged in an antiparallel direction (Kim et al. 2006). The treatment of Cell-I or Cell-II in the liquid ammonia allows the formation of either Cell-III₁ or Cell-III₂, which can be further converted by heating to Cell-IV₁ and Cell-IV₂, respectively (O'Sullivan 1997, Wada et al. 2004).

Interestingly, the skeletons of these polymorphs are completely different from each other from the mechanical point of view. Nishino et al. measured the elastic modulus of several cellulose polymorphs using X-ray diffraction (XRD), revealing that Cell-I, -II, -III₁, -III₂ and -IV₁ have a modulus of 138, 88, 87, 58, 75 GPa, respectively (Nishino et al. 1995). Deformation of cellulose involves complex stretching and re-organisation of the H-bonds, which differs greatly for crystalline and amorphous phases, thus resulting in various tensile properties. Cell-I is believed to be the strongest allomorph with a theoretical ultimate tensile strength of about 13–17 GPa. Cellulose II and amorphous cellulose are less strong with tensile strength of around 9 and 0.8 ± 0.1 GPa, respectively (Staiger and Tucker 2008). Overall, the mechanical properties of cellulose compete well with other engineering materials such as aluminium (70 GPa) or glass fibres (76 GPa) (Nishino et al. 2003).

3.2 Cellulose fibers

In this section the properties of only those fibers, natural and man-made, that are used in this thesis, will be described. They are cellulose nanofibrils (CNFs), natural fibers such as flax, and man-made cellulose fibers (MMCFs).

3.2.1 Cellulose nanofibrils

CNF is a general term for nanoscale cellulose fiber with a lateral dimension ranging from few to few tens nm and over 1 μm in length. CNF is often composed of the aggregated elementary fibrils. CNF are typically produced by using so-

called top-down methods: via mechanical disintegration using high-pressure fluidizers, high-pressure homogenizers, cryo-crushing or grinding (Bandera et al. 2014, Ho et al. 2015, Hu et al. 2015, Khalil et al. 2014, Nechyporchuk et al. 2016, Qing et al. 2013, Wang et al. 2012a). Multiple lignocellulose sources such as wood, sugar beet, hemp and flax have been used to extract CNF (Chirayil et al. 2014, García et al. 2016, Josset et al. 2014, Santucci et al. 2016, Trifol et al. 2017). Examples of various CNF obtained via homogenization using different pretreatments are given in Figure 3.2. The produced CNF have high aspect ratio and excellent mechanical properties, however, the distribution in fibril diameter is polydisperse due to inherent aggregating tendency driven by H-bond formation between nanofibrils (Figure 3.2 a).

Figure 3.2. AFM images of CNF produced from different hardwood kraft pulp using homogenization: (a) non-pretreated, (b) carboxymethylated, (c) carboxylated via TEMPO-mediated oxidation and (d) quaternized cellulose (adapted with permission from Nechyporchuk et al. 2016).

High energy consumption, over 25000 kWh per ton, has been one of the main challenges in commercializing the mechanically disintegrated CNF (Klemm et al. 2011). Therefore, the strategies targeting to increase the number of anionic/cationic groups on the surface of the nanofibrils, and thus increase their repulsion, has been explored by pretreatments such as carboxymethylation (Figure 3.2 b, Junka et al. 2014), carboxylation via 2,2,6,6-tetramethylpiperidine-1-oxyl radical mediated oxidation (TEMPO-oxidation) (Figure 3.2 c, Isogai et al. 2011) or quaternization (Figure 3.2 d, Aulin et al. 2010, Olszewska et al. 2011), which in turn enhances the fibrillation process with reduced energy demand. Enzymatic hydrolysis is another efficient pretreatment to produce CNF, and a monocomponent endoglucanase (Novozym 476 from Novozymes A/S, Denmark) was used as an enzyme (Henriksson et al. 2007; Pääkkö et al. 2007). Indeed, all above-mentioned methods yield thinner CNF with a decreased diameter polydispersity in the aqueous suspensions, however, these

treatments lead to either decrease of the degree of polymerization or reduction of fiber length (Qing et al. 2013), as revealed in Figure 3.2.

3.2.2 Natural fibers

Herein natural fibers refer to the cellulose elementary fiber, which can be sketched as a multi-layer single cell wall structure with a diameter of 10-40 μm . Generally, the cell wall is composed of the middle lamellae (ML), primary wall (P), the secondary wall (S) with three different layers (S1, S2 and S3). In addition, there is an inner warty layer and lumen section for wood fiber (Figure 3.1b) and plants fibers such as flax (Figure 3.3), respectively. The middle lamella binds the neighboring elementary fibers together to form fiber bundle (Nechyporchuk et al. 2016). The P layer is flexible enough to allow wall expansion during growth and contains less ordered cellulose, hemicellulose, and a matrix composed of pectins and proteins. As presented in Figure 3.3, the P layer of an elementary flax fiber is only 0.2 μm thick (Charlet et al. 2007). The bulk of the fiber is essentially constituted by the layer S2 of the S layer (dominating the cross section). This thickest layer (S2) contains high content of highly ordered and densely packed cellulose, which is the agglomerated cellulose nanofibrils located almost perpendicularly (10°) to the cell and provide the fiber with its high tensile strength. Depending on the source of natural fiber, the thickness of the S2 layer may vary considerably (Müssig 2010).

Figure 3.3. Schematic representation of the multi-scale composite structure of flax elementary fiber (reproduced from Charlet et al. 2007).

The use of natural fibers dates back in history about 8000 BC (Pickering 2008). For example, hemp fiber imprints have been found in 10000 years old pottery shards in China. Ramie is believed to have been used in mummy cloths in Egypt during the period 5000 $\pm$ 3300 BC. The use of flax to produce linen dates back over 5000 years. There are also references in early Chinese history to natural fibers for papermaking. The basic parameters and mechanical properties of some natural fibers are listed in Table 3.1. The combination of excellent mechanical and physical properties together with their environmentally friendly character attracted the interest to natural materials especially in the 21st century to decrease the dependence on non-renewable resources. Flax, as an example, has been considered as a promising alternative to classical reinforcing glass fibers.

Table 3.1. Basic parameters and mechanical properties of some (elementary) natural fibers (adapted from Jonoobi et al. 2014, Pickering 2008).

Fiber	Density (g/cm ³)	Length (mm)	Diameter (μm)	Strain at break (%)	Tensile strength (MPa)
wood	-	3	15	-	400-800
Flax	1.38	5±38	10±65	1.2±3	343±1035
Jute	1.23	0.8±6	5±25	1.5±3.1	187±773
Sisal	1.20	0.8±8	7±47	1.9±3	507±855
Hemp	1.35	5±55	10±51	1.6±4.5	580±1110
Ramie	1.44	40±250	18±80	2±4	400±938
Bagasse	1.2	0.8±2.8	10±34	0.9	20±290
Pineapple	1.5	3±8	8±41	1±3	170±1627

3.2.3 Man-made cellulose fibers

In contrast to natural cellulose fibers which are produced as a result of photosynthesis and are usually composed of cellulose, lignin and hemicellulose as main components, MMCFs are industrially processed fibers made from purified, dissolved and regenerated cellulose sources. To date, there are mainly three commercially relevant processing technologies for MMCFs: the cupro process, the viscose process, and the lyocell process. The cupro process occurred first in the 1890s and used cuprammonium hydroxide (cuoxam) as cellulose solvent. However, the production of cupro fiber is limited nowadays due to its high cost and environmental concerns (Courtney 1953, Liebert 2010, Wang et al. 2016). The viscose process, in which cellulose is dissolved as cellulose xanthate by treatment with alkali and carbon disulphide (CS₂), was developed in almost the same period as cupro process. Currently, the majority of the global production of MMCF is based on the viscose process, and the production of viscose fiber is still expected to grow in the coming future (Bywater 2011, Ma 2018a). However, the major drawback is that the utilization of large amounts of CS₂ and caustic soda results in hazardous by-products such as hydrogen sulfide (H₂S) gas and other volatile thio-compounds, which may cause severe damage to the environment (Bywater 2011). The lyocell process is used to produce the so-called Lyocell fibers. It is the only existing process which utilizes direct cellulose solvent N-methylmorpholin N-oxide monohydrate (NMMO) on the industrial level (Fink et al. 2001). However, this process suffers from a strong exothermic reaction at high temperature, thus requiring the addition of stabilisers to avoid the runaway reaction and extensive cellulose degradation. Moreover, to guarantee the necessary spinning stability, the above-mentioned MMCF processes require highly purified dissolving or paper grade pulp. The presence of non-cellulosic contents will affect the xanthation of the pulp in the viscose process or lead to unexpected difficulties during the dissolution in the lyocell process, thus affecting the subsequent spinning (Gübitz et al. 1998, Fink et al. 2004).

In recent years, an alternative direct solvent for lyocell process has been explored by using ionic liquids (IL, more details will be provided in the next

section), thus avoiding the problems and limitations mentioned above. The obtained fibers have a generic name Ioncell, and the most successful results in terms of the properties of fibers were obtained using a protic acidic IL 1,5-diazabicyclo [4.3.0] non-5-enium acetate ([DBNH]OAc) as cellulose direct solvent (Sixta et al. 2015). Benefiting from the excellent dissolution power of ionic liquids for lignin and hemicelluloses containing cellulosic substrates (Sun et al. 2009), waste cellulosic sources like newspapers (Ma et al. 2016) and textiles (Haslinger et al. 2019), high content lignin containing-cellulose blends (Ma et al. 2015) and lignocellulose like low refined pulps (Ma et al. 2018b) were successfully spun into high performance MMCFs utilizing Ioncell process.

Unlike natural cellulose fibers, which are known to have a hierarchical morphological structure built by bottom-up assembly of the elementary fibrils, the morphological organization of the MMCFs is still a subject of debates mainly due to the limitations in the characterisation techniques. The early reports demonstrated a fibril model of lyocell fiber with a range of fibril size levels: elementary fibrils cluster to microfibrils, and these again aggregating into macrofibrils (Schuster et al. 2003, Rous et al. 2006). The observation of the ‘splitting’ behavior induced by so-called ‘interfibrillar’ swelling of both lyocell and viscose fibers seems to further support the fibril model of MMCFs (Öztürk et al. 2006a, Öztürk et al. 2006b, Öztürk et al. 2008). Additionally, both lyocell and viscose fibers were believed to have a skin-core structure (Sisson 1960, Biganska 2002). A structure model of MMCF formed by the lyocell process is detailed in Figure 3.4, which shows a lyocell fiber with a compact fiber core, a porous middlezone and a semipermeable skin.

Figure 3.4. A structure model of regenerated cellulose fiber formed by the lyocell process (adapted with permissions from Abu-Rous et al. 2007).

3.3 Ionic liquid as cellulose solvent

Ionic liquid is a liquid salt, namely molten salt, with a melting temperature lower than 100 °C. It is composed solely of an equal number of organic cations and organic or inorganic anions and thus the overall structure is electrically neutral. ILs have several advantages over conventional solvents, like lower volatility, high thermal stability, and low flammability (Laus et al. 2005, Luo et al. 2012). Some studies suggested that ILs can be toxic to the living organisms (Couling et al. 2006, Singh and Kumar 2008). Admittedly, the toxicity of the ILs has not been fully revealed till now. The variety of the combination possibilities of different cations and anions allows having uncountable ILs with different physicochemical properties, thus making the ILs promising for a broad range of applications, including organic/polymer synthesis, catalysis, electrochemistry, extractions and biomass fractionation, dissolution and shaping (Rogers and Seddon 2003, Shih et al. 2011, Dupont et al. 2002, Lu et al. 2006, Wei et al. 2003, Sun et al. 2011, Wang et al. 2012b). For example, the subcategory of room-temperature ILs (RTILs) may solidify at temperatures lower than 25 °C, which is generally the result of the combination of bulky and unsymmetrical cations and small anions. While the thermal stability of the IL can be affected by the nature of the anion and the side chains of the IL, the ILs containing saturated side chains are thermally more stable than those with unsaturated chains.

The basic strategy of the dissolution of cellulose in ILs is the disruption of the inter- and intra-hydrogen bond links (Li et al. 2018a, Pinkert et al. 2009, Wang et al. 2012b). This was confirmed by using analysis techniques such as wide-angle X-ray scattering (WAXS), small-angle X-ray diffraction (SAXS) and ¹³C solid-state NMR spectroscopy, suggesting that the dissolution involved mainly the interaction between the anion and the cellulose hydroxyl groups to form an electron donor-electron acceptor complex (Remsing et al. 2006, Li et al. 2018). Thus, it has been widely agreed that anions play a vital role in the dissolution of cellulose in ILs. As schematically summarized in Figure 3.5, recent studies revealed a change in the interactions between the anions and the OH groups of cellulose from a non-bridging to a bridging state after performing the structural investigations on cellulose/IL 1-ethyl-3-methylimidazolium acetate ([Emim][OAc]) solutions in the large interval of cellulose concentrations (Endo et al. 2016). It was also shown that 26–28 wt % of cellulose is the upper limit of complete dissolution at room temperature (Le et al. 2014, Rein et al. 2014). In addition to IL anions, cations also play an important role during the dissolution of cellulose, although this cannot be probed easily due to weak interactions between cations and cellulose (Endo et al. 2016, Li et al. 2018a). Moreover, it is believed that the location of the cations can be anywhere between the sheets in the anion-bridging region, see Figure 3.5.

Figure 3.5. Schematic summary of non-bridging to bridging state transformation with the increase of cellulose concentration in [Emim][OAc] (adapted with permissions from Endo et al. 2016).

The ILs containing, for example, anions such as OAc⁻, HCOO⁻ and Cl⁻, were generally efficient for cellulose dissolution owing to the strong H-bond basicity of the anions, which has been correlated to the breakage of inter- and intra-chain H-bonds within the cellulose chains. ILs with low H-bond basicity did not dissolve cellulose efficiently. Thus, the higher H-bond basicity improves the H-bond acceptability of the IL anion, which leads to better dissolution (Brandt et al. 2013, Isik et al. 2014, Gupta and Jiang 2015). The H-bond basicity and acidity can often be described by empirical Kamlet-Taft parameters as β and α , respectively (Spange et al. 1998, Fukaya et al. 2006). It was demonstrated that the ability of a solvent to dissolve cellulose is described by $\beta - \alpha$ (net basicity) which takes the adverse effect of any intrinsic H-donor into account (Hauru et al. 2012). It was further shown that cellulose solvents should be located in a region roughly defined by $0.80 < \beta < 1.20$ and $0.35 < \beta - \alpha < 0.9$ with higher dissolution power corresponding to higher values within these intervals (Hauru et al. 2012). The addition of water to IL usually leads to a decreased solubility of cellulose. This can be well probed by Kamlet-Taft parameters. Upon the addition of water, β was found to decrease in an almost linear fashion and the approximate slope was the same for different ILs (Hauru et al. 2012). This indicates that the solvent power of IL is tuneable by just varying the water content.

3.4 Swelling and dissolution of cellulose (macro) fibers in ILs

Swelling and dissolution of cellulose fibers are believed to be “visually” two different processes as observed using optical microscope: the former leads to an increase in fiber volume due to the uptake of the swelling agent while the latter is a transition from a two-phase system to a one-phase system (cellulose solution) accompanied by a decrease in fiber diameter and destruction of the original supramolecular structure of cellulose (Klemm et al. 1998, Zhang et al. 2006). Hence, most of the work concerning cellulose swelling and dissolution under controlled conditions have been performed directly by light microscopy, no matter from early reports or current studies (Hock 1954, Glas et al. 2015, Peng et al. 2017, Mäkelä et al. 2018).

In a series of studies by Cuissinat and Navard, five different modes of dissolution and swelling mechanisms were suggested, some modes of which seems to be applicable to both natural and regenerated (man-made) cellulose fibers such

as viscose and Lyocell when being immersed in various solvents including NMMO monohydrate or sodium hydroxide water mixtures or ionic liquids (Cuissinat and Navard 2006a, Cuissinat and Navard 2006b, Cuissinat et al. 2008, Le Moigne and Navard 2010, Chaudemanche and Navard 2011). Figure 3.6 summarizes these different swelling and dissolution mechanisms of wood and cotton fibers as a function of the solvent quality, which have been also observed for ILs and its mixtures with water. Specifically, the five modes were identified according to the dissolution power of the solvents: Mode 1, rapid dissolution by disintegration into fragments in a good solvent; Mode 2, swelling by ballooning followed by complete dissolution in a moderate solvent; Mode 3, swelling by ballooning without dissolution in a bad solvent; Mode 4, homogeneous swelling with no dissolution in a bad solvent; Mode 5, no swelling or dissolution in a non-solvent. It is worth noting that the above case of ballooning exclusively belongs to the outer cell wall layers reserved for natural fibers such as wood or cotton, and it was further revealed that the presence of wax and pectin in the natural fibers may prevent the ballooning behavior regardless of the outer cell wall layers (Cuissinat and Navard 2008).

Figure 3.6. Swelling and dissolution mechanisms of wood and cotton fibres as a function of the solvent quality (adapted with permissions from Le Moigne and Navard 2010).

3.5 All-cellulose composites (ACCs)

As introduced in **Chapter 1**, the ingenious combination of the current trends towards cellulose fibers reinforced biocomposites and self-reinforced polymer composites has led to the development of ACCs. Being the new generation of biocomposites, ACCs have the advantages of 100% natural resources combining biocompatibility, biodegradability, nontoxicity, renewability and eased recyclability (Spörl et al. 2017). Figure 3.7 shows the life cycle of ACCs, which originates from nature and return to nature. In general, most of the lignocellulosic biomass resources can be used as the starting materials of ACCs. Using different

fabrication approaches, high-strength ACCs with tuneable properties have been designed, exhibiting their potential application in diverse fields, such as packaging, structural materials, filtration materials, photoelectric device and biomedical engineering (Arévalo and Peijs 2016, Yousefi et al. 2011, Fang et al. 2013, He et al. 2014, Wang and Chen et al. 2011).

Figure 3.7. Schematic presentation of ACCs preparation via selective dissolution strategies, application and the whole life cycle (adapted with permissions from Li et al. 2018b).

It is challenging to provide a general assessment and review of the mechanical properties of ACCs. One of the main reasons is that they are influenced by numerous factors such as cellulose resource, type of reinforcement, manufacturing process conditions, etc. (Singh et al. 2015, Baghaei and Skrifvars 2020). So far, the ACCs with tensile strength ranging from several tens to more than 900 MPa and Young's modulus ranging from few GPa to more than 40 GPa were produced, as summarized in Figure 3.8. It shows that the tensile strength and Young's modulus of most of ACCs are located below 200 MPa and 20 GPa, respectively. In the following section, the main manufacturing methods used for ACCs preparation in relation to the work performed in this thesis are presented. They are: i) manufacturing ACCs via selective dissolution strategy, or more precisely, when the cellulose fibers are “glued” by dissolved cellulose or added cellulose solution and, ii) manufacturing ACCs via self-binding by hydrogen bondings, that is to say, CNF based nanopaper.

Figure 3.8. Mechanical properties of most of the ACCs reported so far (adapted from Baghaei and Skrifvars 2020).

3.5.1 Manufacturing ACCs via selective dissolution strategy

Selective or partial dissolution is the most conventional strategy for ACCs fabrication. As illustrated in Figure 3.7, mainly two distinct routes for the fabrication of ACCs via selective dissolution strategy have been demonstrated in the literature: i) One-step method and ii) Two-step method.

So far, most efforts concerning the production of ACCs have followed the One-step method by using direct cellulose solvents to partially dissolve either aligned cellulose fibers (both natural cellulose and various MMCFs) or structured cellulosic materials such as pulp sheet, filter paper, wood ply and fabric (Soykeabkaew et al. 2008, Huber et al. 2012b, Piltonen et al. 2016, Kröling et al. 2018, Khakalo et al. 2019). In this method the cellulose fibers are “glued” together by the partially dissolved cellulose matrix phase and the non-dissolved cellulose reinforcing phase is retained, thus allowing to achieve a high-volume fraction of the reinforcing phase in the final ACCs. It is challenging to precisely control the dimension and content of the reinforcing phase, especially when lacking a deep understanding of the kinetics of the fibers dissolution under the processing conditions. Moreover, the influence of the dissolution time on the structure and properties of the produced ACCs via One-step method is not well established yet, which is especially important when the fabrication process of the targeting product (ACCs) does not need complete dissolution of cellulose. For example, the aligned ramie fibers were immersed in lithium chloride/N, N-dimethylacetamide (LiCl/DMAc) for 1 to 12 h; exceptional longitudinal tensile properties (460 MPa tensile strength and 28 GPa Young’s modulus) were obtained after 2 h immersion (Soykeabkaew et al. 2008). When a conventional filter paper was impregnated with the same solvent, much more time, 12 h, was needed to get the strongest (within that study) ACCs with a tensile strength of 211 MPa and Young’s modulus of 9 GPa (Nishino and Arimoto 2007). Nevertheless, when a filter paper was impregnated with 1-butyl-3-methylimidazolium chloride, 2.5 h

were needed to reach the maximum values of around 90 MPa and 5 GPa for the tensile strength and Young's modulus, respectively (Duchemin et al. 2009).

In the two-step method of the preparation of ACCs, different cellulose raw materials can be used as the matrix and reinforcing phase. The matrix of ACCs is usually the regenerated cellulose from the pre-prepared cellulose solutions, often microcrystalline cellulose (MCC) solution, and the reinforcing phase includes natural cellulose fibers or regenerated fibers or cellulose nanofibers or nanocrystals, which are added into the cellulose solution (Nishino et al. 2004, Ma et al. 2011, Nadhan et al. 2012, Yang et al. 2015, Korhonen et al. 2019). ACCs produced via direct impregnation the fabrics/textiles with pre-prepared cellulose solution is also the case of using this Two-step method (Adak and Mukhopadhyay 2017, Spörl et al. 2017). Different from the One-step method, the Two-step method of preparing ACCs involves the dissolution of cellulose (that will become the matrix) and the following "mixing" with the reinforcing phase, thus allowing a good control of the concentration of the reinforcing phase and an easily adjustable ratio of the reinforcing phase and matrix. However, despite a good interfacial strength between the matrix and reinforcing phase, voids are often formed decreasing the mechanical properties of ACCs (Korhonen et al. 2019, Baghaei and Skrifvars 2020).

In terms of cellulose solvent options for the production of ACCs via selective dissolution strategy with One- or Two-step methods, lithium chloride/dimethylacetamide (LiCl/DMAc), aqueous NaOH and imidazolium-based ILs are the most commonly used solvents (see, for example, Soykeabkaew et al. 2008, Spörl et al. 2017, Korhonen et al. 2019). In particular, ILs attracted attention as cellulose solvents due to their high dissolution power, low vapor pressure and high thermal stability (Hauru et al. 2012). One of the advantages of ILs is that some are capable of dissolving cellulose even at room temperature, which is the case for 1-ethyl-3-methylimidazolium acetate ([EMIM][OAc]). However, some drawbacks of imidazolium-based ionic liquids should be taken into account if they are to be used for cellulose processing: for example, in the presence of impurities in the solvent, side reactions occur at temperatures around 100 °C (Zweckmair et al. 2015, Abushammala and Mao 2020). Table 3.2 lists ACCs made from different sources of cellulose and ILs using both One-step and Two-step methods. Most of the studies involve heating the IL, even [EMIM][OAc], despite that it is room-temperature IL, most probably supposing that the decrease in viscosity should reduce the dissolution time.

Table 3.2. Examples of ACCs manufactured using ILs as solvents. (The abbreviation of imidazolium-based ionic liquids: 1-ethyl-3-methylimidazolium acetate [EMIM][OAc], 1-butyl-3-methylimidazolium chloride [BMIM]Cl, 1-butyl-3-methylimidazolium acetate [BMIM][OAc] and 1-(2-hydroxyethyl)-3-methyl imidazolium chloride [HeMIM]Cl).

IL	Raw Materials	Impregnation Condition	Method	Ref.
[BMIM]Cl	Cotton fabric	100 °C (30 min) and 150 °C (hot press, 30 min)	One-step	Shibata et al. 2013
	Hinoki lumber	100 °C (30 min) and 210 °C (hot press, 30 min)		
[BMIM]Cl	Jute fabric	110 °C (2–8 h)		Bapan and Samrat 2016
	Filter paper			
[BMIM]Cl	Filter paper	80 °C (20–160 min)		Duchemin et al. 2009
[BMIM]Cl	MCC	80 °C (20, 40, 80 and 160 min)		Gindl et al. 2012
[BMIM]Cl	Lyocell fabric	110 °C (3 h)		Adak and Mukhopadhyay 2016
[BMIM]Cl	Lyocell fabric	110 °C (hot press, 0.5–4 h)		Adak and Mukhopadhyay 2018
[BMIM]Cl	Hemp fabric	100–130 °C (hot press, 10 min)		Chen et al. 2020
[BMIM][OAc]	Cordenka textile	95 °C (hot press, 60 min)		Huber et al. 2012b
[BMIM][OAc]	Linen textile	110 °C (hot press, 80 min)	Two-step	Huber et al. 2012c
	Rayon textile			
[EMIM][OAc]	Paper	95 °C (10 s) and 95 °C (hot press, 0.5–6.5 h)		Kröling et al. 2018
[EMIM][OAc]	Birch wood plies	95 °C (30 min)		Khakalo et al. 2019
[EMIM][OAc]	Silk/hemp/cotton thread	60 °C (5 min)		Haverhals et al. 2010
[BMIM]Cl	Lyocell nonwoven mats/MCC	103 °C (1 min)		Gindl et al. 2012
[BMIM]Cl	Lyocell fabric/ cellulose powder	110 °C (hot press, 1–2 h)		Adak and Mukhopadhyay 2017
[EMIM][OAc]	Cordenka fabric/MCC	80 °C (hot press, 0.5–1 h)		Spörl et al. 2017
[HeMIM]Cl	Nanocrystalline cellulose/MCC	85 °C (2 h), 50 °C (10 min)		Ma et al. 2011

3.5.2 Manufacturing ACCs via self-binding

The ACCs described above involve the selective dissolution of cellulose fiber surfaces to form a matrix phase or using cellulose solution to bond the cellulose fibers together. A much eco-friendlier ACCs solely based on cellulose fibers without the use of solvents or binders has also received attention even more than 20 years ago. The commercial product based on self-binding microfibrillated cellulose aiming at the construction market is Zelfo® (Svoboda et al. 2000). The basic strategy of the structure formation relies on cellulose fibers self-binding via H-bonding (Arévalo and Peijs 2016). In terms of this strategy, high surface area of cellulose fibers contributing to the efficient H-bonding, is the key to produce high-performance binder-free ACCs. This approach promoted the exploration of nanosized cellulose fibers, CNFs, which are extracted from (ligno)cellulose biomass and are suspended in water (see more details in **Section 3.2.2**). After casting/filtering the suspension and drying (often using

vacuum-filtration), CNFs are converted into the so-called “cellulose nanopaper”. Hydrogen bonding and nanofiber entanglements are controlling the structure formation and nanopaper properties. The scheme of cellulose nanopaper preparation via vacuum filtration is revealed in Figure 3.9a. Figure 3.9b presents an overview of the mechanical properties of cellulose nanopaper produced from different cellulosic sources. In general, for most of the reported unmodified cellulose nanopapers, the maximal mechanical strength is below 350 MPa while the values of strain at break are around of 4%-10% (Henriksson et al. 2008, Fukuzumi et al. 2009, Sehaqui et al. 2010, Benítez et al. 2013, Österberg et al. 2013).

Figure 3.9. (a) Schematic presentation of cellulose nanopaper preparation from TEMPO-oxidized CNF via vacuum filtration (redrawn from Benítez and Walther et al. 2017). (b) Elastic modulus versus tensile strength for cellulose nanopaper produced from different cellulosic sources (redrawn from Meng and Wang 2019): (1) softwood (Henriksson et al. 2008, Sehaqui et al. 2010, Benítez et al. 2013), (2) hardwood (Fukuzumi et al. 2009, Österberg et al. 2013, Chen et al. 2017), (3) bamboo (Puangsin et al. 2013, Chen et al. 2017), (4) bacteria (Yousefi et al. 2013, Wang et al. 2018a), (5) hemp bast (Puangsin et al. 2013), (6) oat straw (Sehaqui et al. 2014), (7) maize stalks (Mtibe et al. 2015), (8) kenaf (Nobuta et al. 2016), (9) corncob (Kang et al. 2017), (10) tobacco stalk (Wang et al. 2018b), (11) sugarcane bagasse (Santucci et al. 2016), (12) rice straw (Jiang et al. 2016), and (13) green macroalgae (Guo et al. 2017).

The influence of the type of building blocks (dimensions, composition and surface charge of CNF), CNF orientation and concentration, way of drying, water content, presence of additives and material density influence the mechanical properties of CNF nanopapers, as discussed by Benítez and Walther et al. (Benítez and Walther 2017a). In particular, the orientation of CNF is believed to be one of the most important parameters which determines the mechanical performance of cellulose nanopaper (Tang et al. 2015, Zhu et al. 2016). By tuning the orientation of CNFs, both anisotropic and isotropic cellulose films and nanopapers featuring high strength and optical transparency have been designed and tailored through nanostructure engineered strategies, targeting, for example, the substrates for the next generation of “green” flexible devices (Toivonen et al. 2015) and solar cells (Zhu et al. 2014, Fang et al. 2014). Anisotropic nanopaper based on oriented CNF exhibits exceptional strength (>350 MPa), however, the strain at break is only ~4%, and, thus these nanopapers do not offer high mechanical toughness (Zhu et al. 2017, Wang et al. 2018a). In contrast, isotropic cellulose nanopaper based on randomly oriented CNFs and its bundles, which are usually obtained by mechanical and/or biochemical fibrillation of wood fibers (Klemm et al. 2005, Pääkkö et al. 2007) possess typically a lower strength (<300 MPa) but a higher fracture strain up to 10% (Nogi et al. 2009, Fukuzumi, et al. 2009, Sehaqui et al. 2010, Österberg et al. 2013). Like many

man-made materials, nanopaper bears a “conflict” between strength and toughness: strong materials are often fragile, whereas ductile materials tend to be weak (Ritchie 2011, Giesa and Buehler 2013). The low ductility of cellulose nanopaper can be a limiting factor for certain applications. For example, petrol-based polyimide films, which have been suggested as a promising substrate in the field of electronics, have a typical elongation at break of >50% and a Young’s modulus of ~3 GPa (Chang et al. 2008). As a matter of fact, it is still challenging to make cellulose nanopaper which maintains a combination of high strength, ductility, toughness, and optical transparency.

In addition to nanosized cellulose fibers, microscale cellulose fibers were also successfully converted to ACCs via self-binding method generally aided by hot-pressing (Nilsson et al. 2010, Arévalo and Peijs 2016). However, the mechanical properties of those composites were rather limited. Yang et al. performed a series of modifications (including degumming and alkali treatment) of ramie fibers to produce fibers with high cellulose purity and further improve interfaces and strength by increasing the mobility of cellulose surface chains of each fiber during consolidation. This strategy resulted in a film with high fiber orientation, high longitudinal mechanical properties (620 MPa), reduced moisture sorption, and high optical transparency (Yang and Berglund 2018). The mechanical performance in transverse direction were quite weak.

3.6 Comments on the tensile testing of ACCs

As already mentioned in **Section 3.5**, it is challenging to provide a general assessment or comparison of the mechanical properties of ACCs. The lack of consistency in tensile testing, an often-ignored fact that inevitably leads to erroneous evaluation of mechanical performance of ACCs, is another reason. Besides the fact that the mechanical values obtained from tensile testing depend on sample geometry (Hervy et al. 2017), there are various methods available so far to obtain the specimen elongation (directly from the tensile machine, from extensometer in which gauges are “clipped” on the material, using video extensometers or digital image correlation (DIC)) (G'Sell et al. 1992, Xiao 2008, Faridmehr et al. 2014, Felling and Doman 2018). DIC technique is the most precise method and is well known in polymer science, but rarely used for natural fiber reinforced polymer composites (Xu et al. 2019, Ramakrishnan et al. 2020) and, to the best of our knowledge, was never considered for the evaluation of the tensile properties of ACCs.

Whatever the approach used, stress-strain dependences are built to characterize the material with Young’s modulus, tensile strength and tensile strain. The obtained results will include different levels of errors depending on the approach used. For example, the displacement directly given by the machine includes not only the elongation of the sample in the gauge length region, but also the displacement induced by the stiffness of the tensile machine, the latter inducing erroneous mechanical properties. Video extensometer using a non-contact measurement will exclude the above-mentioned problem (G'Sell et al. 1992). However, the displacement of the specimen may not be homogeneous

along the specimen length. The displacement measured using video extensometer may depend on the location of the marks on the sample and also on the length L which can be either sample length or the distance between selected two points. Finally, the most precise (but the most time-consuming) way of having a complete information on the deforming material is DIC that allows obtaining a map of local strains on the specimen surface due to video cameras in stereovision which monitor the displacements of the markers (or speckles) placed randomly on the sample surface (Sutton et al. 2009, Candau et al. 2016).

As far as ACCs are concerned in this thesis, the majority of the reported tensile properties were obtained directly from machine (Piltonen et al. 2016, Sirviö et al. 2017, Soykeabkaew et al. 2008, Soykeabkaew et al. 2009, Korhonen et al. 2019, Wei et al. 2020). Few works report the results obtained with video extensometer (Duchemin et al. 2009, Kröling et al. 2018, Mat Salleh et al. 2017). In all examples mentioned above nominal stress-strain curves were used to calculate Young's modulus, tensile strength and elongation at break. The influence of the method used to obtain stress-strain curves of ACCs and further values of Young's modulus, tensile strength and elongation at break of ACCs is an open question.

3.7 Concluding remarks

The above presented information shows that in order to design ACC with predictable properties, a good understanding of cellulose fibers swelling/dissolution kinetics and mechanism governing these processes is very important. This helps to comprehend the structure (cellulose fibers)-processing (cellulose dissolution/swelling)-property (ACCs) correlations, and in turn guides us to use multiway dissolution/swelling strategies for designing high performance ACCs. Therefore, this thesis will start with the fundamental studies of the effect of fiber structure and solvent power on the swelling and dissolution kinetics of different cellulose fibers. Then the strategies involving controlled dissolution and swelling of cellulose fibers were adopted to design various ACCs based on unidirectional fibers and on isotropic filter paper. The effect of the dissolution time on the morphology, composite density and crystallinity was studied and correlated with ACC mechanical properties. Digital image correlation was explored for the analysis of the tensile properties of filter paper-based ACC as well. Finally, the ACCs from CNF via self-binding method involving swelling of nanoscale cellulose fibers were produced with the purpose of making ductile cellulose nanopaper while keeping high strength and toughness

4. Experimental

This chapter describes the main materials and experimental methods used in this thesis. Each methodology is briefly presented, and the corresponding articles are referenced accordingly. More detailed information on all the materials and applied methods can be found in **Papers I-IV**.

4.1 Materials

4.1.1 Cellulose macroscale fibers

Four different macroscale cellulose fibers: one natural fiber and three MMCFs, were used in this thesis. Flax fibers (**Papers I-II**) were from the outer bast layer of the plant stem in the shape of roving yarns with low twist degree. A commercially available high-strength rayon filament yarn Cordenka 700 (**Paper I**) was kindly donated by Cordenka GmbH & Co. KG., and two other MMCFs were produced by spinning of an unbleached birch kraft pulp-IL solutions resulting in Ioncell-FL fibers (**Paper I**), and of a prehydrolysed kraft birch pulp-IL solution, resulting in Ioncell-F fibers (**Paper I**). Their characteristics (molecular weight, composition and crystallinity) are shown in **Section 5.1**.

4.1.2 Cellulose nanofibrils (CNF)

The suspension of CNF in water (**Paper IV**) at a concentration of 1.82 wt. % was prepared by passing never-dried, bleached birch pulp (kindly provided by UPM from a Finnish pulp mill) six times through a chamber pair (200 μm and 100 μm) arranged in series in a high-pressure microfluidization (Microfluidics Corp., USA), under a pressure of 2000 bar. CNF characteristics (composition, crystallinity and topological structure) are provided in **Section 5.6.1**.

The 0.4 wt. % CNF suspension was used as the starting batch for making nanopaper. It was obtained by diluting the 1.82 wt. % CNF suspension with water and magnetically stirring for 12 h. Then the 0.4 wt% CNF suspension was diluted to different concentrations of CNF (Table 4.1) using either 50 wt.% IL-50 wt.% water or 80 wt.% IL-20 wt.% water or with water (reference samples) under magnetic stirring at around 700 rpm for 5 min. The IL, [EMIM][OAc], used to dilute the CNF suspensions, is detailed in **Section 4.1.4**. Reference suspensions of CNF-water (without ionic liquid) with the same corresponding CNF concentrations were prepared by diluting the starting 0.4 wt.% suspension with water. Freshly prepared suspensions were always used. The nomenclature and

concentrations of all components in CNF suspensions and corresponding nanopaper (the details on nanopaper preparation is given in **Section 4.2.4**) are listed in Table 4.1.

Table 4.1. Nomenclature and concentrations of all components in CNF suspensions and corresponding nanopaper.

Suspension code	Dispersant	IL concentration (wt. %)	CNF concentration (wt. %)	Nanopaper code
Starting CNF batch	water	0	0.4	CNF
0.34%CNF-5%IL-W	IL-water	5	0.34	CNF5
0.28%CNF-15%IL-W	IL-water	15	0.28	CNF15
0.16%CNF-30%IL-W	IL-water	30	0.16	CNF30
0.15%CNF-50%IL-W	IL-water	50	0.15	CNF50
0.34%CNF-5%water	water	0	0.34	-
0.28%CNF-15%water	water	0	0.28	-
0.16%CNF-30%water	water	0	0.16	-

4.1.3 Cellulosic filter paper

Qualitative VWR® Grade 415 filter paper (**Paper III**) made of pure cellulose was purchased from VWR International, France.

4.1.4 Ionic liquids (ILs)

1-Ethyl-3-methylimidazolium acetate ([EMIM][OAc], purity >95%) in **Papers I-IV** was purchased from IoLiTec, Germany, and novel IL N-methyl-1,5-diazabicyclo[4.3.0]non-5-enium dimethyl phosphate ([mDBN][DMP]) was kindly provided by Alistair King, the University of Helsinki, Finland. The moisture content of [EMIM][OAc] and [mDBN][DMP] was 0.27% and 0.08%, respectively, as determined by Karl-Fischer titration. Both room temperature ILs were used as received. Figure 4.1 presents the chemical structures of the two ILs.

Figure 4.1. Chemical structures of IL (a) [EMIM][OAc] and (b) [mDBN][DMP] (adapted from Parviainen et al. 2014).

4.1.5 Other materials

The milli-Q® water or double distilled water was used to dilute the ILs and CNF suspensions (**Papers I and IV**). In other conditions, the water used was general deionized water.

4.2 Preparation of all-cellulose composites

This part describes the preparation of four different types of ACCs adopting different fabrication strategies: 1) Unidirectional flax-based ACCs via selective dissolution (**Paper II**); 2) Unidirectional flax-based ACCs via selective swelling (**unpublished results**); 3) Isotropic macroscale paper-based ACCs (**Paper III**) and 4) Isotropic cellulose nanopaper (**Paper IV**). More detailed information is given in the corresponding papers.

4.2.1 Fabricating unidirectional flax-based ACCs via selective dissolution

Flax yarns were unidirectionally aligned in two layers (around 145 yarns, 3 g in total) on a Teflon mold and fixed at both ends to prevent shrinkage and distortion. The ACC manufacturing method is illustrated in Figure 4.2. Fibers were impregnated with 20 mL of [EMIM][OAc], kept under ambient conditions for desired times (10, 25, 40 and 55 min) and then pressed for 5 min (80 bar, room temperature) to complete the impregnation. The total duration of fiber treatment with ionic liquid was thus 15, 30, 45 and 60 min. Then, the sample was washed in a large amount of deionized water for 72 h to remove the IL from the system. Subsequently, the specimen was dried by hot pressing (50 bar, at 80 °C for 2.5 h and then at 60 °C for 0.5 h). A temperature gradient during drying was used to prevent the warping and/or heterogeneous contraction of the sample. The obtained flax-based ACCs were coded SD (selective dissolution) 15, SD30, SD45 and SD60, respectively.

Figure 4.2. Fabricating scheme for ACCs produced in **Paper II**.

4.2.2 Fabricating unidirectional flax-based ACCs via selective swelling

The as-received flax yarns (around 145 bundles, 3 g) were hand aligned unidirectionally in two layers and fixed at both ends in a Teflon mould to prevent shrinkage and distortion. The manufacturing method is depicted in Figure 4.3. Flax fibers were impregnated with 20 mL of mixed solvent ([mDBN][DMP]+5% water), kept at ambient conditions for 1 h to guarantee sufficient adsorption of solvent. After that, hot pressing (at 50°C and 80 bar for 30 min) was applied to the sample. Then the sample was washed in a large amount of deionized water for 72 h to remove IL [mDBN][DMP] from the system. Subsequently, the specimen was dried by hot pressing (around 50 bar, keep at 80°C for 2.5 h and then at 60°C for 0.5 h). The obtained paper-based ACC was coded SW30 (SW means selective swelling).

Figure 4.3. Fabricating scheme for ACCs produced via selective swelling.

4.2.3 Fabricating isotropic macroscale paper-based ACCs

The macroscale paper-based ACCs manufacturing method is illustrated in Figure 4.4. Two pieces of filter papers were soaked in [EMIM][OAc] for 1 min and then the stack was subsequently hot pressed at 60 °C. The pressing times were 5 min, 10 min, 30 min and 60 min with the pressure kept constant (around 100 bar). Then the sample was immersed in a large amount of deionized water for 72 h to remove the ionic liquid from the system. Finally, the specimen was dried by hot pressing (around 50 bar, 80 °C for 2.5 h and then at 60 °C for 0.5 h). The obtained paper-based ACCs were coded P5, P10, P30 and P60, respectively.

Figure 4.4. Fabricating scheme for paper-based ACCs produced in **Paper III**.

4.2.4 Fabricating cellulose nanopaper

Figure 4.5 briefly presents the scheme for making nanopapers (**Paper IV**). The detailed information (nomenclature and concentration) of CNF-water suspension and CNF-IL-water suspensions for the production of nanopapers and the corresponding nanopapers is presented in Table 4.1.

1) Nanopaper from CNF-water suspension as the reference. CNF-water suspension (0.4 wt.%) was low vacuum filtered on a hydrophilic polyvinylidene fluoride filter membrane (0.22 μm , GVWP, Millipore) until a wet gel cake was formed and no vibration of a water layer was observed when the filtering apparatus was sharply tapped. The filtration step was completed typically in 10 min. Then a second filter membrane was placed on top of the gel cake, and the whole assembly was dried for 3 days at 25 °C and 50% RH under a 100 g weight. Samples were stored at 25 °C and 50% RH.

2) Nanopapers from CNF-IL-water suspensions were produced as described for nanopaper from CNF-water suspension but the gel cake was washed with water under vacuum filtration for 30 min to remove IL, then filtered to remove water and dried as above. The IL-water mixture may be then collected and re-used, after adjusting the IL concentration, for the subsequent preparations of nanopaper.

Figure 4.5. Fabricating scheme for nanopapers produced in **Paper IV**.

4.3 Characterization methods

4.3.1 Optical microscopy observations of fiber swelling and dissolution

The swelling and dissolution of different cellulose macroscale fibers in ILs and ILs-water mixtures were observed by optical microscope (**Papers I-II**). One elementary fiber was placed between two glass plates with the in-between distance around 140 μm controlled by spacers. The distance between two glass slides is much larger than the fiber's thickness. The ends of the fiber were fixed by tape and solvent added. Fiber diameter was recorded by a DM4500P (Leica) optical microscope in transmission mode equipped with a CCD camera (Metallux 3, Leitz) and Linkam TMS 91 hot stage to control temperature. The evolution of the fiber diameter in time t was calculated as D_t/D_0 , where D_0 and D_t are initial diameter of the fiber at $t = 0$ and diameter of fiber at time t , respectively.

4.3.2 Methods for matter characterisation in the solid state

This part describes the main physicochemical characterizations of the matter in the solid state including raw materials (macroscale cellulose fibers and filter paper) and the ACCs (unidirectional flax-based ACCs, macroscale paper-based ACCs and cellulose nanopapers)

Chemical composition: The composition (carbohydrates, total lignin) of all macroscale cellulose fibers, starting CNFs and nanopapers was determined according to NREL/TP-510-42618 norm (**Papers I-II and IV**). The amount of carbohydrates was detected by high performance anion exchange chromatography with pulse amperometric detection (HPAEC-PAD) using a Dionex ICS-300 system. Cellulose and hemicellulose contents were calculated according to the amount of monosaccharides following the Janson formula (Janson 1970). The acid-soluble lignin was determined by using a Shimadzu UV 2550 spectrophotometer at a wavelength of 205 nm using absorption coefficient of 110 $\text{L g}^{-1} \text{cm}^{-1}$.

Molecular weight distribution: The molecular weight distribution of cellulose in all macroscale cellulose fibers was characterized by gel permeation chromatography (GPC) according to the procedure described elsewhere (Ma et al. 2018), and number-average and weight-average molecular weights, M_n and M_w , were calculated (**Papers I-II**). Prior to the analysis, fibers were cut into small pieces. The GPC system consisted of a pre-column (PLgel Mixed-A, 7.5×50 mm), four analytical columns ($4 \times$ PLgel Mixed-A, 7.5×300 mm) and a RI-detector (Shodex RI-101). The fibers were pre-activated by water/acetone/DMAc solvent exchange sequence. The samples were then dissolved in a 90 g/L LiCl/DMAc mixture at room temperature. The solution was diluted to 9 g/L LiCl/DMAc, filtered through a 0.2 mm syringe filter and analyzed by using a Dionex Ultimate 3000 system with refractive index (RI) detection (Shodex RI-101).

Crystalline phase and crystallinity: XRD patterns of all macroscale cellulose fibers (**Papers I-II**) and unidirectional flax-based ACCs (**Paper II**) were

collected on an X-ray diffractometer (a X'Pert Pro MRD, PAN'alytical, Lelyweg, The Netherlands) with Cu-K α radiation ($\lambda = 1.5418 \text{ \AA}$) in reflection mode. All samples were ground to powders and mounted on a multi-position sample holder. Data were collected in a 2θ range between 5° and 50° .

The XRD patterns of filter paper and filter paper-based ACCs in **Paper III**, and all produced cellulose nanopapers in **Paper IV**, were collected from an X-ray instrument, SmartLab (RIGAKU). The scans were performed in the 2θ range from 5° to 60° by $\theta/2\theta$ mode. Background intensity profile without sample was collected in the same conditions, and it was subtracted from the obtained data.

More details about the setting of X-ray instrument, calculations of crystallinities (**Papers I-IV**) and volume fractions of Cell-I and Cell-II (**Papers II and III**), can be found in the corresponding papers.

Dynamic vapor sorption: A DVS apparatus with a measuring accuracy of 0.1 mg was used to record the kinetics of water vapor sorption by the macroscale cellulose fibers in **Paper I**. Around 15 mg of grinded fibers were placed in the sample pan and their weight evolution was recorded upon decrease of the relative humidity (RH) to 0% at 25°C under nitrogen (flow rate $100 \text{ cm}^3/\text{s}$). Equilibrium was considered to be reached when sample mass change was below 0.001% per minute over 10 min. Then RH was increased to 60% and sample weight evolution and time to reach equilibrium (t_s) were recorded. Moisture desorption M_{des} (from M_{amb} at ambient conditions to M_0 at 0% RH) and sorption M_s (from M_0 to M_{60} at 60% RH) were calculated as follows:

$$M_{\text{des}} = \frac{M_{\text{amb}} - M_0}{M_0} \times 100\% \quad (1)$$

$$M_s = \frac{M_{60} - M_0}{M_0} \times 100\% \quad (2)$$

Morphology: The morphology of the flax fibers and the flax-based ACCs in **Paper II**, of the initial filter paper and paper-based ACCs in **Paper III** and of cellulose nanopapers in **Paper IV**, were observed using a scanning electron microscope (Zeiss Sigma VP FE-SEM, Jena, Germany) at an accelerating voltage of 4 kV. Prior to examination, the surface and cross section of the ACCs were coated with a thin layer of gold. The cross sections for cellulose nanopapers were observed after cryo-fracture and tensile-fracture. In addition, in **Paper IV**, Atomic Force Microscopy (AFM, MultiMode 8 Scanning Probe Microscope, Bruker AXS Inc.) was used to analyze the the surface morphology and roughness of the obtained nanopapers. The AFM scans ($15 \mu\text{m} \times 15 \mu\text{m}$) were collected under tapping mode in air with silicon cantilevers (NSC15/AIBS, MicroMasch). Ten different areas were scanned to obtain mean value of roughness R_q (the root mean square average of height deviation taken from the mean image data plane) and R_a (the arithmetic average of the absolute values of the surface height deviations measured from the mean plane).

Density and porosity: The bulk density of the ACCs (**Papers II-III**) (“density” in the following) and of cellulose nanopapers (**Paper IV**) was determined by measuring its weight and dividing it by its volume. The volume was calculated from the thickness of the nanopaper and its area, the dimensions were measured by using L&W Micrometer (Lorentzen & Wettre Products, ABB,

Switzerland) with an error of $\pm 1 \mu\text{m}$ or 0.1% of the reading, whichever is greater. Porosity was estimated from the bulk density of the ACCs and nanopaper by using a value of 1.46 g cm^{-3} as the skeletal density of cellulose (Sun 2007) using the following equation:

$$\text{Porosity (\%)} = \left[1 - \frac{\rho_{\text{ACCs, nanopaper}}}{\rho_{\text{cellulose}}} \right] \times 100\% \quad (3)$$

Ultraviolet–Visible Light (UV–vis) Spectroscopy: The optical properties of transmittance and haze of the filter paper-based ACCs in **Paper III** and cellulose nanopapers in **Paper IV** were obtained using a Shimadzu UV-2600 with an ISR-2600 Plus Integrating Sphere Attachment (Shimadzu, Japan), in the interval between 1200 nm and 200 nm. Optical haze was used to quantify the percentage of the forward light scattering as follows (Zhu et al. 2013):

$$\text{Haze} = \left[\frac{T_4}{T_2} - \frac{T_3}{T_1} \right] \times 100\% \quad (4)$$

where T_1 , T_2 , T_3 and T_4 are defined as background checking, total transmitted illumination, beam checking and pure diffusive transmittance, respectively.

Tensile testing: The mechanical properties of unidirectional flax-based ACCs (**Paper II**) and cellulose nanopapers (**Paper IV**) were studied using an Instron 4204 Universal Tensile Tester (INSTRON, Buckinghamshire, UK). All the samples were conditioned for 24 h in a controlled environment of 50% RH and 23 °C. For flax-based ACC (**Paper II**), at least five specimens ($50 \times 5 \text{ mm}$, length and width, respectively) with known thickness of each formulation were analyzed at a gauge length of 20 mm and an extension rate of 10 mm/min with a load of 1 kN. For nanopaper (**Paper IV**), more than ten specimens with known thicknesses ($20 \text{ mm} \times 4 \text{ mm}$, length and width, respectively) of each formulation were measured; specimen edges were glued onto a paper frame (leaving a gauge length of 10 mm) to avoid slippage and deformed at a rate of 0.5 mm/min using a 100 N load cell.

Tensile testing applying DIC analysis: The mechanical properties of filter paper and of all prepared macropaper-based ACCs made from filter paper (**Paper III**) were studied using an electro-mechanical tensile test machine Zwick-2.5 kN at 23 °C and 50% RH. Figure 4.6a presents the geometry of the tensile sample with a gauge length (L_0) and a width (W) of 15 mm and 10 mm, respectively. The measurement was carried out at a strain rate of $1 \times 10^{-3} \text{ s}^{-1}$. The displacement fields on face of the sample were recorded using a two-cameras system (Figure 4.6b). Front surface of the samples was coated with a white spray on which a random speckle pattern was then generated (Figure 4.6c), thus allowing the Digital Image Correlation of the series of images post-processed using VIC-3D software package (Figure 4.6d). More details concerning the engineering (or nominal) and true stress-strain curves from machine and from DIC analysis can be found in **Paper III**.

Figure 4.6. The tensile testing setup in this study: (a) Geometry of the tensile sample, units are in mm. (b) Experimental setup based on two independent stereovision systems to measure simultaneously strain fields on sample surface. (c) Speckle sample for the Digital Image Correlation. (d) True (local) strain field obtained by DIC analysis using VIC-3D software, S is the surface over which the true strain in the longitudinal direction is averaged (adapted from **Paper III**).

4.3.3 Methods for matter characterisation in liquid state

This part describes the main physicochemical characterization methods of a matter in liquid state, the latter being ILs, ILs-water mixture, CNF-water suspensions and CNF-IL-water suspensions.

Thermal properties: The phase transitions of both ILs ([EMIM][OAc] and [mDBN][DMP]) were measured using a Differential Scanning Calorimetry (PerkinElmer, DSC 8000) with a liquid nitrogen cooling system for temperature control. Samples were placed in aluminium hermetically sealed pans and measured at a rate of 10 °C / min from –130 °C to 60 °C. The thermal stabilities of both ILs were measured using Thermogravimetric Analysis (TGA, TA Instruments Q500). Samples were placed in a platinum alloy pan and measured at a rate of 5 °C / min from 20 °C to 600 °C.

Kamlet–Taft parameters: The K-T parameters of the neat [EMIM][OAc] and [EMIM][OAc]-water mixtures (**Paper I**) were determined from the absorption peaks of three different dyes: Reichardt's dye (RD, range 518–585 nm), N,N-diethyl-4-nitroaniline (DENA, 402–414 nm) and 4-nitroaniline (NA, 406–398 nm). The dyes were weighed and mixed with the IL or IL-water mixture. A Varian UV–Vis spectrometer equipped with a thermostat (precision ± 0.1 °C) was used. The milli-Q® water was measured for background subtraction. Spectra were collected at a resolution of 1 nm and 10–30 nm of absorbance and data around the peak were fitted with a Gaussian function in order to precisely locate the maximum. More details on the measurement of Kamlet–Taft parameters can be found in ref. (Hauru et al. 2012).

Rheology: The rheological properties of ILs, IL-water and CNF suspensions were characterized using an Anton Paar MCR 302 rheometer equipped with a Peltier temperature control system. Viscosity-shear rate dependences were recorded with a plate-plate geometry (25 mm plate diameter, 1 mm gap) from 1 to 100 s⁻¹ at fixed temperature which was varied from 20 to 60 °C. Viscoelastic properties of CNF suspensions were studied using cone-plate geometry (cone angle 1°; 50 mm plate diameter) at 25 °C. Strain sweep experiments were conducted within a strain range from 0.01% to 100% at a fixed frequency of 1 Hz in order to determine the linear viscoelastic region which was up to 10% strain.

Frequency sweep measurements were carried out at angular frequency range from 0.1 to 1000 rad/s at a strain of 1%.

Topological structure of CNF: Atomic Force Microscopy (AFM, MultiMode 8 Scanning Probe Microscope, Bruker AXS Inc.) was used to analyze the initial CNF dispersed in water (**Paper IV**). The initial CNF suspension was diluted to 0.01 wt.% and spin-coated onto polyethyleneimine-coated mica. The nanofibril-coated substrate was dried overnight at room temperature before imaging. The AFM scans ($3\ \mu\text{m} \times 3\ \mu\text{m}$) were collected under tapping mode in air with silicon cantilevers (NSC15/AIBS, MicroMasch).

Cryogenic Transmission Electron Microscopy: The morphology of CNF bundles before and after the treatment with IL was monitored by Cryo-TEM (JEOL 3200FSC Cryo-TEM). The detailed samples preparation can be found in **Paper IV**. 3 μL of CNF-15%-IL-water or CNF-15%-water was placed onto a carbon copper grids (200 mesh, Science Services), from where most of the samples were blotted with a filter paper under 100% humidity, leaving a thin layer of sample over the grids. The specimens were shock-vitrified by fast immersion into liquid ethane-propane mixture at around $-180\ ^\circ\text{C}$ inside a FEI Vitrobot (Zeiss Cryobox, Zeiss NTS GmbH). The vitrified samples were then cryo-transferred to the Cryo-TEM (JEOL 3200FSC Cryo-TEM) operated at 300 kV in bright field mode. The specimens' temperature was kept at $-183\ ^\circ\text{C}$. The imaging was carried out with an Omega-type Zero-loss energy filter and acquired with Gatan Ultrascan 4000 CCD camera.

5. Results and Discussion

This chapter presents the main results obtained in this thesis, in which the four research questions stated in **Chapter 2** will be discussed. The physicochemical characterizations of the macroscale cellulose fibers, ILs and ILs-water mixtures are presented in the first two sections (**Section 5.1 and 5.2**, respectively) followed by the discussion on the kinetics of various macroscale cellulose fibers dissolution and swelling in solvent power tuned ILs (**Section 5.3**). Next, the performance of unidirectional flax-based ACCs produced via selective dissolution and via selective swelling methods are compared (**Section 5.4**). Then, the analysis of the mechanical properties of the isotropic macroscale paper-based ACCs applying Digital Image Correlation is explored (**Section 5.5**). Finally, the properties of isotropic cellulose nanopaper which combines high ductility with high mechanical strength and toughness are presented (**Section 5.6**). More detailed results and discussion can be found in the attached **Papers I-IV**.

5.1 Characterization of macroscale cellulose fibers

Structurally different macroscale cellulose fibers, such as natural fiber flax, MMCFs Cordenka, Ioncell-F and Ioncell-FL (the latter containing lignin and hemicelluloses), were used for the study of fiber swelling and dissolution kinetics in ionic liquid (**Paper I**), and flax was also used for ACCs fabrication (**Paper II**). In order to interpret the kinetics results, fibers' chemical composition, cellulose molecular weight, crystallinity index and accessibility were first analysed.

The composition of the fibers is shown in Table 5.1. Flax contains 83.3% cellulose, 11.3% hemicelluloses and 2.3% lignin, which is in accordance with the results in the literature (Yan et al. 2014; Bolton 1994). Cordenka is spun from a high-grade dissolving pulp, thus containing only small amounts of hemicelluloses. Ioncell-F produced from a standard dissolving-grade pulp has a higher hemicellulose content. Ioncell-FL is spun from an unbleached kraft pulp and thus contains notable amounts of both hemicelluloses and lignin.

The M_n and M_w molecular weights of cellulose in each fiber are presented in Table 5.1, and the corresponding molecular weight distributions are shown in Figure 5.1a. The results are similar for all MMCFs and are much higher for flax. A distinct low molecular weight peak for Ioncell-FL and a subtle shoulder for flax and Ioncell-F correspond to the hemicellulose fraction, as shown in Table 5.1.

Table 5.1. Characteristics of macroscale cellulose fibers involved in this thesis. (adapted with permissions from Chen et al. 2020, **Paper I**)

Fibers	Cellulose %	Hemicellulose %	Lignin %	M _n kDa	M _w kDa	CRI _{total} %	M _{des} %	M _s %	t _s min
Flax	83.3	11.3	2.3	652	714	45.1	1.3	7.15	115.7
Cordenka	92.3	2.4	-	68	133	28.1	7.2	11.91	305.2
Ioncell-F	88.9	8.2	-	45	134	40.3	7.5	9.82	177.5
Ioncell-FL	51.1	21.3	22.9	45	176	27.3	10	9.87	177.5

Figure 5.1. Cellulose molecular mass distribution (a) and X-ray diffraction profiles (b) of flax, Cordenka, Ioncell-F and Ioncell-FL (adapted with permissions from Chen et al. 2020, **Paper I**).

The XRD profiles of the fibers are presented in Figure 5.1b. Flax contains Cell-I with crystallinity index (CRI_{total}) of around 45%, which is typical for plant cellulose (Placet et al. 2012, Moryganov et al. 2018). The MMCFs contain the Cell-II allomorph, as expected. The CRI_{total} is around 28%, 40% and 27% for Cordenka, Ioncell-F and Ioncell-FL, respectively (Table 5.1). Cordenka, a viscose type cellulose fiber, has low crystallinity, in-line with data in literature (Kreze and Malej 2003; Okubayashi et al. 2005). As the crystallinity is calculated over the total material, and non-cellulose fraction in Ioncell-FL is around 50%, cellulose crystallinity in Ioncell-FL is higher than CRI_{total} and was reported to be around 40% (Ma et al. 2018).

The dynamic water vapor desorption and sorption were measured to compare the accessibility of the fibers. The desorption (to 0% RH) and sorption (to 60% RH) curves can be found in **Paper I** (Figure S1). Moisture desorption (M_{des}), time to reach equilibrium t_s from 0 to 60%RH and moisture sorption (M_s) for each fiber are shown in Table 5.1. M_{des} reflects the amount of water which is desorbed from ambient conditions to 0% RH and it is the lowest for flax. Cordenka, as viscose fiber, absorbs the highest amount of moisture (M_s) due to its lowest crystallinity and larger pore volume (Okubayashi et al. 2005). Time to reach equilibrium, t_s = 305.2 s, is the longest for Cordenka (Table 5.1) probably because of hornification phenomena (Siroka et al. 2008) as viscose fibers can

be overdried, and also because absorption of a larger amount of vapor takes more time. The lignin-free fiber Ioncell-F and lignin-containing fiber Ioncell-FL show the same moisture sorption characteristics, like those of commercial Lyocell fibers with a moisture sorption around 9–10% at 60% RH and room temperature (Okubayashi et al. 2004). The presence of hydrophobic lignin does not influence the water vapor sorption behavior, in line with previously reported results (Ma et al. 2015). Flax absorbs the least amount of vapor probably because of the “resistant” primary wall (Okubayashi et al. 2004; Xie et al. 2011; Le Moigne et al. 2008) and higher cellulose crystallinity (Table 5.1).

5.2 Characterization of ILs and ILs-water mixtures

5.2.1 Thermal properties of ILs

The ionic liquids [EMIM][OAc] and [mDBN][DMP] used in this thesis are room temperature ILs. The DSC traces are shown in Figures 5.2a and 5.2b. No melting or crystallization of both ILs was detected at temperature from $-100\text{ }^{\circ}\text{C}$ to $60\text{ }^{\circ}\text{C}$; glass transition temperatures were $-82\text{ }^{\circ}\text{C}$ and $-75\text{ }^{\circ}\text{C}$ for [EMIM][OAc] and [mDBN][DMP], respectively. Figures 5.2c and 5.2d show the TGA profiles of [EMIM][OAc] and [mDBN][DMP], respectively. Both ILs are stable within $100\text{ }^{\circ}\text{C}$. No phase transition and thermal degradation related to ionic liquids will interfere in the kinetics study of swelling and dissolution of fibers and the production of various ACCs, since they are performed at between $20\text{ }^{\circ}\text{C}$ to $95\text{ }^{\circ}\text{C}$.

Figure 5.2. The DSC traces of ILs (a) [EMIM][OAc] and (b) [mDBN][DMP]. The TGA profiles of ILs (c) [EMIM][OAc] and (d) [mDBN][DMP].

5.2.2 Kamlet–Taft parameters

The K–T parameters (see detailed description in **Section 3.3**) of [EMIM][OAc] with different water contents were measured in the range of 20–60 °C (**Paper I**). Figure 5.3 shows the values of β and $\beta-\alpha$ as a function of water content at 25 °C and 60 °C, revealing that the effect of temperature on K-T values was very small. Within the range of the studied water content, both β and $\beta-\alpha$ values show a linear decrease with the increase of water content, indicating that a decreased dissolution ability with 15 wt.% water was at the limit of the solubility window. It was reported that above 15 wt.% water in [EMIM][OAc] microcrystalline cellulose forms swollen aggregates (Le et al. 2012). Therefore, in the following kinetics study (**Paper I**) [EMIM][OAc] containing 0, 5 and 15 wt.% of water was used as solvents with different power to monitor fiber swelling and dissolution behavior.

Figure 5.3. β (red symbols) and $\beta-\alpha$ (blue symbols) plotted against water content in IL [EMIM][OAc] at 25 °C (solid symbol) and 60 °C (open symbol) (adapted with permissions from Chen et al. 2020, **Paper I**).

5.2.3 Rheological properties of ILs and ILs-water mixtures

The kinetics of cellulose fiber swelling and dissolution and thus the ACCs fabrication process may depend on solvent viscosity, the latter was measured at various temperatures. Both ILs showed Newtonian behavior over the whole shear rate range applied in this thesis, and similar results have already been reported in literature for [EMIM][OAc] (Gericke et al. 2009). The mean values of viscosity were used to plot it as a function of temperature in Figure 5.4a. As expected, each IL displays a decreasing of viscosity with temperature increase. [mDBN][DMP] has slightly higher viscosity than that of [EMIM][OAc] at all temperatures studied. Viscosity-temperature dependence was analyzed using Arrhenius approach (Figure 5.4b):

$$\ln \eta = \ln \eta_0 + \frac{E_{a,\eta}}{RT} \quad (5)$$

where E_a is the activation energy which reflects the energy needed for a fluid to flow, R is the universal gas constant, and η_0 is an adjustable parameter. The activation energy is usually deduced from the slope of $\ln(\eta)$ versus inverse temperature if this dependence is linear within the experimental errors. For both ionic liquids $\ln(\eta)$ vs inverse temperature is slightly concave, as already reported previously for [EMIM][OAc] (Sescousse et al. 2010), however, the activation energy can be determined with $R_2 > 0.99$. E_a for [mDBN][DMP] is practically the same as for [EMIM][OAc], 37.1 kJ/mol vs 36.8 kJ/mol, respectively. For [EMIM][OAc] the value obtained correlate well with what was published previously, around 40 kJ/mol (Gericke et al. 2009).

Figure 5.4. (a) Newtonian viscosity of ILs as a function of temperature (the error bar is within the symbols). (b) Arrhenius plot of the Newtonian viscosity as a function of inverse temperature for [EMIM][OAc] and [mDBN][DMP].

In general, for the same solvent quality (or power) and at the same temperature, lower viscosity should accelerate the dissolution rate because of a quicker solvent diffusion. On the one hand, the addition of water to [EMIM][OAc] is known to decrease ionic liquid viscosity (Hall et al. 2012), but on the other hand, water is cellulose anti-solvent. In order to take both solvent characteristics into account, we measured the viscosity of [EMIM][OAc] with various water content of 0–15 wt.% as a function of shear rate at different temperatures (Figure S2 in **Paper I**). All studied mixtures are Newtonian liquids. Their viscosity is plotted as a function of water content at 25, 30 and 40 °C; in particular, it was found that [EMIM][OAc] at 40 °C and [EMIM][OAc]-5 wt.% water at 30 °C have the same viscosity (Figure 3 in **Paper I**). It was interesting to check which input, solvent quality or viscosity, is more important in controlling the dissolution rate. These two solvents were used as an example of solvents with the same viscosity but different dissolution power (Figure 5.3) in the kinetics study.

5.3 Kinetics of various cellulose fibers swelling and dissolution

5.3.1 Solvent: [EMIM][OAc] and [EMIM][OAc]-water mixtures

Benefitting from the development of optical microscopy with various set-ups (temperature control, video capture, and image analysis), the cellulose fibers' evolution during swelling and dissolution in a solvent can be followed and precisely visualized. As described in **Section 3.4** and revealed in Figure 3.6, five different modes of dissolution and swelling mechanisms were suggested in terms of solvent power. However, the studies of the kinetics of fiber dissolution are very scarce and no report is available comparing the kinetics of dissolution and/or swelling of different fibers, natural and man-made, under the same conditions. Moreover, there is no doubt that various factors have to be taken into account to understand fiber swelling and dissolution behavior: their composition, properties of primary and secondary layers in natural fibers or properties of a skin in man-made fibers, accessibility, porosity, and, potentially, cellulose crystallinity and molecular weight. Besides, in the view of making all-cellulose composites, the dissolution and/or swelling processes is of special importance and have to be well understood and controlled. Thus, the first question, as stated in **Chapter 2** of this thesis, is as follows: *What is the effect of fiber structure and solvent power on the dissolution and swelling kinetics of natural and man-made cellulose fiber?*

To address this question, **Paper I** compared both the dissolution and swelling kinetics of flax and various man-made fibers (Cordenka, Ioncell-FL and Ioncell-F) with different characteristics (see **Section 5.1**) in solvent power tuned [EMIM][OAc] by adding water (See **Section 5.2**).

Figure 5.5 schematically presents the evolution of structurally different cellulose fibers in [EMIM][OAc], [EMIM][OAc]-5% water and [EMIM][OAc]-15% water together with the corresponding plots of the normalized diameter of these fibers as a function of time at 30 °C. The optical microscopy images can be found in **Paper I** (see Figures 4, 7 and 10). At high solvent power ([EMIM][OAc]), all fibers dissolve and the dissolution rate is controlled mainly by the fiber accessibility. Here the dissolution rate was calculated, in the first approximation, as a slope to each set of experimental data approximated by a linear dependence. The dissolution rate of cellulose fibers in neat [EMIM][OAc] follows the order Ioncell-F > Ioncell-FL > flax > Cordenka, the same trend at other temperatures (25 °C, 40 °C, 50 °C and 60 °C) can be found in **Paper I** (see Figure 5). This can be explained by the physico-chemical characteristics of fibers, see Table 5.1 in **Section 5.1**. Cordenka has the lowest dissolution rate as it has the lowest accessibility as determined by DVS. The second lowest dissolution rate shows flax, mainly due to its hierarchical morphology together with high molecular weight cellulose. Ioncell-F has a higher dissolution rate as compared to that of Ioncell-FL. We speculate that slower dissolution of Ioncell-FL is due to the presence of lignin (Table 5.1) which is known to slow down cellulose dissolution (Isogai and Atalla 1998, Shi et al. 2014). It was also shown that there is a log-log direct correlation between solvent viscosity and dissolution rate of each fiber (see Figure 6 in **Paper I**).

Figure 5.5. Schematic illustration of the evolution of structurally different cellulose fibers in solvent power tuned IL ([EMIM][OAc], [EMIM][OAc]-5% water, [EMIM][OAc]-15% water) with corresponding plots of the normalized diameter of these fibers as a function of time at 30 °C (adapted with permissions from Chen et al. 2020, **Paper I**).

With the decrease of solvent power, the nature of fibers, man-made versus natural, becomes the main factor controlling their behavior. Flax, which has a hierarchical structure with strong secondary layer, turned out to be the most “sensitive” to the presence of water. Despite that [EMIM][OAc]-5 wt.% water was expected to dissolve cellulose, flax was only swelling. MMCFs show the same dissolution rate order as in neat [EMIM][OAc]: Ioncell-F > Ioncell-FL > Cordenka. All fibers had a similar water content at ambient conditions, with flax having the least, thus ruling out that the “intrinsic” water could be the reason of its insolubility in [EMIM][OAc]-5 wt.% water. It should be reminded here that the dissolution experiments were performed in static conditions, without mixing. Finally, in the presence of 15 wt.% water in ionic liquid, all fibers showed only swelling.

It is remarkable that both the kinetics of dissolution (the cases of all fibers in neat [EMIM][OAc] and all man-made fibers in [EMIM][OAc]-5 wt.% water) and of swelling (the cases of all fibers in [EMIM][OAc]-15 wt.% water) show the same order: Ioncell-F > Ioncell-FL > flax > Cordenka (Figure 5.5). Rising temperature was found to amplify both the dissolution and swelling phenomena but did not change the observed trend. In addition, the fibers’ behavior in two solvent systems with the same viscosity was compared: [EMIM][OAc]-5 wt.% water at 30 °C and neat [EMIM][OAc] at 40 °C. Except for flax which is not dissolving in [EMIM][OAc]-5 wt.% water, the dissolution rate of man-made fibers decreased in the presence of water as compared to the neat ionic liquid (see Figure 8 in **Paper I**). This indicates that the dissolution kinetics of fibers is governed by the solvent power rather than viscosity of the solvent system.

5.3.2 Solvent: [mDBN][DMP] and [mDBN][DMP]-water mixtures

Although no significant difference was found between IL [EMIM][OAc] and [mDBN][DMP] in terms of viscosity, cellulose fibers showed different and particular evolution in [mDBN][DMP], which was the case especially for flax. Interestingly, flax with hierarchical cell-wall structure (see the description in **Section 3.2.2**) was first radially dissolving from fiber surface (Stage I) and then homogenously swelling with a core-shell structure (Stage II), see example for 40 °C in Figure 5.6a. The corresponding evolution of the normalized diameter as a function of time is presented in Figure 5.6b. It was further confirmed that the swollen core-shell structure was sustained even at high temperature of 95 °C for 3 h (Figure 5.6c). We believe that the differences in the composition and structure of each layer inside a flax fiber can be used to interpret this anomalous two-step dissolving-swelling phenomenon: the outer layers (P and S1 layers) (containing less ordered cellulose and hemicelluloses) were dissolving in [mDBN][DMP] (Stage I), while the inner layer (cellulose with high crystallinity and high M_w) were only swelling due to the limited dissolution power of [mDBN][DMP] (Stage II). The same two-step dissolving-swelling phenomenon was also found for flax in [mDBN][DMP]-5% water.

Figure 5.6. (a) Optical microscope images of flax fiber evolution: dissolution (Stage I) first, and then swelling (Stage II) in [mDBN][DBN] at 40 °C. (b) Corresponding normalized diameter of flax fiber dissolving and swelling in [mDBN][DBN] as a function of time at 40 °C. (c) An optical microscope image under polarized light indicates a swollen core-shell structure in [mDBN][DBN] at 95 °C for 3 h.

5.4 Unidirectional flax-based ACCs: Selective dissolution vs Selective swelling

As mentioned earlier, one of the major directions of this thesis is to use different dissolution/swelling strategies, inspired by the kinetics study, to design high-performance ACCs. The following results will demonstrate how to make the best use of the fundamentals to produce unidirectional flax-based ACCs via conventional selective dissolution method (**Paper II**), and also selective swelling strategy. To the best of our knowledge, the latter has never been addressed by the researchers so far in terms of constructing a better interface between the matrix and the reinforcement in the ACCs.

5.4.1 Selective dissolution strategy

When converting natural fibers into ACCs and given their inherent hierarchical layered structure, the expected strategy, as illustrated in Figure 5.7a, is to selectively dissolve the mechanically weaker outer layers and transform them into the matrix phase while maintaining the undissolved fiber “core”. In particular, the mechanically strong inner layers should be kept intact to reinforce ACC. In the case of flax used in this thesis, the outer layers (primary and S1 layers) represents roughly about 10% of the total thickness of the elementary fiber (Charlet et al. 2007), see also Figure 3.3 in **Section 3.2.2**. The results on the kinetics of flax dissolution in [EMIM][OAc] (see Section 5.3.1, Figure 5a in **Paper I** and Figure 4 in **Paper II**) suggest using [EMIM][OAc] at room temperature as it allows a better control of dissolution. At high temperatures the dissolution of flax fiber is too quick and may involve the destruction of the fiber inner layers. Although the outer layers of a flax elementary fiber alone can be dissolved within about 20 min at room temperature, when impregnating many fibers closely aligned to prepare ACCs, slower dissolution is expected. Solvent diffusion decreases rapidly as more and more cellulose dissolves, and there is no convection-promoting mass transfer. Therefore, to find out the optimized processing conditions to obtain flax-based ACCs with the best possible mechanical properties, the impregnation times selected at room temperature were 15, 30, 45 and 60 min (see detailed fabrication process in **Section 4.2.1**). The corresponding ACCs were coded SD15, SD30, SD45 and SD60.

Figure 5.7. (a) Schematic representation of the formation of interfaces between the inner (undissolved) part of cellulose fibers and dissolved matrix during the impregnation stage for the manufacturing of ACCs via selective dissolution strategy (SD). (b) Tensile strength and Young's modulus of the as-prepared flax-based ACCs as a function of impregnation time (adapted from **Paper II**). (c) Cross-section images of flax-based ACCs as a function of impregnation time, scale bar is 100 μm . (d) Specific strength and specific modulus of flax-based ACCs as a function of impregnation time (adapted from **Paper II**).

The mean values of the tensile strength and Young's modulus of the prepared ACCs in the fiber direction as a function of impregnation time are presented in Figure 5.7b, the corresponding values together with the other characteristics (Density, CRI, Cell-II volume fraction and strain at break) are given in Table 5.2. Both tensile strength and Young's modulus increase with increasing impregnation time and reach a maximum at 45 min with a tensile strength of 151.3 MPa and a Young's modulus of 10.1 GPa. Thereafter, the mechanical properties drop. Density also increases with impregnation time and reaches a plateau at 45 min (Table 5.2, Figure 7c in **Paper II**). The density increase is due to the dissolved cellulose "filling" the voids between fibers; the SEM images can be found in Figure 5 of **Paper II** and Figure 5.7c. Furthermore, the specific mechanical properties (specific strength and specific modulus) were calculated, they are shown in Table 5.2 and in Figure 5.7d as a function of impregnation time. Both do not vary significantly, being within the experimental errors, for 15–45 min impregnation, but decrease at 60 min.

Table 5.2. Characteristics of unidirectional flax-based ACCs using solvent [EMIM][OAc] and [mDBN][DMP]-5% water. “SD” corresponds to selective dissolution and “SW” to selective swelling strategies, respectively; the mechanical characteristics are in fiber direction.

Solvent	[EMIM][OAc]				[mDBN][DMP]-5% water
ACC code	SD15	SD30	SD45	SD60	SW30
Density (g/cm ³)	0.69 ± 0.01	0.76 ± 0.02	0.81 ± 0.01	0.82 ± 0.03	0.97 ± 0.07
CRI (%)	44.6	44.9	43.9	39.9	37.4
Cell-II (vol.%)	0.05	0	20	28	0.2
Tensile strength (MPa)	121.1 ± 7.9	134.9 ± 9.9	151.3 ± 9.5	117.9 ± 7	213.5 ± 0.7
Young’s modulus (GPa)	8.5 ± 0.1	8.8 ± 0.4	10.1 ± 0.4	8.4 ± 0.4	9.9 ± 0.6
Strain (%)	3.0 ± 0.5	2.5 ± 0.3	2.7 ± 0.2	2.2 ± 0.1	4.8 ± 0.2
Work of fracture (MJ/m ³)	2.2 ± 0.5	1.9 ± 0.4	2.3 ± 0.4	1.5 ± 0.1	6.4 ± 0.4
Specific strength (MPa/g/cm ³)	176.2	177.5	186.4	144.4	219.7
Specific modulus (GPa/g/cm ³)	12.3	11.6	12.4	10.3	10.2

It is worth discussing the influence of the impregnation time on the evolution of CRI and Cell-II volume fraction (Table 5.2), since this may provide a direct evidence of well-controlled selective dissolution of the outer layer of flax fiber. The initial flax fibers contained cellulose I with a crystallinity of around 45%. After short impregnation times (15 min and 30 min), the crystallinity remains nearly constant at about 45%, and the Cell-II volume fraction is still around zero (within the accuracy of the method). This is because only pectin, hemicelluloses and low molecular weight and amorphous cellulose in the outer layer are initially dissolved and converted into the matrix, which has little effect on the CRI. However, ACCs produced by 45 and 60 min of impregnation clearly show a Cell-II polymorph and the Cell-II volume fraction is 20% and 28% for 45- and 60-min impregnation, respectively. Impregnation for 60 min decreased the crystallinity to around 40%.

The combination of the results of tensile testing with the results of the X-ray analysis reveals that tensile properties of the ACCs depend on two counteracting effects. On the one hand, sufficient amounts of cellulose need to be dissolved and converted into a continuous matrix to act as cellulosic “adhesive” and “fill” the voids. The increase in the mechanical properties is governed by the increase in composite density. On the other hand, the overall crystallinity has to be preserved as much as possible, and only minimum amounts of crystalline cellulose I domains should be converted to cellulose II or amorphous cellulose. The decrease in crystallinity with the increased Cell-II volume is the reason for the decrease in the mechanical properties at 60 min of impregnation, as the densities after 45- and 60-min impregnation times are the same. Thus, optimum mechanical properties are reached through intermediate impregnation times that

promote the dissolution of cellulose in the outer layer of the flax fiber but not in the inner S2 layer.

The mechanical properties of the prepared ACCs in the transverse direction are much weaker than in longitudinal direction, as expected, and also as early reported in the work from Nishino et al. 2004. For example, the maximal tensile strength was only around 2 MPa for ACCs SD45 (see Figure S3 in **Paper II**). Further improvement of the interfacial strength can be achieved by “remodeling” the interface utilizing the anomalous 2-step dissolution-swelling phenomenon, as presented in **Section 5.3.2**. This approach will be called “selective swelling (SW) strategy” and discussed in the next section.

5.4.2 Selective swelling strategy

The swelling strategy is shown in Figure 5.8a. It consists of using the swollen layer as an “additional” interface between non-swollen core and dissolved matrix. We hypothesise that the presence of the swollen layer brings two advantages in terms of the improvement of ACC mechanical properties. The first one is that in addition to hydrogen bonds formed between the dissolved and non-dissolved cellulose as shown in Figure 5.7a, the dissolved chains penetrate into the swollen part thus enhancing the adhesion between the matrix and the fiber. The second is that swollen parts help filling the “gaps” between the aligned fibers. With the addition of water during the washing-out of the solvent, the swollen layers are strongly shrinking “pulling” together both dissolved and non-dissolved parts.

Using selective swelling strategy, ACC were made utilizing the 2-step dissolving-swelling phenomenon as shown in **Section 5.3.2**. The solvent used for the ACCs fabrication was [mDBN][DMP]-5% water rather than neat [mDBN][DMP], since the presence of 5% water not only decreases the solvent viscosity which enables better solvent diffusion at room temperature, but also slows down the dissolution and swelling kinetics that makes the manufacturing process better controlled.

The SEM surface and cross section morphology of ACC SW30 fabricated using selective swelling strategy with 30 min impregnation of aligned flax fibers with [mDBN][DMP]-5% water (see detail in **Section 4.2.2**) is shown in Figure 5.8 b and c, respectively. ACC SW30 shows a dense structure with compact cross section, which was further supported by a significantly increased density value of 0.97 g.cm⁻³ as compared to 0.81 g.cm⁻³ for the best performing ACC SD45 obtained via selective dissolution strategy using [EMIM][OAc] as solvent (see Table 5.2). This confirms the above-mentioned hypothesis of “better filled” spaces between flax fibers due to the additional swollen layer during ACC fabrication. As revealed in **Section 5.4.1**, a mere dissolution of the outer layer of flax had insignificant effect on the final CRI value of ACC made via selective dissolution, with only slight decrease of the CRI (see table 5.2). However, ACC SW30 shows a relatively decreased CRI (37.7%) as compared to 44.6% for the initial flax, with practically no cellulose II (0.2 vol.%). This may be an indication that swelling (Stage II) irreversibly destroys the cellulose crystalline structure, thus resulting in the decrease of the CRI value.

Figure 5.8. (a) Schematic presentation of ACC adopting selective swelling strategy using [mDBN][DMP]-5% water as solvent. Surface (b) and cross section (c) morphology observed by SEM of ACC SW30. Representative stress-strain curves of SW30 and the best ACC SD45 using [EMIM][OAc] as presented in the previous section in fiber direction (d) and in the transverse direction (e).

The stress-strain curves of ACC SW30 in the longitudinal and transverse direction are compared with those of ACC SD45 (see Figure 5.8 d and e), and the corresponding mechanical characteristics are presented in Table 5.2. In fiber direction (Figure 5.8d), ACC SW30 shows an almost similar Young's modulus as ACC SD45 (9.9 vs 10.1 GPa, respectively) with increased tensile strength (up to 214 MPa vs 151 MPa) and strain at break (up to 5% vs 2.7%) and thus a much higher toughness (6.4 MJ/m³ vs 2.3 MJ/m³). More precisely, comparing with ACC SD45, the tensile strength, strain at break and toughness for ACC SW30 increased up to 30%, 200% and 300%, respectively. The increase of specific strength of ACC SW30 as compared with that of ACC is not only due to increased density but also because of enhanced interfacial strength that enables better stress transfer. A lower specific modulus of ACC SW30 is a result of lower CRI. Most importantly, in transverse direction (Figure 5.8e), selective swelling strategy also shows a dramatically improved mechanical strength, from around 2 MPa for ACC SD45 to around 12 MPa for ACC SW30, evidencing the improved interfacial strength.

In summary, benefiting from the understanding of cellulose fiber swelling and dissolution kinetics, unidirectional flax-based ACCs were designed. Table 5.3

compared the best values obtained with the mechanical properties of polymer composites reinforced with flax fibers. While the Young's moduli of ACCs are lower than those of flax-epoxy composites, the maximal tensile strength in longitudinal direction is much higher than that in flax-polymer composites. ACCs route provides a promising way of making fully bio-based materials with excellent mechanical properties. Selective swelling approach helps improving ACC mechanical performance in transverse direction. In addition, it is worth mentioning that the IL used for making ACC may contain water which is an advantage in terms of simplifying the recycling. In general, contrary to spinning fibers where a complete dissolution is needed, which is very sensitive to the presence of water.

Table 5.3. Comparison of the mechanical properties of unidirectional flax reinforced polymer composites and the best value of flax-based ACCs obtained in this thesis.

Matrix	Flax content	Longitudinal strength (MPa)	Young's modulus (GPa)	Transverse strength (MPa)	Ref.
Starch	60 wt.%	78	9.3	-	Romhány et al. 2003
PLA	30 wt.%	54	6.3	-	Bax and Müssig 2008
Epoxy	40 vol.%	133	28	4.5	Van et al. 2003
Epoxy	37 wt.%	132	15	-	Oksman K 2001
PP	30 wt.%	113	6.1	15.1	Miao and Shan 2011
	All flax-based ACCs	151.3	10.1	~ 2	Paper II , SD45
	All flax-based ACCs	213.5	9.9	~ 12	This thesis , SW30

5.5 Isotropic macroscale paper-based ACCs: Exploring DIC analysis of mechanical properties

In addition to unidirectional (or anisotropic) flax-based ACCs as discussed in the previous section, isotropic ACCs made from filter paper adopting selective dissolution strategy (see detailed manufacturing process in **Section 4.2.3**) were also investigated in this thesis. There were two goals for this investigation: i) to advance the understanding in processing-properties correlations in isotropic ACCs and ii) to explore Digital Image Correlation (DIC) for the analysis of ACC mechanical properties. The following results will discuss the evolution of the basic characteristics (density, morphology, crystallinity and optical properties) of the paper-based ACCs as a function of dissolution time and interpret the mechanical properties applying DIC analysis (**Paper III**).

5.5.1 Evolution of the main characteristics of paper-based ACCs as a function of impregnation time

Table 5.4 lists the main characteristics of the as prepared paper-based ACCs at various impregnation times, [EMIM][OAc] was used as cellulose solvent. As expected, density increases with the impregnation time indicating strong decrease

in material porosity, from 73% for filter paper to 11% for P60. No noticeable evolution is recorded after 30 min of dissolution. The XRD profiles, which probed the crystalline phase evolution of these ACCs, can be found in Figure 4, **Paper III**. A small diffraction peak at $2\theta \approx 12^\circ$, which indicates cellulose II allomorph, was observed for the initial filter paper. It has been reported that a paper sheet, despite supposed to be native cellulose, may contain a small amount of cellulose II crystalline structure (Sirviö et al. 2017, Piltonen et al. 2016). The amount of cellulose II strongly increases after 5 min impregnation, from around 7 vol.% for the initial filter paper to around 34 vol.%, but then does not vary significantly (Table 5.4). Crystallinity drops from around 56% for the initial filter paper to 43% for first 5 min impregnation and then slowly decreases to around 40% for longer impregnation times. These results indicate that the dissolution was stopped after the first 5 minutes. The reason is that cellulose concentration was too high (>40 wt.%), above the dissolution limit in ionic liquid. It was demonstrated that at least 3 ionic liquid molecules per anhydroglucose unit are needed to dissolve cellulose in [EMIM][OAc] which is translated into maximum cellulose solubility of around 25-27 wt.% (Le KA et al. 2014). It should also be taken into account that the viscosity of the dissolved phase is very high at high cellulose concentration, and dissolution (impregnation) was performed in static conditions, without mixing, also preventing cellulose dissolution.

Table 5.4. Density, porosity, CRI and corresponding Cell-II volume fraction of filter paper and paper-based ACCs.

ACC code	Impregnation time min	Density g/cm ³	Porosity %	CRI %	Cell-II vol.%
Filter paper	0	0.40 ± 0.03	73 ± 1.7	55.9	7.7
P5	5	0.85 ± 0.02	42 ± 1.6	43.2	33.9
P10	10	0.90 ± 0.03	39 ± 2.2	42	29.8
P30	30	1.32 ± 0.01	10 ± 0.3	40.7	36.9
P60	60	1.31 ± 0.03	10.9 ± 0.3	40.5	34.1

Figure 5.9 presents the surface and cross-section morphologies of the initial paper and obtained ACCs. The starting material shows individual fibers typical for a filter paper with large number of voids, as confirmed by low density. After 5 min of impregnation, fibers can still be distinguished but they are well embedded into the dissolved cellulose matrix demonstrating excellent adhesion (Figure 5.9a). The cross-section shows some remaining pores (Figure 5.9b). After 10 min and longer impregnation times the fibrous structure of the paper had almost disappeared, and no pores can be seen. The SEM cross-section images also reveal the decrease of ACCs cross-section dimension (thickness of ACCs). Those observations are in-line with density and XRD results: cellulose that could be dissolved was dissolved during the first 5 minutes (strong increase of cellulose II fraction and drop of crystallinity) and further morphology evolution is due to the distribution of dissolved phase within the pores under pressure (no evolution of cellulose II fraction and crystallinity but continuous increase in density).

Figure 5.9. (a) The surface of filter paper and paper-based ACCs. (b) The corresponding cross-section of filter paper and ACCs. (c) Optical transmittance of filter paper and the ACCs. (d) Optical haze of filter paper and the ACCs. (e) ACC P60 in close contact with the colored letters underneath to show its high light transmittance. (f) ACC P60 1 cm away from the same substrate to indicate its high haze (Adapeted from **Paper III**).

The optical properties are correlated with the morphology of the ACCs. Figure 5.9 (c and d) displays the optical transmittance and haze of the filter paper and the as-prepared ACCs. As the filter paper consists of randomly packed irregular cellulose fibers and micron-size voids, it is opaque in the visible light. In ACCs, the dissolved cellulose fills the voids with the matter of the same refractive index as fibers, surface roughness is decreased, and the material becomes transparent in the visible light (Figure 5.9c). More homogeneous morphology also decreases the forward light scattering resulting in the reduction of haze (Figure 5.9d). Both transmittance and haze show a sharp transition of properties at impregnation times longer than 5 min, in-line with ACC morphology (Figure 5.9a) and density (Table 5.4). It is worth noting that ACCs P60 is transparent (optical transmittance ~ 80% at 550 nm) but still with high haze (> 70% at 550 nm), which makes it promising as photonic material for optoelectronic applications such as solar cells, as haze increases light scattering and absorption. The digital photos of ACC P60 (Figure 5.9 e and f) confirm high transmittance and high haze.

5.5.2 Mechanical properties

Two types of analysis tensile properties of ACCs based on filter paper were performed: comparison of stress-strain data obtained i) from machine sensors and from DIC analysis and ii) nominal and true values obtained from DIC. In case of using DIC, the true and nominal stress-strain curves were obtained over the surface S (see **Section 4.3.2**). An example of strain distributions over the sample surface obtained from DIC for tensile loading is shown for ACC P5 (see Figure 7 in **Paper III**); the strain field is heterogeneous with strain concentration on the upper side and failure is initiated in this area. This type of analysis was performed for all other samples.

First, the nominal and true stress-strain curves obtained from DIC over the surface S (see details of the construction of different stress-strain curves in **Paper III**) are compared (Figure 5.10a). The true stress is slightly higher than the nominal one with slightly lower strain at failure. The similarity between true and nominal stress-strain curves can be explained by the low level of ACC deformation. For material exhibiting large deformation, more differences can be observed between nominal and true strain-stress curves (Faridmehr et al. 2014). Then, the nominal stress-strain curve directly derived from the machine and that derived from DIC over the surface S are compared (Figure 5.10b). Interestingly, the difference is significant: the strain at failure determined directly from machine is twice higher than that determined from DIC. With tensile strength being almost the same, Young's modulus calculated from DIC is much higher than that calculated directly from machine. The latter provides results with the systematic error arising from the stiffness of the tensile machine.

Figure 5.10. (a) Comparison of nominal and true stress-strain curves obtained from DIC over the surface S for ACC P5 as example. (b) Comparison of nominal stress-strain curves obtained from the machine and from DIC over the surface S, ACC P5 as example. (c) Young's modulus of initial filter paper and as-prepared ACCs as a function of density. (d) Tensile strength of initial filter paper and as-prepared ACCs as a function of density. (e) Strain at maximal stress of initial filter paper and as-prepared ACCs as a function of density. (f) Work of fracture of initial filter paper and as-prepared ACCs as a function of density (adapted from **Paper III**).

As already addressed in **Section 3.6**, almost all the literature concerning ACCs report nominal stress-strain curves no matter the approach used. Therefore, nominal stress-strain curves (see Figure S1 in **Paper III**) and corresponding nominal mechanical characteristics (Young's modulus, tensile strength, strain and toughness) for all samples from machine and DIC are compared. All mechanical characteristics of the filter paper and ACCs can be found in Table S1 in **Paper III**, their dependence on the impregnation time is shown in Figure S2 in **Paper III** and on density in Figure 5.10 c-f. The increase in ACC density, which corresponds to the increase of impregnation time, leads to a strong increase of Young's modulus whatever is the way of its determination (Figure 5.10 c). All values calculated from nominal stress-strain curves from DIC are much higher than those calculated from nominal ones from machine, as expected from Figure 5.10b. DIC approach, which is a non-contact method, provide more accurate results than those obtained from machine.

It has been demonstrated in **Section 5.4** and the previous study that density plays the essential role in the mechanical performance of ACCs (Korhonen et al. 2019). Hence, an adequate comparison with literature can be made only for the materials either of the same density or for the specific values of mechanical characteristics. Unfortunately, the density of ACC is not always reported. Given that moduli values can be calculated from machine or from non-contact extensometer, the comparison with the results obtained in literature becomes even more delicate. In addition to Young's modulus, tensile strength and toughness increase as well with density increase. Interestingly, strain at break also increases, from 4 to 9%, the latter corresponding to ACC of density around 0.9 g/cm^3 (impregnation time 10 min); at higher density strain at break remains on the same level.

Figure 5.10 b-f show that while Young's modulus calculated from nominal stress-strain curves from DIC is higher than that calculated from machine, the opposite was obtained for the strain at maximal stress and toughness. A lower toughness obtained from DIC is due to a much lower nominal strains at maximal stress as compared to those obtained via machine. Tensile strength values did not depend on the approach used within the errors.

Overall, a simple strategy of filter paper impregnation with ionic liquid for 30-60 min allowed increasing tensile strength in almost 10 times, of Young's modulus in 5 times and of toughness in 25 times as compared to the initial filter paper.

5.6 Isotropic cellulose nanopaper: toward large ductility combining high strength and toughness

As addressed in **Section 3.5.2** in relation to ACCs fabrication via H-bonds aided self-binding, cellulose nanopaper featuring high mechanical strength and optical transparency have received considerable attention over past ten years. Most studies on nanopaper target high mechanical strength, which usually compromises ductility and toughness. Making cellulose nanopaper ductile combining high strength and toughness remains still unexplored. Recent investigations reveal that the fracture of cellulose nanopaper under tension involves alignment of CNFs parallel to the tension direction and interfibrillar slippage with a cascade of breaking and reforming H-bonds (Henriksson et al. 2008, Zhu et al. 2015). This leads to the dissipation of a significant amount of energy and contributes to inelastic deformation. In the case of anisotropic nanopaper, low strain and toughness is due to too strong H-bonding between highly ordered nanofibrils, whereas for isotropic nanopaper, an increased strain is due to randomly packed CNFs enabling interfibrillar slippage and inelastic deformation. As demonstrated for polymer materials (Fava et al. 2006), this is an indication that cellulose nanopaper with highly disordered and long CNFs may be prone to an effective slippage, significantly contributing to inelastic deformation and causing the stored energy to be released.

In this regard, we developed a strategy for the design of highly ductile cellulose nanopaper that combines high strength and toughness by disordering mechanically fibrillated wood CNFs utilizing solvent power tuneable IL ([EMIM][OAc]). More precisely, we used swelling of the hemicelluloses which remains in-between the elementary fibrils in IL-water to disintegrate CNF bundles. First, the properties of CNF-water and CNF-IL-water suspensions are presented. Then nanopaper was prepared and its optical and mechanical properties are analysed.

5.6.1 Swelling induced delamination of CNF (bundles)

First, it was confirmed that the IL concentration in the IL-water mixture is below the dissolution limit of cellulose and hemicellulose. The concentration of IL was varied from 5 wt.% to 50 wt.% and of CNF from 0.34 wt.% to 0.15 wt.% correspondingly (Table 4.1). The analysis of the composition of the CNF (after mechanical disintegration) before and after the treatment with IL showed that hemicelluloses indeed remained in the system after washing out the IL (see Table S1 in the Supporting information, **Paper IV**). Cellulose was not dissolved either since there was no change in the type of cellulose crystalline phase, and the degree of crystallinity remained constant within the experimental errors (see Figure S2 and Table S1 in the Supporting Information, **Paper IV**). The 50% IL-water mixture was used only as a limiting case to demonstrate that no hemicellulose and cellulose was dissolved even at this high IL concentration; no nanopaper was produced using this IL-water mixture.

The successful delamination of CNF bundles after adding IL in CNF-water suspension was monitored by cryo-TEM (Figure 5.11a). To decrease the inherent wood CNF polydispersity and better visualize the influence of the treatment

with IL, only large bundles were selected for cryo-TEM imaging by successive centrifugation (see details given in Figure S3 in the Supporting Information, **Paper IV**). The suspension of the as-prepared fractionated large bundles was then diluted either with IL–water to CNF–15% IL–water or with water to match the same CNF concentration. CNF dispersed in water (Figure 5.11b) contains mainly bundles of fibrils with diameters up to hundreds of nanometers, as also shown by AFM for the initial 0.4% CNF–water suspension (Figure S1 in the Supporting Information, **Paper IV**). In the presence of 15 wt.% IL, CNF bundles are separated into thinner ones (Figure 5.11c), and even an entangled nano-network of individual elementary nanofibrils can be observed (Figure 5.11d).

Figure 5.11. (a) Schematic presentation of the hemicellulose swelling induced delamination of CNF bundles in the presence of IL. (b) Cryo-TEM imaging of the fractionated CNF of large diameter dispersed in water. (c) and (d) Cryo-TEM imaging of the same fractionated CNF but dispersed in 15%IL-water. (e) Elastic (G' , filled symbols) and viscous (G'' , open symbols) moduli of 0.28% CNF–water (black squares) and of 0.28% CNF–15% IL–water suspensions (red circles). (f) Relative viscosity of the same suspensions. (g) Elastic moduli of CNF–water and CNF–IL–water suspensions as a function of CNF concentration at $\omega = 7.2$ rad/s (Images b–g are adapted from **Paper IV**).

Driven by the observation of this nano-network, the viscoelastic properties of CNF–IL–water suspensions were probed by dynamic rheology. Figure 5.11e shows an example of the frequency dependence of elastic (G') and viscous (G'') moduli of 0.28% CNF dispersed in 15% IL–water and in water; examples for other CNF concentrations can be found in Figure S5 in the Supporting Information of **Paper IV**. All suspensions show gel-like behavior, with G' being one

order of magnitude higher than the corresponding G'' , which is typical for CNF suspensions (Li et al. 2015, Geng et al. 2018). There is a significant difference between IL–water-based and pure aqueous suspensions: the moduli of 0.28%CNF–15%IL–W suspension are more than 300 times higher than their corresponding values without ionic liquid. In addition, the frequency-independent region of G' and G'' of 0.28% CNF–15% IL–W suspension is much wider than that of 0.28% CNF–water, which is also an indication of a stronger network. Similar results were recorded for all prepared CNF suspensions of other concentrations (Figure S5 in the Supporting Information, **Paper IV**). At high frequencies, CNF–water suspension undergoes a partial phase separation, reflected by both moduli increase with a frequency increase (Charani et al. 2013), which is much less pronounced in the case of the CNF–IL–water suspension. Figure 5.11f demonstrates that the relative viscosity of 0.28% CNF–15%–IL is 200 times higher than that of the 0.28% CNF–water suspension.

Moreover, as depicted in Figure 5.11g, in both dispersing media (water and IL – water), G' shows a power-law dependence on the CNF concentration with the exponent α being equal to 2.7:

$$G' = KC^\alpha \quad (6)$$

where α is a parameter related to network structure (Naderi et al. 2014) and K is a constant proportional to the fiber elastic modulus E_0 and the square of fiber aspect ratio (Tatsumi et al. 2002, MacKintosh et al. 1995). The constant K of CNF–water suspensions is in the same range as that reported previously for CNF dispersed in water, from few tens to a thousand (Tatsumi et al. 2002, Naderi et al. 2014). K of the CNF-IL-water suspension is more than 300 times higher than that of their pure aqueous counterparts. The pronounced difference in K value is attributed to the delamination of CNF bundles, leading to a decrease in the bundle's diameter while keeping its length: as a consequence, the aspect ratio increases. We suppose that the Young's modulus of the network “building block fiber” is also increased as the modulus of an elementary CNF fibril should logically be higher than that of a bundle of nanofibrils assembled together.

In the view of the results obtained we hypothesise that hemicelluloses that are present in-between the elementary nanofibrils is swelling in IL-water leading to CNF delamination into thinner ones. Thinner dispersed entities are more flexible and form a highly entangled elastic network (Figures 5.11c and d).

5.6.2 Performance of nanopaper from CNF-IL-water suspension

The CNF suspensions were then converted into isotropic nanopaper via filtration, washing with water to remove the IL, further filtration, and drying (see details in **Section 4.2.4**). First, it is worth mentioning that a shrinkage occurred during drying, resulting in the decrease of the dimensions in the longitudinal direction and increase in nanopaper thickness (see Figure S8 in the Supporting Information, **Paper IV**). We hypothesize that the long and flexible nanofibrils adopt an “accordion” like structure during drying, thus potentially causing the pronounced high elongation under tension, because of the gradual

unfolding of the nanofibrils. The density of nanopaper decreases from 1.26 g/cm³ to 0.99 g/cm³ as the IL concentration in the initial dispersing medium increases from 0 to 15%, respectively. Further increase in the IL concentration does not affect the nanopaper density within experimental errors (see Table S3 in the Supporting Information, **Paper IV**). As a consequence, the nanopaper porosity strongly increases from ~13% to 32% for the dispersing medium with 0–15% IL and then remains ~30% for 30% IL (see Table S3 in the Supporting Information, **Paper IV**).

Both reference nanopaper CNF and CNF15 (Figure 5.12a) are highly transparent with no visual difference, and the optical transmittance at a wavelength of 550 nm is 86.7% and 86.2%, respectively (Figure 5.12b); similar transmittance was recorded for the other nanopapers (see Table S3 in the Supporting Information, **Paper IV**). The haze is increased from 44.9% (reference nanopaper CNF) to 47.5% (nanopaper CNF15) at a wavelength of 550 nm (Figure 5.12b). The increased haze might derive from the porosity of IL-treated CNF due to folded nanofibrils. As mentioned in **Section 5.5.1**, a high haze is a positive effect in applications such as solar cells, as haze increases light scattering and absorption.

Figure 5.12. (a) Digital image of nanopaper CNF15 from CNF-15%IL-water suspension. (b) Optical transmittance and haze of reference nanopaper CNF and CNF15. (c) Representative stress–strain curves for reference nanopaper CNF and CNF15. (d) Comparison of the mechanical characteristics of reference nanopaper CNF (black bars) and CNF15 (red bars). (e) and (f) SEM images of the fractured reference nanopaper CNF and CNF15, respectively (b, c, d, e and f are adapted from **Paper IV**).

The stress–strain curves for the reference nanopaper CNF and CNF15 are shown in Figure 5.12c, three tests per formulation are given as an example, to demonstrate reproducibility. CNF15 exhibits an extraordinary combination of large ductility (up to 35%) and high tensile strength (up to 260 MPa). To the best of our knowledge, such a high elongation at break coupled with high strength have never been reported previously for non-modified CNF nanopapers. The mean values of elongation and tensile strength of nanopaper CNF15 are much higher than their corresponding values of the reference nanopaper CNF (Figure 5.12d). The Young's modulus of CNF15 shows a 30% decrease compared to that of the reference nanopaper. The properties of other nanopapers, CNF5 and CNF30, can be found in Table S3 (Supporting information, **Paper IV**), all showing high ductility and tensile strength with a Young's modulus similar to that of CNF15. Interestingly, the large increase in the ductility of nanopaper CNF15 does not compromise its tensile strength. As a result, the toughness, expressed as a work of fracture, is 38.1 ± 13.1 MJ/m³ for CNF15, which is a very high value for unmodified nanocellulose-based materials (Zhu et al. 2017, Henriksson et al. 2008, Zhu et al. 2015, Lossada et al. 2018, Reyes et al. 2018). To the best of our knowledge, only one cellulose-based nanopaper (Benítez and Walther 2017b), with incorporated tetrahexyl ammonium ions (THA⁺) had a comparable high toughness (38 MJ/m³), strain at break (21%), and tensile strength (272 MPa).

The morphology of the fractured surfaces after tensile failure of nanopaper CNF15 and of reference nanopaper CNF is compared in Figures 5.12e and f, respectively. The laminated nature of the reference nanopaper CNF is typical for cellulose nanopaper and is attributed to the flocculation of nanofibrils at a high concentration during filtration (Henriksson et al. 2008, Sehaqui et al. 2011) confirming a brittle fracture without any fibril pullouts. The fractured surface of nanopaper CNF15 is extremely bumpy, with many microvoids and pullouts of the mesoscale layers (Figure 12f), similar to ductile modified nanopapers and their polymer composites (Benítez and Walther 2017b, Benítez et al. 2016). This brittle-to-ductile transition is a significant sign of excellent energy dissipation.

Based on above results, several factors should be considered to interpret the mechanical properties of the obtained nanopapers after pre-treatment with ionic liquid. Under tension, CNF itself does not show plasticity (Henriksson et al. 2008, Tang et al. 2015, Ansari and Berglund 2016). Interfibril and intrafibril H-bonds are breaking and reforming during fibrils slippage, with the latter being “helped” by the presence of hemicelluloses, which may act as a “lubricant”. The fact that CNF are highly disordered also contributed to the decrease in interfibrillar bonding and, thus, to the efficient sliding. This ease of interfibrillar sliding of entangled CNF allows reaching high elongation at break without losing tensile strength. The increased porosity of nanopapers is also important: pores act as energy dissipators under applied tension. Both factors, slippage and porosity, lead to high ductility and strength but a lower modulus. Shrinkage under drying may play an important role as well. If nanofibrils are folding under drying, they unfold under tension and align in the stress direction, leading to strain hardening. A slight increase of the slope of the tensile curves (Figure 12c) may be an indication of the strain hardening stage. A similar phenomenon was

also observed for nanopaper in previous studies (Toivonen et al. 2015, Benítez and Walther 2017b) and indicates an enhanced interfibrillar bonding under tension, confirming the alignment of nanofibrils under deformation.

In summary, hemicellulose containing CNFs have been proven to be separated into thinner fibrils by hemicellulose swelling in the presence of low-concentrated IL-water, which is a physical process without dissolution of both cellulose and hemicellulose. Understanding and control of the structure formation is crucial in the design of materials with desired mechanical properties.

6. Conclusions and Perspectives

This thesis explores various possibilities to design high performance all-cellulose composites, with a purpose of bringing new perspectives to this field. This was done by first acquiring a fundamental understanding of the dissolution and swelling kinetics of cellulose fibers in ionic liquids, and investigating how the dissolution and swelling kinetics of natural and man-made cellulose fibers are affected by the fiber structure and solvent power (Research question 1). Then unidirectional macroscopic natural fiber flax-based ACCs were designed and the optimal ACCs fabricating conditions were determined utilizing the obtained fundamental knowledge on the dissolution and swelling of flax fibers (Research question 2). Besides unidirectional ACCs, isotropic ACCs based on filter paper were also produced; their mechanical properties were assessed by a digital image correlation analysis technique to improve the accuracy of the determination of the material mechanical properties (Research question 3). In addition to ACCs produced by adopting the conventional selective dissolution strategy, ACCs fabricated via self-binding from nanoscopic cellulose fibers were explored. The obtained isotropic nanopaper was ductile while combining high strength and toughness (Research question 4). The main findings of this thesis and the research perspectives will be presented below.

6.1 Main findings of this thesis

6.1.1 Swelling and dissolution of cellulose fibers

The behavior of flax and man-made fibers (Cordenka, Ioncell-FL and Ioncell-F) in ionic liquid and its mixtures with water was investigated. The rate of fibers' dissolution in neat [EMIM][OAc] (high solvent power) depends on their accessibility and solvent viscosity. The water-induced decreased solvent power dominates the general fiber behavior despite the decrease in solvent viscosity. Flax appeared to be the most "sensitive" to the solvent power due to its hierarchical structure, since even a moderate amount of water (5 wt.%) in the [EMIM][OAc] results in fiber homogeneous swelling with a core-shell structure while all man-made fibers were still dissolving under this condition. Further increase of water content (15 wt.%) induces radial swelling of all fibers with no dissolution. Both the fastest dissolution and swelling was recorded for Ioncell and the slowest for Cordenka and attributed to the fiber morphology. (**Paper I**)

An anomalous two-step dissolution-swelling of flax fiber was observed in another IL, [mDBN][DMP], which was also confirmed in [mDBN][DMP] containing 5% water (**unpublished results**). Besides the known strategy for ACCs design via mere “selective dissolution”, this finding promoted a new idea of ACCs design targeting the enhancement of the interfacial strength by “remodeling” the interface.

6.1.2 Unidirectional flax-based ACCs via selective dissolution and selective swelling

Unidirectional ACCs based on oriented flax fibers were prepared via controlled impregnation with [EMIM][OAc] at room temperature, as suggested by the described above fundamental study on fibers swelling and dissolution. The performance of the ACCs depends on a compromise between the formation of the matrix that fuses fibers together and fills the voids, resulting in an increased density on the one hand, and the non-dissolution of the inner strong cell walls and the minimization of the formation of lower crystallinity and mechanically weaker cellulose II on the other hand. The best values were obtained for the ACC with 45 min impregnation (a mean value for maximal tensile strength of 151.3 MPa and a Young's modulus of 10.1 GPa). (**Paper II**)

The fundamental understanding of the evolution of flax in cellulose solvent performed in this study allowed finding a suitable strategy for making high-performance ACCs and making full use of the excellent mechanical properties of the flax itself. However, the mechanical properties in transverse direction of this ACC was found to be very weak (maximal tensile strength around 2MPa). This was improved by utilizing the observed anomalous two-step dissolution-swelling phenomenon of flax in [mDBN][DMP], thus artfully remodelling the interface between the matrix and the undissolved reinforcement. As a result, in addition to the increased maximal tensile strength in the transverse direction (up to 6 times increase, around 12 MPa), the tensile strength in the fiber direction was also increased to 214 MPa with an increased strain at break due to a better stress transfer (**unpublished results**).

Overall, the tensile properties of the produced unidirectional flax-based ACCs are better than those for many polymer composites reinforced with flax fibers, providing a promising way of making fully bio-based materials with excellent mechanical properties.

6.1.3 Isotropic macroscopic paper-based ACCs

Digital Image Correlation aided tensile testing was conducted on isotropic ACCs made from filter paper via controlled impregnation with ionic liquid [EMIM][OAc]. Tensile testing was performed using different methods to obtain the specimen elongation: i) data directly taken from machine sensors and ii) using digital image correlation technique. The latter excludes the errors related to the stiffness of the tensile testing machine itself. True and nominal stress-strain curves were also built and compared. Although the nominal tensile strength values from DIC and machine are similar, the nominal Young's

modulus from DIC appears to be much higher with a lower nominal strain and toughness value. It was also found that the DIC derived nominal stress–strain curve and the corresponding true stress-strain curve are quite similar. In addition, it can be concluded that ACCs fabrication strategy with only 30–60 min impregnation using ionic liquid allows increasing tensile strength, Young’s modulus and toughness of a filter paper in almost 10 times, 5 times and 25 times, respectively. The as prepared paper-based ACCs with tuneable optical properties combining overall good mechanical properties are promising for high-end applications such as substrates for flexible displays, optics and solar cells. **(Paper III)**.

6.1.4 Isotropic cellulose nanopaper

Instead of targeting a super strong cellulose nanopaper from highly ordered CNFs, which inevitably compromises ductility and toughness, nanopaper constructed by highly disordered and entangled CNFs through self-binding was also explored in this thesis. The approach was based on the swelling of hemicelluloses in-between the nanofibrils in [EMIM][OAc]–water mixtures at a low IL concentration, below the dissolution limit of cellulose and hemicellulose. It allows delamination of thick CNF bundles into thinner ones without influencing the length of the fibrils. This approach resulted in a strong nanonetwork of entangled fibrils on the one hand, and efficient interfibrillar slippage and energy dissipation in the final nanopaper on the other hand. It was suggested that porosity which was created because of the folding of nanofibrils during drying and unfolding under tension also plays an important role in the mechanical properties of nanopaper. The combination of high ductility (up to 35%), strength (up to 260 MPa), transparency (86%), and toughness (up to 51 MJ/m³) allows the potential use of cellulose nanopaper as sustainable and biodegradable support for various applications, for example, in flexible electronics. **(Paper IV)**

6.2 Research perspectives

Although this thesis was mainly focused on the design and characterization of various ACCs, the starting fundamental study itself on fibers swelling and dissolution is an interesting topic, in which there are still a lot of important aspects to be understood. For example, as demonstrated in this thesis, there may be a direct correlation between the processes of cellulose dissolution and swelling: the same solvent system can act either as a swelling agent or as a dissolution agent depending on the properties of the fiber and dissolution conditions. However, how the two processes are correlated is an open question. Therefore, a deeper understanding of swelling of cellulose fibers is necessary, in particular, the properties of cellulose in the swollen “shell”, as cellulose transformation upon swelling is still not very clear. Additionally, the observed anomalous two-step dissolution-swelling behavior can be further investigated by studying other kinds of natural fibers or using other cellulose solvents. We believe all these investigations may contribute to a new insight into the mechanism of cellulose dissolution and swelling, in turn further promoting versatile ACCs design.

In terms of the production of ACCs in this thesis, the design and characterization of the composites were focusing mainly on their mechanical performance as structural materials. In fact, cellulose nanopaper and the obtained macroscale filter paper-based ACCs as well are promising to be used for high-end applications such as functional filtration membranes, optics, flexible devices and solar cells, considering their optical properties with overall excellent mechanical performance. The research on these topics started to be published but still there is a lot to do. For example, benefiting from the solvent-aided ACCs strategy that enables cellulose surface and interface engineering, various structures incorporating other building blocks or nanoparticles can be built for above desired applications.

The application of IL for hemicellulose swelling induced mild fibrillation of CNF is one of the key findings in this work, which allows fabrication a ductile nanopaper combining high strength and toughness. It is necessary to investigate the CNF-IL-water suspensions in more detail and thus to elucidate the role of hemicellulose and IL in the formation of the nano-network. It will be also interesting to test if the use of other cellulose solvents below their dissolution limit could lead to a similar result. Benefiting from the highly disordered and entangled CNF in the CNF-IL-water suspension, the production of cellulose macroscale fiber or hydro-/aero-/cryogels other than nanopaper presented in the thesis can be further designed targeting excellent but specific performance.

The ACCs strategy via selective dissolution and via selective swelling as demonstrated in this thesis opens up several application pathways for all cellulose based materials. Thus, further investigating the possibilities of producing ACCs from recycled cellulose sources such as waste textiles, newspaper and cardboard, will be of significance and bring interesting outcomes.

References

- Abu-Rous M, Varga K, Bechtold T, Schuster KC (2007) A new method to visualize and characterize the pore structure of TENCEL®(Lyocell) and other man-made cellulosic fibres using a fluorescent dye molecular probe. *J Appl Polym* 106:2083-91.
- Abushammala H, Mao J (2020) A Review on the Partial and Complete Dissolution and Fractionation of Wood and Lignocelluloses Using Imidazolium Ionic Liquids. *Polymers* 12:195.
- Adak B, Mukhopadhyay S (2016) Effect of pressure on structure and properties of lyocell fabric-based all-cellulose composite laminates. *J Text Inst* 108:1010-1017.
- Adak B, Mukhopadhyay S (2017) A comparative study on lyocell-fabric based all-cellulose composite laminates produced by different processes. *Cellulose* 24:835-49.
- Adak B, Mukhopadhyay S (2018) All-cellulose composite laminates with low moisture and water sensitivity. *Polymer* 141:79-85.
- Ansari F, Berglund LA (2016) Tensile Properties of Wood Cellulose Nanopaper and Nanocomposite Films. In *Multifunctional Polymeric Nanocomposites Based on Cellulosic Reinforcements*; David, J., Ed.; William Andrew Publishing: Oxford, UK pp:115- 130.
- Arévalo R, Peijs T (2016) Binderless all-cellulose fibreboard from microfibrillated lignocellulosic natural fibres. *Compos Part A-Appl Sci Manuf* 83:38-46.
- Atalla R, Vanderhart D (1984) Native cellulose: a composite of two distinct crystalline forms. *Science* 223:283-285.
- Aulin C, Johansson E, Wågberg L, Lindström T (2010) Self-organized films from cellulose I nanofibrils using the layer-by-layer technique. *Biomacromolecules* 11:872-82.
- Baghaei B, Skrifvars M (2020) All-Cellulose Composites: A Review of Recent Studies on Structure, Properties and Applications. *Molecules* 25:2836.
- Bandera D, Sapkota J, Josset S, Weder C, Tingaut P, Gao X, Foster EJ, Zimmermann T (2014) Influence of mechanical treatments on the properties of cellulose nanofibers isolated from microcrystalline cellulose. *React Funct Polym* 85:134-141.
- Bapan A, Samrat M (2016) Jute based all-cellulose composite laminates. *Indian J Fibre Text* 41:380-384.
- Baghaei B, Skrifvars M (2020) All-Cellulose Composites: A Review of Recent Studies on Structure, Properties and Applications. *Molecules* 25:2836.
- Bax B, Müssig J (2008) Impact and tensile properties of PLA/Cordenka and PLA/flax composites. *Compos Sci Technol* 68:1601-1607.
- Benítez AJ, Torres-Rendon J, Poutanen M, Walther A (2013) Humidity and multiscale structure govern mechanical properties and deformation modes in films of native cellulose nanofibrils. *Biomacromolecules* 14:4497-506.
- Benítez AJ, Walther A (2017a) Cellulose nanofibril nanopapers and bioinspired nanocomposites: a review to understand the mechanical property space. *J Mater Chem A* 5:16003-24.

- Benítez AJ, Walther A (2017b) Counterion size and nature control structural and mechanical response in cellulose nanofibril nanopapers. *Biomacromolecules* 18:1642-53.
- Biganska, O (2002) Etude physico-chimique des solutions de cellulose dans la N-methylmorpholine-N-oxyde. Doctoral Thesis, L'Ecole Nationale des Mines de Paris.
- Bledzki AK, Gassan J (1999) Composites reinforced with cellulose based fibres. *Prog Polym Sci* 24:221-74.
- Bolton AJ (1994) Natural fibers for plastic reinforcement. *Mater Technol* 9:12-20.
- Brandt A, Gräsvik J, Hallett JP, Welton T (2013) Deconstruction of lignocellulosic biomass with ionic liquids. *Green Chem* 15:550-583.
- Brown Jr, RM, Saxena, IM (2000) Cellulose biosynthesis: a model for understanding the assembly of biopolymers. *Plant Physiol Biochem* 38:57-67.
- Bywater N (2011) The global viscose fibre industry in the 21st century – the first 10 years. *Lenzinger Ber* 89:22-29.
- Candau N, Pradille C, Bouvard JL, Billon N (2016) On the use of a four-cameras stereo-vision system to characterize large 3D deformation in elastomers. *Polym Test* 56:314-20.
- Capiati NJ, Porter RS. (1975) The concept of one polymer composites modelled with high density polyethylene. *J Mater Sci* 10:1671-1677.
- Chang WY, Fang TH, Lin YC (2008) Physical characteristics of polyimide films for flexible sensors. *Appl Phys A Mater Sci Process* 92:693.
- Charani PR, Dehghani-Firouzabadi M, Afra E, Shakeri A (2013) Rheological characterization of high concentrated MFC gel from kenaf unbleached pulp. *Cellulose* 20:727-40.
- Charlet K, Baley C, Morvan C, Jernot JP, Gomina M, Bréard J (2007) Characteristics of Hermès flax fibres as a function of their location in the stem and properties of the derived unidirectional composites. *Compos Part A-Appl Sci Manuf* 38:1912-21.
- Chaudemanche C, Navard P (2011) Swelling and dissolution mechanisms of regenerated Lyocell cellulose fibers. *Cellulose* 18(1):1-5.
- Chen K, Xu W, Ding Y, Xue P, Sheng P, Qiao H, He J (2020) Hemp-based all-cellulose composites through ionic liquid promoted controllable dissolution and structural control. *Carbohydr Polym* 235:116027.
- Chen Y, Geng B, Ru J, Tong C, Liu H, Chen J (2017) Comparative characteristics of TEMPO-oxidized cellulose nanofibers and resulting nanopapers from bamboo, softwood, and hardwood pulps. *Cellulose* 24:4831-44.
- Chen F, Sawada D, Hummel M, Sixta H, Budtova T (2020) Swelling and dissolution kinetics of natural and man-made cellulose fibers in solvent power tuned ionic liquid. *Cellulose* 27:7399-415.
- Cheng SZ (Ed.) (2008) Phase transitions in polymers: the role of metastable states. Elsevier.
- Chirayil CJ, Mathew L, Thomas S (2014) Review of recent research in nano cellulose preparation from different lignocellulosic fibers. *Rev Adv Mater Sci* 37:20-28.
- Couling DJ, Bernot RJ, Docherty KM, Dixon JK, Maginn EJ (2006) Assessing the factors responsible for ionic liquid toxicity to aquatic organisms via quantitative structure–property relationship modeling. *Green Chem* 8:82-90.
- Courtney EJ (inventor) (1953) Method of making a cuprammonium cellulose solution. US patent 2,651,582.
- Cuissinat C, Navard P (2006a) Swelling and dissolution of cellulose part 1: Free floating cotton and wood Fibres in N-methylmorpholine-N-oxide-water mixtures. *Macromol Symp* 244: 1-18.

- Cuissinat C, Navard P (2006b) Swelling and dissolution of cellulose part II: Free floating cotton and wood fibres in NaOH-water-additives systems. *Macromol Symp* 244: 19-30.
- Cuissinat C, Navard P (2008) Swelling and dissolution of cellulose, Part III: plant fibres in aqueous systems. *Cellulose* 15(1):67-74.
- Cuissinat C, Navard P, Heinze T (2008) Swelling and dissolution of cellulose. Part IV: Free floating cotton and wood fibres in ionic liquids. *Carbohydr Polym* 72(4):590-6.
- Deblois S and Wiegel J (1990) Hemicellulases in lignocellulose degradation, in *Microbial and Plant Opportunities to Improve Lignocellulose Utilization by Ruminants*, Elsevier, New York, NY, pp. 275-287.
- Duchemin BJ, Mathew AP, Oksman K (2009) All-cellulose composites by partial dissolution in the ionic liquid 1-butyl-3-methylimidazolium chloride. *Compos Part A-Appl Sci Manuf* 40:2031-7.
- Dupont J, de Souza RF, Suarez PA (2002) Ionic liquid (molten salt) phase organometallic catalysis. *Chem Rev* 102:3667-92.
- Egusa S, Kitaoka T, Goto M, Wariishi H (2007) Synthesis of cellulose in vitro by using a cellulase/surfactant complex in a nonaqueous medium. *Angew Chem Int Ed Engl* 46:2063-5.
- Endo T, Hosomi S, Fujii S, Ninomiya K, Takahashi K (2016) Anion bridging-induced structural transformation of cellulose dissolved in ionic liquid. *J Phys Chem Lett* 7:5156-61.
- Fang Z, Zhu H, Preston C, Han X, Li Y, Lee S, Chai X, Chen G, Hu L (2013) Highly transparent and writable wood all-cellulose hybrid nanostructured paper. *J Mater Chem C* 1:6191-7.
- Fang Z, Zhu H, Yuan Y, Ha D, Zhu S, Preston C, Chen Q, Li Y, Han X, Lee S, Chen G (2014) Novel nanostructured paper with ultrahigh transparency and ultrahigh haze for solar cells. *Nano Lett* 14:765-73.
- Faridmehr I, Osman MH, Adnan AB, Nejad AF, Hodjati R, Azimi M (2014) Correlation between engineering stress-strain and true stress-strain curve. *Am J Civ Eng Archit* 2(1):53-9.
- Fava D, Fan YS, Kumacheva E, Winnik MA, Shinozaki DM (2006) Order versus disorder: Effect of structure on the mechanical properties of polymer material. *Macromolecules* 39:1665-9.
- Felling AJ, Doman DA (2018) A New Video Extensometer System for Testing Materials Undergoing Severe Plastic Deformation. *J Eng Mater Technol* 140.
- Fink HP, Hofmann D, Philipp B (1995) Some aspects of lateral chain order in cellulose from X-ray scattering. *Cellulose* 2:51-70.
- Fink HP, Weigel P, Ganster J, et al (2004) Evaluation of new organosolv dissolving pulps. Part II: Structure and NMMO processability of the pulps. *Cellulose* 11:85-98.
- Fink HP, Weigel P, Purz HJ, Ganster J (2001) Structure formation of regenerated cellulose materials from NMMO-solutions. *Prog Polym Sci* 26:1473-1524.
- French AD (2017) Glucose, not cellobiose, is the repeating unit of cellulose and why that is important. *Cellulose* 24:4605-9.
- Fukaya Y, Sugimoto, A, Ohno, H (2006) Superior solubility of polysaccharides in low viscosity, polar, and halogen-free 1,3-dialkylimidazolium formates. *Biomacromolecules* 12:3295-3297.
- Fukuzumi H, Saito T, Iwata T, Kumamoto Y, Isogai A (2009) Transparent and high gas barrier films of cellulose nanofibers prepared by TEMPO-mediated oxidation. *Biomacromolecules* 10:162-5.

- Gao C, Yu L, Liu H, Chen L (2012) Development of self-reinforced polymer composites. *Prog in Polym Sci* 37:767-80.
- García A, Gandini A, Labidi J, Belgacem N, Bras J (2016) Industrial and crop wastes: A new source for nanocellulose biorefinery. *Ind Crops Prod* 93:26-38.
- Geng L, Mittal N, Zhan C, Ansari F, Sharma PR, Peng X, Hsiao BS, Söderberg LD (2018) Understanding the mechanistic behavior of highly charged cellulose nanofibers in aqueous systems. *Macromolecules* 51:1498-506.
- Gericke M, Schlutter K, Liebert T, Heinze T, Budtova T (2009) Rheological properties of cellulose/ionic liquid solutions: from dilute to concentrated states. *Biomacromolecules* 10:1188-94.
- Giesa T, Buehler MJ (2013) Nanoconfinement and the strength of biopolymers. *Annu Rev Biophys* 42:651-73.
- Gindl AW, Keckes J, Plackner J, Liebner F, Englund K, Laborie MP (2012) All-cellulose composites prepared from flax and lyocell fibres compared to epoxy-matrix composites. *Compos Sci Technol* 72:1304-1309.
- Glas D, Paesen R, Depuydt D, Binnemans K, Ameloot M, De Vos DE, Ameloot R (2015) Cellulose amorphization by swelling in ionic liquid/water mixtures: a combined macroscopic and second-harmonic microscopy study. *ChemSusChem* 8(1):82-6.
- Gross AS, Chu JW (2010) On the molecular origins of biomass recalcitrance: the interaction network and solvation structures of cellulose microfibrils. *J Phys Chem B* 114:13333-41.
- G'Sell C, Hiver JM, Dahoun A, Souahi A (1992) Video-controlled tensile testing of polymers and metals beyond the necking point. *J Mater Sci* 27:5031-9.
- Gübitz GM, Stebbing DW, Johansson CI, Saddler JN (1998) Lignin-hemicellulose complexes restrict enzymatic solubilization of mannan and xylan from dissolving pulp. *Appl Microbiol Biotechnol* 50:390-395.
- Guo J, Uddin KM, Mihhels K, Fang W, Laaksonen P, Zhu JY, Rojas OJ (2017) Contribution of residual proteins to the thermomechanical performance of Cellulosic Nanofibrils isolated from green macroalgae. *ACS Sustain Chem Eng* 5:6978-85.
- Gupta KM, Jiang J (2015) Cellulose dissolution and regeneration in ionic liquids: A computational perspective. *Chem Eng Sci* 121:180-189.
- Hall CA, Le KA, Rudaz C, Radhi A, Lovell CS, Damion RA, Budtova T, Ries ME (2012) Macroscopic and microscopic study of 1-ethyl-3-methyl-imidazolium acetate-water mixtures. *J Phys Chem B* 116:12810-12818
- Haslinger S, Wang Y, Rissanen M, Lossa MB, Tantt M, Ilen E, Määttänen M, Harlin A, Hummel M, Sixta H (2019) Recycling of vat and reactive dyed textile waste to new colored man-made cellulose fibers. *Green Chem* 21:5598-610.
- Hauru LK, Hummel M, King AW, Kilpelainen I, Sixta H (2012) Role of solvent parameters in the regeneration of cellulose from ionic liquid solutions. *Biomacromolecules* 13:2896-905.
- Haverhals LM, Reichert WM, De Long HC, Trulove PC (2010) Natural Fiber Welding. *Macromol Mater Eng* 295:425-430.
- He X, Xiao Q, Lu C, Wang Y, Zhang X, Zhao J, Zhang W, Zhang X, Deng Y (2014) Uniaxially aligned electrospun all-cellulose nanocomposite nanofibers reinforced with cellulose nanocrystals: scaffold for tissue engineering. *Biomacromolecules* 15:618-27.
- Hearle JW (1958) A fringed fibril theory of structure in crystalline polymers. *J Polym Sci* 28:432-5.
- Henriksson, M, Henriksson, G, Berglund, LA, Lindström, T (2007) An environmentally friendly method for enzyme-assisted preparation of microfibrillated cellulose (MFC) nanofibers. *Eur Polym J* 43:3434-3441.

- Henriksson M, Berglund LA, Isaksson P, Lindstrom T, Nishino T (2008) Cellulose nanopaper structures of high toughness. *Biomacromolecules* 9:1579-85.
- Henrissat and Davies (1997) Structural and sequence-based classification of glycoside hydrolases. *Curr Opin Struc Biol* 7:637-44.
- Hervy M, Santmarti A, Lahtinen P, Tammelin T, Lee KY (2017) Sample geometry dependency on the measured tensile properties of cellulose nanopapers. *Mater Design* 121:421-9.
- Ho TTT, Abe K, Zimmermann T, Yano H (2015) Nanofibrillation of pulp fibers by twin-screw extrusion. *Cellulose* 22:421-433.
- Hock, CW (1954) In *Cellulose and cellulose derivatives (Part 1): IV Structure and Properties of Cellulose Fibres, C Microscopic Structure*; Emil Ott, H. M. S., Grafflin, M. W., Eds.; Interscience: New York.
- Hu C, Zhao Y, Li K, Zhu J, Gleisner R (2015) Optimizing cellulose fibrillation for the production of cellulose nanofibrils by a disk grinder. *Holzforschung* 69:993-1000.
- Hua S, Chen F, Liu ZY, Yang W, Yang MB (2016) Preparation of cellulose-graft-poly(lactic acid) via melt copolycondensation for use in polylactic acid based composites: Synthesis, characterization and properties. *RSC Adv* 6:1973-83.
- Huber T, Müssig J, Curnow O, Pang S, Bickerton S, Staiger MP (2012a) A critical review of all-cellulose composites. *J Mater Sci* 47:1171-86.
- Huber T, Bickerton S, Müssig J, Pang S, Staiger MP (2012b) Solvent infusion processing of all-cellulose composite materials. *Carbohydr Polym* 90:730-733.
- Huber T, Pang S, Staiger MP (2012c) All-cellulose composite laminates. *Compos Part A- Appl Sci Manuf* 43:1738-1745.
- Iguchi M, Yamanaka S, Budhiono A (2000) Bacterial cellulose—a masterpiece of nature's arts. *J Mater Sci* 35:261-70.
- Isik M, Sardon H, Mecerreyes D (2014) Ionic liquids and cellulose: Dissolution, chemical modification and preparation of new cellulosic materials. *Int J Mol Sci* 15:11922-11940.
- Isogai A, Atalla RH (1998) Dissolution of cellulose in aqueous NaOH solutions. *Cellulose* 5:309-319.
- Isogai A, Saito T, Fukuzumi H (2011) TEMPO-oxidized cellulose nanofibers. *Nanoscale* 3:71-85.
- Jacob M, Joseph S, Pothan LA, Thomas S (2005) A study of advances in characterization of interfaces and fiber surfaces in lignocellulosic fiber-reinforced composites. *Compos Interfaces* 12:95-124.
- Janson J (1970) Calculation of the polysaccharide composition of wood and pulp. *Pap Puu Pap Tim* 52:323-329.
- Jiang F, Kondo T, Hsieh YL (2016) Rice straw cellulose nanofibrils via aqueous counter collision and differential centrifugation and their self-assembled structures. *ACS Sustain Chem Eng* 4:1697-706.
- Jonoobi M, Mathew AP, Oksman K (2014) Natural Resources and Residues for Production of Bionanomaterials. In *HANDBOOK OF GREEN MATERIALS: 1 Bionanomaterials: separation processes, characterization and properties*, pp. 19-33.
- Josset S, Orsolini P, Siqueira G, Tejado A, Tingaut P, Zimmermann T (2014) Energy consumption of the nanofibrillation of bleached pulp, wheat straw and recycled newspaper through a grinding process. *Nord Pulp Pap Res J* 29:167-175.
- Junka K, Guo J, Filpponen I, Laine J, Rojas OJ (2014) Modification of cellulose nanofibrils with luminescent carbon dots. *Biomacromolecules* 15:876-881.
- Kalpakjian S, Schmid SR (2009) *Manufacturing Engineering and Technology*, International edition. 4th Ed. Prentice Hall, Inc.

- Kanari N, Pineau JL, Shallari S (2003). End-of-Life Vehicle Recycling in the European Union. *Jom* 55:15-9.
- Kang X, Sun P, Kuga S, Wang C, Zhao Y, Wu M, Huang Y (2017) Thin cellulose nanofiber from corncob cellulose and its performance in transparent nanopaper. *ACS Sustain Chem Eng* 5:2529-34.
- Khakalo A, Tanaka A, Korpela A, Hauru LKJ, Orelma H (2019) All-Wood Composite Material by Partial Fiber Surface Dissolution with an Ionic Liquid. *ACS Sustain Chem Eng* 7:3195-3202.
- Khalil HA, Davoudpour Y, Islam MN, Mustapha A, Sudesh K, Dungani R, Jawaid M (2014) Production and modification of nanofibrillated cellulose using various mechanical processes: a review. *Carbohydr Polym* 99:649-665.
- Kim NH, Imai T, Wada M, Sugiyama J (2006) Molecular directionality in cellulose polymorphs. *Biomacromolecules* 7:274-80.
- Klemm D, Heublein B, Fink HP, Bohn A (2005) Cellulose: fascinating biopolymer and sustainable raw material. *Angew Chem Int Ed Engl* 44:3358-93.
- Klemm D, Kramer F, Moritz S, Lindström T, Ankerfors M, Gray D, Dorris A (2011) Nanocelluloses: A new family of nature-based materials. *Angew Chem Int Ed Engl* 50:5438-5466.
- Klemm D, Philipp B, Heinze T, Heinze U, Wagenknecht W (1998) Comprehensive cellulose chemistry. Volume 1: Fundamentals and analytical methods. Wiley-VCH Verlag GmbH.
- Korhonen O, Sawada D, Budtova T (2019) All-cellulose composites via short-fiber dispersion approach using NaOH–water solvent. *Cellulose* 26:4881-93.
- Kreze T, Malej S (2003) Structural characteristics of new and conventional regenerated cellulosic fibers. *Text Res J* 73:675-684.
- Kröling H, Duchemin B, Dormanns J, Schabel S, Staiger MP (2018) Mechanical anisotropy of paper-based all-cellulose composites. *Compos Part A-Appl Sci Manuf* 113:150-7.
- Kuzmina O, Bhardwaj J, Vincent SR, et al (2017) Superbase ionic liquids for effective cellulose processing from dissolution to carbonisation. *Green Chem* 19:5949-5957.
- Langan P, Sukumar N, Nishiyama Y, Chanzy H (2005) Synchrotron X-ray structures of cellulose I β and regenerated cellulose II at ambient temperature and 100 K. *Cellulose* 12(6):551-62.
- Lossada F, Guo J, Jiao D, Groeer S, Bourgeat-Lami E, Montarnal D, Walther A (2018) Vitrimers chemistry meets cellulose nanofibrils: bioinspired nanopapers with high water resistance and strong adhesion. *Biomacromolecules* 20:1045-55.
- Laus G, Bnetivoglio G, Schottenberger H, et al (2005) Ionic liquids: current development, potential and drawbacks for industrial applications. *Lenzinger Ber* 84:71-85.
- Le KA, Rudaz C, Budtova T (2014) Phase diagram, solubility limit and hydrodynamic properties of cellulose in binary solvents with ionic liquid. *Carbohydr Polym* 105:237-43.
- Le Moigne N, Montes E, Pannetier C, Höfte H, Navard P (2008) Gradient in dissolution capacity of successively deposited cell wall layers in cotton fibres. *Macromol Symp* 262:65-71.
- Le Moigne N, Navard P (2010) On the Specific Behaviour of Native Cellulose Fibers upon Dissolution. In *Cellulose Solvents: For Analysis, Shaping and Chemical Modification* (pp. 137-148). American Chemical Society.

- Lee KY, Aitomäki Y, Berglund LA, Oksman K, Bismarck A (2014) On the use of nanocellulose as reinforcement in polymer matrix composites. *Compos Sci Technol* 105:15-27.
- Li J, Nawaz H, Wu J, Zhang J, Wan J, Mi Q, Yu J, Zhang J (2018b) All-cellulose composites based on the self-reinforced effect. *Compos Comm* 9:42-53.
- Li MC, Wu Q, Song K, Lee S, Qing Y, Wu Y (2015) Cellulose nanoparticles: structure-morphology-rheology relationships. *ACS Sustain Chem Eng* 3:821-32.
- Li Y, Wang J, Liu X, Zhang S (2018a) Towards a molecular understanding of cellulose dissolution in ionic liquids: anion/cation effect, synergistic mechanism and physicochemical aspects. *Chem Sci* 9:4027-43.
- Liebert T (2010) Cellulose solvents-remarkable history, bright future. In *Cellulose solvents: for analysis, shaping and chemical modification* (pp. 3-54). American Chemical Society.
- Luo N, Lv Y, Wang D, Zhang J, Wu J, He J, Zhang J (2012) Direct visualization of solution morphology of cellulose in ionic liquids by conventional TEM at room temperature. *Chem Comm* 48:6283-5.
- Lu X, Hu J, Yao X, Wang Z, Li J (2006) Composite system based on chitosan and room-temperature ionic liquid: direct electrochemistry and electrocatalysis of hemoglobin. *Biomacromolecules* 7:975-80.
- Ma H, Zhou B, Li HS, Li YQ, Ou SY (2011) Green composite films composed of nanocrystalline cellulose and a cellulose matrix regenerated from functionalized ionic liquid solution. *Carbohydr Polym* 84:383-9.
- Ma Y, Asaadi S, Johansson LS, Ahvenainen P, et al (2015) High-Strength Composite Fibers from Cellulose-Lignin Blends Regenerated from Ionic Liquid Solution. *ChemSusChem* 8:4030-9.
- Ma Y, Hummel MM, Määttänen M, Särkilähti A, Harlin A, Sixta H (2016) Upcycling of waste paper and cardboard to textiles. *Green Chem* 18:858-66.
- Ma Y (2018a). Fibre spinning from various low refined, recycled lignocelluloses using ionic liquid. Doctoral thesis, Aalto University.
- Ma Y, Stubb J, Kontro I, Nieminen K, Hummel M, Sixta H (2018b) Filament spinning of unbleached birch kraft pulps: Effect of pulping intensity on the processability and the fiber properties. *Carbohydr Polym* 179:145-51.
- MacKintosh FC, Käs J, Janmey PA (1995) Elasticity of semiflexible biopolymer networks. *Phys Rev Lett* 75:4425.
- Mäkelä V, Wahlström R, Holopainen-Mantila U, Kilpeläinen I, King AW (2018) Clustered single cellulosic fiber dissolution kinetics and mechanisms through optical microscopy under limited dissolving conditions. *Biomacromolecules* 19:1635-45.
- Malcolm Jr R, Saxena IM (2007) *Cellulose: molecular and structural biology: selected articles on the synthesis, structure, and applications of cellulose*. Springer Science & Business Media.
- Mat Salleh M, Magniez K, Pang S, Dormann JW, Staiger MP (2017) Parametric optimization of the processing of all-cellulose composite laminae. *Adv Manuf Polym Compos Sci* 3(2):73-9.
- Meng Q, Wang TJ (2019) Mechanics of strong and tough cellulose nanopaper. *Appl Mech Rev* 71:040801.
- Miao M, Shan M (2011) Highly aligned flax/polypropylene nonwoven preforms for thermoplastic composites. *Compos Sci Technol* 71:1713-8.
- Michud A, Tantt M, Asaadi S, et al (2016) Ioncell-F: ionic liquid-based cellulosic textile fibers as an alternative to viscose and Lyocell. *Text Res J* 86:543-552.

- Mohanty A, Misra M, Drzal L (2002) Sustainable bio-composites from renewable resources: opportunities and challenges in the green materials world. *J of Polym Environ* 10 (1):19-26.
- Moon RJ, Martini A, Nairn J, Simonsen J, Youngblood J (2011) Cellulose nanomaterials review: structure, properties and nanocomposites. *Chem Soc Rev* 40:3941-94.
- Moryganov AP, Zavadskii AE, Stokozenko VG (2018) Special features of X-ray analysis of cellulose crystallinity and content in flax fibres. *Fibre Chem* 49:382-387.
- Mtibe A, Liganiso LZ, Mathew AP, Oksman K, John MJ, Anandjiwala RD (2015) A comparative study on properties of micro and nanopapers produced from cellulose and cellulose nanofibres. *Carbohydr Polym* 118:1-8.
- Müssig, J (Ed.) (2010) Industrial Applications of Natural Fibres: Structure. In *Properties and Technical Applications*. John Wiley & Sons, Ltd. United States of America.
- Naderi A, Lindström T, Sundström J (2014) Carboxymethylated nanofibrillated cellulose: rheological studies. *Cellulose* 21:1561-71.
- Nadhan AV, Rajulu AV, Li R, Jie C, Zhang L (2012) Properties of regenerated cellulose short fibers/cellulose green composite films. *J Polym Environ* 20:454-8.
- Nakagaito AN, Iwamoto S, Yano H (2005) Bacterial cellulose: the ultimate nano-scalar cellulose morphology for the production of high-strength composites. *Appl Phys A-Matter* 80:93-7.
- Nechyporchuk O, Belgacem MN, Bras J (2016) Production of cellulose nanofibrils: A review of recent advances. *Ind Crops Prod* 93:2-5.
- Nilsson H, Galland S, Larsson PT, Gamstedt EK, Nishino T, Berglund LA, Iversen T (2010) A non-solvent approach for high-stiffness all-cellulose biocomposites based on pure wood cellulose. *Compos Technol* 70:1704-12.
- Nishino T, Takano K, Nakamae K (1995) Elastic modulus of the crystalline regions of cellulose polymorphs. *J Polym Sci B Polym Phys* 33(11):1647-51.
- Nishino T, Matsuda I, Hirao K (2003) Cellulose self-reinforced composite. Paper presented at the ecomposites, University of London.
- Nishino T, Matsuda I, Hirao K. (2004) All-cellulose composite. *Macromolecules* 37:7683-7687.
- Nishino T, Arimoto N (2007) All-cellulose composite prepared by selective dissolving of fiber surface. *Biomacromolecules* 8:2712-6.
- Nobuta K, Teramura H, Ito H, Hongo C, Kawaguchi H, Ogino C, Kondo A, Nishino T (2016) Characterization of cellulose nanofiber sheets from different refining processes. *Cellulose* 23:403-14.
- Nogi M, Iwamoto S, Nakagaito AN, Yano H (2009) Optically transparent nanofiber paper. *Adv Mater* 21:1595-8.
- Nechyporchuk O, Belgacem MN, Bras J (2016) Production of cellulose nanofibrils: A review of recent advances. *Ind Crops Prod* 93:2-5.
- Olszewska A, Eronen P, Johansson LS, Malho JM, Ankerfors M, Lindström T, Ruokolainen J, Laine J, Österberg M (2011) The behaviour of cationic nanofibrillar cellulose in aqueous media. *Cellulose* 18:1213.
- Orr RS, DeLuca LB, Burgis AW, Grant JN (1959) Fiber Structure and Mechanical Properties of Untreated and Modified Cottons. *Text Res J* 29:144-50.
- Oksman K (2001) High quality flax fibre composites manufactured by the resin transfer moulding process. *J Reinf Plast Compos* 20:621-627.
- Oksman K, Mathew AP, Bismarck A, Rojas O, Sain M (2014) *Handbook of Green Materials: Processing Technologies, Properties and Applications*. World Scientific and Engineering Academy and Society, Singapore.

- Okubayashi S, Griesser UJ, Bechtold T (2004) A kinetic study of moisture sorption and desorption on lyocell fibers. *Carbohydr Polym* 58(3):293–299.
- Okubayashi S, Griesser UJ, Bechtold T (2005) Water accessibilities of man-made cellulosic fibers—effects of fiber characteristics. *Cellulose* 12:403–410.
- O’Sullivan AC (1997) Cellulose: the structure slowly unravels. *Cellulose* 4:173–207.
- Österberg M, Vartiainen J, Lucenius J, Hippi U, Seppälä J, Serimaa R, Laine J (2013) A fast method to produce strong NFC films as a platform for barrier and functional materials. *ACS Appl Mater Inter* 5:4640–7.
- Öztürk HB, Okubayashi S, Bechtold T (2006a) Splitting tendency of cellulosic fibers—Part 1. The effect of shear force on mechanical stability of swollen lyocell fibers. *Cellulose* 13:393–402.
- Öztürk HB, Okubayashi S, Bechtold T (2006b) Splitting tendency of cellulosic fibers. Part 2: Effects of fiber swelling in alkali solutions. *Cellulose* 13:403–9.
- Öztürk HB, Bechtold T (2008) Splitting tendency of cellulosic fibers. Part 3: splitting tendency of viscose and modal fibers. *Cellulose* 15:101–9.
- Pääkkö M, Ankerfors M, Kosonen H, Nykänen A, Ahola S, Österberg M, Ruokolainen J, Laine J, Larsson PT, Ikkala O, Lindström T (2007) Enzymatic hydrolysis combined with mechanical shearing and high-pressure homogenization for nanoscale cellulose fibrils and strong gels. *Biomacromolecules* 8:1934–41.
- Parviainen H, Parviainen A, Virtanen T, Kilpeläinen I, Ahvenainen P, Serimaa R, Grönqvist S, Maloney T, Maunu SL (2014) Dissolution enthalpies of cellulose in ionic liquids. *Carbohydr Polym* 113:67–76.
- Payen A (1838) Mémoire sur la composition du tissu propre des plantes et du ligneux. *Comptes rendus* 7:1052–1056.
- Peng H, Dai G, Wang S, Xu H (2017) The evolution behavior and dissolution mechanism of cellulose in aqueous solvent. *J Mol Liq* 241:959–966.
- Pickering K (Ed.) (2008) Properties and performance of natural-fibre composites. Elsevier.
- Piltonen P, Hildebrandt NC, Westerlind B, Valkama JP, Tervahartiala T, Illikainen M (2016) Green and efficient method for preparing all-cellulose composites with NaOH/urea solvent. *Compos Sci Technol* 135:153–8.
- Pinkert A, Marsh KN, Pang S, Staiger MP (2009) Ionic liquids and their interaction with cellulose. *Chem Rev* 109:6712–6728.
- Placet V, Trivaudey F, Cisse O, Gucheret-Retel V, Boubakar ML (2012) Diameter dependence of the apparent tensile modulus of hemp fibres: a morphological, structural or ultrastructural effect? *Compos Part A-Appl Sci Manuf* 43:275–87.
- Postek MT, Vladár A, Dagata J, Farkas N, Ming B, Wagner R, Raman A, Moon RJ, Sabo R, Wegner TH (2010) Development of the metrology and imaging of cellulose nanocrystals. *Meas Sci Technol* 22:024005.
- Puangsin B, Yang Q, Saito T, Isogai A (2013) Comparative characterization of TEMPO-oxidized cellulose nanofibril films prepared from non-wood resources. *Int J Biol Macromol* 59:208–13.
- Qing Y, Sabo R, Zhu J, Agarwal U, Cai Z, Wu Y (2013) A comparative study of cellulose nanofibrils disintegrated via multiple processing approaches. *Carbohydr Polym* 97:226–234.
- Ramakrishnan KR, Corn S, Le Moigne N, Ienny P, Slangen P (2020) Experimental assessment of low velocity impact damage in flax fabrics reinforced biocomposites by coupled high-speed imaging and DIC analysis. *Compos Part A-Appl Sci Manuf* 110:6137.

- Remsing RC, Swatloski RP, Rogers RD, Moyna G (2006) Mechanism of cellulose dissolution in the ionic liquid 1-n-butyl-3-methylimidazolium chloride: a ^{13}C and $^{35/37}\text{Cl}$ NMR relaxation study on model systems. *Chem Comm* 12:1271-3.
- Rein D M, Khalfin R, Szekely N, Cohen Y (2014) True molecular solutions of natural cellulose in the binary ionic liquid-containing solvent mixtures. *Carbohydr Polym* 112:125-133.
- Reyes G, Borghei M, King AW, Lahti J, Rojas OJ (2018) Solvent welding and imprinting cellulose nanofiber films using ionic liquids. *Biomacromolecules* 20:502-14.
- Ritchie RO (2011) The Conflicts between Strength and Toughness. *Nat Mater* 10:817-822.
- Rogers RD, Seddon KR (2003) Ionic liquids-solvents of the future? *Science* 302:792-3.
- Romhány G, Karger-Kocsis J, Czigány T (2003) Tensile fracture and failure behavior of thermoplastic starch with unidirectional and cross-ply flax fiber reinforcements. *Macromol Mater Eng* 88:699-707.
- Rous MA, Ingolic E, Schuster KC (2006) Visualisation of the fibrillar and pore morphology of cellulosic fibres applying transmission electron microscopy. *Cellulose*. 2006 13:411-9.
- Santucci BS, Bras J, Belgacem MN, da Silva Curvelo, Antonio Aprigio, Pimenta MTB (2016) Evaluation of the effects of chemical composition and refining treatments on the properties of nanofibrillated cellulose films from sugarcane bagasse. *Ind Crops Prod* 91:238-248.
- Sarkanen KV, Ludwig CH (1971) Liguins. Occurrence, formation, structure, and reactions. Wiley-Interscience, New York.
- Schuster KC, Aldred P, Villa M, Baron M, Loidl R, Biganska O, Patlazhan S, Navard P, Rüf H, Jericha E (2003) Characterising the emerging lyocell fibres structures by ultra small angle neutron scattering (USANS). *Lenzinger Berichte* 82:107-17.
- Sehaqui H, Liu A, Zhou Q, Berglund LA (2010) Fast preparation procedure for large, flat cellulose and cellulose/inorganic nanopaper structures. *Biomacromolecules* 11:2195-8.
- Sehaqui H, Zhou Q, Berglund LA (2011) Nanostructured biocomposites of high toughness—a wood cellulose nanofiber network in ductile hydroxyethylcellulose matrix. *Soft Matter* 7:7342-50.
- Sehaqui H, Zimmermann T, Tingaut P (2014) Hydrophobic cellulose nanopaper through a mild esterification procedure. *Cellulose* 21:367-82.
- Sescousse R, Le KA, Ries ME, Budtova T (2010) Viscosity of cellulose–imidazolium-based ionic liquid solutions. *J Phys Chem B*. 114:7222-8.
- Shibata M, Teramoto N, Nakamura T, Saitoh Y (2013) All-cellulose and all-wood composites by partial dissolution of cotton fabric and wood in ionic liquid. *Carbohydr. Polym* 98:1532-1539.
- Shih YH, Singco B, Liu WL, Hsu CH, Huang HY (2011) A rapid synthetic method for organic polymer-based monoliths in a room temperature ionic liquid medium via microwave-assisted vinylization and polymerization. *Green Chem* 13:296-9.
- Shi Z, Yang Q, Cai J, Kuga S, Matsumoto Y (2014) Effects of lignin and hemicellulose contents on dissolution of wood pulp in aqueous NaOH/urea solution. *Cellulose* 21:1205-1215.
- Singh G, Kumar A (2008) Ionic liquids: Physico-chemical, solvent properties and their applications in chemical processes. *Indian J Chem* 47:495-503.
- Singh P, Duarte H, Alves L, Antunes F, Moigne NL, Dormanns J, Duchemin B, Staiger MP, Medronho B (2015) From cellulose dissolution and regeneration to added value applications—Synergism between molecular understanding and material

- development. In *Cellulose: Fundamental Aspects and Current Trends*. Matheus P, Ornaghi HLJ (Eds) InTech: Rijeka, Croatia.
- Siroka B, Noisternig M, Griesser UJ, Bechtold T (2008) Characterization of cellulosic fibers and fabrics by sorption/desorption. *Carbohydr Res* 343:2194–2199.
- Sirviö JA, Visanko M, Hildebrandt NC (2017) Rapid preparation of all-cellulose composites by solvent welding based on the use of aqueous solvent. *Eur Polym J* 97:292–8.
- Sisson WA (1960) The spinning of rayon as related to its structure and properties. *Text Res J* 30:153–70.
- Sixta H (Ed.) (2006) *Handbook of Pulp* (pp. 3–19). Weinheim: WILEY-VCH Verlag GmbH & Co. KGaA.
- Sixta H, Michud A, Hauru L, Asaadi S, Ma Y, King AW, Kilpeläinen I, Hummel M (2015) Ioncell-F: a high-strength regenerated cellulose fibre. *Nord Pulp Pap Res J* 30:43–57.
- Soykeabkaew N, Arimoto N, Nishino T, Peijs T (2008) All-cellulose composites by surface selective dissolution of aligned ligno-cellulosic fibres. *Compos Sci Technol* 68:2201–7.
- Soykeabkaew N, Nishino T, Peijs T (2009) All-cellulose composites of regenerated cellulose fibres by surface selective dissolution. *Compos Part A-Appl Sci Manuf* 40:321–328.
- Spange S, Reuter A, Vilsmeier E, Heinze T, Keutel D, Linert WJ (1998) Determination of empirical polarity parameters of the cellulose solvent N, N-dimethylacetamide/LiCl by means of the solvatochromic technique. *Polym Sci Part A: Polym Chem* 36: 1945–1955.
- Spörl JM, Batti F, Vocht MP, Raab R, Müller A, Hermanutz F, Buchmeiser MR (2017) Ionic Liquid Approach Toward Manufacture and Full Recycling of All-Cellulose Composites. *Macromol Mater Eng* 303:1700335.
- Staiger MP, Tucker N (2008) In Pickering KL (ed), *Properties and performance of natural-fibre composites*, vol 1. Woodhead Publishing Limited, Cambridge, p 269.
- Strobl GR (Ed.) (2007) *The physics of polymers*. Third edition, Berlin: Springer.
- Štuncová A, Davies GR, Eichhorn SJ (2005) Elastic modulus and stress-transfer properties of tunicate cellulose whiskers. *Biomacromolecules* 6:1055–61.
- Sun CC (2008) Mechanism of Moisture Induced Variations in True Density and Compaction Properties of Microcrystalline Cellulose. *Int J Pharm* 346:93–101.
- Sun N, Rahman M, Qin Y, et al (2009) Complete dissolution and partial delignification of wood in the ionic liquid 1-ethyl-3-methylimidazolium acetate. *Green Chem* 11:646–655.
- Sutton MA, Orteu JJ, Schreier H (2009) *Image correlation for shape, motion and deformation measurements: basic concepts, theory and applications*. Springer Science & Business Media.
- Svoboda MA, Lang RW, Bramsteidl R, Ernegg M, Stadlbauer W (2000) Zelfo-an engineering material fully based on renewable resources. *Mol Cryst Liq Cryst* 353:47–58.
- Tang H, Butchosa N, Zhou Q (2015) A transparent, hazy, and strong macroscopic ribbon of oriented cellulose nanofibrils bearing poly (ethylene glycol). *Adv Mater* 27:2070–6.
- Tatsumi D, Ishioka S, Matsumoto T (2002) Effect of fiber concentration and axial ratio on the rheological properties of cellulose fiber suspensions. *J Soc Rheol Japan* 30:27–32.
- Toivonen MS, Kaskela A, Rojas OJ, Kauppinen EI, Ikkala O (2015) Ambient-dried cellulose nanofibril aerogel membranes with high tensile strength and their use for

- aerosol collection and templates for transparent, flexible devices. *Adv Funct Mater* 25:6618–26.
- Trifol J, Sillard C, Plackett D, Szabo P, Bras J, Daugaard AE (2017) Chemically extracted nanocellulose from sisal fibres by a simple and industrially relevant process. *Cellulose* 24:107–118.
- Wada M, Heux L, Sugiyama J (2004) Polymorphism of cellulose I family: Reinvestigation of cellulose IV₁. *Biomacromolecules* 5:1385–1391.
- Van de Weyenberg I, Ivens J, De Coster A, Kino B, Baetens E, Verpoest I (2003) Influence of processing and chemical treatment of flax fibres on their composites. *Compos Sci Technol* 63:1241–6.
- VanderHart DL, Atalla RH (1984) Studies of microstructure in native celluloses using solid-state carbon-13 NMR. *Macromolecules* 17:1465–72.
- Wang Y, Chen L (2011) Impacts of nanowhisker on formation kinetics and properties of all-cellulose composite gels. *Carbohydr Polym* 83:1937–46.
- Wang Q, Zhu J, Gleisner R, Kuster T, Baxa U, McNeil S (2012a) Morphological development of cellulose fibrils of a bleached eucalyptus pulp by mechanical fibrillation. *Cellulose* 19:1631–1643.
- Wang H, Gurau G, Rogers RD (2012b) Ionic liquid processing of cellulose. *Chem Soc Rev* 41:1519.
- Wang S, Lu A, Zhang L (2016) Recent advances in regenerated cellulose materials. *Prog Polym Sci* 53:169–206.
- Wang S, Li T, Chen C, Kong W, Zhu S, Dai J, Diaz AJ, Hitz E, Solares SD, Li T, Hu L (2018a) Transparent, anisotropic biofilm with aligned bacterial cellulose nanofibers. *Adv Funct Mater* 28(24):1707491.
- Wang Q, Du H, Zhang F, Zhang Y, Wu M, Yu G, Liu C, Li B, Peng H (2018b) Flexible cellulose nanopaper with high wet tensile strength, high toughness and tunable ultraviolet blocking ability fabricated from tobacco stalk via a sustainable method. *J Mater Chem A* 6:13021–30.
- Wei GT, Yang Z, Chen CJ (2003) Room temperature ionic liquid as a novel medium for liquid/liquid extraction of metal ions. *Anal Chim Acta* 488:183–92.
- Wei QY, Lin H, Yang B, Li L, Zhang LQ, Huang HD, Zhong GJ, Xu L, Li ZM (2020) Structure and Properties of All-Cellulose Composites Prepared by Controlling the Dissolution Temperature of NaOH/Urea Solvent. *Ind Eng Chem Res* 59:10428–10425.
- Xiao X (2008) On the measurement of true fracture strain of thermoplastics materials. *Polym Test* 27:284–95.
- Xie Y, Hill CA, Jalaludin Z, Curling SF, Anandjiwala RD, Norton AJ, Newman G (2011) The dynamic water vapour sorption behaviour of natural fibres and kinetic analysis using the parallel exponential kinetics model. *J Mater Sci* 46(2):479–489.
- Xu D, Cerbu C, Wang H, Rosca IC (2019) Analysis of the hybrid composite materials reinforced with natural fibers considering digital image correlation (DIC) measurements. *Mech Mater* 135:46–56.
- Yan L, Chouw N, Jayaraman K (2014) Flax fibre and its composites—a review. *Compos Part B Eng* 56:296–317.
- Yang Q, Saito T, Berglund LA, Isogai A (2015) Cellulose nanofibrils improve the properties of all-cellulose composites by the nano-reinforcement mechanism and nanofibril-induced crystallization. *Nanoscale* 7:17957–63.
- Yang X, Berglund LA (2018) Water-based approach to high-strength all-cellulose material with optical transparency. *ACS Sustain Chem Eng* 6:501–10.

- Yousefi H, Nishino T, Faezipour M, Ebrahimi G, Shakeri A (2011) Direct fabrication of all-cellulose nanocomposite from cellulose microfibrils using ionic liquid-based nanowelding. *Biomacromolecules* 12:4080-5.
- Yousefi H, Faezipour M, Hedjazi S, Mousavi MM, Azusa Y, Heidari AH (2013) Comparative study of paper and nanopaper properties prepared from bacterial cellulose nanofibers and fibers/ground cellulose nanofibers of canola straw. *Ind Crops Prod* 43:732-7.
- Zhang J, Xu L, Yu J, et al (2016) Understanding cellulose dissolution: effect of the cation and anion structure of ionic liquids on the solubility of cellulose. *Sci China Chem* 59:1421-1429.
- Zhang YH, Cui J, Lynd LR, Kuang LR (2006) A transition from cellulose swelling to cellulose dissolution by o-phosphoric acid: evidence from enzymatic hydrolysis and supramolecular structure. *Biomacromolecules* 7:644-648.
- Zhu H, Parvinian S, Preston C, Vaaland O, Ruan Z, Hu L (2013) Transparent nanopaper with tailored optical properties. *Nanoscale* 5:3787-92.
- Zhu H, Fang Z, Preston C, Li Y, Hu L (2014) Transparent paper: fabrications, properties, and device applications. *Energy Environ Sci* 7:269-87.
- Zhu H, Zhu S, Jia Z, Parvinian S, Li Y, Vaaland O, Hu L, Li T (2015) Anomalous scaling law of strength and toughness of cellulose nanopaper. *Proc Natl Acad Sci U S A* 112:8971-6.
- Zhu M, Song J, Li T, Gong A, Wang Y, Dai J, Yao Y, Luo W, Henderson D, Hu L (2016) Highly anisotropic, highly transparent wood composites. *Adv Mater* 28:5181-7.
- Zhu M, Wang Y, Zhu S, Xu L, Jia C, Dai J, Song J, Yao Y, Wang Y, Li Y, Henderson D (2017) Anisotropic, transparent films with aligned cellulose nanofibers. *Adv Mater* 29:1606284.
- Zweckmair T, Hettegger H, Abushammala H, Bacher M, Potthast A, Laborie MP, Rosenau T (2015) On the mechanism of the unwanted acetylation of polysaccharides by 1, 3-dialkylimidazolium acetate ionic liquids: Part 1—Analysis, acetylating agent, influence of water, and mechanistic considerations. *Cellulose* 22: 3583-96.

ISBN 978-952-64-0235-2 (printed)

ISBN 978-952-64-0236-9 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University
School of Chemical Engineering
Department of Bioproducts and Biosystems
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**