Recycling and Spinning of Superbase-Based Ionic Liquid Solutions in the Lyocell Process: Potential and Limitations

Sherif Elsayed

Recycling and Spinning of Superbase-Based Ionic Liquid Solutions in the Lyocell Process: Potential and Limitations

Sherif Elsayed

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Chemical Engineering, at a public examination held at the meeting hall Halko of the school on 09 April 2021 at 12:00.

The defense is available via the Remote connection link:
<https://aalto.zoom.us/j/65571290575>

Aalto University
School of Chemical Engineering
Department of Bioproducts and Biosystems
Biorefineries

Supervising professor

Professor Herbert Sixta, Aalto University, Finland.

Thesis advisor

Dr. Sanna Hellsten, Aalto University, Finland.

Preliminary examiners

Professor Gotoh Yasuo, Shinshu University, Japan.

Professor Armando Silvestre, Aveiro University, Portugal.

Opponent

Associate Professor Héctor Rodríguez, University of Santiago de Compostela, Spain.

Aalto University publication series

DOCTORAL DISSERTATIONS 24/2021

© 2021 Sherif Elsayed

ISBN 978-952-64-0280-2 (printed)

ISBN 978-952-64-0281-9 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-64-0281-9>

Unigrafia Oy

Helsinki 2021

Finland

Author

Sherif Elsayed

Name of the doctoral dissertation

Recycling and Spinning of Superbase-Based Ionic Liquid Solutions in the Lyocell Process: Potential and Limitations

Publisher School of Chemical Engineering

Unit Department of Bioproducts and Biosystems

Series Aalto University publication series DOCTORAL DISSERTATIONS 24/2021

Field of research Biorefineries

Manuscript submitted 30 November 2020

Date of the defence 9 April 2021

Permission for public defence granted (date) 17 February 2021

Language English

☐ **Monograph**

☒ **Article dissertation**

☐ **Essay dissertation**

Abstract

This thesis demonstrates the recyclability of superbase-based ionic liquids in the scope of developing a sustainable Lyocell process for the man-made cellulose fiber industry. Ioncell is a Lyocell-based technology that utilizes ionic liquids in the direct dissolution of cellulose and the production of textile-grade fibers via a dry-jet wet spinning process. In order to commercialize this technology, there are several important criteria to be met: The selection of a solvent with a strong cellulose dissolution power, a stable spinning process, good mechanical properties of the regenerated fibers, and above of all, the quantitative recovery of the solvent from the coagulation bath without impairing its solvation power. The work presented herein aspires to cover all the mentioned challenges. We chose a thermal recovery path to recycle the ionic liquids while identifying potential solvent alterations taking place. Such alterations include the consumption of the ionic liquid in nucleophilic hydrolysis reactions, the selective vaporization of the base during recovery, and the residual water in the recovered solvent. The combination of these alterations can interfere with the dissolution process. Initially, we investigated the potential of guanidine- and amidine-based ionic liquids, in comparison to N-methylmorpholine N-oxide, as solvents capable of producing textile-grade fibers. We also presented the recyclability of the guanidine-based ionic liquid, 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-enium acetate, and the amidine-based ionic liquid, 1,5-diaza-bicyclo[4.3.0]non-5-enium acetate, in the Ioncell process, while we quantitatively analyzed the changes in solvent composition (= alterations) occurring during the thermal recovery stages. The results revealed that the 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-enium acetate is hydrothermally more stable, implying that the alterations in the solvent did not affect its dissolution capabilities. Contrarily, a relatively large fraction of the 1,5-diaza-bicyclo[4.3.0]non-5-enium acetate was consumed in undesired hydrolysis reactions and in the vaporization of the neutral base, which inhibited the dissolution power of the recovered solvent. Additionally, we simulated the solvent alterations in both ionic liquids to explore the thresholds for cellulose dissolution and the impact of the alterations on the rheological properties of the solution and the spinnability of the fibers. The outcome confirmed the tolerance of 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-enium acetate to substantially more alterations in its composition, while the fibers produced from it exhibited superior properties. These findings favor 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-enium acetate as a promising solvent in the Lyocell process and can be regarded as an important milestone in the scaling up of the Ioncell process.

Keywords ionic liquid, superbase, regenerated fiber, MMCF, solvent recycling, cellulose dissolution

ISBN (printed) 978-952-64-0280-2

ISBN (pdf) 978-952-64-0281-9

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Helsinki

Location of printing Helsinki **Year** 2021

Pages 144

urn <http://urn.fi/URN:ISBN:978-952-64-0281-9>

Acknowledgements

This work was carried out from December 2016 to December 2020 in the Department of Bioproducts and Biosystems, Aalto University, Finland, under the supervision of Professor Herbert Sixta. The research was primarily in the scope of the SolvRec project (Technical Development of Ioncell-F with special Emphasis on the Solvent Recycling) that was funded mainly by Business Finland, along with industrial collaborators. Besides, the research also received special support from Aalto University, which is currently upscaling the Ioncell process. In 2021, the start-up of the pilot-plant Biofactory is scheduled.

I would like to thank my Professor Herbert Sixta for his continuous support over the course of my degree. Honestly, his availability and guidance never left me feeling lost. Herbert is not only a great scientific mentor, but also a proficient leader and a master of live presentations. I have learned a lot from you. My deepest gratitude is also to my Postdoctoral researchers Sanna Hellsten, Cham-seddine Guizani and Joanna Witos, who were always my companions in research, and were always available for discussion and planning. I'm also grateful for Professor Michael Hummel for his scientific advices whenever they were needed.

It was my pleasure to work in the SolvRec project, and to collaborate with experts from different fields. Special thanks to Dr. Susanne Wiedmer and Professor Ilkka Kilpeläinen, University of Helsinki, for their friendly cooperation and support. I would like to extend my gratitude to Professor Ville Alopaeus for providing the main model parameters and data for the water removal simulation. Also, my warm appreciation to Simone Haslinger and Inge Schlapp-Hackl for their support in measuring the Kamlet-Taft parameters and the TGA-DSC measurements. I would like to thank all my co-authors for their significant contributions, and in particular to Benjamin Viard (Master thesis student) for his extraordinary motivation and exceptional work.

Working in the lab was truly enjoyable because of the great mood, support and even humor from all my colleagues. Thank you, Sami Rantasalo, for everything, for being there, for our talks, for the assistance, and for making my work in the lab a pleasant time. It was delightful to be a member of the Ioncell group, and to share the ups and downs. I am grateful to all my colleagues, Yibo Ma, Shirin Asaadi, Kaniz Moriam, Leena Katajainen, Mikaela Trogen, Hilda Zahra, Marja Rissanen, Daisuke Sawada and Nicole Nygren. Also, to the technical staff, Timo Ylönen, Seppo Jääskeläinen, Hans Orasaari and Terho Konttinen, for maintaining the lab units and for being available even in short notice.

To Guillaume Riviere, I was lucky to have you as my office mate. It is nice to see how our friendship developed over the years. Indeed, time has gone fast. You were my best companion and our workdays were never boring. Also, thanks to Joice Kaschuk, Sara Ceccherini, Ling Wang, Janika Lehtonen and Roberta Teixeira Polez for the coffee breaks and the after-work chats.

To my family, Simone you were my additional motive. Your help and support in my last year have been priceless. Thank you, Magdy, my dear father and brother, for your love and support. Finally, to my mother, you are the first person I think of whenever I want to share something. I still talk to you, and you still listen. Mother, although you have departed from this world, in my heart you always live.

Espoo, 09 November 2020
Sherif Elsayed

Contents

1.	Introduction	1
2.	Thesis Objectives.....	5
3.	Background	7
3.1	Cellulose.....	7
3.2	Technologies for Cellulose Dissolution.....	8
3.2.1	Lyocell Process	9
3.3	Dissolution of Cellulose in ILs.....	11
3.4	Rheological Properties	13
3.5	Dry-Jet Wet Spinning	14
3.6	Methods for IL Recycling.....	16
3.7	Properties of Superbase-based ILs During Thermal Recovery	18
3.8	Impurities and Side-Products in Ioncell	21
4.	Experimental	23
4.1	Cellulose, Ionic Liquids and Other Raw Materials	23
4.2	Methods	24
4.2.1	IL Synthesis	24
4.2.2	Cellulose Solution Preparation.....	24
4.2.3	Fiber Spinning	27
4.2.4	Spinbath Recycling.....	30
4.2.5	Dress Making.....	31
4.3	Analytics.....	33
4.3.1	Cellulose Solutions and Fibers	33
4.3.2	Pure IL and IL-Rich Solutions.....	36
4.3.3	Dilute IL Solutions	37
4.4	Simulation for the Energy Demand for IL Recycling	37
5.	Results and Discussion.....	39
5.1	Lyocell Solvents for Cellulose Dissolution and Fibers Regeneration	39
5.2	Dissolution of Cellulose in Altered ILs	42

5.2.1	Effect of [mTBDH][OAc] Alterations	42
5.2.2	Effect of [DBNH][OAc] Alterations	48
5.3	Recycling of ILs in the Lyocell Process: A Comparison of [mTBDH][OAc] and [DBNH][OAc]	49
5.3.1	ILs Recycling	49
5.3.2	Solvent Recovery Rate	54
5.3.3	Energy Demand.....	56
5.3.4	Properties of the Cellulose Solutions and Spun Fibers	57
5.3.5	Demonstration Dress.....	58
5.4	Additional Spinning Using [mTBDH][OAc]	59
5.5	Additional Recycling Using [mTBDH][OAc]	61
6.	Future Outlook.....	65
7.	Conclusions	67
	References	69
	Appendix 1	82
	Appendix 2.....	84
	Appendix 3.....	85

List of Abbreviations and Symbols

[emim][OAc]	1-ethyl-3-methylimidazolium acetate
[EtNH ₃][NO ₃]	ethylammonium nitrate
[DBNH][OAc]	1,5-diaza-bicyclo[4.3.0]non-5-enium acetate
[DBUH][OAc]	1,8-diazabicyclo(5.4.0)undec-7-enium acetate
[H-mTBD-1][OAc] acetate	1-[3-(methylammonio)propyl]-1,3-diazinan-2-onemium acetate
[H-mTBD-2][OAc]	1-(3-ammoniopropyl)-3-methyl-1,3-diazinan-2-one- mium acetate
[mTBDH][OAc]	7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-enium acetate
[TBDH][OAc]	1,5,7-Triazabicyclo[4.4.0]dec-5-enium acetate
[ΣH-mTBD][OAc]	1-[3-(methylammonio)propyl]-1,3-diazinan-2-one- mium acetate and] 1-(3-ammoniopropyl)-3-methyl- 1,3-diazinan-2-onemium acetate
A	pre-exponential factor
ABS	aqueous biphasic system
APPac	1-(3-acetamidopropyl)-2-pyrrolidone
A.T.	additional trial
A/B ratio	acid-to-base ratio
A-mTBD-1	1-[3-(acetamido)propyl]-1,3-diazinan-2-one
A-mTBD-2	1-3-(acetamidopropyl)-3-methyl-1,3-diazinan-2-one
[APPH][OAc]	1-(3-aminopropyl)-2-pyrrolidonium acetate
COP	cross-over point
CE	capillary electrophoresis
<i>CI</i>	crystallinity index
CS ₂	carbon sulfide

CW_{hkl}	crystal widths
DBN	1,5-diaza-bicyclo[4.3.0]non-5-ene
DBU	1,8-diazabicyclo(5.4.0)undec-7-enene
DENA	N,N-diehyl-4-nitro-aniline dye
D.M.C.	dry matter content
DP	degree of polymerization
DR	draw ratio
DR	max maximum draw ratio
EC ₅₀	median effective concentration
ET(30) and ET(33)	solvent polarity values
E _A	activation energy of flow
f_a	amorphous orientation
f_c	crystalline orientation
f_t	total orientation
G'	storage modulus
G''	loss modulus
H ₂ S	hydrogen sulfide
$I(\theta)$	sample intensity
$I_{bg}(\theta)$	background intensity
IL	ionic liquid
K	shape factor
K ₃ PO ₄	potassium phosphate
LDPE	low density polyethylene resin
L/D	length-to-diameter
MeOH	methanol
MMCF	man-made cellulosic fibers
M _n	number average molar mass
mTBD	7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-ene
M _w	weight average molar mass
NA	4-nitroaniline dye
Na ₂ SO ₄	Sodium sulfate

NMMO	N-methylmorpholine N-oxide monohydrate
R	universal gas constant
TBD	1,5,7-Triazabicyclo[4.4.0]dec-5-ene
TFE-1	first stage thin-film evaporator
TFE-2	second stage thin-film evaporator
UV	ultraviolet
WAXS	wide-angle X-ray scattering
WB	phenolate
ZnSO ₄	Zinc sulfate
α	acidity
β	basicity
β_{hkl}	full width at half maximum of the diffraction peak
$\beta - \alpha$	net basicity
Δn	birefringence
θ	diffraction angle
η^*	complex viscosity
η_o	zero shear viscosity
λ	wavelength
π^*	solvent polarizability
ω	angular frequency

List of Publications

This doctoral dissertation consists of a summary and of the following publications which are referred to in the text by their numerals

1. Elsayed, Sherif; Hummel, Michael; Sawada, Daisuke, Guizani, Chamseddine; Rissanen, Marja; Sixta, Herbert. 2021. Superbase-Based Protic Ionic Liquids for Cellulose Filament Spinning. *Cellulose*, volume 28, issue 01, pages 533–547. DOI: 10.1007/s10570-020-03505-y.

2. Elsayed, Sherif; Hellsten, Sanna; Guizani, Chamseddine; Witos, Joanna; Rissanen, Marja; Rantamäki, Antti H.; Varis, Pauliina; Wiedmer, Susanne K.; Sixta, Herbert. 2020. Recycling of Superbase-Based Ionic Liquid Solvents for the Production of Textile-Grade Regenerated Cellulose Fibers in the Lyocell Process. *ACS Sustainable Chemistry & Engineering*, volume 08, issue 37, pages 14217–14227. DOI: 10.1021/acssuschemeng.0c05330.

3. Elsayed, Sherif; Viard, Benjamin; Guizani, Chamseddine; Hellsten, Sanna; Witos, Joanna; Sixta, Herbert. 2020. Limitations of cellulose dissolution and fibers spinning in Lyocell process using [mTBDH][OAc] and [DBNH][OAc] solvents. *Industrial & Engineering Chemistry Research*, volume 59, issue 45, pages 20211–20220. DOI: 10.1021/acs.iecr.0c04283.

Author's Contribution

Paper I: Superbase-Based Protic Ionic Liquids for Cellulose Filament Spinning

SE and MH planned for the study. SE conducted the dope preparations, fiber spinning, scanning-electron microscopy measurements and fiber birefringence measurements. DS conducted the X-ray diffraction measurements. MR planned and supervised fiber tensile measurements. Data interpretation and manuscript writing was done by SE. CG, MH and HS supervised the research and reviewed the manuscript.

Paper II: Recycling of Superbase-Based Ionic Liquid Solvents for the Production of Textile-Grade Regenerated Cellulose Fibers in the Lyocell Process

SE, SH and CG planned the study. SE conducted the experiments. CG and SE performed NMR measurements. JW, AR and SW performed the CE analysis of the samples. MR planned and supervised fiber tensile measurements. AR and SW executed the toxicity study. MR and PV planned and executed the yarn spinning and dress making. SE wrote the manuscript, supervised and reviewed by HS.

Paper III: Limitations of cellulose dissolution and fibers spinning in Lyocell process using [mTBDH][OAc] and [DBNH][OAc] solvents

SE, BV and CG designed the [mTBDH][OAc] study. BV conducted the lab experiments. SE and SH planned the [DBNH][OAc] study. SE conducted the experiments. SE and BV planned and executed fiber tensile measurements. JW conducted the quality control analysis of the solvents and the superbases. Manuscript writing was conducted by SE, supervised and reviewed by HS.

1. Introduction

It was not until the 1973 oil embargo that many Western societies envisioned a fossil-independent economy. Back in 1973, when the OPEC enforced the infamous oil crisis on the West for political and economic pressure, it led to catastrophic consequences on the entirely oil-driven economies. Creating long queues for petrol stations, these nations were left to deal with major power and fuel shortages until the political uncertainties could be settled. After learning the lesson, the Western World commenced in developing cleaner alternatives for power and oil-based products.

Since then, the share of renewable power has steadily increased all over the world. Already in 2018, the EU reported a collective share of renewables of 18% on the path of 20 % by 2020 (EU Climate & Energy Package 2020), where countries like Sweden, Finland, Denmark and Estonia already surpassed their 2020 targets (Eurostat 2020). In the transport sector, 8.3 % of the fuel in 2018 was procured from clean resources with France, Norway and England announcing a ban on diesel cars in the near future (Szymkowski 2017; Eurostat 2020). Moreover, the EU parliament adopted stricter policy from 2019 to ban single-use plastics by 2021 (European Parliament 2019).

However, in the textile industry, the dependence on oil-based synthetic fibers, such as polyesters, polyamides, acrylics, and nylons has increased since the 1960s (Eichinger 2012). By the 2000s, the share of synthetic fibers overshadowed cotton, and progressed to contribute to 62 % of the total market share in 2018, matched by only 26 % for cotton and 6 % for man-made cellulose fibers (MMCF) (Eichinger 2012; *The Fiber Year* 2019). The global production of cotton has been stagnant since 2005 at 25 million tonnes annually (Industrievereinigung Chemiefaser 2019), while further expansions are facing many challenges. This is especially pronounced since the availability of arable land is now limited, and when available, it is rather allocated for food agriculture to cope with the increase in the global population. Moreover, producing 1 kg of cotton requires about 10 000 liters of water, a scarce resource that many countries cannot afford to waste on a single product (Mekonnen & Hoekstra 2011).

On the other hand, the impact of fast fashion on the consumer has led to double the global apparel consumption in just fifteen years, reaching more than 100 billion units in 2015, while the usage time of 50 % of the items dropped to less than one year (Ellen MacArthur Foundation 2017). While societies struggle to introduce an efficient sorting and recycling system for textiles, most of the clothes are still being landfilled and incinerated. Meanwhile, the environmental

concerns of textile waste are not restricted to the ultimate disposal, but also to the uncontrolled accumulation of plastics in the environment. Nowadays, more and more studies are confirming the negative impact of synthetic fibers on marine life already during their life cycle (Cesa *et al.* 2020; Hernandez, Nowack & Mitrano 2017; Napper & Thompson 2016). Napper and Thompson (2016) reported an average of 700 000 fibers possibly released during a single laundry wash of a 6 kg load. Inevitably, this discharged plastic debris will enter the marine environment, where it will be further fragmented and transformed into secondary, smaller microplastics that can be ingested by the marine invertebrates (Goldstein & Goodwin 2013). As our consumption of synthetic fibers is not set to decrease in the future, the microplastic concentration in the ocean is expected to substantially grow. Recently, a 50-fold increase in the buoyant microplastics was estimated that about 50 particles per cubic meter, and 8000 particles per kilogram of sedimented microplastics will prevail in the oceans by 2100 (Everaert *et al.* 2018).

Despite the growth in the synthetic fiber industry, the natural and soft feeling of cotton has always coined it as a premium fiber. Moreover, cotton exhibits intrinsic properties such as breathability and being hypoallergenic, which cannot be easily replaced. MMCF are associated to cotton properties since the core polymer is the same, which is cellulose. Besides, most of the MMCF originate from countries that dominate the pulp and paper industry, where trees grow on rainfall and require little or no resources, thus making it an ecofriendly option. Therefore, a future potential for MMCF to fill the cotton gap can be anticipated.

In 2018, the total production capacity of MMCF was 6.8 million tonnes of which viscose fibers accounted for 5.6 million tonnes (*The Fiber Year* 2019). Although the viscose technology is the biggest player in the MMCF market, it poses a large environmental threat since the dissolution of cellulose requires large amounts of caustic soda and carbon disulfide (CS_2), while the fibers regeneration takes place in sulfuric acid, emitting hazardous gases such as hydrogen sulfide (H_2S) and CS_2 , which endangers both the environment and the work personnel (Shen, Worrell & Patel 2010). For that reason, the EU has imposed strict environmental regulations to monitor viscose implementations in Europe, allowing it to thrive in Asia. By 2015, China, India and Indonesia contributed to 84% of the global viscose production (Water Footprint Network 2017).

The Lyocell process is among the alternative technologies to produce MMCF. Lyocell is a generic term that originates from the Greek word *lyein* (meaning to dissolve) and *cell* from cellulose. The dissolution of cellulose in the Lyocell process occurs in a polar solvent directly without the need of polymer derivatization, while the regenerated fibers are produced through a dry-jet wet spinning process. Since the 1960s, there has been continuous development of this technology using the solvent N-methylmorpholine N-oxide monohydrate ($\text{NMMO} \cdot \text{H}_2\text{O}$) with the commencing of the first commercial plant in the early 1990s. Currently, the Lyocell fibers are being sold under the trademark Tencel owned by Lenzing AG, Austria. The undeniably premium quality of these fibers promoted the production capacity of Tencel to reach about 220 000 annual tonnes in 2018 (Lenzing 2019). More importantly, Lyocell is labelled as a green

technology, since it overcomes the environmental drawbacks of the viscose as no harmful solvents are required, and likewise, no toxic gases are emitted during the spinning process. Despite these advantages, there are certain concerns with the stability of the NMMO solvent that can undergo multiple degradation pathways, even in the presence of cellulose (Rosenau *et al.* 2001; Konkin *et al.* 2007). Therefore, stabilizers are essential to prohibit potential runaway reactions that may cause explosion, and therefore compromise the whole process (Rosenau *et al.* 2001).

Although NMMO has been the most widely utilized solvent in the Lyocell process, its stability issues incited the development of other direct solvents. Ionic liquids (ILs), typically classified as liquid salts under 100 °C, have emerged during the early 21st century as solvents capable of directly dissolving lignocellulosic polymers (Wang, Gurau & Rogers 2012; Pinkert *et al.* 2009; Brandt *et al.* 2013; Vitz *et al.* 2009; Swatloski *et al.* 2002). Laus *et al.* (2005) were among the first to produce Lyocell fibers from IL solutions. Ioncell is a technology, introduced in 2013, that utilizes protic superbase ILs to produce MMCF for textile and technical applications. This Lyocell-based technology has recently been employing an amidine-based superbase solvent 1,5-diaza-bicyclo[4.3.0]non-5-enium acetate ([DBNH][OAc]) yielding fibers of similar quality to Tencel (Sixta *et al.* 2015; Hummel *et al.* 2015). At the same time, no exothermic runaway reactions occur when using ILs, and therefore foreign stabilizers are not required (Sixta *et al.* 2015). The potential of Ioncell is not only limited to spinning of fibers from virgin wood pulp as promising results have been published on the recycling and upcycling of textile wastes, newspaper and cardboard to produce new fabrics (Haslinger *et al.* 2019a; Ma *et al.* 2016). These promising findings have attracted growing attention to Ioncell in recent years, which is now allowing a scale-up to a pilot-plant in 2021. However, the success of this technology is also directly linked to the quantitative recyclability of the IL.

Like the NMMO-based Lyocell process, the fiber spinning process in Ioncell is carried out *via* a dry-jet wet spinning technology in which the cellulose filaments are pumped through spinneret capillaries, stretched in an air-gap, and regenerated in an aqueous coagulation bath. Therefore, in a continuous process, the dilute IL solution must be recovered. The solvent recovery consists of purification of the solvent from solute-derived impurities, and secondly the removal of excess water, e.g. by evaporation. Because of the analytically undetectable impurities during spinning on a small laboratory scale, we limit the scope of solvent recovery in this PhD work to the removal of water to restore the dissolving ability for cellulose.

Several recycling methods have been outlined previously for different IL solutions, yet not all are feasible for the Ioncell process due to the hydrophilicity of the superbases and/or the insufficient rate of recovery (Mai, Ahn & Koo 2014; Palomar *et al.* 2009; Dibble *et al.* 2011). Out of these methods, evaporation has already proven feasible recovery rates for the NMMO solution (> 99 %) (Potthast *et al.* 2002). Yet, the elevated temperature during evaporation can induce selective vaporization of the ionic compounds and cause undesired hydrolysis reactions, which alter eventually the IL composition (Ahmad *et al.* 2016;

Parviainen *et al.* 2015). Besides, the accumulation of such undesired compounds in a continuous plant can negatively impact the economy of the process since make-up IL will be required to keep the solvent-to-solute ratio constant.

In the search for an IL with excellent cellulose solubility in combination with a significantly improved hydrothermal stability compared to [DBNH][OAc], [mTBDH][OAc] was selected after extensive screening of the superbase-based ILs as an IL that exhibits these properties in all points. These results were filed as a patent application (WO2018138416A1).

In this thesis, the focus was put on the IL 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-enium acetate ([mTBDH][OAc]), which as our patented preliminary investigations have shown, is more stable against thermal and hydrolytic degradation reactions than the amidine-based IL and can therefore be recovered by evaporation with minimal losses. Another focus was the production of spinnable cellulose solutions (dope) from the recovered [mTBDH][OAc] solvent. This took place by spinning of fibers and recycling of the solvent in various successive cycles. Additionally, we conducted multiple trials to optimize several process parameters that would benefit the lab-scale process as well as the pilot-plant. Our findings were published in three peer-reviewed scientific articles (**Paper I, II and III**). Moreover, the results from our optimization trials, additional trials (**A.T. 1 and 2**), were included in this work as highly relevant.

We investigated [mTBDH][OAc] in comparison to other ILs with reference to NMMO·H₂O in terms of cellulose dissolution, rheology of spinning dopes, fiber spinning, and mechanical properties of the fibers. These findings are summarized in **Paper I**. In **Paper II**, we progressed to construct a recycling scheme, which allowed us to track and quantify deviations in the IL composition taking place during the recovery process. Moreover, the recovered IL was used to dissolve and spin a 13 wt.% cellulose solutions in consecutive cycles. Thereafter, several parameters related to dope preparation and fiber spinning were tested in **A.T. 1**. In order to further elucidate the effect of the solvent deviations occurring during recovery, we altered the solvent composition to contain different concentrations of the undesired side-products, while aiming to dissolve and spin cellulose fibers (**Paper III**). This study was particularly helpful in identifying the IL specifications needed from the recovery process to deliver good cellulose dissolution. In **A.T. 2**, we aimed to use [mTBDH][OAc] in the Ioncell process for 20 cycles. Therein, we could monitor dope rheology, spinnability and test spinning in an enriched IL spinbath. Table 1 provides the purpose of each trial.

Table 1. A summary of the publications and trials found herein.

Publication / A.T.	Purpose
Paper I	Comparative testing of Lyocell solvents for spinning of textile-grade cellulose fibers
Paper II	Spinning and recycling of [mTBDH][OAc] and [DBNH][OAc] in the Lyocell process
Paper III	Identifying the thresholds of good dissolution and spinning while deviations in solvent composition are present
A.T. 1	Optimizing spinning parameters for [mTBDH][OAc]
A.T. 2	Extended spinning and recycling of [mTBDH][OAc] in the Ioncell process

2. Thesis Objectives

This thesis aims to prove the recyclability of selected ILs in the Ioncell process, while producing textile-grade fibers. The necessity of the work executed in this thesis came along with the decision of Aalto's management to scale-up the Ioncell process to a pilot-plant scale. This followed several years of successfully manifesting the potential of the Ioncell products in various international events. Still, the recycling of the solvents was lacking.

Before commencing the work, preliminary efforts were made to recover and recycle [DBNH][OAc] as it is currently the commonly utilized solvent in Ioncell. However, the outcome was only disappointing. Upon adopting [mTBDH][OAc], we started to examine several aspects related to the fiber spinning side, and the solvent recovery side. Systematically, we identified the main solvent parameters that change during the thermal concentration and which reduce or even prevent the solvation capacity of the recovered IL. These solvent alterations comprise the formation of hydrolysis products, a change in the acid-to-base ratio of the IL (A/B ratio) and the amount of residual water. Increasing one of these parameters or their combination beyond a certain level will undoubtedly impede the dissolution of cellulose. Hence, we can provide our main research questions in the below table.

Research questions

- Are there significant changes in the dope rheology and fiber properties when using an amidine-based compared to a guanidine-based IL?
- Can we quantify the changes in the IL composition during recovery?
- Are the changes in the composition occurring to [mTBDH][OAc] during recovery sufficient to dissolve and spin cellulose? Is it the same for [DBNH][OAc]?
- To what extent can the changes in the [mTBDH][OAc] and [DBNH][OAc] allow good cellulose dissolution and fiber spinning?
- Can the hydrolysis reactions be curbed and if so, how?
- Are there major degradations in cellulose degree of polymerization when using recovered IL compared to pure IL?
- What is the effect of an increasing number of recovery cycles on the solution and fibers quality?

3. Background

3.1 Cellulose

Ever since its discovery by Anselme Payene in 1837, cellulose has evoked extensive research interest due to its natural abundance. However, it was not until the 1960s that its crystal structure could finally be fully elucidated by X-ray diffraction (Hon 1994). Cellulose represents a linear polymer composed of anhydroglucose units that are interlinked *via* $\beta(1-4)$ glycosidic bonds. In tiny organisms such as algae or bacteria, cellulose is predominant in its Ia form, whereas in higher plant species such as wood, cotton, or hemp, it adapts a so-called Ib structure (Heinze 2015). When dissolved, cellulose transforms to a thermodynamically more stable state referred to cellulose II (Isogai & Atalla 1998; Wada *et al.* 2004; Kolpak & Blackwell 1976). Through chemical or heat treatments, cellulose can further be converted to thermodynamically reversible forms such as cellulose IV or III (Chidambareswaran *et al.* 1982).

As for all structures, their difference merely lies in their distinct intermolecular hydrogen bonding pattern established between the hydroxy groups of anhydroglucose (Heinze 2015; Hinterstoisser & Salmén 2000). In cellulose I, illustrated in Figure 1, hydrogen bonding mainly occurs between the hydroxymethyl group of the C6 atom and the hydroxy group attached to the C3 position (Gardner & Blackwell 1974). These strong intermolecular interactions lead to the formation of microfibrils, which significantly contribute to the strength and stability of the polymer. In plants, usually more than 40 cellulose chains are linked to each other *via* this bonding mechanism, resulting in structures with Young's moduli of around 130 GPa (Sakurada *et al.* 1964; Matsuo *et al.* 1990). Cellulose chains also experience intersheet interactions through VanderWaals forces that are induced by the aliphatic nature of the anhydroglucose heterocycle (Diddens *et al.* 2008). Owing to these forces, cellulose exhibit an amphiphilic nature that deems it recalcitrant to modifications. Besides, cellulose cannot be melted, hence when intended to be processed, it requires dissolution in solvents that can weaken both, hydrophobic and hydrophilic interactions.

Figure 1. Cellulose structure showing the inter- and intramolecular interactions. Reprinted with permission from (Pinkert *et al.* 2009). Copyright (2020) American Chemical Society.

3.2 Technologies for Cellulose Dissolution

Historically, solvents capable of dissolving cellulose were classified into three main groups: Solvents that require cellulose derivatization as a pre-requisite, other solvents act as chelating agents that are able to form stable cellulose water-soluble complexes, and finally solvents that can perform the dissolution directly. For the first category, the derivatization step is usually achieved *via* chemically modifying the hydroxyl groups located at the C2, C3 and C6 of the anhydroglucose unit, and forming new groups that are can interact with the solvent. Among the cellulose derivatives, cellulose xanthate (the viscose process), cellulose acetate, and cellulose carbamate, are the most popular. However, the history of MMCF date back to the early 1850s, when George Audemars (Switzerland) discovered that nitrated cellulose could be dissolved in a mixture of alcohol and ether, and air spun producing nitrocellulose fibers (Audemars 1855). However, the scale-up and commercialization of this process was unsuccessful as the nitrate-fibers were very flammable to an explosive extent, often called ‘guncotton’ (Woodings 2001).

Nowadays, almost 82.3 % of MMCF are produced from the cellulose xanthate derivative (*The Fiber Year* 2019). In the viscose process, first, cellulose is subjected to alkalization. Thereafter, the DP of the produced alkalicellulose is pre-adjusted to 270 – 350 in an ageing step at temperatures around 50 °C in the presence of catalyst. This also activates the anhydroglucose side groups producing a cellulose alkoxide derivative. The dissolution of the cellulose derivative takes place *via* reacting with CS₂ gas (xanthagonation step) at 25 – 37 °C over a prolonged duration. The spinning of the rayon fibers is done in a wet-spinning process, where the dissolved xanthogenate solution is pumped through a spinneret into a coagulating bath containing mainly H₂SO₄ and sodium sulfate (Na₂SO₄), and to a lower extent zinc sulfate (ZnSO₄) (Wilkes 2001). The filaments are instantly regenerated *via* the neutralization of the xanthagonate groups with the acid producing Na₂SO₄ and releasing the toxic gases, H₂S and CS₂ (Wilkes 2001). Consequently, the viscose process involves harmful chemicals that pose both environmental and personal threat. From this process, the classic viscose fibers, 21.5 cN/tex and 22.6 % elongation (Jiang *et al.* 2012), are produced. In order to produce fibers of higher modulus (modal fibers), the concentration of ZnSO₄ in the bath is increased since it functions as a coagulation

retarding agent (Papkov, Ukhanova & Antipova 1969), allowing the fibers to regenerate over an extended period (modal fibers), thus increasing the crystallinity and improving their strengths.

On the other hand, the cuprammonium process is among the technologies utilizing chelating agents in forming stable cellulose complexes that are water-soluble. The cuprammonium comprises inorganic complexes, cuoxen ($[\text{Cu}(\text{NH}_2(\text{CH}_2)_2\text{NH}_2)_2[\text{HO}]_2]$) and cadoxen ($[\text{Cd}(\text{NH}_2(\text{CH}_2)_2\text{NH}_2)_2[\text{HO}]_2]$) for deprotonating and binding the hydroxyl groups of C2 and C3 positions (Liebert 2010). The commercialization of this process was limited due to the need of using cotton pulp together with the high cost of the copper salts. Currently, this process is only noticeable in Asahi Japan for medical fibers applications (Kamide & Nishiyama 2001). However, the inorganic complexes are still widely employed in analysis of cellulose intrinsic viscosity (normalized as ASTM D1795 (2013) and ASTM D4243 (2009)). Cellulose dissolution is achieved through deprotonating and binding the hydroxyl groups in C2 and C3 positions (Liebert 2010).

On the other hand, the Lyocell solvents dissolve cellulose directly. It is now the second most utilized technology in the MMCF production scale. Currently, it has a global production capacity of 220 000 annual tonnes, and an on-going expansion of 100 000 annual tonnes, due in 2020 – 2021 (Lenzing 2019). The undeniably increasing interest in this technology is due to its multiple advantages over the viscose process. In the next section, we discuss in detail several aspects of this promising process.

3.2.1 Lyocell Process

NMMO-based Lyocell Process

NMMO belongs to the family of heterolytic amine oxides. This solvent discovered back in the 1939 by Swiss chemists Charles Graenacher and Richard Sallman was only in 1969 described for its potential in dissolving cellulose (White 2001). Evidently, the key property of this molecule is the highly polar N–O group, with the highest electron density around the oxygen (Rosenau *et al.* 2001). The solvation power of this compound originates from its ability to disrupt the hydrogen bonding system responsible for intra- and interchain linkages through merely acid-base interactions (donor – acceptor) (Fink *et al.* 2001; Rosenau *et al.* 2002).

In industry, the NMMO is used in the monohydrate form (13.3 wt.% water), which is also capable of fully dissolving the C6 biomass. The melting point of the $\text{NMMO} \cdot \text{H}_2\text{O}$ is 78 °C compared to 184 °C for the neat anhydrous NMMO (Maia, Peguy & Pérez 1981), offering lower process conditions (e.g. dissolution and spinning temperatures). The cellulose dissolution occurs by, first forming a slurry of 50 – 60 wt.% NMMO, 20 – 30 wt.% water and 10 – 15 wt.% pulp. Thereafter, the slurry is vigorously mixed, and the excess water is evaporated till the stable monohydrate complex is produced, which rapidly produces a homogenous dissolved cellulose solution (Rosenau *et al.* 2001). The cellulose regeneration takes place in a dry-jet wet spinning process, where the filaments are mechanically pressed through spinneret capillaries, of micrometer dimensions,

stretched in an air-gap, and finally coagulate in an aqueous spinbath. The dilute solvent in the coagulation bath is subsequently recovered by the removal of water in a thin-wall evaporator utilizing vacuum (e.g. thin-film evaporator). Only a 50 – 60 wt.% of target residual water is sufficient at this stage since the remainder of the water can be removed while cellulose is dissolving to form NMMO·H₂O, as explained above.

The advantages of the NMMO-based Lyocell over the viscose technology are not limited to the low toxicity of the former (Meister & Wechsler 1998), but also NMMO·H₂O is capable of directly dissolving pulp of wider molar mass distribution and in shorter time, which the viscose lacks. This is because the ageing step is necessary in the viscose process to adjust the DP for better cellulose activation to produce the alkoxide derivative. Moreover, the Lyocell fibers (Tencel) have a pronounced crystallinity and tenacity, a stronger modulus and a uniform longitudinal and cross-sectional morphology (Adusumali *et al.* 2006; Jiang *et al.* 2012). That said, NMMO can also undergo homolytic degradation that cleaves the N–O bond and produces aminyl radicals, N-Methylmorpholine and morpholine, as intermediates (Rosenau *et al.* 2001; Jonsson, Wayner & Luszyk 1996). Furthermore, heterolytic reactions are known to take place, causing severe degradation to the polymer *via* oxidation reactions, and can cause permanent discoloration to the fibers (Lang *et al.* 1986; Buijtenhuijs, Abbas & Witteveen 1986). The degradation of NMMO is described as exothermic runaway reactions. For these reasons, propyl gallate, a phenolic antioxidant, is used as a stabilizer, which in return oxidizes to ellagic acid, and therefore can limit the byproduct formation (Rosenau *et al.* 2002). These safety concerns, and the growing interest in the Lyocell process were triggering factors for researchers to investigate other direct solvents.

ILs-based Lyocell Process

The history of ILs dates back to the early 20th century. In 1914, ethylammonium nitrate [EtNH₃][NO₃] was described as a low melting point fused salt (Walden 1914). However, it was only in the 90s when ILs came under the spotlight as worthy chemicals. Consequently, by 2005, around 1000 ILs were already synthesized in literature with 300 commercially available (ChemFiles 2005). By modifying the cations and anions, one can tailor an enormous range of ILs for specific applications, for example as inorganic and organic solvents, in phase separations and even as electrolytes for supercapacitors (Welton 1999; Hallett & Welton 2011). Besides, as a result of their inherently low vapor pressure and non-flammability, they can be safely recycled with good recovery rates, which often tags them as green chemicals (Earle & Seddon 2000; Zhao, Xia & Ma 2005).

From the wide classes of ILs, superbase ILs exhibit the capability to directly dissolve cellulose without prior need of activation (Swatloski *et al.* 2002; Wu *et al.* 2004; Liu *et al.* 2005). Also, hemicelluloses can be selectively dissolved in IL/water systems (Roselli *et al.* 2014). These ILs are characterized by an asymmetric bulky cation and a strong anion, creating a delocalized charge. Notably, the early research of cellulose-dissolving ILs was conducted using imidazolium

cations, while the promising anions were halides (Swatloski *et al.* 2002), carboxylates (Fukaya *et al.* 2008), and phosphates (Fukaya *et al.* 2008; Brandt *et al.* 2010). Owing to their low viscosity and processing temperatures, imidazolium-based ILs, especially the imidazolium halides and acetates excelled in early stage research, dissolving significant concentrations of cellulose and other biopolymers. Nevertheless, severe limitations have curbed their potential for fiber spinning, since they can decompose at relatively high temperatures (Meine, Benedito & Rinaldi 2010; Kosmulski, Gustafsson & Rosenholm 2004), inducing irreversible degradations of the C6 and C5 polymers (King *et al.* 2012; Liebner *et al.* 2010; Ebner *et al.* 2008).

Alternatively, amidine- and guanidine-based ILs have also been portrayed as excellent cellulose solvents, especially when conjugated with a Brønsted acid (e.g. acetic acid), without the drawbacks of the imidazole derivatives (Parviainen *et al.* 2013) nor the dangerous runaway exothermic degradations of the NMMO. [DBNH][OAc], an amidine-based IL that has been so far adopted in Ioncell, has shown to dissolve 13 – 17 wt.% cellulose forming homogenous solutions that are adequate for a dry-jet wet spinning process (Asaadi *et al.* 2016; Ma *et al.* 2015; Sixta *et al.* 2015; Michud *et al.* 2016). The properties of the regenerated fibers (especially tenacity) exceeded in some cases other commercial Lyocell fibers (Hummel *et al.* 2015), which boosted the Ioncell technology to be recognized in various international events.

For Brønsted acidic ILs, the ionicity term describes the extent of proton transfer, and can be estimated by ΔpK_a that is the difference between the pK_a 's of the base and the acid. Previously, it was indicated that ILs with a ΔpK_a of 8 – 10 have ideal ionicity (Angell, Byrne & Belieres 2007). In the case of DBN and mTBD, the pK_a of mTBD in water is 13 – 15 (Hyde *et al.* 2019), and of acetic acid is 4.75, then a ΔpK_a of 8.25 – 10.25 can be estimated for the [mTBDH][OAc] IL revealing a high ionicity. The pK_a of DBN in water has not been reported yet but can be considered close to that of DBU (11.5 – 13.5) (Hyde *et al.* 2019), therefore the ΔpK_a of [DBNH][OAc] is about 6.75– 8.75. This approximation shows that [mTBDH][OAc] has a higher ionicity than [DBNH][OAc].

The high basicity of the guanidine- and amidine-based superbases arises from the sp^2 hybridization of the deprotonating nitrogen atom, resonance stabilization of the acid and a bicyclic ring system that enforces overlap of lone pair electrons at the sp^3 hybridized nitrogen(s) into the neighboring π^* orbital, thereby increasing electron density at the sp^2 -hybridized nitrogen.

3.3 Dissolution of Cellulose in ILs

When a polymer is placed in a solvent, the solvent molecules will readily contact the polymer and diffuse into its surface layer, disrupting its physical properties to a certain extent, while the solid structure remains unaffected (Lindman, Karlström & Stigsson 2010; Medronho & Lindman 2015). At this stage the polymer is swollen, and a gel-like structure is formed. Usually, the swelling behavior is followed by complete dissolution, where the polymer is molecularly dispersed. The Gibbs free energy of mixing is the driving force of dissolution, and

it is defined as the sum of the enthalpy (positive) and the entropy (negative) of the mixture before and after dissolution. For dissolution to take place, the free energy must be negative, otherwise a phase separation is induced between the polymer and the solvent.

Therefore, it is comprehensible that a gain in entropy is essential during the dissolution. It is more difficult to dissolve polymer of high molecular weight due to the low gain in entropy (Mai, Ahn & Koo 2014). Also, polymers that exhibit low conformational freedom have low gain in enthalpy and are thus less favorable for dissolution. For this reason, the flexibility of cellulose is minimized due to its fully equatorial β -linked glucopyranose units, which adds stability to its chair structure (Medronho & Lindman 2015).

The dissolution mechanism of cellulose in ILs is broadly the same as the NMMO case. For protic ILs, the anion readily forms new hydrogen bonds with the polar domain of the polymer (Figure 2), thus weakening the interactions among the cellulose chains (Xu, Wang & Wang 2010; Fukaya *et al.* 2008; Remsing *et al.* 2006; Swatloski *et al.* 2002). Although, the role of the base was not fully understood in the dissolution mechanism, some studies have revealed VanderWaals interactions taking place between the non-polar cellulose domain and the cation (Rabideau, Agarwal & Ismail 2014; Swatloski *et al.* 2002). Others have claimed that a hydrogen bond is established between the oxygen groups of cellobiose and the cation proton (Zhang *et al.* 2010).

Figure 2. Cellulose dissolution mechanism in protic ILs. Reprinted with permission from (Parviainen *et al.* 2013). Copyright (2020) John Wiley and Sons.

In IL synthesis, the H-bond basicity of the anion and the H-bond acidity of the cation are important terms to determine the gain in enthalpy upon the dissolution of cellulose (Novoselov *et al.* 2007). Cations of high H-bond acidity tend to compete with the polar OH-groups by donating hydrogen bonds to the anion (Parviainen *et al.* 2013; Novoselov *et al.* 2007). An empirical relation has been established using Kamlet-Taft solubility parameters (H-bond acceptor, β , and H-bond donor, α) to further understand the solvent capabilities towards cellulose (Hauru *et al.* 2012). Hauru *et al.* (2012) adopted the net basicity ($\beta - \alpha$) as

a function of β , as a term to classify ILs (Figure 3), showing a good cellulose dissolution window is in the range of $1.2 > \beta > 0.8$ and $0.9 > \beta - \alpha > 0.35$. According to Kuzmina *et al.* (2017), [DBNH][OAc] has a β of 1.17 and a $\beta - \alpha$ of 0.55, which fits in the cellulose dissolution window defined by Hauru *et al.* (2012).

Figure 3. Empirical Kamlet-Taft parameters $\beta - \alpha$ plotted against β for ILs, showing in the dashed box the region of good cellulose dissolution. Reprinted with permission from (Hauru *et al.* 2012). Copyright (2020) American Chemical Society.

The type of the anion and its influence on cellulose dissolution appears to have little debate in literature. Anions that are good hydrogen bond acceptors such as acetates, halides and phosphates perform better than weaker anions (Fukaya *et al.* 2008; Swatloski *et al.* 2002) such as dicyanamide (Xu, Wang & Wang 2010). In contrast, the structure of the base seems to be more complex as several parameters such as polarizability, hydrophobicity (Swatloski *et al.* 2002; Hauru *et al.* 2012) and the presence of functional groups including hydroxides (Feng & Chen 2008) and alkoxy groups (Zhao *et al.* 2008) can contribute to the state of dissolution

On the anion side, longer carboxylic chains inversely affect the solvent capability (Swatloski *et al.* 2002; Kuzmina *et al.* 2017). For example, only 0.8 wt.% cellulose dissolve in [DBNH]hexanoate, whereas 5.5 wt.% cellulose dissolved in [DBNH]butanoate and even 22 wt.% cellulose in [DBNH]acetate (Kuzmina *et al.* 2017). The same was found for elongating the side groups of the cation (Swatloski *et al.* 2002; Kuzmina *et al.* 2017) implying that ILs from derived DBN with an ethyl side group ([DBNET][OAc]) only tolerated 2.2 wt.% cellulose (Kuzmina *et al.* 2017). This confirms that the structure of both the anion and the cation plays an important role in cellulose dissolution.

3.4 Rheological Properties

The rheological properties of the cellulose dope provide information on the solution state, viscoelastic properties, molar mass distribution and relaxation of polymer chains. Frequency sweep tests can be used to easily measure the complex viscosity (η^*), the storage and loss moduli, G' and G'' , respectively. These properties reflect the viscoelasticity of the solution and are obviously dependent

on the temperature, the type of solvent, the cellulose concentration and the molar mass distribution. The Lyocell dopes are characterized by a Newtonian plateau in the η^* at low angular frequency (ω) < 0.01 , followed by a shear-thinning behavior at higher frequencies $100 > \omega > 0.01$ (Hummel *et al.* 2015; Sammons *et al.* 2008; Gericke *et al.* 2009). The transformation in η^* represents the realignment of the cellulose chains from random entanglements to a parallel orientation, which also reflects the change in the viscoelastic behavior of the solution. As the frequency increases, G' (elastic domain) increases, then intersects, and finally exceeds G'' (viscous domain) (Gericke *et al.* 2009; Sammons *et al.* 2008; Chen *et al.* 2009). The point of intersection of the two moduli is the cross-over point (COP).

The zero-shear viscosity (η_0) is obtained by calculating the limiting value from η^* using the Cross model. However, the assumption that the complex viscosity corresponds to the dynamic viscosity is only true if the Cox-Merz rule is valid: the complex and the dynamic viscosity as a function of shear rate and ω superimpose perfectly (Haward *et al.* 2012). Dopes of large cellulose concentration or DP exhibit a pronounced η_0 , but shear-thinning starts at relatively small ω (Sammons *et al.* 2008; Hummel, Michud & Sixta 2011; Chen *et al.* 2009). In the same manner, a large concentration triggers a pronounced elastic domain that prevails at a COP at a lower ω (Hummel, Michud & Sixta 2011; Michud, Hummel & Sixta 2015). On the other hand, an increase in the temperature is balanced by a drop in η^* , and a shift of COP to a larger ω (Michud, Hummel & Sixta 2015).

For the Ioncell solutions, it has been shown that the dopes are optimal for the dry-jet wet spinning process at η_0 of 20 000 – 35 000 Pa.s and COP of 2500 – 4000 Pa and ca. $1 \text{ s}^{-1} \omega$, which corresponds to a spinning temperatures of 70 – 80 °C (Asaadi *et al.* 2016; Michud, Hummel & Sixta 2016; Ma *et al.* 2016).

3.5 Dry-Jet Wet Spinning

Figure 4 illustrates a dry-jet wet spinning process. After filtration, the cellulose solution is split into smaller dopes depending on the production capacity. The solution is then supplied by a gear pump to the spinnerets, each consisting of hundreds to thousands of holes with a diameter between 50 and 150 micrometers through which the solution is extruded and regenerated in an aqueous coagulation bath. Throughout this process, spinning godets apply longitudinal stretching forces on the cellulose solution in the spinneret capillaries, air-gap and the first section of the coagulation until complete fiber regeneration takes place. The solid fibers are then collected on the godets after exiting the coagulation bath.

Figure 4. A schematic drawing of the dry-jet wet spinning process

While travelling through the spinneret capillaries, the shaping of the cellulose solution takes place and the polymer chains undergo structural pre-orientation as a result of the uni-axial shear forces (Fink *et al.* 2001). Immediately after exiting the capillary, the shear forces disappear and an instant relaxation in the chains occur that increases the fluid diameter. This phenomenon is known as die swell (Fink *et al.* 2001; Ziabicki 1976), and is compensated by the stretching from the godets. In the air-gap, an extensional flow of the cellulose solution is created by the godets, causing further alignment of the polymer chains.

The air-gap is one of the most significant factors, when it comes to spinnability and fiber properties. Dependent on the viscoelastic properties of the spin dope, several fracture mechanisms can be triggered that rupture of the spun filaments. Capillary fractures usually occur as a result of strong longitudinal waves that distort the extruded solution. Optimizing the spinneret diameter or the extrusion velocity can control the amplitude of these waves (Ziabicki 1976; Ziabicki & Takserman-Krozer 1964b). Melt fractures are another type of breakages that are characterized by an irregular flow of the viscoelastic solution through the spinneret capillary. Under critical shear rates, the threads become rough and irregular, thus easily broken (Ziabicki 1976). Hence, the viscoelastic parameters (e.g. dynamic viscosity) of the spun solution and the applied temperature can affect this phenomenon. In addition to the previous types, cohesive fractures can take place when the tensile stress in the viscoelastic solution exceeds the critical tensile strength. An increase in tensile stress can be a result of a small filament diameter, high godet speed or high spinning temperatures (Ziabicki & Takserman-Krozer 1964a; Ziabicki & Takserman-Krozer 1964b).

A phase transfer to the regenerated cellulose fibers occurs in the coagulation bath by the diffusion of the non-solvent (water) into the dope, the simultaneous diffusion of the solvent molecules into the coagulation bath (Coulsey 1995). The cation hydrophilicity facilitates the re-formation of hydrogen bonds between the anion and the water (Hauru *et al.* 2012). Consequently, a liquid core is formed, which upon further diffusion, leads to the fortification of a lamellar crystalline structure (Coulsey 1995). Recently, the initiation of the coagulation process has been characterized by density fluctuations, most likely caused by spinodal decomposition (Nishiyama *et al.* 2019).

The degree of crystallinity is little influenced by the draw ratio, but mainly by the choice of the spinning bath medium. As indicated before, the structure formation is largely a factor of the diffusion coefficient, implying that strong anti-solvents, e.g. water, or elevated coagulation temperatures allow fibers of higher crystallinity to form, while mild anti-solvents such as alcohols may yield fibers of lower crystallinity. Slow diffusion speeds therefore also contribute to a better elasticity, which is more prone to withstand deformation (Fink *et al.* 2001).

Besides shear forces, deformation in the spinning process also results from the draw ratio applied. The draw ratio describes the relation between the take-up speed of the godets and the extrusion velocity of the filaments at the spinning cylinder (Michud *et al.* 2016). In dry-jet wet spinning, high draw ratios are usually required to reduce the fiber diameter and to enhance the tensile strength of the fibers. Michud *et al.* found that the fiber orientation gradually increases with the draw ratio until a plateau is reached at a value no bigger than 6 (Michud, Hummel & Sixta 2015).

3.6 Methods for IL Recycling

In industry, ILs are utilized in a variety of applications that inevitably necessitate an efficient separation and recycling mechanism for economical and environmental reasons. ILs are known for their relatively high cost compared to molecular solvents, which makes their high recovery a major concern. However, in the future, the cost of ILs synthesis is expected to drop along with the on-going developments that will trigger higher production levels. An overview of the recycling techniques of ILs from various products can be viewed in (Abu-Eishah 2011; Sklavounos *et al.* 2011). In this section, we focus on the recycling strategies of ILs in the Lyocell process. Typically, after fiber spinning, the coagulation bath solution and the washing liquors are combined and first subjected to several purification steps, such as filtration and flotation, to remove tiny particles and colloidal precipitates, e.g. inorganics and biopolymers. Thereafter, the removal of water takes place in order to restore the IL solvation power. Theoretically, there are several separation methods available for the water removal from ILs such as adsorption, liquid-liquid extraction, thermal evaporation, membrane processes, freeze crystallization, and aqueous biphasic systems, yet, only few of these methods can be adopted in the Ioncell technology. It is important to distinguish between the removal of the major part of water, 10 wt.% and higher, and the residual water (< 10 wt.%), since the removal of the major amount of water is relatively easy and may not compromise the quality of the IL.

During recovery, ILs exhibit different interactions based on the molecular size, structure and the hydrophobicity of the IL, which plays an important role particularly for the recovery from aqueous mediums. The adsorption method can be used to separate IL-water solutions. However, most of the studies were done on removing the IL from the water and not vice versa (Blanchard *et al.* 1999; Anthony, Maginn & Brennecke 2001; Lemus *et al.* 2012). This is comprehensible since large amounts of the sorbent, e.g. activated carbon, will be required in case the amounts of water were significant. Hence, this method is only suitable

for removing the residual water. Another important aspect is the hydrophilic nature of the superbase ILs, which may leave a fraction of the IL attached along with the water, thus reducing the separation efficiency (Palomar *et al.* 2009). Also, the long residence times and drastic process temperatures that are usually required during adsorption and regeneration may induce degradations in the ILs and create further losses in the solvent. This was confirmed in the SolvRec project (unpublished results), while using silica zeolites to lower the residual water content from a 14 wt.% aqueous [DBNH][OAc] solution to about 3 wt.%, around 11 wt.% of hydrolysis products were detected.

Liquid-liquid extraction is based on the non-miscibility of ILs with molecular solutions. In fact, hydrophilic ILs can be extracted by water from hydrophobic systems (Huddleston *et al.* 1998). This technique is also frequently applied to extract thermally sensitive components (Zhao, Xia & Ma 2005). A recovery of 89 wt.% was concluded for the separation of 1-ethyl-3-methylimidazolium acetate ([emim][OAc]) from pre-treated biomass by using a solvent mixture containing acetone, isopropanol and small amounts of water (Dibble *et al.* 2011). In the scope of the Lyocell solvents, the introduction of a new component to extract the IL will increase the complexity of the recycling process, and compromise the green tag associated with Lyocell chemicals.

On the other hand, separating IL-water systems *via* the evaporation of the latter has already provided promising results (Parviainen *et al.* 2015; King *et al.* 2011; Ostonen *et al.* 2016). Originally, thermal treatments were studied for the distillation, and consequently purification, of ILs. Earle *et al.* (2006) reported the distillation of aprotic ILs at elevated temperatures (300 °C) and reduced pressures (0.1 – 0.6 mbar), although these conditions were high enough to initiate the thermal decomposition of the IL. Nowadays, thermal evaporation is being used to recover ILs from aqueous solutions. It is a simple method that relies on the difference between the low vapor pressure of the ILs and the greater volatility of water. Yoshizawa *et al.* (2003) have correlated the rise in the boiling point temperature to the ΔpK_a of the salt; A large ΔpK_a requires high energy for vaporization. Although this technique may require a high energy input, it has been adopted industrially in the NMMO process achieving > 99 % recovery (Potthast *et al.* 2002; Rosenau *et al.* 2001). As promising as it sounds, ILs may undergo thermal decomposition and undesired-side reactions when exposed to intense temperatures (Parviainen *et al.* 2015; King *et al.* 2012). This will be further outlined in the next section.

Membrane techniques such as pervaporation are best applied only for the removal of the residual water, while they have limited usability when the water content is too high. Schäfer *et al.* (2001) reported evident recovery rates (~ 99 %) of imidazolium-based IL from water. However, this method requires solutions of low viscosity in combination with an elevated temperature (100 °C) and long treatment times (5 hr) (Schäfer *et al.* 2001; Sun *et al.* 2017), and therefore is unviable for ILs that are prone to hydrothermal degradations. Freeze crystallization is also a convenient technique for separating solids and removing the residual water from the IL, while avoiding solvent losses (Su *et al.* 2010; Choudhury *et al.* 2005). Unfortunately, the sole reliance on crystallization to

achieve a full recovery of dilute IL solutions might not be feasible, since preliminary solid-liquid equilibrium data revealed the need of extremely negative temperatures, ca. - 75 °C for a coherent separation (Osmanbegovic *et al.* 2020).

Hydrophilic ILs were found to create an aqueous biphasic system (ABS) when a kosmotropic salt such as potassium phosphate (K_3PO_4) was introduced (Gutowski *et al.* 2003). The ABS consisted of an IL-rich upper phase and a K_3PO_4 -rich lower phase made of hydrates. The separation efficiency was improved when the concentration of the added salt increased (Gutowski *et al.* 2003; Deng *et al.* 2009). This phenomenon is known as salting-out, and it follows the Hofmeister series (Dupont, Depuydt & Binnemans 2015), which originally ranked the strength of ions to precipitate proteins. Recently, the formation of the hydrate complexes was revealed to be favored because of the increase in the entropy of hydration (Shahriari *et al.* 2012). ABS separation method can be considered as one of the alternative ways to remove water, yet it also adds another challenge to the recycling process in the separation of the kosmotropic salt from the IL.

When constructing the optimum recycling strategy for the Ioncell solvent system, combining one or more separation method may be of a higher benefit. For instance, an evaporation system for IL preconcentration followed by crystallization, or a combined evaporation - pervaporation system. In the work herein, we selected vacuum evaporation as the recycling route, because it is the least complex method, and eliminates any introduction of additional chemicals. Furthermore, multiple-effects evaporators have a better specific energy advantage than other methods. Meanwhile, we could optimize the generation of undesired-side products, and induced alterations in the solvent composition. Also, as mentioned above, this method has already proven its success in the recovery of NMMO, thus it appeared useful to establish a point of reference for the Ioncell process.

3.7 Properties of Superbase-based ILs During Thermal Recovery

For fully ionic compounds, strong cohesive forces result from extensive interacting charges. Typically, ionic bonds are characterized by very strong Coulombic forces due to the high magnitude of the charges and the very short bond length ($< 2 \text{ \AA}$). On the other hand, the hydrogen bond in ILs operate on a few Ångströms ($2.8 - 3.5 \text{ \AA}$), and hence the low melting point. Nevertheless, in ILs, the ions experience interactions with the neighboring ions up to the third solvation shells (Sklavounos *et al.* 2011). Therefore, it takes a lot of energy to overcome the cohesive charge network during evaporation, which is reflected in the low vapor pressure of ILs.

As aforementioned, the recovery of IL from the water coagulation bath takes place *via* the evaporation of the latter, which is usually achieved at elevated temperatures and reduced pressures. Surely, the vapor pressure of the system reduces gradually while water is being removed. Baird *et al.* (2020) has shown for an aqueous [mTBDH][OAc] system at 350 K, around 115 mbar pressure corresponded to a water content of 20 wt.%, the vapor pressure dropped to about 25

mbar when the water content was 5 wt.% (Figure 5 a). Under such elevated conditions, a fraction of IL can vaporize during the removal of water. The mechanism of evaporation was explained by the initial dissociation (de-ionization) of the ionic compounds into neutral acid and base, $[BH][A]_{liq} \rightarrow [B]_{liq} + [AH]_{liq}$, which are more prone to vaporization because of their weak interactions, $[B]_{liq} + [AH]_{liq} \rightarrow [B]_g + [AH]_g$ (Ribeiro *et al.* 2017). Interestingly, although the acid has a higher volatility than the base, it was found that the base is more prone to vaporization from concentrated solutions (Ribeiro *et al.* 2018; Ahmad *et al.* 2016). This is a result of the tendency of the acid to form hydrogen bonds with the IL in the liquid phase, protecting it from vaporization (Ribeiro *et al.* 2018). Under more drastic conditions, this phenomenon proceeds until an azeotropic composition is reached, where the system exhibits the best thermal stability (lowest vapor pressure) as noted in Figure 5 b (Baird *et al.* 2020; Ribeiro *et al.* 2018). Despite this, a build-up of neutral acid in the solvent system is undesired because the solvent strength is rather attributed to the presence of an equimolar ratio of anions and cations.

Figure 5. a. Vapor pressure for aqueous [mTBDH][OAc] of 1:1 ratio at different temperatures. b. Vapor pressure of the aqueous [mTBDH][OAc] as a function of composition. Figures reprinted with permission from (Baird *et al.* 2020). Copyright (2020) American Chemical Society.

For ILs of the same anion, the extent of the azeotropic composition can be directly related to their ionicity (Ribeiro *et al.* 2018; Ribeiro *et al.* 2017). ILs of high degree of ionization require higher energy to dissociate and evaporate. Since mTBD is a stronger base than DBN, the azeotropic composition of [mTBDH][OAc] is 3/2, which is less than the 5/3 of [DBNH][OAc] (Ahmad *et al.* 2016; Baird *et al.* 2020), reflecting a better thermal stability of the guanidine-based IL. In the Lyocell process, the vaporized stream containing traces of IL compounds is condensed and can be further utilized as a first fiber washing step or recycled back to the coagulation bath to avoid solvent losses.

Apart from the specific component vaporization, the presence of water may trigger nucleophilic reactions that cleave the unsaturated N–C bond in the amidine- and guanidine-based ILs (Hyde *et al.* 2019), producing undesired hydrolysis products. This is induced at elevated temperatures. In a continuous Lyocell process, the accumulation of such hydrolysis products in the solvent will undeniably threaten the feasibility of the process, since large make-up IL will be required. For [DBNH][OAc], the hydrolysis reaction produces the primary amine 1-(3-aminopropyl)-2-pyrrolidonium acetate ([APPH][OAc]), which under more drastic conditions may condense through an irreversible acetylation reaction yielding 1-(3-acetamidopropyl)-2-pyrrolidone (APPAc) (Parviainen *et al.* 2015). Similarly, for [mTBDH][OAc], a mixture of 1-[3-(methylammonio)propyl]-1,3-diazinan-2-onemium acetate [H-mTBD-1][OAc] and 1-(3-ammonio)propyl-3-methyl-1,3-diazinan-2-onemium acetate [H-mTBD-2][OAc] is produced, which may also condense to 1-[3-(acetamido)propyl]-1,3-diazinan-2-one (A-mTBD-1) and 1-[3-(acetamidopropyl)-3-methyl-1,3-diazinan-2-one (A-mTBD-2), respectively (Hyde *et al.* 2019). Figure 6 displays the hydrolysis pathways of [DBNH][OAc] and [mTBDH][OAc].

Figure 6. Hydrolysis pathways for [DBNH][OAc] and [mTBDH][OAc].

In a study by Hyde *et al.* (2019), the extent of hydrolysis for the guanidine-based superbases 1,5,7-Triazabicyclo[4.4.0]dec-5-ene (TBD) and mTBD was compared to the amidine-based superbases 1,8-diazabicyclo[5.4.0]undec-7-ene

(DBU) and 1,5-diaza-bicyclo[4.3.0]non-5-ene (DBN). Mainly, the guanidine-based superbases exhibited greater resistance to hydrolysis than the amidine-based ones, which is associated with the higher electron density at the sp^2 -hybridized carbon of the guanidine (Hyde *et al.* 2019), and the presence of higher amount of ionic species. On the other side, a fast cleave of the of the ring strain takes place in DBU and DBN, observed in the small ΔG of -6.2 and -8.3 kcal/mol, respectively, thus creating their primary amines (Hyde *et al.* 2019). Consequently, the hydrolysis rate was fastest for DBN > DBU > mTBD > TBD (Hyde *et al.* 2019). Although mTBD does not show the highest tolerance towards hydrolysis, especially compared to TBD, its lower melting point (17°C) makes it more favorable for the conversion to an IL with excellent dissolving properties of cellulose.

3.8 Impurities and Side-Products in Ioncell

The presence of impurities in the solvent and the solute, besides the degradations occurring in the Ioncell process, will alter the composition of the solvent mixture. Unlike NMMO-based Lyocell, which requires stabilizers, the IL-based Lyocell does not need any extra chemicals, which simplifies the tracing of the possible degradations.

On the solute side, impurities may originate from the raw materials (e.g. pulp and waste textile) in the form of inorganics, ash, residual hemicelluloses and lignin. At small inorganic concentrations, ions of high charge density (e.g. calcium) may overcome the polarity of the IL, and trigger ion-exchange reactions that will undoubtedly modify the behavior of the solvent (Dupont, Depuydt & Binnemans 2015). At noticeable concentrations and in the presence of water, the inorganic salts may interact with the water causing the salting-in/out phenomena for the ILs (Ventura *et al.* 2009; Gutowski *et al.* 2003). Hemicelluloses, e.g. xylan, can be dissolve in ILs at moderate concentrations (Roselli 2017), but it is expected that they precipitate in the coagulation bath during spinning. Meanwhile, a certain amount of lignin can be utilized during the spinning process if carbon fibers are desired (Le *et al.* 2020; Ma *et al.* 2015). Beside impurities, one can expect minor losses in the degree of polymerization (DP) of cellulose over the dissolution and regeneration stages (Parviainen *et al.* 2015). Since, in the presence of water, the unconjugated superbases create an alkaline environment, which in turn, at higher temperatures, lead to alkali-induced peeling reactions, thus degrading sugars from the reducing end and producing carboxylic acids.

In the NMMO process, batteries of cation and anion exchangers are installed to remove the charged solute degradation products such as salts and carboxylic acids, however this is not convenient for ILs due to their ionic nature. In our trials, we were not able to analytically quantify the amounts of solute-based impurities in the system due to the small-scale of operation, and therefore they were not part of this work. Although, they did not affect the stability of the process, yet in the future, it is critical to develop specific purification techniques for a continuous process.

On the solvent side, impurities are traced back to the superbase synthesis process. One example is the appearance of traces of the precursor TBD in mTBD. The synthesis process proceeds *via* the methylation of TBD using an alkylating agent such as dimethyl carbonate (Welter 2012). After the reaction is completed, the product (mTBD) is distilled out of the system (Welter 2012), though fractions of TBD may still reside with the final superbase. TBD per se is a superbase, but only a certain content of TBD can be accepted since its elevated melting point necessitates intense processing temperatures. The precursor of DBN is a lactam (Welter 2012), which is an impurity as it is not a cellulose solvent and therefore should only be present in DBN in minimal amounts.

Additionally, the solvent deviations taking place during the thermal recovery negatively affects the solvent system. For instance, the hydrolysis reaction consumes the superbases, and therefore requires a make-up. Parviainen *et al.* (2015) correlated the diminishing solvation power of a recovered [DBNH][OAc] towards a 7 wt.% cellulose with the accumulated content of [APPH][OAc]. Also, the strong hydrogen-bond acidity of the residual water in the recovered solvent may induce the anion solvation of the IL (Zhao *et al.* 2013; Liu *et al.* 2011), thus diminishing its basicity and causing the IL to exit the dissolution window defined earlier (Hauru *et al.* 2012). Figure 7 trace the effect of water in decreasing the Kamlet-Taft terms. Similarly, the build-up of excess acetic acid (from the base vaporization) is also undesirable, as it is not a cellulose solvent and can form hydrogen bonds with the IL that may conflict with the cation-cellulose interactions.

Figure 7. Effect of water on the Kamlet-Taft parameters of the solvents. Reprinted with permission from (Hauru *et al.* 2012). Copyright (2020) American Chemical Society.

It is therefore clear that the increase in one or more of the previous factors can compromise the dissolution quality. Herein, we identify the main parameters influencing the solvent power as water, hydrolysis products and A/B molar ratio. For simplification, we refer to them later in this work as solvent alterations.

4. Experimental

4.1 Cellulose, Ionic Liquids and Other Raw Materials

Cellulose of an ECF bleached birch prehydrolysis kraft pulp (Pure by Stora Enso, Enocell mill, Uimaharju, Finland) was used as the sole biomass source throughout this research. The pulp (Enocell) was delivered in the form of pulp sheets and ground in a Wiley mill to 0.5 mm prior of usage. The pulp dry mater content (D.M.C.) was 94.5 – 95.5 wt.%. The intrinsic viscosity of Enocell was 494 ml/g, while the main characteristics are available in Table 2.

Table 2. Enocell pulp sugar analysis, brightness and molar mass distribution.

	Cellulose	Hemicelluloses (C5+C6)	Lignin	ISO-brightness	M _n	M _w	PDI	DP > 2000	DP < 100
	%	%	%	%	kDa	kDa	-	%	%
Enocell pulp	92.7	6.8	0.5	89.9	44.5	160.5	3.6	12.2	4.8

The superbases were received as follows: DBN (99 %) from Fluorochem, UK and DBU (98 %) from Merck, Germany. mTBD was received from different suppliers due to its limited availability, **Paper I & III** and **A.T. 1 & 2** (98 %, BOC Sciences, USA), **Paper II** (99 %, University of Helsinki, Finland). [emim][OAc] (> 95 %) was available from Merck, Germany. In addition to the ILs, NMMO·H₂O (98%, Alfa Aesar, Germany) was purchased and used as such. University of Helsinki, Finland supplied the hydrolysis products of [mTBDH][OAc], [ΣH-mTBD][OAc], which comprised of ~90 mole% [H-mTBD-1][OAc] and ~10 mole% [H-mTBD-2][OAc]. Likewise, it supplied the [APPH][OAc]. TBD of 99.2 % purity was available from BOC Sciences, USA and used as such. Table 3 summarizes all the main materials and additional components per publication / **A.T.**

Table 3. List of raw materials per set of trials.

Publications and trials	Materials	
	Cellulose & ILs	Additional components
Paper I	<ul style="list-style-type: none"> Enocell pulp Fresh [mTBDH][OAc] 	-

Paper II	<ul style="list-style-type: none"> • Fresh [DBNH][OAc] • Fresh [DBUH][OAc] • Fresh [emim][OAc] • Fresh NMMO·H₂O • Enocell pulp • Fresh and recovered [mTBDH][OAc] • Fresh and recovered [DBNH][OAc] 	-
Paper III	<ul style="list-style-type: none"> • Enocell pulp • Fresh [mTBDH][OAc] • Fresh [DBNH][OAc] 	<ul style="list-style-type: none"> • [ΣH-mTBD][OAc] • TBD • Acetic acid • mTBD • [APPH][OAc] • H₂O
A.T. 1	<ul style="list-style-type: none"> • Enocell pulp • Fresh [mTBDH][OAc] 	-
A.T. 2	<ul style="list-style-type: none"> • Enocell pulp • Recovered [mTBDH][OAc] 	-

4.2 Methods

4.2.1 IL Synthesis

Synthesis of equimolar ILs took place *via* adding stoichiometric glacial acetic acid (100%, Merck, Germany) to the respective base in a controlled temperature glass reactor. To avoid IL crystallization during solvent synthesis, the vessel temperature was kept at 70 °C for [DBNH][OAc], [DBUH][OAc] and 80 - 90 °C for [mTBDH][OAc]. After all the acid was added, the reactor continued stirring at the corresponding temperature for an additional 60 min to ensure complete reaction.

4.2.2 Cellulose Solution Preparation

In general, the protocol for dope preparation was almost the same in all trials. Only minor variations existed as specifically indicated in the later section. Initially, the IL bottles were melted in a water bath at 80 – 85 °C for 2 hours. Thereafter, the liquid solvent was poured into a vertical kneader to which Enocell pulp of 13 wt.%, total mass, is later added. Table 4 includes the applied kneader conditions during cellulose dissolution for the fresh as well as the recovered solutions. The purpose of vacuum, shown in Table 4, is to eliminate entrapped air bubbles from the solution.

Table 4. Kneader conditions for cellulose dissolution in the Lyocell solvents.

Solvent	Condition	T °C	Pressure mbar	Time min	Mixing speed rpm
[mTBDH][OAc]	Fresh	85	11-20	90	30
	Recovered	75 - 85	11-20	75	30
[DBNH][OAc]	Fresh	80	11-20	90	30
	Recovered	80	11-20	75	30
[DBUH][OAc]	Fresh	95	20	90	30
[emim][OAc]	Fresh	80	20	90	30
NMMO·H ₂ O	Fresh	95	20	90	30

Shortly after kneading, the homogeneous cellulose solution is filtrated in a hydraulic press filtration system (150 – 200 bar, metal filter fleece, 5 – 6 μm absolute fineness). Finally, the clear solution is shaped to a mold (adequate to the spinning unit cylinder), wrapped against moisture and stored in a cool dry place. Figure 8 displays the steps of dope preparation.

Figure 8. Steps of dope preparation. **a.** IL and cellulose mixture before dissolution. **b.** Homogeneous cellulose solution after kneading. **c.** Dope filtration. **d.** Dope shaping for spin unit dimensions.

In **A.T. 1**, using [mTBDH][OAc], a 12 and 14 wt.% cellulose solutions were prepared on top of the standard 13 wt.% solution. In the same trials, a 13 wt.% cellulose dope was prepared under atmospheric pressure. In **A.T. 2**, using [mTBDH][OAc], the prepared dopes were not filtrated prior to spinning.

Cellulose Dissolution Study in Presence of Solvent Alterations

In **Paper III**, additional components were introduced to the [mTBDH][OAc] and [DBNH][OAc] ILs in order to mimic the alterations in the solvent composition taking place during solvent thermal recovery, and therefore monitor the dissolution capability of the adjusted solvent towards cellulose. These alterations composed of hydrolysis products, changing the A/B ratio and water. A list of the added components is summarized in Table 5. Based on the findings of these trials, certain dopes were selected for the fiber spinning process.

Table 5. Concentration of solvent alterations in [mTBDH][OAc] and [DBNH][OAc].

IL	H ₂ O*	Hydrolysis products*	A/B molar ratio*	[TBD][OAc]**
	wt.%	wt.%	-	wt.%
[mTBDH][OAc]	1 – 10	0 – 40	0.8 – 1.6	up to 30
[DBNH][OAc]	1 – 7.5	0 – 20	1 – 1.2	-

*The percentages are solvent-based

**Added individually with no other components than the IL.

[mTBDH][OAc] alterations. For the dissolution trials in [mTBDH][OAc], only small amounts of dope of 25 g were prepared because of the costly price of the base (~ 4000 € per kg) and the numerous experiments planned. As explained in **Paper III**, a Box-Behnken design of 27 experiments was utilized when planning for these trials. The design aimed to study the combined effect of H₂O, [ΣH-mTBD][OAc] and different AcOH/mTBD ratio when present in the IL. Also, the dissolution time (30 – 120 min) was also taken into consideration. The dissolution conditions were 85 °C, 30 rpm and 15 mbar. The role of TBD was similarly studied for cellulose dissolution. But TBD was solely introduced with no other alterations. Cellulose dissolution took place at 85 °C, 30 rpm and 15 mbar.

Another set of trials was performed under atmospheric conditions to further clarify the contribution of pressure during cellulose dissolution, also described in **Paper III**. However, the fiber spinning of these dopes was not carried out because the role of vacuum is essential for removing air bubbles and homogenizing the dope. This is particularly important when elevated solvent alteration exist, which might create inhomogeneous solutions.

Using Axio Zeiss A1 optical light microscope, several images were taken in polarized mode in order to quantify the extent of dissolution (Elsayed *et al.* 2020b).

[DBNH][OAc] alterations. The protocol for [DBNH][OAc] was different since DBN is more prone to hydrolysis (in the presence of water), and in **Paper II** showed lower tolerance to side-products (Elsayed *et al.* 2020a). For these reasons, it was preferred to introduce the H₂O, [APPH][OAc] and different

AcOH/DBN ratios, in small incremental steps individually and as combined parameters to explore both scenarios. In order to limit the undesired side reactions, we initiated and monitored the cellulose dissolution in the heated stage (80 °C) of the Axio Zeiss A1 optical light microscope to minimize the dissolution sample, which significantly shortened the dissolution time to around 9 min (Elsayed *et al.* 2020b).

4.2.3 Fiber Spinning

To simplify the fiber spinning protocol in this thesis, it is easier to allocate the different trials to the corresponding fiber spinning units as seen in Table 6. Two customized dry-jet wet piston spinning units (Fourné Polymertechnik, Germany) were available, KS-80 of 2.5 L and KS-15 of 0.1 L.

Table 6. Allocation of the trials to KS-80 and KS-15.

Publication and trials	Spinning unit	Spinbath solution recovery
Paper I	KS-80	No
Paper II	KS-80	Yes (5 cycles for [mTBDH][OAc] and 1 cycle for [DBNH][OAc])
Paper III	KS-80 and KS-15	No
A.T. 1	KS-80	No
A.T. 2	KS-15	Yes (20 cycles)

Trials with the KS-80 Fiber Spinning Unit

The filtrated and solidified (from storage) dope was first placed into the spinning cylinder and melted over a period of 2 – 3 hours. Usually, the applied temperature was set to the spinning temperature + 5 – 10 °C. After melting, the piston unit was set in motion to extrude the cellulose solution through the spinneret holes into the air-gap and finally into the water coagulation bath (110 – 125 L), where the fiber regeneration took place (Figure 9). An axial draw force was applied to the fibers by spinning godets, which stretched the fibers dominantly in the air-gap and in the subsequent coagulation phase until complete regeneration occurred. The regenerated fibers were finally collected on the spinning godets.

Figure 9. KS-80 spinning unit.

The spinning temperature corresponded to a η_0 of 20 000 – 35 000 Pa.s, which throughout the different trials matched 80 – 95 °C. For all trials, a spinneret of 200 holes x 100 μm diameter and length-to-diameter (L/D) ratio of 0.2 was used, except for one spinning trial in **A.T. 2** where a 400 holes spinneret (with the same hole dimensions) was utilized. The extrusion speed (V_e) was 3.5 – 5.5 m/min. The air-gap was set to 1 cm and the bath temperature was fixed at 10 – 12 °C. The draw ratio (DR) is the ratio of the godet speed to the extrusion speed. The term maximum draw ratio (DR max) was given to the DR at which the spinning process can proceed for ≥ 5 min without breakages and beyond which complete breakages are triggered. Commonly, a DR of 11 – 12 was needed in order to yield fibers of textile properties (~ 1.3 dtex) at the given spinning conditions. In other cases, to test the spinnability of the dope, we reached the DR max as in the case of **Paper III**.

After the spinning procedure came to an end, the collected fibers were instantly cut to 4 cm pieces. Following this, the fibers were washed for 2 hours at 70 °C, while changing the water to fresh at half-time.

Trials for KS-15 Fiber Spinning Unit

The spinning capacity of the KS-15 unit was 0.1 L. For this volume, we utilized a single-hole spinneret to spin valuable dopes and for trials with many recovery cycles, which was the case for dopes from [mTBDH][OAc] in **Paper III** and **A.T. 2** (20 recovery cycles). Using this setup, dopes of only 15 – 25 g were sufficient for the spinning process. This allowed the use of a substantially smaller spinbath of 4 L. The setup of KS-15 spinbath (Figure 10), portrayed in our recent publication (Guizani *et al.* 2020), enabled the fiber to freely flow from the immersion to the exit positions as a result of a drag force exerted by the water. The difference in elevation between the exit and immersion positions, the former being slightly shorter, created a constant movement of water inside the bath, which even accelerated in the lower tube because of the smaller cross-sectional

area. Outside of the bath, an external godet is placed to stretch the fibers for a higher DR.

Figure 10. KS-15 unit with additional IL in spinbath.

The air-gap and bath temperature were 1 cm and 10 – 12 °C, respectively. The single-hole spinneret was of 100 μm diameter and L/D ratio of 2, and the extrusion speed was 1.3 m/min. Both the spinneret and the extrusion speed were constant in all runs. Likewise, the DR was increased to 12 or to DR max according to the purpose of the spinning process. The spinning temperature ca. 85 °C of the [mTBDH][OAc] dopes was equivalent to η_0 of 25 000 – 35 000 Pa.s.

In **A.T. 2**, an additional [mTBDH][OAc] was added to the spinbath (10 – 40 wt.%) during spinning to test the spinnability of [mTBDH][OAc] dopes in aqueous solutions of 20 wt.% [mTBDH][OAc]. This IL also served as a make-up to compensate for the combined losses accounting from the solvent residues in the spinbath and the thermal recovery stages.

After spinning, the collected fibers were cut and washed in the same way as explained earlier.

Fiber Spinning Troubleshooting

The lab scale fiber spinning is a sensitive procedure, involving multiple parameters that may compromise the stability of the process. Thus, it takes time for the personnel to master this technique. In this section we summarize few of the common problems that might arise during batch spinning.

Of course, all the aforementioned conditions (spinning temperature, spinbath temperature and air-gap distance) are important to be kept within minor fluctuations. However, other factors are also essential to be checked. The spinneret holes must be kept clean with no residues from previous spinning occasions.

This can be done by immersing the spinneret, directly after spinning, in an ultrasonic bath for few hours then using pressurized air to remove micro-regenerated particles. The acceleration during increasing the DR has to be in a small stepwise manner rather than big leaps. The center point of the spinneret must vertically coalign with the breaking roller/plate in the spinbath. It is advisable to sandpaper the breaking roller/plate regularly to reduce friction.

In some occasions, increasing the spinning temperature can minimize the formation of agglomerates. In other occasions, the filaments are broken with the least applied draw. This usually reflects a high spinning temperature and requires cooling of the dope. Also, increasing the piston extrusion speed can sometimes help. Often, when the dope is about to end, entrapped air between the piston and the head of the spinning solution diffuses through the spinneret holes, which destroys the filaments and leads to total breakage.

4.2.4 Spinbath Recycling

Prior to recycling, the spinbath solution was first filtrated by a filter paper of 12 – 15 μm particle retention size (VWR). The recovery of the IL from the water took place through successive thermal treatments. An overview for the process including the recycling steps as adopted in **Paper II** is sketched in Scheme 1. In general, the large volume of the spinbath solution from the KS-80 spinning process, and the substantially insignificant IL concentration in the spinbath, required a pre-concentration evaporation step. An available centrifuge evaporator (Alfa Laval Centritherm) was used to concentrate the solution at a 50 kg/hr flowrate. The internal evaporator conditions were 400 rpm, 62 °C and 250 mbar. Due to the large amount of the distillate stream, containing only traces of IL as explained in Chapter 5.3, it was disposed with no further recycling. Meanwhile, the residue streams (IL-rich) were collected and further concentrated in a two-stage agitated thin-film evaporator (UIC GmbH, RF10) (TFE-1 and TFE-2) displayed in Figure 11. The heating jacket was made of stainless steel of a 0.1 m² area of heat transfer. A condenser was installed after each TFE to recovery the distillate stream and recycle it to the spinbath of the following cycle.

Scheme 1. General overview of the process showing cellulose dissolution, spinning of regenerated fibers and recycling of the diluted IL.

Figure 11. Thin-film evaporator unit

In **A.T. 2** (KS-15 trials), the spinbath concentration was adjusted to 20 wt.% IL during spinning. This and the fact that the spinbath volume is only 4 L made the pre-concentration step in the centrifuge evaporator unnecessary.

Table 7 shows the temperature and pressure used in the TFE-1 and TFE-2. The pump flowrate and agitation speed were fixed to 3.5 kg/hr and 400 rpm, respectively. Directly after the TFE, a condenser at 2 °C was fixed to condense and trap the vapor stream from the evaporator. Also, a cold trap containing liquid nitrogen was installed and utilized for the safety of the vacuum pump. The IL finally recovered from TFE-2 was recycled back to be used for the dissolution of 13 wt.% cellulose in the following cycle.

Table 7. Conditions of the thin-film evaporators (TFE).

Trial	IL	Number of cycles	Feed Temperature °C	TFE-1		TFE-2	
				Temperature °C	Pressure mbar	Temperature °C	Pressure mbar
Paper II	[mTBDH][OAc]	5	22	61	20	82	17
	[DBNH][OAc]	1	22	61	20	75	17
A.T. 2	[mTBDH][OAc]	20	22	61	20	82	17

4.2.5 Dress Making

The suitable fibers spun from the dopes of fresh and recovered [mTBDH][OAc] were combined to prepare a demonstration dress designed and executed by Marimekko Oy, Finland. The fibers of the dress comprised 38 wt.% Ioncell fibers, weft, and 62 wt.% warp Tencel fibers. It was essential to incorporate Tencel fibers since the weaving mill (Söktas Tekstil A.Ş, Turkey) operates on industrial capacities, and therefore requires large amount of fibers for the process of the machines.

Spin and Yarn Finishing

The spin finishing of the Ioncell fibers was carried out with a mixture of Afilan CVS:Leomin PN (80:20) (Archroma, Switzerland) of 0.83 g/L in the treatment bath and 20:1 liquor-to-dry fiber ratio. The treatment lasted for 5 min at 50 °C. Thereafter, the fibers were pressed to 0.25 % spin finish before air-drying. Next, the dry fibers were opened using fiber opener Trash Analyzer 281C Mesdan Lab, Mesdan S.p.A., Italy, and conditioned over night at 20 °C and 65 % relative humidity.

For yarn spinning, 25 g fiber batches were carded using Carding Machine 337A, Mesdan Lab, Mesdan S.p.A., Italy, to produce a fiber web and subsequently into a sliver. Using a drafting machine (Stiro Roving Lab 3371, Mesdan Lab, Mesdan S.p.A, Italy), each sliver was elongated and doubled with another sliver before further elongation. Thereafter, the slivers were false-twisted to form a roving. The spinning of the yarn proceeded with a ring spinning machine (Ring Lab 82BA, SER.MA.TES Srl, Italy) employing a Z direction twist. The twist factor (α_e) and the target yarn count were 4.2 and 20 tex (Nm 50/1, Ne 30/1), respectively. In total, the yarn incorporated 900 twists per meter.

Yarn Tensile Testing

The yarn was conditioned before the measurements at 20 ± 2 °C and 65 ± 2 % relative humidity. Following this, a MTS 400 tensile tester equipped with 50 N load cell was used to determine the tenacity and elongation thereof. The test employed a 250 mm/min test speed, 250 mm gauge length and 30 specimen count. The average linear density value was evaluated from a 10 m hank of yarn ($n = 14$). The tensile testing for commercial Tencel yarn (20 tex, Nm 50/1, Ne 30/1) was provided by Orneule Oy, Finland, which incorporated 880 twists per meter also with a Z torsion.

Weaving and Printing

In Söktas weaving mill, the Ioncell yarn (20 tex Z 900) was used as a filling yarn (weft yarn) in the weaving machine (Picanol, Belgium), while the warp yarn was the commercial Tencel yarn (Nm 50/1, Ne 30/1). The weaving produced a twill structure with a density of the warp and weft yarns of 48 and 29 yarns/cm, respectively. The fabric width was 150 cm with a mass per unit area of 139 g/m², containing 62 wt.% Tencel yarn and 38 wt.% Ioncell yarn.

Post-weaving, the fabric was treated to remove impurities, and improve dyes adsorption. In the same mill, the singeing process eliminated all protruding fibers, while the warp sizes were removed in the desizing process. Thereafter, the fabric was washed to remove dirt. A cold mercerization using NaOH 20° Bé was performed to improve dye uptake (Goswami *et al.* 2011). Finally, the fabric was wash cleaned with cellulase enzyme (Morgado, Cavaco-Paulo & Rousselle 2000; Carrillo *et al.* 2003) before final drying.

Printing took place in the Marimekko Oy printing mill (Finland). The selected design for the print was “Unikko”, designed by Maija Isola in 1964, employing a navy-blue reactive dye (Huntsman Novacron P). The printing was done by a rotary-screen printing machine, and fixed by a steamer at 103 °C saturated steam for 8 min. After fixation, washing was done (95 °C) to remove unfixed dye and printing paste. Next, the fabric was dried and transported for fabric finishing back in Söktas mill. A sequence of fabric finishing was performed to improve the visual and final touch of the textile. First, a resin finishing mixture (resin + low density polyethylene resin (LDPE) + MicroSilicone + wetting agent, no acid) improved wrinkle recovery (Jaturapiree *et al.* 2011). A mechanical Pentek finishing gave a soft touch to the fabric, and finally, the sanforizing process reduced the shrinkage of the fabric (Ahn *et al.* 2005).

Dress Making

Dress sewing took place in Marimekko facilities in Finland. The interlining fabric (belt, collar, cuffs, and front pieces) was attached to the main fabric by steam ironing at 141 °C for 12 s. The edge text for the dress was transfer printed on the fabric by steam ironing at 160 °C for 15 s.

Fabric testing was conducted by Marimekko and Intertek. The tests included color fastness: to alkaline and acid perspiration (EN ISO 105-E04), to washing at 30 and 40 °C (EN ISO 105-C06), and to rubbing (EN ISO X-12). For abrasion resistance and pilling determination, the Martindale-equipment was used following the EN ISO 12947-2 and EN ISO 12945-2, respectively. The tensile strength of fabric was determined according to the EN ISO 13934-2 grab-test. Moreover, the tearing strength of the fabric was determined according to the ISO 13937-1 using Elmendorf equipment. Following ISO 13936-1, the resistance to the seam slippage was determined by the fixed opening method. The dimensional changes were determined after laundering at 30 °C. All the test results were evaluated in comparison to a the commercial Tencel control fabric with the similar weave structure, fabric density and fabric weight.

4.3 Analytics

4.3.1 Cellulose Solutions and Fibers

Light Microscopy

Small samples were taken after dope preparation for light microscopy analysis to quantify the extent of dissolution *via* the Axio Zeiss A1 optical light microscope (equipped with a polarizer). The microscopy images were taken at a 1296 x 972 resolution *via* a 5x magnification power in cross-polarized mode and analyzed using ImageJ v1.52t software. Furthermore, in **Paper III**, a Python script was developed to auto-analyze the dissolution extent in multiple images (Elsayed *et al.* 2020b). In principle, the software converted all blue, green and red (BGR) pixels into a shade of grey with an integer of 0 to 255 (white = 255 and black = 0). Next, we introduced a threshold of 50 to differentiate between black and white pixels. The software then quantified the ratio of the white pixels (undissolved) to black pixels (dissolved) in the image.

Rheological Characterization

The shear rheological properties were analyzed using an Anton Paar MCR 302 rheometer with a plate and plate geometry (25 mm plate diameter, 1 mm gap size). For the cellulose solutions, an oscillatory measurement was selected for temperatures of 60 – 120 °C in steps of 5/10 °C, 0.01 – 100 s⁻¹ ω , and a 1 % constant shear rate. The test recorded the η^* , G' and G'' . By fitting the data to the Cross-viscosity model, as in the below equation, the η_0 was determined for every temperature, where C and p are (cross) time and rate constant, respectively.

$$\eta = \frac{\eta_0 - \eta_\infty}{1 + (C\dot{\gamma})^p} + \eta_\infty \quad (1)$$

Master curves for the η^* , and G' and G'' were derived from the reduced variables *via* the WLF time–temperature superposition at 85 and 90 °C. The shift factors and reduced variables were calculated as previously described (Sammons *et al.* 2008). The neat ILs were also measured within the range of 20 – 100 °C.

Molar Mass Distribution of Cellulose

The molar mass distribution (MMD) was determined by a gel permeation chromatography system (Dionex Ultimate 3000 HPLC). The HPLC contained a pre-column (PLgel Mixed-A, 7.5 x 50 mm), four analytical columns (4 x Agilent PLgel Mixed-A, 7.5 x 300 mm), a Shodex RI-101 refractive index and a Viscotek/Malvern SEC/MALS 20 multi-angle light-scattering detector. Samples preparation took place *via* cellulose activation through a solvent exchange process (Potthast *et al.* 2015; Potthast *et al.* 2002). Lithium chloride/N,N-dimethylacetamide was used as a solvent. The determination of the detector constants was conducted with a narrow polystyrene standard ($M_w = 96\,000$ g/mol, $\bar{D} = 1.04$) in a 0.9 % Lithium chloride/N,N-dimethylacetamide. A broad polystyrene standard ($M_w = 248\,000$ g/mol, $\bar{D} = 1.73$) was utilized for the detector

calibration. For celluloses in 0.9 % LiCl in N,N-dimethylacetamide, a 0.136 mL/g $\partial n/\partial c$ (refractive index increment) was used.

The peaks were smoothened using the LOESS smoothing function, 0.1 span, available in Origin 2019b software. Afterwards, we calculated the degree of polymerization (DP), number average molar mass (M_n) and weight average molar mass (M_w).

Scanning Electron Microscopy

Utilizing a Zeiss Sigma VP SEM (1.5 kV acceleration voltage), the cross-sectional images of the fibers were obtained. The fibers were pre-sputter coated with Au.

Tensile Properties

The fibers tensile properties: breaking tenacity, breaking force, elongation at break and linear density, were measured on an automatic single-fiber tester (Favigraph, Texttechno, Germany) for conditioned and wet properties. The fibers were pre-conditioned over night at 20 °C and 65 % relative humidity. The test employed a 20 mm gauge length, 200 mm/min speed, 20 specimen count and a of 5.9 ± 1.2 mN/tex pretension weight (according to DIN the 53816 standard). The Young's modulus of the fibers was estimated from the stress strain curves according to ASTM standard D2256/D2256.

X-Ray Diffraction

Wide-angle X-ray scattering (WAXS) measurements for the fibers were conducted by a SmartLab (RIGAKU) instrument (45 kV, 200 mA and 1.5418 Å). First, the fibers were cut and pressed into pellets. Thereafter, the fibers diffraction data were obtained in a continuous line scan mode, $\theta/2\theta$ geometry from 5° to 60° 2 θ . Azimuthal profiles of (020) diffraction peak were scanned with chi scan mode. Air diffraction profiles were also determined without fibers and under the same conditions and deducted from the sample's intensity. Noise from the data was removed by the Savitzky-Golay function (29 window size and a polynomial order of 1).

For each sample profile, the background profile ($I_{bkg}(\theta)$) was estimated using a smoothing method applying the Savitzky-Golay filter (8° to 55° 2 θ), 201 window size (corresponding to 4° by 2 θ) and polynomial order of 1. The estimation of the background was iterated 50 times until no pronounced reduction in the area was observed. From this data, the crystallinity index (CI), ratio of the of total intensity and background intensity, was calculated from 9° to 50° 2 θ according to equation 2.

$$CI = 100 * \frac{\int I(\theta) d\theta - \int I_{bkg}(\theta) d\theta}{\int I(\theta) d\theta} \quad (2)$$

The background profiles were fitted (lmfit) with four pseudo-Voigt functions for (1-10), (110), and (020) equatorial diffraction peaks, and a (002) meridian diffraction peak.

From the azimuthal profile, the Herman's orientation parameter, between the cylindrical longitudinal direction and the crystallographic c-axis of unit cell, was

derived assuming cylindrical symmetry along the fiber as previously explained (Yoshiharu *et al.* 1997).

Birefringence

Fibers total orientation (f_t) was measured on a polarized light microscope (Zeiss Axio Scope) equipped with a 5λ Berek compensator. The estimation of the birefringence, Δn , was possible by dividing the retardation of the polarized light by the fiber thickness, while the f_t was determined by dividing the Δn by the maximum birefringence of cellulose (0.062) (Jürgen, Josef & E. 2009). A $f_t = 0$ means full randomness in the orientation, while $f_t = 1$ means the chains are perfectly aligned.

The estimation of the amorphous orientation (f_a) is achieved from equation (4) by knowing the f_t , the crystallinity x_c and the crystalline orientation f_c .

$$f_a = \frac{f_t - (x_c * f_c)}{(1 - x_c) * 0.91} \quad (3)$$

where 0.91 is the ratio of the cellulose amorphous to the crystalline densities.

4.3.2 Pure IL and IL-Rich Solutions

Kamlet-Taft Parameters

The empirical Kamlet-Taft solubility parameters were measured for fresh [mTBDH][OAc] and [DBNH][OAc]. The dyes 4-nitroaniline (NA, Sigma), N,N-diethyl-4-nitro-aniline (DENA, Sigma) were available, while the 2,6-dichloro-(2,4,6-triphenyl-1-pyridino) phenolate dye (WB) was prepared according to the earlier protocol (Kessler & Wolfbeis 1989). The dyes were dissolved in acetone to yield a 30 mmol concentration. Thereafter, a 10 μl DENA, 30 μl NA, and 100 - 500 μl WB were taken to Eppendorf tubes and let to evaporate all the acetone. A 500 μl of IL was later added to each tube separately. The samples were heated in an oven at 100°C for 5 min and vortexed to ensure the dissolution of the dyes in the IL. Then, the samples were transferred to glass corvettes and the UV spectra was recorded on a Shimadzu UV-2550 spectrophotometer at 70 °C for the wavelengths (λ) of 200 - 600 nm. The peaks were observed as follows: 402 - 414 nm for λ_{DENA}, 398 - 406 nm for λ_{NA} and 518 - 585 nm for λ_{WB}. A Gaussian fit function was applied to calculate the peak maxima. Using the below equations, we could calculate the di-polarity polarizability ratio (π^*), the hydrogen bond acidity (α), the hydrogen bond basicity (β) and the solvent polarity values (ET(30) and ET(33)) as descriptors for cellulose solubility in ILs.

$$ET(30) = 0.979 * ET(33) - 7.461 \quad (4)$$

$$ET(33) = \frac{28591.5}{\lambda_{WB}} \quad (5)$$

$$\pi^* = 0.314 * \left(27.52 - \frac{1}{\lambda_{DENA} * 0.0001} \right) \quad (6)$$

$$\alpha = 0.0649 * ET(30) - 2.03 - (0.72 * \pi^*) \quad (7)$$

$$\beta = \left(1.035 * \frac{1}{\lambda_{DENA} * 0.0001} + 2.64 - \frac{1}{\lambda_{NA} * 0.0001} \right) * 2.8^{-1} \quad (8)$$

Thermogravimetric Analysis and Differential Scanning Calorimetry

Thermogravimetric analysis (TGA) for the pure equimolar [mTBDH][OAc] and [DBNH][OAc] was performed under N₂ atmosphere on a Q500 TGA (TA Instruments, Germany) for the temperature range of 40 to 900 °C.

Differential Scanning Calorimetry measurements (DSC) of the pure equimolar [mTBDH][OAc] and [DBNH][OAc] were done on a Q2000 MT-DSC (TA Instruments, Germany) for the same temperature interval.

Nuclear Magnetic Resonance

Composition analysis of the fresh [mTBDH][OAc] and [DBNH][OAc] as well as their concentrated (recovered) streams from TFE was carried out by a proton nuclear magnetic resonance spectroscopy, ¹H NMR (Bruker 400 MHz Ultra Shield NMR), using the solvent dimethyl sulfoxide, DMSO-d₆ (Sigma-Aldrich, purity > 99.9 %). Eight transients were measured with a 2.5 s acquisition time at 23 °C. The spectra, peaks and chemical shift were identified on MestReNova software.

Karl Fischer Titration

The water content of the fresh and the recovered ILs was determined by a Mettler Toledo Karl Fischer device ready with a DL38 volumetric titrator. The samples were dissolved in Hydranal Methanol Rapid solvent and titrated with Hydranal Composite 5 (Fluka Analytical).

4.3.3 Dilute IL Solutions

Capillary Electrophoresis

The capillary electrophoresis (CE) device, Agilent 7100 (Santa Clara, USA), analyzed the dilute IL solutions (distillate streams) containing mTBD, DBN, and their hydrolysis products. The unit was equipped with a diode-array detector and an air-cooling device for the capillary cassette. A calibration curve for each component was first acquired at 0.01 to 0.2 mg·mL⁻¹. A 0.02 mg/mL Benzyltrimethylammonium chloride (Sigma Aldrich, Germany) was used as an internal standard. The measurement separation voltage was - 25 kV for mTBD and its hydrolysis products, and - 20 kV for DBN and its hydrolysis products. The samples were injected for 10 s at 25 °C and 10 mbar. The UV detector was set to 200 nm. The background electrolyte solution was composed of sodium acetate buffer (pH 4.0) with the ionic strength of 10 mM and 20 mM for the superbases and their decomposition products, respectively. The pH of the background electrolyte solutions could be adjusted with 1 M NaOH or 1 M HCl. Before usage, the buffer was filtered with a 0.45 µm PVDF filters (Phenomenex, Denmark).

The concentration of the acetate was analyzed *via* a Hewlett Packard 3D CE model G1600GX (Agilent, Germany). The acetate calibration curve 0.0025 to 0.2 mg/mL was initially measured (correlation coefficient 0.9997). The internal standard for the acetate measurements was 0.05 mg/mL Propionic acid (Acrös Organics/Thermo Fischer Scientific, Belgium). The samples were injected at 45

mbar, 25 °C for 10 s. A separation voltage of -10 kV and UV-Vis detector of 254 nm were used. The background electrolyte solution was composed of 20 mM 2,3-pyridinedicarboxylic acid (Sigma-Aldrich, Germany) and 0.3 mM myristyltrimethylammonium hydroxide (100 mM concentrate, Waters, USA) in 10:90 (v/v) MeOH:H₂O. The pH of the solution was adjusted to 9 with a 25 % (v/v) ammonia (VWR international, Belgium). The buffer was filtered through a 0.45 µm PVDF filter (Aireka Cells, Hong Kong) before use.

4.4 Simulation for the Energy Demand for IL Recycling

A model was built using Aspen Plus V11 software to simulate the energy demand during the recovery of the [mTBDH][OAc]/water system. The model design was based on a NRTL method with specific binary interactions as previously described by Baird *et al.* (2020). The model included the interactions of water with the IL at an AcOH/mTBD molar ratio of 1 and 3/2 (the azeotropic composition), while it did not include the interactions of the hydrolysis products. The design consisted of a heater and a flash separator, which simulate a single-effect evaporator. Based on this, we were able to run a sensitivity analysis to calculate the heat of vaporization (H_{vap}), at atmospheric pressure, resembled in the heat duty of the flash separator at dew point, for different feed water concentrations. We also estimated the energy demand to recover an 80 wt.% water/IL solution to reach 5 wt.% residual water in the concentrated IL using equation 9. The feed stream was at 25 °C and 1 bar. The heater and flash separator conditions were 80 °C and 1 atm and 80 °C and 55 mbar, respectively.

$$Energy_{per\ ton\ of\ fibers}\ [GJ] = \frac{(Energy_{heater} + Energy_{evaporator}) \left[\frac{J}{s} \right] \times dry\ pulp\ weight\ [kg] \times (1 - pulp\ wt.\%) }{pulp\ wt.\% \times feed\ IL\ in\ solution\ wt.\% \times feed\ flow\ rate \left[\frac{kg}{s} \right] \times 10^6} \quad (9)$$

5. Results and Discussion

5.1 Lyocell Solvents for Cellulose Dissolution and Fibers Regeneration

The role of the amidine-based ILs [DBNH][OAc] and [DBUH][OAc], the guanidine-based IL [mTBDH][OAc], and NMMO·H₂O, were researched in their ability to dissolve commercial dissolving pulp to produce a 13 wt.% cellulose solution for dry-jet wet spinning of Lyocell fibers. The aim was to show good performance of the ILs so that we could select few of them for recycling in later research. The Kamlet-Taft solubility parameters of the [DBUH][OAc] were reported earlier by Kuzmina *et al.* (2017). As illustrated in Table 8, we also extended the study to [DBNH][OAc] and [mTBDH][OAc]. All ILs comprised parameters, $\beta - \alpha$ and β , which fit in the good dissolution window of cellulose that was described earlier ($1.2 > \beta > 0.8$ and $0.9 > \beta - \alpha > 0.35$) (Hauru *et al.* 2012).

Table 8. Kamlet-Taft parameters of [DBUH][OAc], [DBNH][OAc] and [mTBDH][OAc].

IL	α	β	$\beta - \alpha$
[DBUH][OAc]*	0.56	1.05	0.48
[DBNH][OAc]	0.53	1.10	0.57
[mTBDH][OAc]	0.42	1.17	0.75

*Values adapted from (Kuzmina *et al.* 2017).
Copyright (2020) Royal Society of Chemistry.

In **Paper I**, all the equimolar pure ILs and NMMO·H₂O readily dissolved 13 wt.% cellulose in 90 mins without complications. The rheology of the Lyocell solutions has been previously discussed (Hummel, Michud & Sixta 2011; Smith *et al.* 2013; Sammons *et al.* 2008; Chen *et al.* 2009). The dope viscoelastic behavior allows the shear thinning of the solution in the capillary during extrusion, where chain orientation already initiates, also it prevents breakages during the stretching when uniaxial stress is applied by the godets (Nishiyama *et al.* 2019; Hummel *et al.* 2015). Frequency sweep oscillatory measurements of the dopes revealed non-Newtonian solutions, outlined in Figure 12 b. The master curves helped to estimate η^* *via* extrapolating the data to even low ω ($< 0.01 \text{ s}^{-1}$). Typically, at such small ω , a Newtonian plateau of η^* is dominant, which changes to a shear thinning slope upon increasing ω until the curves superimpose. Figure

12 b displays a comparable η^* for all solutions, although the NMMO·H₂O- and [DBUH][OAc]-based dopes had slightly larger η_0 of 30 000 Pa.s at 90 °C, compared to a 30 000 at 85 °C and 80 °C for [mTBDH][OAc]- and [DBNH][OAc]-based dopes, respectively. The larger η^* of [DBUH][OAc]- than [DBNH][OAc]-based dopes is in agreement with solution viscosities reported by Kuzmina *et al.* (2017).

Figure 12. Rheological properties of the neat ILs (a) and of the IL-cellulose solutions: b. Complex viscosity master curves at 90 °C. c. Dynamic moduli, G' and G'' , at 90 °C.

Kosan *et al.* (2008) introduced a hypothesis relating the role of the size of the cation in the state of cellulose solution. Cations of smaller size diffuse easier between the cellulose strings and loosen the interchain bonds, thus reducing the solution viscosity. Whereas, cations of larger size, or longer side groups, have less power (Kosan, Michels & Meister 2008). However, this can only be partly true as the viscosity of the neat IL greatly influences the viscosity of the prepared solution. The rheology of the neat pure ILs (Figure 12 a) revealed a higher viscosity for the [DBUH][OAc] followed by [mTBDH][OAc] and [DBNH][OAc]. In Figure 12 c, the dynamic moduli, G' and G'' , were akin for all cellulose solutions, which is a good feature as the spinning specifications can be achieved *via* minor alterations in the dope temperature.

The fiber spinning of the dopes proceeded *via* a dry-jet wet spinning process at a temperature corresponding to a η_0 of 30 000 Pa.s. Only minor agglomerates were formed during spinning that are typical for a small-scale batch spinning process. The scanning electron microscopy images of the fibers, at DR 2 and 12, show a correlation of increased stretching on uniforming the fibers and eliminating surface irregularities (Elsayed *et al.* 2021). The structural properties of the regenerated fibers were accessed by birefringence and WAXS measurements to estimate the crystalline and amorphous regions, summarized in Table 9.

Table 9. Fibers birefringence measurements and structural analyses (WAXS).

	DR	[DBUH][OAc]	[mTBDH][OAc]	NMMO	[DBNH][OAc]
n	2	0.042	0.038	0.041	0.040
	5	0.042	0.043	0.041	0.043
	12	0.043	0.046	0.041	0.044
f_t	2	0.68	0.61	0.66	0.64
	5	0.68	0.69	0.66	0.69
	12	0.70	0.74	0.66	0.71
x_c	2	0.35	0.34	0.32	0.35
	5	0.36	0.36	0.33	0.35
	12	0.38	0.36	0.35	0.35
f_c	2	0.79	0.74	0.73	0.71
	5	0.80	0.80	0.79	0.86
	12	0.83	0.80	0.79	0.85
f_a	2	0.68	0.60	0.69	0.66
	5	0.67	0.68	0.65	0.66
	12	0.68	0.77	0.65	0.69

All Lyocell fibers demonstrated high orientation and crystallinity (n , f_t and x_c) even at a DR of 2, which is a result of the axial chain orientation of the polymer taking place in the air-gap. In some cases, especially at DR 2, f_a was slightly bigger than f_t . Such divergence is associated with discrepancies in fibers spun from low DRs that have a more prominent amorphous density ratio than the general value (0.91). Compared to n of a regular viscose fiber (0.025) (Jiang *et al.* 2012), the studied Lyocell fibers had a substantially greater birefringence (0.038 – 0.046). The worse birefringence of viscose is a result of the wet spinning process in which the filaments are instantly regenerated in the bath, creating an amorphous structure with only a few crystalline regions (Kreze & Malej 2003). The increase in DR enhanced f_t and f_c of the fibers, where a plateau in the f_c could be noted already at DR 5. Interestingly, f_c of the IL-based fibers was somewhat higher than of NMMO-based fibers. Contrarily, the increase in DR didn't improve x_c of the fibers as it was already pronounced at low DR.

Figure 13 depicts the evolution of tenacity and elongation upon increasing the DR. At DR 3, all fibers had tenacities between 30 – 46 cN/tex, which already exceeds the regular viscose fiber (Fink *et al.* 2001; Jiang *et al.* 2012; Hummel *et al.* 2015). As expected, a linear correlation between the total orientation and tensile properties of the fibers was evident (Krässig & Kitchen 1961; Adusumalli

et al. 2009); The increase in the DR to 12 resulted in fibers of linear density between 1.2 – 1.3 dtex with improved tenacities, and corresponds to elongations of about 12.3 % for NMMO·H₂O and [DBNH][OAc]-based fibers, and about 10 % for [DBUH][OAc]- and [mTBDH][OAc]-based fibers. The shorter stretchability of the [mTBDH][OAc]- and [DBUH][OAc]-based fibers was also reflected in a high elastic modulus of 17.4 and 16.2 GPa, respectively. On the other side, a smaller modulus was observed for [DBUH][OAc]- and NMMO-based fibers with 13.9 and 14.4 GPa, respectively.

Figure 13. Mechanical properties, tenacity and elongation, of the regenerated fibers at DR 3 - 12.

From the results above, we notice only minor discrepancies in the properties of the regenerated fibers from the Lyocell solvents, also clear in the analogous rheology of the respective dopes. This is comprehensible since the dissolution and regeneration mechanism of cellulose in these ILs is akin, deeming them suitable solvents for producing textile-grade fibers. However, the hydrothermal stability of the ILs, and tolerance to side-products can favor some on others.

5.2 Dissolution of Cellulose in Altered ILs

We selected [mTBDH][OAc] and [DBNH][OAc] to proceed with the dissolution studies of 13 wt.% cellulose in the ILs of altered composition (**Paper III**), and the comparative recycling and spinning of the ILs in the Lyocell process (**Paper II**). The choice of the guanidine-based superbase is based on the promising results over DBN and DBU in resisting hydrolysis reactions as outlined by Hyde *et al.* (2019), also confirmed in our patent application (WO2018138416A1) through internal kinetic studies related to IL degradations. [DBNH][OAc] was used to symbolize the amidines, in addition to serving as a reference since it is the solvent employed in multiple of the Ioncell publications (Haslinger *et al.* 2019b; Haslinger *et al.* 2019a; Ma *et al.* 2015; Ma *et al.* 2015; Asaadi *et al.* 2016).

5.2.1 Effect of [mTBDH][OAc] Alterations

In order to understand the influence of the changes occurring in the solvent during thermal recovery (residual water, hydrolysis generations and change in AcOH/mTBD ratio), we decided to alter the solvent composition to include these parameters while attempting to dissolve the same cellulose concentration

(13 wt.%). Under atmospheric pressure, the extent of dissolution was assessed for different concentrations of alterations in [mTBDH][OAc] (Table 10). The dissolution thresholds were defined here as good for 97 % dissolution, partial for 80 – 97 % and bad for less than 80%. These ranges of the dissolution were qualitative; however, it is known in industry that a few percentile of undissolved cellulose can turn the whole process into unprofitable. Therefore, it is necessary to keep the content of dissolved cellulose close to 100 % (> 97 % in this trial).

Table 10. Dissolution of 13 wt.% cellulose in [mTBDH][OAc] under atmospheric pressure, 85 °C for 90 min with single and combined compositions of solvent alterations.

No.	Composition			Dissolution %
	H ₂ O	AcOH/mTBD	[ΣH-mTBD][OAc]	
	wt.%	molar ratio	wt.%	
1	7.5	1	0	99.7 ± 0.6
2	8.75	1	0	97.5 ± 4.2
3	10	1	0	92.6 ± 6.4
4	5	1.15	7.5	99.6 ± 0.9
5	6.25	1.15	7.5	88.4 ± 4
6	7.5	1.15	7.5	93.8 ± 2.7
7	3	1.2	10	99.8 ± 0.1
8	3	1.2	20	99.6 ± 0.3
9	5	1.2	5	95.4 ± 2
10	5	1.2	10	90.5 ± 9

As illustrated in Table 10, while only water is present at ≤ 8.75 wt.%, an excellent dissolution could be achieved of > 97 %. The dissolution extent is worsened upon raising the water content to 10 wt.% as seen in Table 10, experiment 3. For combined alterations, experiments 4 to 6, a maximum of 5 wt.% water is accepted when the hydrolysis products and AcOH/mTBD ratio are 1.15 and 7.5 wt.%, respectively. The increase in hydrolysis products and AcOH/mTBD ratio necessitates further reduction in the water content to 3 wt.% (experiments 7 – 10).

Usually, applying vacuum is essential during dope preparation to homogenize the solution and to remove the entrapped air bubbles (degassing), which otherwise may diffuse during the spinning process through the spinneret capillaries, and ultimately causing filament breakages. The reduced pressure may also aid in the removal of solvent-residual water from the recovery process. Hence, we conducted another set of trials under fixed reduced pressure (15 mbar) to cover a wider range of solvent alterations using the Box-Behnken design model. Moreover, dopes having good extent of dissolution qualified for the fiber spinning process. Figure 14 describes the extent of cellulose dissolution in [mTBDH][OAc]-containing solvent alterations; three water levels are displayed 1, 5.5 and 10 wt.% covering the ranges of 0.8 – 1.6 AcOH/mTBD ratio and 0 – 40 wt.% hydrolysis products ([ΣH-mTBD][OAc]). Aside from the previous parameters, the dissolution time (30 – 120 min) in the kneader was also included

in the initial design model. Nonetheless, due to its trivial coefficient, it was rather excluded from the model as explained in **Paper III**. Incorporating pressure, as a varied parameter, in this model would have complicated the study since it intertwines with residence time, temperature, water content and degree of applied vacuum. Thus, increasing the number of experiments and consequently, the level of uncertainties.

Figure 14. Dissolution contours for 13 wt.% cellulose in [mTBDH][OAc] in different AcOH/mTBD and hydrolysis products compositions at 1 wt.% water (a), 5.5 wt.% water (b) and 10 wt.% water (c).

The statistical variance of the model including the main and interacting parameters was reported in **Paper III**. The design center point composition composed of 5.5 wt.% water, 20 wt.% hydrolysis products, 1.25 AcOH/mTBD ratio and 75 min dissolution time. The case of 1 wt.% water objectively simulates the existence of water in the system as a result of the pulp moisture content, while 5.5 and 10 wt.% water cases depict the IL condition during recovery. In all figures, the guanidine-based IL had an elevated endurance to the combined alterations. As anticipated, the increase of water reduces the IL acceptance to other alterations (hydrolysis products and AcOH/mTBD ratio) and vice versa. At 5.5 wt.% water (Figure 14 b), the thresholds in attaining a high extent of dissolution are ~ 25 wt.% hydrolysis products and AcOH/mTBD ratio of 1.38 in the IL. At the combined center point composition, where greater combined alterations dominate, only a partial dissolution was achievable at 88 %. When the concentration of water in the combined alterations reach 10 wt.%, Figure 14 c, the region of partial dissolution is shifted towards milder concentrations of hydrolysis

products and AcOH/mTBD ratios with 22.5 wt.% and 1.32, respectively. These concentrations only indicate the thresholds of cellulose dissolution in the altered IL and are not directly quantitative to the recovered IL specifications. In other words, it can be possible to remove the water from the solvent while preserving the IL composition (AcOH/mTBD ratio and hydrolysis products) at even lower figures.

Based on the previous figures, it is clear that vacuum plays a role in the removal of water from the system during dissolution. For example, although Figure 14 b and Table 10 (experiment no 9 and 10) feature similar water content (5 and 5.5 wt.%), an increased tolerance of hydrolysis products and AcOH/mTBD ratio is noticed for the trial employing vacuum. Despite this, it was not possible to quantitatively measure the amount of vaporized water from the system since the initial dopes (25 g) comprised a water content corresponding to 0.22 – 2.2 g, which can be easily entrapped in the tubing of the vacuum system. In a scaled-up process, it may be useful to initiate the dissolution in a solvent containing a relatively high water content (~ 10 wt.%) to decrease the solution viscosity, and consequently the work needed for pumping, while complete dissolution can be obtained under vacuum during degassing and homogenizing stages.

For the fiber spinning process, we chose certain dopes that belonged to the region of good dissolution, in addition to the dope of the design center point composition and a dope prepared from pure equimolar [mTBDH][OAc]. The properties of the solutions and the spun fibers thereof are available in Table 11.

Table 11. Compositions, rheological and fiber properties for the selected dopes with combined alterations in [mTBDH][OAc].

No.	Composition			Rheological properties at 85 °C				Fiber properties at DR 8				DR max
	Water wt. %	AcOH/mTBD molar ratio	[ZH-mTBD][OAc] wt. %	η_0 Pa.s	ω s ⁻¹	COP Pa		Titer dtex	Tenacity cN/tex	Elongation %		
1*	0.1	1	0	28 400	0.83	3 881		1.7 ± 0.3	47.6 ± 3.4	10.3 ± 1.9		15
2	1	0.8	20	25 640	1.01	4 420		1.9 ± 0.2	41.8 ± 3.5	9.4 ± 0.9		14
3	1	1.25	20	31 198	0.70	3 974		2 ± 0.3	37.6 ± 7.3	7.4 ± 1.1		14
4	1	1.25	0	21 196	1.01	3 589		1.7 ± 0.3	37.4 ± 7.7	8.1 ± 1.7		15
5	5.5	0.8	0	26 594	0.97	4 263		1.8 ± 0.4	39.8 ± 7.7	8.8 ± 1.2		14
6	5.5	0.8	20	36 860	0.69	4 324		1.7 ± 0.2	48.7 ± 5.3	9 ± 1.2		15
7	5.5	1.25	0	26 564	0.92	4 090		1.7 ± 0.2	48.2 ± 4.3	11.1 ± 1.1		15
8**	5.5	1.25	20	70 129	0.38	4 352		1.81 ± 0.3	22.8 ± 4.1	4.8 ± 1		9
9	10	0.8	20	31 195	0.88	4 658		2.1 ± 0.3	37.8 ± 5.2	9.2 ± 1		15
10	10	1.25	0	30 725	0.92	4 676		2.1 ± 0.4	33 ± 5.5	7.6 ± 1.4		8
Avg.***	-	-	-	28 746 ± 4 441	0.88 ± 0.11	4 261 ± 322		1.9 ± 0.3	40.5 ± 5.8	8.8 ± 1.2		-

*Dope from unmodified equimolar [mTBDH][OAc]

**Dope with the design center-point composition

*** Average values, excluding No. 1 and 8.

All dopes that belonged to the region of good dissolution displayed η_0 akin to the pure equimolar solution with only minor deviations (Figure 15 a). The same was noted for the dynamic moduli, where the overlapping between the storage modulus and the loss modulus only slightly varied (Figure 15 b); The maximum frequency recorded was 1.01 s⁻¹ for the COP of 4420 and 3589 Pa, which is still comparable to the dynamic moduli recorded for the pure equimolar dope.

Therefore, the results confirmed that the alterations in the IL, while below the good dissolution limitation, merely changed the viscoelastic properties of the prepared solutions. On the other hand, the partially dissolved solution displayed a low ω in combination with a high complex viscosity, suggesting a pronounced elastic modulus. However, this behavior is mainly attributed to the portion of undissolved polymer that falsely distorted the measurement.

Figure 15. Rheological properties of cellulose solution from altered [mTBDH][OAc] solvent. **a.** η_0 **b.** dynamic moduli. The curve terminology is as follows: Experiment number (water wt.%, AcOH/mTBD ratio and $[\Sigma\text{H-mTBD}][\text{OAc}]$ wt.%). Experiment 1 (0.1 wt.%, 1, 0), 2 (1 wt.%, 0.8, 20 wt.%), 3 (1 wt.%, 1.25, 20 wt.%), 7 (5.5 wt.%, 1.25, 0), 8 (5.5 wt.%, 1.25, 20 wt.%), 10 (10 wt.%, 1.25, 0).

Spinning of regenerated cellulose fibers was carried out on the KS-15 unit using the mono-hole spinneret. The maximum achieved DR and the fibers tensile properties from the conditioned measurements are provided in Table 11. The results agree with the trend of the rheology measurements; a high DR max was easily obtained for all dopes of the good dissolution region. Moreover, at DR 8, the tensile properties of the regenerated fibers were comparable to the fibers from pure, equimolar IL. The tenacities of the fibers slightly varied between 37.6 – 48.7 cN/tex. For the dope with only 10 wt.% water and 1.25 AcOH/mTBD (10), we witnessed deteriorated tensile properties that are also reflected in a DR max of 8. Previously, we attributed the inferior properties to the increased initial water content, but this can also be due to a mechanical shortcoming from the spinning unit since the KS-15 spinning unit is very sensitive as previously explained in the methods section. In contrast, the spinning of the dope of the design center-point composition had multiple agglomerates that increased the difficulty of the regeneration process. The tensile properties of the fibers thereof were worse.

These results can serve as an important guideline for the specifications of the recovered IL. They imply that if the alterations in the IL during thermal recovery are below the thresholds of good dissolution, indicated above, then the dissolution capability, fiber spinnability and fiber properties should not deteriorate.

The work also included the mTBD precursor, TBD. As stated in **Paper III**, while adding only [TBDH][OAc] to the IL, a high cellulose dissolution extent was possible for even 30 wt.% of the [TBDH][OAc]. It is of course undesired to have such lofty concentrations since the immense melting point associated with [TBDH][OAc], 157 °C (Kuzmina *et al.* 2017), will undoubtedly require intense

temperatures for processing, and might even undergo partial precipitation in the process. The spinning of 5 and 10 wt.% [TBDH][OAc] solutions produced fibers of about 52 cN/tex and 7.2 % elongation at DR 12. These findings are beneficial for the Ioncell process as mTBD of imperfect purity can still be accepted, which will cut extra purification costs.

5.2.2 Effect of [DBNH][OAc] Alterations

Table 12 reveals the findings of individual and combined alterations, in addition to a pure equimolar trial sample (1) as a reference.

Table 12. Impact of individual and combined alterations in [DBNH][OAc] on the dissolution of a 13 wt.% cellulose, rheological properties, spinnability and fiber properties.

No.	Composition		Dissolution %	Rheological properties at 80°C			Fiber properties at DR 8			DR max
	Water wt. %	AcOH/DBN molar ratio	[APPH][OAc] wt. %	η_0 Pa.s	ω s ⁻¹	COP Pa	Titer dtex	Tenacity cN/tex	Elongation %	
1*	1	1	0	31 125	0.95	4 950	1.8 ± 0.2	43.4 ± 4.9	13.2 ± 2	16
2	3	1	0	25 154	0.96	4 872	1.7 ± 0.2	40 ± 6.2	11.1 ± 2.4	14
3	5	1	0	25 248	1.24	4 207	1.5 ± 0.1	35.9 ± 4.3	10.5 ± 1.8	12
4	7.5	1	0	-	-	-	-	-	-	-
5	1	1.1	0	20 466	1.29	4 302	1.8 ± 0.3	37.1 ± 5	11.4 ± 2.1	12
6**	1	1.15	0	56 079	N.D.	N.D.	1.9 ± 0.5	23.4 ± 5.3	6.9 ± 1.6	8
7	1	1.2	0	-	-	-	-	-	-	-
8	1	1	10	23 820	0.92	4 437	1.7 ± 0.2	44.6 ± 4.6	13.1 ± 2.1	14
9	1	1	15	30 900	0.75	3 943	1.7 ± 0.2	41.4 ± 3.9	13.3 ± 2	12
10	1	1	20	-	-	-	-	-	-	-
11	3	1.05	5	25 480	0.92	3 564	1.8 ± 0.2	37.7 ± 2.7	11.6 ± 1.1	10
12	3	1.1	5	-	-	-	-	-	-	-
13	3	1	10	28 753	0.48	2 926	1.8 ± 0.2	38.8 ± 4.6	13.9 ± 2.7	14
14	3	1.05	10	44 300	0.48	2 971	1.8 ± 0.4	23.5 ± 5.5	8.5 ± 2.4	8
15	3	1.1	10	-	-	-	-	-	-	-
16	3	1.15	10	-	-	-	-	-	-	-
17	5	1.05	5	-	-	-	-	-	-	-

*Dope from unmodified equimolar [DBNH][OAc]

**N.D. No detection of cross-over points

It was necessary to first identify the endurance of [DBNH][OAc] towards individual alterations before adding combined alterations. This approach was based on our earlier experience with this IL that usually exhibited higher sensitivity towards composition changes. In general, we can summarize for the individual alterations (no. 2 – 10) that a water content up to 5 wt.% can yield good dissolution extents. The dissolution is then hindered upon further increasing the water content. Also, the loss modulus, depicted in ω , shifted from 0.96 s^{-1} at 3 wt.% (no. 2) to 1.24 s^{-1} at 5 wt.% (no. 3), reflecting a growing viscous behavior of the dope. A relation between the decrease in DR max and the rise in the concentration of the individual alterations was visible. The increase in the water content from 1 to 5 wt.%, negatively affected the DR max that reduced from 16 to 12, respectively. The same trend is found for the hydrolysis products; a maximum of 15 wt.% [APPH][OAc] is accepted in the IL while maintaining a DR max of 12. On the other side, the slight change in the AcOH/DBN ratio to 1.1 already killed the dissolution capability towards 13 wt.% cellulose (no. 5). Consequently, at a 1.15 AcOH/DBN ratio, the viscoelasticity of the solution was distorted, and no cross-over point was detected. Appendix 1 Figure A1 monitors the progress of cellulose dissolution under light microscopy for the individual alterations, 5 wt.% water, 15 wt.% hydrolysis products and 1.1 AcOH/DBN ratio. Based on these dissolution results, we optimized the range of combined alterations (no. 11 – 17), which revealed that an AcOH/DBN ratio of 1.05 or less is crucial for good dissolution and spinnability. This, in combination with 3 wt.% water and about 5 wt.% [APPH][OAc] can be considered as the target specification of the solvent to achieve good cellulose dissolution. Any step-increase in the main parameters negatively affects the dissolution (Appendix 1 Figure A2), and the DR max.

In comparison to [mTBDH][OAc] tolerance to alterations, [DBNH][OAc] proved to be the more sensitive IL which may be associated with its weaker ionicity (base) and lower $\beta - \alpha$. In order to confirm this hypothesis, the study of the Kamlet-Taft parameters needs to be extended in the future to include these IL alterations. This also highlights the challenge for the recycling of the [DBNH][OAc] in Ioncell since it is critical to preserve its composition below 3 wt.%, 1.05 and 5 wt.%, water, AcOH/DBN and [APPH][OAc], respectively.

5.3 Recycling of ILs in the Lyocell Process: A Comparison of [mTBDH][OAc] and [DBNH][OAc]

5.3.1 ILs Recycling

A comparison of the hydrothermal stability of [mTBDH][OAc] and [DBNH][OAc] in the Lyocell process was summarized in **Paper II** (Elsayed *et al.* 2020a). [mTBDH][OAc] was used to dissolve and spin a 13 wt.% cellulose concentration with the KS-80 unit. After spinning, the spinbath solution was thermally concentrated in multiple evaporation steps as illustrated in Scheme 1. The amount of recovered [mTBDH][OAc] reduced every cycle because of han-

dling losses arising over the different batch steps, nevertheless, the applied conditions achieved a residual water content of only 2.2 – 3.1 wt.% in the recovered IL (Table 13).

Table 13. Residual water concentrations of [mTBDH][OAc] streams before and after the consecutive evaporator units measured by Karl-Fischer (KF) titration.

Cycle	Spinbath*	After centrifuge evaporator	After TFE-1	After TFE-2 (Recovered IL)
	wt. %	wt. %	wt. %	wt. %
Fresh IL	-	-	-	0.2 ± 0.01
1	98.5 ± 0.1	54.4 ± 1.2	15.1 ± 1.1	3.1 ± 0.1
2	98.8 ± 0.2	76.9 ± 0.5	14.3 ± 0.3	2.2 ± 0.05
3	99.2 ± 0.04	93.7 ± 0.4	29.2 ± 1.2	2.7 ± 0.05
4	99.7 ± 0.02	90.7 ± 0.4	26.6 ± 0.8	2.8 ± 0.02
5	99.9 ± 0.01	92.8 ± 0.6	57.6 ± 3.2	2.6 ± 0.04

* Values calculated indirectly by capillary electrophoresis (CE) as the difference between the total sample amount and the total amount of the measured compounds (base, acid and degradation products).

Owing to the large volume of the spinbath (110 – 125 L), and the expensive cost of the mTBD base, it was not possible to pre-adjust the solvent concentration in the spinbath prior to recovery (e.g. to 20 wt.% IL). Consequently, the energy demand for the recovery of 0.1 – 1.5 wt.% IL in spinbath (Table 13) is tremendously high and therefore, the recovery scheme is only applicable in a lab scale process. The expensive cost of the guanidine-based superbases synthesis and purification is due to its limited production capacity, which endangers the profitability and sustainability of a large process. Yet, the future expansion of the ILs in the Lyocell process will simultaneously correspond to developing more affordable synthesis pathways of the superbases.

During the thermal recovery, alterations in solvent composition took place as previously noted. Remarkably, in Table 14, only minimal hydrolysis products were detected in the solvent during the recovery of [mTBDH][OAc] in TFE-1 (61 °C and 20 mbar), while the amount was even below the detection limit for the centrifuge evaporator (62 °C and 250 mbar) probably because of the low thermal load employed within these stages.

Table 14. Distillate and residue compositions of the centrifuge evaporator and the TFE-1.

Cy- cle	Centrifuge evaporator				TFE-1			
	Distillate		Residue		Distillate		Residue	
	[mTBD][OAc]	[ΣH- mTBD][OAc]	[mTBD][OAc]	[ΣH- mTBD][OAc]	[mTBD][OAc]	[ΣH- mTBD][OAc]	[mTBD][OAc]	AcOH/ mTBD mole ratio
	wt. %	wt. %	wt. %	wt. %	wt. %	wt. %	wt. %	
1	0.14 ± 0.01	-	45.6 ± 1.5	-	0.03 ± 0.01	-	84.1 ± 0.8	1.02
2	0.14 ± 0.01	-	23.1 ± 0.7	-	0.05 ± 0.01	0.004 ± 0.001	84.9 ± 0.03	1.02
3	0.07 ± 0.01	-	6.3 ± 0.5	-	0.03 ± 0.01	-	70.4 ± 1.2	1.05
4	0.09 ± 0.01	-	9.2 ± 0.4	-	0.23 ± 0.01	0.065 ± 0.002	72.9 ± 0.8	1.12
5	0.10 ± 0.01	-	7.2 ± 0.7	-	0.03 ± 0.01	-	60.4 ± 3.2	1.11

In TFE-2 the combination of temperature and pressure, 82 °C and 15 mbar was sufficient to yield the desired water content (Table 15). Meanwhile, a small amount of hydrolysis products was detected (average of 1.6 wt.%) over the five cycles. Also, the AcOH/mTBD ratio of the solvent deviated, from the equimolar ratio of the fresh IL, to reach an average of 1.12. Figure 16 displays the NMR spectra of the recovered solvent over five cycles. The spectra show the relative increase in the integral of the methyl protons of the acetate, 1.62 ppm, to that of the mTBD, 2.97. The peaks of H-mTBD-1 and H-mTBD-2 are observed at 2.24 and 2.76 ppm, respectively. Interestingly, we did not detect any APPAc in these trials. These alterations fall within the region of good dissolution (Figure 14 a) and pose no threat to the quality of the dissolution, which was confirmed as the dissolution of the 13 wt.% cellulose was not hindered in any of the five cycles.

Table 15. Fresh [mTBDH][OAc] composition and the composition of the concentrate and distillate streams in the TFE-2 during recycling.

Cycle	Concentrate stream				Distillate stream			IL _{Theor} recovery rate
	[mTBDH][OAc]		[ΣH-mTBD][OAc]	Water	[mTBDH][OAc]		[ΣH-mTBD][OAc]	
	wt.%	AcOH/mTBD molar ratio	wt.%	wt.%	wt.% of feed IL	A/mTBD molar ratio	wt.% of feed IL	wt.%
Fresh IL	99.8	0.99	-	0.2 ± 0.0	-	-	-	-
1	96.4	1.10	0.5	3.1 ± 0.1	1.5 ± 0.03	0.06	0.37 ± 0.01	99.3
2	96.8	1.10	1.0	2.2 ± 0.1	0.9 ± 0.03	0.11	0.27 ± 0.01	99.1
3	95.8	1.11	1.5	2.7 ± 0.1	0.6 ± 0.03	0.07	0.16 ± 0.02	99.9
4	94.5	1.16	2.6	2.8 ± 0.0	0.2 ± 0.02	0.24	0.98 ± 0.14	99.1
5	94.9	1.14	2.5	2.6 ± 0.0	0.3 ± 0.07	0.15	0.18 ± 0.01	99.9
Avg.	95.7	1.12	1.6	2.7 ± 0.1	0.7 ± 0.04	0.13	0.4 ± 0.04	99.5

Figure 16. Stacked ¹H NMR of fresh and recovered [mTBDH][OAc] IL showing the peaks of the acetate, the base and the hydrolysis products.

The recycling of [DBNH][OAc] followed the same scheme. Table 16 reveals a 3.3 wt.% residual water and a significant 14.4 wt.% hydrolysis products in the recovered solvent. The AcOH/DBN ratio was also high (1.27). The consumption of the IL in the hydrolysis reactions resulted in only 86.4 wt.% of the recovered IL. Obviously, the composition of the recovered solvent did not allow the dissolution of cellulose in the following cycle. This is in alignment with the findings in Table 12 and justifies the bad dissolution mostly with the elevated AcOH/DBN ratio and APPH.

Table 16. Fresh [DBNH][OAc] composition and the composition of the concentrate and distillate streams in TFE-2 during recycling.

Cycle	Concentrate stream				Distillate stream		IL ^{Theor reco-} very rate
	[DBNH][OAc]		APPH	Water	[DBNH][OAc]	APPH	
	wt. %	AcOH/DBN molar ratio	wt. %	wt. %	wt. % of feed IL	wt. % of feed IL	
Fresh IL	99.8	0.99	-	0.1 ± 0.01	-	-	-
1	86.4	1.27	14.4	3.3 ± 0.1	1.2 ± 0.3	2.1 ± 0.1	85.7

The extremely low extent of hydrolysis products in Table 15 suggests that an equilibrium between the amine and the mTBD base is reached at the respective TFE-2 conditions. The hydrolytic stability of the guanidine salt is better than the amidine counterpart mainly due to the higher ionicity of the [mTBDH][OAc], which reduces the amount of the unprotonated base that is prone to hydrolysis reactions. Also, the guanidine-based superbases express a higher electron density of the sp²-hybridized carbon in the mTBD ring that relatively protects the base against the nucleophilic reactions. Contrarily, a fast cleavage in the cyclic ring of the amidine is triggered producing APPH (Hyde *et al.* 2019). Earlier, it was reported that it was possible to reverse the hydrolysis reactions of DBN and DBU *via* heating in presence of catalytic acids under constant water removal (Oediger *et al.* 1966; Oediger, Möller & Eiter 1972). While this can revive the hope for DBN, the equilibrium composition between the lactam and the base is still unclear, and whether it can also yield the undesired amides. As discussed in **Paper III**, the hydrolysis content in the DBN IL (with combined alterations) must be suppressed below 5 wt.%, which adds challenges to the recovery of DBN.

TGA and DSC results of pure [DBNH][OAc] and [mTBDH][OAc] are available in Figure 17). [DBNH][OAc] exhibited higher volatility with an onset temperature at 177 °C, while the onset temperature for [mTBDH][OAc] was at 199 °C. The same behavior can be expected to the recovered solutions from both ILs. This is attributed to the lower pK_a of DBN compared to mTBD, and therefore it is expected that [DBNH][OAc] contains a higher fraction of neutral species that evaporates under thermal stress. The base diffusion rate is reflected in the A/B ratio of the ILs, where the AcOH/mTBD over the five cycles changed to 1.1 – 1.16 in comparison to the AcOH/DBN of 1.27.

Figure 17. TGA and DSC of the ionic liquids [DBNH][OAc] and [mTBDH][OAc].

5.3.2 Solvent Recovery Rate

Generally speaking, solvent losses in the Lyocell process occur as a result of losses in the fiber washing steps and solvent degradations that mainly take place during the recovery stages. In the NMMO-based Lyocell process, the coagulation bath solution is pumped through a similar sequence of thermal recovery units, where the water evaporates until a residual 13.3 wt.% is reached at which the thermally stable NMMO·H₂O solvent is formed. Over the decades, the recycling of the NMMO solvent was constantly optimized to increase the recovery rate to more than 99 %. Strictly speaking, in the case of [mTBDH][OAc], not all the alterations occurring in the solvent during recovery are considered losses, since the distillate stream containing IL traces can be recycled back to the coagulation bath. Additionally, residual water in the recovered IL can be accepted if it is kept below the threshold of the good dissolution limitations. It is, however, the accumulation of hydrolysis products that can amount to the solvent losses, and therefore the optimization of the process should proceed to limit and prevent their generation.

In this thesis, we do not discuss the residual IL in the fibers after washing as it is rather left to separate research. Basically, the IL rate of recovery ($IL_{recovery\ rate}$) can be simply estimated according to the below equation

$$IL_{recovery\ rate} = \frac{IL\ weight_{(distillate\ stream + residue\ stream)}}{IL\ weight_{(feed\ stream)}} \% \quad (10)$$

where the amount of IL was analyzed by NMR for the residue and feed streams, and by CE for the distillate stream.

The contribution of the centrifuge evaporator and the TFE-1 in generating hydrolysis products was insignificant, and thus could be excluded. However, when applying this equation to TFE-2 in the [mTBDH][OAc] trials, we only get low

recovery rates of 83 wt.% (cycle 1) to 50 wt.% (cycle 5), which are highly inaccurate because the average value of hydrolysis products in the recovered IL is only 1.6 wt.% as seen in Table 15. For instance, by applying equation 10 for Table 15 cycle 2:

$$IL_{recovery\ rate\ cycle\ 2} = \frac{9.7 [g]_{(distillate\ stream)} + 768 [g]_{(residue\ stream)}}{975.2 [g]_{(feed\ stream)}} \% = 79.7\ wt.\ \%$$

The amounts of [mTBDH][OAc] and water in the feed, residue and distillate streams are given in Table A1, Appendix 2. The inferior recovery rates are largely due to the losses taking place inside the evaporator unit, where some of the IL remain trapped inside after all the feed is pumped through. This is why, we even observe a higher drop in the $IL_{recovery\ rate}$ as the number of cycles increase, e.g. cycle 5, because the amount of feed IL is reduced. For this reason, identifying the $IL_{recovery\ rate}$ with this principle in the current small-scale process is inconvenient.

Alternatively, a more accurate $IL_{recovery\ rate}$ can be estimated assuming that there are no losses taking place inside the unit, which should be the case in a continuous operation. While this is only theoretical, but it can be more representative to the cycles herein. The amount of theoretical distillate (D_{Theor}) and residue (R_{Theor}) streams were calculated following a simple over all mass balance and a component (water) mass balance for the TFE-2 unit as seen below,

$$D_{Theor} + R_{Theor} = 100\ \% \quad (11)$$

$$Water_{(D_{Theor}+R_{Theor})} = Water_{(feed\ stream)} \quad (12)$$

where the amount of water was measured by Karl Fischer titration for the residue and feed streams, and indirectly from CE measurements for the distillate stream. The new IL theoretical recovery rate ($IL_{Theor\ recovery\ rate}$) can be easily calculated according to a modified version of equation 10.

$$IL_{Theor\ recovery\ rate} = \frac{IL\ weight_{(D_{Theor}+R_{Theor})}}{IL\ weight_{(feed\ stream)}} \quad (13)$$

It is important to note that this approach also suffers from discrepancies arising from the different measuring techniques. The new $IL_{Theor\ recovery\ rate}$ gives a 99.1 - 99.9 wt.%, illustrated in Table 15, which are promising figures for the [mTBDH][OAc], but definitely lack the confirmation in a continuous process. An example of the calculations for Table 15 cycle 2 is given below assuming a feed of 100 g.

$$96\ wt.\ \% \ D_{Theor} + 2.2\ wt.\ \% \ R_{Theor} = 15.1\ wt.\ \% \times 100\ g_{(feed\ stream)} \quad (12)$$

by substituting this in equation 11, then the weights of the theoretical distillate and residue streams were

$$D_{Theor} = 13.8\ g \ \& \ R_{Theor} = 86.2\ g$$

and therefore, the $IL_{Theor\ recovery\ rate}$, equation 13, was

$$\begin{aligned}
 IL_{Theor\ recovery\ rate,\ cycle\ 2} &= \frac{3.4\ wt.\ \% \times 13.8\ [g]_{(D_{Theor})} + 96.8\ wt.\ \% \times 86.2\ [g]_{(R_{Theor})}}{84.7\ wt.\ \% \times 100\ [g]_{(feed\ stream)}} \\
 &= 99.1\ wt.\ \%
 \end{aligned}$$

On the other side, the $IL_{Theor\ recovery\ rate}$ of [DBNH][OAc] was 85.7 wt.% (Table 16) due to the significant hydrolysis products formation, deeming this solvent as unfeasible and uneconomical for a large scale process.

5.3.3 Energy Demand

Generally, when the amount of water is high in the solution, basically only water is evaporating. On the other side, at low water concentrations, the equilibrium mixture of the IL-water increases the heat demand for evaporation. Figure 18 show the heat of vaporization (H_{vap}) for the [mTBDH][OAc]/water solution simulated on Aspen Plus software at different water concentrations. This design model only considered an AcOH/mTBD molar ratio of 1 and did not include the effect of hydrolysis products. For very dilute solutions, where the water fraction is 1 – 0.3 wt/wt, we observed a plateau in H_{vap} of $\sim 2265\ J/g$ that is very similar to that of pure water. On a molecular level, the 0.3 wt/wt is already equivalent to almost a water of 0.9 mol/mol, indicating that stronger molecular interactions initiate at this concentration. This is also in alignment with the drop in the values of vapor pressure seen in Figure 5 a. The H_{vap} gradually increases to reach 3590 J/g for about 0.05 water wt/wt, which can be considered one of the solvent specifications during recycling.

Figure 18. Heat duty for the [mTBDH][OAc]-water system, simulated by Aspen Plus V11 software.

Also, using the Aspen Plus software, we could extract initial figures for the energy demand of the thermal recovery process; To be able to concentrate a 20

wt.% IL solution to a 95 wt.% IL solution, a 65.36 GJ/ton of fiber is required, derived from equation 9 assuming a 13 wt.% cellulose concentration. This figure was based on the modelling of a single-effect evaporator and can be expected to decrease when additional effects are included.

5.3.4 Properties of the Cellulose Solutions and Spun Fibers

The rheological properties of the solutions of fresh and recycled (cycle 1 – 5) solvents are available in Table 17. The dopes of recycled [mTBDH][OAc] exhibited an average η_0 of 29 676 Pa.s, 3905 Pa COP at an ω of 0.79 s⁻¹, with a narrow discrepancy. Furthermore, the dynamic moduli and complex viscosity were akin to those from fresh [mTBDH][OAc], confirming that the composition of the recovered ILs did not alter the viscoelastic properties of the solutions.

Table 17. Rheological properties of the fresh and recycled dopes prepared from [mTBDH][OAc] and birch PHK pulp (13 wt.%), and the molar mass distribution of the fibers spun thereof.

Cycle	Rheological properties				Molar mass distribution			
	T °C	η_0 Pa.s	ω s ⁻¹	COP Pa	M _n kDa	M _w kDa	DP > 2000 %	DP < 100 %
Enocell pulp 1 (Fresh)	-	-	-	-	44.5	160.5	12.2	4.8
2	85	28 953	0.78	3 776	49.3	158.4	12.6	4.4
3	85	28 500	0.84	3 996	48.2	148.2	11.9	4.4
4	85	31 200	0.74	3 918	47.3	138.4	10.6	4.6
5	85	26 835	0.81	3 630	54.5	146.4	11.5	4.1
5	85	32 890	0.76	4 203	47.6	148	11.6	4
Avg.	85	29 676	0.79	3 905	-	-	-	-
St.dev.	0	± 2 379	± 0.04	± 218	-	-	-	-

The spinning of cellulose fibers was successful in all five cycles *via* the KS-80 spin unit. During spinning, the applied draw on the fibers gradually increased until a DR of 12 was reached at which the fibers were collected. Table 17 show the MMD of the spun fibers M_n and M_w, and the degree of polymerization, Dp < 100 and Dp > 2000. The values reveal that fibers spun from fresh [mTBDH][OAc] almost fully preserved the MMD of the virgin PHK pulp. On the other hand, the GPC measurements detected slight degradations in the M_w and M_n of the fibers spun using recovered [mTBDH][OAc] from 49.3 and 158.4 kDa, cycle 1, to 47.6 and 148 kDa, cycle 5, respectively. This implies a narrower distribution (PDI) of the fibers spun from recovered IL. The same trend is visible in the slight reduction in the long polymer chain fraction, Dp > 2000, 11.6 % (cycle 5) from 12.6 % (cycle 1). The existence of the short cellulose chains in the recovered IL did not have a visible impact on the behavior of the process. Nevertheless, it will be necessary to develop a suitable separation method in a continuous large-scale process.

The tensile properties and total orientation f_t of the spun fibers from [mTBDH][OAc]- and [DBNH][OAc]-based solutions are summarized in Table 18. A dtex of 1.2 – 1.3 corresponded well to the fibers at DR 12. Fibers from fresh

[mTBDH][OAc]- and [DBNH][OAc]-based solutions retained similar tenacities, although the cycle 1 [mTBDH][OAc]-based fibers had somewhat less stretchability than those of [DBNH][OAc]-based fibers. This is in alignment with the previous tensile properties noted in section 5.1. Likewise, the f_t of the [mTBDH][OAc]-based fibers was more pronounced than the fibers from the amidine-based IL. Fibers of cycle 2 and 3 (recovered ILs) showed the same properties as of cycle 1. In contrast, we observed inferior fiber properties, tenacities and elongation of cycle 4 and 5, which were associated with a mechanical shortcoming during the spinning process as a result of the very small dope sizes in the respective cycles as explained in **Paper II**. Another important aspect is the ability of the fibers from recovered [mTBDH][OAc] to preserve their high tenacities under wet state (wet-to-dry tenacities of almost 1) in all cycles as demonstrated in Table 18.

Table 18. Tensile properties of conditioned fibers from [mTBDH][OAc] (cycles 1-5) and [DBNH][OAc]

Fibers	Titer dtex	Tenacity cN/tex	Elongation %	f_t -	Wet-to-dry tenacity -
Cycle 1	1.2 ± 0.3	49.9 ± 3.8	9.5 ± 1.2	0.70 ± 0.06	0.99 ± 0.10
Cycle 2	1.3 ± 0.2	48.4 ± 2.8	9.3 ± 0.6	0.67 ± 0.06	0.99 ± 0.06
Cycle 3	1.2 ± 0.2	52.8 ± 3.2	10.1 ± 1	0.73 ± 0.11	0.97 ± 0.05
Cycle 4	1.3 ± 0.2	39.8 ± 4.6	7.5 ± 1.7	0.73 ± 0.04	1.01 ± 0.04
Cycle 5	1.2 ± 0.2	38.6 ± 3.3	8.5 ± 1.2	0.72 ± 0.07	1.01 ± 0.08
[DBNH][OAc]	1.2 ± 0.2	48.3 ± 2.8	13.7 ± 1.5	0.60 ± 0.11	0.97 ± 0.09

5.3.5 Demonstration Dress

The Paju dress was designed and executed by Marimekko to incorporate the yarn from fresh and recovered [mTBDH][OAc]. Also, it is a good possibility to test the fibers in industrial textile machines, like the ones in the Söktas mill. Due to the limited capacity of the Ioncell process, the fibers were used as weft, while it was necessary to include Tencel fibers as warp for the fabric production in Söktas mill. The Paju dress, Figure 19, composed of 62 wt.% Tencel fibers and 38 wt.% Ioncell fibers. From the wearing trials, the fabric felt soft with a nice feeling on the skin. A slightly stiffer feeling was felt when drying after the first wash, yet this can be reversed by steam ironing the fabric which improved the softness of the garment. The yarn tensile strength and wearing tests are available in Appendix 3 Table A2 and Table A3, respectively.

Figure 19. Marimekko's Paju dress (38 wt.% loncell fibers and 62 wt.% Tencel fibers). Designer: Riikka Buri, Marimekko. Photographer: Sebastian Johansson.

5.4 Additional Spinning Using [mTBDH][OAc]

The **A.T. 1** were carried out to further inspect the spinnability of cellulose solutions using fresh [mTBDH][OAc], and the properties of the fibers thereof. The 13 wt.% cellulose solutions were prepared at 85 °C, 15 mbar, 90 min and 30 RPM. The study employed a 200-hole spinneret and was performed with the KS-80 unit. Figure 20 extends the range of spun DRs to 15, up from 12 in Figure 13. The trend shows a visible linear correlation between the increase in the DR and the improved strength of the fibers. The Young's modulus also steadily increases to reach about 18 GPa at DR 13 – 15 at which the fibers are of 1.08 – 1.04 dtex.

Figure 20. Tensile properties of the fibers spun from a 13 wt.% cellulose solution with a V_e of 5.5 m/min using a 200 holes spinneret, illustrating the elongation, tenacity and young's modulus for DRs 3 – 15.

The master curves of the complex viscosity of the 12, 13 and 14 wt.% solutions (Figure 21 a) show the largest viscosity curve attributed to the 14 wt.% polymer

concentration. The extrapolated η_0 at 85 °C of the solutions was 18 600, 28 400 and 45 500 Pa.s for the 12, 13 and 14 wt.% solutions, respectively. Moreover, due to the relatively large polymer concentration in the 14 wt.% solution, the shear-thinning phase initiated prior to the ones of lower concentrations, agreeing with the studies by Sammons *et al.* (2008) and Hummel *et al.* (2011). Also, a higher elastic modulus of the 14 wt.% solution is depicted in Figure 21 b, where the COP of the dynamic moduli is triggered at lower ω than the 12 and 13 wt.% solutions.

Figure 21. Comparison of 12, 13 and 14 wt.% cellulose solutions of [mTBDH][OAc]. **a.** Complex viscosities of the solutions. **b.** Dynamic moduli of the solutions. **c.** Tensile properties of the spun fibers at DR 11.

All solutions were spun at a temperature equivalent to 30 000 Pa.s, 77, 85 and 92 °C for the 12, 13 and 14 wt.%, respectively. The tensile properties, Figure 21 c, specify that all fibers from the different concentrations have almost matching tenacities, however fibers from 13 and 14 wt.% solutions exhibited slightly better elongation.

In addition to the previous trials, we were also interested in testing the spinnability of a 13 wt.% cellulose solution prepared under atmospheric pressure to access whether the entrapped air bubbles in the dope solution can disturb the spinning process. Interestingly, the dope spinning was smooth with no significant interruptions. In another trial, a 400-hole spinneret was used instead. Table 19 summarizes the tensile properties of the spun fibers from the 13 wt.%

cellulose solutions. With the 400-hole spinneret, we observed more stability during spinning when the temperature was decreased from 85 °C (30 000 Pa.s) to 77 °C (40 000 Pa.s). Besides the number of holes, other spinneret parameters can modify the spinning conditions such as hole density and geometry of the inner capillary, which were not investigated in these trials.

Table 19. Tensile properties of spun fibers at DR 11 spun from 13 wt.% cellulose solutions with a V_e of 5.5.

Condition	No.	Titer	Tenacity	Elongation
		dtex	cN/tex	%
No vacuum	1	1.3 ± 3	49.9 ± 6.1	9.5 ± 1.8
400 hole spinneret	2	1.3 ± 0.3	52.6 ± 6	8.9 ± 1.9

5.5 Additional Recycling Using [mTBDH][OAc]

An extended set of trials, **A.T. 2**, took place over 20 cycles to dissolve and spin 13 wt.% cellulose using [mTBDH][OAc] IL, and recover the dilute solvent thereof. The study was performed on the KS-15 spin unit using a single-hole spinneret and the 4 L coagulation bath. The purpose of these trials was first to test the coagulation of the cellulose filament in a spinbath-containing higher IL concentrations, which was possible because of the small volume of the KS-15 coagulation bath. Consequently, this eliminated the need of the centrifuge evaporator during the solvent recovery process. Therefore, the solvent was recycled only *via* TFE-1 and TFE-2 units. Additionally, we wanted to study the effect of numerous recycling cycles on the solvent properties. Figure 22 a describes the composition of the recovered IL from TFE-2. It comprised a residual water in the range of 3.4 – 4.6 wt.%, hydrolysis products of 0.4 – 2.7 wt.% and an AcOH/mTBD ratio of 1.08 – 1.16. Likewise, this composition allowed complete dissolution of cellulose in all cycles. Interestingly, the dopes were not filtrated before spinning, which had no effect on the spinnability of the dopes.

While adopting the same $IL_{Theor\ recovery\ rate}$ term defined above, we can deduce that 97.8 – 99.5 wt.% of the IL was recovered with the remainder amount consumed in the hydrolysis reactions as seen in Figure 22 b. In this trial, it is clear that there is no accumulation in the hydrolysis products. On the contrary, as shown in Figure 22 b, the hydrolysis trend decreases in the recovered solvent over the increasing number of cycles, which again suggests that the solvent mixture can reach an equilibrium at low hydrolysis concentrations. Hence, little make-up IL can be anticipated in a large-scale process. The same is true for the AcOH/mTBD ratio, where a plateau was predominant in Figure 22 a, implying a vapor-liquid molar equilibrium at these conditions.

Figure 22. Thermal recovery of [mTBDH][OAc] in **A.T. 2**. **a.** Composition of the recovered solvent. **b.** Recovery rate of the IL relative to the hydrolysis content. **c.** Rheological properties of the 13 wt.% cellulose solutions at 85 °C.

The rheological properties of the cellulose solutions are provided in Figure 22 c, showing marginal discrepancies (apart from the inconsistent values of cycle 12) in η_0 (25 000 – 40 000 Pa.s), COP (3500 – 4500 Pa) and ω (0.6 – 1.2 s⁻¹). In cycle 6 and 7, the fiber spinning process was not possible because of a wrong set-up of the spinning unit. As mentioned, one of the purposes of **A.T. 2** was to test the spinning at various solvent concentrations in the spinbath, starting from pure water to 10, 20, 30 and even 40 wt.% IL. The spinnability was good by and large at concentrations below 40 wt.%. A DR max of 16 was achieved for pure water, 10 and 20 wt.% IL, but dropped to 14 for 30 wt.% IL and further to 10 for the 40 wt.% IL. In Figure 23 a, the tensile properties (DR 11) of the fibers from 10, 20 and 30 wt.% indicate similar figures, matching that of spinbath with pure water. The ability to spin stable fibers in a spinbath of high solvent concentration benefits the economy of the Ioncell process by reducing the total energy needed in the evaporation stages. Nevertheless, this was only tested using the single-hole spinneret and hence, needs to be confirmed in the future with the 200- and 400-hole spinnerets.

Based on these results, we chose to include the fiber spinning at 20 wt.% spinbath concentration in all the cycles that succeeded cycle 3. As disclosed in Figure 23 b, the average DR max increased with the progress of the cycles, reaching 14

– 15. This may reflect a better experience in executing the spinning process rather than a specific property change of the spun solution. The tenacity and Young's modulus were recorded for the fibers thereof, Figure 23 c. A Young's modulus of 16 – 20 GPa is in good alignment with the figure depicted in **Paper I** (17.4 GPa) of the same IL.

Figure 23. a. Tensile properties of the fibers spun in a spinbath of different solvent concentrations b. DR max of the fibers from a pure spinbath and that of 20 wt.% IL c. Tenacity and Young's modulus of the spun fibers (DR11) from a pure spinbath and that of 20 wt.% IL.

6. Future Outlook

As mentioned earlier, the scaling up of the Ioncell process is on-going. The start-up of the pilot-plant is expected to take place during 2021. Hence, several parameters are being investigated to facilitate the expansion process. For example, the replacement of a blade kneader with a screw extruder may reduce the dissolution time significantly, from 60 – 90 mins to around 12 mins, and therefore the thermal stress on the IL during dissolution is also decreased. Meanwhile, it may be beneficial to target the residual water in the recovered IL to about 10 wt.% while initiating the mixing of the polymer and the solvent at milder viscosities. The removal of the remaining water will then occur in the extruder at high vacuums to achieve full dissolution. However, this might affect the generation of hydrolysis products, which need to be closely monitored. The dimensions of the spinneret, number of holes, hole density and the geometry of the capillary, are also important parameters for the scale-up. As the processing of large flow rates of the solution requires a spinneret with a large number of holes to compensate the pressure build-up in the spinning cylinder. Currently, a 500 holes spinneret of L/D of 1 is being inspected. The air-gap conditioning with a suitable humidifier may improve the fiber stretchability (elasticity) in the air-gap and consequently, their tensile properties. It can also allow using spinnerets of higher hole density without the gluing of the filaments in the air-gap.

Although [mTBDH][OAc] proved to be a very promising solvent, yet, the continuous pursuit of a more hydrothermally stable IL with higher ionicity, and is able to deliver fibers of better properties, can replace [mTBDH][OAc]. Still, more efforts are needed to develop a strategy to revert the hydrolysis products back to the superbase in a side-stream, which can allow the use of the cheaper DBN in a large-scale process. The same can be applied to the other amidine-based superbase DBU since it is more stable towards hydrolysis than DBN. It may also be interesting to research ILs of mixed bases and an acid conjugate, where the acid-to-individual base mole ratio is near the azeotropic composition, yet the acid-to-total bases mole ratio is 1. This may disrupt the crystalline lattice of the mixture and create a solvent system of low melting point, which may benefit the process economy. On the other hand, this can add further complications to the recycling process, as the hydrolysis products would emerge from both superbases.

Finally, further studies are needed on a large scale to quantify and separate the inorganics and short polymer that can accumulate in a continuous process.

7. Conclusions

This work summarized in this thesis serves as a first milestone in the development of the Ioncell technology towards a closed-loop process. Strictly speaking, we focused on the recyclability of the ILs in the scope of producing MMCFs. The recovery of the solvent from the coagulation bath was achieved by adopting a sequence of evaporation stages that allowed ≤ 4.6 wt.% residual water. The work structure was established to select a solvent with an increased cellulose dissolution power, a pronounced hydrothermal stability, and which is capable of producing fibers of high mechanical properties. The guanidine-based IL [mTBDH][OAc] matched all the required criteria and proved to be a better choice as a solvent over the amidine-based IL [DBNH][OAc] in the Lyocell process, answering one of the main research questions. The simulation of the ILs composition to include the alterations (hydrolysis products, different A/B ratio and residual water) revealed that [mTBDH][OAc] is more tolerant to all alterations in the individual or in the combined state, while [DBNH][OAc] proved to be more sensitive, particularly to the slight increase of the A/B ratio to 1.1.

Although, when both ILs are pure and equimolar, they are capable of fully dissolving the 13 wt.% cellulose. However, the thermal recovery of [DBNH][OAc] revealed significant hydrolysis products and an elevated A/B ratio that killed the solvation power of the IL. Contrarily, [mTBDH][OAc] demonstrated substantially better resistance to hydrolysis reactions, and to the base vaporization. Moreover, there was no accumulation in the hydrolysis products nor increase in the A/B ratio over the prolonged cycles (**A.T. 2**), which supports an evident equilibrium in the recovered IL composition. Consequently, the alterations present in the recovered [mTBDH][OAc] were well in the region of good cellulose dissolution ($> 97\%$). The rheological properties of the cellulose solutions of recovered [mTBDH][OAc] were akin to that of the fresh IL with barely any deviation in the complex viscosity and the dynamic moduli, which confirms the preservation of the viscoelastic properties of the solutions. Similarly, we detected slight reductions in the cellulose MMD from the recovered [mTBDH][OAc] that did not impact the properties of the produced fibers. Finally, we validated the ability to spin fibers in a coagulation bath containing 20 – 30 wt.% IL with no complications.

While these results are promising for the development of the IL-based Lyocell process, the proof of the long-term hydrothermal stability of the [mTBDH][OAc] need to be established in a continuous large-scale process. This will be a good foundation for a future comparison between the guanidine-based

solvent and NMMO in aspects concerning the economy and profitability of the Lyocell process and future aspirations in the MMCF market.

References

- Abu-Eishah, SI 2011, 'Ionic Liquids Recycling for Reuse' in *Ionic Liquids - Classes and Properties*, ed S Handy, InTech, pp. 239–273.
- Adusumali, R-B, Reifferscheid, M, Weber, H, Roeder, T, Sixta, H & Gindl, W 2006, 'Mechanical Properties of Regenerated Cellulose Fibres for Composites', *Macromolecular Symposia*, vol. 244, no. 1, pp. 119–125.
- Adusumalli, R-B, Keckes, J, Martinschitz, KJ, Boesecke, P, Weber, H, Roeder, T, Sixta, H & Gindl, W 2009, 'Comparison of molecular orientation and mechanical properties of lyocell fibre tow and staple fibres', *Cellulose*, vol. 16, no. 5, pp. 765–772.
- Ahmad, W, Ostonen, A, Jakobsson, K, Uusi-Kyyny, P, Alopaeus, V, Hyväkkö, U & King, AWT 2016, 'Feasibility of thermal separation in recycling of the distillable ionic liquid [DBNH][OAc] in cellulose fiber production', *Chemical Engineering Research and Design*, vol. 114, pp. 287–298.
- Ahn, C, Yoo, HJ, Oh, Y-S, Han, S-S, Lee, HJ, Kim, JH, Song, K-H & Rhie, JS 2005, 'Evaluating the physical and fabric hand characteristics of lyocell fabrics made with different wood pulps', *Textile Research Journal*, vol. 75, no. 2, pp. 139–143.
- Angell, CA, Byrne, N & Belieres, J-P 2007, 'Parallel Developments in Aprotic and Protic Ionic Liquids: Physical Chemistry and Applications', *Accounts of Chemical Research*, vol. 40, no. 11, pp. 1228–1236.
- Anthony, JL, Maginn, EJ & Brennecke, JF 2001, 'Solution Thermodynamics of Imidazolium-Based Ionic Liquids and Water', *The Journal of Physical Chemistry B*, vol. 105, no. 44, pp. 10942–10949.
- Asaadi, S, Hummel, M, Hellsten, S, Härkäsalmi, T, Ma, Y, Michud, A & Sixta, H 2016, 'Renewable High-Performance Fibers from the Chemical Recycling of Cotton Waste Utilizing an Ionic Liquid', *ChemSusChem*, vol. 9, no. 22, pp. 3250–3258.
- Audemars, G, *Obtaining and Treating Vegetable Fibres* 1855, British Patent 283.
- Baird, ZS, Uusi-Kyyny, P, Witos, J, Rantamäki, AH, Sixta, H, Wiedmer, SK & Alopaeus, V 2020, 'Vapor–Liquid Equilibrium of Ionic Liquid 7-Methyl-

- 1,5,7-triazabicyclo[4.4.0]dec-5-enium Acetate and Its Mixtures with Water', *Journal of Chemical & Engineering Data*, vol. 65, no. 5, pp. 2405–2421.
- Blanchard, LA, Hancu, D, Beckman, EJ & Brennecke, JF 1999, 'Green processing using ionic liquids and CO₂', *Nature*, vol. 399, no. 6731, pp. 28–29.
- Brandt, A, Gräsvik, J, Hallett, JP & Welton, T 2013, 'Deconstruction of lignocellulosic biomass with ionic liquids'. *Green Chemistry*, vol. 15, no. 3, pp. 550–583.
- Brandt, A, Hallett, JP, Leak, DJ, Murphy, RJ & Welton, T 2010, 'The effect of the ionic liquid anion in the pretreatment of pine wood chips', *Green Chemistry*, vol. 12, no. 4, pp. 672–679.
- Buijtenhuijs, FA, Abbas, M & Witteveen, AJ 1986, 'The degradation and stabilization of cellulose dissolved in N-methylmorpholine-N-oxide (NMMO)', *Papier*, vol. 40, no. 12, pp. 615–619.
- Carrillo, F, Colom, X, Valldeperas, J, Evans, D, Huson, M & Church, J 2003, 'Structural characterization and properties of lyocell fibers after fibrillation and enzymatic defibrillation finishing treatments', *Textile Research Journal*, vol. 73, no. 11, pp. 1024–1030.
- Cesa, FS, Turra, A, Checon, HH, Leonardi, B & Baroque-Ramos, J 2020, 'Laundering and textile parameters influence fibers release in household washings', *Environmental pollution (Barking, Essex : 1987)*, vol. 257, p. 113553.
- ChemFiles 2005. Available from: <https://www.sigmaaldrich.com/technical-documents/articles/chemfiles/ionic-liquidso.html>.
- Chen, X, Zhang, Y, Cheng, L & Wang, H 2009, 'Rheology of Concentrated Cellulose Solutions in 1-Butyl-3-methylimidazolium Chloride', *Journal of Polymers and the Environment*, vol. 17, no. 4, pp. 273–279.
- Chidambareswaran, PK, Sreenivasan, S, Patil, NB & Lokhande, HT 1982, 'Further studies on cellulose III polymorphs. Transformations to cellulose IV lattices and subsequent reactions', *Journal of Applied Polymer Science*, vol. 27, no. 2, pp. 709–730.
- Choudhury, AR, Winterton, N, Steiner, A, Cooper, AI & Johnson, KA 2005, 'In situ crystallization of low-melting ionic liquids', *Journal of the American Chemical Society*, vol. 127, no. 48, pp. 16792–16793.
- Coulsey, HA 1995, 'The formation and structure of a new cellulosic fiber', *Lenzinger Berichte*, vol. 75, pp. 60–61.
- Deng, Y, Long, T, Zhang, D, Chen, J & Gan, S 2009, 'Phase Diagram of [Amim]Cl + Salt Aqueous Biphasic Systems and Its Application for [Amim]Cl Recovery [†]', *Journal of Chemical & Engineering Data*, vol. 54, no. 9, pp. 2470–2473.

- Dibble, DC, Li, C, Sun, L, George, A, Cheng, A, Çetinkol, ÖP, Benke, P, Holmes, BM, Singh, S & Simmons, BA 2011, 'A facile method for the recovery of ionic liquid and lignin from biomass pretreatment', *Green Chemistry*, vol. 13, no. 11, pp. 3255–3264.
- Diddens, I, Murphy, B, Krisch, M & Müller, M 2008, 'Anisotropic Elastic Properties of Cellulose Measured Using Inelastic X-ray Scattering', *Macromolecules*, vol. 41, no. 24, pp. 9755–9759.
- Dupont, D, Depuydt, D & Binnemans, K 2015, 'Overview of the Effect of Salts on Biphasic Ionic Liquid/Water Solvent Extraction Systems: Anion Exchange, Mutual Solubility, and Thermomorphic Properties', *The Journal of Physical Chemistry B*, vol. 119, no. 22, pp. 6747–6757.
- Earle, MJ & Seddon, KR 2000, 'Ionic liquids. Green solvents for the future', *Pure and applied chemistry*, vol. 72, no. 7, pp. 1391–1398.
- Earle, MJ, Esperança, JMSS, Gilea, MA, Canongia Lopes, JN, Rebelo, LPN, Magee, JW, Seddon, KR & Widegren, JA 2006, 'The distillation and volatility of ionic liquids', *Nature*, vol. 439, no. 7078, pp. 831–834. Available from: <https://doi.org/10.1038/nature04451>.
- Ebner, G, Schiehser, S, Potthast, A & Rosenau, T 2008, 'Side reaction of cellulose with common 1-alkyl-3-methylimidazolium-based ionic liquids', *Tetrahedron Letters*, vol. 49, no. 51, pp. 7322–7324.
- Eichinger, D 2012, 'A vision of the world of cellulosic fibers in 2020', *Lenzinger Berichte*, vol. 90, pp. 1–7.
- Ellen MacArthur Foundation 2017, *A New Textiles Economy: Redesigning Fashion's Future*. Available from: https://www.ellenmacarthurfoundation.org/assets/downloads/publications/A-New-Textiles-Economy_Full-Report_Updated_1-12-17.pdf.
- Elsayed, S, Hellsten, S, Guizani, C, Witos, J, Rissanen, M, Rantamäki, AH, Varis, P, Wiedmer, SK & Sixta, H 2020a, 'Recycling of Superbase-Based Ionic Liquid Solvents for the Production of Textile-Grade Regenerated Cellulose Fibers in the Lyocell Process', *ACS Sustainable Chemistry & Engineering*, vol. 8, no. 37, pp. 14217–14227.
- Elsayed, S, Hummel, M, Sawada, D, Guizani, C, Rissanen, M & Sixta, H 2021, 'Superbase-based protic ionic liquids for cellulose filament spinning', *Cellulose*, vol. 28, no. 01, pp. 533–547.
- Elsayed, S, Viard, B, Guizani, C, Hellsten, S, Witos, J & Sixta, H 2020b, 'Limitations of Cellulose Dissolution and Fiber Spinning in the Lyocell Process Using [mTBDH][OAc] and [DBNH][OAc] Solvents', *Industrial & Engineering Chemistry Research*, vol. 59, no. 45, pp. 20211–20220.
- European Parliament 2019, *Parliament seals ban on throwaway plastics by 2021*. Available from: <https://www.europarl.europa.eu/news/en/press-room/20190321IPR32111/parliament-seals-ban-on-throwaway-plastics-by-2021>.

- Eurostat 2020, *Renewable energy in the EU in 2018*. Available from: https://ec.europa.eu/eurostat/statistics-explained/index.php/Renewable_energy_statistics#Share_of_renewable_energy_almost_doubled_between_2004_and_2018.
- Everaert, G, van Cauwenberghe, L, Rijcke, M de, Koelmans, AA, Mees, J, Vandegehuchte, M & Janssen, CR 2018, 'Risk assessment of microplastics in the ocean: Modelling approach and first conclusions', *Environmental Pollution*, vol. 242, pp. 1930–1938.
- Feng, L & Chen, Z-l 2008, 'Research progress on dissolution and functional modification of cellulose in ionic liquids', *Journal of Molecular Liquids*, vol. 142, 1-3, pp. 1–5.
- Fink, H-P, Weigel, P, Purz, HJ & Ganster, J 2001, 'Structure formation of regenerated cellulose materials from NMMO-solutions', *Progress in Polymer Science*, vol. 26, no. 9, pp. 1473–1524.
- Fukaya, Y, Hayashi, K, Wada, M & Ohno, H 2008, 'Cellulose dissolution with polar ionic liquids under mild conditions: required factors for anions', *Green Chemistry*, vol. 10, no. 1, pp. 44–46.
- Gardner, KH & Blackwell, J 1974, 'The structure of native cellulose', *Biopolymers*, vol. 13, no. 10, pp. 1975–2001.
- Gericke, M, Schlufte, K, Liebert, T, Heinze, T & Budtova, T 2009, 'Rheological properties of cellulose/ionic liquid solutions: from dilute to concentrated states', *Biomacromolecules*, vol. 10, no. 5, pp. 1188–1194.
- Goldstein, MC & Goodwin, DS 2013, 'Gooseneck barnacles (*Lepas* spp.) ingest microplastic debris in the North Pacific Subtropical Gyre', *PeerJ*, vol. 1, e184.
- Goswami, P, Blackburn, RS, Taylor, J & White, P 2011, 'Sorption of dyes on cellulose II: effect of alkali treatment of fibre and dye structure', *Cellulose*, vol. 18, no. 4, pp. 1063–1072.
- Guizani, C, Larkiala, S, Moriam, K, Sawada, D, Elsayed, S & Rantasalo, S 2020, 'Air gap spinning of a cellulose solution in an ionic liquid with a novel vertically arranged spinning bath to simulate a closed loop operation in the Ioncell® process.', *Journal of Applied Polymer Science*, vol. 138, no. 5, e49787.
- Gutowski, KE, Broker, GA, Willauer, HD, Huddleston, JG, Swatoski, RP, Holbrey, JD & Rogers, RD 2003, 'Controlling the Aqueous Miscibility of Ionic Liquids: Aqueous Biphasic Systems of Water-Miscible Ionic Liquids and Water-Structuring Salts for Recycle, Metathesis, and Separations', *Journal of the American Chemical Society*, vol. 125, no. 22, pp. 6632–6633.
- Hallett, JP & Welton, T 2011, 'Room-temperature ionic liquids: solvents for synthesis and catalysis. 2', *Chemical reviews*, vol. 111, no. 5, pp. 3508–3576.

- Haslinger, S, Hummel, M, Anghelescu-Hakala, A, Määttänen, M & Sixta, H 2019a, 'Upcycling of cotton polyester blended textile waste to new man-made cellulose fibers', *Waste management (New York, N.Y.)*, vol. 97, pp. 88–96.
- Haslinger, S, Wang, Y, Rissanen, M, Lossa, MB, Tantt, M, Ilen, E, Määttänen, M, Harlin, A, Hummel, M & Sixta, H 2019b, 'Recycling of vat and reactive dyed textile waste to new colored man-made cellulose fibers', *Green Chemistry*, vol. 21, no. 20, pp. 5598–5610.
- Hauru, LKJ, Hummel, M, King, AWT, Kilpeläinen, I & Sixta, H 2012, 'Role of solvent parameters in the regeneration of cellulose from ionic liquid solutions', *Biomacromolecules*, vol. 13, no. 9, pp. 2896–2905.
- Hauru, LKJ, Hummel, M, Nieminen, K, Michud, A & Sixta, H 2016, 'Cellulose regeneration and spinnability from ionic liquids', *Soft matter*, vol. 12, no. 5, pp. 1487–1495.
- Haward, SJ, Sharma, V, Butts, CP, McKinley, GH & Rahatekar, SS 2012, 'Shear and extensional rheology of cellulose/ionic liquid solutions', *Biomacromolecules*, vol. 13, no. 5, pp. 1688–1699.
- Heinze, T 2015, 'Cellulose: Structure and Properties' in *Cellulose Chemistry and Properties: Fibers, Nanocelluloses and Advanced Materials*, ed OJ Rojas, Springer International Publishing, Cham, pp. 1–52.
- Hernandez, E, Nowack, B & Mitrano, DM 2017, 'Polyester textiles as a source of microplastics from households: a mechanistic study to understand microfiber release during washing', *Environmental science & technology*, vol. 51, no. 12, pp. 7036–7046.
- Hinterstoisser, B & Salmén, L 2000, 'Application of dynamic 2D FTIR to cellulose', *Vibrational Spectroscopy*, vol. 22, no. 1, pp. 111–118.
- Hon, DN-S 1994, 'Cellulose: a random walk along its historical path', *Cellulose*, vol. 1, no. 1, pp. 1–25.
- Huddleston, JG, Willauer, HD, Swatoski, RP, Visser, AE & Rogers, RD 1998, 'Room temperature ionic liquids as novel media for 'clean' liquid–liquid extraction', *Chem. Commun.*, no. 16, pp. 1765–1766.
- Hummel, M, Michud, A & Sixta, H (eds.) 2011, *Extensional rheology of cellulose-ionic liquid solutions*, Nordic Rheology Conference Helsinki.
- Hummel, M, Michud, A, Tantt, M, Asaadi, S, Ma, Y, Hauru, LKJ, Parviainen, A, King, AWT, Kilpeläinen, I & Sixta, H 2015, 'Ionic Liquids for the Production of Man-Made Cellulosic Fibers: Opportunities and Challenges' in *Cellulose Chemistry and Properties: Fibers, Nanocelluloses and Advanced Materials*, ed OJ Rojas, Springer International Publishing, Cham, pp. 133–168.

- Hyde, AM, Calabria, R, Arvary, R, Wang, X & Klapars, A 2019, 'Investigating the Underappreciated Hydrolytic Instability of 1,8-Diazabicyclo[5.4.0]undec-7-ene and Related Unsaturated Nitrogenous Bases', *Organic Process Research & Development*, vol. 23, no. 9, pp. 1860–1871.
- Industrievereinigung Chemiefaser 2019, *Weltproduktion von Fasern*. Available from: <https://www.ivc-ev.de/de/weltproduktion-von-fasern-balkendiagramm>.
- Isogai, A & Atalla, RH 1998, 'Dissolution of Cellulose in Aqueous NaOH Solutions', *Cellulose*, vol. 5, no. 4, pp. 309–319.
- Jaturapiree, A, Manian, AP, Lenninger, M & Bechtold, T 2011, 'The influence of alkali pretreatments in lyocell resin finishing—Changes in fiber accessibility to crosslinker and catalyst', *Carbohydrate polymers*, vol. 86, no. 2, pp. 612–620.
- Jiang, G, Huang, W, Li, L, Wang, X, Pang, F, Zhang, Y & Wang, H 2012, 'Structure and properties of regenerated cellulose fibers from different technology processes', *Carbohydrate polymers*, vol. 87, no. 3, pp. 2012–2018.
- Jonsson, M, Wayner, DDM & Luszyk, J 1996, 'Redox and Acidity Properties of Alkyl- and Arylamine Radical Cations and the Corresponding Aminyl Radicals 1', *The Journal of Physical Chemistry*, vol. 100, no. 44, pp. 17539–17543.
- Jürgen, L, Josef, S & E., W 2009, *On the Elongation Mechanism of Regenerated Cellulose Fibres*, vol. 48. Available from: <https://www.degruyter.com/view/j/hfsg.1994.48.issue-s1/hfsg.1994.48.s1.72/hfsg.1994.48.s1.72.xml>.
- Kamide, K & Nishiyama, K 2001, 'Cuprammonium processes' in *Regenerated Cellulose Fibres*, ed C Woodings, Woodhead Publishing, pp. 88–155.
- Kessler, MA & Wolfbeis, OS 1989, 'ET(33), a solvatochromic polarity and micellar probe for neutral aqueous solutions', *Chemistry and Physics of Lipids*, vol. 50, no. 1, pp. 51–56.
- King, AWT, Asikkala, J, Mutikainen, I, Järvi, P & Kilpeläinen, I 2011, 'Distillable acid–base conjugate ionic liquids for cellulose dissolution and processing', *Angewandte Chemie International Edition*, vol. 50, no. 28, pp. 6301–6305.
- King, AWT, Parviainen, A, Karhunen, P, Matikainen, J, Hauru, LKJ, Sixta, H & Kilpeläinen, I 2012, 'Relative and inherent reactivities of imidazolium-based ionic liquids: the implications for lignocellulose processing applications', *RSC Advances*, vol. 2, no. 21, pp. 8020–8026.
- Kolpak, FJ & Blackwell, J 1976, 'Determination of the structure of cellulose II', *Macromolecules*, vol. 9, no. 2, pp. 273–278.
- Konkin, A, Wendler, F, Meister, F, Roth, H-K, Aganov, A & Ambacher, O 2007, 'Degradation processes in the cellulose/N-methylmorpholine-N-oxide

- system studied by HPLC and ESR. Radical formation/recombination kinetics under UV photolysis at 77 K', *Cellulose*, vol. 14, no. 5, pp. 457–468.
- Kosan, B, Michels, C & Meister, F 2008, 'Dissolution and forming of cellulose with ionic liquids', *Cellulose*, vol. 15, no. 1, pp. 59–66.
- Kosmulski, M, Gustafsson, J & Rosenholm, JB 2004, 'Thermal stability of low temperature ionic liquids revisited', *Thermochimica Acta*, vol. 412, 1-2, pp. 47–53.
- Kreze, T & Malej, S 2003, 'Structural Characteristics of New and Conventional Regenerated Cellulosic Fibers', *Textile Research Journal*, vol. 73, no. 8, pp. 675–684.
- Krässig, H & Kitchen, W 1961, 'Factors influencing tensile properties of cellulose fibers', *Journal of Polymer Science*, vol. 51, no. 155, pp. 123–172.
- Kuzmina, O, Bhardwaj, J, Vincent, SR, Wanasekara, ND, Kalossaka, LM, Griffith, J, Potthast, A, Rahatekar, S, Eichhorn, SJ & Welton, T 2017, 'Superbase ionic liquids for effective cellulose processing from dissolution to carbonisation', *Green Chemistry*, vol. 19, no. 24, pp. 5949–5957.
- Lang, H, Laskowski, I, Lukanoff, B, Schleicher, H, Mertel, H, Franz, H & Taeger, E 1986, 'Cellulose in N-Methylmorpholin-N-Oxid (MMNO)(Investigations of Solutions of Cellulose in N-Methylmorpholin-N-Oxid)', *Cellulose Chemistry and Technology*, vol. 20, no. 3, pp. 289–301.
- Le, N-D, Trogen, M, Ma, Y, Varley, RJ, Hummel, M & Byrne, N 2020, 'Cellulose-lignin composite fibers as precursors for carbon fibers: Part 2 - The impact of precursor properties on carbon fibers', *Carbohydrate polymers*, vol. 250, p. 116918.
- Lemus, J, Palomar, J, Heras, F, Gilarranz, MA & Rodriguez, JJ 2012, 'Developing criteria for the recovery of ionic liquids from aqueous phase by adsorption with activated carbon', *Separation and Purification Technology*, vol. 97, pp. 11–19.
- Lenzing 2019, *Lenzing Lays the Foundation Stone for World's Largest Lyocell Fibers Plant*. Available from: <https://www.lenzing.com/newsroom/press-releases/press-release/lenzing-lays-the-foundation-stone-for-worlds-larg>.
- Liebert, T 2010, 'Cellulose solvents—remarkable history, bright future' in *Cellulose solvents: for analysis, shaping and chemical modification*, ACS Publications, pp. 3–54.
- Liebner, F, Patel, I, Ebner, G, Becker, E, Horix, M, Potthast, A & Rosenau, T 2010, 'Thermal aging of 1-alkyl-3-methylimidazolium ionic liquids and its effect on dissolved cellulose', *Holzforschung*, vol. 64, no. 2.
- Lindman, B, Karlström, G & Stigsson, L 2010, 'On the mechanism of dissolution of cellulose', *Journal of Molecular Liquids*, vol. 156, no. 1, pp. 76–81.

- Liu, H, Sale, KL, Simmons, BA & Singh, S 2011, 'Molecular Dynamics Study of Polysaccharides in Binary Solvent Mixtures of an Ionic Liquid and Water', *The Journal of Physical Chemistry B*, vol. 115, no. 34, pp. 10251–10258.
- Liu, Q, Janssen, MHA, van Rantwijk, F & Sheldon, RA 2005, 'Room-temperature ionic liquids that dissolve carbohydrates in high concentrations', *Green Chemistry*, vol. 7, no. 1, pp. 39–42.
- Ma, Y, Asaadi, S, Johansson, L-S, Ahvenainen, P, Reza, M, Alekhina, M, Rautkari, L, Michud, A, Hauru, L, Hummel, M & Sixta, H 2015, 'High-Strength Composite Fibers from Cellulose-Lignin Blends Regenerated from Ionic Liquid Solution', *ChemSusChem*, vol. 8, no. 23, pp. 4030–4039.
- Ma, Y, Hummel, M, Määtänen, M, Särkilahti, A, Harlin, A & Sixta, H 2016, 'Upcycling of waste paper and cardboard to textiles', *Green Chemistry*, vol. 18, no. 3, pp. 858–866.
- Mai, NL, Ahn, K & Koo, Y-M 2014, 'Methods for recovery of ionic liquids—a review', *Process Biochemistry*, vol. 49, no. 5, pp. 872–881.
- Maia, E, Peguy, A & Pérez, S 1981, 'Cellulose organic solvents. I. The structures of anhydrous N-methylmorpholine N-oxide and N-methylmorpholine N-oxide monohydrate', *Acta Crystallographica Section B Structural Crystallography and Crystal Chemistry*, vol. 37, no. 10, pp. 1858–1862.
- Matsuo, M, Sawatari, C, Iwai, Y & Ozaki, F 1990, 'Effect of orientation distribution and crystallinity on the measurement by x-ray diffraction of the crystal lattice moduli of cellulose I and II', *Macromolecules*, vol. 23, no. 13, pp. 3266–3275.
- Medronho, B & Lindman, B 2015, 'Brief overview on cellulose dissolution/regeneration interactions and mechanisms', *Advances in colloid and interface science*, vol. 222, pp. 502–508.
- Meine, N, Benedito, F & Rinaldi, R 2010, 'Thermal stability of ionic liquids assessed by potentiometric titration', *Green Chemistry*, vol. 12, no. 10, pp. 1711–1714.
- Meister, G & Wechsler, M 1998, 'Biodegradation of N-Methylmorpholine-N-oxide', *Biodegradation*, vol. 9, no. 2, pp. 91–102.
- Mekonnen, MM & Hoekstra, AY 2011, 'The green, blue and grey water footprint of crops and derived crop products', *Hydrology and Earth System Sciences*, vol. 15, no. 5, pp. 1577–1600.
- Michud, A, Hummel, M & Sixta, H 2015, 'Influence of molar mass distribution on the final properties of fibers regenerated from cellulose dissolved in ionic liquid by dry-jet wet spinning', *Polymer*, vol. 75, pp. 1–9.
- Michud, A, Hummel, M & Sixta, H 2016, 'Influence of process parameters on the structure formation of man-made cellulosic fibers from ionic liquid

- solution', *Journal of Applied Polymer Science*, vol. 133, no. 30, pp. 177–185.
- Michud, A, Tanttu, M, Asaadi, S, Ma, Y, Netti, E, Kääriäinen, P, Persson, A, Berntsson, A, Hummel, M & Sixta, H 2016, 'Ioncell-F: ionic liquid-based cellulosic textile fibers as an alternative to viscose and Lyocell', *Textile Research Journal*, vol. 86, no. 5, pp. 543–552.
- Morgado, J, Cavaco-Paulo, A & Rousselle, M-A 2000, 'Enzymatic treatment of lyocell—clarification of depilling mechanisms', *Textile Research Journal*, vol. 70, no. 8, pp. 696–699.
- Napper, IE & Thompson, RC 2016, 'Release of synthetic microplastic plastic fibres from domestic washing machines: Effects of fabric type and washing conditions', *Marine pollution bulletin*, vol. 112, 1-2, pp. 39–45.
- Nishiyama, Y, Asaadi, S, Ahvenainen, P & Sixta, H 2019, 'Water-induced crystallization and nano-scale spinodal decomposition of cellulose in NMMO and ionic liquid dope', *Cellulose*, vol. 26, no. 1, pp. 281–289.
- Novoselov, NP, Sashina, ES, Petrenko, VE & Zaborsky, M 2007, 'Study of dissolution of cellulose in ionic liquids by computer modeling', *Fibre Chemistry*, vol. 39, no. 2, pp. 153–158.
- Oediger, H, Kabbe, H-J, Möller, F & Eiter, K 1966, '1,5-Diaza-bicyclo[4.3.0]nonen-(5). Ein neues Reagenz zur Einführung von Doppelbindungen', *Chemische Berichte*, vol. 99, no. 6, pp. 2012–2016.
- Oediger, H, Möller, F & Eiter, K 1972, 'Bicyclic Amidines as Reagents in Organic Syntheses', *Synthesis*, vol. 1972, no. 11, pp. 591–598.
- Osmanbegovic, N, Yuan, L, Lorenz, H & Louhi-Kultanen, M 2020, 'Freeze Concentration of Aqueous [DBNH][OAc] Ionic Liquid Solution', *Cryscals*, vol. 10, no. 3, pp. 147–160.
- Ostonen, A, Bervas, J, Uusi-Kyyny, P, Alopaeus, V, Zaitsau, DH, Emel'yanenko, VN, Schick, C, King, AWT, Helminen, J, Kilpeläinen, I, Khachatryan, AA, Varfolomeev, MA & Verevkin, SP 2016, 'Experimental and Theoretical Thermodynamic Study of Distillable Ionic Liquid 1,5-Diazabicyclo[4.3.0]non-5-enium Acetate', *Industrial & Engineering Chemistry Research*, vol. 55, no. 39, pp. 10445–10454.
- Palomar, J, Lemus, J, Gilarranz, MA & Rodriguez, JJ 2009, 'Adsorption of ionic liquids from aqueous effluents by activated carbon', *Carbon*, vol. 47, no. 7, pp. 1846–1856.
- Papkov, SP, Ukhanova, ZV & Antipova, RV 1969, 'Effect of zinc sulphate in the coagulation bath and a modifier in the viscose on the first fibre-spinning stage', *Fibre Chemistry*, vol. 1, no. 2, pp. 172–174.
- Parviainen, A, King, AWT, Mutikainen, I, Hummel, M, Selg, C, Hauru, LKJ, Sixta, H & Kilpeläinen, I 2013, 'Predicting cellulose solvating capabilities of acid-base conjugate ionic liquids', *ChemSusChem*, vol. 6, no. 11, pp. 2161–2169.

- Parviainen, A, Wahlström, R, Liimatainen, U, Liitiä, T, Rovio, S, Helminen, J, Hyvää, U, King, AWT, Suurnäkki, A & Kilpeläinen, I 2015, 'Sustainability of cellulose dissolution and regeneration in 1,5-diazabicyclo[4.3.0]non-5-enium acetate: a batch simulation of the IONCELL-F process', *RSC Advances*, vol. 5, no. 85, pp. 69728–69737.
- Pinkert, A, Marsh, KN, Pang, S & Staiger, MP 2009, 'Ionic Liquids and Their Interaction with Cellulose', *Chemical reviews*, vol. 109, no. 12, pp. 6712–6728.
- Potthast, A, Radosta, S, Saake, B, Lebioda, S, Heinze, T, Henniges, U, Isogai, A, Koschella, A, Kosma, P & Rosenau, T 2015, 'Comparison testing of methods for gel permeation chromatography of cellulose: coming closer to a standard protocol', *Cellulose*, vol. 22, no. 3, pp. 1591–1613.
- Potthast, A, Rosenau, T, Buchner, R, Röder, T, Ebner, G, Bruggachner, H, Sixta, H & Kosma, P 2002, 'The cellulose solvent system N, N-dimethylacetamide/lithium chloride revisited: the effect of water on physicochemical properties and chemical stability', *Cellulose*, vol. 9, no. 1, pp. 41–53.
- Rabideau, BD, Agarwal, A & Ismail, AE 2014, 'The role of the cation in the solvation of cellulose by imidazolium-based ionic liquids', *The Journal of Physical Chemistry B*, vol. 118, no. 6, pp. 1621–1629.
- Remsing, RC, Swatoski, RP, Rogers, RD & Moyna, G 2006, 'Mechanism of cellulose dissolution in the ionic liquid 1-n-butyl-3-methylimidazolium chloride: a ^{13}C and $^{35/37}\text{Cl}$ NMR relaxation study on model systems', *Chemical Communications*, no. 12, pp. 1271–1273.
- Ribeiro, FMS, Lima, CFRAC, Silva, AMS & Santos, LMNBF 2018, 'Experimental Evidence for Azeotrope Formation from Protic Ionic Liquids', *Chemphyschem*, vol. 19, no. 18, pp. 2364–2369.
- Ribeiro, FMS, Lima, CFRAC, Vaz, ICM, Rodrigues, Ana S. M. C., Sapei, E, Melo, A, Silva, AMS & Santos, LMNBF 2017, 'Vaporization of protic ionic liquids derived from organic superbases and short carboxylic acids', *Physical chemistry Chemical Physics*, vol. 19, no. 25, pp. 16693–16701.
- Roselli, A 2017, 'Extraction of Hemicelluloses from a Kraft Paper Pulp with an Ionic Liquid water Mixture', *95260756*.
- Roselli, A, Hummel, M, Monshizadeh, A, Maloney, T & Sixta, H 2014, 'Ionic liquid extraction method for upgrading eucalyptus kraft pulp to high purity dissolving pulp', *Cellulose*, vol. 21, no. 5, pp. 3655–3666.
- Rosenau, T, Potthast, A, Adorjan, I, Hofinger, A, Sixta, H, Firgo, H & Kosma, P 2002, 'Cellulose solutions in N-methylmorpholine-N-oxide (NMMO) – degradation processes and stabilizers', *Cellulose*, vol. 9, pp. 283–291.
- Rosenau, T, Potthast, A, Sixta, H & Kosma, P 2001, 'The chemistry of side reactions and byproduct formation in the system NMMO/cellulose (Lyocell process)', *Progress in Polymer Science*, vol. 26, no. 9, pp. 1763–1837.

- Sakurada, I, Ito, T & Nakamae, K 1964, 'Elastic moduli of polymer crystals for the chain axial direction' *Die Makromolekulare Chemie*, vol. 75, no. 1, pp. 1–10.
- Sammons, RJ, Collier, JR, Rials, TG & Petrovan, S 2008, 'Rheology of 1-butyl-3-methylimidazolium chloride cellulose solutions. I. Shear rheology', *Journal of Applied Polymer Science*, vol. 110, no. 2, pp. 1175–1181.
- Schäfer, T, Rodrigues, CM, Am Afonso, C & Crespo, JG 2001, 'Selective recovery of solutes from ionic liquids by pervaporation—a novel approach for purification and green processing', *Chemical Communications*, no. 17, pp. 1622–1623.
- Shahriari, S, Neves, Catarina M. S. S., Freire, MG & Coutinho, JAP 2012, 'Role of the Hofmeister series in the formation of ionic-liquid-based aqueous biphasic systems', *The journal of physical chemistry. B*, vol. 116, no. 24, pp. 7252–7258.
- Shen, L, Worrell, E & Patel, MK 2010, 'Environmental impact assessment of man-made cellulose fibres', *Resources, Conservation and Recycling*, vol. 55, no. 2, pp. 260–274.
- Sixta, H, Michud, A, Hauru, L, Asaadi, S, Ma, Y, W.T. King, A, Kilpeläinen, I & Hummel, M 2015, 'Ioncell-F: A High-strength regenerated cellulose fibre', *Nordic pulp & paper research journal*, vol. 30, no. 1, pp. 43–57.
- Sklavounos, E, Helminen, JKJ, Kyllönen, L, Kilpeläinen, I & King, AWT 2011, 'Ionic Liquids: Recycling' in *Encyclopedia of inorganic and bioinorganic chemistry*, ed RA Scott, John Wiley and Sons, Inc, [Hoboken, NJ], pp. 1–16.
- Smith, JA, Webber, GB, Warr, GG & Atkin, R 2013, 'Rheology of protic ionic liquids and their mixtures', *The journal of physical chemistry. B*, vol. 117, no. 44, pp. 13930–13935.
- Su, L, Li, M, Zhu, X, Wang, Z, Chen, Z, Li, F, Zhou, Q & Hong, S 2010, 'In situ crystallization of low-melting ionic liquid [BMIM][PF6] under high pressure up to 2 GPa', *The Journal of Physical Chemistry B*, vol. 114, no. 15, pp. 5061–5065.
- Sun, J, Shi, J, Murthy Konda, N. V. S. N., Campos, D, Liu, D, Nemser, S, Shamshina, J, Dutta, T, Berton, P, Gurau, G, Rogers, RD, Simmons, BA & Singh, S 2017, 'Efficient dehydration and recovery of ionic liquid after lignocellulosic processing using pervaporation', *Biotechnology for Biofuels*, vol. 10, no. 1, pp. 154–167.
- Swatloski, RP, Spear, SK, Holbrey, JD & Rogers, RD 2002, 'Dissolution of Cellulose with Ionic Liquids', *Journal of the American Chemical Society*, vol. 124, no. 18, pp. 4974–4975.

- Szymkowski, S 2017, *UK to ban diesel, gasoline car sales by 2040; follows France, Norway, Holland bans*. Available from: https://www.green-carreports.com/news/1111770_uk-to-ban-diesel-gasoline-car-sales-by-2040-follows-france-norway-holland-bans.
- The Fiber Year. World survey on textiles & nonwovens* 2019. Available from: <http://www.thefiberyear.com/>.
- Wada, M, Chanzy, H, Nishiyama, Y & Langan, P 2004, 'Cellulose III I Crystal Structure and Hydrogen Bonding by Synchrotron X-ray and Neutron Fiber Diffraction', *Macromolecules*, vol. 37, no. 23, pp. 8548–8555.
- Walden, P 1914, 'Molecular weights and electrical conductivity of several fused salts', *Bull Acad Imp Sci (St-Petersbourg)*, pp. 405–422.
- Wang, H, Gurau, G & Rogers, RD 2012, 'Ionic liquid processing of cellulose', *Chemical Society Reviews*, vol. 41, no. 4, pp. 1519–1537.
- Water Footprint Network 2017, *Viscose Fibres Production, An Assessment of Sustainability Issues*. Available from: https://waterfootprint.org/media/downloads/Viscose_fibres_Sustainability.pdf.
- Welter, TR, *Methods to produce alkylated polycyclic guanidine compounds* 2012, US WO2013055747A1.
- Welton, T 1999, 'Room-temperature ionic liquids. Solvents for synthesis and catalysis', *Chemical reviews*, vol. 99, no. 8, pp. 2071–2084.
- Ventura, SPM, Neves, Catarina M. S. S., Freire, MG, Marrucho, IM, Oliveira, J & Coutinho, JAP 2009, 'Evaluation of Anion Influence on the Formation and Extraction Capacity of Ionic-Liquid-Based Aqueous Biphasic Systems', *The Journal of Physical Chemistry B*, vol. 113, no. 27, pp. 9304–9310.
- White, P 2001, 'Lyocell: the production process and market development' in *Regenerated Cellulose Fibres*, ed C Woodings, Woodhead Publishing, pp. 62–87.
- Wilkes, AG 2001, 'The viscose process' in *Regenerated Cellulose Fibres*, ed C Woodings, Woodhead Publishing, pp. 37–61.
- Vitz, J, Erdmenger, T, Haensch, C & Schubert, US 2009, 'Extended dissolution studies of cellulose in imidazolium based ionic liquids', *Green Chemistry*, vol. 11, no. 3, pp. 417–424.
- Woodings, C 2001, 'A brief history of regenerated cellulosic fibres' in *Regenerated Cellulose Fibres*, ed C Woodings, Woodhead Publishing, pp. 1–21.
- Wu, J, Zhang, J, Zhang, H, He, J, Ren, Q & Guo, M 2004, 'Homogeneous Acetylation of Cellulose in a New Ionic Liquid', *Biomacromolecules*, vol. 5, no. 2, pp. 266–268.
- Xu, A, Wang, J & Wang, H 2010, 'Effects of anionic structure and lithium salts addition on the dissolution of cellulose in 1-butyl-3-methylimidazolium-

- based ionic liquid solvent systems', *Green Chemistry*, vol. 12, no. 2, pp. 268–275.
- Yoshizawa, M, Xu, W & Angell, CA 2003, 'Ionic liquids by proton transfer: vapor pressure, conductivity, and the relevance of ΔpK_a from aqueous solutions', *Journal of the American Chemical Society*, vol. 125, no. 50, pp. 15411–15419.
- Zhang, J, Zhang, H, Wu, J, Zhang, J, He, J & Xiang, J 2010, 'NMR spectroscopic studies of cellobiose solvation in EmimAc aimed to understand the dissolution mechanism of cellulose in ionic liquids', *Physical Chemistry Chemical Physics*, vol. 12, no. 8, pp. 1941–1947.
- Zhao, H, Baker, GA, Song, Z, Olubajo, O, Crittle, T & Peters, D 2008, 'Designing enzyme-compatible ionic liquids that can dissolve carbohydrates'. *Green Chemistry*, *Green Chemistry*, vol. 10, no. 6, pp. 696–705.
- Zhao, H, Xia, S & Ma, P 2005, 'Use of ionic liquids as 'green' solvents for extractions', *Journal of Chemical Technology & Biotechnology: International Research in Process, Environmental & Clean Technology*, vol. 80, no. 10, pp. 1089–1096.
- Zhao, Y, Liu, X, Wang, J & Zhang, S 2013, 'Insight into the Cosolvent Effect of Cellulose Dissolution in Imidazolium-Based Ionic Liquid Systems', *The Journal of Physical Chemistry B*, vol. 117, no. 30, pp. 9042–9049.
- Ziabicki, A 1976, *Fundamentals of fibre formation. The science of fibre spinning and drawing*, John Wiley and Sons, London.
- Ziabicki, A & Takserman-Krozer, R 1964a, 'Effect of rheological factors on the length of liquid threads', *Kolloid-Zeitschrift und Zeitschrift für Polymere*, vol. 199, no. 1, pp. 9–13.
- Ziabicki, A & Takserman-Krozer, R 1964b, 'Mechanism of breakage of liquid threads', *Kolloid-Zeitschrift und Zeitschrift für Polymere*, vol. 198, 1-2, pp. 60–65.

Appendix 1

Figure A1. Images of the dissolution state of 13 wt.% cellulose in [DBNH][OAc] containing the individual alterations 5 wt.% water (a), 15 wt.% [APPH][OAc] (b) and 1.1 A/B ratio (c).

Figure A2. Dissolution state of 13 wt.% cellulose in [DBNH][OAc] containing water, [APPH][OAc] and A/B ratio of 3 wt.%, 10 wt.% and 1.05, respectively, over a 15 min duration.

Appendix 2

Table A1. Mass balance of [mTBDH][OAc] and water in TFE-2 over the 5 cycles.

Cy- cle	Feed					Residue					Distillate				
	To- tal g	IL		Water		To- tal g	IL		Water		To- tal g	IL		Water	
		g	wt.%	g	wt.%		g	wt.%	g	wt.%		g	wt.%	g	wt.%
1	1455	1223	84.1	232	15.9	1033	996	96.4	32	3.1	334	18.4	5.5	312	93.1
2	1151	975	84.7	173	15.1	793	768	96.8	17.2	2.2	289	9.7	3.4	277	95.7
3	1093	748	68.5	324	29.6	602	577	95.8	16	2.7	481	11	2.3	469	97.5
4	647	460	71.1	175	27.1	333	315	94.5	9.4	2.8	244	2	0.8	237	97.3
5	427	251	58.9	169	39.6	130	123	94.9	3.4	2.6	243	2.3	1	240	98.9

Appendix 3

Table A2. Yarn mechanical properties for Marimekko demonstration dress.

Yarn	Linear den- sity	Breaking force	Elongation at break	Breaking tenac- ity
	tex	cN	%	cN/tex
[mTBDH][OAc]- lon- cell®	19.9 ± 0.9	490 ± 77	5.7 ± 0.7	24.6 ± 3.7
Tencel™	19.9 ± 0.2	443 ± 34	7.7 ± 0.7	22.3 ± 1.7

Table A3. The fabric testing results of the loncell/Tencel blend fabric (38/62 wt.%) and a reference 100% Tencel fabric. Color fastness and pilling ratings are from 1 to 5 where 5 is the best rating.

Property		loncell/Tencel fab- ric	Tencel fabric*
Dimensional change after 30 °C washing (%)	Warp	+2.2	+1.8
	Weft	+2.6	+0.4
Color fastness to washing at 30 °C	Shade change	4	Blue 4 White 3-4
	Staining CO	4	4
Color fastness to washing at 40 °C	Shade change	4-5	4
	Staining CO	4	4
Color fastness to rubbing after laun- dering at 30 °C	Dry	4-5	3
	Wet	3-4	3
Color fastness to perspiration	Shade change	4-5	n.a.
	Staining CO	4-5	n.a.
Tensile strength (N)	Warp	495	n.a.
	Weft	127	n.a.
Tear strength (g)	Warp	1946	n.a.
	Weft	1880	n.a.
Pilling		4-5	4-5
Abrasion resistance (cycles)		2000	4000
Seam slippage (N)	Warp	116	n.a.
	Weft	>200	n.a.

*Tencel fabric as a reference

9 789526 402802

ISBN 978-952-64-0280-2 (printed)

ISBN 978-952-64-0281-9 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University

School of Chemical Engineering

Department of Bioproducts and Biosystems

www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**