Improving sulphide-mineral flotation with sustainable cellulose-based frother formulations

Ted Nuorivaara

Improving sulphide-mineral flotation with sustainable cellulose-based frother formulations

Ted Nuorivaara

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Chemical Engineering, at a public examination held via remote connection on 7 May 2021 at 12:00.

Remote connection link: <https://aalto.zoom.us/j/68957920838>

Aalto University
School of Chemical Engineering
Department of Chemical and Metallurgical Engineering
Mineral Processing and Recycling

Supervising professor

Assistant Professor Rodrigo Serna-Guerrero, Aalto University, Finland

Preliminary examiners

Dr. Saeed Farrokhpay, Process Optimization For Future, Australia

Associate Professor Saeed Chelgani, Luleå University of Technology, Sweden

Opponent

Associate Professor Przemyslaw Kowalczyk, Norwegian University of Science and Technology, Norway

Aalto University publication series

DOCTORAL DISSERTATIONS 35/2021

© 2021 Ted Nuorivaara

ISBN 978-952-64-0303-8 (printed)

ISBN 978-952-64-0304-5 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-64-0304-5>

Unigrafia Oy

Helsinki 2021

Finland

Author

Ted Nuorivaara

Name of the doctoral dissertation

Improving sulphide-mineral flotation with sustainable cellulose-based frother formulations

Publisher School of Chemical Engineering

Unit Department of Chemical and Metallurgical Engineering

Series Aalto University publication series DOCTORAL DISSERTATIONS 35/2021

Field of research Processing of Materials

Manuscript submitted 27 November 2020

Date of the defence 7 May 2021

Permission for public defence granted (date) 18 March 2021

Language English

☐ **Monograph**

☒ **Article dissertation**

☐ **Essay dissertation**

Abstract

Froth flotation is still the most prominent mineral enrichment process, though its origins are over a century old. Its ample popularity is based on versatile, yet effective operations, and favorable cost efficiency. Despite the historical success of the process, the trend of decreasing grades in available ore bodies, as well as increasing environmental awareness are driving the mining industry towards a new era of sustainable and efficient operations. The present work aims to contribute towards this end by proposing a fundamentally novel type of frother formulation, where typical frothers are partly substituted with a nontoxic and biodegradable cellulose derivative, namely hydroxypropyl methyl cellulose (HPMC), thus forming an interactive polymer-surfactant (PS) mixture.

Considering that there are no earlier reports of this specific PS-mixture and that this kind of an approach had not been explored before in flotation, this thesis presents the first ever scientific investigation to evaluate the applicability of this novel chemistry to be used as reagents in mineral froth flotation. All aspects of this study contain a comparison between two commercial frothers (DowFroth 200 and NasFroth 240), HPMC and their corresponding PS-mixtures.

The first part of this study is focused on interfacial characterization of the PS-mixtures in terms of properties relevant to flotation, i.e., dynamic surface tension, bubble size, foam depth and foam stability. The short-term diffusivity of each species was determined based on the surface tension results. The second part of this study consists of three flotation campaigns conducted with i) natural Cu ore; ii) synthetic Cu ore and synthetic Zn ore, iii) Cu containing tailings.

The results of this thesis show that PS-mixtures exhibit a distinct behavior at the air-liquid interfaces compared with single surfactant species used as commercial frothers. In the first place, the interactions between HPMC and NasFroth 240 resulted in a faster adsorption rate of the PS-complex, which was responsible of generating smaller bubbles that were likely maintained by the steric protection provided by the polymeric component. Furthermore, the presence of HPMC improved foam stability both in single species systems and as a part of a PS-mixture. The observed PS-synergism and its effect on interfacial properties showed clear improvements in flotation performance in all aspects of this thesis. The main advantages were observed as improvements recovery and flotation kinetics, which were connected to a combination of improved froth stability and reduced bubble sizes. Furthermore, the self-stability provided by the PS-mixture helped to maintain a steady level of performance in conditions considered detrimental to flotation (e.g., significantly lower collector concentration or deviance in pH level).

Ultimately, the findings of this thesis indicate the possibility of increasing throughputs by only changing flotation chemistry and exploring novel circuit design or flotation chemicals whose application requires an increased froth stability that is less dependent on mineral hydrophobicity.

Keywords Froth Flotation; Green Chemistry; Hydroxypropyl methyl cellulose; Polymer-surfactant mixture, Frother

ISBN (printed) 978-952-64-0303-8

ISBN (pdf) 978-952-64-0304-5

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Helsinki

Location of printing Helsinki **Year** 2021

Pages 170

urn <http://urn.fi/URN:ISBN:978-952-64-0304-5>

Tekijä

Ted Nuorivaara

Väitöskirjan nimi

Sulfidimineraalien vaahdotusprosessin parantaminen selluloosapohjaisten vaahdotuskemikaalien avulla

Julkaisija Kemian tekniikan korkeakoulu**Yksikkö** Kemian tekniikan ja metallurgian laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 35/2021**Tutkimusala** Materiaalien prosessointi**Käsikirjoituksen pvm** 27.11.2020**Väitöspäivä** 07.05.2021**Väittelyluvan myöntämispäivä** 18.03.2021**Kieli** Englanti☐ **Monografia**☒ **Artikkeliväitöskirja**☐ **Esseeväitöskirja****Tiivistelmä**

Vaahdotus on edelleen yksi merkittävimmistä mineraalien rikastusprosesseista, vaikka sen alkuperät ovat yli vuosisadan takaiset. Sen suosio perustuu monipuoliseen ja tehokkaaseen prosessiin sekä hyvään kustannustehokkuuteen. Prosessin historiallisesta menestyksestä huolimatta, jatkuvasti laskevat arvometallipitoisuudet nykyisissä malmioissa, ja kasvava ympäristötietoisuus ajavat kaivosteollisuutta kohti ympäristöystävällisempää ja tehokkaampaa, aikakautta. Tämä väitöskirja pyrkii edistämään tätä muutosta esittelemällä perustavanlaatuisesti uudenlaisen vaahdotevalmisteen, jossa tyypilliset vaahdotteet korvataan osittain myrkyttömällä ja biohajoavalla selluloosajohdannaisella, hydroksipropyli metyyliiselluloosalla (HPMC), täten muodostaen interaktiivisen polymeeri-tensidi (PT) -yhdistelmän.

Ottaen huomioon, että näistä PT-yhdistelmistä ei ole aiempaa tutkimustietoa ja että tällaista lähestymistapaa ei ole tutkittu vaahdotuksen yhteydessä, tämä työ esittelee ensimmäisen tieteellisen tutkimuksen, joka arvioi tämän vaahdotevalmisteen soveltuvuutta mineraalien vaahdotuksessa. Työn kussakin osa-alueessa verrataan kahden kaupallisen vaahdotteen (DowFroth 200 ja NasFroth 240) suorituskykyä HPMC-polymeerin ja näiden PT-yhdistelmiin.

Tutkimuksen ensimmäisessä osassa keskitytään PT-yhdistelmien vaahdotukselle relevanttien ominaisuuksien karakterisointiin (mm. dynaaminen pintajännitys, kuplakoko ja diffuusiokerroin). Väitöskirjan toinen osa käsittelee kolme vaahdotuskampanjaa, jotka suoritettiin i) luonnolliselle kuparimalmille; ii) synteettisille kupari- ja sinkkimalmeille; iii) kuparipitoiselle rikastushiekalle.

Työn tulokset osoittavat PT-yhdistelmien käyttäytyvän ainutlaatuisesti ilma-vesi -rajapinnalla. Ensiksi, HPMC ja NasFroth 240 yhdistelmän käyttö johti PT-kompleksin nopeampaan adsorptioon verrattuna samoihin yksittäisiin kemikaaleihin. Tämä edesauttoi pienempien kuplien muodostumisessa, jonka arveltiin säilyvän polymeerin aiheuttaman steerisen esteen ansiosta. HPMC:n läsnäolo lisäsi vaahdon stabiilisuutta sekä yksinään että osana PT-yhdistelmää. Käytetyn PT-yhdistelmän vaikutukset ilma-vesi -rajapinnan ominaisuuksiin johtivat selkeisiin hyötyihin vaahdotuskokeissa. Tärkeimmät edut suorituskyvyn suhteen havaittiin parantuneena arvomineraalisaantina, sekä kiihdytettynä prosessikinetiikkana, jotka yhdistettiin aiemmin havaittuun pieneen kuplakokoon sekä vaahdon kasvaneeseen stabiilisuuteen. Lisäksi PT-yhdistelmän aiheuttama vaahdon stabiilisuus mahdollisti tasaisen suorituskyvyn myös olosuhteissa, jotka olivat haitallisia vaahdotukselle.

Tulokset osoittavat, että käyttämällä PT-yhdistelmää vaahdotteena on mahdollista kasvattaa prosessin tuottavuutta ja tutkia uudenlaisia vaahdotusmenetelmiä, joiden käyttö vaatii parempaa vaahdon stabiilisuutta, joka on vähemmän riippuvainen mineraalien hydrofobisuudesta.

Avainsanat Vaahdotus; vihreät kemikaalit; hydroksipropyli metyyliiselluloosa; polymeeri-tensidi -sekoite; vaahdote

ISBN (painettu) 978-952-64-0303-8**ISBN (pdf)** 978-952-64-0304-5**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Helsinki**Painopaikka** Helsinki**Vuosi** 2021**Sivumäärä** 170**urn** <http://urn.fi/URN:ISBN:978-952-64-0304-5>

Preface

The Legend begins....

It was a sunny Saturday afternoon on August 29th in the year 2009, when I was walking towards the campus of Helsinki University of Technology for the very first time. Not knowing what to expect upon this new chapter in my life, I decided to face everything with an open mind and utmost curiosity.

Already during the early years of my university studies, I ended up joining the laboratory of Mechanical Processing and Recycling lead by Prof. Kari Heiskanen. My job was to run experiments for a doctoral candidate called Zoltán Jávör. That is how I made my first contact with bubbles. I knew practically nothing about the topic when I started, but somehow, I thought that bubbles, and flotation as a technology, seemed truly fascinating. But what really made me enjoy working in the research group was the positive and encouraging working environment. I am deeply grateful for Prof. Heiskanen, Zoltán Jávör and Nóra Schreithofer who so kindly welcomed me into the world of experimental science. At the time, I did not yet think about the future after my looming graduation, and even brushed off a comment from Zoltán's opponent asking, when am I making my phd.

Towards the end of my master level studies in 2015, things had changed. Helsinki University of Technology had changed to Aalto University already a long time ago, Prof. Heiskanen had retired and there was a new professor in the research group. I was offered an opportunity to continue in the team and after some discussions with Prof. Rodrigo Serna, I decided to embark on this incredible journey in the research group of Mineral Processing and Recycling, as it is nowadays called.

I've had the honor of meeting some great people along the years and I am grateful for all the relationships I've formed during my time at the university, thank you Vuorimieskilta, WKraatio11, Kultainen Raati 13 and W-clubi. As a counterbalance for my highly university-based life, I've always been able to chill with the amazing Skavabölen Turakullit, and even shared an apartment with a bunch of them for some years during this project, those were the times!

Of course, a research project such as this could not have been possible without financial support. I am forever grateful of the trust shown by the Steel and Metal Producers' Fund (Metallinjalostajien rahasto) by funding the first three years of my research with a personal scholarship. During this time we noticed that there may be something special in this project and with the never ending support of

Janne Raula we were able to attract further funding for the project. I would like to express my deepest gratitude for Business Finland and all the associated people who believed in us.

I wish to thank Tommi Rinne, Eero Jokinen, Joseph Lamberti, Peetu Westenius and Juho Hentman for their invaluable help with the experimental work that was necessary to get this thesis done. Special thanks go to our hidden hero, Janne Vuori, who was always ready to help with practical issues that arose in the lab. I also wish to thank my past and current colleagues from our extended lunch group and the hydro group as well as Sebastian Oosten, Valtteri Lehtinen, Huggins Mkurazhizha and Robert Hartmann for all the inspiring scientific and not so scientific discussions we had over the years. I am ever grateful that I was able to meet the late Omar Velazquez Martinez, who was a dear friend and colleague, may you rest in peace.

As one project is about to end, there is already a hint of a sequel in sight. I hope that together with Dr. Kari-Pekka Syrjä and our other collaborators in the CellFroth team we can reach the future success that we are striving towards.

Still, this work would have not been possible without the support of the best boss I've ever had, Prof. Rodrigo Serna. You are the only person I've met whose feedback can totally crush someone in a way that inspires them to reach for further heights after the befallen destruction, truly amazing. I am wholeheartedly happy that I decided to start this journey with you all those years ago, and believe it or not, I have learned so much from you.

Finally I wish to thank my parents for their endless support and care for my well-being, my brother and his lovely wife for all the shared moments that we have been blessed with, and of course the limitless support I get at home from my love, Sanna, and our little doggo, Freija (aka Femelussi, Pempu, Pötkylä).

Espoo, 24 November 2020
Ted Nuorivaara

**Dedicated to my late friend and colleague
Omar Velazquez Martinez**

“I did¹ my own² research³”

1 watched

2 someone else’s

3 Youtube video

Contents

Preface	I
List of Abbreviations and Symbols	IX
List of Publications	XII
Author's Contribution.....	XIII
1. Introduction.....	1
2. Theoretical Background	5
2.1 Relevance of frothers and froth properties on flotation	5
2.2 Properties of surface-active cellulose derivatives	9
3. Materials and methods.....	17
3.1 Frothers and other reagents	17
3.2 Equipment and methods	19
3.2.1 Characterization protocol of interfacial properties.....	19
3.2.2 Dynamic surface tension	19
3.2.3 Bubble size, foam depth and foam stability	21
3.2.4 Interfacial property studies of DF200	24
3.2.5 Mineral sample preparation.....	24
3.2.6 Grinding	25
3.2.7 Flotation Campaigns	25
4. Main results and discussion	35
4.1 Preliminary interfacial characterization.....	35
4.2 Dynamic adsorption properties	35
4.3 Diffusion rate	39
4.4 Bubble size	40
4.5 Foam properties.....	44
4.6 DF200	46
4.7 Flotation results	48
4.7.1 Cu Ore.....	49
4.7.2 Model ores.....	51
4.7.3 Tailings	62

5. Conclusions67

6. Recommendations for future investigations.....69

References 71

List of Abbreviations and Symbols

Abbreviations

AI	as-is, i.e., not re-ground
BPA	bubble pressure analyzer
Ca(OH) ₂	calcium hydroxide
CI	confidence interval
CuSO ₄	copper sulfate
CCC	critical coalescence concentrations
CCC ₉₅	concentration for 95 % reduction in bubble size
DF ₂₀₀	DowFroth 200
DP	degree of polymerization
DS	degree of substitution
DST	dynamic surface tension
EC	ethyl cellulose
EHEC	ethyl hydroxyethyl cellulose
F	frother only
HLB	hydrophilic-lipophilic balance
HPC	hydroxypropyl cellulose
HPMC	hydroxypropyl methyl cellulose
HPMC _{10k}	HPMC (M _w 10 kDa)
HPMC _{22k} /HP	HPMC (M _w 22 kDa)
ICP	induced coupled plasma
MC	methyl cellulose
Mix _{10k}	polymer-surfactant mixture with HPMC _{10k} as the polymeric component

Mix22k	polymer-surfactant mixture with HPMC22k as the polymeric component
MS	molar substitution
NaCMC	sodium carboxymethyl cellulose
NaCN	sodium cyanide
NaHS	sodium hydrosulfide
NaOH	sodium hydroxide
NF/NF240	NasFroth 240
NSG	non-sulfidic gangue
PEG	polyethylene glycol
PLS	partial least squares
PPG	polypropylene glycol
ppm	parts per million
PS	polymer-surfactant
PW	pure water
RG	re-ground
rpm	revolutions per minute
SEX	sodium ethyl xanthate
SIBX	sodium isobutyl xanthate
SE	separation efficiency
UPW	ultra pure water
XRF	x-ray fluorescence
ZNSO ₄	zinc sulfate

Symbols

γ	surface tension (mN/m)
γ_0	initial surface tension (mN/m)
π	3.1416
A	range of bubble size reduction (mm)
b	decay constant (LNo.05/CCC95)
c	% of metal in the concentrate

C	concentration (ppm)
C_{o-3}	model coefficients
C_b	total bulk concentration (mmol/l)
C_{col}	collector concentration
C_f	fraction of total feed weight that reports to the concentrate
C_{pH}	pH level
D	diffusion coefficient (m ² /s)
D_l	limiting (minimum) bubble size with certain frothing agent (mm)
D_{eq}	equivalent diameter (mm)
D_{32}	sauter mean diameter (mm)
f	% of metal in the feed
k	first order kinetic rate constant (s ⁻¹)
k_c	collection zone kinetic rate constant (s ⁻¹)
m	% of metal content in the valuable mineral
M_w	molecular weight (g/mol)
n	constant in the Ward-Tordai equation
R	universal gas constant (Jmol ⁻¹ K ⁻¹)
R_f	froth recovery
R_g	recovery of gangue
R_m	recovery of valuable mineral
R_{max}	maximum theoretical recovery
R_t	total recovery
σ_x	standard error of the mean
T	absolute temperature (K)
t	time (s)
Y	response of the PSL model

List of Publications

This thesis is based on the following publications, which are referred in the manuscript by the following Roman numbers.

- I. Nuorivaara, T., Serna-Guerrero, R. A study on the properties of foams produced with cellulose-based molecules with an outlook on flotation. Quebec, Canada, Proceedings of XXVIII International Mineral Processing Congress (IMPC2016), 11-15 2016 September.
- II. Nuorivaara, T., Serna-Guerrero, R. Flotation of a porphyry copper ore with cellulose-surfactant mixtures as frother agents, Vancouver, Canada, Proceedings of Copper 2019, 18-21 2019 August.
- III. Nuorivaara, T., Serna-Guerrero, R. 2020. Unlocking the potential of sustainable chemicals in mineral processing: improving sphalerite flotation using amphiphilic cellulose and frother mixtures, *Journal of Cleaner Production* 261, 121143, <https://doi.org/10.1016/j.jclepro.2020.121143>.
- IV. Nuorivaara, T., Serna-Guerrero, R. 2020. Amphiphilic cellulose and surfactant mixtures as green frothers in mineral flotation. 1. Characterization of interfacial and foam stabilization properties, *Colloids and Surfaces A* 604, 125297, <https://doi.org/10.1016/j.colsurfa.2020.125297>.
- V. Nuorivaara, T., Serna-Guerrero, R. 2020. Amphiphilic cellulose and surfactant mixtures as green frothers in mineral flotation. 2. Flotation of chalcopyrite and Cu-containing tailings, *Colloids and Surfaces A* 603, 125298, <https://doi.org/10.1016/j.colsurfa.2020.125298>

Author's Contribution

Publication I: *A study on the properties of foams produced with cellulose-based molecules with an outlook on flotation*

TN composed the initial conceptualization and theoretical investigations. TN and RS jointly formulated the experimental design. TN was responsible of conducting the experimental work and formal analysis of the measurement data under supervision of RS. TN wrote the original draft of the manuscript which was reviewed and edited by RS.

Publication II: *Flotation of a porphyry copper ore with cellulose-surfactant mixtures as frother agents*

TN composed the initial conceptualization and theoretical investigations. TN and RS jointly formulated the experimental design. TN was responsible of conducting the experimental work and formal analysis of the measurement data under supervision of RS. TN wrote the original draft of the manuscript which was reviewed and edited by RS.

Publication III: *Unlocking the potential of sustainable chemicals in mineral processing: improving sphalerite flotation using amphiphilic cellulose and frother mixtures*

TN composed the initial conceptualization and theoretical investigations. TN and RS jointly formulated the experimental design. TN was responsible of conducting the experimental work and formal analysis of the measurement data under supervision of RS. TN wrote the original draft of the manuscript which was reviewed and edited by RS.

Publication IV: *Amphiphilic cellulose and surfactant mixtures as green frothers in mineral flotation. 1. Characterization of interfacial and foam stabilization properties*

TN composed the initial conceptualization and theoretical investigations. TN and RS jointly formulated the experimental design. TN was responsible of conducting the experimental work and formal analysis of the measurement data under supervision of RS. TN wrote the original draft of the manuscript which was reviewed and edited by RS.

Publication V: *Amphiphilic cellulose and surfactant mixtures as green frothers in mineral flotation. 2. Flotation of chalcopyrite and Cu-containing tailings*

TN composed the initial conceptualization and theoretical investigations. TN and RS jointly formulated the experimental design. TN was responsible of conducting the experimental work and formal analysis of the measurement data under supervision of RS. TN wrote the original draft of the manuscript which was reviewed and edited by RS.

1. Introduction

Mining and refining of metal minerals have been an essential element for the development of modern societies. Along with the constant population growth and increasing consumption of metals per capita, there is an ever-accumulating demand for more raw materials. While some metals can already be recycled efficiently, most of the supply is still being produced from primary resources, i.e. mines.

To put the scale of the mining industry in perspective, there are over 2000 known ore deposits around the world just for copper-containing minerals (Mudd and Jowitt, 2018) and the global annual mine production of copper has been around 20 million tons in recent years (USGS, 2020). Considering that over 70% of all mined copper is concentrated with froth flotation (Mudd and Jowitt, 2018) before further refining the metal, it is evident that flotation has and will play a key role in the constant supply of essential raw materials.

Flotation is a physico-chemical process with the aim of selectively separating profitable minerals from heterogeneous mixtures. Such separation is made possible by exploiting a wide variety of surface phenomena on all three fundamental phases of matter (i.e. solid, liquid and gas).

In the state-of-the-art industrial practice, flotation occurs in cells or columns, where air is dispersed through an agitated mineral slurry. The agitation enables collisions between bubbles and particles, an instance where specific mineral species attach onto the bubbles as a result of a specific physicochemical environment, typically after modification of the mineral surface properties either directly (e.g., through the adsorption of hydrophobic reagents) or indirectly (e.g., by altering the pulp potential).

The goal is to render specific mineral species hydrophobic while maintaining others hydrophilic. This allows for selective attachment of these desired minerals onto the air bubbles to occur. After the hydrophobic particles have attached onto the air bubbles, their buoyancy lifts the bubble-particle aggregate towards the surface, where groups of these aggregates form a mineralized foam called the froth, which is collected as the product of the process. This is called direct flotation. Alternatively, it is possible to purify a high-grade feed material by selectively floating the gangue minerals in a process called reverse flotation. The decision between direct and reverse flotation is usually based on the concentration of the valuable minerals, logically the smaller fraction is often the floated species.

One of the biggest benefits of froth flotation technology is the possibility to adjust the chemical system in order to treat each specific system of interest. Thus, flotation has become the most important mineral enrichment process around the world.

While flotation has been successfully operated for over a century, the future prospects of the industry present new challenges. The sizes of mines have increased significantly from 1970 to 2000, for example (Rötzer and Schmidt, 2018). Consequently, there is an increasing amount of ore that is being processed, a trend that is likely to continue due to declining ore grades (Mudd & Jowitt, 2018). In the past decades, this growth of throughput has been managed by increasing the sizes of individual flotation cells. However, there is a theoretical upper limit for cell sizes according to Neethling et al. (2019). In such work, they explained that a larger flotation cell increases the probability of transitioning from first to zero order kinetics, a phenomenon that is extremely detrimental for flotation performance. One of the proposed solutions to the occurrence of zero rate kinetics was to increase the flow of available surface area, i.e. either producing smaller bubbles, or more bubbles of similar size, both of which are difficult to achieve through purely mechanical methods, as an increase in gas flow often increases bubble sizes as well.

Furthermore, until recent years, beneficiation of metal minerals has partly occurred at the expense of possible health and especially environmental hazards. In flotation of some essential metal minerals, chemicals such as sodium hydrosulfide (NaHS), xanthates ($\text{ROCS}_2 \text{M}^+$, where R = alkyl; $\text{M}^+ = \text{Na}^+$ or K^+), and sodium cyanide (NaCN) are commonly used, all of which are classified as either hazardous to the environment or toxic to human beings.

Simultaneously, a globally increasing interest on topics such as sustainability, green chemistry and circular economy has emerged (Stahel, 2016; van Schalkwyk et al., 2018; Kinnunen and Kaksonen, 2019; Velázquez Martínez et al., 2019) and the implementation of more sustainable chemicals as well as reductions in environmental impact has since gained attention in the mining industry (Huang et al., 2019; Peçanha et al., 2019).

Along with degrading ore grades and increased environmental awareness of the public, the need for utilization of flotation chemicals to their fullest potential both in terms of performance and sustainability has been recently acknowledged by scholars of the mining industry (Nagaraj and Farinato, 2016).

The work presented in this thesis aims to contribute towards a more sustainable future in the field of minerals processing, while simultaneously improving flotation performance by introducing a fundamentally new type of reagent to be used as a flotation frother. The proposed concept revolves around increasing control over the important froth phase via the use of an environmentally friendly cellulose derivative, namely hydroxypropyl methyl cellulose (HPMC). The results of this research project demonstrate the possibility of utilizing a new type of flotation chemistry by understanding the fundamental properties that govern flotation performance.

In order to successfully adapt to using cellulose derivatives as flotation frothers, one needs to contemplate the differences between the fundamental

properties of current flotation frothers and surface-active polymers and the physical consequences they provide.

There has been a large divergence in the nature of the experimental procedures between interfacial studies of flotation frothers and surface-active cellulose derivatives. For example, the surface tension reducing properties of cellulose derivatives have often been studied in concentrations significantly higher compared to frother studies (Grau, 2006; Pérez et al., 2008; Caimno et al., 2009; Jávora, 2014). In the few investigations at low concentrations of cellulose derivatives (Nahringbauer, 1995), the property of interest was the equilibrium surface tension and not the dynamic surface tension, which is often more relevant in flotation (Jávora et al., 2010). Therefore, it is necessary to i) build an understanding on the fundamental properties of frothers, along with the flotation-related phenomena that they facilitate, and ii) identify cellulose derivatives that present interfacial properties relevant for flotation.

In addition to the theoretical analysis, the main experimental objectives of this research project were:

- 1) To measure the interfacial properties of HPMC and its polymer-surfactant (PS) mixtures with experimental procedures that are relevant in froth flotation, including dynamic surface tension, short time diffusion approximation, bubble size, foam depth and foam stability measurements.
- 2) To compare the behavior of the cellulose derivatives at the air-liquid interface to those of current commercial frothers and to identify the key differences between the two chemistries with an outlook on flotation.
- 3) To connect the identified differences in fundamental properties to flotation performance by conducting flotation experiments and analyzing the resulting recoveries, grades, separation efficiencies (SE) and flotation kinetics based on existing information regarding frother, bubble and froth properties as well as their impact on flotation performance.

Since there is no prior information of cellulose derivatives being used as flotation frothers (to the best knowledge of the author's knowledge) apart from publications by the author and his supervisor (Nuorivaara and Serna, 2016; Nuorivaara and Serna, 2020a; Nuorivaara and Serna, 2020b; Nuorivaara and Serna, 2020c) and Master's theses that were written under the guidance of the author and his supervisor (Rinne, 2018; Lamberti, 2019), there is not sufficient information regarding the synthesis of new cellulose chemistries for this application. Thus, this aspect was considered beyond the scope of this research. Therefore, a more reasonable approach was to conduct a study on the interfacial properties of currently available cellulose derivatives and compare them to the vast collective knowledge gathered on oligomeric flotation frothers. Furthermore, the properties of cellulose derivatives and their surfactant mixtures in the bulk phase were also considered to be outside the scope of this study.

This thesis consists of a theoretical background investigation that discusses the role of frothers in flotation as well as their typical fundamental properties,

which is followed by a review of the interfacial properties of surface-active cellulose derivatives and their PS-mixtures.

Based on the literature review, it was decided to study HPMC and its PS-mixtures together with typical polyethylene and polyglycol type frothers available commercially, namely NasFroth 240 (NF240) and DowFroth 200 (DF200). These combinations are expected to express a weaker, hydrophobic, interaction (Brackman, 1990), that is potentially the most suitable alternative for flotation purposes.

In order to evaluate the applicability of the proposed novel frother chemistry it was necessary to first characterize its interfacial properties relevant for flotation and consequently connect these observations to phenomena occurring in laboratory scale flotation tests.

The thesis is finalized by presenting conclusions of the research project along with recommendations for further investigations.

The promising results that are presented throughout this thesis were used as the basis of a patent application (WO2019155116).

2. Theoretical Background

2.1 Relevance of frothers and froth properties on flotation

In froth flotation, frothers are a group of surface-active reagents that represent only a small subgroup of surfactants. They have a heteropolar structure which consists of a hydrophobic hydrocarbon chain (branched or linear), called the “tail”, and a hydrophilic “head”. The hydrophilic group usually consists of hydroxyl (OH) groups, carboxyl (COOH) groups, carbonyl (C=O) groups or ester (COOR) groups (Laskowski, 1998).

Currently, the most common types of molecules used as frothers are either relatively short chained polyethylene glycols (PEG), polypropylene glycols (PPG) or aliphatic alcohols (Jávor, 2014; Drzymala and Kowalczyk, 2018).

Energetically, the most satisfying orientation for such a molecule is achieved when the hydrophobic group(s) are in contact with air and the hydrophilic group(s) are in contact with water, i.e. settling at the air-liquid interface where both conditions can be fulfilled. (Figure 1).

In their seminal study, Derjaguin and Dukhin (1961) classified the air-liquid interface into three different layers: the actual interface, the sublayer and the bulk solution. The bulk solution is the liquid phase in which the surfactant has been dissolved. The sublayer is the area close to the interface where the surface-active molecules are being transported by diffusion. The adsorption of surface-active agents occurs at the actual air-liquid interface. Upon the adsorption of the surface-active molecules onto the air-liquid interface, the phenomena occurring in these three layers determine the surface properties of the interface (e.g. surface tension, surface viscoelasticity and film thickness).

Furthermore, the molecular exchange between the bulk and the interface is determined by the adsorption-desorption properties of the surfactants (Jávor et al., 2010). Changes in the fundamental properties of the interface in turn affect bubble size, foamability, bubble rising velocity and froth stability, thus frothers govern crucial aspects for flotation performance.

Figure 1. Image of surfactants at an A/L interface

The frother, or more precisely its structure, can influence the selectivity and recovery of the flotation process. For example, in a recent series of publications (Finch and Zhang, 2014; Tan and Finch, 2016; Tan and Finch, 2018a), the authors observed that the chain length of a frother along with the position of the hydroxyl group and possible methyl branches affected the concentration at which bubbles reached minimum rising velocity. Furthermore, the maximum recoverable particle size decreases with increasing branching of the frother (Farrokhpay, 2011), while the presence of branches in PPG vs PEG frothers has been related to more efficient decreases in rising velocity (Tan and Finch, 2018b). Thus, it is generally accepted that no single frother can be exclusively associated to a certain type of ore (Harris, 1982; Wills and Finch, 2015).

As there are only small differences between frother types and their respective properties, different classification methods have been established that are based either on attributes of the molecule itself, e.g. ionic nature, hydrophilic-lipophilic balance (HLB), chemical composition, structure etc. or a combination of its surface and bubble properties (Javor, 2014; Drzymala and Kowalczyk, 2018).

In order to better understand the fundamental functionality of frothers at the air-liquid interfaces, their experiments are often conducted in two-phase systems (Grau, 2006; Javor, 2014; Tan and Finch, 2018b). Although it is generally accepted that the presence of particles affects surface properties, the benefits of this approach is that it enables detailed studying of sensitive interfacial characteristics, such as surface tension; surface elasticity; adsorption kinetics; bubble rising velocity and bubble coalescence, thus providing valuable insight to the fundamental phenomena governing frother activity.

Considering that bubbles are responsible for transporting the mineral particles from the pulp into the froth and that the froth phase is responsible of recovering the valuable particles, bubble size and froth stability management are arguably the most important tasks for a flotation frother. Hence, these two topics deserve to be discussed in further detail.

One of the key phenomena that determines bubble size is coalescence between bubbles upon collisions. Bubble coalescence takes place when the contact time between colliding bubbles is sufficient for drainage to take place in the trapped liquid film so that a critical film thickness is reached, leading to bubble coalescence (Marucci, 1969; Chesters, 1991).

The relationship between bubble size and frother is concentration dependent and there is a critical concentration after which the sauter mean diameter (D_{32}) of the bubble population does not decrease, which has been defined as the critical coalescence concentration (CCC) (Cho and Laskowski, 2002).

Regardless of the CCC value, the minimum sauter mean diameter (D_{32}) achieved with current frothers (Drzymala and Kowalczyk, 2018) and even their mixtures (Elmahdy and Finch, 2013) is usually at the same size range at around 1 mm (Neethling et al., 2019). The extensive further studies conducted in the past two decades have led to the identification of three different methods for frothers to affect the bubble size in the flotation cell:

1. Bubble coalescence inhibition (Cho and Laskowski, 2002)
2. Bubble-breakup induced bubble size reduction (Chu et al., 2017)
3. Affecting bubble size already during the initial formation of the bubble (Jávor et al., 2014).

In terms of the concrete flotation process, it has been shown that smaller sizes of individual bubbles increase the flotation performance by the means of two different mechanisms:

1. Increasing the total number of bubbles in the cell and consequently the probability of bubble-particle collisions due to a larger overall interfacial area available for the particles to attach onto (Wills and Finch, 2015).
2. Smaller bubbles have smaller buoyancy, thus there is a higher probability of bubble-particle collisions when observing individual bubbles.

Both phenomena increase the collection rate and consequently the amount of valuable minerals that report to the froth phase.

Once the valuable particles have successfully been collected to the froth phase, it still needs to be recovered in order to generate a concentrate and therefore maintaining proper froth stability is crucial for achieving good flotation performance. Historically froth stability has been associated with many properties. Harris (1982) classified such factors as (1) frother surface activity; (2) adsorption rate on a newly formed surface; (3) surface viscosity of the air-liquid interface and (4) the bulk viscosity of the medium. Whereas according to Jávor (2014), a higher dynamic elasticity of the air-liquid interface renders the

surface less mobile and consequently inhibits drainage. Such increasing immobility of the interface also increases the required contact time for bubbles to coalesce.

An unstable froth causes the bubbles to burst and all associated particles are drained back to the slurry from where they have to re-attach to a new bubble in the pulp in order to be collected. This phenomenon decreases the process kinetics due to increased retention times of particles that loop around between pulp and froth before finally reporting to the concentrate. The collection efficiency of the froth is often described with a metric called froth recovery, which represents the fraction of particles entering the froth that report to the concentrate.

While it is difficult to measure in continuous processes, some indirect methods have been proposed (Tsatouhas et al., 2006). A widely accepted definition of froth recovery is expressed with the help of the first order rate constants (Savassi et al., 1997):

$$R_f = \frac{k}{k_c} \quad (1)$$

Where R_f is the froth recovery, k is the overall first order rate constant so that it treats the collection and froth phases as a single phase and k_c is the collection zone rate constant. As seen from Equation 1, the kinetic constant acts as a proxy for froth recovery: If less bubbles burst, more bubbles are reporting from the froth phase into the product, i.e. when the kinetic constant of the process is higher the froth recovery is often more efficient as well.

Although frothers play a key role in froth stability, it is ultimately a combination of multiple factors and flotation performance is always dependent on the overall interactions between all species present in the process (Bulatovic, 2007). For example, some frothers may adsorb onto the mineral surfaces (e.g. methyl isobutyl carbinol onto carbonate minerals – (Bournival et al., 2015)), which consequently reduces froth stability (Bulatovic, 2007). Furthermore, sufficiently hydrophobic particles help stabilizing the froth (Tan et al., 2010), while particles with low hydrophobicity can stabilize froths when a closely packed monolayer is formed in the froth film (Bulatovic, 2007).

Many industrial operations still struggle with finding a proper frother for their process due to froth instability, which has been reported as one of the main reasons behind reduced froth recovery (Farrokhpay, 2011). Typical causes for such instability are the lack of sufficiently hydrophobic particles down the flotation bank (Farrokhpay, 2011), the presence of ultra-fine clay or the presence of ionic species in the pulp (Bulatovic, 2007).

Another important property for frothers is low sensitivity towards changes at pH. Often pH levels vary between different stages, which consequently affects froth properties with many current commercial frothers (Bulatovic, 2007).

Furthermore, as discussed in the introduction, it may be necessary to further reduce bubble size in the largest scale industrial flotation cells to counteract the possible occurrence of zero rate kinetics. This may not be possible with the

existing frother chemistries without affecting flotation performance (Neethling et al., 2019).

Considering the above-mentioned aspects, careful consideration is necessary when selecting reagents for a flotation process and it is evident that there is a need for better performing flotation frothers, especially in terms of robustness of operations throughout the flotation bank.

Furthermore, it is important to note that different types of frothers with similar dynamic surface properties do not always yield the same bubble sizes and vice versa (Jávor, 2014). Thus, it must be kept in mind that the measurement of a single property may not fully answer the complex questions of surfactant phenomena on the air-liquid interface. Consequently, a detailed characterization of interfacial properties is necessary when exploring new frother chemistries.

Fortunately, decades of thorough frother research has provided the means for identifying combinations of key properties and working principles of the state-of-art frothers and thus enabled the possibility of studying completely new types of frother chemistries with a similar outlook.

An option recently explored by some authors to implement green chemistry in mining operations has been the use of cellulose-based additives. The literature offers some examples on the use of cellulose derivatives as adsorbents of metallic ions (Beyki et al., 2014), flocculants (Yang et al., 2014), depressants (Hamilton et al., 2009, Kor et al., 2014) or collectors (Laitinen et al., 2014; Laitinen et al., 2016).

While the use of more sustainable solutions is of high interest within the scientific community, developments towards more environmentally friendly industrial processes are more likely to occur when the changes also demonstrate significant advantages in productivity.

The following chapter describes the properties of surface-active cellulose derivatives and compiles the available information relevant for flotation.

2.2 Properties of surface-active cellulose derivatives

A major advantage regarding the use of cellulose derivatives arises from the possibility of modifying their properties by substituting the native hydroxyl groups with other active groups (Wüstenberg, 2015). This introduces the possibility to synthesize a vast range of unique cellulose derivatives with distinct properties that are connected to the nature of its functional groups. The most important parameters impacting the behavior of a cellulose derivative are degree of substitution (DS), molar substitution (MS), degree of polymerization (DP) and molecular weight (Mw). (Coffey et al., 2006)

As an example, Figure 2, illustrates the natural cellulose I -structure along with examples of some cellulose derivative structures.

Figure 2. Structures of a) Cellulose, b) Methyl Cellulose with a DS of 2 and c) Hydroxypropyl Cellulose with a MS of 2 (Adapted from Coffey et al., 2006)

As shown in Figure 2-a, the naturally occurring cellulose I structure has three hydroxyl groups. These groups are the locations available for possible functionalization along the cellulose backbone structure. DS is a numerical value which tells the average amount of hydroxyl groups substitution within a single anhydroglucose unit throughout the whole polymer. Consequently, its value is between 0 and 3, where 0 represents no substitution and 3 represents functionalization at all active sites per anhydroglucose unit (Figure 2-b). However, DS is only used to describe substitutions occurring at the original hydroxy groups present in the cellulose I structure. If further chain growth occurs at a single site, it cannot be described with DS. For example, if the existing hydroxyl group is substituted with a propylene oxide as the substituting species, a possible site for further reactions to occur is reproduced. Such cases of continued chain growth originating from a single hydroxy group are expressed with MS. In other words, MS describes the number of moles of alkylating agent per mole of anhydroglucose in the chain. Consequently, the ratio between MS and DS indicates the average chain length of the side-chain substitutes within a single anhydroglucose unit (Figure 2-c). DP describes the average number of monomer units in the polymer and an average Mw can be derived if DP and MS are known. (Coffey et al., 2006)

Considering the near-infinite amount of potential functional group combinations introduced into the cellulose backbone, there is a great potential to use cellulose based chemicals in flotation beyond its current applications (e.g., as depressants).

As discussed in **Section 2.1**, in order to match typical properties of commercial frothers, a suitable cellulose derivative should be: i) water soluble, ii) sufficiently surface-active and iii) preferably tolerant towards changes at pH and ionic composition of the solution.

Information on some commercially important water-soluble cellulose ethers is compiled in Table 1 (Nahringbauer, 1995; Persson et al., 1996; Majewicz and Podlas, 2000; Coffey et al., 2006; Wüstenberg, 2015; Paraskevopoulou and Kiossegolou, 2013). As is evident from Table 1, only few of the presented derivatives meet the required standards. For example, in certain geographical mining locations, the ambient temperatures may easily exceed 40°C during summer, which means that derivatives that either gelate or precipitate when approaching such temperatures may not be suitable for global flotation applications.

Table 1. Information on commercially important water-soluble cellulose ethers

Derivative	Solubility	pH stability	Surface activity	Reaction with Ca ²⁺ ions	Impact of electrolytes	Lower critical solution temperature
Methyl cellulose (MC)	High	2-12	High	Low	Low	45-50 °C
Hydroxypropyl cellulose (HPC)	Soluble in 0-38 °C	2-11	High	Low	Presence of salts and sugar decrease flocculation temperature	40-45 °C
Hydroxypropyl methyl cellulose (HPMC)	High	2-12	Very high	Low	Low	75-90 °C
Ethyl cellulose (EC)	Water soluble at DS 0.8-1.3 / Commercial grades not water soluble (DS 2.2-2.8)	1-14	-	Low	Low	-
Ethyl hydroxyethyl cellulose (EHEC)	High	3-11	Very High	Unknown	Unknown	28-65 °C
Sodium carboxymethyl cellulose (NaCMC)	High	3-10	Low	High (gelation or precipitation)	Presence of monovalent ions affect viscosity and di-/trivalent cations cause precipitation or gelation	-

Based on the information presented in Table 1, HPMC seems like a viable alternative, especially since the strength of its surface activity can be varied by modifying its methyl-to-hydroxypropyl ratio (Camino et al., 2009; Paraskevopoulou and Kiossegolou, 2013). HPMC is currently used in e.g., the food and pharmaceutical industries due to its good foam and emulsion stabilizing properties (Paraskevopoulou and Kiossegolou, 2013). Additionally, HPMC is non-ionic and biodegradable (Camino et al., 2009; Sannino et al., 2009), which makes it an interesting prospect for flotation purposes both from sustainability and performance point of views, the latter since it is expected to interact only at the air-liquid interface. Considering the above-mentioned information, a clear understanding of the similarities and differences in interfacial properties and adsorption behavior between short-chained surfactants and surface-active cellulose derivatives is integral for identifying the possibilities of using such polymers as flotation frothers.

A prime example of significant differences in interfacial behavior between surface-active polymers and short-chained frothers can be found when comparing their adsorption behavior. The adsorption of typical frothers with short molecular chains is relatively fast and through a simple mechanism,

resulting in a perpendicular orientation towards the air-liquid interface (Jávor et al., 2010) (Figure 1). However, the adsorption of macromolecular species is a result of a series of stages occurring consecutively and concurrently, namely: 1) transportation of the polymers from the bulk to the sub-surface; 2) spreading/unfolding of molecules; 3) adsorption of hydrophobic polymer segments from the subsurface to the interface and 4) rearrangement of the adsorbed polymer segments between the interface and the sub-surface (Nahringbauer, 1995).

Another disparity between low molecular weight and macromolecular surfactants lies on their mechanisms to achieve local equilibrium between the subsurface and the interface. In the simple model of smaller surfactants, one active site per molecule is occupied (Jávor, 2014). This is not the case in polymer adsorption, where the local equilibrium is reached when a large number of polymer segments (i.e. active groups along the polymer backbone structure) are in contact with the surface (Nahringbauer, 1995).

The three-dimensional structure of cellulose derivatives particularly complicates their adsorption behavior (Norde et al., 1986; Dickinson, 2003). Furthermore, the structure of a cellulose derivative usually contains unevenly distributed hydrophobic and hydrophilic regions which can lead to significant differences in behavior between individual molecules (Pérez et al., 2007). This structural variance results in a characteristic orientation of adsorbed species, commonly represented by the train-tail-loop model (Figure 3) (Wollenweber, 2000). The unevenly segmented hydrophobic and hydrophilic regions of the polymer adsorb on the interface according to their respective properties. Trains are the hydrophobic segments of the polymer which have adsorbed onto the air-liquid interface, loops are unadsorbed segments between two trains and tails are the non-adsorbed segments that exist in one or both ends of the polymer.

Figure 3. Illustration of the train-loop-tail model

Consequently, interfaces with adsorbed polymers can have a wide variety of properties based on the orientation of the polymer at the interface (Paraskevopoulou and Kiossegolou, 2013). According to previous studies (Nahringbauer, 1995; Pérez et al., 2008), surface-active cellulose derivatives first adsorb in a flat-like orientation which slowly changes towards a more perpendicular orientation (Figure 3), where only the most surface-active segments remain adsorbed onto the interface. Thus, the surface properties are more strongly influenced by the number of polymer segments adsorbed on the interface rather than the total number of adsorbed molecules (Nahringbauer, 1995).

Perhaps the most interesting property of cellulose derivatives from the flotation point of view is the reported capability of forming a protective layer against coalescence and mechanical stress (Wege et al., 2008; Xhanari et al., 2011). This could assist in maintaining small bubbles even in turbulent conditions, something which current frothers cannot accomplish (Jávor et al., 2014). Furthermore, the active groups along the cellulose backbone reportedly provide potential adsorption sites for surfactant adsorption and consequent polymer-surfactant (PS) complexation (Katona et al. 2008).

PS-mixtures have been used in many industries due to their flexibility in obtaining desirable surface properties in multiple applications (Sannino et al., 2009; Bureiko et al., 2015; Wei et al., 2018). Depending on the nature of both the polymer and the surfactant there can be either synergistic, antagonistic or no interaction between the species (Goddard and Ananthapadmanabhan, 1993). Consequently, a wide variety of surface properties originates from the synergistic PS-layer being able to access non-equilibrium states (Bain et al., 2010). While PS interactions can take place either in the bulk or at an interface (Goddard and Ananthapadmanabhan, 1993), in this thesis the focus is solely in phenomena occurring at the air-liquid interface.

Schreithofer et al., (2011) studied the effects of mixtures of NaCMC and DF200 on foam and froth properties. They identified interactions as increased foamability and foam stability in air-liquid systems, which consequently disappeared when solids were added to the system due to the affinity towards solids that NaCMC possesses.

In another example, a PS-complex composed of an oppositely charged polymer and surfactant had strong electrostatic interactions, while a neutral polymer and an ionic surfactant had a weaker, hydrophobic, interaction (Petkova et al., 2012). Thus, the strength of the interaction is also dependent on its nature (e.g. electrostatic vs. hydrophobic).

Furthermore, the interfacial properties are not only defined by the ionic nature of the components, i.e., each combination of PS-mixtures can have unique properties regardless of the type of interaction between the components (Table 2). Additionally, there are two important factors that need to be considered when studying PS-systems: 1) the prediction of their interfacial properties, e.g. surface tension, foamability and foam stability, is not trivial (Petkova et al., 2012) and 2) the properties of a PS-mixed layer at dynamic and static conditions are not comparable (Bain et al., 2010; Angus-Smyth et al.,

2013). Thus, novel PS-mixtures require detailed interfacial characterization in order to assess their compatibility as a flotation frothers.

Table 2. Dynamic adsorption behavior of different PS-mixtures.

Polymer	Surfactant	Type of polymer	Type of surfactant	Inter-molecular interaction	Dynamic adsorption behavior	Reference
Poly-dimethyl diallyl ammonium chloride	Sodium dodecyl sulfate	Cationic	Anionic	Strong	Enhanced adsorption rate at low total concentrations due to formation of more hydrophobic complexes	Campbell et al. 2007
Poly-ethylene oxide	Sodium dodecyl sulfate	Nonionic	Anionic	Weak	Decreased adsorption of surfactant in the presence of polymer	Angus Smyth et al. 2012
Poly-ethylene oxide	Tetradecyl trimethyl ammonium bromide	Nonionic	Cationic	No interaction	Surfactant displaces polymer upon small increases of surfactant concentration	Angus Smyth et al. 2012
Poly N-vinyl formamide	Sodium dodecyl sulfate	Nonionic	Anionic	Weak	Increased adsorption of PS-mix compared to pure chemicals due to formation of surface-active PS-complex	Petkova et al. 2012
Poly-ethylene imine	Sodium dodecyl sulfate	Cationic	Anionic	Strong	Reduced diffusion rate due to increased size of bulk aggregates	Angus Smyth et al. 2013

According to Petkova et al. (2012), the observed PS-synergy in a weakly interacting system is a combination of faster adsorption of the surfactant (which facilitates foaming) and strong steric repulsion by the PS-complex that enhances interfacial stability. In bubble formation, this could reflect a combination of fast surfactant adsorption that decelerates film thinning, providing additional time for the polymeric species to adsorb before bubble coalescence occurs. Consequently, the adsorption of polymeric species would further prevent coalescence theoretically.

Considering the spectrum of possible interfacial properties induced by a PS-mixed layer, selecting an appropriate PS-mixture hypothetically enables the modification of properties at the air-liquid interface without affecting bulk properties, while simultaneously maintaining similar concentration levels as with conventional frothers.

While surface-active cellulose derivatives and their PS-mixtures may have the necessary natural tendencies to adsorb and modify the properties of the air-liquid interface, before the present work, it was unknown to what extent their properties allowed control of bubble size and froth stabilization, particularly from a froth flotation perspective.

3. Materials and methods

This section presents the materials used and describes the methodology applied in the experimental work of this thesis. The studied frothers and other flotation reagents are presented first, after which all equipment is presented along with their respective standard procedures. Finally, the experimental campaigns are discussed in detail, highlighting the possible sources of discrepancy between campaigns conducted with the same equipment.

3.1 Frothers and other reagents

Throughout this research work, the interfacial properties and flotation performance of HPMC and its PS-mixtures was compared with representative commercial frothers. The commercial frothers studied in this thesis were NF240, a polyethylene glycol, and DF200, a polypropylene glycol (Table 3). Both frothers were supplied by Nasaco International LLC.

Table 3. Commercial frothers used in this thesis

Name	Abbreviation	Chemical formula	Molecular weight (g/mol)
Dowfroth 200	DF200	$\text{CH}_3(\text{OC}_3\text{H}_6)_3\text{OH}$	206.28
Nasfroth 240	NF240	$\text{C}_4\text{H}_9(\text{OC}_2\text{H}_4)_3\text{OH}$	206.28

Two different types of HPMC-molecules were purchased from Sigma-Aldrich (Products No. H8384 and 423238). A generalized structure of HPMC is presented in Figure 4. According to the product specifications, Product No. H8384 has an average molecular weight of 22 kDa with a methoxyl content of 28-30 % and a hydroxypropoxyl content of 7-12 % and is hereby labeled as HPMC22k. Product No. 423238 has an average molecular weight of 10 kDa with a methoxyl content of 29 % and a hydroxypropyl content of 7 % and is referred to as HPMC10k in this thesis. Further details provided by the supplier are found in Table 4.

HPMC

R = H; CH₃ or CH₂CH(OH)CH₃

Figure 4. General structure of HPMC (adapted from the product specification of the supplier) (Nuorivaara and Serna, 2020a)

Table 4. Details of the two HPMC molecules according to the supplier

Product number	Name	Methoxy content (w-%)	DS	Poropylene oxide content (w-%)	MS	Average molecular weight of repeating segments (g/mol)*
423238	HPMC 10k	29	1.8 - 2.0	7	0.2 - 0.3	186.45
H8384	HPMC 22k	28 - 30	Not specified	7 - 12	Not specified	190.77

*Calculated by the author based on the average methoxy and propylene oxide contents provided by the supplier

Due to the extensive amount of concentrations and PS-mixture combinations used in this thesis, a name code was implemented to facilitate this discussion. The code is explained next and these coded labels are used in this thesis from hereon. When PS-mixture formulations and their concentrations are discussed, the type of PS-mixture is denoted as Mix10k or Mix22k depending on the HPMC molecule (10k or 22k) used. This is followed by the concentration of the mixture components, presented as “NX” or “DY” for the commercial frother and “HZ” for the polymer, where N stands for NF240, D stands for DF200, H stands for HPMC, and X, Y or Z describes the concentration of the respective species in parts per million (ppm). As illustrative examples 1) Mix22k-N8-H16 refers to a PS-mixture of 8 ppm NF240 and 16 ppm HPMC22k and 2) Mix10k-D16-H16 refers to a PS-mixture of 16 ppm DF200 and 16 ppm HPMC10k.

In addition to frothers, a series of chemical reagents listed in Table 5 were used during flotation. All chemicals used in this research work were used as received, without any further purification.

Table 5. Details of other reagents used in this thesis

Name	Abbreviation	Use	Supplier	Catalog No	Purity
Calcium hydroxide	Ca(OH) ₂	pH regulator in flotation experiments	VWR Chemicals Belgium	470300-588	>98 %
Sodium hydroxide	NaOH	pH regulator in bubble size and foam property measurements	Merck	106495	300*
Sodium isobutyl xanthate	SIBX	Collector in Cu-bearing mineral flotation	Industrial grade	-	-
Sodium ethyl xanthate	SEX	Collector in Zn bearing mineral flotation	TCI	E0195	>95 %
Copper sulfate	CuSO ₄ · 5H ₂ O	Activator in Zn bearing mineral flotation	VWR Chemicals Belgium	23165.298	>98 %
Zinc sulfate	ZnSO ₄ · 7H ₂ O	Depressant in Cu ore experiments	Industrial grade	-	-

*According to internal quality standard of the Merck Group

3.2 Equipment and methods

This section presents the equipment used in this thesis, along with a general description of their standard operating procedures. Specific details of conditions used in each experimental campaign are compiled at the end of this section.

In all aspects of this thesis, the frother concentration was determined in ppm as a mass ratio between frother and the total mass of liquids in solution. For example, a dilution to 10000 ppm was created by adding 1 g of frother (or HPMC) to 99 g of water. In flotation experiments, the mass of frother was related to the mass of process water used in each experiment.

3.2.1 Characterization protocol of interfacial properties

The experimental procedure and conditions used in air-liquid interface experiments was based on the preliminary work presented in **Publication I**. This first publication revolved around building a protocol for proper characterization of the interface for both the frothers and the surface-active polymers in terms of properties relevant for flotation. These established measurement procedures are presented in the following two **Sections (3.2.2 and 3.2.3)**.

3.2.2 Dynamic surface tension

The influence of reagent type and concentration on the dynamic surface tension (DST) of an aqueous solution was measured in a BPA-800P bubble tensiometer (Attension, formerly KSV instruments). For each measurement, 100 ml sample

of aqueous solutions with known frother concentrations were prepared into a glass container with a diameter of 8 cm and a height of height 4.7 cm. The BPA-800P automatically determines the dynamic surface tension values as a function of bubble lifetime by using the maximum bubble pressure method.

A brief explanation on the experimental procedure used with this equipment is provided next. The needle of the apparatus descends into the frother solution while feeding a continuous stream of air bubbles. The equipment monitors the fluctuations in bubble pressure within the capillary. The pressure increases steadily until the radius of the bubble grows as large as the diameter of the capillary itself. This is the point where the maximum bubble pressure is observed (Jávor, 2014). A schematic illustration of the evolution of bubble pressure as a function of time is presented in Figure 5. The water used in DST experiments was purified to 18.2 M Ω with a Millipore Direct-Q water purification system, referred as ultra pure water (UPW) from now on.

Figure 5. Evolution of bubble pressure as a function of time in BPA-800p (Adapted from Jávor, 2014)

The DST measurements were conducted separately for each studied frother system, i.e. NF240, HPMC10k, HPMC22k and PS-mixtures thereof. A thorough characterization of the dynamic adsorption behavior was conducted for mixtures consisting of NF240 and HPMC22k. The concentrations of frother solutions measured with these experiments are presented in Table 6. The studied concentrations were selected to characterize the formulations within a concentration range expected to be used in industrial flotation processes. Furthermore, the DST experiments were conducted in the neutral pH of the UPW (5.5), in order to study the behavior of each frother formulation in as pristine conditions as possible. The results presented in **Section 4.1** are mean

values of all measured repetitions. Additionally, reference measurements were conducted in UPW as benchmark.

Table 6. Surfactant concentrations used in DST measurements

NF240 (ppm)	HPMC22k (ppm)	HPMC10k (ppm)	Mix22k with constant NF240 and varying HPMC22k (ppm)	Mix10k with constant NF240 (ppm)	Mix10k with constant HPMC10k (ppm)
8 ^a	8 ^a	8 ^a	N8 + H8 ^b /16 ^b /32 ^a /48 ^a	N16 + H8 ^a /16 ^a /32 ^a	N8 ^a /16 ^a /32 ^a + H16
16 ^a	16 ^a	16 ^a	N16 + H8 ^a /16 ^a /32 ^a /48 ^a		
32 ^a	32 ^a	32 ^a	N32 + H8 ^a /16 ^a /32 ^a /48 ^b		
48 ^a	48 ^a	48 ^a	N48 + H8 ^a /16 ^a /32 ^a /48 ^a		

^a) 3 repetitions

^b) 2 repetitions

The mean DST results were used to determine a single value for the diffusion rate of corresponding frother formulations. This was calculated by applying the short time approximation of the Ward-Tordai equation, combined with the Gibbs-isotherm (Nahringbauer, 1995; Eastoe and Dalton, 2000; Kanokkarn et al., 2017):

$$\gamma(t)_{t \rightarrow 0} = \gamma_0 - 2nRTC_b \sqrt{\frac{Dt}{\pi}} \quad (2)$$

where $\gamma(t)$ is surface tension at time t expressed in seconds (which needs to be close to zero, to represent the early stage diffusion-controlled region), γ_0 is the initial surface tension, $n = 1$ for nonionic surfactants and 2 for ionic surfactants, R is the universal gas constant (8.314 J mol⁻¹ K⁻¹), T is the absolute temperature (K), C_b is the total bulk concentration in mmol/l, D is the diffusion coefficient and π equals 3.1416. The form of Equation (2) originates from the fractional derivation used to solve the initial Ward-Tordai problem (Hristov, 2016). The BPA800-P monitors the temperature of the solution, which was on average 23.4 °C in the experiments that were used to determine diffusion coefficients. Equation 2 was solved by plotting γ vs. $\sqrt{t}$ using DST data from the first 0.85 seconds of each measurement and equaling the slope to $2nRTC_b \sqrt{D/\pi}$.

It is important to note that Equation 2 can only be applied to polymers in dilute concentrations (< 400 ppm) and by using the concentration of polymer segments in the solution as the value of C_b (Nahringbauer, 1995). The molecular weight of HPMC segments used in this work are presented in Table 4 and were calculated as an average value based on the specifications provided by the supplier (**Section 3.1**).

DST results measured with BPA are reported in **Publication I, III and IV**.

3.2.3 Bubble size, foam depth and foam stability

To determine the bubble size and foam properties of the frother systems studied in this thesis, the experimental setup presented in Figure 6 was used. The setup consists of a 1.5 l stirred vessel for the continuous mixing of an aqueous frother solution that is fed through a previously calibrated peristaltic pump to the

bottom of a flotation column. The laboratory-scale column consists of a Plexiglas® cylindrical vessel with a volumetric capacity of 10 l, manufactured in-house. Air is introduced at the bottom of the column through a sparger with opening sizes of 5 μm . The air flow rate was set at 0.4 l/min with a manual control valve attached to a rotameter.

Figure 6. Schematic diagram of the laboratory column experimental setup for measurement of foam properties (Nuorivaara and Serna, 2020a; Nuorivaara and Serna, 2020b)

To measure the bubble size distribution, a sampling tube was immersed into the column, at the aqueous-phase level. The sampling tube was connected to a viewing chamber with a red background light and a glass screen. A digital single-lens reflex camera (Nikon D750) was used to take pictures of the collected bubbles at intervals of four seconds. The camera parameters used were: F9.0, shutter speed 1/20000 and ISO1000. The water used in bubble size and foam property measurements was treated with an Elga Purelab Option-R 7/15 purifier, up to a resistance of 15 M Ω , referred to as pure water (PW) from now on. The pH was controlled with NaOH in bubble and foam property experiments conducted in elevated pH levels. The elevated pH level was selected based on typical pH-levels for chalcopyrite flotation (Bulatovic, 2007), and to corroborate whether the proposed tolerance towards changes in pH for HPMC (Coffey, 2006) were applicable also in bubble and foam properties at low concentrations.

The bubble size and foam property measurements for NF240, HPMC molecules and their PS-mixtures were conducted using reagent concentrations presented in Table 7 and were done in triplicate in order to ensure reproducibility. The conditions presented in Table 7 were based on a previously measured CCC value for NF240 (Jávor, 2014) as well as an assumption of a suitable concentration range to be studied for HPMC and its PS-mixtures. The results in **Sections 4.4** and **4.5** are presented as mean values of the repeated experiments. After each frother addition, the aqueous solution was circulated

through the column for at least 40 minutes before starting the measurement. This ensured a homogeneous frother concentration throughout the experimental setup, as calculated through mass balance and corroborated by DST measurements conducted on samples taken after the 40-minute homogenization period.

Table 7. Concentrations of bubble size and foam property measurements of NF240, both HPMC molecules and their PS-mixtures

Pure chemicals	NF240	HPMC 10k	HPMC 22k
Concentrations (ppm)	8/16/32/48 *	8/16/32/48	8/16/32/48 *
Mixtures	Mix10k	Mix22k	
Combinations	Mix10k-N16-H8/16/32	Mix22k-N16-H8/16/32 *	
Combinations	Mix10k-N8/16/32-H16	Mix22k-N8/16/32-H16 *	

* Measurements conducted at pH 10 as well

The obtained bubble images were processed using a MATLAB® routine to measure their diameter, thus generating a bubble size distribution. The routine consists on finding an adaptive threshold level, defining the edges of the bubbles and fitting to an ellipse on these edges, finally calculating the equivalent diameter based on the maximum and minimum diameter of the ellipse using Eq. 3 (Jávor et al., 2015):

$$D_{eq} = \sqrt[3]{D_{max}^2 \cdot D_{min}} \quad (3)$$

It should be noted that the minimum bubble diameter detected with this method was of 0.02 mm. The Sauter mean diameter (D_{32}) of each measured concentration was calculated based on the diameter results received from the MATLAB® routine (Jávor et al., 2015).

$$D_{32} = \frac{\sum D_{eq}^3}{\sum D_{eq}^2} \quad (4)$$

After determining the D_{32} for each frother system and concentration, the results were used to calculate the concentration for 95 % reduction in bubble size (CCC95) values for each frother formulation according to the following model (Cho and Laskowski, 2002; Quinn et al., 2014)

$$D_{32} = D_l + A \cdot \exp(-b \cdot C) \quad (5)$$

where D_l is the limiting (i.e. minimum) bubble size achieved with each frothing agent, A is the range between D_{32} of pure water and D_l , b is a decay function constant and C is the frother concentration. Consequently, CCC95 can be determined from the following Equation (6):

$$b = \frac{LN0.05}{CCC95} \quad (6)$$

For all measured frother concentrations, foam depth and stability were also measured. Foam depth was measured directly at the column through its transparent Plexiglas® walls with a measuring tape at 2 points around the column diameter. Foam stability was measured as the time it took for half of the existing foam to collapse after the air flow was turned off (Tsatouhas et al., 2006).

Bubble size measurements conducted with this set up are reported in **Publication I, II, III and IV**.

3.2.4 Interfacial property studies of DF200

In addition to the thorough interfacial studies conducted with NF240 as the surfactant component in the PS-mixtures, a brief interfacial characterization was conducted with DF200. Considering that DF200 and NF240 are similar frothers with the same molecular weight and only a minor variance in their structure (Jávor, 2014), it was reasonable to assume that their behavior as a component in the PS-mixtures was going to be comparable as well. In order to corroborate this hypothesis, it was decided to run interfacial characterization for DF200 formulations in the same conditions that were studied in the flotation of Zn model ore (**Section 3.2.7.2**).

This set of experiments consisted of measuring DST as presented in **Section 3.2.2**, as well as bubble size, foam depth and foam stability as presented in **Section 3.2.3** in conditions compiled to Table 8. It is important to note that the bubble size and foam characterization experiments were conducted in pH 11.1 in order to study these properties in similar conditions compared to the flotation experiments.

Table 8. Experimental conditions for DST, bubble size, foam depth and foam stability measurements for DF200 and its PS-mixtures

Frother system (repetitions)	Total concentration (ppm)
DF200 (x3)	30
Mix10k-D15-H15 (x2)	30
Mix22k-D15-H15 (x2)	30

Interfacial characterization conducted for DF200 and its PS-mixtures are reported in **Publication III**.

3.2.5 Mineral sample preparation

The mineral samples that were obtained as rocks or pebbles (Cu ore, Chalcopyrite, Sphalerite) were crushed in two stages: first, with a laboratory-scale jaw crusher (Wedag MN 931/1 with a 200x125 mm gap and a minimum opening of 12 mm) and second, with a laboratory-scale roller crusher (Wedag) to a nominal particle size of <2.8 mm. After this initial crushing stage, the samples were divided into representative samples of specific weights so that the

targeted total mass of a sample used in a single flotation experiment was 600 g. The target weights for each mineral or ore were determined separately for each experimental Campaign (details in **Section 3.2.6**). This stage of sample preparation was conducted with a Retsch rotary sampling device and the masses of the samples were verified with a Precisa XB 6200D laboratory scale. Even when samples did not need crushing (e.g., quartz, Cu-containing tailings), they were divided into representative samples as explained above.

3.2.6 Grinding

Depending on the properties, type and mass of the studied mineral samples, the grinding was conducted either completely in a laboratory scale ball mill (Technical research center of Finland, type 14MK3/9), or dry ground in a ring mill (Fritsch Pulverisette 9) with tungsten carbide rings as grinding media. The volume of the ball mill was 5.67 l, and the grinding was conducted with a ball charge of 5.5 kg and with a 1:1 solid-to-water ratio.

The grinding time required for each mineral sample was determined separately with milling curves of grinding time vs. particle size (e.g. d80) obtained experimentally. The particle sizes were measured with a laser diffraction particle size analyzer (Mastersizer 3000).

3.2.7 Flotation Campaigns

The operating conditions used in the experiments of each specific flotation campaign are presented at the end of this chapter. The general procedures applied in sample preparation were presented in **Sections 3.2.4** and **3.2.5**. Additionally, a digital camera was used to capture video footage of the froth during all flotation experiments. These videos were used for qualitative froth analysis between different frothers.

After the comminution steps presented above, the mineral samples were inserted in an Outokumpu 1.5 liter laboratory scale flotation cell. Before commencing each experiment, an initial wetting and conditioning procedure was conducted. While the exact procedure varied between Campaigns (details presented later), the general conditioning procedure was as follows:

1. The sample was stirred with an impeller speed of 1300 rpm for 5 minutes
2. Reduction of impeller speed to 900 rpm for the duration of reagent additions
3. Addition of activator or depressant (if applicable), let mix for 3 minutes
4. Addition of collector (if applicable), let mix for 3 minutes
5. Addition of frother, let mix for 3 minutes
6. Increase of impeller speed back to 1300 rpm and turning on the air flow

PW was used in all flotation experiments. The natural pH PW is 5.5 and $\text{Ca}(\text{OH})_2$ was used to elevate the pH already in the water used in the grinding mill, when basic pH was required.

When using PS-mixtures, the commercial frother component (DF200 or NF240) was always added first and immediately afterwards the respective HPMC (22k or 10k). Finally, turning on the air flow was regarded as the beginning of the flotation experiment (i.e. $t = 0$). The operating parameters constantly used throughout all flotation experiments are presented in Table 9.

Table 9. Constant conditions used in flotation experiments

Parameter	Value
Air flow rate	4 l/min
Impeller speed	1300 rpm
Mass of solids	600 g
Solids content	33 %
Total volume of suspension	1.5 l

Different total flotation times were used in each campaign. Regardless of the total flotation time, all experiments followed the same pattern of collecting froth fractions: 0-3; 3-6; 6-10; 10-14; 14-20 and 20-30 minutes. The maximum flotation time for each Campaign is presented later in this chapter. Additionally, the same froth scraping pattern was used throughout all flotation experiments as follows: in the first 10 minutes, the froth was scraped 10 times every 30 seconds; from 10 to 20 minutes, 15 times every 60 seconds; and from 20 to 30 minutes 20 times every 120 seconds. In all experiments, additional water containing the corresponding frother at its target concentration was added between each collected froth fraction in order to maintain the original pulp level. After each flotation experiment, the collected froth fractions, as well as the final tailings, were dewatered, first by filtration in a funnel and finally by heating overnight in a convection oven at 50 °C.

The flotation performance of the studied frothers in all experimental Campaigns was evaluated in terms of grade, recovery, mass pull, SE and the first order kinetic constant. The grade of each fraction was determined with an Oxford Instruments, X-Met5100 x-ray fluorescence (XRF) gun with a specific setting for high sulfur grade mineral samples. A sub-group of the samples was additionally characterized with induced coupled plasma (ICP) elemental analysis. A correction factor for the XRF data was determined based on the ICP results, which was subsequently applied to all results. This procedure was performed separately for each flotation Campaign. The recoveries of species were calculated based on the measured mass balances and grades of the fractions. Furthermore, the feed grade values were always determined separately for each flotation sample based on these assays.

The SE for each flotation experiment was calculated with the method presented by Wills and Finch (2015), where separation efficiency is determined according to Eq. 7:

$$SE = R_m - R_g = \frac{100 C_f m (c-f)}{(m-f) f} \quad (7)$$

where SE is Separation Efficiency, R_m is % recovery of the valuable mineral, R_g is % recovery of the gangue into the concentrate, C_f is the fraction of total feed weight that reports to the concentrate, f is % of metal in the feed, c is % of metal in the concentrate, and m is % of metal content in the valuable mineral (varied between Campaigns).

In all flotation experiments, a first-order flotation rate was assumed, and thus, the flotation kinetic constant was calculated for each experiment with Equation (8) (Wills and Finch, 2015).

$$R_t = R_{max}[1 - \exp(-kt)] \quad (8)$$

where R_t is total recovery at time (t), R_{max} is maximum theoretical recovery, k is kinetic constant, and t is time in seconds.

Equation (8) was solved using an iterative routine in Microsoft Excel™, which determined the values of k and R_{max} that was based on the measured cumulative recovery values.

Additionally, a partial least squares (PLS) model created with the MODDE software was applied to the flotation results from experiments conducted with synthetic ores (**Section 3.2.7.2**) with the goal to evaluate the sensitivity of each frother system towards changes in experimental conditions (i.e., collector concentration and pH). This was achieved by comparing the values of the coefficients of each factor in the model. The model created by MODDE follows the form presented in Equation 9:

$$Y = C_0 + C_1 * C_{col} + C_2 * C_{pH} + C_3 * C_{col*pH} \quad (9)$$

Where Y is the response (e.g. recovery or grade of the froth product), C_{0-3} are model coefficients, C_{col} is the collector concentration and C_{pH} is the pH level and the model also considers the interaction of the two.

3.2.7.1 Flotation Campaign 1 – Chalcopyrite natural ore

The first mineral sample studied in this thesis was a chalcopyrite containing sulfidic ore provided by First Quantum Minerals Ltd.'s Pyhäsalmi mine in Finland. The provided sample was in pebble form (up to few centimeters) and was collected after the primary crushing stage. The valuable metallic minerals that are industrially separated from this ore are sphalerite and chalcopyrite. Based on the elemental characterization of the sample, it is expected to have ca. 1 % Cu; 1.5 % Zn and >30 % of Fe. The majority of Fe is present in the form of pyrite, as this ore is known to be exceptionally rich in this mineral.

The ore was received as rocks and thus it was crushed before dividing it into representative samples of approximately 600 g (see **Section 3.2.5**). The particle size distribution of the ore sample used for flotation experiments is presented in Table 10.

Table 10. Particle size distribution of Pyhäsalmi ore after 45 minutes of grinding in a laboratory-scale ball mill

d10 (µm)	d50 (µm)	d90 (µm)
4.5	40.5	115

In order to reproduce the conditions of the Pyhäsalmi concentrator plant as closely as possible, the flotation chemical reagents were added during sample grinding. After 15 min of grinding, ZnSO₄ (depressant) was added and, after 30 min, SIBX (collector) was added. After the total grinding time of 45 minutes, the sample was transported from the mill into the laboratory-scale flotation cell. At this point, stirring and frother addition was carried out. The froth fractions were collected at six time periods up to 30 minutes.

Due to the complex nature of flotation and the unknown nature of the studied systems, particularly HPMC and its PS-mixtures, a systematic preliminary study (not included in this thesis) was carried out to select a suitable range of chemical dosages to identify the differences in flotation performance between the studied frother systems (Rinne, 2018). For example, the preliminary studies showed that, in the presence of pure HPMC, no froth formed in concentrations smaller than 30 ppm. Additionally, as will be presented in **Section 4.5**, 30 ppm is beyond the CCC of NF240 and both HPMC molecules and the D₃₂ in the presence of the respective PS-mixtures also sufficiently small. Furthermore, overdosing of frother is to be avoided to obtain acceptable performance. Therefore, this was selected as the concentration level of the total frother dosage for the experimental conditions used in this set of experiments. The pH level was set at 12.4 in an effort to depress the pyrite present in the ore. The experimental conditions used in this campaign are compiled in Table 11.

Table 11. Experimental conditions of flotation experiments conducted with Cu ore

Experiment name	Frothing agent used	Concentration of frothing agent (ppm)	SIBX (g/t)	ZnSO ₄ (g/t)	pH	Calculated Head grade (%)
NF	NF240	30	30	500	12.4	1.08
HPMC	HPMC22k	30	30	500	12.4	0.89
Mix 1	Mix22k-N16-H16	16 + 16	30	500	12.4	1.01
Mix 2	Mix10k-N16-H16	16 + 16	30	500	12.4	0.97
Mix 3	Mix10k-N10-H20	10 + 20	30	500	12.4	1.03
Mix 4	Mix10k-N20-H10	20 + 10	30	500	12.4	0.99

The results with natural ore containing chalcopyrite are presented in **Publication II**.

3.2.7.2 Flotation Campaign 2 - Model ores

Although some advantages were reported with the experimental HPMC-based frothers during the flotation campaign presented in **Section 3.2.7.1**, a deeper understanding of the froth stabilization mechanisms of PS-mixtures was needed. Thus, the focus was shifted towards more ideal systems, i.e. by studying flotation performance using model ores. Two parallel experimental Campaigns

were performed, the first one with a chalcopyrite (CuFeS_2) containing model ore and the second with a sphalerite $[(\text{Zn},\text{Fe})\text{S}]$ containing model ore. The goal of these two Campaigns was to identify specific strengths and limits of the proposed formulations while simultaneously verifying their applicability in selective flotation of with ores containing minerals other than chalcopyrite.

The first model ore consisted of a mixture of chalcopyrite (CuFeS_2) and quartz (SiO_2). Chalcopyrite samples were ordered from Ward's Science (Catalog No. 470025-376), originating from Durango, Mexico, with an approximate Cu grade of 27.14 % according to ICP analyses conducted in-house. The gangue mineral in the synthetic ore sample was quartz (SiO_2) provided by Sibelco Nordic Oy Ab. The declared nominal purity of the quartz was 99.2 % and the nominal particle size was 0.1-0.6 mm.

The second model ore consisted of a mixture of sphalerite and quartz. Sphalerite samples were ordered from Ward's Science (Catalog No. 470025-804), originating from Piedras Verdes, Chihuahua, Mexico, with an approximate Zn grade of 54 % according to ICP analyses. The gangue mineral in the synthetic ore sample was quartz (SiO_2) provided by Sibelco Nordic Oy Ab (same as above).

The chalcopyrite and sphalerite samples had to be crushed before dividing them into representative samples of approximately 50 g and 90 g, respectively. Consequently, the quartz was divided into representative samples of approximately 550 g and 510 g. The head grade of these samples was 2.2 % on average for Cu and 8.27 % for Zn as verified by ICP-analysis.

Due to the differences in the hardness of the minerals, the components of the synthetic ore were ground separately. The pure chalcopyrite and sphalerite samples were ground in the ring mill for 12 seconds and 25 seconds respectively. Whereas the quartz was ground in the ball mill for 45 minutes and 50 minutes (see **Section 3.2.6**). The target particle size of the Cu model ore was $d_{80} = 100 \mu\text{m}$ and $d_{80} = 90 \mu\text{m}$ for the Zn model ore.

The conditioning procedure for Cu model ore was conducted without the additions of depressant or activator, while for the Zn model ore, the conditioning phase was done exactly as in **Section 3.2.7** with only activator addition as the third step. The froth fractions were collected up to 20 minutes for Cu model ore and up to 14 minutes for Zn model ore.

The three frother systems evaluated with the Cu model ore were i) pure NF240, ii) pure HPMC10k and iii) their PS-mixture (Mix10k formulations 1:1 ratio) at a total concentration of 32 ppm (Table 12). For the Zn model ore, the different frother systems studied were 1) DF200, 2) HPMC 10k, 3) HPMC 22k, 4) Mix 10k, (DF200 + HPMC 10k as a 1:1 mixture) 5) Mix 22k, (DF200 + HPMC 22k as a 1:1 mixture) at a total frother concentration of 30 ppm (Table 13). The frother concentrations for each ore type were chosen so that the CCC of each commercial frother is exceeded (Jávor, 2014), while attempting to avoid excessive concentrarions, which can be detrimental for flotation performance.

The experimental conditions for the two synthetic ores are presented in Tables 11 and 12. The factor 1 values for collector concentration and pH represent those typically used in industrial applications, while the factor 2 values were chosen

to demonstrate operating conditions considered detrimental for froth stability and flotation performance according to previous studies. Indeed, pH 12 for chalcopyrite and pH 11.1 for sphalerite flotation are commonly used in their respective industrial flotation processes (Bulatovic, 2007). Whereas, species of reduced hydrophobicity are reportedly forming at the varied pH levels; iron hydroxide formation on the surface of chalcopyrite at pH < 6 (Bulatovic, 2007) and colloidal cupric hydroxide formation on copper activated sphalerite at high pH levels (Chandra and Gerson, 2009).

Table 12. Factorial Design of synthetic Cu ore experiments

Factor	Factor value 1	Factor value 2
Collector (g/t)	30	5
pH	12	5.5
Frother formulations studied in each condition		
NF240 = 32 ppm		
HPMC10k = 32ppm		
Mix10k-N16-H16		

Table 13. Experimental set up of the flotation experiments conducted with synthetic Zn ore

Factor	Factor value 1	Factor value 2
Collector (g/t)	80	20
pH	11.1	12.3
CuSO ₄ (g/t)	1565	
Frother formulations studied in each condition		
DF200 = 30 ppm		
HPMC10k = 30ppm		
HPMC22k = 30ppm		
Mix10k-D15-H15		
Mix22k-D15-H15		

Furthermore, the reproducibility of these Campaigns was evaluated by running separate sets of additional experiments for both synthetic ores (samples Cu1-Cu8 for synthetic Cu ore and samples Zn1-Zn6 for synthetic Zn ore) in conditions according to Tables 14 and 15. The experimental error was evaluated in terms of standard error of the mean (σ_x) and 95 % confidence interval (CI).

Table 14. Conditions of repeated experiments for synthetic Cu ore

Sample	Frother	Collector concentration (g/t)	pH
Cu1-Cu8	Mix10k-N16-H16	20 g/t	10

Table 15. Conditions of repeated experiments for synthetic Zn ore

Sample	Frother	Collector concentration (g/t)	pH
Zn1	DF200	80	12.3
Zn2	DF200	80	12.3
Zn3	DF200	80	12.3
Zn4	DF200	80	12.3
Zn5	DF200	20	12.3
Zn6	Mix22k-D15-H15	20	12.3

Cu model ore results are presented in **Publication V** and Zn model ore results are presented in **Publication III**.

3.2.7.3 Campaign 3 - Flotation of Cu tailings

The final flotation campaign was conducted on low grade Cu-containing tailings. The goal of this campaign was to evaluate the applicability of the proposed frother formulations with a feed material that is known to be exceptionally difficult to process effectively.

A sample of real tailings was obtained from First Quantum Minerals Ltd.'s Pyhäsalmi mine located in Central Finland. The sample was obtained in the form of a wet cake with moisture content determined experimentally to be 2.8 % and did not undergo any further processing before the flotation experiments. To properly assess the flotation behavior of this Campaign, it is important to mention that the tailings produced by the Pyhäsalmi concentrator are the result of the sequential flotation of chalcopyrite, sphalerite and pyrite. Therefore, the tailings have undergone conditioning for pyrite flotation as the last flotation stage before reaching the tailings pond. In previous studies, the main components of the tailings have been reported as pyrite (FeS_2), Barite (BaSO_4), plagioclase $[(\text{Na,Ca})\text{Al}(\text{Al,Si})\text{Si}_2\text{O}_8]$, quartz (SiO_2), hornblende $[(\text{Ca,Na})_{2-3}(\text{Mg,Fe,Al})_5(\text{Al,Si})_8\text{O}_{22}(\text{OH,F})_2]$ as well as residual sphalerite $[(\text{Zn,Fe})\text{S}]$ and chalcopyrite (CuFeS_2) (Nuorivaara et al., 2019).

An initial XRF analysis of the tailings showed a negligible amount of Ba (< 0.5 %), high concentration of Fe (> 30 %) and intermediate amounts of Ca (ca. 6 %). According to ICP analysis, the average Fe content was 36.7 % and the Cu content was 0.10 %. The samples were divided into representative samples of 600 g.

Because the extent of the remnant hydrophobicity of the tailings was unknown and their particle sizes were within ranges acceptable for flotation, it was decided to run flotation tests first in the presence of untreated tailings, followed by a set of experiments where a short (i.e., 7.5 minute) regrinding procedure in the ball mill, which was applied with the goal of liberating or reactivating chalcopyrite surfaces, rather than to further decrease particle sizes. The particle size distributions of unground and reground tailings samples are presented in

Figure 7. The conditioning step of the tailings included an extended initial wetting period of 10 minutes, since a more intensive initial stirring improved the flotation performance in the presence of tailings in a recent study (Nuorivaara et al., 2019). Furthermore, the only flotation reagent type used in this set of experiments was the frother.

The conditions studied in the presence of tailings are presented in Table 16. While tailings have a reputation of being notoriously difficult to float efficiently, the aim of this Campaign was to study the possibility of recovering Cu from tailings with as little modification to the chemical conditions as possible. Along with the omission of xanthates, it was decided to slightly increase the frother concentrations compared to previous Campaigns in an effort to aid in maintaining a proper froth phase during flotation. Consequently, the altered pH level was chosen to represent slightly less extreme conditions. As seen, the tailings flotation campaign consisted of experiments exploring the flotation performance with the three frother systems for untreated and re-ground tailings.

Figure 7. Cumulative particle size distribution for as is and reground tailings samples

Table 16. Experimental design of the flotation tests conducted with Cu-bearing tailings (*NF*: NF240, *HP*: HPMC 22k, *Mix*: PS-mixture 22k, *AI*: as-is, i.e., not re-ground, *RG*: re-ground, *F*: frother only, 5: pH 5.5, 10: pH 10)

Experiment	Chemicals	pH	Re-grinding
NF-AI-F-5	NF240 48ppm	5.5	No
HP-AI-F-5	HPMC22k 48ppm	5.5	No
Mix-AI-F-5	Mix22k-N32-H16	5.5	No
NF-AI-F-10	NF240 48ppm	10	No
HP-AI-F-10	HPMC22k 48ppm	10	No
Mix-AI-F-10	Mix22k-N32-H16	10	No
NF-RG-F-5	NF240 48ppm	5.5	Yes
HP-RG-F-5	HPMC22k 48ppm	5.5	Yes
Mix-RG-F-5	Mix22k-N32-H16	5.5	Yes
NF-RG-F-10	NF240 48ppm	10	Yes
HP-RG-F-10	HPMC22k 48ppm	10	Yes
Mix-RG-F-10	Mix22k-N32-H16	10	Yes

Cu tailings results are presented in **Publication V**.

4. Main results and discussion

The main results of this research project are summarized in this section. First, the fundamental interfacial properties of aqueous systems in the presence of the studied frothers are presented. This is followed by the froth flotation experiments of various mineral species. As will be presented, there appears to be a correlation between the observed interfacial behavior of the experimental frothers and their flotation behavior.

4.1 Preliminary interfacial characterization

The first experiments in this project were conducted with an aim to determine a suitable measurement protocol for characterizing the interfacial properties of commercial frothers, HPMC and their PS-mixtures. As mentioned in the **Introduction**, apart from studies directly connected to this research project (Nuorivaara and Serna, 2016; Rinne, 2018; Lamberti, 2019; Nuorivaara and Serna, 2020a; Nuorivaara and Serna, 2020b; Nuorivaara and Serna, 2020c) no prior work has studied the interfacial properties of surface-active polymers with methods utilized in frother studies. Thus, the findings of **Publication I** could be regarded as identifying a reliable method for measuring and interpreting the results of surface-active polymers at the air-liquid interface. These findings were later applied in the thorough interfacial characterization of the studied species (presented from **Sections 4.2. to 4.5**).

The results obtained in **Publication I** showed the first indications of the unique behavior of HPMC as foam stabilization reagent. Therefore, the results of this first study can be considered as the source of the initial incentive to further study the applicability of HPMC as a flotation frother.

4.2 Dynamic adsorption properties

While it is known that HPMC can significantly affect the surface tension of the air-liquid interface (Camino et al., 2009; Paraskevopoulou and Kiossegoulou, 2013), most of the data available in the literature present values of surface tension at thermodynamic equilibrium (Nahringbauer, 1995; Pérez et al., 2008; Caimno et al., 2009). Furthermore, as discussed in the **Introduction** section, the strength of surface activity in HPMC varies depending on the ratio of its hydroxypropyl and methoxy groups along the cellulose backbone. Considering

that the nature of flotation is highly dynamic and bubble lifetimes in a flotation cell are typically within the range of a few minutes (Diaz and Yianatos, 2010), it was necessary to study the surface tension of HPMC and its PS-mixtures with short bubble lifetimes as provided by the BPA. This approach was used as the first step in characterizing the influence of new frother formulations on surface tension in comparison with commercial frothers. The behavior of the frothers are first presented as aqueous mixtures of a single surfactant species. Afterwards, the properties of their mixtures were compared with those of the single frother systems. The results presented in this section are mean values of all experiments performed in each of the conditions.

Figure 8. Evolution of γ in the presence of pure reagents (note the change in the scale of y-axis) (Nuorivaara and Serna, 2020b)

The results presented in Figure 8 showcase the differences between the interfacial behavior of small surfactant molecules and surface-active polymers. NF240 adsorbs rapidly on the interface, resulting in significant reductions to γ at short bubble lifetimes and low concentrations. However, in the presence of HPMC, the results indicate the existence of an induction time before the polymer starts to significantly affect γ .

As discussed in **Section 2.2**, the initial orientation of adsorbed polymers is flat and it slowly changes towards a perpendicular arrangement. According to previous studies (Nahringbauer, 1995; Pérez et al., 2006) this phenomenon is dependent on both time and concentration. Such observations are corroborated by the results presented in Figure 8, although the results also demonstrate an additional affiliation to the size of the polymer. Indeed, when comparing the results of HPMC10k and HPMC22k, a rapidly decaying γ with the former is already observed at 32 ppm concentration. On the other hand, the first

indications of γ reduction within 10 s are observed only at 48 ppm of HPMC22k. Based on these observations it can be claimed that the uncoiling and rearrangement of polymer segments occurs faster for shorter polymers, which is observed as a shorter induction time for HPMC10k. The results presented here thus demonstrate that the length of the induction time is also determined by the polymer chain length. However, the size of the polymer is not expected to alter the equilibrium surface tension, which has been connected to the amount of polymer segments adsorbed at the interface and thus are independent of polymer size (Nahringbauer, 1995).

When the interfacial behavior of single species systems is compared to their PS-mixture counterparts (Figure 9), their behavior is not merely an average of their pure components. Instead, they seem to mimic the most active component of the mixture. For example, when observing Mix22k formulations, the mixtures always achieved lower γ values compared to pure NF240 during the first few seconds. This effect was most evident in the HPMC-rich mixture in 48 ppm total concentration (Mix22-N16-H32, Figure 9-C). After the initial adsorption, their γ values approach those of pure NF240 towards the end of each experiment. These results indicate that the presence of the studied PS-mixtures leads to i) accelerated adsorption of surface-active species and ii) comparable surface-activity of the adsorbed species to NF240 at bubble lifetimes of approximately 10 s.

In Mix10k formulations the initial adsorption behavior is similar to Mix22k formulations. However, at bubble lifetimes exceeding the induction time of HPMC10k, a significant drop in γ is observed (Figure 9 D & E), thus achieving γ values significantly smaller compared to pure NF240. Similar to pure HPMC10k, the decrease of γ is accelerated by increasing the total concentration of Mix10k formulations.

Figure 9. DST comparison of PS-mixes and pure components at total concentrations of 16, 32 and 48 ppm. Mix22k formulations are presented in the left column and Mix10k formulations are presented in the right column (Nuorivaara and Serna, 2020b)

Evidently, the rate of γ change and its final value depend on the total concentration of the applied frother formulation and the ratio between the polymer and the surfactant (when using PS-mixtures). Nonetheless, there are clear indications of synergistic acceleration in γ dynamics observed in the presence of PS-mixtures. According to Bain et al. (2010), the decreased γ values can be regarded as concrete evidence of synergistic PS-complexation at the interface. As discussed above, such interactions were observed already in the

initial stages ($t < 0.85$ s) of adsorption in the presence of both PS-mixtures. Similar observations have been made by scholars studying various PS-mixtures (Noskov et al., 2007; Petkova et al., 2012; Slastanova et al., 2020), but the results presented here represent the first such observations with a nonionic polymer and a nonionic surfactant pair (to the best knowledge of the author).

In summary:

- I. There is an induction time for HPMC, after which the γ starts rapidly decreasing.
- II. The induction time of HPMC is dependent on time, concentration and molecular weight.
- III. At similar total concentrations, the presence of PS-mixtures accelerated the reductions of γ during the initial adsorption compared to the pure reagents.
- IV. After the initial adsorption, the behavior of the PS-mixed layer mimicked that of the more surface-active component at each concentration.
- V. At 10 s bubble lifetime, the surface-activity of PS-mixed layers are comparable to those of NF240 and thus can be regarded as a suitable frother formulation.

4.3 Diffusion rate

The diffusion rates of the studied chemicals were calculated as described in **Section 3.2.2** in order to further understand the adsorption behavior of these new PS-mixtures. Figure 10 presents the diffusion results of all measured Mix22k formulations. The reported natural tendency of decreasing diffusion rates with increasing total concentration (Eastoe and Dalton, 2000; Guzmán et al., 2016) is also observed in Figure 10. However, there is an apparent difference in the behavior of pure surfactant systems compared to their PS-mixtures. PS-mixtures with small amounts of HPMC have similar rates of diffusion as pure NF240, yet when the ratio of HPMC is increased, the resulting diffusion rate is accelerated compared to their pure component counterparts. Furthermore, the decrease in diffusion rate is smaller when the total concentration is increased purely by adding more HPMC into the mixture. Such phenomenon is indicative of a highly influential role of the HPMC22k molecule on the adsorption kinetics of this particular PS-mixture. This is further corroborated when observing the results obtained in mixtures with less than 50 % HPMC22k, where the diffusion rates match closely to those of pure NF240, thus indicating the dominance of the surfactant fraction. These results show clear evidence of the importance of the polymeric component in the observed acceleration of the diffusion rate. Considering that pure HPMC does not present faster diffusion properties compared to NF240, the acceleration of diffusion rates represents concrete evidence of synergistic effects between the components in the PS-mixtures. A reasonable explanation to this was found to the work of Babak et al. (2007). Accordingly, the interaction of the surfactant towards the polymer can effectively resemble an additional active group, thus working as a driving force

towards faster adsorption kinetics and diffusion rates of the polymeric component of the mixture.

In summary:

- I. Mixtures with ≥ 50 % HPMC demonstrated faster diffusion rates compared to their pure reagent counterparts.
- II. The results indicate that the presence of HPMC is highly influential in increasing diffusion rate.
- III. This observed acceleration is the very first concrete evidence of synergistic adsorption of the components in this specific PS-mixture (according to the best knowledge of the author).
- IV. Based on the results presented in this section, PS-mixtures with ≥ 50 % HPMC seem more attractive formulations to be used in flotation.

Figure 10. Diffusion rates of different concentrations of Mix22k with static NF240 concentration and increasing HPMC concentration. The labels in the figure display the molar concentration ratio of HPMC22k in the mixture, while the lines serve as a visual guide that helps following a single static NF240 concentration (Nuorivaara and Serna, 2020b)

4.4 Bubble size

After identifying the synergistic adsorption tendencies of the proposed frother formulations, their bubble size reducing properties were studied in terms of D_{32} and bubble size distribution. D_{32} results of the pure component systems are presented in Figure 11 and the results of their PS-mixtures are presented in Figure 12. According to Figure 11, the bubble size reducing properties of NF240 and both studied HPMC molecules are comparable. However, when the components are mixed together (Figure 12), a second synergistic phenomenon is observed as the measured bubble size further decreases, compared to those of

the pure component systems. Previous reports of frother mixtures have shown a successful reduction in the CCC concentration, but the minimum bubble size was unaffected regardless of the frother mixture used (Elmahdy and Finch, 2013). This further reduction in bubble size was the most substantial in mixtures where its HPMC concentration was kept constant and the NF240 concentration was increased beyond its pure component CCC. These results indicate that the synergistic interaction between components of the PS-mixtures also assists in the formation of smaller bubbles compared to single surfactant species.

Figure 11. D_{32} as a function of total frother concentration and determined CCC95 values for pure frother systems at pH 5.5 (Nuorivaara and Serna, 2020)

Figure 12. D_{32} as a function of total frother concentration and determined CCC95 values for PS-mixture systems at pH 5.5 (Nuorivaara and Serna, 2020b)

In order to fully understand the underlying reasons behind this behavior, it is necessary to also investigate the bubble size distribution of the studied frother formulations (Figure 13). The most peculiar observation from Figure 13 is the

spontaneous formation of a bi-modal distribution in the presence of both samples of pure HPMC molecules. It is known that pure water exhibits a bi-modal bubble size distribution, which has been connected to different bubble-bubble interactions (Quinn and Finch, 2012). According to the current frother knowledge, the distribution always progresses towards a uni-modal distribution when the frother concentration approaches its CCC, as is observed in the case of pure NF240 (Finch et al., 2008; Jàvor, 2014). The fact that the amount of both HPMC molecules used in the experiments of Figure 13 exceed their CCC-values, proves that this macromolecular surfactant offers bubble stabilization properties that have not been reported earlier in association with frother studies. It is likely that one of such properties provided by HPMC is a superior coalescence prevention compared to commercial frothers, reflected by the large population of bubbles with diameters smaller than 0.5 mm which, in combination with larger bubbles may be advantageous for flotation (Tao et al., 2005).

Figure 13. Bubble size distribution in the presence of pure water and different frother formulations at pH 5.5 (Nuorivaara and Serna, 2020b)

Based on the results presented in Figures 11-13, a viable explanation for the observed bubble size reduction is connected to a description of PS-mixed layers by Petkova et al. (2012). They claimed that during film formation in PS-mixed systems, the surfactant adsorbs fast and consequently decelerates the film thinning during the initial stages of film formation. Thus, additional time for polymer adsorption is provided before film rupture can occur. Considering that an induction time was necessary in order for HPMC to start affecting the surface tension of the interface (as presented in **Section 4.2**), it is likely that the coalescence prevention properties provided by HPMC are also time dependent. Therefore, bubbles that collide early will coalesce, while bubbles that collide after a critical induction period already experience the steric protection of HPMC. The combination of these events results in a bi-modal bubble size distribution. Furthermore, when a frother is added to the system, it helps

preventing coalescence during the above-discussed critical time, resulting in a uni-modal distribution. Based on these results, the use of PS-mixtures offers the possibility of further reducing bubble sizes beyond the smallest possible diameter obtained with commercial frothers. Considering that the current consensus among flotation scholars is that, within the typical range used in flotation, the effective bubble size in the process should be as small as possible (Bulatovic, 2007; Wills and Finch, 2015) before reaching a limiting size (ca. < 0.2 mm) where bubbles will not have sufficient buoyancy to float particles efficiently (Farrokhpay et al., 2020). Thus, the results presented in this section can be considered as the first concrete advantage provided by the PS-mixture.

In summary:

- I. The synergistic effects identified for PS-mixtures in surface adsorption and diffusion rate studies manifested as further decreased bubble sizes.
- II. The most significant reductions in bubble sizes were observed when the HPMC concentration was kept constant and NF240 concentration was increased.
- III. The spontaneous formation of a bi-modal bubble size distribution in the presence of pure HPMC was attributed to a strong steric protection that was initiated only after an induction period, which enabled bubble coalescence during short bubble lifetimes and consequently prevented bubble coalescence at longer bubble lifetimes.
- IV. In PS-mixtures the surfactant species adsorbed faster and inhibited film thinning during short bubble lifetimes, as a consequence there was less coalescence before the stronger coalescence prevention of HPMC was enforced, resulting in a smaller overall bubble population.
- V. Based on bubble size results, mixtures with 16 ppm HPMC and ≥ 16 ppm NF240 seem most compelling as these formulations demonstrated steadily decreasing bubble sizes. Although, the final decision on the total frother concentration depends on the ore and associated froth properties.

4.5 Foam properties

The final bubble-related property studied in this thesis was foam depth and stability, presented in Tables 17 and 18 respectively. According to the results presented in Table 17, there is a clear difference between NF240, HPMC and their PS-mixtures. The foam depth is almost negligible in the presence of NF240 and it collapsed immediately after the air flow was turned off. As discussed in **Section 2.1**, it is generally accepted that sufficiently hydrophobic particles help maintaining froth stability in three-phase flotation and evidently NF240 is a frother that requires the presence of such particles in order to prevent froth collapse (Tan et al., 2010).

However, HPMC and its PS-mixtures were capable of building up a significant amount of foam and maintain it for a measurable period of time. Additionally, it seems that, in the presence of the PS-mixture, the amount of HPMC dictates the degree of foam stability and especially foam depth. This can be noticed by comparing the mixtures with constant HPMC concentration (Mix10k-N8/16/32-H16 & Mix22k-N8/16/32-H16) with those increasing HPMC levels (Mix10k-N16-H8/16/32 & Mix22k-N16-H8/16/32). In the experiments with constant concentration of HPMC, the addition of NF240 had no influence on the foam depth, whereas in those with constant NF240, the foam depth increased as HPMC concentration was elevated. These results indicate that the improved coalescence prevention provided by HPMC also results in a more stable foam. As discussed in **Section 2**, froth instability has been a major issue in many flotation processes, therefore a moderate improvement in foam stability can be beneficial from a flotation point of view, while simultaneously considering that excessive froth stability can be detrimental for the process (Farrokhpay, 2011).

In summary:

- I. The foam depth and stability were neglectable in all concentrations of pure NF240, while the presence of HPMC increased foam depth and stability as its concentration increased. Additionally, these effects were further enhanced when the larger HPMC22k polymer was used in concentrations exceeding 16 ppm.
- II. In PS-mixtures the concentration of HPMC seemed to be the defining factor for both foam depth and stability.
- III. The results indicate that PS-mixtures with high HPMC concentrations (≥ 32 ppm) may attribute towards significantly stable froths, which is considered detrimental for flotation.

Table 17. Foam depth (in mm) in the presence of frothing agents at pH 5.5 and pH 10 in parentheses when applicable (Nuorivaara and Serna, 2020b)

Total concentration		Foam depth (mm)			
Pure frothers	NF240	HPMC 10k		HPMC 22k	
8 ppm	3 (2)	7		3 (14)	
16 ppm	4 (2)	9		9 (21)	
32 ppm	4 (1)	10		12 (30)	
48 ppm	5 (1)	12		17 (50)	
Mix10k	Mix10k-N16-H8/16/32	Mix10k-N8/16/32-H16	Mix22k	Mix22k-N16-H8/16/32	Mix22k-N8/16/32-H16
24 ppm	6	11	24 ppm	6 (11)	8 (19)
32 ppm	10	10	32 ppm	9 (18)	9 (18)
48 ppm	12	12	48 ppm	12 (43)	8 (19)

Table 18. Foam stability in the presence of frothing agents at pH 5.5 and pH 10 in parentheses when applicable (Nuorivaara and Serna, 2020b)

Total concentration		Foam stability (s)			
Pure frothers	NF240	HPMC 10k		HPMC 22k	
8 ppm	0 (0)	5.6		0 (18.9)	
16 ppm	0 (0)	8.3		10.7 (23.3)	
32 ppm	0 (0)	12.3		24.9 (33.0)	
48 ppm	0 (0)	16.6		24.7 (54.4)	
Mix10k	Mix10k-N16-H8/16/32	Mix10k-N8/16/32-H16	Mix22k	Mix22k-N16-H8/16/32	Mix22k-N8/16/32-H16
24 ppm	9.6	10.6	24 ppm	15.5 (18.8)	14.8 (25.7)
32 ppm	14.2	14.2	32 ppm	19.2 (23.8)	19.2 (23.8)
48 ppm	15.3	19.6	48 ppm	26.6 (46.1)	20.1 (25.1)

4.6 DF200

In order to corroborate the initial hypothesis of DF200 demonstrating similar properties as a component in PS-mixtures as NF240, a brief interfacial property study was conducted.

The first studied property of DF200 and its PS-mixtures was their DST. The results presented in Figure 14 show fast adsorption and an overall weak effect on the surface tension provided by DF200. These observations are in line with Jávora et al. (2010). The two PS-mixtures show a tendency that slightly varies from what was observed in **Section 4.2**. Indeed, in the presence of the PS-mixtures, the initial γ is much closer to that of UPW compared to results presented in Figure 9. However, similarly to the NF240 mixtures, the γ values approach that of pure DF200 towards the end of the experiments. While it is difficult to evaluate the underlying reasons behind this slightly different behavior during short bubble lifetimes based on measurements conducted in a single concentration, it can be assumed that all studied PS-mixtures have similar tendencies in terms of surface-activity at bubble lifetimes relevant for flotation.

Figure 14. DST results of DF200, Mix10k-D15-H15 and Mix22k-D15-H15

In addition to the DST measurements, the bubble and foam properties of DF200 and its PS-mixtures were studied. The measured D_{32} in the presence of each frother formulation was in the same size range (Table 19). Furthermore, their corresponding bubble size distributions demonstrated a narrow uni-modal distribution (Figure 15). Considering that the concentration used in these experiments was such that the CCC of DF200 was exceeded (Jávor, 2014) and mixtures of NF240 and HPMC demonstrated small bubble sizes in similar concentrations (Figure 12), the observed results seemed reasonable, while further confirming the initial hypothesis.

Table 19. D_{32} of DF200, Mix10k-D15-H15 and Mix22k-D15-H15

Frother	D_{32}
DF200	1.02 (0.05)
Mix10k-D15-H15	1.04 (0.08)
Mix22k-D15-H15	1.05 (0.04)

Figure 15. Bubble size distributions of DF200, Mix10k-D15-H15 and Mix22k-D15-H15

The final aspect under inspection for DF200 and its PS-mixtures was the foam depth and foam stability. In the presence of pure DF200 the foam formation and stability were negligible similar to what was observed in the presence of pure NF240 (Tables 17 and 18). Correspondingly, the foam depths measured for these DF200 and HPMC mixtures (Table 20) were in line with results obtained for NF240 mixtures, considering the elevated pH that was used here. Although the foam stability that these mixtures demonstrated was slightly higher compared to those of the NF240 mixtures, it is reasonable to consider the behavior of the DF200 mixtures akin to NF240 mixtures.

In summary:

- I. Based on the results presented in this section, it is reasonable to assume that the initial hypothesis of NF240 mixtures having similar properties as DF200 mixtures is acceptable within the conditions studied in this thesis.

Table 20. Foam depth and foam stability of DF200, Mix10k-D15-H15 and Mix22k-D15-H15

Frother	Average foam depth (mm)	Foam stability (s)
DF200	0	0
Mix10k-D15-H15	23.5	40
Mix22k-D15-H15	19	35

4.7 Flotation results

After characterizing the relevant bubble properties of HPMC and its PS-mixtures, it was necessary to determine their performance in actual froth flotation experiments. These tests work as a proof of concept for the proposed frother formulations both in terms of fundamental behavior analysis and productivity performance. In other words, their goal is to show that the PS-mixtures preferentially act on the air-liquid interface and that the identified beneficial bubble properties are manifesting as concrete improvements in flotation performance.

4.7.1 Cu Ore

The first proof of concept for the proposed frother formulations was conducted in the presence of a Cu-containing natural ore from First Quantum Minerals Ltd.'s Pyhäsalmi mine in central Finland. The main source of Cu in this ore was in the form of chalcopyrite. While there was also approximately 1.5 % of Zn in the ore, mainly as sphalerite, the beneficiation was focused purely on chalcopyrite in this part of the study. Because the natural ore used in this Campaign was extremely high in pyrite ($\text{Fe} > 30\%$) and no cyanide was used in the laboratory flotation studies, in all studied frother systems the results showed relatively low Cu grades ($< 5\%$) compared to previous reports of 10-15 % with the same ore and collector (Leppinen et al., 1997). Figures 16 and 17 illustrate different performance parameters (Grade, Rec, SE & Mass pull) of Mix22k and Mix10k formulations as a function of the HPMC proportion in the PS-mixture, with pure NF240 on the left side and pure HPMC on the right side of the x-axis.

A multitude of preliminary experiments in varying conditions were conducted in the presence of pure HPMC in an effort to determine which conditions would be most favorable. These results are not a part of this thesis but are detailed in the work of Rinne (2018). According to such work there was a critical minimum concentration for pure HPMC (approximately 30ppm) under which froth formation was negligible. The proposed explanation for poor performance for both pure HPMC species in Figures 16 and 17 was this inability to generate a stable froth. The aforementioned work further explains that, when the concentration of HPMC22k was increased to 40 ppm, the grade of Cu in product decreases significantly indicating a loss of selectivity. In such conditions, only a relatively good performance ($\text{SE} \approx 38\%$) was obtained. While measurements with pure HPMC were conducted for further characterization and comparison in the campaigns to follow, the results of this first flotation Campaign indicated that only the PS-mixture formulations could compete with commercial frothers from a performance point of view, as will be discussed next.

The most unexpected aspect in these results was that the performance of the PS-mixtures was not an average result from between its pure component counterparts. As seen in Figures 16 and 17, the recovery of Cu is significantly higher in the presence of both PS-mixtures. Consequently, the grades obtained with the mixtures were lower compared to pure NF240. However, the tradeoff between grade and recovery is well known in the flotation industry (Wills and Finch, 2015). The significantly higher recoveries with PS-mixtures also manifest as higher SE values. When the polymeric component of the mixture was substituted to the smaller polymer (HPMC10k), it only resulted in a slight decline in recovery, while simultaneously significantly improving grade. This resulted in improved SE levels compared to the Mix22k formulation. Another interesting aspect from the Mix10k results was the slight differences in performance between different HPMC ratios. Based on the results presented in Figure 17, it seems possible to fine-tune the performance of the flotation process by varying the HPMC ratio of the PS-mixture. The latter provides a possibility for prioritizing recovery over grade or vice versa if significant variation in the feed quality is observed. Additionally, slightly faster flotation kinetics were

observed with most PS-mix formulations: Mix 1 = 0.00163; Mix 2 = 0.00143; Mix 3 = 0.00120; Mix 4 = 0.00147 vs. NF = 0.00132.

In summary

- I. These results were the first proof of concept for this specific PS-mixture being used as a frother to selectively separate chalcopyrite from a natural ore.
- II. The PS-mixtures provided better recoveries and SE while flotation kinetics were slightly faster compared to NF240.
- III. Mix22k formulation provided the highest recovery and Mix10k formulations the best SE.

Figure 16. Comparison of the flotation performance at the end of Cu ore experiments between NF240, HPMC22k and Mix22k-N16-H16 (Mix 1). (Nuorivaara and Serna, 2019)

Figure 17. Comparison of the flotation performance at the end of Cu ore experiments between NF240, HPMC10k, Mix10k-N10-H20 (Mix 3), Mix10k-N16-H16 (Mix 2) and Mix10k-N20-H10 (Mix 4). The hollow data points represent repetitions of Mix 2 and results for HPMC10k in conditions close to what was used in this campaign, data reproduced from Rinne (2018). (Nuorivaara and Serna, 2019)

4.7.2 Model ores

In an effort to explicitly identify the working principles behind the benefits and limitations of the proposed frother formulations, the proof of concept conducted with natural ore was followed by two model ore campaigns. The first model ore comprised chalcopyrite (CuFeS_2) as the valuable mineral and quartz (SiO_2) as the gangue mineral. The three different frother systems studied with this material were NF240, HPMC10k and Mix10k formulations. The second model ore consisted of sphalerite (Zn(Fe)S) and quartz (SiO_2), and was tested with five frother formulations (DF200, HPMC10k, HPMC22k, Mix10k & Mix22k).

Both campaigns were evaluated in three different operating conditions that represented at least: i) typical industrial practice (Figures 18 and 19), ii) changes at pH (Figures 20 and 21); and finally, iii) reductions in collector concentration (Figures 22 and 23). This approach allowed the decoupling of different phenomena taking place when operational conditions were varied.

In experiments conducted under conditions comparable to industrial practices, the performance of the commercial frothers (NF240 & DF200) and their PS-mixtures was significantly better compared to pure HPMC formulations. As seen, the results in Figures 18 and 19 confirmed that the studied PS-mixtures are capable of selectively separating valuable sulfidic minerals from non-sulfidic gangue (NSG) with grade and recovery levels comparable with commercial frothers.

Figure 18. Grade-recovery curves of synthetic Zn ore in industrial conditions (80 g/t collector and pH 11.1), all data points follow the same tendency of time fractions as exemplified for HPMC 22k (the dotted lines are visual references representing SE threshold values) (Nuorivaara and Serna, 2020a)

Figure 19. Grade-recovery curve of synthetic Cu ore in industrial conditions (30 g/t collector and pH 12), all data points follow the same tendency of time fractions as exemplified for NF240 (the dotted lines are visual references representing SE threshold values) (Nuorivaara and Serna, 2020c)

When the pH was altered, a negative impact in grades and recoveries was observed in the presence of the commercial frothers (Figures 20 and 21). The critical role of pulp pH in terms of flotation performance is generally accepted among flotation scholars. Depending on the ore composition, changes on pH level can have positive (Farrokhpay and Zalin, 2012) or negative effects (Sheni et al., 2018).

Based on a visual assessment in Zn experiments at elevated pH, the froth produced by the commercial frother decayed into an extremely brittle state which collapsed immediately and almost completely when the froth was attempted to be scraped. A similar decline in performance was observed by Goryachev et al. (2015), who reported a reduction in sphalerite recovery in the presence of methyl isobutyl carbinol when pH was above 12. Indeed, sphalerite is known to float poorly without copper activation at pH levels over 6.5-7 due to its iso-electric point (Göktepe, 2002). However, according to Chandra and Gerson (2009), precipitation of colloidal $\text{Cu}(\text{OH})_2$ on sphalerite surfaces upon copper activation occurs at high pH levels, which consequently reduces the surface hydrophobicity of sphalerite. It is thus reasonable to assume that the underlying reasons behind the loss of performance in the case of the commercial frother is related to such reductions in surface hydrophobicity.

While the froth produced by the commercial frother was not as brittle in the Cu flotation, the bursting of bubbles was significantly more frequent at lowered pH levels. In this case, the decline in flotation performance was expected to be

caused by the formation of iron hydroxide on the mineral surfaces at pH <6 (Bulatovic, 2007).

The observed sensitivity of commercial, polyglycol-based frothers to pH changes can be understood for two main reasons: i) state-of-art frothers are known to require sufficiently hydrophobic particles to form a stable froth (Tan et al., 2010) and ii) polyglycol-based frothers are known to be sensitive towards changes at pH even in two-phase foams (Sheni et al., 2018).

Ultimately, for both synthetic ores the decline in froth stability caused by reduced surface hydrophobicity impaired flotation kinetics and overall recovery in the presence of the commercial frothers. As a result, they presented the worst overall flotation performance when pH levels deviated from those used ideally in current industrial practice.

However, the performance of HPMC and its PS-mixtures remained largely unchanged. Films stabilized by HPMC are known to possess relatively high tolerance towards changes at pH (Coffey, 2006). This phenomenon seems to be present also in flotation. Thus, it is reasonable to assume that the self-stabilizing effects observed in **Section 4.5** are responsible for the observed superior froth stability, which consequently enables the flotation of less hydrophobic particles. This manifests as a more robust flotation performance under varying pH levels. Based on the results presented in Figures 20 and 21, such robustness remains when HPMC is a part of a PS-mixture.

Figure 20. Grade-recovery curves of synthetic Zn ore in increased pH (80 g/t collector and pH 12.3), all data points follow the same tendency of time fractions as exemplified for DF200 (the dotted lines are visual references representing SE threshold values) (Nuorivaara and Serna, 2020a)

Figure 21. Grade-recovery curve of synthetic Cu ore in reduced pH (30 g/t collector and pH 5.5), all data points follow the same tendency of time fractions as exemplified for Mix10k (the dotted lines are visual references representing SE threshold values) (Nuorivaara and Serna, 2020c)

In the final experimental conditions, the collector dose was reduced significantly (down to 5 g/t for Cu and 20 g/t for Zn) compared to its initial concentration (Figures 22 and 23). As seen, with commercial frothers there were only minor variations in performance with the synthetic Cu ore, while the performance of the single component formulations declined significantly with the Zn ore. Considering that collectors usually are solely responsible for hydrophobizing the valuable minerals (Bultovic, 2007), a diminished performance with lower concentration is expected, and similar results have been reported by other scholars as well (Celic, 2015).

However, a similar decline in flotation performance was not observed in the presence of the PS-mixtures. The results presented here further highlight the observation from above, where the improved foam stability observed in **Section 4.5**, is maintained in three-phase flotation, and consequently renders the interfacial stability less reliant towards the hydrophobicity of the particles in the froth, thus enabling the selective separation of less hydrophobic particles compared to the commercial frothers. These findings seem feasible, since both increased froth stability and small bubble sizes (**Section 4.4**) observed in the presence of the PS-mixtures have been connected to improved flotation performance (Wills and Finch, 2015). While this seems like suitable explanation for the observed robust performance of HPMC and its PS-mixtures, it is still unknown whether there is any interaction with particles. Although this aspect was considered to be outside the scope of this thesis, it is something that needs to be highlighted and confirmed in further characterization experiments.

The results hereby presented demonstrate the potential of a new type of frother formulation that provides a highly stable yet selective flotation performance that is able to match commercial frothers in industrial conditions and significantly outperform them throughout a wide variety of conditions. Considering that the observations were much alike with both synthetic ores, the results indicate that the performance of the studied PS-mixtures is not mineral dependent with sulfide minerals.

Figure 22. Grade-recovery curves of synthetic Zn ore in decreased collector concentration and increased pH (20 g/t collector and pH 12.3), all data points follow the same tendency of time fractions as exemplified for HPMC10k (the dotted lines are visual references representing SE threshold values) (Nuorivaara and Serna, 2020a)

Figure 23. Grade-recovery curve of synthetic Cu ore in reduced collector and pH (5 g/t collector and pH 5.5), all data points follow the same tendency of time fractions as exemplified for NF240 (the dotted lines are visual references representing SE threshold values) (Nuorivaara and Serna, 2020c)

The degree of robustness provided by the PS-mixtures could be quantified by creating separate PLS models for each frother system. The coefficient values provided by the model represent the tolerance that each formulation has towards variance in operational conditions. A smaller coefficient value is indicative of higher tolerance towards changes, while a larger value suggests a significant influence of operating parameters on the frother in question. The results presented in Figures 24 and 25 further highlight the high tolerance of HPMC, and especially its PS-mixtures, towards changes in operational conditions. Indeed, the largest coefficient values for each model ore were observed in the presence of the commercial frother.

Within the conditions studied, the biggest influence on flotation performance when using commercial frothers occurred due to changes in pH in the Cu measurements and in Zn measurements variance in collector concentration was the most influential.

Figure 24. Coefficient values of each frother system in terms of recovery, grade and maximum SE in flotation of synthetic Zn ore (Nuorivaara and Serna, 2020a)

Figure 25. Coefficient values of each frother system in terms of recovery, grade and maximum SE in flotation of synthetic Cu ore (Nuorivaara and Serna, 2020c)

The final performance factor evaluated was the flotation kinetics. In simple terms, higher kinetics reflect better productivity and are thus preferred. The results presented in Table 21 show superior kinetics in the presence of the PS-mixtures in all measured conditions with both synthetic ores. The kinetics of the commercial frothers slowed down in direct proportion to reductions in mineral hydrophobicity as the conditions were varied. The kinetics of the PS-mixtures maintained higher performance levels regardless of the changes in conditions. This observed improvement is likely due to higher froth stability and reduced bubble size provided by the PS-mixture (Farrokhpay et al., 2020), resulting in a lower dependency on the presence of highly hydrophobic minerals (Ahmed and Jameson, 1989; Tan et al., 2010; Wei et al., 2018).

A combination of such selective, robust and accelerated flotation performance by modifying the chemical system of the process can significantly impact the approach to industrial flotation practices in the future. While improved kinetics can be translated to higher throughputs in existing industrial circuits, the use of PS-mixtures can also initiate a new perspective on flotation by the means of reducing cell sizes or by utilizing a completely new type of circuit design, cell design or chemical system that is based on the unique properties provided by this novel frother chemistry. Admittedly, all these aspects can only be realized by further studying the peculiarities of the PS-mixtures.

Table 21. Values of first order kinetic constant in s^{-1} for experiments with model ores under various operating conditions (Nuorivaara and Serna, 2020a; Nuorivaara and Serna, 2020c)

Kinetic constant in flotation of synthetic Zn ore			
Frother	Industrial conditions (80/11.1)	Increased pH (80/12.3)	Reduced collector (20/12.3)
DF200	0.0111	0.0137	0.0100
HPMC 22k	0.0067	0.0085	0.0056
HPMC 10k	0.0107	0.0098	0.0100
Mix 22k	0.0159	0.0204	0.0140
Mix 10k	0.0202	0.0186	0.0146
Kinetic constant in flotation of synthetic Cu ore			
Frother	Industrial conditions (30/12)	Lowered pH (30/5.5)	Reduced collector (5/5.5)
NF240	0.0264	0.0114	0.0123
HPMC10k	0.0254	0.0100	0.0136
Mix10k	0.0267	0.0127	0.0169

Finally, the reliability of these campaigns was evaluated by running repetitions in selected experimental conditions (see Tables 14 and 15 for details). The results of these measurements are presented in Tables 22 and 23. The flotation experiments seem sufficiently reproducible with only minor CI values at a 95 % confidence when observing experiments with a high amount of repetitions (>4). A larger variance in 95 % CI is observed for synthetic Zn ore in both repetitions with 20 g/t collector and pH 12.3 (factors 2 & 2). However, the CI determination is based on the t-distribution and thus is highly dependent on the amount of repetitions. For example, the t-value used with two observations is 12.71; with

three observations 4.303 and with four observations 2.776. Thus, even minor standard errors can result in a very high 95 % CI due to a limited amount of repetitions. Nonetheless, the relatively small standard error values obtained from only two experiments combined with the good reproducibility of experiments with more repetitions imply that the other experiments would have acceptable 95 % CI as well if more repetitions were made. Therefore, it can be concluded that the flotation experiments presented in this section are within an acceptable degree of confidence. Considering that the experimental methodology used in all flotation experiments was similar throughout all flotation Campaigns and that the other Campaigns were conducted in conditions common for flotation, it is reasonable to assume that flotation results in the other two Campaigns are also reliable.

In summary:

- I. The studied PS-mixtures were capable of matching commercial frothers when floating model ores in industrial conditions.
- II. The performance of commercial frothers declined when pH levels were altered, while HPMC and its PS-mixtures were maintaining high performance levels.
- III. Reductions in collector concentration further reduced SE levels of the commercial frothers while the PS-mixtures maintained their performance.
- IV. PS-mixtures demonstrated equal or faster flotation kinetics compared to the commercial frothers in all studied conditions.

Table 22. Results of reproducibility measurements for synthetic Cu ore

Sample	Final Mass Pull (%)	Final Grade (%)	Final Recovery (%)	Max SE (%)	k (s ⁻¹)
Cu1	15.08	14.00	98.72	90.33	0.0111
Cu2	14.17	14.86	99.12	92.92	0.0196
Cu3	11.86	17.66	99.14	94.07	0.0138
Cu4	11.47	18.33	99.04	93.66	0.0125
Cu5	14.25	15.74	98.96	91.90	0.0147
Cu6	14.21	15.28	99.48	92.52	0.0134
Cu7	13.67	15.61	98.43	91.33	0.0122
Cu8	14.56	14.47	98.17	90.11	0.0115
Statistic	Final Mass Pull (%)	Final Grade (%)	Final Recovery (%)	Max SE (%)	k (s ⁻¹)
Mean	13.66	15.74	98.88	92.11	0.0136
σ_x	0.49	0.57	0.16	0.55	0.0010
CI (95 %)	1.13	1.32	0.37	1.27	0.0024

Table 23. Results of reproducibility measurements for synthetic Zn ore

Sample	Mass pull (%)	Recovery (%)	Grade (%)	Max SE (%)	k (s ⁻¹)
Increased pH (80/12.3)					
Original DF200	14.04	76.54	47.81	71.90	0.0137
Zn1	14.17	72.25	47.71	67.50	0.0109
Zn2	14.59	78.06	44.62	72.48	0.0119
Zn3	15.82	80.37	43.93	74.10	0.0119
Zn4	15.21	76.39	45.44	70.72	0.0119
Statistic	Mass pull (%)	Recovery (%)	Grade (%)	Max SE (%)	k (s ⁻¹)
Mean	14.77	76.72	45.90	71.34	0.0121
σ_x	0.33	1.33	0.80	1.10	0.0005
95 % CI	±0.93	±3.69	±2.21	±3.07	±0.0013
Reduced collector (20/12.3)					
Sample	Mass pull (%)	Recovery (%)	Grade (%)	Max SE (%)	k (s ⁻¹)
Original DF200	11.22	55.83	42.85	51.18	0.0100
Zn5	17.21	56.92	32.84	48.59	0.0106
Statistic	Mass pull (%)	Recovery (%)	Grade (%)	Max SE (%)	k (s ⁻¹)
Mean	14.21	56.38	37.85	49.89	0.0103
σ_x	3.00	0.55	5.01	1.29	0.0003
95 % CI	±38.09	±6.96	±63.64	±16.45	±0.0040
Reduced collector (20/12.3)					
Sample	Mass pull (%)	Recovery (%)	Grade (%)	Max SE (%)	k (s ⁻¹)
Original Mix22k	29.78	96.03	28.75	87.42	0.0140
Zn6	23.88	98.87	35.16	90.19	0.0132
Statistic	Mass pull (%)	Recovery (%)	Grade (%)	Max SE (%)	k (s ⁻¹)
Mean	26.83	97.45	31.96	88.81	0.0136
σ_x	2.95	1.42	3.20	1.39	0.0004
95 % CI	±37.46	±18.05	±40.70	±17.62	±0.0049

4.7.3 Tailings

The final evaluation of the studied frother formulations was conducted with Cu-bearing tailings. Considering that the previous Campaigns showed promising results in terms of floating minerals of low hydrophobicity, tailings seemed like an adequate material to truly test the limits of these new formulations.

The first clear observation was the significant difference in the froth when comparing its properties in the presence of different formulations. As seen in Figure 26, the froth is shallow and bright in the presence of NF240, indicating both minuscule amounts of particles present on the bubble interfaces and low froth stability. These observations further highlight the reliance on hydrophobic particles, that has been connected to oligomeric glycol frothers (Tan et al., 2010). On the contrary, the presence of HPMC by itself or as a part of the PS-mixture, demonstrated an entirely different behavior by generating a stable, mineral rich froth.

Figure 26. Images of flotation froths of the studied frother systems (NF-RG-F-10, HP-RG-F-10 & Mix-RG-F-10 respectively) (Nuorivaara and Serna, 2020c)

The observed froth behavior was reflected as clear differences in the mass pull of each formulation. The results presented in Table 24 show that HPMC contributed to a larger mass pull of minerals compared to pure NF240 in all conditions of this Campaign, while the use of mixtures resulted in an intermediate mass pull from between the pure components. This behavior suggests that HPMC is the main contribution to the increased mass pull in the presence of the PS-mix. Considering that the tailings had been conditioned for pyrite flotation before being directed to the tailings pond, a remanent degree of hydrophobicity can be expected in them. These results are thus in line with the observations from **Section 4.7.2**, where HPMC and its mixtures were capable of separating minerals with lower levels of hydrophobicity. The differences in mass pull are connected to the self-stabilizing properties of HPMC and its mixtures, as was observed in **Section 4.5**. The faster flotation kinetics observed in the presence of HPMC and its PS-mixtures (Table 24) can also be connected to increased froth stability and the consequent increases in froth recovery (Savassi et al., 1997).

Table 24. Cumulative mass pull and flotation kinetics of flotation experiments (NF: NF240, HP: HPMC 22k, Mix: PS-mixture 22k, AI: as-is, i.e., not re-ground, RG: re-ground, F: frother only, 5: pH 5.5, 10: pH 10) (Nuorivaara and Serna, 2020c)

Not ground	Final mass pull (%)	k (s ⁻¹)
NF-AI-F-5	0.27	0
HP-AI-F-5	38.35	0.0096
Mix-AI-F-5	27.29	0.0015
NF-AI-F-10	0.45	0
HP-AI-F-10	27.52	0.0051
Mix-AI-F-10	4.94	0.0013
Re-ground		
NF-RG-F-5	2.41	0.0012
HP-RG-F-5	10.14	0.0079
Mix-RG-F-5	4.50	0.0021
NF-RG-F-10	3.69	0.0017
HP-RG-F-10	14.34	0.0100
Mix-RG-F-10	6.24	0.0031

One of the most important aspects of frothers is to provide conditions that favor true flotation, i.e. the froth should be selective, and the effect of entrainment should be minimized. Although thorough entrainment studies were outside the scope of this thesis, it was deemed necessary to briefly assess the degree of entrainment in the presence of the studied frother formulations. While the results of **Section 4.7.2** demonstrated that HPMC and its PS-mixtures are capable of selective flotation, the results of Table 24 could suggest significant entrainment levels. However, upon a deeper examination, these observations are in contradiction with classical entrainment. For example, there was a larger mass pull in the experiments without regrinding.

Nevertheless, it was of interest to assess the degree of entrainment under the use of HPMC and PS-mixtures. One of the most common ways of assessing the degree of entrainment is to compare water recoveries with gangue recoveries. In this thesis, it was decided to use pure quartz as a proxy for entrainment, since it is known to be a highly hydrophilic mineral and it has a tendency of remaining in the water due to its repulsive van der Waals forces (Gilles et al., 2005). Thus, all quartz recovery can be assumed to occur via entrainment. This is further corroborated by the results presented in Figure 27, as the relationship between quartz recovery and water recovery is linear (Neethling and Cilliers, 2002; Yang et al., 2019). However, the amount of quartz recovered purely by entrainment is significantly smaller compared to the mass pulls in Table 24, implying that tailings flotation is not solely the result of entrainment.

Figure 27. Degree of entrainment in quartz flotation experiments (Nuorivaara and Serna, 2020c)

This claim is further verified when inspecting the XRF measurements of experiments conducted in RG-10-F conditions. The results in Table 25 show a steady grade of Fe and Ca with NF240, which is indicative of an unselective recovery of both sulfidic and non-sulfidic species. However, in the presence of HPMC or its PS-mixture, the grade of Fe is high in the early froth fractions and decreases with longer flotation time, while the behavior of Ca was the exact opposite. This behavior represents a selective separation of Fe-containing minerals that cannot be a result of entrainment only.

Table 25. XRF-results of entrainment experiments (Nuorivaara and Serna, 2020c)

Flotation time	NF240		HPMC 22k		PS-mix 22k	
	Fe	Ca	Fe	Ca	Fe	Ca
0-3 min	30.99	2.23	33.77	0.36	34.02	0.30
3-6 min	29.31	3.19	32.28	1.60	33.33	1.08
6-10 min	30.41	3.05	-	-	32.21	2.11
10-14 min	30.09	3.20	-	-	32.49	2.40
14-20 min	30.57	2.92	-	-	32.04	2.90
20-30 min	30.49	3.07	-	-	29.68	3.57
Tailings	33.21	0.57	31.84	0.75	31.70	0.66

Although entrainment is not investigated in more detail, the presented results imply that the high levels of mass pull obtained in the presence of HPMC and the PS-mixture were due to true flotation, which was facilitated by the bubble properties and froth stability provided by HPMC. This seems viable since reportedly some frother mixtures have been able to reduce the degree of entrainment while increasing froth stability (McFadzean et al., 2016). Admittedly, it is important to note that this inspection regarding entrainment is not comprehensive enough to claim conclusive results about the degree of entrainment in all operating conditions with the studied frothers.

When the experiments are observed from the grade and recovery point of view, the results in Figure 28 demonstrate the superior performance of the PS-mixtures that was based on a combination of higher recovery and acceptable grade. Thus, the PS-mixtures present the capability of outperforming commercial frothers even with a material that is known to be notoriously difficult to float.

The robustness of PS-mixtures observed in previous sections seems to be present also in flotation of tailings. Considering that the maximum grade obtained in the presence of the PS-mixture was 0.7, it would be possible to redirect a product of this quality into a scavenging bank in order to recover as much Cu as possible.

In summary:

- I. The observed mass pull was significantly higher in the presence of HPMC and its PS-mixtures compared to pure NF240.
- II. Based on a brief entrainment assessment, the observed high mass pull was not solely due to entrainment and thus a significant degree of true flotation occurred.

- III. Higher recoveries and faster flotation kinetics in the presence of HPMC and its PS-mixtures were connected to self-stabilizing properties identified in two-phase studies.

Figure 28. Cu grade-recovery curves and Separation Efficiency (SE) for flotation with re-ground samples using NF240 (NF-RG-F-5, NF-RG-F-10), HPMC (HP-RG-F-5, HP-RG-F-10) and HPMC-NF240 mixture (Mix-RG-F-5, Mix-RG-F-10) at pH = 5.5 (hollow) and pH = 10 (full). All data points follow the same tendency of time fractions as exemplified for Mix-RG-F-10 (the dotted lines are visual references representing SE threshold values) (Nuorivaara and Serna, 2020c)

5. Conclusions

This thesis represents the first ever thorough compilation of a research project studying the use of polymer-surfactant mixtures as flotation frothers. The thesis comprises of various experimental campaigns that studied both interfacial properties and flotation performance in the presence HPMC and its PS-mixtures using typical commercial frothers as benchmark. The results highlight unique bubble formation and froth stabilization properties observed in the presence of PS-mixtures.

In the detailed campaign studying interfacial properties, a synergistic adsorption of the PS-mixture was observed during DST measurements, which further decreased the initial γ compared to its corresponding pure components. The faster initial adsorption of γ was identified to occur due to the synergistic acceleration in diffusion of the PS-mixture in contrast to the single species systems, a phenomenon that has not been reported before. It was further noticed that the acceleration in diffusion rate was higher in PS-mixtures with a higher proportion of HPMC.

A spontaneous creation of a bi-modal bubble size distribution was observed in the presence of pure HPMC even in concentrations that exceeded its CCC. This phenomenon was connected to the presence of an induction time in the dynamic adsorption of HPMC and an increased coalescence prevention provided by steric repulsion of the polymer. When mixed with NF240, the synergistic adsorption manifested as a combination of smaller initial bubbles while maintaining their size via steric hinderance provided by the polymeric species of the mixture. The most efficient decrease in bubble sizes was observed when the concentration of HPMC was kept constant and the amount of NF240 was increased.

The presence of the PS-mixtures contributed towards better foamability and foam stability compared to their commercial frother counterparts. The effect was further promoted with an increasing concentration of HPMC in the mixture. However, it is important to note that too stable froth is considered detrimental for flotation and thus it is necessary to carefully choose a suitable formulation for such PS-mixtures to enable effective and selective flotation.

The observed synergistic adsorption and its consequences on bubble properties reflected clear improvements in laboratory bench-scale flotation experiments within the conditions studied in thesis. Indeed, in all flotation conditions, the PS-mixtures consistently outperformed the commercial frothers used as benchmarks. The most evident advantages were identified as better

recovery, higher maximum SE and faster flotation kinetics. Furthermore, within the studied conditions, the PS-mixtures displayed a unique tolerance towards changes in operational conditions that hindered the hydrophobicity of the targeted minerals, thus demonstrating a remarkable robustness towards significant changes in the operating conditions.

This special combination of properties could enable numerous benefits in industrial flotation processes and because of that, the results presented in this thesis have been used as the basis of a patent application (WO2019155116). The laboratory-scale results presented hereby suggest the possibility to increase the throughput of mineral concentrators by simply modifying the chemical system utilized and without extensive additional capital expenses. Furthermore, the capability of reducing xanthate consumption without major decline in flotation performance could be a vital benefit for mines in the future, as environmental permits are getting increasingly strict regarding hazardous chemicals. Finally, the findings of this thesis indicate the possibility of utilizing novel circuit design, cell design or operational conditions that have previously been regarded as impractical due to froth instability (e.g., flotation of tailings), but that may become a significant source of valuable materials in the not-so-distant future.

While it is reasonable to expect that the studied PS-mixtures can be applied successfully in various conditions and with different types of ores, it is important to note that the presented results represent a limited set of operating conditions. Thus, the proposed improvements in performance and robustness can only be considered as indicative of the behavior of PS-mixtures for these specific minerals and conditions. Consequently, performance in other systems needs to be confirmed with further experiments before these properties can be conclusively claimed as more universal traits of the PS-mixtures.

6. Recommendations for future investigations

While the results presented in this thesis show great potential for partly substituting current frothers with sustainable polymers, there are two specific aspects of research that the author would like to highlight as the most important features to study in the future.

While the synergistic adsorption behavior of the studied PS-mixtures was successfully identified, there are still various fundamental aspects that remain unknown. First of all, only two different types of HPMC molecules were studied in this thesis and, as discussed in the Introduction, it is possible to craft an HPMC molecule with distinct properties in terms of MS, DS and DP. Therefore, it is theoretically possible to tailor the structure of the applied polymer to perfectly match flotation purposes. Such detailed fundamental study would be of great interest. Furthermore, the results presented in this thesis cannot be used to comment on the possible interaction between HPMC and mineral surfaces, such as adsorption and the consequent changes in hydrophobicity. In order to have a more comprehensive understanding of PS-mixtures interaction with mineral surfaces, further characterization is necessary. One interesting possibility could be contact angle measurements complimented with contact timer analysis as presented by Hartmann and Serna (2020). According to Schulze-Zachau and Braunschweig (2017), the ratio between the polymer and the surfactant can have a significant impact on the surface properties provided by the PS-mixture. Considering that the scope of this thesis only allowed the study of a limited number of HPMC-to-surfactant ratios, a thorough characterization over a wider range of PS-mixture compositions would be beneficial. The importance of different unique PS-mixtures cannot be overlooked either. It is possible that the mixtures studied in this thesis represent only a small portion of possible PS-mixtures that can be applied successfully in the flotation process.

In addition to the fundamental aspects highlighted above, the author proposes further flotation studies to be conducted with the proposed frother formulations presented in this thesis. Since there are only two different valuable minerals targeted in this manuscript (chalcopyrite and sphalerite), experiments conducted with different minerals are proposed as well. In particular, flotation of oxide minerals species may be of interest, since the results of this thesis imply that the proposed formulations perform well in flotation of sulfidic minerals.

Finally, perhaps the most important feature to study, in terms of the formulations presented in this thesis, is scale up experiments along with a complete cost analysis of such campaign. It is generally accepted within the industry that scaling up from laboratory scale into industrial scale is not a trivial task and therefore the necessary steps towards this objective are highly recommended by the author.

References

- Ahmed, N., Jameson, G.J., 1989. Flotation kinetics. *Miner. Process. Ext. Met. Rev.* 5, 77-99. <https://doi.org/10.1080/08827508908952645>
- Angus-Smyth, A., Campbell, R.A., Bain, C.D. 2012. Dynamic adsorption of weakly interacting polymer/surfactant mixtures at the air/water interface, *Langmuir* 28 (34), 12479–12492. <https://doi.org/10.1021/la301297s>
- Angus-Smyth, A., Bain, C.D., Varga, I., Campbell, R.A. 2013. Effects of bulk aggregation on PEI–SDS monolayers at the dynamic air–liquid interface: depletion due to precipitation versus enrichment by a convection/spreading mechanism, *Soft Matter* 9, 6103. <https://doi.org/10.1039/c3sm50636c>
- Babak, V.G., Auzely, R., Rinaudo, M. 2007. Effect of electrolyte concentration on the dynamic surface tension and dilational viscoelasticity of adsorption layers of chitocan and dodecyl chitosan, *J. Phys. Chem. B* 111, 9519–9529. <https://doi.org/10.1021/jp0718653>
- Bain, C.D., Claesson, P.M., Langevin, D., Meszaros, R., Nylander, T., Stubenrauch, C., Titmuss, S., von Klitzing, R. 2010. Complexes of surfactants with oppositely charged polymers at surfaces and in bulk. *Adv. Colloid Interface Sci.* 155 (1-2), 32-49. <https://doi.org/10.1016/j.cis.2010.01.007>
- Beyki, M.H., Bayat, M., Miri, S., Shemirani, F., Alijani, H. 2014. Synthesis, characterization and silver adsorption property of magnetic cellulose xanthate from acidic solution: prepared by one step and biogenic approach, *Ind. Eng. Chem. Res.* 53, 14904–14912. <https://doi.org/10.1021/ie501989q>
- Bournival, G., Ata, S., Wanless, E.J. 2015. The roles of particles in multiphase processes: particles on bubble surfaces, *Adv. Colloid Interface Sci.* 225, 114–133. <https://doi.org/10.1016/j.cis.2015.08.008>
- Brackman, J., 1990. The Interaction between Water-Soluble Polymers and Surfactant Aggregates. Ph.D. thesis. University of Groningen, The Netherlands.
- Bulatovic, S.M., 2007. Handbook of Flotation Reagents: Chemistry, Theory and Practice, first ed. Elsevier Science & Technology Books, Oxford, United Kingdom, p. 458.
- Bureiko, A., Trybala, A., Kovalchuk, N., Starov, V., 2015. Current applications of foams formed from mixed surfactant-polymer solutions. *Adv. Colloid Interface Sci.* 222, 670-677. <https://doi.org/10.1016/j.cis.2014.10.001>
- Camino, N.A., Pérez, O.E., Carrera Sanchez, C., Rodríguez Patino, J.M., Pilosof, A.M.R. 2009. Hydroxypropylmethylcellulose surface activity at equilibrium and adsorption dynamics at the air-water and oil-water interfaces, *Food Hydrocoll.* 23, 2359–2368. <https://doi.org/10.1016/j.foodhyd.2009.06.013>
- Campbell, R.A., Ash, P.A., Bain, C.D. 2007. Dynamics of adsorption of an oppositely charged polymer–surfactant mixture at the air–water interface:

- poly(dimethyldiallylammonium chloride) and sodium dodecyl sulfate, *Langmuir* 23 (6), 3242–3253. <https://doi.org/10.1021/la0632171>
- Celic, I.B., 2015. Mineralogical interpretation of the collector dosage change on the sphalerite flotation performance. *Int. J. Miner. Process.* 135, 11–19. <https://doi.org/10.1016/j.minpro.2014.12.003>
- Chandra, A.P., Gerson, A.R. 2009. A review of the fundamental studies of the copper activation mechanisms for selective flotation of the sulfide minerals, sphalerite and pyrite. *Adv. Colloid Interface Sci.* 145, 97–110. <https://doi.org/10.1016/j.cis.2008.09.001>
- Chesters, A.K. 1991. The modelling of coalescence properties in fluid-liquid dispersions: a review of current understanding. *Chem. Eng. Res. Des.* 69, 259–270.
- Cho, Y.S., Laskowski, J.S. 2002. Effect of flotation frothers on bubble size and foam stability, *Int. J. Miner. Process.* 64, 69–80. [https://doi.org/10.1016/S0301-7516\(01\)00064-3](https://doi.org/10.1016/S0301-7516(01)00064-3)
- Chu, P., Waters, K.E., Finch, J.A. 2017. Break-up in formation of small bubbles: an energy consideration. *Can. Metall. Q.* 56:1, 30–34. doi.org/10.1080/00084433.2016.1245255
- Coffey, D.G., Bell, D.A., Henderson, A. 2006. Cellulose and cellulose derivatives. In: Stephen, A.M., Philips, G.O., Williams, P.A. (Eds.), *Food Polysaccharides and Their Applications*, second ed. CRC Press, Boca Raton, 147–179.
- Derjaguin, B.V., Dukhin, S.S. 1961. Theory of flotation of small and medium-size particles. *Transaction of the Institution of Mining and Metallurgy*, 70, 221–246.
- Diaz, F., Yianatos, J. 2010. Residence time distribution in large industrial flotation cells. *Atoms of Peace*, 3 (1). doi.org/10.1504/AFP.2010.031015
- Dickinson, E., 2003. Hydrocolloids at interfaces and the influence on the properties of dispersed systems. *Food Hydrocoll.* 17 (1), 25–39. [https://doi.org/10.1016/S0268-005X\(01\)00120-5](https://doi.org/10.1016/S0268-005X(01)00120-5)
- Drzymala, J., Kowalczyk, P.B. 2018. Classification of flotation frothers, *Minerals* 8 (2). 53. <https://doi.org/10.3390/min8020053>
- Eastoe, J., Dalton, J.S. 2000. Dynamic surface tension and adsorption mechanisms of surfactants at the air–water interface, *Adv. Colloid Interface Sci.* 85 (2–3), 103–144. [https://doi.org/10.1016/S0001-8686\(99\)00017-2](https://doi.org/10.1016/S0001-8686(99)00017-2)
- Elmahdy, A.M., Finch, J.A. 2013. Effect of frother blends on hydrodynamic properties, *Int. J. Miner. Process.* 123, 60–63. <https://doi.org/10.1016/j.minpro.2013.04.019>
- Farrokhpay, S. 2011. The significance of froth stability in mineral flotation – a review, *Adv. Colloid Interface Sci.* 166, 1–7. <https://doi.org/10.1016/j.cis.2011.03.001>
- Farrokhpay, S., Zanin, M. 2012. An investigation into the effect of water quality on froth stability, *Adv. Powder Technol.* 23 (4). 493–497. <https://doi.org/10.1016/j.appt.2012.04.012>
- Farrokhpay, S., Filippova, I., Filippov, L., Picarra, A., Rulyov, N. 2020. Flotation of fine particles in the presence of combined microbubbles and conventional bubbles. *Miner. Eng.* 155, 106439. doi.org/10.1016/j.mineng.2020.106439
- Finch, J.A., Nasset, J.E., Acuña, C., 2008. Role of frother on bubble production and behavior in flotation. *Miner. Eng.* 21, 949–957. <https://doi.org/10.1016/j.mineng.2008.04.006>
- Finch, J.A., Zhang, W. 2014. Frother function-structure relationship: dependence of CCC95 on HLB and the H-ratio, *Miner. Eng.* 61, 1–8, <https://doi.org/10.1016/j.mineng.2014.02.006>

- Gilles, G., Kappl, M., Butt, H.-J. 2005. Direct measurements of particle-bubble interactions, *Adv. Colloid Interface Sci.* 114-115, 165–172. <https://doi.org/10.1016/j.cis.2004.08.003>
- Goddard, E.D., Ananthapadmanabhan, K.P., 1993. Interactions of Surfactants with Polymers and Proteins. CRC Press, Boca Raton, pp. 123-277.
- Goryachev, B.E., Kyaw, Z.Y., Nikolaev, A.A., Polyakova, Y.N., 2015. Peculiarities of sphalerite flotation by butyl potassium xanthate and sodium dithiophosphate in lime medium. *Tsvetnye Met.* 11. <https://doi.org/10.17580/tsm.2015.11.02>
- Grau, R.A. 2006. An investigation of the effect of physical and chemical variables on bubble generation and coalescence in laboratory scale flotation cells. Ph.D. Dissertation, Helsinki University of Technology. Department of Materials Science and Engineering.
- Guzmán, E., Llamas, S., Maestro, A., Fernández-Peña, L., Akanno, A., Miller, R., Ortega, F., Rubioa, R.G. 2016. Polymer-surfactant systems in bulk and at fluid interfaces. *Adv. Colloid Interface Sci.* 233, 38-64. <https://doi.org/10.1016/j.cis.2015.11.001>
- Göktepe, F. 2002. Effect of pH on Pulp Potential and Sulphide Mineral Flotation. *Turkish J. Eng. Env. Sci.* 26, 309 – 318.
- Hamilton, D., Natarajan, R., Nirdosh, I. 2009. Sphalerite flotation using an arylhydroxamic acid collector: improving grade while using a reduced amount of copper sulfate for activation, *Ind. Eng. Chem. Res.* 48 (12), 5584–5589. <https://doi.org/10.1021/ie900305r>
- Harris, P.J. (1982). Frothing phenomena and frothers. In: *Principle of Flotation*; Ed.: King, R.P., *South African Institute of Mining and Metallurgy*, Johannesburg, South Africa, pp. 237-250.
- Hartmann, R., Serna-Guerrero, R. 2020. Towards a quantitative analysis of the wettability of microparticles using an automated contact timer apparatus, *Miner. Eng.* 149, 106240. <https://doi.org/10.1016/j.mineng.2020.106240>
- Hristov, J. 2016. A unified nonlinear fractional equation of the diffusion-controlled surfactant adsorption: reappraisal and new solution of the ward–tordai problem, *J. King. Saud. Univ. Sci.* 28, 7–13. <https://doi.org/10.1016/j.jksus.2015.03.008>
- Huang, Z., Cheng, C., Liu, Z., Zeng, H., Feng, B., Zhong, H., Luo, W., Hu, Y., Guo, Z., He, G., Fu, W. 2019. Utilization of a new Gemini surfactant as the collector for the reverse froth flotation of phosphate ore in sustainable production of phosphate fertilizer. *J. Clean. Prod.* 221, 108-112. <https://doi.org/10.1016/j.jclepro.2019.02.251>
- Jávor, Z., Schreithofer, N., Heiskanen, K. 2010. Fast adsorption phenomena at air/liquid interfaces. In: *XXV International Mineral Processing Congress*, Brisbane, Australia, pp. 2015-2023.
- Jávor, Z., 2014. Frother Controlled Interfacial Phenomena in Dynamic Systems - a Holistic Approach. Ph.D. Dissertation. Aalto University. Department of Materials Science and Engineering.
- Jávor, Z., Schreithofer, N., Heiskanen, K. 2014 Validity of critical coalescence concentration in dynamic conditions, *Int. J. Miner. Process.* 127, 16–22. <https://doi.org/10.1016/j.minpro.2013.12.005>
- Jávor, Z., Schreithofer, N., Heiskanen, K. 2015. Micro- and nano-scale phenomena effect on bubble size in mechanical flotation cell. *Miner. Eng.* 70, 109-118. <https://doi.org/10.1016/j.mineng.2014.09.010>
- Kanokkarn, P., Shiina, T., Santikunaporn, M., Chavadej, S. 2017. Equilibrium and dynamic surface tension in relation to diffusivity and foaming properties: effects of surfactant type and structure, *Colloids Surf. A Physicochem. Eng. Asp.* 524, 135–142, <https://doi.org/10.1016/j.colsurfa.2017.04.043>

- Katona, J.M., Sovilj, V.J., Petrović, L.B. 2008. Rheological investigation on dynamic and structure of separated phases in polymer mixture–ionic surfactant ternary system, *Carbohydr.* 74 (2), 193–200. <https://doi.org/10.1016/j.carbpol.2008.02.002>
- Kinnunen, P.H., Kaksonen, A.H., 2019. Towards circular economy in mining: Opportunities and bottlenecks for tailings valorization. *J. Clean. Prod.* 228, 153–160. <https://doi.org/10.1016/j.jclepro.2019.04.171>
- Kor, M., Korczyk, P.M., Addai-Mensah, J., Krasowska, M., Beattie, D.A. 2014. Carboxymethylcellulose adsorption on molybdenite: the effect of electrolyte composition on adsorption, bubble–surface collisions, and flotation, *Langmuir* 30 (40), 11975–11984. <https://doi.org/10.1021/la503248e>
- Laitinen, O., Kemppainen, K., Ämmälä, A., Sirviö, J.A., Liimatainen, H., Niinimäki, J. 2014. Use of chemically modified nanocelluloses in flotation of hematite and quartz, *Ind. Eng. Chem. Res.* 53, 20092–20098. <https://doi.org/10.1021/ie503415t>
- Laitinen, O., Hartmann, R., Sirviö, J.A., Liimatainen, H., Rudolph, M., Ämmälä, A., Illikainen, M. 2016. Alkyl aminated nanocelluloses in selective flotation of aluminium oxide and quartz, *Chem. Eng. Sci.* 1444, 260–266. <https://doi.org/10.1016/j.ces.2016.01.052>
- Lamberti, J.A.G. 2019. Cellulose based surfactants as frothers on sphalerite flotation. Master's thesis. Aalto University. Department of Chemical and Metallurgical Engineering. Available at <http://urn.fi/URN:NBN:fi:aalto-201902031551>
- Laskowski, J.A. 1998. Frothers and Frothing. In: Laskowski, J.A and Woodburn, E.T. (EDS.), *Frothing in Flotation II: Recent advances in coal processing*, vol 2. CRC Press, 1–49.
- Majewicz, T.G., Podlas, T.J. 2000. Cellulose Ethers. In: Kirk, R.E., Othmer, D.F. *Kirk-Othmer encyclopedia of chemical technology*. John Wiley & Sons, Inc. doi.org/10.1002/0471238961
- Marrucci, G. 1969. A theory of coalescence. *Chem. Eng. Sci.* 24, 975–985. [https://doi.org/10.1016/0009-2509\(69\)87006-5](https://doi.org/10.1016/0009-2509(69)87006-5)
- McFadzean, B., Marzova, T., Wiese, J. 2016. Flotation frother mixtures: decoupling the subprocesses of froth stability, froth recovery and entrainment, *Miner. Eng.* 85, 72–79. <https://doi.org/10.1016/j.mineng.2015.10.014>
- Mudd, G.M., Jowitt, S.M. 2018. Growing global copper resources, reserves and production: discovery is not the only control on supply. *Econ. Geol.* 113 (6), 1235–1267. doi.org/10.5382/econgeo.2018.4590
- Nagaraj, D.R., Farinato, R.S., 2016. Evolution of flotation chemistry and chemicals: a century of innovations and the lingering challenges. *Miner. Eng.* 96–97, 2–14. <https://doi.org/10.1016/j.mineng.2016.06.019>
- Nahringbauer, I., 1995. Dynamic surface tension of aqueous polymer solutions, I: ethyl (hydroxyethyl)cellulose (BERMOCOLL cst-103), *J. Colloid Interface Sci.* 176, 318–328. <https://doi.org/10.1006/jcis.1995.9961>
- Neethling, S.J., Cilliers, J.J. 2002. The entrainment of gangue into a flotation froth, *Int. J. Miner. Process.* 64 (2–3), 123–134. [https://doi.org/10.1016/S0301-7516\(01\)00067-9](https://doi.org/10.1016/S0301-7516(01)00067-9)
- Neethling, S.J., Brito-Parada, P.R., Hadler, K., Cilliers, J.J. 2019. The transition from first to zero order flotation kinetics and its implications for the efficiency of large flotation cells. *Miner. Eng.* 132, 149–161. <https://doi.org/10.1016/j.mineng.2018.11.039>

- Norde, W., MacRitchie, F., Nowicka, G., Lyklema, J. 1986. Protein adsorption at solid–liquid interfaces: Reversibility and conformation aspects. *J. Colloid. Interface. Sci.* , 112(2), 447–456. [https://doi.org/10.1016/0021-9797\(86\)90113-X](https://doi.org/10.1016/0021-9797(86)90113-X)
- Noskov, B.A., Grigoriev, D.O., Lin, S.-Y., Loglio, G., Miller, R. 2007. Dynamic surface properties of polyelectrolyte/surfactant adsorption films at the air/water interface: poly(diallyldimethylammonium chloride) and sodium dodecylsulfate, *Langmuir* 23, 9641–9651, <https://doi.org/10.1021/la700631t>.
- Nuorivaara, T., Serna-Guerrero, R. A study on the properties of foams produced with cellulose-based molecules with an outlook on flotation. Quebec, Canada, Proceedings of XXVIII International Mineral Processing Congress (IMPC2016), 11-15 2016 September.
- Nuorivaara, T., Björkqvist, A., Bacher, J., Serna-Guerrero, R. 2019. Environmental remediation of sulfidic tailings with froth flotation: reducing the consumption of additional resources by optimization of conditioning parameters and water recycling, *J. Environ. Manage.* 236, 125–133. doi.org/10.1016/j.jenvman.2019.01.107
- Nuorivaara, T., Serna-Guerrero, R. 2019. Flotation of a porphyry copper ore with cellulose-surfactant mixtures as frother agents, Proceedings of Copper 2019, Vancouver, Canada, August 18-21, 2019.
- Nuorivaara, T., Serna-Guerrero, R. 2020a. Unlocking the potential of sustainable chemicals in mineral processing: Improving sphalerite flotation using amphiphilic cellulose and frother mixtures. *J. Clean. Prod.* 261, 121143. <https://doi.org/10.1016/j.jclepro.2020.121143>
- Nuorivaara, T., Serna-Guerrero, R. 2020b. Amphiphilic cellulose and surfactant mixtures as green frothers in mineral flotation. 1. Characterization of interfacial and foam stabilization properties. *Colloids and Surfaces A*, 604 (125297), doi.org/10.1016/j.colsurfa.2020.125297
- Nuorivaara, T., Serna-Guerrero, R. 2020c. Amphiphilic cellulose and surfactant mixtures as green frothers in mineral flotation. 2. Flotation of chalcopyrite and Cu-containing tailings. *Colloids and Surfaces A*, 603 (125298), doi.org/10.1016/j.colsurfa.2020.125298
- Paraskevopoulou, A., Kiosseglou, V. 2013. Interfacial properties of biopolymers, emulsions and emulsifiers, *Handbook of Biopolymer-Based Materials: From Blends and Composites to Gels and Complex Networks*, Wiley-VHC.
- Pérez, O.E., Carrera-Sánchez, C., Rodríguez-Patino, J.M., Pilosof, A.M.R., 2006. Thermodynamic and dynamic characteristics of hydroxypropylmethylcellulose adsorbed films at the air-water interface. *Biomacromolecules* 7, 388-393. <https://doi.org/10.1021/bm050757o>
- Pérez, O.E., Carrera-Sánchez, C., Rodríguez-Patino, J.M., Pilosof, A.M.R. 2007. Adsorption dynamics and surface activity at equilibrium of whey proteins and hydroxypropyl-methyl-cellulose mixtures at the air-water interface. *Food Hydrocoll.* 21, 794-803. <https://doi.org/10.1016/j.foodhyd.2006.11.013>
- Pérez, O.E., Carrera-Sánchez, C., Pilosof, A.M.R., Rodríguez-Patino, J.M. 2008. Dynamics of adsorption of hydroxypropyl methylcellulose at the air-water interface, *Food Hydrocoll.* 22, 387–402. <https://doi.org/10.1016/j.foodhyd.2006.12.005>
- Persson, B., Nilsson, S., Sundelöf, L-O. 1996. On the characterization principles of some technically important water-soluble nonionic cellulose derivatives. Part II: Surface tension and interaction with a surfactant. *Carbohydr. Polym.* 29, 119-127. [doi.org/10.1016/0144-8617\(96\)00010-0](https://doi.org/10.1016/0144-8617(96)00010-0)

- Petkova, R., Teholakova, S., Denkov, N.D. 2012. Foaming and foam stability for mixed polymer-surfactant solutions: effect of surfactant type and polymer charge. *Langmuir* 28, 4996-5009. <https://doi.org/10.1021/la3003096>
- Peçanha, R.E., da Fonseca de Albuquerque, M.D., Antoun Simão, R., de Salles Leal Filho, L., de Mello Monte, M.B. 2019. Interaction forces between colloidal starch and quartz and hematite particles in mineral flotation. *Colloids Surf., A* 562, 79-85. <https://doi.org/10.1016/j.colsurfa.2018.11.026>
- Quinn, J.J., Finch, J.A. 2012. On the origin of bi-modal size distributions in the absence of frother, *Miner. Eng.* (36-38), 237-241. <https://doi.org/10.1016/j.mineng.2012.04.001>
- Quinn, J.J., Sovechles, J.M., Finch, J.A., Waters, K.E. 2014. Critical coalescence concentration of inorganic salt solutions, *Miner. Eng.* 58, 1-6, <https://doi.org/10.1016/j.mineng.2013.12.021>
- Rinne, T.J. 2018. The utilization of hydroxypropyl methylcellulose as a flotation frother for chalcopyrite-containing ores. Master's thesis. Aalto University. Department of Chemical and Metallurgical Engineering. Available at <http://urn.fi/URN:NBN:fi:aalto-201811135734>
- Rötzer, N., Schmidt, M. 2018. Decreasing metal ore grades – is the fear of resource depletion justified? *Resources*, 7(4), 88. <https://doi.org/10.3390/resources7040088>
- Sannino, A., Demitri, C., Madaghiele, M., 2009. Biodegradable cellulose-based hydrogels: design and applications. *Materials* 2, 353-373. <https://doi.org/10.3390/ma2020353>
- Savassi, O.N., Alexander, D. J., Johnson, N. W., Franzidis, J. P., Manlapig, E.V. 1997. Measurement of Froth Recovery of Attached Particles in Industrial Flotation Cells. Madang, Papua New Guinea, Proceedings of Sixth Mill Operators' Concerence, 6-8 October, 1997.
- Schreithofer, N., Weise, J., McFazdean, B., Harris, P., Heiskanen, K., O'Connor, C. 2011. Frother depressant interactions in two and three phase systems. *Int. J. Mineral Process.* 100, 33-40. <https://doi.org/10.1016/j.minpro.2011.04.008>
- Schulze, H.J., Stöckelhuber, K.W., Wenger, A. 2001. The influence of acting forces on the rupture mechanism of wetting films – nucleation or capillary waves, *Colloids Surf. A* 192, 61-72. [https://doi.org/10.1016/S0927-7757\(01\)00717-8](https://doi.org/10.1016/S0927-7757(01)00717-8)
- Schulze-Zachau, F., Braunschweig, B., 2017. Structure of polystyrenesulfonate/surfactant mixtures at air-water interfaces and their role as building blocks for macroscopic foam. *Langmuir* 33, 3499-3508. <https://doi.org/10.1021/acs.langmuir.7b00400>
- Sheni, N., Corin, K., Wiese, J. 2018. Considering the effect of pulp chemistry during flotation on froth stability, *Miner. Eng.* 116, 15-23. <https://doi.org/10.1016/j.mineng.2017.11.002>
- Slastanova, A., Campbell, R.A., Snow, T., Mould, E., Li, P., Welbourn, R.J.L., Chen, M., Robles, E., Briscoe, W.H. 2020. Synergy, competition and the “hanging” polymer layer: Interactions between a neutral amphiphilic ‘tardigrade’ comb co-polymer with an anionic surfactant at the air-water interface, *J. Colloid Interface Sci.* 561, 181-194, <https://doi.org/10.1016/j.jcis.2019.11.017>
- Stahel, W.R., 2016. The circular economy. *Nature* 435-438. <https://doi.org/10.1038/531435a>
- Tan, S.N., Yang, Y., Horn, R.G., 2010. Thinning of a vertical free-draining aqueous film incorporating colloidal particles. *Langmuir* 26, 63-73. <https://doi.org/10.1021/la9021118>

- Tan, Y.H., Finch, J.A. 2016. Frother structure-property relationship: effect of hydroxyl position in alcohols on bubble rise velocity, *Miner. Eng.* 92. 1–8, <https://doi.org/10.1016/j.mineng.2016.02.003>
- Tan, Y.H., Finch, J.A. 2018 a. Frother structure-property relationship: effect of polyethylene glycols on bubble rise velocity, *Miner. Eng.* 116. 56–61. <https://doi.org/10.1016/j.mineng.2017.09.014>
- Tan, Y.H., Finch, J.A. 2018 b. Frothers and gas dispersion: A review of the structure-property-function relationship. *Physicochem. Probl. Miner. Process.*, 54(1), 40–53. <https://doi.org/10.5277/ppmp1814>
- Tao, D., 2005. Role of bubble size in flotation of coarse and fine particles - a review. *Separ. Sci. Technol.* 39 (4), 741–760. <https://doi.org/10.1081/SS-120028444>
- Tsatouhas, G., Grano, S.R., Vera, M. 2006. Case studies on the performance and characterization of the froth phase in industrial flotation circuits, *Miner. Eng.* 19, 774–783. <https://doi.org/10.1016/j.mineng.2005.09.033>
- USGS. Minerals Yearbook: Volume I. – Mineral commodity summaries. 2020. Available online: <https://pubs.usgs.gov/periodicals/mcs2020/mcs2020-copper.pdf> (Accessed on 7th of October 2020)
- van Schalkwyk, R.F., Reuter, M.A., Gutzmer, J., Stelter, M., 2018. Challenges of digitalizing the circular economy: assessment of the state-of-the-art of metallurgical carrier metal platform for lead and its associated technology elements. *J. Clean. Prod.* 186, 585–601. <https://doi.org/10.1016/j.jclepro.2018.03.111>
- Velázquez Martínez, O., Van Den Boogaart, K.G., Lundström, M., Santasalo-Aarnio, A., Reuter, M., Serna-Guerrero, R., 2019. Statistical entropy analysis as tool for circular economy: proof of concept by optimizing a lithium-ion battery waste sieving system. *J. Clean. Prod.* 212, 1568–1579. <https://doi.org/10.1016/j.jclepro.2018.12.137>
- Wege, H.A., Kim, S., Paunov, V.N., Zhong, Q., Velev, O.D. 2008. Long-term stabilization of foams and emulsions with in-situ formed microparticles from hydrophobic cellulose, *Langmuir* 24, 9245. <https://doi.org/10.1021/la801634j>
- Wei, B., Li, H., Li, Q., Lu, L., Li, Y., Pu, W., Wen, Y., 2018. Investigation of synergism between surface-grafted nano-cellulose and surfactants in stabilized foam injection process. *Fuel* 211, 223–232. <https://doi.org/10.1016/j.fuel.2017.09.054>
- Wills, B.A., Finch, J.A., 2015. *Wills' Mineral Processing Technology: an Introduction to the Practical Aspects of Ore Treatment and Mineral Recovery*. Butterworth-Heinemann.
- Wüstenberg, T. 2015. *Cellulose and Cellulose Derivatives in the Food Industry*. Wiley-VHC.
- WO2019155116. 2019. Cellulose-based derivatives as chemical aids for mineral enrichment in froth flotation. Laine IP Oy, Helsinki, Finland. (Nuorivaara, T., Serna-Guerrero R.) PCT/FI2019/050023. 13.01.2019. Publ. 15.08.2019. 37 p.
- Wollenweber, C., Makievski, A.V., Miller, R., Daniels, R. 2000. Adsorption of hydroxypropyl methylcellulose at the liquid/liquid interface and the effect on emulsion stability, *Colloids Surf. A Physicochem. Eng. Asp.* 172, 91–101. [https://doi.org/10.1016/S0927-7757\(00\)00569-0](https://doi.org/10.1016/S0927-7757(00)00569-0)
- Yang, Z., Yuan, B., Li, H., Yang, Y., Yang, H., Li, A., Cheng, R. 2014. Amphoteric starch-based flocculants can flocculate different contaminants with even opposite surface charges from water through molecular structure control, *Colloids Surf. A Physicochem. Eng. Asp.* 455, 28–35. <https://doi.org/10.1016/j.colsurfa.2014.04.043>

- Yang, B., Yin, W., Zhu, Z., Wang, D., Han, H., Fu, Y., Sun, H., Chu, F., Yao, J. 2019. A new model for the degree of entrainment in froth flotation based on mineral particle characteristics, Powder Technol. 354, 358–368. <https://doi.org/10.1016/j.powtec.2019.06.017>
- Xhanari, K., Syverud, K., Stenius, P. 2011. Emulsions stabilized by microfibrillated cellulose: the effect of hydrophobization, concentration and o/w ratio, J. Dispers. Sci. Technol. 32, 447. <https://doi.org/10.1080/01932691003658942>

ISBN 978-952-64-0303-8 (printed)

ISBN 978-952-64-0304-5 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University
School of Chemical Engineering
Department of Chemical and Metallurgical Engineering
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**