Imaging and digital design for medical applications of additive manufacturing

Eero Huutilainen

Imaging and digital design for medical applications of additive manufacturing

Eero Huutilainen

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Science, at a public examination held at the lecture hall F239a of the school on 18 January 2019 at 12:00.

Aalto University
School of Science
Department of Neuroscience and Biomedical Engineering

Supervising professors

Professor Ari Koskelainen, School of Science, Aalto University, Finland

Professor Jouni Partanen, School of Engineering, Aalto University, Finland

Preliminary examiners

Professor Miika Nieminen, University of Oulu, Finland

Professor Igor Drstvenšek, University of Maribor, Slovenia

Opponent

Professor Paulo Bartolo, University of Manchester, United Kingdom

Aalto University publication series

DOCTORAL DISSERTATIONS 3/2019

© 2019 Eero Huutilainen

ISBN 978-952-60-8363-6 (printed)

ISBN 978-952-60-8364-3 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-60-8364-3>

Unigrafia Oy

Helsinki 2019

Finland

Author

Eero Huottilainen

Name of the doctoral dissertation

Imaging and digital design for medical applications of additive manufacturing

Publisher School of Science**Unit** Department of Neuroscience and Biomedical Engineering**Series** Aalto University publication series DOCTORAL DISSERTATIONS 3/2019**Field of research** Biomedical engineering**Manuscript submitted** 28 August 2018**Date of the defence** 18 January 2019**Permission to publish granted (date)** 1 November 2018**Language** English☐ **Monograph**☒ **Article dissertation**☐ **Essay dissertation****Abstract**

Since their inception in the late 80s, additive manufacturing (AM) technologies have contributed largely in the paradigm change of production engineering. A focal area where these processes offer exceptional contemporary applications and future potential is the medical milieu; low production volumes, high degree of customization, and complexity of required shapes are strong drivers leading towards digital fabrication.

Medical applications of additive manufacturing are classified to span five distinct categories: medical models, external prostheses and guides, surgical tools, inert implants, and biomanufacturing. The primary aim for this dissertation is to develop the five-step process for medical applications of AM: medical imaging, digital design, fabrication, post-processing, and clinical application.

In the center of a successful clinical AM application lies the digital design phase. The results of this dissertation present optimization framework for medical imaging in order to ensure quality of source material for the designs. Subsequently, the design step is enhanced by developing and presenting practical and computational methods for design automation and conversion techniques into efficient clinical applications.

The research focusing on the critical steps of the process is complemented with a holistic view on the complete process. Apart from the technical solutions offered, the collaborative needs, and information and communication flows within the process are essential for successful medical application of additive manufacturing. Critical future research topics required in the research area include novel material and software development as well as more efficient utilization of existing technologies.

Keywords additive manufacturing, 3D printing, medical imaging**ISBN (printed)** 978-952-60-8363-6**ISBN (pdf)** 978-952-60-8364-3**ISSN (printed)** 1799-4934**ISSN (pdf)** 1799-4942**Location of publisher** Helsinki**Location of printing** Helsinki **Year** 2019**Pages** 104**urn** <http://urn.fi/URN:ISBN:978-952-60-8364-3>

Tekijä

Eero Huotilainen

Väitöskirjan nimi

Kuvantaminen ja digitaalinen suunnittelu ainetta lisäävän valmistuksen lääketieteellisiin sovelluksiin

Julkaisija Perustieteiden korkeakoulu**Yksikkö** Neurotieteen ja lääketieteellisen tekniikan laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 3/2019**Tutkimusala** Lääketieteellinen tekniikka**Käsikirjoituksen pvm** 28.08.2018**Väitöspäivä** 18.01.2019**Julkaisuluvan myöntämispäivä** 01.11.2018**Kieli** Englanti☐ **Monografia**☒ **Artikkeliväitöskirja**☐ **Esseeväitöskirja****Tiivistelmä**

Ainetta lisäävä valmistus (additive manufacturing, AM) on ollut noin kolmen vuosikymmenen ajan merkittävä tekijä valmistustekniikan paradigman muutoksessa. Lääketiede ja terveydenhoito ovat näille tekniikoille erityisen kiinnostava sovelluskohde; matalat tuotantovolyymit, korkea kustomoinnin aste, sekä vaadittujen rakenteiden kompleksisuus ovat tekijöitä, jotka ajavat kohti digitaalista tuotantoa.

Ainetta lisäävän valmistuksen lääketieteelliset sovellukset ovat järjestettävissä viiteen luokkaan: lääketieteelliset mallit, kehon ulkopuoliset proteesit ja ohjurit, kirurgiset työkalut, kehonsisäiset implantit, sekä biovalmistus. Tämän väitöstutkimuksen päätavoite on ainetta lisäävän valmistuksen lääketieteellisten sovellusten viisivaiheisen prosessin kehittäminen: lääketieteellinen kuvantaminen, digitaalinen suunnittelu, valmistus, jälkikäsittely, ja kliininen sovellus.

Onnistuneen kliinisen AM-sovelluksen toteuttamisessa kriittinen vaihe on digitaalinen suunnittelu. Tämän väitöstutkimuksen tulokset muodostavat rungon lääketieteellisen kuvantamisen optimoimiseen, jotta suunnittelussa tarvittava lähdemateriaalin laatu turvataan. Suunnitteluvaihetta tehostetaan kehittämällä käytännöllisiä ja laskennallisia menetelmiä suunnitteluautomaatioon ja konversioon kohti tehokasta, onnistunutta kliinistä applikaatiota.

Prosessin kriittisten vaiheiden tutkimusta täydennetään koko prosessin yleiskuvauksella. Tässä tutkimuksessa tuotettujen teknisten ratkaisujen ohella yhteistyö sekä informaatio- ja kommunikaatiovuot prosessin ja verkoston osien välillä ovat tärkeitä. Tulevaisuuden tutkimuskohteista tällä alueella tärkeimpiä ovat uusien materiaalien sekä ohjelmistojen kehitys, ja olemassaolevien tekniikoiden tehokkaampi hyödyntäminen.

Avainsanat ainetta lisäävä valmistus, 3D-tulostus, lääketieteellinen kuvantaminen**ISBN (painettu)** 978-952-60-8363-6**ISBN (pdf)** 978-952-60-8364-3**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Helsinki**Painopaikka** Helsinki**Vuosi** 2019**Sivumäärä** 104**urn** <http://urn.fi/URN:ISBN:978-952-60-8364-3>

Acknowledgements

I would like to express my gratitude to my supervising professor Ari Koskelainen, as well as the co-supervising and advising professor Jouni Partanen. As the doctoral project has attempted to converge various engineering, scientific and clinical disciplines, sailing has been occasionally rough in these uncharted waters – only with the invaluable direction from my supervisors during these years, I feel that the ship finally found its right trajectory. I am equally thankful to the preliminary examiners and the opponent, as my project is nearing the defense date.

In addition, I would like to thank for the support given by fellow researchers in our team; especially Jukka Tuomi, Mika Salmi, Roy Björkstrand, Iñigo Flores Ituarte, Sergei Chekurov, and Kirsi Kukko, as well as all the other colleagues and collaborators I have had pleasure to work with during my project. Special acknowledgements are directed also to Antti Mäkitie, Jan Lindahl, Jan Wolff, and other medical professionals who have helped me understand the vast, albeit extremely interesting, differences between engineering and clinical environments. Finally, I want to thank Heidi and my family for their continuing support along this journey.

Helsinki, 17 December 2018
Eero Huutilainen

Contents

1.	Introduction	9
1.1	The research gap	10
1.2	General aim	10
1.3	Specific aims	11
2.	Background	13
2.1	Additive manufacturing	13
2.1.1	Development phases of AM	13
2.1.2	Types of additive manufacturing processes	13
2.2	Medical applications of additive manufacturing	16
2.2.1	Medical models	16
2.2.2	Medical aids, supportive guides, splints, and prostheses	17
2.2.3	Surgical tools, instruments, and parts for medical devices	17
2.2.4	Inert implants	17
2.2.5	Biomanufacturing	18
2.3	Medical imaging and design for additive manufacturing	18
2.3.1	Medical imaging modalities for AM models	20
2.3.2	Image processing, reconstruction, and 3D design	20
2.4	Materials used in medical applications	22
3.	Materials and methods	23
3.1	Medical imaging (Publications I, II, IV)	23
3.2	3D design and modeling (Publications I-IV)	23
3.3	Additive manufacturing (Publications II-IV)	25
3.4	Post-processing operations (Publications II-IV)	26
3.5	Surface scanning and characterization (Publications II, III)	26
3.6	Cytotoxicity assessment (Publication III)	29
4.	Results	30
4.1	Imaging modalities and parameters for clinical applications of additive manufacturing	30
4.2	Reconstruction accuracies for medical models	33

4.3	Surface characterization and cytotoxicity of implants	36
4.4	Computer-assisted possibilities for complex surgeries.....	38
4.5	Online platform for collaboration and case dissemination	41
5.	Discussion	43
6.	Conclusions.....	46
	References	46
	Publications	54

List of Abbreviations

ACL	Anterior cruciate ligament
AM	Additive manufacturing
CAD	Computer aided design
CAM	Computer aided manufacturing
CBCT	Cone beam computed tomography
CNC	Computer numerical control
CT	Computed tomography
DICOM	Digital imaging and communications in medicine
DMLS	Direct metal laser sintering
EBM	Electron beam melting
FDM	Fused deposition modeling
HU	Hounsfield unit
MRI	Magnetic resonance imaging
MSCT	Multi-slice computed tomography
PBF	Powder bed fusion
PEEK	Polyether-ether-ketone
PET	Positron emission tomography
PMMA	Poly(methyl methacrylate)
PSI	Patient-specific implant
RM	Rapid manufacturing
RP	Rapid prototyping
RT	Rapid tooling
SEM	Scanning-electron microscopy
SLA	Stereolithography

SLM	Selective laser melting
SLS	Selective laser sintering
SPECT	Single-photon emission computed tomography
STL	File format, triangular mesh representation

List of Publications

This doctoral dissertation consists of a summary and of the following publications which are referred to in the text by their numerals:

I. Huotilainen E, Paloheimo M, Salmi M, Paloheimo KS, Björkstrand R, Tuomi J, Markkola A, Mäkitie AA. Imaging requirements for medical applications of additive manufacturing. *Acta Radiologica*, 2014, 55(1):78-85. doi: 10.1177/0284185113494198

II. Huotilainen E, Jaanimets R, Valášek J, Marcián P, Salmi M, Tuomi J, Mäkitie AA, Wolff J. Inaccuracies in additive manufactured medical skull models caused by the DICOM to STL conversion process. *Journal of Craniomaxillofacial Surgery*, 2014, 42(5):e259-65. doi: 10.1016/j.jcms.2013.10.001

III. Tuomi J, Björkstrand R, Pernu M, Salmi M, **Huotilainen E**, Wolff J, Vallittu P, Mäkitie AA. In vitro cytotoxicity and surface topography evaluation of additive manufacturing titanium implant materials. *Journal of Materials Science: Materials in Medicine*, 2017, 28:53. doi: 10.1007/s10856-017-5863-1

IV. Huotilainen E, Salmi M, Lindahl J. 3D Printed Surgical Templates for Fresh Cadaveric Osteochondral Allograft Surgery with Dimension Verification by Multivariate CT Analysis. (submitted)

V. Tuomi J, Paloheimo KS, Vehviläinen J, Björkstrand R, Salmi M, **Huotilainen E**, Kontio R, Rouse S, Gibson I, Mäkitie AA. A Novel Classification and Online Platform for Planning and Documentation of Medical Applications of Additive Manufacturing. *Surgical Innovation*, 2014, 21(6):553-9. doi: 10.1177/1553350614524838

Author's Contribution

Publications I, IV

Design of the research plan was carried out by Eero Huutilainen in collaboration with the co-authors. Eero Huutilainen performed most of the experimental work and was responsible for medical 3D modeling. He carried out the measuring method development and experimental measurements with the help of co-authors, and developed the computational methods described in Publication IV. The results were interpreted together with the co-authors. Eero Huutilainen was the main contributor and corresponding author in writing of the publications, with contributing sections from the co-authors.

Publication II

Design of the research plan was carried out by Eero Huutilainen in collaboration with the co-authors. Eero Huutilainen performed the 3D modeling step as the representative of one of the three collaborating institutions, as well as the CAD/CAM comparative analysis and initial interpretation of the results. Rest of the conclusions and finalizing of the publication were performed in collaboration with the co-authors. Eero Huutilainen and Risto Jaanimets were joint primary authors for this publication.

Publications III, V

Eero Huutilainen developed the research framework and questions with co-authors, and contributed to the practical conducting of the research as well as to drafting of the publications' manuscripts.

1. Introduction

Additive manufacturing (AM) is defined as production of physical objects by constructing them layer by layer based on digital files detailing a three-dimensional representative model of the object [Gibson, Rosen and Stucker, 2010]. In this dissertation, the term additive manufacturing is preferred, yet it can be used interchangeably with the more popular term 3D printing. The emergence of AM processes as a novel manufacturing paradigm is sometimes referred to as a new industrial revolution. However, when compared to traditional manufacturing production processes, subtractive processes, e.g. milling or CNC machining, often outperform additive manufacturing in mechanical stability and surface or aesthetic quality. On the other hand, direct per part costs can be driven lower by using formative processes such as injection molding, or other methods of mass production. In exchange, additive manufacturing is characterized by freedom of design, allowing straightforward production of complex shapes which are either cumbersome or impossible to manufacture with traditional manufacturing processes. With digitality embedded into its roots, additive manufacturing is also strongly linked with the overall digitalization of production processes alongside other contemporary production concepts such as Internet of Things or digital twins.

Although useful in industrial setting, the areas where additive manufacturing truly excels include the creation of highly specialized, low-volume, or individually customized products. The medical setting is a prime environment requiring such products: Patients are inherently individual with their respective anatomies and varying medical conditions. When compared to products designed for consumer markets with relatively homogenous customer needs, benefits of additive manufacturing (e.g. enhanced part functionality, freedom of customization, and leanness of manufacture) more often outweigh direct production costs.

As an input for additive manufacturing, one needs the digital design. When a medical application is pursued, a natural option is to turn to various medical imaging modalities as medical imaging capabilities are both extensively developed and routinely utilized in everyday radiology of patients.

1.1 The research gap

The main purposes for which medical imaging was traditionally developed were diagnosis and preoperative planning instead of three-dimensional manufacture. Because of this, both the imaging modalities and conventional radiological workflows differ significantly from the practices most optimal for models needed for additive manufacturing. The literature on medical imaging, clinical practice, orthopedics, or surgery is abundant, but it is only marginally connected to the concepts and methodology of production engineering. Conversely, the research on mechanical engineering rarely aims at medical applications, or even clinical relevance. This doctoral dissertation pursues to converge the body of knowledge between these two disciplines, as the included studies have been performed in teams of engineers and surgeons, and most results have been published in medical journals.

Table 1 highlights the focal points of this dissertation with respect to the five-step workflow for medical applications of additive manufacturing (the table columns). Of this process, the Step 2, i.e. the digital design phase, is in the centerpoint of this thesis as it is recognized to be the transformative step between commonplace medical imaging (Step 1) and truly innovative novel medical applications (Step 5). The various AM production processes (Step 3) have been already extensively studied in literature, whereas post-processing activities (Step 4) are less thoroughly charted.

It is to be acknowledged that this research topic is, in addition to being highly cross-disciplinary, extremely vast, and not everything is covered within the scope of this dissertation. Additive manufacturing is a production method with exceptional possibilities and, even more importantly, a wide accessibility to reach persons previously unfamiliar with manufacturing engineering activities. While this paradigm change shakes medical milieu by enabling completely novel user-based solutions, it also creates substantial challenges for communication between various disciplines and necessity for further education and research.

1.2 General aim

The aim of this thesis is to develop the process for medical applications of additive manufacturing. As the design step is in the core of this workflow, the first objective is to create a selection framework for suitable medical imaging to ensure the quality of input required for modelling activities. The second objective is to optimize the conversion step from design into efficient clinical application.

Table 1. The main foci of the publications (rows) charted against the process of medical applications of additive manufacturing (columns). This process consists of five steps: (Step 1) Medical imaging encapsulates radiology, from which the medical imaging data is segmented and reconstructed into a (Step 2) digital model (e.g. computer assisted design, CAD, or surface mesh representations). (Step 3) includes the production by additive manufacturing, and (Step 4) post-processing operations such as support removal, surface polishing, or sterilization. Finally, (Step 5) represents the actual application of the produced part.

Publication	1 Medical imaging	2 Digital design	3 Additive manufacturing	4 Post-processing	5 Clinical application	Publication focus
I	X	X				Imaging to design
II		X	X			Design to manufacturing
III		X	X	X		Manufacturing to post-processing
IV		X			X	Design to application
V	X	X	X	X	X	Whole process, collaboration

1.3 Specific aims

The specific aims of this Doctoral Thesis are:

1. To optimize medical imaging modality and parameter selection for medical applications of additive manufacturing.
2. To analyze the outcome variance in medical model creation process, and assess the main sources of it.
3. To characterize the surface structure and assess cytotoxicity of medical-grade titanium alloys processed using two AM processes commonly used in inert implant manufacture: direct metal laser sintering and electron beam melting.
4. To design and trial a patient-specific solution for a complex surgical problem using additive manufacturing. Furthermore, a CT-based computational design and analysis procedure is created for solution feasibility verification, design automation, and optimization.
5. To design and implement an online collaboration platform, where medical experts may document and share their clinical additive manufacturing cases based on the created application classification and process workflow framework.

2. Background

2.1 Additive manufacturing

2.1.1 Development phases: rapid prototyping, rapid tooling and rapid manufacturing

The first modern additive manufacturing device is considered to be stereolithography (SLA) process, published in 1984 by 3D Systems (CA, USA). By the 90s, the first powder bed fusion machines were commercialized, and additive manufacturing started to get utilized in the form of rapid prototyping (RP) in early product development phases in the industry. Rapid prototyping refers to the creation of pre-production prototype models by additive manufacturing techniques.

Next concept to be established was rapid tooling (RT), i.e. the utilization of additive manufacturing techniques in cost-efficient and lean production of molds, mold inserts, and tools for investment casting purposes [Hopkinson and Dickens 2003]. Rapid tooling increased prominently approaching the late 90s, and by early 2000s another approach, rapid manufacturing (RM), had emerged. This refers to the direct production of end-use parts by additive manufacturing processes. Rapid manufacturing is also varyingly known as direct digital fabrication, or direct digital manufacturing. The applicability of rapid manufacturing has traditionally been limited mainly for small-batch production and mass customization needs. However, as the processes and their capabilities develop, RM is becoming more and more attractive production method for larger variety of applications from aerospace to medical industries. [Levy 2003]

2.1.2 Types of additive manufacturing processes

After the discovery of SLA in the 1980s, new process approaches and variations emerged during the following decades. Contemporary additive manufacturing processes are divided into seven distinct categories according to the industry ASTM standard [ISO / ASTM52900]. These categories are vat photopolymerization, material jetting, binder jetting, material extrusion, powder bed fusion, sheet lamination, and directed energy deposition. Within each category, there are several technologies, each with their manufacturer-specific implementations.

Vat photopolymerization includes techniques where liquid resins are solidified by photopolymerization, usually layer by layer. Stereolithography is the classic example of such process. In SLA, the energy is introduced by a directed laser beam into each position to be cross-linked. Another common polymerization strategy is illuminating a whole layer at a time with a specifically designed projector or masking method, as performed in digital light projection (DLP) technique. Photopolymerization process can be optimized to yield parts with micrometer-level resolutions and ten-micron-level layer thicknesses. However, the material engineering is relatively complex. Because of this, SLA products often have limitations in their mechanical properties or long-term stability (due to unintentionally continuing photocuring). The materials are also relatively expensive.

In *material jetting*, material is jetted in a three-dimensional inkjet process to appropriate positions, and potentially locally solidified by ultraviolet or different wavelength illumination – in which case the process type is photopolymeric jetting. The materials used in material jetting process are usually wax-like, and common in rapid prototyping applications as the support material may be chemically or mechanically removed with relative ease. A common example of this category is the Stratasys PolyJet technology.

In *binder jetting* process, the material is commonly in powder form, spread layer-by-layer onto a build bed. Binder is then applied from an inkjet-like printhead to cure required parts of each layer, and the process is repeated until the full height of the objects under production is achieved. Depending on the equipment, apart from powder removal, post-processing of binder jetted parts might include e.g. epoxy coating to strengthen the brittle detailed parts of the objects. Full-color part production is relatively straightforward, as color pigments may be deposited along with the binder application.

As the most widely spread additive manufacturing process, *material extrusion* category encapsulates the extrusion of thermoplastic filaments, as well as syringe-based extrusion of paste materials. The common trade name for these techniques is Fused Deposition Modelling (FDM), as used by Stratasys. Material extrusion is the process type normally utilized in inexpensive hobbyist kits as the production mechanism requires only simple computer-controlled linear motion with controlled heating and deposition of material. Additionally, suitable materials such as acrylonitrile butadiene styrene (ABS) and polylactides (PLA) are inexpensive and widely available in the required filament form. During the peak of the recent 3D printing hype, the entry-level machinery was often burdened with overall process unreliability, poor material adhesion to the build platform, or excessive part warping due to lack of temperature control in open-chamber systems. These issues have since been alleviated in several low-cost devices by process optimization and utilization of expiring patents. More expensive industrial tier machines offer advantages like closed-chamber architecture for improved temperature management, and they can

manufacture using more advanced materials, e.g. polyether ether ketone (PEEK). Surface quality remains an issue with material extrusion, because filament layers are normally visible as stepped structures in end-products. Additionally, part porosity or delamination of layers may affect their mechanical properties. A currently booming application, desktop metal printing, can be accomplished by using an inexpensive material extruder to print a filament made of polymer-metal mixture. The adhesive polymer can be then chemically removed, and the remaining metal part can be sintered in a dedicated oven to produce a solidified metal part. This process is prone to warping and porosity of the end-product due to removal of the adhesive material, but is extremely cost-efficient when compared to investments into AM devices capable of directly producing metal parts.

Similarly as in binder jetting, in *powder bed fusion* processes the material is in powder form and usually inserted into the build chamber layer by layer with a dedicated roller mechanism. Computer-controlled energy source applies energy locally to each layer, curing the required areas. Depending on the process type, the actual curing mechanism might be sintering (such as in selective laser sintering, SLS) or melting (such as in selective laser melting, SLM, and in Direct Metal Laser Sintering, DMLS). For these techniques, the required energy is applied by a laser light source. Alternatively, electron beam (electron beam melting, EBM) or locally-powered resistors (selective heat sintering, SHS) may be utilized. Usable materials vary from metals (e.g. titanium, aluminum, stainless steel, or precious metals) to plastics from common polyamides to high-performance engineering polymers such as PEEK. The processes yield usually high resolutions, and with polymer fusion, also good surface qualities. In metal fusion, support structures are required to both carry the mass of the object and to conduct heat into the build platform. These supports need to be machined, and usually the design should be optimized to account for this requirement.

In *sheet lamination* processes, sheets of material are stacked, cut (mechanically or optically) layer-by-layer, and the sheets are bound by adhesive on areas overlapping the required design. The rest of the non-adhered material is discarded. This process is relatively uncommon and only a few manufacturers employ this process type; As raw material, common office paper may be used. However, by contrast with most other processes, the discarded material is not directly recyclable as build material for next production batches, causing this process to provide more waste.

The Directed Energy Deposition (DED) process is somewhat analogous to welding in three-dimensional space, where the material is extruded and consecutively solidified in a welding-like process at required positions while controlled by a designated robot or robotic arm. In theory, this can be performed without any chamber size limitations as long as the DED tool head can be moved into appropriate positions by robotic means. Attempting to achieve high accuracies usually render this process relatively complex and expensive.

2.2 Medical applications of additive manufacturing

We [Tuomi 2011] classified medical applications of additive manufacturing into five distinct categories: (1) Medical models; (2) Medical aids, supportive guides, splints, and prostheses; (3) Surgical tools, instruments, and parts for medical devices; (4) Inert implants; and (5) Biomanufacturing – Figure 1 presents an example of each category.

Figure 1. Various medical applications of additive manufacturing. (a) Medical models include preoperative, intraoperative, postoperative models as well as models used for training, education, and communication purposes. (b) Medical aids, supportive guides, splints, and prostheses are patient-specific applications designed to support or guide the body functions. (c) Surgical tools, instruments, and parts for medical devices (the instrument in the Figure is used for complex jaw surgery). (d) Inert implants, such as the meshed titanium implant replicating missing mandibular bone tissue. (e) Parts for biomanufacturing, which is defined as a combination of additive manufacturing and tissue engineering.

2.2.1 Medical models

The first class of medical applications of additive manufacturing includes various models replicating actual anatomy. Preoperative models are used prior to non-routine surgeries to get better assessment of the three-dimensional clinical situation, or for operation planning where e.g. simple pen markings can be added. Preoperative models can also be utilized for communication on situation with the patient or the relatives of the patient. Medical models can also

be utilized intraoperatively, in which case they have to be either of sterilizable material or sealable in a sterile bag. Postoperative uses of medical models would in turn serve similar purposes as regular postoperative medical imaging – for assessment of the surgery results, planning of follow-up steps, and communication with the patient. [Lethaus 2012, Salmi 2016]

2.2.2 Medical aids, supportive guides, splints, and prostheses

This class of medical applications includes various parts designed to either support or guide the patient's anatomy. Typically, these are external to the patient body, with invasive components such as bone screws normally not additively manufactured. These include also orthodontic applications: such case was demonstrated by Salmi et al. [2013] who designed and produced occlusal splints with an SLA process. Also, the earliest example of an actual final product manufactured with additive manufacturing was patient-specific auricular prostheses [Sykes 2004, Jiao 2004, Mardini 2005, Subburaj 2007, Karayazgan 2009, Turgut 2009, Liacouras 2011]. Rapid manufacturing of such prosthesis is an ideal application, as the hearing aids are sufficiently small yet high-value products, which greatly benefit from patient-specific mass customization options to ensure proper fit in the patient's ear.

2.2.3 Surgical tools, instruments, and parts for medical devices

The third category includes patient-specific tools, custom surgical items designed for a specific operation, as well as various parts for medical devices. These can be, for instance, titanium-alloy tools designed for short-term biological tissue interaction (and not left for long-term contact) such as an instrument designed and manufactured for a mandible fracture reduction by Kontio et al. [2012], non-ferromagnetic peripherals and accessories for fMRI studies as utilized by Kamara [2012], or phantoms for PET/SPECT studies [Hunt 2009, Beekman 2009].

2.2.4 Inert implants

This class of medical applications includes all directly or indirectly produced inert implants; parts which are inserted inside the body, and which stay there for mid- to long-term. Clinically common alternative term is patient-specific implant (PSI). Indirect production of inert implants is possible e.g. by first printing patient-specific wax models followed by investment casting suitable biocompatible materials to create the required implants. Most commonly utilized materials are titanium alloys, as in implantology in general. Salmi et al. [2012] designed and produced (using direct metal laser sintering process) a meshed titanium orbital implant to replace a fractured orbital floor of the patient. Implants produced using additive manufacturing have also been utilized to treat cranial defects (e.g. Walter Reed Army Medical Center's cranial implants [Rouse 2009]), as well as mandible and other cranio-maxillofacial defects [Poukens 2008].

2.2.5 Biomanufacturing

The final class of medical applications of additive manufacturing is biomanufacturing, which is defined as the combination of additive manufacturing and tissue engineering. Additive manufacturing has been extensively utilized in the production of three-dimensional scaffolds, into which stem cells and growth factors are inserted and cultivated. The scaffold functions as a three-dimensional petri dish, giving the cells their needed support for growth into required dimensions. On microscopic level, the exact scaffold configuration, porosity rate, pore dimensions, and sub-unit details can be engineered to provide optimal growth conditions. The macroscopic dimensions of the scaffold can be designed to align with patient-specific anatomy, e.g. when missing tissue is replaced. Additive manufacturing has also been utilized directly as bio-plotting, i.e. controlled deposition of living cells, growth factors, or tissue cultivation mediums replacing manual pipetting. [Bartolo 2009, Domingos 2009, Khalil 2009]

2.3 Medical imaging and design for additive manufacturing

In order to be able to produce objects by additive manufacturing, a three-dimensional representation of the part is required. Conventionally, these have been designed in dedicated CAD (computer-assisted manufacture) software. However, in the medical environment, one usually processes complex organic shapes, for which the more engineering-orientated solutions are not optimal: parametric CAD model representations are normally based on well-defined primitive shapes, straight or repeating angles, parallelism, straight lines, measure relations, and other abstract geometric but not naturally-appearing (in strict sense) features. To faithfully follow the complex organic shapes, these are often represented with explicitly defined polygon meshes. When compared to theoretical CAD models, imaging and triangulation error reduces the accuracy of the models while the file sizes are typically considerably larger due to explicit local definition of the whole shape instead of e.g. abstraction of primitives possible in CAD.

Medical imaging for AM applications has certain requirements, which overlap with traditional imaging objectives only partially. As most prevalent uses for medical imaging have been diagnostic imaging and preoperative planning, clinicians are often working with planar or projection images. These include both natively projective images, such as results from an X-ray scan, as well as planar representations of 3D images, such as viewing a single layer of interest from a CT image stack. In diagnostic imaging, the images are often used as qualitative representations, e.g. to verify the existence of a certain condition in the patient's body. Therefore, they rarely require high spatial resolution or three-dimensional images at all. For preoperative planning, both higher spatial accuracy and the availability of 3D images are more valuable, but are often still not essential as trained surgeons are often capable of filling the clinical details with their professional expertise.

Figure 2 plots the image dimensionality against anatomical accuracy. Dimensionality is positioned conceptually along a smooth transition between pure-planar and pure-3D images; Native X-ray scans are an example of the former while computed tomography scanning using isotropic voxels represents the latter. While capable of capturing 3D images, MRI and ultrasonography are commonly performed using higher slice thicknesses or otherwise non-isotropic voxels resulting in partial loss of three-dimensionality.

The anatomical accuracy axis refers to the correctness of planar feature representation, including minimum feature sizes and place resolution. Faded gray labels in the figure show approximate positions for various imaging modalities, while three imaging objectives are plotted with blue shapes. Here, diagnostic imaging and preoperative planning represent traditional imaging objectives. It is important to recognize that the available medical imaging modalities as well as the radiological workflows the clinicians are following are designed to adapt for these two common purposes. Medical applications of AM introduce notable changes to these requirements; namely, the increased demand for absolute anatomical accuracy in all three dimensions.

Figure 2. Requirements for medical imaging separating traditional imaging objectives (diagnostic imaging, preoperative planning) from imaging for additive manufacturing (in here, implant design). On faded grey, typical medical imaging modalities are positioned regarding their offered dimensionality and spatial resolutions.

2.3.1 Medical imaging modalities for AM models

By far, the most utilized medical imaging modality in clinical applications of additive manufacturing is computed tomography (CT). This is partly explained by most prevalent application types; As typical additive manufacturing processes produce parts from hard materials (in their solidified form), they have been extensively employed in, for instance, reproduction of bone-mimicking structures (e.g. titanium implants). Computed tomography is the natural choice for these needs, given its excellent hard-soft tissue contrast, which can be further enhanced with suitable contrast agents and by adjusting the imaging parameters; For example, by raising the tube current (radiation dose), more photons are expected to pass through any given voxel, which can be used to either increase the signal-to-noise ratio or to reduce voxel dimensions (i.e. increase spatial resolution). However, as the unwanted radiation burden onto the patient increases with the dose, dose maximization cannot be considered an optimal strategy.

As additive manufacturing materials and processes are developed to support softer, elastic, or for example hybrid materials, the superior soft tissue imaging capabilities of magnetic-resonance imaging (MRI) might prove more viable. In MRI, the main downside is its long imaging times – three-dimensional MR image might take 20 minutes or more to reconstruct, which incurs costs and might also introduce motion artifacts. Despite these limitations, MRI has been utilized previously e.g. in mapping the extents of cerebral tumor for models produced using additive manufacturing [Chang 2011], and in the creation of post-mortem models [Schievano 2010].

Medical imaging modalities used less frequently for creation of 3D models include 3D ultrasonography (US), and nuclear isotope imaging. Ultrasonic imaging has been utilized in fetal imaging [Werner 2010], mainly due to its safety to both the mother and the fetus. For PET/SPECT imaging, additive manufacturing has been employed in the production of anatomically accurate phantom parts [Hunt 2009, Beekman 2009]. Alike CT, nuclear isotope imaging introduces harmful radiation burden to the patient.

2.3.2 Image processing, reconstruction, and 3D design

Most three-dimensional medical imaging modalities produce volumetric models, i.e. spatially aligned collection of voxels (volumetric pixels carrying distinct intensity values). In computed tomography, these intensity values refer to the radiodensity of said voxel; Values are typically normalized into Hounsfield units (HU), which is an intensity scaling convention where the radiodensity of air corresponds to HU of -1000 and water corresponds to HU of 0. The standard format for medical image stacks is Digital Imaging and Communications in Medicine, DICOM. Segmentation of DICOM images refers to the detection of object boundaries; that is, dividing the imaging volume into a sub-volume containing the required part, and its complement. Several segmentation algorithms and approaches exist. The simplest algorithm is intensity thresholding, where a suitable threshold value is chosen either

manually, semiautomatically, or automatically, and all voxels carrying intensity values above the threshold are included in the binary image. In medical applications, these regions of interest often denote hard tissues, e.g. bone. In its basic form, threshold segmentation is a global process whose feasibility is dependent on both the required application as well as the exact image type. For situations with, for example, locally varying intensity scaling or overlapping of several tissue types in either intensity space or within same voxel (partial volume artifact), more advanced segmentation methods are needed. These include gradient-based algorithms, edge detection algorithms, region growing/snake-based methods, or histogram analysis. Most of these approaches may be performed either (semi)manually or automatically.

As the segmentation task is completed, the next step is reconstruction of the model. A common way to do this is to utilize a variation of marching cubes algorithm [Lorensen and Cline, 1987], which converts the volumetric model into an isosurface: this is a boundary mesh consisting of collection of triangle vertices and their orientation normals. These triangular meshes are most commonly stored in a STL file format (named after stereolithography), as most additive manufacturing equipment directly support these models. Polygon mesh manipulations are also possible with dedicated software tools, although parametric modification of them is usually more complex than with CAD models.

The reconstructed models can get extensively complex and large; as the medical data is essentially organic in shape, it can usually not be compressed into abstractions in a similar fashion as, for instance, a CAD software would store the model features as parametric primitives. Also, as STL models are decimated triangular representations of organic structures, they are inherently inaccurate. They also require all solid objects to be defined by watertight surfaces, and regularly, this condition fails, i.e. the models exhibit broken or missing triangles.

Some error correction algorithms have been developed, but often fixing of these require substantial manual labor or even reverting to creating a completely new reconstruction. Several suggestions for replacement of the limited STL file format have been given throughout nearly its whole existence. One notable example is Additive Manufacturing (AMF) file format, with backwards compatibility to STL coupled with support for curved triangles/splines, solid constructive geometry (SCG), and material gradient encodings. However, the industry has not yet embraced this nor other alternatives to STL despite the benefits they would offer. Most likely STL will remain as the de facto industrial standard for at least near future; eventual replacement of it will more probably stem from the needs of a future breakthrough printing application instead of technologically-oriented gradual improvements.

2.4 Materials used in medical applications

In implant applications, the most used materials include titanium alloys, for instance Ti6Al4V (ELI), and cobalt chromium (CoCr) for dental applications such as directly sintered bridges and crowns. For other application types, suitable materials vary widely. For medical models, most materials will be applicable – in case of intraoperative models, the material needs to be sterilizable or alternatively, sealable in a sterile bag. Otherwise, inexpensive plastics such as ABS or PLA can be used. Depending on the application, medical models can benefit from multimaterial capabilities, or elastic materials to provide haptic response e.g. when simulating soft tissue in medical student training situations. Photopolymeric resins are also commonly utilized, partly as stereolithography was the first technique to be used in production of medical models; additionally, SLA resins may offer other advantages such as transparency.

The term biomaterial may refer to a material either being biologically compatible or biodegradable. In general, implant applications require biocompatibility, an example of such material being poly(methyl methacrylate) (PMMA), as well as in certain applications biodegradability, in which case e.g. polylactides (PLA) might prove functional. Poly(trimethylene carbonate) (PTMC) and poly(L-Lactide-co-ε-Caprolactone) (PLCL) are among the currently studied alternatives. A shift from rigid non-degradable materials (mostly titanium alloys) is often strived for among the clinical practitioners, but no currently approved biopolymer offers paralling mechanical properties suitable for replicating bone structures.

Additionally, the long approval processes of new biodegradable polymers will contribute in conserving the status quo for the proximal future. Hence, metals are expected to remain in prevalence despite the potential of highly-researched novel functional polymers. Partly, the non-biology-resembling properties of e.g. titanium can be modified by for example alterations to the design – for bone applications, trabecular bone can be printed as solid metal and cancellous bone may be emulated by building porous or meshed structures. A typical non-metal approach for bone emulation is to print calcium-based minerals, such as hydroxyapatite (HA) [Leukers 2005, Cox 2015], Calcium Phosphate (CaP), or Tricalcium Phosphate (TCP), possibly in conjunction with collagen scaffolds [Inzana 2014]. Whenever novel biomaterials are developed, an additional engineering step is required to optimize them suitable to be processed by additive manufacturing, and in certain cases, the extreme production conditions (e.g. high temperatures during sintering or laser melting process) might alter the chemistry and intended functionality of the material.

3. Materials and methods

3.1 Medical imaging (Publications I, II, IV)

The medical imaging for this dissertation was performed on a variety of computed tomography devices. All of the used machinery are commercial models which are in common clinical use. Equally, the parameter sets were chosen by experienced radiologists according to the current care guidelines at several Finnish hospitals.

For publication I, a collection of computed tomography images from the skull base of a patient were captured using a Siemens CT device (SOMATOM Definition AS+, Siemens Medical Systems, Erlangen, Germany). A pair of images was reconstructed: The first reconstruction was performed with a “soft” algorithm at 1.0-mm slice thickness, and the second with “bone”-type reconstruction kernel at 0.6-mm slice thickness. For both images, a 120 peak kilovoltage (kVp) and a tube current of 58 mA were used.

For publication II, the head of a patient undergoing tumor surgery at the Tampere University Hospital was imaged using a Planmeca ProMax 3D Max (Planmeca, Helsinki, Finland) cone-beam computed tomography device. Reconstructions were performed on a Philips Brilliance CT workstation (Royal Philips Electronics, Amsterdam, The Netherlands) using a 0.9 mm slice thickness and a slice overlap of 0.45 mm, resulting in an effective slice thickness of 0.45 mm. The peak kilovoltage was 96, and the tube current was 11 mA. The spatial resolution (voxel size) was 0.4 x 0.4 x 0.4 mm³.

In publication IV, the patient was imaged using GE LightSpeed VCT device, with a tube current of 100 mA, 120 kVp, and a “detailed” convolution kernel. The planar resolution was 0.4 x 0.4 mm², and slice thickness 0.6 mm.

3.2 3D design and modeling (Publications I-IV)

Here, 3D design and modelling refer to all reconstruction, modification, and analysis operations on the digital designs which take place after the image acquisition. The processing is performed mainly on triangular surface meshes (STL files), with non-imaging-based modelling in native CAD format and additional computations done in volumetric (voxel) space, i.e. in 3D image

stacks using Matlab (versions R2015a through R2017b, Natick, MA) numerical computing environment.

For publication I, the DICOM files were opened, segmented, and triangulated into STL models with OsiriX medical image viewer. OsiriX is a widely used and powerful medical image viewer and processor for Macintosh systems, and is available both as free of charge Lite version and FDA-cleared class II medical device, OsiriX MD. The used threshold intensity was 300 Hounsfield units, and no smoothing was performed at this stage. The resulting models were subsequently opened in Viscam RP, a CAD/CAM (computer-assisted manufacturing) software suite by Marcam Engineering (Bremen, Germany). Finally, the 0.6-mm slice thickness model was processed into a third model by applying a low-pass filter (in order to reduce noise) and smoothing (smoothing factor 0.1, 50 iterations).

The initial 3D design and modeling steps in publications II and IV were performed in Viscam RP, mainly for its ability to perform Boolean operations on triangular meshes. Additional reconstructions for publication II were created by two other institutions, allowing them to use their software of choice or proprietary tools. These actions were regarded to take place inside of a black box by study design. In publication IV, the template model was meshed in DeskArtes 3Data Expert (DeskArtes, Espoo, Finland), for it offered an optimized module to perform said specialized task. All computer tomography image processing, analysis, and optimization tools were created in Matlab. Assessment of surface intactness and section volume was performed by defining the initial shape and optimization directions within the CT image space. Then, three voxel planes were sampled (horizontally, diagonally, and vertically) between the eight defined control points – these correspond to the superior and anterior extrema points of the section.

Due to the shape restrictions, the independent dimensions were restricted into four: the horizontal and vertical section lengths (representing the distance between the femoral surface and the starting point of the diagonal cut, for both orthogonal directions respectively), and horizontal and vertical total allograft lengths, defined as the depth and height of the bounding box of the whole allograft. The orthogonal section lengths were bound to be smaller than total dimensions, i.e. the diagonal section was required to be present in each design candidate. The surface intactness rating for each triplane section surface was defined as the area of above-threshold planar voxels divided by the area of morphological image closing of said voxels. As a structuring element, an element with a radius of 10 mm was used, effectively resulting in a near-concave-hull operation. Two alternatives were compared to the morphological closing approach. First, convex hull operation was trialed for acquisition of the area for the denominator. This approach underestimated the surface intactness rates, as the actual concavity of the femoral surfaces was conceived to represent unwanted porosity. Conversely, using an actual concave hull operation neglected factual porosity resulting in overestimation of the surface intactness.

The acquired surface intactness and section volume values were used first to verify feasibility of the manually performed virtual operation. Furthermore, as

analysis can be performed in any dimension between 1D to 4D, an optimization strategy for design automation was created. This is postulated as Eq. 1:

$$\arg \max_{\{d_v, D_v, d_h, D_h\}} F = \frac{SI(d_v, D_v, d_h, D_h)^\alpha}{V(d_v, D_v, d_h, D_h)^\beta} \quad (\text{Eq. 1})$$

where F is a fitness function to be maximized. d_v , D_v , d_h , and D_h correspond to the four independent dimensions, SI to the surface intactness rate (between 0 and 100%), V to the section volume, and $\alpha \in \mathbb{R}$ and $\beta \in \mathbb{R}$ to the loading parameters dictating whether the optimization emphasizes minimization of volume ($\alpha < \beta$) or maximization of surface intactness ($\alpha > \beta$). All verification and optimization tasks described here were performed postoperatively – the initial design feasibility was manually assessed in collaboration with the surgeon responsible for the operation, as obligated by the law and good clinical practice. Using design automation, optimization, and similar techniques for actual preoperative planning purposes would require the method to be cleared as a medical device.

For Publication III, the sample discs were simple cylinders designed in CAD, and nominally dimensioned at thickness of 2 mm, diameter of 17 mm, and surface area of 560 mm².

3.3 Additive manufacturing (Publications II-IV)

The additive manufacturing techniques utilized in the thesis research include binder jetting (Publications II and IV), selective laser sintering (Publication IV), and electron beam melting and direct metal laser sintering processes (publication III).

The SLS machine used for sintering polyamide (PA2200) for the surgical templates was from EOS (Electro Optical Systems GmbH, Krailing, Germany); sintering of PA offers moderate-cost industrial-quality parts with adequate mechanical properties and biocompatibility. For binder jetting, we used Zprinter 450 with the proprietary ZP150 powder which is essentially starch-like material selectively cured with epoxy-based hardener. This device was selected as it allows production of relatively large (up to 10.5 dm³) complex 3D structures without supports, and includes a possibility of adding colors to the surfaces. These parts are however not biocompatible due to the epoxy coating. For publication III, the samples were produced with electron beam melting (Arcam AB) and direct metal laser sintering device, using Ti6Al4V ELI Titanium alloy. The EBM alloy has considerably larger particle sizes than DMLS alloy, but explicit powder characterization was not performed as the commonly used manufacturing process was followed instead. Both of these production processes have been utilized in direct manufacture of medical implants [Ciocca 2011, Salmi 2012, Mangano 2011, Parthasarathy 2010].

3.4 Post-processing operations (Publications II-IV)

Figure 3. Sample discs used for surface structure characterization and cytotoxicity assessment. Top row: EBM as-processed (notice the rough surface) and EBM polished. Middle row: DMLS as-processed and DMLS polished. Bottom row: Commercial mandible plate (control).

The medical models created with binder jetting technology (Publications II and IV) were cleaned from build powder residues and further cured using proprietary epoxy hardener (Zbind 150). No support structures were needed in the manufacture of these parts, but the parts are not suitable for tissue contact and hence were sealed in a sterile bag prior to being used intraoperatively. Polyamide templates for publication IV were manufactured in a support-free process (selective laser sintering of polymers), and they were sterilized following the procedures of the hospital performing the surgery using a common autoclave process.

For EBM and DMLS metal processes (Publication III), support removal is required and was performed by the part suppliers. For surface polishing, preliminary metallurgical grinding of the discs was done using silicon carbide abrasive paper with a FEPA grit size of P320 to P4000 (ISO 6344). Final grinding was performed using a 3 μm diamond suspension and a polishing cloth. Lastly, all discs were purified using ultrasonic cleaning (ethanol) for three minutes. The actual average test piece dimensions ranged from 6% over nominal values for EBM as-processed and 5% over nominal values for DMLS as-processed, to 10 and 5% under nominal values for EBM and DMLS polished, respectively. Prior to cytotoxicity assessment, the sample discs and the control plate were sterilized using a dedicated autoclave in accordance to the ISO 17664 specifications.

3.5 Optical and mechanical surface scanning and characterization (Publications II, III)

For imaging activities outside the realm of medical imaging (CT, MRI), we analyzed part surfaces both optically and using mechanical probing.

Surface topography of the EBM and DMLS produced titanium samples for publication III was analyzed by Innovatest TR-200 (Maastricht, The Netherlands) Ra measuring equipment. However, EBM as-processed samples

were out of the measuring range, and for those specimens Taylor Hobson Form Talysurf Inductive 120 (Leicester, UK) equipment was used. The microscopy images of the samples were acquired by scanning-electron microscope (SEM).

CAD/CAM measurement in publication II was performed with GOM stereophotogrammetry scanner and GOM Inspect mesh inspection software (GOM GmbH, Braunschweig, Germany), which performs partial Procrustes analysis. In this process, the optical scanner captures a point cloud representation of the object, the software reconstructs it into a contiguous surface, and these surfaces are inter-aligned by translations and rotations. Scaling is not allowed unlike in full Procrustes analysis. For each point, the Euclidean norm to the nearest point in the compared model is calculated to represent the local deviation, and the optimal registration is achieved by minimizing the function F , i.e.

$$\arg \min_{\mathbf{T}} F = \sum_{n=1}^N \text{norm}(\mathbf{P}_{A,n} - \mathbf{P}_{B,n}) = \sum_{n=1}^N \sqrt{\sum_{d=1,2,3} (P_{A,n,d} - P_{B,n,d})^2}$$

where $\mathbf{P}_B = \mathbf{T}\mathbf{P}_A$ and $\mathbf{T}$ is a rigid-body transformation matrix without scaling factor. N is the number of vertices in the surface mesh or points in the point cloud, $\mathbf{P}_{A,n}$ is the 3D vector of point or vertex position, and $P_{A,n,d}$ is the scalar spatial component ($d=\{1,2,3\}$) of the vector.

Figure 4. Measurement protocol used in publication II. A common set of CT-captured DICOM layers were reconstructed into STL models independently at three different institutes. From each model, a physical part was produced, and optically scanned. Finally, the scans were inspected, by numerically comparing them with each other as well as with the original STL models (CAD-CAM analysis).

3.6 Cytotoxicity assessment (Publication III)

For cytotoxicity assessment of the metal-produced test pieces, Positive Bioreaction (Lot: FoDo14) (US Pharmacopeia, Rockville, MD, USA) was used as a positive control. The test material contains an organo-tin compound, which upon release in cell culture tests, causes cell damage. High-density polyethylene (Lot: HoFo46) from US Pharmacopeia was used as a negative control. Cell culture medium was used as a blank control. The test pieces were submerged in Eagle's minimum essential medium with 10% FBS, at a ratio of 3 cm²/ml medium, at $+37 \pm 1$ °C for 24 h. The assessment protocol was performed following the ISO 10993 standard.

4. Results

4.1 Imaging modalities and parameters for clinical applications of additive manufacturing

Based on the performed literature analysis of medical applications of additive manufacturing, by far the most employed imaging modality is computed tomography. CT is ideal for reconstruction of hard tissue anatomies, and on the other hand, most modern production processes as well as medical-grade materials in additive manufacturing excel in manufacture of hard structures – most notably, Titanium alloys in implant and surgical tool manufacture, biopolymers for biomanufacturing (e.g. 3D cultivation scaffolds). However, as flexible and hybrid material processing capabilities offered by additive manufacturing gain ground, magnetic resonance imaging may prove increasingly valuable in capturing soft tissue structures and interfaces. A range of applications already exist utilizing MRI using both anatomy and function/physiology/pathology weighted imaging sequences (T1/T2 and others). Other medical imaging such as ultrasonic and nuclear isotope imaging (e.g. PET/SPECT phantoms) are less frequent but can be employed on a case-by-case basis. Ultrasound imaging has a few drawbacks. First, ultrasound imaging has the innate limitation of ultrasonic waves being unable to properly penetrate air (e.g. in lungs) and hard tissues. Second, while ultra-high frequency US transducers have been developed for micrometer-level resolutions, their penetration depth is decreased as the wave attenuation increases with raising frequency.

The sample study conducted in publication I demonstrated the utmost significance of employing accuracy-conserving imaging parameters such as hard convolution kernels in order to achieve intended outcomes from the digital design and physical production steps. The necessity to minimize radiation doses in CT or the prolonged 3D imaging times in MRI preclude imaging at highest-possible resolutions, making it essential to avoid loss of accuracy due to lack of communication within the network of operators or to partial optimization of processes. For instance, in the study we found value-destroying practices in some hospitals' radiology work flows: Image resolutions were compressed when saving the images to PACS, and having to utilize these "packed" images instead

of raw source images unnecessarily hinders the design and additive manufacturing processes. Hence, regardless of current radiological protocols, the high-frequency model details should be preserved at the process upstream as all filtration and decimation tasks can be performed closer to the design or production steps if needed.

Table 2 presents the key results from the literature analysis and the original study. The details concerning each application type, used imaging modalities, imaging parameters, and production parameters are shown. The parameters varied widely, and many literature sources did not list every imaging parameter in detail. The main observation was that requirements differing between traditional medical imaging objectives and for clinical applications of additive manufacturing were the increased need of accuracy in all three spatial dimensions. In medical imaging, depending on the clinical need, 1.5- or even 3-mm slice thicknesses may be considered adequate. On the other hand, layer thicknesses in high-accuracy SLM processes range typically between 15 and 50 μm , and even when high build speeds are targeted, layer thicknesses around 200 μm (up to 500 μm) are typical. Even inexpensive material extrusion processes offer 200 to 300 μm layer thicknesses and correspondingly slightly larger minimum feature sizes. Hence, the difference between the medical image and AM production layer thicknesses may be over two scales of magnitude.

In medical imaging, resolution is normally optimized for planar viewing. This applies both to image processing and storage (e.g. increasing slice thickness prior to exporting DICOM to PACS), as well as to the actual imaging; For example, MR imaging is often performed from orthogonal directions (axial, sagittal, coronal) using anisotropic voxels emphasizing the in-plane resolution. Methods allowing the combination of such image sets could prove useful for additive manufacturing purposes: this manifests itself essentially as an image fusion problem, as the imaging data between scans is not necessarily commensurate (e.g. different MRI contrast sequences used), but still complementary in describing truly 3D structures as image isotropicity is artificially reconstructed.

While only the highest clinically used CT resolutions (in the range of 100-200 μm voxel dimensions) match the lateral placement accuracies of AM processes, the smallest feature sizes provided by various AM processes can be several times larger than their placement accuracy. Therefore, the lack of ultra-high-frequency details in the images is usually not the most critical issue. More importantly, the voxel-based image reconstruction strategies most commonly utilized in medical imaging may be suboptimal, as the imaging voxels (e.g. 0.5 mm in width) are not perfectly aligned with the structures to be imaged or produced, resulting in partial volume effects or similar phenomena. In certain AM processes, e.g. SLM, build rates may be improved by processing the part surfaces with a fine beam size while the core of the part is processed with a wider diameter beam and possibly skipping layers (“skin-core” processing [Schuh 2012]). Similar strategy would be especially interesting for medical imaging: If the voxel size could be dynamically altered along the imaging space, one could target the more interesting structures such as the model surfaces with high-

Results

resolution imaging (i.e. utilizing disproportionately large share of imaging time, photons, etc. there) while skipping the bulk of the space with low-intensity imaging and large voxel sizes. Such an approach would arguably be challenging to achieve, but while especially helpful in imaging for AM, it would also be attractive for perspectives beyond that. Spatial and temporal dose modulation techniques have been developed for CT imaging, but those methods mostly modulate the momentary overall tube current instead of adjusting pixel-wise intensities for localized photon trajectories.

Table 2. Essential imaging and production parameters collected from the literature analysis and our own study.

Application	Modality	Imaging details	Production details	Reference
implant (cranial)	CT			Rotaru 2012
implant (orbital)	CT		DMLS	Salmi 2012
biomanufacturing	CT			Thesleff 2011
preoperative models	CT, CBCT	64-slice Philips Brilliance, Imaging Sciences ICAT, processed in Materialise Mimics	Material extrusion	Lethaus 2012
auricular prostheses	CT	1.25 or 0.625 mm slice thickness, soft tissue kernel		Sykes 2004, Jiao 2004, Mardini 2005, Subburaj 2007, Karayazgan 2009, Turgut 2009, Liacouras 2011
cardiovascular	MRI, CT	<i>MRI</i> : 1.5T with sense-cardiac coil, Philips; echo time 2.4 ms, repetition time 5.1 ms, voxel size 1.2 x 1.2 x 1.8 mm ³ , reconstructed to 0.7 x 0.7 x 0.9 mm ³ <i>CT</i> : ECG-gated, Siemens Somatom Definition, 64 slices, FOV 145 mm, 512 x 512 matrix, slice thickness 0.8 mm	Binder jetting	Riesenkampff 2009
cardiovascular	CTA	64-slice Philips Brilliance, Toshiba Aquilion 16, iodine contrast, 80-120 kV, 100-300 mA, 1.0 mm slice, 0.5s gantry rotation, 0.6-0.7-mm beam pitch	SLA, urethane	Shiraishi 2010
cardiology	CTA	40-slice Philips Brilliance, iodine contrast	Material extrusion	Kim 2008
mapping of extents of cerebral tumor	MRI + fMRI	T1 MPRAGE, EPI BOLD	Binder jetting	Chang 2011
postmortem fetal and infant anatomies	MRI	1.5-T and 9.4-T, T2-weighted 3D turbo spin echo sequence	SLA	Schievano 2010
custom ancillaries for fMRI studies				Kamara 2012
fetus models	3D-US, CT, MRI	<i>US</i> : harmonic imaging, 4-8 MHz transducer <i>CT</i> : 0.75 mm slices, mean radiation dose 3.12 mGy <i>MRI</i> : 4.0 mm slices		Nelson 2000, Werner 2009
nuclear imaging phantoms	SPECT, PET/CT	<i>SPECT</i> : 1.7 x 1.7 x 1.7 mm ³ voxels <i>PET/CT</i> : Philips GEMINI, 4.0 x 4.0 x 4.0 mm ³ voxels		Hunt 2009

nuclear imaging phantoms	section photography, SPECT, uCT	20um coronal slices of a Wistar rat sectioned and photographed	SLA, 0.036 mm layer thickness	Beekman 2009
skull base models	CT	0.6 and 1.0 mm slices, 120 kVp, 58 mA tube current	Binder jetting	Huottilainen 2014
vascular models	CTA	64-slice CTA, Siemens Somatom Definition AS, contrast iohexol, 0.6-mm thickness, 140 kV, 250 mA, 1-s per rotation	Material extrusion	Govsa 2017
veterinary, orthopaedics	CT	GE Lightspeed VCT 64-slice helical scan, transverse 1.25mm slices, 50% overlap, high-frequency bone algorithm	SLA	Radtko 2017
CT and US phantoms	CT, US	<i>CT</i> : Siemens Sensation 16, 120 kVp, 250 mAs, 0.5 second rotation time, 0.8 pitch, 1.2 mm detector collimation; reconstructed with soft-tissue algorithm at 3-mm slice thickness at 3-mm intervals and 2-mm slice thickness at 1-mm intervals <i>US</i> : 8 MHz linear probe (Siemens Acuson P300), scanned in transverse and sagittal plane		Mooney 2017
dental prosthetics, image fusion	CT, optical scanning	<i>Optical</i> : common dental cast 3D scanned with 3D Medical Print KG (Hagenberg, Austria) <i>CT</i> : Siemens SOMATOM Sensation Open, 1 mm axial slice thickness, 120 kV, 100 mAs, reconstruction bone, reconstructed slice 0.6 mm, reconstruction interval 0.6 mm	polyjet (Objet Eden 500V), photopolymer resin	Cuddy 2018
congenital heart disease replicas	CT	MSCT	SLA	Shiraishi 2014

4.2 Reconstruction accuracies for medical models

As Table 2 suggests, preoperative models remain as the most prevalent application category, and varying imaging strategies have been utilized for creation of these models. After the imaging phase, the medical imaging data (normally in DICOM format) is reconstructed into STL models in order to be manufactured using AM. During this, a sequence of technical image operations such as segmentations and filtrations is required. For the part orderer, these operations manifest themselves as a black box, where the input is imaging data and the output are tangible medical models.

In Publication III, a cranial CT scan was utilized as a source data and provided for three distinct institutions – two universities and one company producing medical devices – with a request to create tangible medical models to be utilized preoperatively. No further specifications were given, as this is equivalent level of detail to similar actual orders on preoperative models. At the digital modeling phase, the volume of the largest STL model was almost twice the volume of the smallest model. The triangle count and thus the file size ratios exhibited similar relationships – the most detailed model utilized more than twice the number of

triangles when compared to the model with the smallest triangle count. The relationship between the digital model volume and the triangle count is however not causal: the latter is equally affected by triangulation accuracy.

Table 3. Deviation between digital and physical models in the study.

Model	STL model volume, ratio	Triangle count, ratio	File size, ratio	Physical model weight, ratio	Comments
A	345.3 cm ³ , 1.29	4134001, 1.58	201.8 MB, 1.58	473 g, 1.04	Highest amount of missing inner structures
B	523.2 cm ³ , 1.96	5639111, 2.16	275.3 MB, 2.16	740 g, 1.63	Thickest inner structures
C	266.8 cm ³ , 1.00	2615360, 1.00	127.7 MB, 1.00	453 g, 1.00	Thinner inner structures than in model B

The weights of the manufactured physical models did not deviate as much the digital model volumes; the heaviest skull model was 63% heavier than the lightest model. This suggests that the model B initially contained more inner details, which were, however, not reproduced during the production process. For example, isolated “islands” in the model would either be completely removed prior to production or if produced, being non-attached to the bulk of the model, would be removed during the powder removal process.

Subsequently, the skull models were optically analyzed. The CAD-CAM analysis results presented in Figures 5, 6, and 7 show that models A and C were relatively close to each other, as most of the Procrustes distances between the respective surfaces stayed in the range of ± 0.25 mm and were more prominent only at certain regions (especially the lesion region in the mandible). Model B was significantly larger than the other models, with its surface deviating 1.0 mm or more from those of the models A and C for most of its outer surface.

The above highlights the overall subjectivity and even arbitrariness of a “medical model” when the operator-freedom as well as the effect of technical processes such as algorithmy and software used is relatively large. Especially, as the domain is relatively new and unfamiliar to the non-technically engrossed clinicians, the clinical case specifications need to be properly communicated when medical models are requested from engineers. By study design, the reconstructions were performed individually in separate processes and institutions. In theory, an appropriate Hounsfield unit value for threshold-based segmentation can be trivially chosen based on the literature ranges, but in practice, more operator-level choices and iterations are required due to e.g. partial volume effects and other artifacts in CT. Alternative segmentation techniques such as active contours or level set methods could lead into more robust and traceable processes, yet they demand some user input as well and can exhibit equivalent outcome variation.

Figure 5. Mesh inspection results with deviation between models A and B mapped on the surface of model A. Positive (red) values indicate areas where model B is larger than model A.

Figure 6. Mesh inspection results with deviation between models B and C mapped on the surface of model B. Negative (blue) values indicate areas where model C is smaller than model B. The grey areas were left out of the inspection as model C was cropped and lacked the dental artifacts.

Figure 7. Mesh inspection results with deviation between models A and C mapped on the surface of model A. Positive (red) values indicate areas where model C is larger than model A. The grey areas were left out of the inspection as model C was cropped and lacked the dental artifacts.

4.3 Surface characterization and cytotoxicity of Titanium processed using AM

Electron beam melting and direct metal laser sintering are two common processes available for direct additive manufacturing of patient-specific metal implants. The parts produced using AM processes exhibit significant micro- and macro-level differences when compared to parts processed using traditional manufacturing methods. Fortuitously, the ultimate tensile strength and yield strength can sometimes be increased due to the rapid solidification process. On the other hand, AM parts often exhibit lower fatigue strengths due to material anisotropy and micro-fracturing within the structure. Under external load, stresses typically concentrate at part surfaces and notches, and according to the elastic theory of materials, cracks are most susceptible to initiate and propagate near stress concentrations. In order to reach sufficient fatigue strengths, surface quality of the parts need to be characterized, and either the production process or post-processing steps need to be optimized based on this characterization. Figure 8 presents scanning electron microscopy images from surfaces of control, EBM, and DMLS samples. Surface roughness (Ra) values for as-processed EBM pieces (Ra 29.94) was considerably higher than for DMLS samples (Ra 7.867) – see Table 4. The surface roughness was decreased by polishing the samples, resulting in Ra of 0.085 for EBM and 0.028 for DMLS. Nevertheless, despite largely homogenous microstructures after surface finishing, small surface defect/flare areas remain in the polished samples as can

be seen in Figure 9. The major differences leading to non-identical surface topographies between production processes include the process differences (electron bombing vs. laser-beam-induced local meltpool creation) as well as the initial powder grain distribution – EBM titanium alloy has considerably larger particle diameters.

Table 4. Surface roughness (Ra) of materials processed with EBM and DMLS processes.

Process	Ra	SD
EBM as-processed	29.94	1.721
EBM polished	0.085	0.007
DMLS as-processed	7.867	0.084
DMLS polished	0.028	0.003
control (commercial mandibular plate)	0.491	0.016

Figure 8. SEM images of the surfaces of the as-processed control plate, EBM, and DMLS pieces. Magnified at x500.

All the test pieces produced by additive manufacturing processes were found to be non-cytotoxic, regardless of post-processing steps performed. This implies that surface finishing does not influence cytotoxicity of an implant, but it is in many clinical cases beneficial as it increases the mechanical endurance of the part as well as its aesthetic characteristics.

Figure 9. SEM images of the polished EBM and DMLS discs showing either incomplete solidification or gas pores in form of fractures.

4.4 Computer-assisted possibilities for complex surgeries

Publication IV demonstrates a novel saw-guide like solution for a specific problem related to a complex orthopedic surgery operation. A patient suffering from defects in the femoral condyle was to be treated with a fresh-cadaveric osteochondral allograft surgery. In order to alleviate the proper dimensioning of both the recipient tissue to be sectioned as well as the donor allograft, a digital surgery was designed and performed based on the specifications from responsible surgeon in the operation. Following this, a set of complementary “saw-guide” templates were produced following the required section lines. The templates were designed meshed in order to fulfil the need of the surgeon to see through the objects for verifying proper match with the tissue surfaces. These templates were produced from polyamide (PA) with a selective laser sintering (SLS) device. Additionally, a set of medical models were created with a binder jetting process from starch powder. These models were used preoperatively where the responsible surgeon created pencil markings at regions of interest, as well as intraoperatively sealed in a sterile bag.

The clinical requirements set out at the start of the virtual operation in Publication IV were fulfilled: (1) the defective volume was completely sectioned, while (2) the section volume was minimized to avoid removal of non-defective tissue. Additionally, (3) damages to the intercondyloid fossa and ACL were minimal. Figure 10 shows the design result from the virtual operation – section lines were decided, and complementary set of saw guides (“inside” -version, blue, on Figure 10) were designed. The guides and the preoperative model were designed, produced, and delivered to the hospital within 36 hours of reception of the imaging data.

Feasibility of the design was numerically analyzed by assessing the section volume and surface intactness (defined as the ratio of voxels above segmentation threshold at section surfaces and the total area of the concave hull of those voxels). Figure 11 presents the resulting surface intactness (left axis) and section volume (right axis) values contingent on changing of each of the four

independent design measures. Coincidence with univariable local maxima can be verified visually. Figure 12 presents the results of two-dimensional multivariate plotting of surface intactness contingent on varying two variables at time, while the other two are fixed. The analysis was extended also for 4D case, and globally optimal design dimensions were recovered by iterating possible values over the design space according to the defined cost function F (Eq. 1). The global optimum was at $\mathbf{d}_v = 13.75$ mm, $\mathbf{D}_v = 27.50$ mm, $\mathbf{d}_h = 11.33$ mm, and $\mathbf{D}_h = 22.65$ mm.

Figure 10. The femur after virtual operation (green), and the saw guide (blue).

Figure 11. The section volume and surface intactness plotted contingent on four independent measures; Total allograft dimensions, and orthogonal section lengths. Dotted lines mark the chosen values.

Results

Figure 12. Sensitivity of surface intactness against changes in horizontal and vertical section lengths and total allograft lengths. Blue contours denote regions with surface intactness above 98%, and white lines show the chosen design dimensions.

Figure 13. The surgical procedure and utilization of the saw guides. (a) Cut lines were drawn on cadaver bone using the larger saw guide. (b) The allograft dimensions were verified by fitting the allograft against the larger guide. (c) The section to recipient knee is made, and its dimensions are verified by fitting the smaller saw guide against the bone. (d) Intraoperative native X-ray scan was taken to verify the fit of the allograft.

The fit of the transplanted allograft was excellent, and in the span of the whole surgical procedure, merely one reiteration cycle of drilling-imaging-redrilling was needed. Figure 13d presents an X-ray scan of the knee after the final placement and attachment of the allograft. The post-operative recovery of the patient was excellent. At four months after the surgery, the FOCA transplant was mostly integrated to the surrounding bone tissue. However, the cartilage layer presented some degenerative changes after four months. Dynamic MRI did not show revascularization probably because the MRI estimation was hampered by relatively small volume of the transplant, and titanium fixation screws caused artifacts in the images.

Conventional saw guides and patient-specific implants are commercially available, but no similar template-based solution existed in the market. Nevertheless, the AM parts seemed to substantially facilitate the critical allograft sizing and fitting task even when the surgeons were inexperienced with the exact surgery type. Following similar processes for other non-routine operations suggests potential to both enhance patient treatment outcomes and create cost-savings due to the reduced operating room times. The exact quantification of these effects would require more systematic medical study, which would, however, partly defy the idea of designing highly-customized solutions for non-routine clinical cases.

This semi-automated design process demonstrates how digital surgery planning and virtual operations is transferred into physical world extremely cost-efficiently. Alternative options for bridging the digital and physical world gap include optical and magnetic surgical navigation, and robotic surgery. However, these methods incur considerably higher costs. Design tasks detailed here can be performed with a consumer-level computer, and the sintering of medical grade plastic templates cost in the range of tens of euros.

4.5 Online platform for collaboration and case dissemination

We have previously [Tuomi 2011] classified the medical applications of additive manufacturing into five distinct categories. During this research, we also specified the five-step process containing the steps to achieve clinical applications. By combining these two dimensions, we created a 5-by-5 matrix framework to describe a medical application of AM in a structured way. Within each use case, several different application types are often present, so the framework allows parallel activities. See Figure 14 which presents an example case documented following the created framework: here, the case includes two types of applications (pre/postoperative models and inert implants). After medical imaging, the 3D modeling is performed on both a preoperative model and an implant design. Both applications are then produced using different additive manufacturing processes (here, SLS for preoperative model and DMLS for the implant). The preoperative model is used for surgical planning as-processed, while the implant is inserted only after surface polishing and sterilization tasks.

	Radiology	Computer Science and Design	Mechanical Engineering	Materials Engineering	Clinical Medicine
	Medical Imaging and 3D Digitizing	3D Modeling	Additive Manufacturing	Finishing	Clinical Application
Pre- and Postoperative Models
Medical Aids					
Tools & Instruments					
Inert Implants
Biomanufacturing					

Figure 14. Matrix-based framework combining the five-step process for medical applications of additive manufacturing, and the five recognized application categories. An example case of orbital implant is drawn within the matrix: here, both pre- and postoperative models and directly manufactured implant is combined in a single clinical case.

To enhance the usability of the matrix framework, an online platform and a database for medical applications of AM cases was created. The online platform provides tools to examine previous medical case studies and upload new case studies to the database. The validity and usability of the platform was tested with 8 different case studies. The platform and the database were created using open source content management system and the case content is open for anyone, barring certain details which would compromise the patient anonymity. The website is located at www.medicalam.info, but is as of the printing of this dissertation at hiatus under further development.

5. Discussion

Additive manufacturing is expected to be a transformative force in a multitude of medical and biological applications due to several reasons: First, its unparalleled freedom of design and complexity allow creation of parts traditionally deemed impossible to manufacture. Secondly, by bringing the manufacture options closer to the end-user, the clinicians are not limited to work with the tools currently available to them – instead, with moderate effort, they can design and produce their own. Arguably, large part of the possibilities are still undiscovered, and will rely on the imaginative and open-minded use of the novel techniques in unprecedented approaches. The challenge with full exploitation of these possibilities is the need for extensive cross-disciplinary collaboration between engineering professionals and clinicians, or alternatively, the medical personnel have to be relatively technologically-oriented. Some training and education could be directed towards increasing the AM understanding of clinicians: especially with consumer-level machinery, the actual production step is by no means difficult to grasp. However, given the complexity of current software and required processes to create actually useful results, the most cost-effective task for the non-acquainted would be to inform about the possibilities of AM, and to induce collaboration and communication with the technical experts.

Apart from communicational challenges, certain institutional and legacy barriers can be detected between state-of-the-art and the full materialization of potential described above. Medical imaging modalities and radiological workflows are optimized for traditional imaging objectives, while imaging for AM would normally benefit from higher anatomical accuracy in all three spatial dimensions. When processing these images further, technological expertise is currently required, which necessitates participation from non-clinically trained engineers. However, even with engineers with AM expertise, given identical feasible solution spaces and end objectives, largely varying AM models are produced as was demonstrated in Publication II. For segmentation task, threshold-based approach is popular due to its seeming simplicity (i.e. choosing a single HU value), but it is also inherently arbitrary and requires labor-intensive iteration from the operator. More robust, reliable, and automated image segmentation techniques such as active contours or level sets would be preferable for converting imaging data into digital models to be manufactured. Within recent years, deep learning algorithms and artificial neural networks have shown considerable potential in automated or supervised image segmentation tasks. Due to the scope of this dissertation, these were not

researched in detail, which is a limitation of the current work. During future research, contemporary methods of artificial intelligence and machine learning should be trialed as their methodology could be well suited for resolution of three-dimensional image ambiguity, artifacts, and automated design needs for additive manufacturing.

Currently, when more design operations are required beyond segmentation and reconstruction, the expertise requirements are accentuated: Even when using state-of-the-art software, the design step requires manual labor and extensive knowledge of the techniques. More user-friendly and faster design tools would allow medically-trained personnel to perform design tasks without the aid of dedicated technicians or engineers. Required processes can be largely parametrized, automated, and even numerically optimized based on the patient-specific medical imaging data. Digital surgery planning is currently replacing the traditional preoperative routines. The forthcoming steps can be forecast to be the convergence of digital planning and computational methods with surgical navigation, individual manufacture of case/patient-specific parts, and even fully-robotic surgery.

From production technology perspective, the major issues concerning additive manufacturing and its widespread usability are currently being solved. These include the production speed: in 2015, Hewlett-Packard (HP) introduced their proprietary-patented, polymer-jetting-like production process, and Carbon3D came out with their photopolymeric CLIP technique. Both have promised several-fold enhancements on the build speed. The range and properties of printable materials will also be improved in the near future; especially in metal manufacture, the chamber sizes, device availability, and powder prices are all improving drastically. In the medical environment, biomaterial development is rapidly ongoing, and although the requirement for approvals slow down their emergence, numerous materials are already in the clearance pipeline and it is not unrealistic to expect major breakthroughs on this front. Especially interesting area is the replacement of over-stiff Titanium alloys with biodegradable bone reconstruction materials; however, their strength and endurance need to be further developed to provide adequate mechanical support. In addition, whenever novel biomaterials are developed, additional engineering effort will usually be required in order to ensure their compatibility with AM processes.

Inexpensive material extrusion devices and hobbyist kits have dominated the machinery volumes for a decade. Partly, the combination of early-2010s hype surrounding the field and the unreliability of low-end printers led into disappointment in the techniques and hype backlash. However, the inexpensive extruders have since then been significantly developed both by original engineering efforts and utilization of expiring patents (e.g. Stratasys' build platform temperature control). Currently the techniques have been matured and commercialized enough to be utilized in any hospital setting without need for extensive maintenance and downtime. On the other hand, the investment costs for industrial-tier machinery have also declined sharply, partly due to the low-end competition. International manufacturing networks have also been

established, and most polymer or metal parts can now be promptly and inexpensively procured from a variety of suppliers.

As the technological components required for successful medical applications of additive manufacturing are maturing, the main challenges remain within the technology integration step. There exist companies developing successful products which resolve parts of this challenge, but for large part, these solutions are expensive and do not scale well due to their labor-intensiveness. As these companies are the ones driving innovation, they also rely on their medical partners in order to truly understand clinical needs. Enabling clinicians to partake more actively in the processes would allow innovation more rooted on the actual end-user requirements.

6. Conclusions

Currently, the dimensional accuracies of the most accurate widely-used clinical imaging modalities are in the same range as production accuracies of least accurate AM devices. Thus, resolution maximization is a viable objective when additive manufacturing is used for creation of bone-mimicking, patient-specific models. Accurate capture and positioning of contiguous surfaces should be the main objective, while detection of isolated $<300\mu\text{m}$ features is less important because they fall below the smallest feature sizes producible with most AM processes. Isotropic voxel imaging is preferable as higher slice thickness compared to the in-plane resolution will result in stepped models with reduced functionality.

Computed tomography remains the prevalent imaging modality for capture of hard tissue anatomies. In CT imaging, hard reconstruction kernels should be utilized, and raw imaging data should be provided for reconstruction, design, and manufacture phases to preserve high-frequency image details. Filtration and decimation operations are always possible to perform at the design step, while reverting lossy compression is not. For robust medical model creation processes, careful and traceable choice of imaging and reconstruction parameters is essential as subtle changes to them may easily yield models with two-fold volume differences, as was shown in this dissertation.

When designing patient-specific implants and surgical tools or guides, the anatomical data is usually not directly converted into physical parts. Instead, the models are either manually or automatically processed further, which means that the imaging accuracy is critical mainly at the interface between tissue and the implant. We created a CT-based method for design verification, automation, and optimization in production of tools for complex surgical procedure. An equivalent design was created manually for a surgical fresh osteochondral allograft transplantation operation, and automatically optimized design was shown to exhibit similar or superior performance.

Common AM processes for direct manufacture of Titanium implants include DMLS and EBM. We characterized the surface structures and cytotoxicity of test pieces from both of these processes. As-processed samples demonstrated rough surface structures, especially with the larger-particle EBM alloy. Individual surface defects remained even post polishing operation, indicating potential initiation sites for fracture. Similar phenomena prevail in parts produced using most AM processes: the mechanical endurance is lowered due to the material or production inhomogeneities. Both as-processed and polished samples were found non-cytotoxic. Hence, surface post-processing in implant production is

mainly needed for maximization of aesthetic characteristics and ensuring adequate fatigue life for load-bearing parts.

The five-category classification of medical applications of additive manufacturing was expanded horizontally to also encompass the five required steps along the process workflow: medical imaging, reconstruction and design, manufacturing, post-processing, and application. These two dimensions were combined into a novel matrix-based framework to conceptualize the technical field. Based on this matrix approach, we built and launched an online collaboration platform where medical experts may document and share their clinical additive manufacturing cases, and view those of others users.

References

- Beekman FJ, Vastenhouw B, van der Wilt G. 3-D rat brain phantom for high-resolution molecular imaging. *Proceedings of the IEEE* 2009; 97: 1997–2005.
- Campbell RI, de Beer DJ, Pei E. Additive manufacturing in South Africa: building on the foundations. *Rapid Prototyp J*, 17(2) (2011), pp. 156–162
- Castellano G, Bonilha L, Li LM, Cendes F. Texture analysis of medical images. *Clin Radiol*, 59(12) (2004), pp. 1061–1069
- Chang PS, Parker TH, Patrick Jr CW, Miller MJ. The accuracy of stereolithography in planning craniofacial bone replacement. *J Craniofac Surg*, 14(2) (2003), pp. 164–170
- Chang Y-C, Nicolls F, Spottiswoode BS. Combination of structural and functional MRI with rapid prototyping as a neurosurgical tool. *Proc Int Soc Magn Reson Med*, 19 (2011), pp. 4149–4149
- Chen J, Wang X, Zuo T. The micro fabrication using selective laser sintering micron metal powder. *Proceedings of SPIE - The International Society for Optical Engineering*. Apr (2003)
- Choi JY, Choi JH, Kim NK, Kim Y, Lee JK, Kim MK. Analysis of errors in medical rapid prototyping models. *Int J Oral Maxillofac Surg*, 31(1) (2002), pp. 23–32
- Ciocca L, Fantini M, De Crescenzo F, Corinaldesi G, Scotti R. Direct metal laser sintering (DMLS) of a customized titanium mesh for prosthetically guided bone regeneration of atrophic maxillary arches. *Med & Biol Eng & Comp*, 49(11) (2011), pp. 1347–1352
- Ciocca L, Mazzoni S, Fantini M, Persiani F, Marchetti C, Scotti R. CAD/CAM guided secondary mandibular reconstruction of a discontinuity defect after ablative cancer surgery. *J Craniomaxillofac Surg*, 40(8) (2012), pp. e511–e515
- Cox SC, Thornby JA, Gibbons GJ, Williams MA, Mallick KK. 3D printing of porous hydroxyapatite scaffolds intended for use in bone tissue engineering applications. *Materials Science and Engineering: C*, 47 (2015), pp. 237–247
- De Vos W, Casselman J, Swennen GR. Cone-beam computerized tomography (CBCT) imaging of the oral and maxillofacial region: a systematic review of the literature. *Int J Oral Maxillofac Surg*, 38(6) (2009), pp. 609–625
- Dietrich CA, Scheidegger CE, Schreiner J, Comba JL, Nedel LP, Silva CT. Edge transformations for improving mesh quality of marching cubes. *IEEE Trans Vis Comput Graph*, 15(1) (2009), pp. 150–159
- Edwards SP. Computer-assisted craniomaxillofacial surgery. *Oral Maxillofac Surg Clin North Am*, 22(1) (2010), pp. 117–134
- Eppley BL. Craniofacial reconstruction with computer generated HTR patient-matched implants. Use in primary bony tumour excision. *J Craniofac Surg*, 13(5) (2002), pp. 650–657
- Esses SJ, Berman P, Bloom AI, Sosna J. Clinical applications of physical 3D models derived from MDCT data and created by rapid prototyping. *AJR Am J Roentgenol*, 196(6) (2011), pp. W683–W688
- Exner H, Horn M, Streek A, Ullmann F, Hartwig L, Regenfuß P. Laser micro sintering: A new method to generate metal and ceramic parts of high resolution with sub-micrometer powder. *Virtual and Phys Prototyping*, 3(1) (2008), pp. 3–11

- Fitzwater KL, Marcellin-Little DJ, Harrysson OL, Osborne JA, Poindexter EC. Evaluation of the effect of computed tomography scan protocols and freeform fabrication methods on bone biomodel accuracy. *Am J Vet Res*, 72(9) (2011), pp. 1178–1185
- Gateno J, Xia JJ, Teichgraber JF, Christensen AM, Lemoine JJ, Liebschner MA. Clinical feasibility of computer-aided surgical simulation (CASS) in the treatment of complex cranio-maxillofacial deformities. *J Oral Maxillofac Surg*, 65(4) (2007), pp. 728–734
- Goiato MC, Santos MR, Pesqueira AA, Moreno A, dos Santos DM, Haddad MF. Prototyping for surgical and prosthetic treatment. *J Craniofac Surg*, 22(3) (2011), pp. 914–917
- Govsa F, Asim M, Suzan O, Cenik S, Ahmet E, Alagoz K. Creating vascular models by postprocessing computed tomography angiography images: a guide for anatomical education. *Surg and Radiol Anat*, 39(8) (2017), pp. 905–910
- Hirsch DL, Garfein ES, Christensen AM, Weimer KA, Saddeh PB, Levine JP. Use of computer-aided design and computer-aided manufacturing to produce orthognathically ideal surgical outcomes: a paradigm shift in head and neck reconstruction. *J Oral Maxillofac Surg*, 67(10) (2009), pp. 2115–2122
- Hopkinson N, Dickens P. Analysis of rapid manufacturing – using layer manufacturing processes for production. *Mech Engineering Science*, 217 (2003), pp. 31–39
- Hou JS, Chen M, Pan CB, Wang M, Wang JG, Zhang B. Application of CAD/CAM-assisted technique with surgical treatment in reconstruction of the mandible. *J Craniomaxillofac Surg*, 40(8) (2012), pp. e432–e437
- Hunt DC, Easton H, Caldwell CB. Design and construction of a quality control phantom for SPECT and PET imaging. *Medical Physics*, 36 (2009), pp. 5404–5404
- Ibrahim D, Broilo TL, Heitz C, de Oliveira MG, de Oliveira HW, Nobre SM. Dimensional error of selective laser sintering, three-dimensional printing and PolyJet models in the reproduction of mandibular anatomy. *J Craniomaxillofac Surg*, 37(3) (2009), pp. 167–173
- Inzana JA, Olvera D, Fuller SM, Kelly JP, Graeve OA, Schwarz EM, Kates SL, Awad HA. 3D printing of composite calcium phosphate and collagen scaffolds for bone regeneration. *Biomaterials*, 35(13) (2014), pp. 4026–4034
- Jiao T, Zhang F, Huang X. Design and fabrication of auricular prostheses by CAD/CAM system. *Int J Prosthodont*, 17 (2004), pp. 460–463
- Kamara S. Producing fMRI Compatible Devices using Additive Manufacturing, conference speech, RAPID 2012, Atlanta, GA.
- Karayazgan-Saracoglu B, Gunay Y, Atay A. Fabrication of an auricular prosthesis using computed tomography and rapid prototyping technique. *J Craniofac Surg*, 20 (2009), pp. 1169–1172.
- Kim MS, Hansgen AR, Wink O. Rapid prototyping - a new tool in understanding and treating structural heart disease. *Circulation* 117 (2008), pp. 2388–2394.
- Kim SJ, Park SB, Kim YI, Cho BH, Hwang DS. The reliability of cone-beam computed tomography (CBCT) – generated frontal cephalograms. *J Craniomaxillofac Surg*, 40(8) (2012), pp. e331–e336
- Kontio R, Bjorkstrand. Designing and Additive Manufacturing A Prototype for A Novel Instrument for Mandible Fracture Reduction. *Surgery*, S1:002 (2012)
- Laoui T, Shaik SK. Rapid prototyping techniques used to produce medical models/implants. ISBN: 1-86058-411-X Proceedings of the 4th national conference on rapid and virtual prototyping and applications, Centre for Rapid

- Design and Manufacture, Buckinghamshire Chilterns University College, UK (2003), pp. 23–32
- Lethaus B, Poort L, Böckmann R. Additive manufacturing for microvascular reconstruction of the mandible in 20 patients. *J Oral Maxillofac Surg*, 40 (2012), pp. 43–46
- Leukers B, Güllkan H, Irsen SH, Milz S, Tille C, Schieker M, Seitz H. Hydroxyapatite scaffolds for bone tissue engineering made by 3D printing. *Journal of Materials Science: Materials in Medicine*, 16(12) (2005) pp. 1121–1124
- Levy GN, Schindel R, Kruth JP. Rapid Manufacturing and Rapid Tooling With Layer Manufacturing (Lm) Technologies, State of the Art and Future Perspectives. *CIRP Annals – Manufacturing Technology*, 52(2) (2003), pp. 589–609
- Liacouras P, Garnes J, Roman N. Designing and manufacturing an auricular prosthesis using computed tomography, 3-dimensional photographic imaging, and additive manufacturing: a clinical report. *J Prosthetic Dentistry*, 105 (2011), pp. 78–82.
- Lorensen WE, Cline HE. Marching cubes: A high resolution 3D surface construction algorithm. *SIGGRAPH '87 Proceedings of the 14th annual conference on Computer graphics and interactive techniques*, ACM Press (1987), pp. 163–169
- Mah P, Reeves TE, McDavid WD. Deriving Hounsfield units using grey levels in cone beam computed tomography. *Dentomaxillofac Radiol*, 39(6) (2010), pp. 323–335
- Mangano F, Chambrone L, van Noort R, Miller C, Hatton P, Mangano C. Direct Metal Laser Sintering Titanium Dental Implants: A Review of the Current Literature. *Int J Biomat* (2014)
- Mardini MA, Ercoli C, Graser GN. A technique to produce a mirror-image wax pattern of an ear using rapid prototyping technology. *J Prosthetic Dentistry*, 94 (2005), pp. 195–198
- Markiewicz MR, Bell RB. Modern concepts in computer-assisted craniomaxillofacial reconstruction. *Curr Opin Otolaryngol Head Neck Surg*, 19(4) (2011), pp. 295–301
- Mavili ME, Canter HI, Saglam-Aydinatay B, Kamaci S, Kocadereli I. Use of three-dimensional medical modeling methods for precise planning of orthognathic surgery. *J Craniofac Surg*, 18(4) (2007), pp. 740–747
- Mertens C, Löwenheim H, Hoffmann J. Image data based reconstruction of the midface using a patient-specific implant in combination with a vascularized osteomyocutaneous scapular flap. *J Craniomaxillofac Surg*, 41(3) (2013), pp. 219–225
- Mooney J, Sarwani N, Coleman M, Fotos J. Evaluation of Three-Dimensional Printed Materials for Simulation by Computed Tomography and Ultrasound Imaging. *Simul in Healthcare*, 12(3) (2017), pp. 182–188
- Nelson TR, Bailey MJ. Solid object visualization of 3D ultrasound data. *Proceedings of SPIE* 2000, 3982, pp. 26–34
- Newman Timothy S, Yi H. A survey of the marching cubes algorithm. *Comput Graph*, 30(5) (2006), pp. 854–879
- Orentlicher G, Goldsmith D, Horowitz A. Applications of 3-dimensional virtual computerized tomography technology in oral and maxillofacial surgery: current therapy. *J Oral Maxillofac Surg*, 68(8) (2010), pp. 1933–1959
- Parthasarathy J, Starly B, Raman S, Christensen A. Mechanical evaluation of porous titanium (Ti6Al4V) structures with electron beam melting (EBM). *J Mech Behav Biomed Mater*, 3(3) (2010), pp. 249–259

- Pham DL, Xu C, Prince JL. Current methods in medical image segmentation. *Annu Rev Biomed Eng*, 2 (2000), pp. 315–337
- Poukens J, Laeven P, Beerens M, Nijenhuis G, Sloten JV, Stoelinga P. A classification of cranial implants based on the degree of difficulty in computer design and manufacture. *Int J Med Robot Comput Assist Surg*, 4(1) (2008), pp. 46–50
- Radtke A, Morello S, Muir P, Arnoldy C, Bleedorn J. Application of computed tomography and stereolithography to correct a complex angular and torsional limb deformity in a donkey. *Vet Surg*, 46(8) (2017), pp. 1131–1138
- Reinbacher KE, Wallner J, Kärcher H, Pau M, Quehenberger F, Feichtinger M. Three dimensional comparative measurement of polyurethane milled skull models based on CT and MRI data sets. *J Craniomaxillofac Surg*, 40(8) (2012), pp. e419–e425
- Rengier F, Mehndiratta A, von Tengg-Kobligk H, Zechmann CM, Unterhinninghofen R, Kauczor HU. 3D printing based on imaging data: review of medical applications. *Int J Comput Assist Radiol Surg*, 5(4) (2010), pp. 335–341
- Riesenkampff E, Rietdorf U, Wolf I. The practical clinical value of three-dimensional models of complex congenitally malformed hearts. *J Thorac Cardiovasc Surg*, 138 (2009), pp. 571–580
- Rotaru H, Stan H, Florian IS. Cranioplasty with custom-made implants: analyzing the cases of 10 patients. *J Oral Maxillofac Surg*, 70 (2012), pp. 169–176.
- Rouse S. At the speed of light – additive manufacturing of custom medical implants. *The TCT Mag*, 17(6) (2009), pp. 47–50
- Salmi M, Tuomi J, Paloheimo K-S, Björkstrand R, Paloheimo M, Salo J. Patient specific reconstruction with 3D modeling and DMLS additive manufacturing. *Rapid Prototyp J*, 18(3) (2012), pp. 209–214
- Salmi M, Paloheimo KS, Tuomi J, Ingman T, Mäkitie AA. A digital process for additive manufacturing of occlusal splints: a clinical pilot study. *J R Soc Interface*, 10(84) (2013)
- Santana RR, Lozada J, Kleinman A, Al-Ardah A, Herford A, Chen JW. Accuracy of cone beam computerized tomography and a three-dimensional stereolithographic model in identifying the anterior loop of the mental nerve: a study on cadavers. *J Oral Implantol*, 38(6) (2012), pp. 668–676
- Schievano S, Sebire NJ, Robertson NJ, Taylor AM. Reconstruction of fetal and infant anatomy using rapid prototyping of post-mortem MR images. *Insights Imaging*, 1 (2010), pp. 281–286
- Shapurian T, Damoulis PD, Reiser GM, Griffin TJ, Rand WM. Quantitative evaluation of bone density using the Hounsfield index. *Int J Oral Maxillofac Implants*, 21(2) (2006), pp. 290–297
- Sharma N, Aggarwal LM. Automated medical image segmentation techniques. *J Med Phys*, 35(1) (2010), pp. 3–14
- Shiraishi I, Yamagishi M, Hamaoka K. Simulative operation on congenital heart disease using rubber-like urethane stereolithographic biomodels based on 3D datasets of multislice computed tomography. *Eur J Cardiothorac Surg*, 37 (2010), pp. 302–306
- Silva DN, Gerhardt de Oliveira M, Meurer E, Meurer MI, Lopes da Silva JV, Santa-Bárbara A. Dimensional error in selective laser sintering and 3D-printing of models for craniomaxillary anatomy reconstruction. *J Craniomaxillofac Surg*, 36(8) (2008), pp. 443–449
- Sinn DP, Cillo Jr JE, Miles BA. Stereolithography for craniofacial surgery. *J Craniofac Surg*, 17(5) (2006), pp. 869–875

- Subburaj K, Nair C, Rajesh S. Rapid development of auricular prosthesis using CAD and rapid prototyping technologies. *Int J Oral Maxillofac Surg*, 36 (2007), pp. 938–943
- Sykes LM, Parrott AM, Owen CP. Applications of rapid prototyping technology in maxillofacial prosthetics. *Int J Prosthodont*, 17 (2004), pp. 454–459
- Thesleff T, Lehtimäki K, Niskakangas T. Cranioplasty with adipose-derived stem cells and biomaterial: a novel method for cranial reconstruction. *Neurosurgery*, 68 (2011), pp. 1535–1540
- Turgut G, Sacak B, Kiran K. Use of rapid prototyping in prosthetic auricular restoration. *J Craniofac Surg*, 20 (2009), pp. 321–325
- van Vlijmen OJ, Rangel FA, Bergé SJ, Bronkhorst EM, Becking AG, Kuijpers-Jagtman AM. Measurements on 3D models of human skulls derived from two different cone beam CT scanners. *Clin Oral Investig*, 15(5) (2011), pp. 721–727
- Webb PA. A review of rapid prototyping (RP) techniques in the medical and biomedical sector. *J Med Eng Technol*, 24(4) (2000), pp. 149–153
- Werner H, Dos Santos JRL, Fontes R. Additive manufacturing models of fetuses built from three-dimensional ultrasound, magnetic resonance imaging and computed tomography scan data. *Ultrasound Obstet Gynecol*, 36 (2010), pp. 355–361
- Wouters V, Mollemans W, Schutyser F. Calibrated segmentation of CBCT and CT images for digitization of dental prostheses. *Int J Comput Assist Radiol Surg*, 6(5) (2011), pp. 609–616
- Yamashina A, Tanimoto K, Sutthiprapaporn P, Hayakawa Y. The reliability of computed tomography (CT) values and dimensional measurements of the oropharyngeal region using cone beam CT: comparison with multidetector CT. *Dentomaxillofac Radiol*, 37(5) (2008), pp. 245–251
- Zimmer Y, Tepper R, Akselrod S. A two-dimensional extension of minimum cross entropy thresholding for the segmentation of ultrasound images. *Ultrasound Med Biol*, 22(9) (1996), pp. 1183–1190

Since their inception in the late 80s, additive manufacturing (AM) technologies have contributed largely in the paradigm change of production engineering. A focal area where these processes offer exceptional contemporary applications and future potential is the medical milieu; low production volumes, high degree of customization, and complexity of required shapes are strong drivers leading towards digital fabrication.

ISBN 978-952-60-8363-6 (printed)
ISBN 978-952-60-8364-3 (pdf)
ISSN 1799-4934 (printed)
ISSN 1799-4942 (pdf)

Aalto University
School of Science
Department of Neuroscience and Biomedical Engineering
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**