Low-Temperature Plasma-Enhanced Atomic Layer Deposition of Silicon Dioxide and Aluminum Oxide

---

Zhen Zhu

Low-Temperature Plasma-Enhanced Atomic Layer Deposition of Silicon Dioxide and Aluminum Oxide

Zhen Zhu

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Electrical Engineering, at a public examination held at the lecture hall AS1 of the school on 6 March 2020 at 12 noon.

Aalto University
School of Electrical Engineering
Department of Electronics and Nanoengineering
Electron Physics Group

Supervising professor

Professor Hele Savin, Aalto University School of Electrical Engineering, Finland

Thesis advisor

Professor Hele Savin, Aalto University School of Electrical Engineering, Finland

Preliminary examiners

Professor Shi-Jin Ding, Fudan University, China

Professor Rita Branquinho, Faculty of Science and Technology of NOVA University of Lisbon, Portugal

Opponent

Professor Henrik Pedersen, Linköping University, Sweden

Aalto University publication series

DOCTORAL DISSERTATIONS 235/2019

© 2019 Zhen Zhu

ISBN 978-952-60-8882-2 (printed)

ISBN 978-952-60-8883-9 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-60-8883-9>

Unigrafia Oy

Helsinki 2019

Finland

Author
Zhen Zhu

Name of the doctoral dissertation

Low-Temperature Plasma-Enhanced Atomic Layer Deposition of Silicon Dioxide and Aluminum Oxide

Publisher School of Electrical Engineering

Unit Department of Electronics and Nanoengineering

Series Aalto University publication series DOCTORAL DISSERTATIONS 235/2019

Field of research Semiconductor Technology

Manuscript submitted 10 September 2019

Date of the defence 6 March 2020

Permission for public defence granted (date) 13 November 2019

Language English

☐ **Monograph**

☒ **Article dissertation**

☐ **Essay dissertation**

Abstract

Atomic layer deposition (ALD) is a powerful deposition technique for the fabrication of highly conformal and precise thickness-controlled films. Recently, there has been a growing interest in low-temperature (<100 °C) ALD because of the emerging applications made of organic and polymeric materials, which are known to be thermally sensitive materials. Due to the inherent disadvantages of low-temperature thermal ALD, such as slow reaction rate, long cycle time, poor film density, high impurity level and poor encapsulation properties of ultra-thin films (<5nm), the plasma-enhanced atomic layer deposition (PEALD) becomes an attractive alternative. However, there is only limited data available to show the effect of plasma parameters on film properties at low process temperatures and thus its full potential remains largely unexplored. This thesis presents the process development for low-temperature PEALD SiO₂ and Al₂O₃ aiming to have a deeper understanding of plasma parameters *vs.* film properties.

The work started with a study on PEALD SiO₂ thin film growth, where oxygen and carbon dioxide were used as oxidizing agents. The results showed that process temperature, plasma power and exposure time used in the deposition had a strong impact on the film growth rate as well as the film properties. For example, the growth-per-cycle (GPC) increased from 0.78 to 1.15 Å/cycle with a decrease of process temperature from 200 to 90 °C, plasma power from 300 to 50 W or plasma exposure time from 6 to 3 s, respectively. Although the high growth rate of ALD film is highly desired in the industry, the film quality should not be neglected. As shown in this work, there is a trade-off between the film properties and film growth rate during SiO₂ thin film deposition. In order to balance the throughput and quality of PEALD SiO₂ thin film, the plasma power of 180 W and plasma exposure of 3 s was suggested.

The studied low-temperature ALD Al₂O₃ processes included either O₂-based PEALD or a process that combines H₂O-based thermal ALD with *in-situ* N₂ plasma treatment. For O₂-based PEALD, the moisture barrier properties of Al₂O₃ films were found to be improved with increasing plasma power when the plasma exposure time was relatively short (1 and 3 s). The best water vapor transmission rate of 4-nm thick Al₂O₃ film was 5×10⁻³ gm⁻²day⁻¹. However, a degradation in the moisture barrier properties was observed if the plasma exposure time reached 6 s. This degradation did not occur in the combined process of H₂O-based thermal ALD with *in-situ* N₂ plasma treatment. In addition to the moisture barrier properties of Al₂O₃ thin films, the growth, refractive index, density, roughness and elemental composition were also investigated. Overall, the results demonstrate that with proper PEALD process optimization, it is possible to fabricate high-quality SiO₂ and Al₂O₃ films for thermally sensitive materials/applications.

Keywords Atomic layer deposition, Plasma-enhanced atomic layer deposition, low temperature, Al₂O₃, SiO₂

ISBN (printed) 978-952-60-8882-2

ISBN (pdf) 978-952-60-8883-9

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Helsinki

Location of printing Helsinki **Year** 2019

Pages 100

urn <http://urn.fi/URN:ISBN:978-952-60-8883-9>

Preface

When I was a second-year student of Master program in Department of Micro- and Nanosciences at Helsinki University of Technology (Presently: Aalto University school of electrical engineering) in 2008, I heard a new technology of “atomic layer deposition” in a lecture. Out of curiosity, I did some research on this keyword and noticed that it is a powerful technique of the thin film deposition which was firstly industrialized by Finnish researchers. More following this technology, I become more interested in it and hoped to be a part of this field someday.

Thanks to Beneq Oy, I started my journey in the world of “atomic layer deposition” in 2011. After a few years working as a process specialist in Beneq Oy, I got an opportunity of continuous my scientific research at Aalto University as a part-time student from 2015 to 2019.

The work presented in this thesis has been performed under the supervision of Prof. Hele Savin in the Electron Physics Group of Department of Electronics and Nanoengineering at Aalto University. I wish to express my utmost gratitude toward Prof. Hele Savin who offered excellent guidance to my scientific research during the last years. I would like to thank Dr. Chiara Modanese and Dr. Saousen Merdes for their encouragement, advice and discussion on the scientific publications.

During the years, I have also had a chance to work closely with many experts for thin film characterization, Prof. Marisa Di Sabatino (from Norwegian University of Science and Technology), Dr. Perttu Sippola (from Aalto University school of electrical engineering), Oili M.E. Ylivaara (from VTT Technical Research Centre of Finland Ltd.), Mikko J. Heikkilä (from University of Helsinki) and Dr. Kenichiro Mizohata (from University of Helsinki). I am very grateful for their valuable contributions during my scientific research. Also, I want to acknowledge Prof. Harri Lipsanen, Haibing Huang, Yameng Bao, Dr. Päivikki Repo, Dr. Guillaume von Gastrow, Dr. Iris Mack and Dr. Ville Vähäniemi from Aalto University and Dr. Emma Salmi, Dr. Markus Bosund, Kari Härkönen, Pekka J. Soininen, Ville Malinen, Kalle Niiranen, Mikael Saarniheim, Sami Sneek, Dr. Mikko Söderlund, Dr. Lei Dong, Zhenzi Chen, Rongxu Bai, Chunliang Liu and Sauli Virtanen from Beneq Oy for the warm discussion and support.

I want to thank some of my former colleagues, Shuo Li, Liang Qiao, Jiahua Chang, Jarmo Maula, Olli Jylhä, Prof. Matti Putkonen, Ismo Heikkinen, Heli Seppänen, whom I spent a great deal of time working together.

Finally, I give my heartfelt appreciation to my wife Cuiwen Chen and my lovely daughter Zhixuan (Amy) Zhu for their loving support. Lastly, I thank my parents, Tiansheng Zhu and Shuling Wang, for their love and support throughout my life.

Espoo, 14 July 2019
Zhen Zhu

Contents

Preface	i
Contents.....	iii
List of Publications	v
Author's Contribution.....	vii
List of Abbreviations.....	ix
List of Symbols	xi
1. Introduction	1
2. Atomic Layer Deposition (ALD)	3
2.1 Thermal ALD	4
2.1.1 Temperature window	4
2.1.2 Precursor pulse and purge time	4
2.1.3 Low-temperature thermal ALD.....	5
2.1.4 Thermal ALD reactors	6
2.2 Plasma-enhanced atomic layer deposition (PEALD)	7
2.2.1 Plasma processing	7
2.2.2 Gas discharge.....	7
2.2.3 Surface chemistry of PEALD	10
2.2.4 PEALD reactors	11
3. Experimental.....	13
3.1 Sample fabrication	13
3.1.1 ALD-cycle sequence of SiO_2	14
3.1.2 ALD-cycle sequence of Al_2O_3	14
3.2 Characterization methods.....	14
3.2.1 Ellipsometry	14
3.2.2 X-ray reflectivity.....	15
3.2.3 Thin film stress analysis.....	16
3.2.4 Moisture permeation analysis.....	17
3.2.5 Compositional analysis.....	17

4.	Results and Discussion	21
4.1	PEALD of SiO ₂ : impact of process parameters	21
4.1.1	Plasma power	21
4.1.2	Process temperature	23
4.1.3	Plasma exposure time	25
4.2	Al ₂ O ₃ for encapsulation: O ₂ -based PEALD process.....	26
4.2.1	Film growth and material properties.....	27
4.2.2	Moisture permeation barrier	29
4.3	Al ₂ O ₃ for encapsulation: combined H ₂ O thermal ALD with <i>in-situ</i> N ₂ plasma treatment process	30
4.3.1	Film growth and material properties.....	31
4.3.2	Moisture permeation barrier	34
5.	Summary.....	35
	References	37

List of Publications

This thesis consists of an overview and the following publications which are referred to in the text by their Arabic numerals.

- 1.** Z. Zhu, C. Modanese, P. Sippola, M. Di Sabatino, H. Savin. “Nanometer-scale depth-resolved atomic layer deposited SiO_2 thin films analyzed by glow discharge optical emission spectroscopy”. *Physica Status Solidi A*, 215, 6, 1700864, March 2018.
- 2.** Z. Zhu, P. Sippola, O.M.E. Ylivaara, C. Modanese, M. Di Sabatino, K. Mizohata, S. Merdes, H. Lipsanen, H. Savin. “Low-temperature plasma-enhanced atomic layer deposition of SiO_2 using carbon dioxide”. *Nanoscale Research Letters*, 14, 55, February 2019.
- 3.** Z. Zhu, P. Sippola, H. Lipsanen, H. Savin, S. Merdes. “Influence of plasma parameters on the properties of ultrathin Al_2O_3 films prepared by plasma enhanced atomic layer deposition below 100 °C for moisture barrier applications”. *Japanese Journal of Applied Physics*, 57, 12, 125502, December 2018.
- 4.** Z. Zhu, S. Merdes, O.M.E. Ylivaara, K. Mizohata, M.J. Heikkilä, H. Savin. “ Al_2O_3 thin films prepared by a combined thermal-plasma atomic layer deposition process at low temperature for encapsulation applications”. *Physica Status Solidi A*, 1900237, September 2019.
- 5.** Z. Zhu, E. Salmi, S. Virtanen. “Residual stress study of thin films deposited by atomic layer deposition”. In IEEE conference proceeding. IEEE 12th International Conference on ASIC (ASICON), Guiyang, China, 233-236, 2017.

Author's Contribution

Publication 1: Nanometer-scale depth-resolved atomic layer deposited SiO₂ thin films analyzed by glow discharge optical emission spectroscopy

The author designed the experiments, fabricated the samples and performed the measurements of ellipsometry and spectrometry. The author contributed to the data analysis of rf-GDOES. The author interpreted the majority of the results and wrote the manuscript.

Publication 2: Low-temperature plasma-enhanced atomic layer deposition of SiO₂ using carbon dioxide

The author designed the experiments, fabricated the samples and performed the measurements of ellipsometry and spectrometry. The author contributed to the data analysis of rf-GDOES and ATR-FTIR. The author interpreted the majority of the results and wrote the manuscript.

Publication 3: Influence of plasma parameters on the properties of ultrathin Al₂O₃ films prepared by plasma enhanced atomic layer deposition below 100 °C for moisture barrier applications

The author designed the experiments, fabricated the samples and performed the measurements of ellipsometry and WVTR. The author interpreted the majority of the results and wrote the manuscript.

Publication 4: Al₂O₃ thin films prepared by a combined thermal-plasma atomic layer deposition process at low temperature for encapsulation applications

The author designed the experiments, fabricated the samples and performed the measurements of ellipsometry. The author analyzed and interpreted the results, wrote the manuscript and presented the results in the conference of "EuroCVD 22-Baltic ALD 16".

Publication 5: Residual stress study of thin films deposited by atomic layer deposition

The author designed the experiments, fabricated the samples and performed the measurements of ellipsometry. The author analyzed and interpreted the results, wrote the manuscript and presented the results in IEEE 12th International Conference on ASIC (ASICON).

Additionally, outside the scope of this thesis, the author has contributed to the published work in References [1–4].

List of Abbreviations

ALD	Atomic layer deposition
ATR-FTIR	Attenuated total reflection Fourier transform infrared spectroscopy
BTBAS	Bis(tertiary-butylamino)silane
CCP	Capacitively coupled plasma
CVD	Chemical vapor deposition
DRAMs	Dynamic random-access memories
ERDA	Elastic recoil detection analysis
FTIR	Fourier transform infrared spectroscopy
GD	Glow discharge
GDOES	Glow discharge optical emission spectroscopy
GPC	Growth-per-cycle.
ICP	Inductively coupled plasma
MEMS	Microelectromechanical systems
MOSFET	Metal oxide semiconductor field effect transistors
OES	Optical emission spectrometer
OLED	Organic light-emitting diode
PEALD	Plasma-enhanced atomic layer deposition
PEN	Polyethylene naphthalate
PVD	Physical vapor deposition
RBS	Rutherford backscattering spectrometry
RF	Radio frequency
SIMS	Secondary ion mass spectrometry
TFEL	Thin film electroluminescent

TMA	Trimethylaluminum
TOF-ERDA	Time-of-flight elastic recoil detection analysis
WVTR	Water vapor transmission rate
XPS	X-ray photoelectron spectroscopy
XRR	X-ray reflectivity

List of Symbols

A	Atoms or radicals
A^*	Atoms in an excited state
$A^{+(-)}$	Positive or negative ions
AB	Molecules
e	Electron
Ψ	Amplitude ratio
Δ	Phase difference
Φ	Incident angle of ellipsometer
θ	Critical angle of X-rays incidence during the measurement of X-ray reflectivity
E_s	Elastic modulus of the substrate
N	Number of ALD cycles
R_o	Substrate curvature radius before the film deposition
R_i	Substrate curvature radius after the film deposition
t	Waiting step between the H ₂ O pulse and the N ₂ plasma exposure
t_f	Thickness of ALD thin film
t_s	Thickness of the substrate
V_s	Poisson's ratio of substrate
σ_f	Stress of thin film

1. Introduction

Atomic layer deposition (ALD) is a thin film growth method which can be considered to belong to a subclass of chemical vapor deposition (CVD), and which offers the exceptional advantages in the form of precise film thickness control combined with pinhole free, high uniformity, and conformal film growth.

ALD was invented independently twice by Prof. Aleskovskii and Prof. Suntola in the 1960s and in 1970s, respectively. [5–7] Prof. Tuomo Suntola firstly introduced this thin film growth method to a specific industrial application, namely a flat panel thin film electroluminescent (TFEL) display that was based on ALD processes of ZnS:Mn, Al₂O₃ and TiO₂ films. [7,8] Nowadays, ALD technology has been widely used in the semiconductor applications, *e.g.* high- κ dielectric ALD thin films are used as gate oxides in the metal oxide semiconductor field effect transistors (MOSFET) and capacitor dielectrics in dynamic random-access memories (DRAMs). [8] In the field of microelectromechanical systems (MEMS), ALD also attracts a lot of attention since ALD layers can be utilized as wear resistant, [9] anti-stiction, [10] and insulating [11] coatings to enhance the performance of MEMS components. Moreover, ALD has been successfully adapted to the applications of photonics, [12–14] photovoltaics, [1,2,15] sensors, [16,17] catalysts, [18] and protective coatings. [19,20]

Recently, the request for low-temperature ALD has grown rapidly because of the emerging applications for organic and polymeric materials. For example, during the fabrication of organic light-emitting diodes (OLED) and flexible displays, the process temperature of ALD is often limited to 100 °C as the organic emitter and polymeric substrate do not tolerate higher temperatures. However, conventional low-temperature thermal ALD processes are known to suffer from shortcomings such as a slow reaction rate, long cycle time, poor structural quality and high impurity levels. [21]

To overcome those challenges, plasma-enhanced atomic layer deposition (PEALD) is potentially an advantageous method to grow high-quality ALD films at low temperatures, considering that the surface chemistry involved in the process is driven by the plasma species rather than the thermal energy. This merit of PEALD has recently attracted a lot of attention in the industrial applications, *e.g.* the spacer-defined double-patterning method in DRAM manufacturing and thin film encapsulation for OLED display. [22] In these industrial applications, PEALD offers excellent film uniformity, high throughput and low process temperature < 100 °C. However, the use of plasma species can also lead to complex surface reactions and degradation of films or substrates. [23] Therefore, further

development and optimization of PEALD processes as well as deeper understanding of the PEALD reactions are highly desired.

The two most common ALD oxide materials are SiO_2 and Al_2O_3 which are amorphous and pinhole free. SiO_2 thin films are studied and developed mostly in the field of microelectronics [8,24–26] and optics [27–29] while Al_2O_3 thin films show good performance in the surface passivation of Si-based solar cells, [1,15] as well as in the moisture barrier for encapsulation applications. [30–32] In this thesis, these common ALD films (SiO_2 and Al_2O_3) were selected to study the impact of low-temperature PEALD process parameters on the resulting film properties aiming to broaden the applications of SiO_2 and Al_2O_3 films to thermally sensitive materials.

The structure of this dissertation consists of five chapters. In the following, the principles of the thermal and plasma-enhanced ALD are presented in **Chapter 2**, together with the configurations of different reactors. **Chapter 3** describes the experimental techniques of film growth and characterization utilized in this thesis. In **Chapter 4**, the main results of low-temperature PEALD oxides, such as SiO_2 (reported in **Publication 1** and **2**) and Al_2O_3 (reported in **Publication 3** and **4** as well as **Publication 5**) are summarized. Finally, the conclusion of this thesis is given in **Chapter 5**.

2. Atomic Layer Deposition (ALD)

Atomic layer deposition is a chemical deposition method, closely related to CVD. Unlike to CVD, in ALD the gas phase precursors are not applied to the reactor simultaneously, and thus no gas phase reactions are involved. ALD film growth occurs through sequential self-terminating gas-solid reactions. An example of one ALD-cycle is shown in Figure 1, illustrating the following four steps:

- i. The self-terminating reaction of the first precursor
- ii. Purge to remove the unreacted precursors and by-products
- iii. The self-terminating reaction of the second precursor
- iv. Purge to remove the unreacted precursors and by-products

As a result of one ALD-cycle, one monolayer is formed. By repeating the ALD-cycle, a film with the desired thickness can be grown. This proportional relationship between film thickness and numbers of ALD-cycle is generally expressed as growth-per-cycle (GPC) which can be obtained by

$$GPC = \frac{t_f}{N} \quad (1)$$

where t_f is the thickness of ALD thin films and N is the number of ALD cycles. Moreover, the above four steps are often divided into two “ALD half-cycles”, shown in Fig. 1.

Figure 1. Schematic of one ALD-cycle (a) pulse of the first precursor, (b) purge, (c) pulse of the second precursor and (d) purge. The steps of (a) and (b) can be referred to the “first ALD half-cycle”, while (c) and (d) belong to the “second ALD half-cycle”.

Generally, ALD can be divided into thermal ALD and plasma-enhanced ALD based on the driven energy of surface reactions. For thermal ALD, the substrate

temperature is a key factor since the surface reactions are mainly driven by thermal energy. For plasma-enhanced ALD, the surface chemistry involved in the process is driven by plasma species, which allows more freedom in the process conditions as compared to thermal ALD. [23] More details of thermal and plasma-enhanced ALD are shown below.

2.1 Thermal ALD

In thermal ALD, the surface reactions are driven by the thermal energy. The process temperature, which is also called as substrate temperature, reactor temperature or growth temperature, is one of the most important key parameters for film growth, thus, emphasizing the need for finding a suitable ALD temperature window in process optimization.

2.1.1 Temperature window

For ideal ALD thin film growth, the GPC is independent on the certain process temperature range and remains a constant. In Figure 2, the schematic of the ALD window is presented as well as some non-ALD growth phenomena. When process temperature is lower than the limit of ALD temperature window, the GPC either increases or decreases depending on the condensation or low reactivity of precursors. At temperatures above the ALD window, the precursor decomposition might lead to a CVD component and results in an increase of GPC, whereas the precursor desorption can lead to a decreased GPC.

Figure 2. Schematic of ALD temperature window. Some non-ALD growth phenomena, such as condensation, low-reactivity, decomposition and desorption of precursor, are illustrated as well.

2.1.2 Precursor pulse and purge time

In order to achieve the desired ALD process, each half-reaction has to be irreversible and saturated. Growth saturation ensures the self-limiting growth mechanism of ALD and has a close relationship with precursor pulse time which is shown in Figure 3. When the pulse time of precursor is long enough, the film growth reaches saturation where the GPC remains a constant and is not dependent on the precursor dose. [33] Otherwise, the unsaturated growth occurs because of the insufficient precursor dose.

In addition to the GPC vs. precursor pulse time, Fig. 3 presents the GPC as a function of the precursor purge time. To prevent the co-existence of two precursors, which leads to an undesired CVD-like film growth, a sufficient purge time is required for the residual removal of unreacted precursors, particularly during the low-temperature process. [21]

Figure 3. GPC as a function of precursor pulse and purge time. The insufficient pulse and purge time of precursor lead to the unsaturated and CVD-like growth, respectively.

2.1.3 Low-temperature thermal ALD

In general, thermal ALD processes are conducted at modest temperatures which are often lower than 350 °C. [34] However, for thermal-sensitive materials, such as organic and polymeric materials, the temperature range between room temperature and 100 °C is highly preferred. In order to achieve the requested low-temperature, highly reactive precursors are preferred. For example, trimethylaluminum (TMA) and water enable the growth of Al_2O_3 at room temperature without a significant decline in GPC ($\sim 1.1 \text{ \AA/cycle}$). [21] Furthermore, the use of catalyst is an effective solution to decrease the process temperature of thermal ALD. [35–37]

At low temperature, due to the lack of thermal energy, the precursor reactivity is relatively low compared to the one at high temperature. As reported in an earlier study of low-temperature ALD Al_2O_3 thin films, [38] the reactivity of the first half ALD-cycle is not enough at low temperature, and thus causes an inefficient removal of $-\text{CH}_3$ surface groups. The residual of $-\text{CH}_3$ groups impact on the reaction in the second half ALD-cycle. This persistent negative effect limits the growth of ALD thin films. Another major issue of low-temperature ALD is CVD-like reactions which are caused by the incomplete removal of “precursor A” before the pulse of “precursor B”. Particularly, for the H_2O -based low-temperature thermal ALD, a long purge time of water, which is often in the range of minutes, is requested. [21,39]

2.1.4 Thermal ALD reactors

Thermal ALD reactors can be divided between temporal and spatial-ALD configurations. In the temporal-ALD reactors, as shown in Figure 4 (a) and (b), the substrates are stationary and the precursor delivery is separated in time with inert gas purge step. Contrary to temporal-ALD, in the spatial-ALD reactors (Fig. 4 (c) and (d)) there is a motion or relative-motion of substrates and the precursors are separated in space.

Depending on the throughput, the temporal-ALD reactors can also be divided into the single-substrate reactor (Fig. 4 (a)) and the batch reactor (Fig. 4 (b)). [40,41] For the batch reactor, multiple substrates can be coated in one run. Although the relatively long cycle-time is needed to prevent the CVD components or chemical side-effects, the deposition-speed-per-substrate, defined by the ratio of total ALD process time and the number of substrates, is much higher than the one of the single-substrate reactor. On the other hand, the large volume and complex configuration of the batch reactor have a larger influence on the control of film thickness uniformity, making it more difficult for process optimization.

Instead of separating the precursor pulsing step, Fig. 4 (c) and (d) show that the precursors are continuously and separately delivered into zone A and B in the spatial-ALD reactors. [42,43] In order to expose the substrate to the precursors, the motion or relative-motion of substrates is needed. For instance, when the substrate travels to zone A, the first ALD half-reaction is taking place. After the substrate passes zone B, the full ALD-cycle is done. Therefore, the GPC of thin films is strongly linked to the travelling or relative-travelling speed of the substrate. If the flexible substrates (*i.e.* polymers) are placed in a spatial-ALD reactor (Fig. 4 (d)), this special configuration is often named as “roll-to-roll ALD”. [44,45]

Figure 4. Schematic of the ALD reactors (a) single-substrate reactor, (b) batch reactor, (c) spatial reactor and (d) roll-to-roll reactor.

2.2 Plasma-enhanced atomic layer deposition (PEALD)

2.2.1 Plasma processing

Plasma processing has been widely applied for many industrial applications, *e.g.* plasma ashing for photoresist removal, [46] cleaning for surface contamination, [47,48] surface activation, [49] etching, [50,51] film densification [52,53] and film deposition, which includes physical vapor deposition (PVD) [54,55] and CVD. [56,57]

Plasma-enhanced atomic layer deposition is one of the plasma-based film depositions, belonging to the category of CVD. Compared to thermal ALD, the surface reactions of the second ALD half-cycle during PEALD process are activated in a plasma environment. Figure 5 presents an example of one ALD-cycle for Al_2O_3 growth using PEALD. Due to the involvement of the plasma species, the surface reactions of PEALD are more complex than the ones of thermal ALD. However, plasma enhancement yields to several potential benefits:

- Improved film properties related to film growth, density and impurity level;
- Reduced film deposition temperature without compromising the film quality;
- Decreased ALD cycle time during the low-temperature process;
- Added possibilities of plasma treatments, including pre-treatment, *in-situ* treatment and post-treatment;

Figure 5. A schematic of one ALD-cycle for PEALD Al_2O_3 growth using TMA and O_2 plasma as precursors.

2.2.2 Gas discharge

As mentioned above, the plasma reactions are complex. In order to understand the surface reactions of PEALD, the gas discharges during the process have to be discussed. In this section, the discharges of O_2 (reported in **Publication 1, 3 and 5**), CO_2 (reported in **Publication 2**), H_2O vapor (reported in **Publication 4**), and N_2 (involved in all processes of reported publications) are briefly described.

Plasma is a gas composed of charged species (*i.e.* electrons, negative and positive ions), radicals, atoms and molecules in their neutral and excited states. The

plasma can be created by providing sufficient kinetic energy to gases in order to exceed their ionization potential, *i.e.* 12.07 eV for O₂, [58] 13.78 eV for CO₂, [59] 12.7 eV for H₂O, [59,60] and 15.7 eV for N₂. [58,59] The kinetic energy can be provided by external sources, such as high-frequency electromagnetic fields (radio frequency (RF), microwave), electric fields, lasers, etc. Table 1 shows the main reactions during a plasma discharge.

For the excitation process, electron collision with an atom or molecule can lead to elevation of the electron to a higher energy level but will still orbit the nucleus. In the process of ionization, ions are formed by gain or loss of an electron from an atom or a molecule. When the atom or molecule gains the electron from the electron collision, it becomes a negatively charged ion. Otherwise, it forms positively charged ion due to the loss of the electron. Electron-impact detachment can be important in destroying atomic or molecular negative ions. After the electron collision, the negative charged atom or molecule becomes neutral. During the dissociation process, the AB molecule can be separated into two reactive atoms of A and B by electron collision. The dissociation products A and B are called radicals which have a significant role in the process of PEALD. During the reaction, the dissociation and ionization can appear simultaneously, and thus lead to a dissociative ionization. For dissociative recombination, the electron collision can destroy the positive charged molecular and lead to the productions of an atom with an excited state and a radical. The process of dissociative attachment produces a negative ion as well as a radical due to the collision between the electron and molecular. As shown in Table 1, the charge transfer corresponds to an electron transfer from a neutral particle to a positive ion. If the reaction has no defect of electronic energy, *i.e.* O⁺ to O, it is called a resonant charge transfer; otherwise, it is referred to nonresonant charge transfer, *i.e.* the electron transfer between O⁺ and N has an energy defect of 1 eV.[61]

Table 1. Representative examples of reactions in a plasma discharge. A and B represent atoms or radicals; AB is expressed as molecules; A⁽⁺⁾ and B⁽⁺⁾ are ions (positive or negative); e describes an electron; A^{*} and B^{*} denote atoms in an excited state. [62]

Process	Reaction
Excitation	$A + e \rightarrow A^* + e$
Ionization	$A + e \rightarrow A^+ + 2e$
Electron-impact detachment	$A^- + e \rightarrow A + 2e$
Dissociation	$AB + e \rightarrow A + B + e$
Dissociative ionization	$AB + e \rightarrow A + B^+ + 2e$
Dissociative recombination	$AB^+ + e \rightarrow A + B^*$
Dissociative attachment	$AB + e \rightarrow A + B^-$
Charge transfer	$A^+ + B \rightarrow A + B^+$

Oxygen discharges

In **Publication 1**, 3 and 5, O₂ plasma was used for the growth of SiO₂ and Al₂O₃ thin films, and therefore the examples of reactions in oxygen discharge are listed in Table 2.

Table 2. Examples of reactions in oxygen discharge. [63–66]

Process	Reaction
Excitation	$O + e \rightarrow O^+ + e$
Ionization	$O + e \rightarrow O^+ + 2e$
Electron-impact detachment	$O^- + e \rightarrow O + 2e$
Dissociation	$O_2 + e \rightarrow O + O + e$
Dissociative ionization	$O_2 + e \rightarrow O + O^+ + 2e$
Dissociative recombination	$O_2^+ + e \rightarrow O + O^+$
Dissociative attachment	$O_2 + e \rightarrow O + O^-$
Charge transfer	$O^+ + O_2 \rightarrow O + O_2^+$

Carbon dioxide discharges

In **Publication 2**, CO₂ plasma was used for the growth of SiO₂ thin films, and therefore the examples of reactions in carbon dioxide discharge are listed in Table 3.

Table 3. Examples of reactions in carbon dioxide discharge. [67,68]

Process	Reaction
Excitation	$CO_2 + e \rightarrow CO_2^+ + e$
Ionization	$CO_2 + e \rightarrow CO_2^+ + 2e$
Dissociation	$CO_2 + e \rightarrow CO + O + e$
Dissociative ionization	$CO_2 + e \rightarrow CO + O^+ + 2e$
Dissociative recombination	$CO_2^+ + e \rightarrow CO + O^+$
Dissociative attachment	$CO_2 + e \rightarrow CO + O^-$
Charge transfer	$CO_2 + CO^+ \rightarrow CO_2^+ + CO$

Water discharges

In **Publication 4**, H₂O plasma was involved in the growth of Al₂O₃ thin films, and therefore the examples of reactions in water vapor discharge are listed in Table 4.

Table 4. Examples of reactions in water vapor discharge. [66,69]

Process	Reaction
Excitation	$OH + e \rightarrow OH^+ + e$
Ionization	$OH + e \rightarrow OH^+ + 2e$
Electron-impact detachment	$OH^- + e \rightarrow OH + 2e$
Dissociation	$H_2O + e \rightarrow H + OH + e$
Dissociative ionization	$H_2O + e \rightarrow H^+ + OH + 2e$
Dissociative recombination	$H_2O^+ + e \rightarrow H + OH^+$
Dissociative attachment	$H_2O + e \rightarrow OH^- + H$
Charge transfer	$H^+ + OH \rightarrow OH^+ + H$

Nitrogen discharges

In this work, N₂ was used as the carrier and purge gas for the growth of all mentioned oxide films. Thus, the examples of reactions in nitrogen discharge have to be considered and are listed in Table 5.

Table 5. Examples of reactions in nitrogen discharge. [63,70,71]

Process	Reaction
Excitation	$N_2 + e \rightarrow N_2^+ + e$
Ionization	$N + e \rightarrow N^+ + 2e$
Dissociation	$N_2 + e \rightarrow N + N + e$
Dissociative ionization	$N_2 + e \rightarrow N + N^+ + 2e$
Dissociative recombination	$N_2^+ + e \rightarrow N + N^+$
Charge transfer	$N^+ + N_2 \rightarrow N + N_2^+$

2.2.3 Surface chemistry of PEALD

Silicon dioxide

In this thesis, the bis(tertiary-butylamino)silane (BTBAS) was used as a Si precursor. The O radicals, which can be generated during the O₂ and CO₂ plasma dissociation reactions as shown in Table 2 and 3, dominated ALD surface reactions as the oxidating agents. In this case, the reactions of the first and second ALD half-cycle for SiO₂ thin films reported in **Publication 1** and **2** can be described by:

where only one ($x=1$) or both ($x=2$) of -NH^tBu ligands, which are shown in the reaction of first ALD half-cycle, can react with the surface -OH groups forming *t*-butylamine molecules into the gas phase. [72]

Aluminum oxide

Based on earlier studies, [73] the surface reactions of PEALD Al₂O₃ using TMA (as Al source) and O₂ plasma (as the oxidant) reported in **Publication 3** and **5** can be written as:

Nevertheless, the surface chemistry of the H₂O plasma involved ALD Al₂O₃ process is more complex since both H₂O molecule [74–76] and OH radicals, [77–80] which are generated during H₂O plasma dissociation reactions (in Table 4), can be regarded as oxidants. The reaction of the first ALD half-cycle can be described as Equation (4), while the reaction of the second ALD half-cycle can be considered as a combination of Equation (6) and (7).

2.2.4 PEALD reactors

There are several different reactor configurations for PEALD, which differ from the design of plasma source and the solution of plasma species delivery. Four common PEALD reactor configurations, the radical-enhanced ALD, direct plasma ALD, inductively coupled plasma (ICP) ALD, and capacitively coupled plasma (CCP) ALD, are shown in Figure 6.

In the radical-enhanced ALD (Fig. 6 (a)), the plasma species have to travel through a long distance to reach the substrate. Consequently, many ions and electrons are lost due to their recombination in the delivery path, and only radicals participate in the film deposition process. However, the flux of radicals can also be reduced by recombination reactions. To reach the saturated surface reaction, long plasma exposure is often required. [23]

Figure 6. Schematic of the PEALD reactors. (a) radical-enhanced ALD, (b) direct plasma ALD and remote plasma ALD with (c) ICP and (d) CCP. Reproduced with permission from [23]. Copyright 2011 American Vacuum Society.

In Figure 6 (b), the reactor configuration presents a direct plasma ALD with a CCP setup, containing two planar electrodes. The discharge between the electrodes is driven by the RF source. The upper electrode is typically powered, while the lower one is grounded. The substrate is located on the lower electrode. Depending on the delivery path of plasma gases, the reactor can also be divided into a “shower-flow reactor”, where gases are introduced into the reactor through the powered electrode, and a “cross-flow reactor”, where the gases are introduced from the side of the electrodes.

Remote plasma ALD often integrates an ICP source which is located remotely from the substrate stage (Fig. 6 (c)). In remote plasma ALD, the flux of radicals and ion bombardment can be tuned by the distance between source and substrate as well as the pressure in the reactor. An alternative approach of remote plasma ALD is shown in Figure 6 (d). In this reactor, a grounded mesh plate is placed between two electrodes. This configuration allows plasma radicals to diffuse to the substrate, while it limits the ion energy and flux towards the deposition surface. [23] In this plasma setup, the operating pressure of the ALD process is of the order of 1 hPa. Due to the short distance between the two electrodes, the high power of the plasma generator is not necessary while a few hundred watts can be satisfied. However, there is a drawback of the short distance between two electrodes, which makes the PEALD process of conducting or metal films more complicated than the one in the ICP plasma setup because of the precursor diffusion. In this case, the flow of shower gas and hole size of the mesh plate have to be well controlled and selected.

3. Experimental

This chapter introduces the methods of fabrication and characterization for SiO_2 and Al_2O_3 thin films used by the author of this thesis. The plasma-enhanced atomic layer deposition equipment will be described in **Section 3.1**. In addition to that, the characterization analyses, such as ellipsometry, X-ray reflectivity (XRR), thin film stress analysis, moisture permeation analysis, Fourier transform infrared spectroscopy (FTIR), glow discharge optical emission spectroscopy (GDOES), and time-of-flight elastic recoil detection analysis (TOF-ERDA) used for the publications will be introduced in **Section 3.2**.

3.1 Sample fabrication

The SiO_2 and Al_2O_3 thin films were grown by a commercial Beneq TFS 200 ALD equipped with a capacitively coupled 13.56 MHz RF plasma source. The process temperature was mainly kept at 90 °C. The schematic of the plasma configuration of TFS 200 ALD is shown in Figure 7. The plasma discharge region was above the substrate. A grounded metal grid was located between the plasma discharge and substrate to prevent the plasma damage of the substrate. N_2 was used as a carrier and purge gas with a through reactor flow of 300-600 sccm and a through plasma system flow of 50-200 sccm. During the processes, the pressure in the reactor was about 1 hPa. Furthermore, the container temperature of precursor A and B was set to 21 °C. The precursor was pulsed into the reactor either by own vapor pressure or with 0.1 s N_2 boost (See Figure 8). The sequence of precursor pulse and plasma exposure depended on the selected precursors. The details of ALD-cycle for SiO_2 and Al_2O_3 growth are shown below.

Figure 7. Schematic representation of the remote plasma configuration in Beneq TFS 200 ALD.

3.1.1 ALD-cycle sequence of SiO_2

When BTBAS was used as the precursor A, the N_2 boost was required. O_2 or CO_2 was used as the precursor C with a constant gas flow, the ALD-cycle sequence consists of

precursor A pulse (0.05-0.5 s) -> purge (0.5-3 s) -> plasma on (1-15 s) -> plasma off -> purge (0.5-3 s).

Figure 8. Precursor pulse with (a) own vapor pressure and (b) N_2 boost of 0.1 s.

3.1.2 ALD-cycle sequence of Al_2O_3

For O_2 -based PEALD, TMA and a constant flow of O_2 were introduced into the reactor through precursor A and C, respectively. The ALD-cycle sequence consists of

precursor A pulse (0.2 s) -> purge (3 s) -> plasma on (1-6 s) -> plasma off -> purge (2 s).

For the combined process of thermal-plasma ALD, TMA and H_2O were used as the precursor A and B, respectively. The ALD-cycle sequence consists of

precursor A pulse (0.2 s) -> purge (3 s) -> precursor B pulse (0.15 s) -> plasma on (1-6 s) -> plasma off -> purge (7 s)

or

precursor A pulse (0.2 s) -> purge (3 s) -> precursor B pulse (0.15 s) -> waiting step (0.5-2 s) -> plasma on (6 s) -> plasma off -> purge (7 s).

3.2 Characterization methods

3.2.1 Ellipsometry

Ellipsometry is a powerful method to determine the thickness of thin films with sub-nm scale precision. The instrument of this technique is called an ellipsometer which often consists of the light source, polarizer, compensators, analyzer and detector. As shown in Figure 9, the light beam, which is emitted by a

light source and linearly polarized by a polarizer, passes through a compensator and irradiates the sample. After surface reflection, the light beam passes another compensator and analyzer, then finally falls into the detector. The measurement of ellipsometry is based on the change in polarization which can be represented as an amplitude ratio (Ψ) and the phase difference (Δ). During the data analysis, the calculated values of Ψ and Δ , which match the experimental data best, determine the film optical constants and thickness. [81]

In this thesis, SENTECH SE400adv ellipsometer, which employs a HeNe laser with a wavelength of 632.8 nm at a 70° angle of incidence (Φ), was used to determine the film thickness and reflective index. Furthermore, the thickness uniformity of thin film was obtained by a wafer scan with statistical data.

Figure 9. The schematic of the ellipsometer.

3.2.2 X-ray reflectivity

X-ray reflectivity (XRR) is a contact-free measurement to obtain film information of thickness, density and roughness. The basic idea behind this technique is to measure the intensity of reflected X-rays from the sample when the reflected angle is equal to the incident angle. Philips X'pert Pro diffractometer was used in this thesis, and the schematic of XRR measurement is shown in Figure 10 (a). When the incident angle is above the critical angle θ , the radiation can penetrate the deposited film. Due to the different density of materials, the reflective and refractive conditions for X-ray beams are unique. On the other hand, if the incident angle is below θ , all X-ray beams will be only reflected on the surface. After the data record, a proper simulation has to be done based on the reflectance curve (see Fig. 10 (b)) to extract the information of film thickness (from the spacing of the oscillations), density (from the location of the critical angle) and surface roughness (from the slope of the oscillations). In this thesis, most of the XRR data were simulated with an in-house developed fitting software which is based on Parratt's formalism and Nevot-Croce roughness approximation. [82]

Figure 10. (a) Schematic representation of XRR measurement and (b) the example of the XRR curve.

3.2.3 Thin film stress analysis

Residual stress is often determined together with the wafer curvature measurement [83] and Stoney's equation [84]

$$\sigma_f = -\frac{E_s}{6(1-\nu_s)} \frac{t_s^2}{t_f} \left(\frac{1}{R_1} - \frac{1}{R_0} \right) \quad (8)$$

where σ_f is the thin film stress; E_s is the elastic modulus of the substrate; ν_s is the Poisson's ratio of the substrate; t_s and t_f are the thickness of the substrate and the film, respectively; R_0 and R_1 are the substrate curvature radius measured before and after the film deposition. In order to obtain accurate film stress, the film thickness nonuniformity over the wafer has to be minimized. Moreover, the backside coating of the thin film should also be avoided due to the effect on curvature measurement. In **Publication 2, 4 and 5**, the TOHO FLX-2320-S was used for wafer curvature measurement and the schematic of the measurement is shown in Figure 11. The 150 mm wafers were scanned in two directions of parallel and perpendicular to the wafer flat using a 120-mm scan length.

Figure 11. Schematic representation of wafer curvature measurement to determine thin film stress.

3.2.4 Moisture permeation analysis

Water vapor transmission rate (WVTR) is a key criterion for describing the moisture permeation barrier properties of thin films. Nowadays, the WVTR measurements are typically conducted by either calcium tests based on the optical and electrical methods [85,86] or using a commercial tool. [87,88] In this thesis, a commercial tool of Systech Illinois 7001 water vapor permeation analyzer was used. This analyzer complies with ASTM standard F-1249. [89] For this method, the maximum active test area on the sample is 50 cm^2 and the measurement range is from 0.002 to $18\text{ gm}^{-2}\text{day}^{-1}$ at temperatures of $5\text{--}50\text{ }^{\circ}\text{C}$. The principle of operation is shown in Figure 12. The sample is clamped to a diffusion chamber and a wet N_2 flow is then introduced into the upper half of the chamber while a dry N_2 flows through the lower half chamber. The water molecules diffuse through the sample into the lower chamber and are conveyed to the sensor. Finally, the detected moisture implies WVTR. The WVTR of Al_2O_3 coated Polyethylene naphthalate (PEN) shown in this thesis (**Publication 3** and 4) was measured under the test conditions of $38\text{ }^{\circ}\text{C}$ (for temperature), 90% (for relative humidity) and 50 cm^2 (for detecting area).

Figure 12. Sample test chamber of Systech Illinois 7001 water vapor permeation analyzer.

3.2.5 Compositional analysis

Composition characterization methods for Al_2O_3 and SiO_2 thin films were carried out with FTIR (**Publication 1, 2 and 3**), TOF-ERDA (**Publication 2 and 4**) and GDOES (**Publication 1 and 2**).

Fourier transform infrared spectroscopy

Fourier transform infrared spectroscopy is a qualitative compositional technique used to identify and provide insight into the chemical bonds of the materials. An FTIR instrument, as shown in Figure 13, consists of the IR source, laser, interferometer, sample compartment, and detector. In the ALD community, FTIR has been often used both *in-situ* and *ex-situ* for thin film chemistry analysis due to its three major advantages over a typical dispersive infrared spectrometer, i) Multiplex advantage: this arises from the fact that relevant information corresponding to wavelength can be collected simultaneously; ii) Throughput advantage: there are no slits needed in the FTIR instrument meaning that more energy reaches the sample and improves the signal-to-noise ratio; and iii) Wavelength accuracy advantage: the wavelength scale is calibrated by a controlled laser beam which provides the reference for both precision and accuracy of the infrared spectrometer.

Figure 13. Schematic of a FTIR instrument.

In this thesis, the modified FTIR, attenuated total reflection Fourier transform infrared spectroscopy (ATR-FTIR) was used. The measurements were done by using a Thermo Electron Corporation Nicolet 380 ATR-FTIR spectrometer with a diamond crystal as an internal reflection element. A 2 cm^{-1} resolution over the $500\text{--}4000\text{ cm}^{-1}$ wavenumber range was used.

Time-of-flight elastic recoil detection analysis

Ion beam analysis techniques, Rutherford backscattering spectrometry (RBS) and elastic recoil detection analysis (ERDA), are very useful for the quantitative determination of the elemental composition in materials. Compared to RBS, ERDA is more sensitive for light elements, such as H, N and C, especially for impurity level analysis. However, the drawbacks of ERDA are the depth resolution and mass separation. To improve the performance of ERDA, the configuration based on the time-of-flight detection was developed. [90,91]. This method is called to time-of-flight elastic recoil detection analysis (TOF-ERDA).

In TOF-ERDA, the sample surface is bombarded with high energy ion beams, such as ^{35}Cl , ^{63}Cu , ^{75}Br or ^{127}I . [92] The surface ion collision results in energetic recoils. An energy detector measures the velocity and kinetic energy of recoiled atoms which later can be converted to an elemental depth profile. [93] The SiO_2 and Al_2O_3 thin films in this thesis (**Publication 2** and **4**) were measured by using $40\text{ MeV } ^{75}\text{Br}$ ions which obtained from a 5 MV tandem accelerator with a detection angle of 40° . The schematic of TOF-ERDA is shown in Figure 14.

Figure 14. Schematic of TOF-ERDA setup used for SiO_2 and Al_2O_3 thin film characterization.

Glow discharge optical emission spectroscopy

As the acronym suggests, GDOES is a technique that combines a glow discharge (GD) with an optical emission spectrometer (OES). It is an analysis method which can be used for either qualitative or quantitative measurement depending on the calibration materials. The schematic of GDOES is presented in Figure 15 (a). During the measurement, Ar gas is used as a glow discharge source and delivered through the anode towards the sample. Due to the high direct voltage between the anode and sample, Ar is dissociated into electrons and cations (Ar^+) which are accelerated towards the sample surface due to the high negative potential. Some atoms are ejected from the sample by Ar cations. After the state change of these ejected sample atoms, the emitted light is generated with a characteristic wavelength spectrum, which contributes to the further chemical composition analysis.

GDOES can provide both the depth profile and the bulk elemental composition of solid materials and thin films. Compared to other analytical techniques, such as secondary ion mass spectrometry (SIMS), X-ray photoelectron spectroscopy (XPS) or ERDA, GDOES has the advantage of high sputtering rate and throughput, short specimen preparation time, high analytical depth (several nm to $\sim 100\ \mu\text{m}$) and large analysis area. [94]

In this thesis, the composition analysis of the SiO_2 thin films was done by a Horiba GD-Profilier 2 instrument. A 4-mm diameter anode and RF power of 35 W in the pulsed mode were used. The spectral information was acquired as an intensity *vs* time profile of the characteristic emission line for each element (as shown in Fig. 15 (b)). During the element analysis, the measured emission intensity was integrated over the whole layer thickness, where the time at the SiO_2/Si interface transition was calculated at 50% of the maximum height. Lacking reference samples, the reported values were not calibrated for compositional depth profiling. The element-dependent emission rate was not considered and thus reported intensities of the given element could be compared among different samples, but comparison among different elements was not feasible.

Figure 15. (a) Schematic of GDOES and (b) example of Si and O emission profiles for the low-temperature PEALD SiO_2 with 150 nm thickness. Reproduced with permission from Z. Zhu, C. Modanese, P. Sippola, M. Di Sabatino and H. Savin, *Phys. Status Solidi A*. 215 (2018) 1700864. Copyright 2017 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim.

4. Results and Discussion

4.1 PEALD of SiO₂: impact of process parameters

This section discusses the results from **Publication 1** and 2, where PEALD SiO₂ thin films were prepared by using O₂ plasma and CO₂ plasma as oxidants. The effect of plasma parameters (power and exposure time) on film growth was studied, as well as the effect of the process temperature. Furthermore, the correlation between the film properties of SiO₂ thin films and plasma parameters was investigated.

4.1.1 Plasma power

This section presents the results related to **Publication 1**, where the growth behavior of PEALD SiO₂ thin films grown with BTBAS and O₂ plasma at 90 °C were investigated. In order to study the dependence of the film properties (*i.e.* refractive index, density, composition and residual stress) on plasma power, a fixed plasma exposure time of 1 s was applied.

Figure 16 shows the GPC and refractive index of PEALD SiO₂ thin film as a function of plasma power. The refractive index slightly increased with an increase in plasma power, while there was a negative correlation between plasma power and GPC. Since the cycle number was controlled for all power conditions, the relatively low GPC and high refractive index of films grown with higher plasma power can be attributed to the better film quality, *e.g.* a higher mass density and lower impurity content.

Figure 16. GPC and refractive index of PEALD SiO₂ thin film as a function of plasma power.

As described in **Section 3.2.5**, the measured values from GDOES were not calibrated for compositional depth profiling. Therefore, the elements shown in Figure 17 (a) and (b) can only be compared among different samples, and comparison among different elements is not feasible.

Figure 17. The element composition of 150-nm thick SiO₂ thin films: (a) main contents of Si and O and (b) impurities of H, C and N. Reproduced with permission from Z. Zhu, C. Modanese, P. Sippola, M. Di Sabatino and H. Savin, Phys. Status Solidi A. 215 (2018) 1700864. Copyright 2017 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim.

As shown in Fig. 17 (a), the plasma power does not influence the Si intensity, that is, the possible differences among the SiO₂ matrices do not lead to a significant change in the Si emission rates. Moreover, the intensities of the detected impurities, H, C and N, are presented in Fig. 17 (b). Although the higher emission intensity for C and H at the beginning of the sputtering was a known surface effect, [95] their qualitative evaluation allowed for an analytical comparison between the different samples. The hydrogen content was mostly contributed as OH-groups in the film. [57,96,97] Also, the emission intensity change of H among the three SiO₂ films grown by plasma powers of 50, 180 and 300 W was within the accuracy of the GDOES method, which is estimated to be within $\pm 15\%$. Based on the findings of Si and H, the similar O intensity level among three different samples can be well understood.

There was an identifiable effect of plasma power on the film impurity levels of C and N. The intensity of the analytes seems to decrease when the plasma power was increased to a level of ≥ 180 W. This suggests that the high power can promote the completion of surface reactions while reducing film impurities due to the contribution of plasma enhancement during the ALD process as reported earlier by Langeris *et al.* [73]

During the measurement of GDOES, different sputtering rates of 11.68, 11.11 and 10.98 nm/s were observed for the SiO₂ thin films grown by three power conditions. The results are shown in Figure 18 and as can be seen, there is a strong power dependence. Furthermore, the density of SiO₂ thin films as a function of plasma power is presented in Fig. 18 as well, where the film density increases with power increasing. The observations of lower sputtering rate and higher density were in good agreement, indicating a better film quality when higher plasma power is used for PEALD SiO₂ thin film deposition.

Figure 18. Film sputtering rate during GDOES measurement and density as a function of plasma power used for PEALD SiO₂ thin film deposition.

Residual stress of 50-nm thick SiO₂ films was measured as a function of plasma power and the results are shown in Figure 19. The film stress shifted from the tensile stress of 16 ± 9 MPa to the compressive stress of 87 ± 16 MPa with a plasma power increase from 50 to 300 W. This trend could be credited to the plasma activity, film density and impurity level.

Figure 19. Residual stress of 50-nm thick SiO₂ films as a function of plasma power.

Based on the above results that were made with a fixed plasma exposure time of 1 s, in order to achieve a low-temperature PEALD SiO₂ thin film with the high growth rate (1.46 Å/cycle), low impurity level, high density (2.1 g/cm³) and low compressive residual stress (25 MPa), the plasma power of 180 W is the recommended choice.

4.1.2 Process temperature

This section discusses the results related to **Publication 2**, where the growth behavior of PEALD SiO₂ thin films grown with BTBAS and CO₂ plasma at a temperature range of 90–200 °C were investigated. To the best of the author's

knowledge, this is the first demonstration of SiO₂ thin films grown by CO₂-based PEALD at such low temperatures.

Before the investigation of process temperature effects, the BTBAS pulse and purge time were optimized. During the processes, a fixed plasma power of 180 W, a CO₂ plasma exposure time of 3 s and a CO₂ plasma purge time of 2 s were applied. Figure 20 (a) and (b) show GPC values as a function of BTBAS pulse and purge time at 90 °C, respectively. For the dependence on pulse time, the BTBAS purge time was set to 3 s, whereas for the dependence on purge time, the BTBAS pulse time was set to 0.3 s. During the parameter optimization, a BTBAS pulse time of 0.1 s was found to be sufficient to reach a self-limiting growth with a GPC of 1.15 Å/cycle, however, for the pulse time of 0.3 s, there was an improvement of the film thickness uniformity in SiO₂ films. Furthermore, there is no significant change in GPC shown in Fig. 20 (b), although the purge time was shortened from 3 to 0.5 s. This indicates that the applied short purge time of BTBAS was sufficient to prevent CVD components. Note however that the uniformity of film thickness was improved with increasing purge time. Based on these findings, the pulse and purge time of BTBAS for further investigations was set to 0.3 s and 3 s, respectively.

Figure 20. GPC of SiO₂ thin films as a function of BTBAS (a) pulse time and (b) purge time. The applied plasma power and process temperature were 180 W and 90 °C, respectively.

Figure 21 shows the effect of the process temperature between 90 and 200 °C on the GPC of SiO₂ thin films which were grown with a plasma power of 180 W, a plasma exposure time of 3 s and a plasma purge time of 2 s. There was a clear decrease of GPC from 1.15 to 0.78 Å/cycle with process temperature increasing from 90 to 200 °C. As shown in **Section 2.2.3**, the presence of -OH surface groups plays an important role in ALD surface reactions. Therefore, the decrease of the GPC with increasing temperature can be attributed to the surface-coverage loss of -OH groups due to the thermally activated dehydroxylation reaction. [33,57,98,99] Furthermore, the trend of GPC *vs.* process temperature shown in Fig. 21 is in good agreement with the earlier report from Dingemans *et al.* [57]

Figure 21. GPC of SiO₂ thin films as a function of the process temperature. The applied plasma power, exposure time and purge time were set as 180 W, 3 s and 2 s, respectively.

4.1.3 Plasma exposure time

The plasma exposure time played a dominant role in tuning the film growth and properties in this work. The GPC, density and element composition of PEALD SiO₂ thin films grown at 90°C are presented in Figure 22 (a) and (b). When plasma exposure time increased from 1 to 6 s, an “inverse V” trend of the GPC is shown in Fig. 22 (a). The highest value of 1.15 Å/cycle was obtained in the SiO₂ thin films grown with a plasma exposure time of 3 s. For 6 s plasma exposure, the lowest GPC of 0.98 Å/cycle was observed.

The density of SiO₂ thin films *vs.* the CO₂ plasma exposure time is also shown in Fig. 22 (a). Although the values were within the measurement error margin, the lowest and highest mean values of film density were obtained in SiO₂ thin films grown with an exposure time of 1 and 6 s, respectively. This indicates that the film density slightly increased with an increase in plasma exposure time. The results of film density support the findings of film growth, that GPC dropped at 6 s, and was most likely related to film densification during the long-time plasma exposure.

Figure 22. (a) GPC and density of SiO₂ thin films as a function of plasma exposure time, and (b) qualitative elemental composition of films grown with the plasma time of 1, 3 and 6 s measured by GDOES. The measurement has an accuracy of $\pm 15\%$ and the cross-elemental comparison of the intensities is not possible (no calibration factor is available). The applied process parameters of the process temperature, plasma power and purge time were 90 °C, 180 W, and 2 s, respectively.

The elemental composition of SiO₂ thin films was measured by GDOES. The detected elements of Si, O, H, N and C are shown in Fig. 22 (b). As displayed on the figure, no significant effects of plasma exposure time on the Si, O, and H contents are observed in any of the samples. This finding is similar to the plasma power effects reported in **Section 4.1.1**, where the SiO₂ thin films were prepared by using O₂-based PEALD. For nitrogen, the intensities of the samples prepared by 1 and 3 s CO₂ plasma exposure were rather constant, whereas a lower intensity was measured for the films prepared by a plasma exposure time of 6 s. This suggests that N impurity removal was more effective during the film densification. Note that, independently of sample growth conditions, all the measured samples showed the same intensity for C content. This is most likely due to the surface contamination since the C impurity was not found by the cross-check of TOF-ERDA measurement.

As shown in this study, there was a trade-off between the film growth rate and process temperature. Considering the throughput and quality of PEALD SiO₂ thin film grown at 90 °C, the plasma power of 180 W and the plasma exposure time of 3 s is suggested. Table 6 presents the film properties of PEALD SiO₂ thin film grown under the process condition optimized in this work and the corresponding values reported in the literature. [57]

Table 6. The film properties of PEALD SiO₂ reported in this work with suggested process condition and from a previous study of Dingemans *et al.* [57]

Film properties		This work	Ref. [57]
GPC (Å/cycle)		1.15	1.4
Residual stress (MPa)		30±10 (tensile)	-
Density (g/cm ³)		2.11±0.05	2.0±0.1
Element (at.%)	Si	31.4±1.0	29.1±0.8
	O	66±1.1	61.3±1.5
	H	2.4±0.6	9.6±0.9
	N	0.17±0.05	-
	C	<0.05 ¹	-
O/Al ratio		2.1	2.1

4.2 Al₂O₃ for encapsulation: O₂-based PEALD process

This section discusses the results from **Publication 3**, where the growth behavior of PEALD Al₂O₃ thin films prepared by O₂ plasma at 90 °C with 20% O₂ concentration was investigated. The dependence of the moisture barrier properties on plasma parameters, including power and exposure time, are presented, as well as other film properties, such as refractive index, density and composition. In addition, the same GPC of Al₂O₃ thin films was present in **Publication 5** where the same process conditions were applied.

¹ Below the detection limit of TOF-ERDA

4.2.1 Film growth and material properties

The dependence of the GPC and refractive index of Al_2O_3 thin films on Si substrates as a function of the plasma power is shown in Figure 23 (a) and (b). The film thickness was in the range of 35–50 nm, which was obtained using the same ALD cycle number of 300 for all the samples. The plasma power was varied from 50 to 300 W with three plasma exposure time of 1, 3 and 6 s. As shown in Fig. 23 (a), for 1 s plasma exposure the GPC increases with the increased plasma power and achieves the highest value (1.57 Å/cycle) when power reaches 100 W or more. For the plasma exposure time of 3 and 6 s, the GPC of Al_2O_3 thin films is found to decrease with an increase of plasma power.

Figure 23. (a) GPC and (b) refractive index of Al_2O_3 thin films, for various plasma exposure time, as a function of plasma power.

Fig. 23 (b) shows the refractive index dependence of Al_2O_3 thin films on plasma power and exposure time. As a general observation, the refractive index is found to increase from 1.6 to 1.66 with increasing exposure time. While the highest refractive index was obtained with a plasma exposure time of 6 s, the lowest one was obtained for films grown with an exposure time of 1 s and a power of 50 W. Note that, independently of plasma exposure time, the constant values (within the error margins) were obtained with a plasma power above 100 W.

To study the effect of plasma power on film properties, the plasma exposure time was fixed at 1 s. The film density, surface roughness and chemical composition were carried out by the XRR and ATR-FTIR measurements. In Figure 24, the density and surface roughness of Al_2O_3 thin films as a function of plasma power are shown. Although the rather constant value of $\sim 2.85 \text{ g/cm}^3$ was found for higher powers, the 50 W process led to films with a lower density of 2.6 g/cm^3 . This lower density of Al_2O_3 thin films was most likely caused by the insufficient plasma power that resulted in a shortage of O radicals and therefore led to an incomplete surface reaction. For surface roughness, the highest value of 1.22 nm was obtained for a plasma power of 50 W, while the sub-nanometer roughness was measured for samples grown with the plasma power of 100, 180 and 300 W. In addition, the XRR measurements also revealed the presence of a $\sim 1.3 \text{ nm}$ interfacial layer of silicon oxide in all measured Al_2O_3 thin films except for the thin films grown with a power of 300 W, for which the silicon oxide layer

had a thickness of ~ 0.7 nm. This reduction of SiO_2 interface layer could be caused by the ion bombardment due to the use of the high plasma power.

Figure 24. Plasma power effect on the film density and surface roughness of PEALD Al_2O_3 . The plasma exposure time and O_2 concentration were fixed at 1 s and 20%, respectively.

The effect of plasma power on the chemical composition of Al_2O_3 thin films is shown in Figure 25. The Al-O bond band fingerprint [100,101] of amorphous Al_2O_3 films was found between 525 and 1000 cm^{-1} for all samples. The broad-band features in the 3200-3800 cm^{-1} region can be assigned to the -OH groups. [100,102] Additionally, all spectra showed a strong Si-O mode band at 1107 cm^{-1} , [101] which hints to the presence of an interfacial silicon oxide layer. The spectrum of Al_2O_3 thin films grown with a power of 50 W was unique as it showed that,

- i. There was a more pronounced intensity of the -OH band compared to other samples;
- ii. There was the band overlapping of bending overtone, symmetric and asymmetric stretching vibrations of the C-H groups in the 2870-2980 cm^{-1} range; [102]
- iii. A band of 1239 cm^{-1} was assigned to deformation vibrations of methyl [102,103] and supported the significant presence of $-\text{CH}_x$ species;
- iv. The pronounced band in the region of 1350-1800 cm^{-1} assigned to symmetric and asymmetric stretching modes of OCO molecule structures. [101]

In fact, the strong signals of C-H, O-C-O and -OH groups shown in the thin films grown at 50 W indicate the incomplete gas-solid interactions which can result in high impurities. Consequently, these high-level impurities inhibited the film growth and thus resulted in a low GPC and low refractive index. Unlike to 50 W, the higher power of 100-300 W led to the highest GPC of 1.57 Å/cycle and the better film properties, such as higher refractive index, higher film density and lower impurity levels. Taking into account the highest GPC and improved film quality, the growth saturation of Al_2O_3 thin films could occur when the plasma power of 100 W or more and plasma exposure time of 1 s were applied.

Figure 25. ATR-FTIR transmission spectra with chemical bond assignments of Al_2O_3 thin films prepared by different plasma powers. The plasma exposure time was fixed at 1 s.

For process condition with 1 s plasma exposure, both unsaturated and saturated growth were observed. Compared to 1 s, for a longer exposure time of 3 and 6 s GPC was found to decrease with an increase of power while the refractive index increased. This observation could be correlated to the film densification which is credited by the long-time plasma interaction.

As stated above, there are three specific stages during the PEALD of Al_2O_3 thin films. The first stage, in which the film growth is unsaturated, results in a low GPC and a low refractive index; the second stage, in which the growth saturation of the films occurs, leads to an increase of the GPC and the refractive index; Finally, the third stage, in which densification of the films dominates, leads to decreased GPC while the refractive index remains high.

In general, so-called saturated growth of a thin film is targeted in the ALD process. As shown in Fig. 23 (a), with 1 s plasma exposure, the growth saturation of Al_2O_3 thin films was observed in the samples prepared by higher plasma powers (≥ 100 W). Such conditions have a higher potential to lead to a good moisture permeation barrier performance.

4.2.2 Moisture permeation barrier

Moisture permeation barrier properties of 4-nm thick Al_2O_3 films grown on PEN substrates with varied plasma power and exposure time were investigated. In Figure 26, the uncoated PEN has an initial WVTR of $1.4 \text{ gm}^{-2}\text{day}^{-1}$. The barrier performance was improved over 250 times upon the growth of 4-nm thick Al_2O_3 films. Power of 50W and exposure time of 1 and 3 s led to WVTR of 4.4×10^{-2} and $1.1 \times 10^{-2} \text{ gm}^{-2}\text{day}^{-1}$, respectively. An improvement was observed with the further increase of the plasma power to 100 and 180 W. This improvement can be attributed to the contribution of growth saturation or film densification. With a further increase of the exposure time to 6 s, the barrier performance of the Al_2O_3 thin films prepared with a power of 50 W was further improved. However, samples grown with 100 and 180 W showed a degradation, which is possibly

related to the ion bombardment during the long-time plasma exposure and thus results in the PEN substrate damage as observed for the Si substrate coated sample grown with a power of 300 W.

As shown above, the plasma parameters have a significant influence on the film properties of Al_2O_3 thin films prepared by O_2 -based PEALD. By choosing an appropriate plasma power and exposure time, comparable properties (e.g. WVTR is of the order of $10^{-3} \text{ gm}^{-2}\text{day}^{-1}$) for encapsulation applications are reachable below the critical film thickness of 5 nm. Thus, such thin films could potentially be used as moisture barriers in flexible devices.

Figure 26. WVTR dependence of 4-nm thick Al_2O_3 coated PEN substrates on plasma power and exposure time. These values are compared to the WVTR of an uncoated PEN substrate.

4.3 Al_2O_3 for encapsulation: combined H_2O thermal ALD with *in-situ* N_2 plasma treatment process

This section shows the results of **Publication 4**, where an alternative for preparing Al_2O_3 thin films was introduced. This particular approach is a combined H_2O thermal ALD with *in-situ* N_2 plasma treatment which was used for the encapsulation application. Furthermore, the growth behavior, density, surface roughness, elemental composition and residual stress of 50-nm thick Al_2O_3 thin films on Si wafers were investigated. Figure 27 (a)-(c) show three different process configurations (process-I, process-II and process-III) with a fixed TMA pulse/purge time of 0.2 s/3 s and H_2O pulse time of 7 s.

- Process-I: a standard thermal ALD process for the optimization of H_2O pulse time.
- Process-II: a combined H_2O thermal ALD with *in-situ* N_2 plasma treatment process. Here, the H_2O pulse was immediately followed by the exposure of N_2 plasma for 1 to 6 s before the purge.
- Process-III: similar to the process-II with 6 s N_2 plasma treatment but involved a waiting step ($t=0.5\text{-}2 \text{ s}$) between the H_2O pulse and the N_2 plasma exposure.

During process-I, the plasma generator was kept in the off-mode whereas in the process-II and -III a plasma power of 180 W was used.

Figure 27. Precursor pulse sequences in (a) process-I, (b) process-II and (c) process-III. Reproduced with permission from Z. Zhu, S. Merdes, O.M.E. Ylivaara, K. Mizohata, M.J. Heikkilä and H. Savin, *Phys. Status Solidi A*, (2019) 1900237. Copyright 2019 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim.

4.3.1 Film growth and material properties

To optimize the H₂O dose, the dependence of the pulse time on the GPC and refractive index of the Al₂O₃ thin films was investigated for process-I and the results are shown in Figure 28 (a). The lowest GPC was obtained with an H₂O pulse time of 0.05 s, indicating the shortage of H₂O dose which leads to an unsaturated growth. When the pulse was set to 0.15 s or more, the self-limiting growth with a GPC of 0.84 Å/cycle was achieved. Surprisingly, there was no clear influence of H₂O pulse time on the refractive index despite the H₂O pulse of 0.05 s. The values of the refractive index were found to remain in the range of 1.58-1.6. Based on the trend seen in Fig. 28 (a), the H₂O pulse time was fixed to 0.15 s for the process-II and -III.

Figure 28. GPC and refractive index of the Al_2O_3 thin films as a function of (a) H_2O pulse time in process-I, (b) plasma exposure time in process-II and (c) waiting step in process-III with 6 s plasma exposure. The plasma power of 180 W was used in the combined processes, while the generator was kept in the off-mode during process-I.

The influence of plasma exposure time on the GPC and refractive index of the Al_2O_3 thin films was also studied and is shown in Figure 28 (b). For process-II, the values of GPC and refractive index were higher than the ones (0.84 Å/cycle and 1.59) measured for samples grown by process-I. It can be attributed to the contributions of plasma interaction that the concentration of surface -OH groups could be increased favoring thereby the absorption of aluminum atoms. In this case, the increase in the amount of -OH groups involved in the surface reactions could result in a higher GPC. When plasma exposure time increased from 1 to 6 s, the GPC decreased from 1.44 to 1.28 Å/cycle while the refractive index increased from 1.6 to 1.63, indicating the film densification. For process-III, the effect of the waiting step ($t=0.5$ -2 s) between the H_2O pulse and the N_2 plasma exposure on the GPC and refractive index of the Al_2O_3 thin films was studied. As shown in Figure 28 (c), when the plasma was ignited right after the H_2O pulse ($t=0$ s), the GPC and refractive index of the Al_2O_3 thin films were 1.28 Å/cycle and 1.63, respectively. However, when the samples were exposed to N_2 plasma 0.5 s after the H_2O pulse, the GPC slightly decreased whereas the refractive index remained the same as in the case of $t=0$ s. There were clear changes when the waiting step ≥ 1 s. Both the GPC and refractive index dropped to the same level as the ones obtained from the process-I. This implies that plasma assistance was only efficient when H_2O was involved in the reaction. In this case, the reactions in the process-II would then occur in the following sequences: (1) thermal ALD, and then (2) a hybrid reaction between thermal ALD and H_2O -based PEALD using the residual water from (1). If the residual water is removed by the sufficient purge step (in the case of process-III), there will be a lack of

oxidant source. Indeed, the effect of plasma interaction can be ignored, and no hybrid reaction will be involved during the process.

The film properties of the Al_2O_3 thin films grown with the process-I and -II, such as density, surface roughness, elemental composition and residual stress, are shown in Table 7. The tensile residual stress was found in all measured samples. The highest value of 475 ± 19 MPa was obtained for the process-I. The value was reduced by adding additional plasma assistance. With 1 s plasma exposure, the residual stress of 380 ± 18 MPa was achieved. The value of residual stress further decreased to 160 ± 13 MPa when the plasma exposure time was increased to 6 s.

Table 7. Results of density, roughness, elemental composition and residual stress for 50-nm thick Al_2O_3 films coated on Si wafer.

Film properties		Process-I	Process-II (1 s)	Process-II (6 s)
Tensile residual stress (MPa)		475 ± 19	381 ± 18	160 ± 13
Density (g/cm^3)		2.7	2.7	3.1
Roughness (nm)		0.7	0.6	0.8
Element (at. %)	Al	33.4 ± 0.5	32.2 ± 0.5	36.3 ± 0.5
	O	55.4 ± 0.7	54.1 ± 0.7	59.2 ± 0.7
	H	10.0 ± 1.0	10.1 ± 1.0	3.8 ± 0.6
	C	1.20 ± 0.10	1.60 ± 0.10	0.17 ± 0.04
	N	0^2	2.1 ± 0.10	0.51 ± 0.06
O/Al ratio		1.7	1.7	1.6

During the density modelling, unlike the films grown with thermal ALD, the ones grown by process-II were found to have a structure requiring a bilayer model for simulation. This could be a consequence of the contribution of both H_2O and OH radicals [104] in the oxidation reactions. The process-II with a plasma exposure time of 1 s gave a film density of $2.7 \text{ g}/\text{cm}^3$, which was in the same range as for films grown with process-I. When plasma exposure time was increased to 6 s, the film density increased to $3.1 \text{ g}/\text{cm}^3$. This density improvement reflects the film densification and is in good agreement with the trend of the refractive index shown in Fig. 28 (b). Moreover, there was no clear roughness difference among measured samples and the values were in the range of 0.6–0.8 nm.

The elemental composition of the films was carried out using TOF-ERDA. Al, O, H and C were detected in all samples from process-I and -II, while nitrogen was only observed in the films grown with the process-II. The presence of N can be attributed to the formation of unstable surface N-species during plasma exposure in a N_2 environment. [105] This “N-contamination” effect could be simply avoided by using argon as a carrier gas. Except for the N impurity, H and C impurities were nearly the same for process-I and process-II with 1 s plasma exposure. Compared to the process-II with 1 s plasma exposure, the Al_2O_3 thin films grown with a plasma exposure time of 6 s had much lower concentrations of H, C and N, indicating the effective impurity removal of long-time plasma

² Below the detection limit of TOF-ERDA

exposure. The reduction of H contents in process-II with 6 s plasma exposure also reveals that the amount of unreacted -OH groups in the film was relatively low. Indeed, this low presence of -OH groups led to O/Al ratio closer to the stoichiometric value of 1.5.

4.3.2 Moisture permeation barrier

Figure 29 shows the comparative study of the WVTR for H₂O thermal ALD (process-I), combined H₂O thermal ALD with *in-situ* N₂ plasma treatment (process-II) and O₂ plasma-enhanced ALD (presented earlier in **Section 4.2.2**). Compared to uncoated PEN, there was no clear improvement of moisture barrier properties for 4-nm thick Al₂O₃ coated substrates, which were prepared by process-I. For process-II with a plasma exposure time of 1 s, the film showed a WVTR of 0.08 gm⁻²day⁻¹, which was more than fifteen-times lower than the one obtained from the sample prepared with the thermal ALD. With further increase of the plasma exposure time to 6 s, the barrier performance of the sample was improved significantly, leading to a WVTR of 2.9×10⁻³ gm⁻²day⁻¹. While for a plasma exposure time of 1 s, the WVTR of samples grown with process-II was higher than the one reported for O₂-based PEALD (7.1×10⁻³ gm⁻²day⁻¹), the best barrier performance was achieved with the process-II using a plasma exposure time of 6 s. This suggests that the substrate damage by ion bombardment during the combined H₂O thermal ALD with *in-situ* N₂ plasma treatment process is negligible, which makes the process gentler and more suitable for sensitive substrates.

Figure 29. Comparative study of the WVTR for H₂O thermal ALD (process-I), combined H₂O thermal ALD with *in-situ* N₂ plasma treatment (process-II) and O₂-based PEALD. Reproduced with permission from Z. Zhu, S. Merdes, O.M.E. Ylivaara, K. Mizohata, M.J. Heikkilä and H. Savin, Phys. Status Solidi A. (2019) 1900237. Copyright 2019 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim.

5. Summary

In this thesis, material properties of low-temperature PEALD SiO_2 and Al_2O_3 thin films were studied and related process optimization was carried out. A special emphasis was placed on the effect of plasma parameters, such as power and exposure time, on film growth as well as resulting structural, compositional, mechanical and moisture permeation barrier properties of the films.

Firstly, O_2 -based PEALD SiO_2 processes, which focused on the plasma power effect on the elemental composition of SiO_2 thin films, were demonstrated. GDOES measurements were used as a primary analysis method. This technique provides the possibility to measure the elemental composition along the film depth with the high-enough resolution. The results indicated that the concentration of C and N impurities decreased with increasing plasma power. In addition to elemental composition, the GDOES was used to evaluate the film density. The sputtering rate implied that the film density increased with the increase of plasma power. The results thus suggest that if high quality film is needed, the plasma power should be set to as high as possible within the limits of plasma damage toleration of the substrate.

Secondly, the study of low-temperature PEALD SiO_2 process using CO_2 as an oxidant was presented in this thesis. To the best of the author's knowledge, this is the first demonstration of SiO_2 thin films grown by CO_2 -based PEALD at 90° . The variation of GPC was observed when plasma exposure time increased from 1 to 6 s. However, a relatively high film quality, such as high density and low impurity levels, was obtained with a longer exposure time. More specifically, it was shown that the film densification appeared with 6 s plasma exposure. In addition to the effect of plasma exposure time, the effect of process temperature on film growth was investigated as well. Due to the dehydroxylation reaction, the GPC of SiO_2 thin films decreased with increasing process temperature.

Thirdly, the studies of PEALD Al_2O_3 growth based on O_2 plasma were carried out. In addition to the film growth of Al_2O_3 , the effect of both plasma power and exposure time on film properties were studied. As the highlight of this study, three specific stages during PEALD Al_2O_3 growth were found: i) the film growth is unsaturated, which results in a low GPC and a low refractive index; ii) the growth saturation, which leads to an increase of the GPC and the refractive index; and iii) densification of the film dominates, which leads to decreased GPC while the refractive index remains high. In addition, a WVRT of $5 \times 10^{-3} \text{ gm}^{-2}\text{day}^{-1}$ was obtained for PEN substrates coated with 4-nm thick Al_2O_3 films.

Nevertheless, due to the ion bombardment, a degradation of barrier performance was found in the samples which were prepared using a long-time plasma exposure.

To retain the good barrier performance and minimize or eliminate the degradation, the other alternative for preparing Al_2O_3 thin films was finally introduced and a combined H_2O thermal ALD with *in-situ* N_2 plasma treatment process was investigated. WVTR measurements of PEN substrates coated with 4-nm thick Al_2O_3 films showed that the proposed combined process is likely to be gentler than the O_2 -based PEALD and therefore is more suitable for sensitive substrates. The best WVTR result of $2.9 \times 10^{-3} \text{ gm}^{-2}\text{day}^{-1}$ was obtained in the combined H_2O thermal ALD with a 6 s *in-situ* N_2 plasma treatment process. Moreover, with the contribution of plasma assistance, the Al_2O_3 thin films achieved a high density of $\sim 3.1 \text{ g/cm}^3$, a low tensile residual stress of $\sim 160 \text{ MPa}$ and low impurity levels of ~ 3.8 , ~ 0.17 and $\sim 0.51 \text{ at.}\%$ for hydrogen, carbon and nitrogen, respectively.

To conclude, the research on low-temperature PEALD of SiO_2 and Al_2O_3 processes indicates that the plasma parameters play a key role in fine-tuning and finding the optimal thin film properties. While the thesis has increased basic understanding of the plasma processes in ALD, the results are also directly applicable to the applications that use thermally sensitive materials. Therefore, in the next step, it will be interesting to apply the developed processes into device fabrication.

References

- [1] Y. Bao, H. Huang, Z. Zhu, J. Lv, and H. Savin, "Silicon surface passivation by mixed aluminum precursors in Al_2O_3 atomic layer deposition", *Energy Procedia*, vol. 92, pp. 304–308, 2016.
- [2] H. Huang, C. Modanese, S. Sun, G. von Gastrow, J. Wang, T.P. Pasanen, S. Li, L. Wang, Y. Bao, Z. Zhu, S. Sneck, and H. Savin, "Effective passivation of p^+ and n^+ emitters using $\text{SiO}_2/\text{Al}_2\text{O}_3/\text{SiN}_x$ stacks: Surface passivation mechanisms and application to industrial p-PERT bifacial Si solar cells", *Solar Energy Materials and Solar Cells*, vol. 186, pp. 356–364, 2018.
- [3] Z. Chen, Z. Zhu, K. Härkönen, and E. Salmi, "Batch processing of aluminum nitride by atomic layer deposition from AlCl_3 and NH_3 ", *Journal of Vacuum Science & Technology A: Vacuum, Surfaces, and Films*, vol. 37, p. 020925, 2019.
- [4] Z. Zhu, E. Østreg, I. Tuoriniemi, Z. Chen, K. Niiranen, and S. Sneck, "Batch atomic layer deposition of aluminum nitride for RF-MEMS and GaN power-devices", in: China Semiconductor Technology International Conference (CSTIC), Shanghai, China, 2019.
- [5] V.B. Aleskovskii, "Chemistry and technology of solids", *Zhurnal Obs. Khimii*, vol. 47, pp. 2145–2157, 1974.
- [6] T. Suntola and J. Antson, "Method for producing compound thin films", Nov. 15 1977, US Patent 4058430.
- [7] R.L. Puurunen, "A short history of atomic layer deposition : Tuomo Suntola's atomic layer epitaxy", *Chemical Vapor Deposition*, vol. 20, pp. 332–344, 2014.
- [8] M. Ritala and J. Niinistö, "Industrial applications of atomic layer deposition", *ECS Transactions*, vol. 25, pp. 641–652, 2009.
- [9] T.M. Mayer, J.W. Elam, S.M. George, P.G. Kotula, and R.S. Goeke, "Atomic-layer deposition of wear-resistant coatings for microelectromechanical devices", *Applied Physics Letter*, vol. 82, no. 17, p. 2883–2885, 2003.
- [10] N.D. Hoivik, J.W. Elam, R.J. Linderman, V.M. Bright, S.M. George, and Y.C. Lee, "Atomic layer deposited protective coatings for micro-electromechanical systems", *Sensors and Actuators A*, vol. 103, pp. 100–108, 2003.
- [11] J. Kynäräinen, J. Saarilahti, H. Kattelus, T. Meinander, M. Suhonen, A. Oja, H. Seppä, P. Pekko, H. Kuisma, S. Ruotsalainen, and M. Tilli, "3D micromechanical compass", *Sensor Letters*, vol. 5, no. 1, pp. 126–129, 2007.
- [12] K. Solehmainen, M. Kapulainen, P. Heimala, and K. Polamo, "Erbium-doped waveguides fabricated with atomic layer deposition method", *IEEE Photonics Technology Letter*, vol. 16, no. 1, pp. 194–196, 2004.
- [13] S. Shestaeva, A. Bingel, P. Munzert, L. Ghazaryan, C. Patzig, A. Tünnermann, and A. Szeghalmi, "Mechanical, structural, and optical properties of PEALD metallic oxides for optical applications", *Applied Optics*, vol. 56, no. 4, pp. C47–C59, 2017.
- [14] C. Kauppinen, K. Isakov, and M. Sopanen, "Grass-like alumina with low refractive index for scalable, broadband, omnidirectional antireflection coatings on glass using atomic layer deposition", *ACS Applied Materials & Interfaces*, vol. 9, pp. 15038–15043, 2017.
- [15] H. Savin, P. Repo, G. von Gastrow, P. Ortega, E. Calle, M. Garín, and R. Alcubilla, "Black silicon solar cells with interdigitated back-contacts achieve 22.1% efficiency", *Nature Nanotechnology*, vol. 10, pp. 624–629, 2015.

- [16] Y.W. Kim, S.E. Sardari, M.T. Meyer, A.A. Iliadis, H.C. Wu, W.E. Bentley, and R. Ghodssi, "An ALD aluminum oxide passivated surface acoustic wave sensor for early biofilm detection", *Sensors and Actuators B: Chemical*, vol. 163, pp. 136–145, 2012.
- [17] A. Purniawan, P.J. French, G. Pandraud, and P.M. Sarro, "TiO₂ ALD nanolayer as evanescent waveguide for biomedical sensor applications", *Procedia Engineering*, vol. 5, pp. 1131–1135, 2010.
- [18] B.J. O'Neill, D.H.K. Jackson, J. Lee, C. Canlas, P.C. Stair, C.L. Marshall, J.W. Elam, T.F. Kuech, J.A. Dumesic, and G.W. Huber, "Catalyst design with atomic layer deposition", *ACS Catalysis*, vol. 5, pp. 1804–1825, 2015.
- [19] B. Díaz, E. Härkönen, J. Światowska, V. Maurice, A. Seyeux, P. Marcus, and M. Ritala, "Low-temperature atomic layer deposition of Al₂O₃ thin coatings for corrosion protection of steel: Surface and electrochemical analysis", *Corrosion Science*, vol. 53, pp. 2168–2175, 2011.
- [20] E. Härkönen, I. Kolev, B. Díaz, J. Światowska, V. Maurice, A. Seyeux, P. Marcus, M. Fenker, L. Toth, G. Radnoczi, M. Vehkamäki, and M. Ritala, "Sealing of hard CrN and DLC coatings with atomic layer deposition", *ACS Applied Materials & Interfaces*, vol. 6, pp. 1893–1901, 2014.
- [21] M.D. Groner, F.H. Fabreguette, J.W. Elam, and S.M. George, "Low-temperature Al₂O₃ atomic layer deposition", *Chemistry of Materials*, vol. 16, pp. 639–645, 2014.
- [22] I.J. Raaijmakers, "Current and future applications of ALD in Micro-electronics", *ECS Transactions*, vol. 41, no. 2, pp. 3–17, 2011.
- [23] H.B. Profijt, S.E. Potts, M.C.M. van de Sanden, and W.M.M. Kessels, "Plasma-assisted atomic layer deposition: basics, opportunities, and challenges", *Journal of Vacuum Science & Technology A: Vacuum, Surfaces, and Films*, vol. 29, p. 050801, 2011.
- [24] D. James, "From strain to high-K/metal gate - The 65-45 nm transition", in: *Advanced Semiconductor Manufacturing Conference*, Cambridge, MA, USA, 2008.
- [25] D. Hiller, R. Zierold, J. Bachmann, M. Alexe, Y. Yang, J.W. Gerlach, A. Stesmans, M. Jivanescu, U. Müller, J. Vogt, H. Hilmer, P. Löper, M. Künle, F. Munnik, K. Nielsch, and M. Zacharias, "Low temperature silicon dioxide by thermal atomic layer deposition: Investigation of material properties", *Journal of Applied Physics*, vol. 107, p. 064314, 2010.
- [26] S. Siddiqui, M.M. Chowdhury, M.J. Brodsky, N. Rahim, M. Dai, S. Krishnan, S. Fugardi, E. Wu, A. Chou, S. Narasimha, J. Li, K. Mcstay, B. Linder, E. Maciejewski, R. Rettmann, S. Mittl, U. Kwon, V. Narayanan, W. Henson, D. Schepis, and M. Chudzik, "Deposited ALD SiO₂ high-k/metal gate interface for high voltage analog and I/O devices on next generation alternative channels and FINFET device structures", *ECS Transactions*, vol. 53, no. 3, pp. 137–146, 2013.
- [27] K. Pfeiffer, S. Shestaeva, A. Bingel, P. Munzert, L. Ghazaryan, C. van Helvoirt, W.M.M. Kessels, U.T. Sanli, C. Grévent, G. Schütz, M. Putkonen, I. Buchanan, L. Jensen, D. Ristau, A. Tünnermann, and A. Szeghalmi, "Comparative study of ALD SiO₂ thin films for optical applications", *Optical Materials Express*, vol. 6, no. 2, pp. 660–670, 2016.
- [28] K. Pfeiffer, U. Schulz, A. Tünnermann, and A. Szeghalmi, "Ta₂O₅/Al₂O₃/SiO₂ - antireflective coating for non-planar optical surfaces by atomic layer deposition", in: *Advanced Fabrication Technologies for Micro/Nano Optics and Photonics X*, San Francisco, California, United States, 2017.
- [29] T. Weiss and W. Ebert, "Atomic Layer Deposition for Coating of Complex 3D Optics", *Optik&Photonik*, vol. 3, pp. 42–45, 2017.
- [30] S.-H.K. Park, J. Oh, C.-S. Hwang, J.-I. Lee, Y.S. Yang, and H.Y. Chu, "Ultrathin film encapsulation of an OLED by ALD", *Electrochemical and Solid-State Letters*, vol. 8, no. 2, pp. H21–H23, 2005.
- [31] M.D. Groner, S.M. George, R.S. McLean, and P.F. Carcia, "Gas diffusion barriers on polymers using Al₂O₃ atomic layer deposition", *Applied Physics Letters*, vol. 88, pp. 051907, 2006.
- [32] P.F. Carcia, R.S. McLean, and S. Hegedus, "Encapsulation of Cu(InGa)Se₂ solar

- cell with Al₂O₃ thin-film moisture barrier grown by atomic layer deposition", *Solar Energy Materials & Solar Cells*, vol. 94, pp. 2375–2378, 2010.
- [33] R.L. Puurunen, "Surface chemistry of atomic layer deposition: A case study for the trimethylaluminum/water process", *Journal of Applied Physics*, vol. 97, p. 121301, 2005.
- [34] R.W. Johnson, A. Hultqvist, and S.F. Bent, "A brief review of atomic layer deposition: From fundamentals to applications", *Materials Today*, vol. 17, no. 5, pp. 236–246, 2014.
- [35] J.W. Klaus, O. Sneh, and S.M. George, "Growth of SiO₂ at room temperature with the use of catalyzed sequential half-reactions", *Science*, vol. 278, pp. 1934–1936, 1997.
- [36] J.W. Klaus and S.M. George, "Atomic layer deposition of SiO₂ at room temperature using NH₃-catalyzed sequential surface reactions", *Surface Science*, vol. 447, pp. 81–90, 2000.
- [37] J.D. Ferguson, E.R. Smith, A.W. Weimer, and S.M. George, "ALD of SiO₂ at room temperature using TEOS and H₂O with NH₃ as the catalyst", *Journal of The Electrochemical Society*, vol. 151, no. 8, pp. G528–G535, 2004.
- [38] V. Vandalon and W.M.M. Kessels, "What is limiting low-temperature atomic layer deposition of Al₂O₃? A vibrational sum-frequency generation study", *Applied Physics Letters*, vol. 108, p. 011607, 2016.
- [39] T. Nam, J.-M. Kim, M.-K. Kim, and H. Kim, "Low-temperature atomic layer deposition of TiO₂, Al₂O₃, and ZnO thin films", *Journal of the Korean Physical Society*, vol. 59, no. 2, pp. 452–457, 2011.
- [40] M.G. Steven, "Atomic layer deposition: an overview", *Chemical Reviews*, vol. 110, no. 1, pp. 111–131, 2010.
- [41] K.E. Elers, T. Blomberg, M. Peussa, B. Aitchison, S. Haukka, and S. Marcus, "Film uniformity in atomic layer deposition", *Chemical Vapor Deposition*, vol. 12, pp. 13–24, 2006.
- [42] D.H. Levy, D. Freeman, S.F. Nelson, P.J. Cowdery-Corvan, and L.M. Irving, "Stable ZnO thin film transistors by fast open air atomic layer deposition", *Applied Physics Letters*, vol. 92, p. 192101, 2008.
- [43] I.T.S. Heikkinen, P. Repo, V. Vähänissi, T. Pasanen, V. Malinen, and H. Savin, "Efficient surface passivation of black silicon using spatial atomic layer deposition", *Energy Procedia*, vol. 124, pp. 282–287, 2017.
- [44] P.S. Maydannik, T.O. Kääriäinen, and D.C. Cameron, "An atomic layer deposition process for moving flexible substrates", *Chemical Engineering Journal*, vol. 171, pp. 345–349, 2011.
- [45] P.S. Maydannik, T.O. Kääriäinen, K. Lahtinen, M. David C. Cameron, M. Söderlund, S. Pekka, P. Johansson, L. Jurkka Kuusipalo, L. Moro, and X. Zeng, "Roll-to-roll atomic layer deposition process for flexible electronics encapsulation applications", *Journal of Vacuum Science & Technology A: Vacuum, Surfaces, and Films*, vol. 32, p. 051603, 2014.
- [46] C. Waldfried, I. Berry, O. Escorcia, H. Qingyuan, and P. Sakthivel, "Plasma ashing process", Oct. 7 2003, US Patent 6630406.
- [47] D.F. O'Kane and K.L. Mittal, "Plasma cleaning of metal surfaces", *Journal of Vacuum Science & Technology*, vol. 11, no. 3, pp. 567–569, 1974.
- [48] W. Petasch, B. Kegel, H. Schmid, K. Lendenmann, and H.U. Keller, "Low-pressure plasma cleaning: a process for precision cleaning applications", *Surface and Coatings Technology*, vol. 97, pp. 176–181, 1997.
- [49] T. Suni, K. Henttinen, I. Suni, and J. Mäkinen, "Effects of plasma activation on hydrophilic bonding of Si and SiO₂", *Journal of The Electrochemical Society*, vol. 149, no. 6, pp. G348–G351, 2002.
- [50] S. Tachi, K. Tsujimoto, and S. Okudaira, "Low-temperature reactive ion etching and microwave plasma etching of silicon", *Applied Physics Letters*, vol. 52, no. 8, pp. 616–618, 1988.
- [51] C.J. Mogab, A.C. Adams, and D.L. Flamm, "Plasma etching of Si and SiO₂- The effect of oxygen additions to CF₄ plasmas", *Journal of Applied Physics*, vol. 49, no. 7, pp. 3796–3803, 1978.
- [52] S. Lee and J.-W. Park, "Effect of oxygen post plasma treatment on characteristics of electron cyclotron resonance CVD fluorine-doped silicon

- dioxide films using SiF_4 and O_2 gas sources", *Journal of The Electrochemical Society*, vol. 146, no. 2, pp. 697–701, 1999.
- [53] Y. Kim, H.J. Kim, J.Y. Kim, and Y. Lee, "Passivation effect on low-k SiOC dielectrics by H_2 plasma treatment", *Journal of the Korean Physical Society*, vol. 40, no. 1, pp. 94–98, 2002.
- [54] T. Minami, S. Ida, and T. Miyata, "High rate deposition of transparent conducting oxide thin films by vacuum arc plasma evaporation", *Thin Solid Films*, vol. 416, pp. 92–96, 2002.
- [55] P. Brault, A. Caillard, A.L. Thomann, J. Mathias, C. Charles, R.W. Boswell, S. Escribano, J. Durand, and T. Sauvage, "Plasma sputtering deposition of platinum into porous fuel cell electrodes", *Journal of Physics D: Applied Physics*, vol. 37, pp. 3419–3423, 2004.
- [56] P. Panek, K. Drabczyk, A. Focsa, and A. Slaoui, "A comparative study of SiO_2 deposited by PECVD and thermal method as passivation for multicrystalline silicon solar cells", *Materials Science and Engineering B*, vol. 165, pp. 64–66, 2009.
- [57] G. Dingemans, C.A.A. van Helvoirt, D. Pierreux, W. Keuning, and W.M.M. Kessels, "Plasma-assisted ALD for the conformal deposition of SiO_2 : process, material and electronic properties", *Journal of The Electrochemical Society*, vol. 159, no. 3, pp. H277–H285, 2012.
- [58] J.T. Tate and P.T. Smith, "The efficiencies of ionization and ionization potentials of various gases under electron impact", *Physical Review*, vol. 39, pp. 270–277, 1932.
- [59] T. Ito, Y. Otani, and N. Namiki, "Electrostatic Separation of Carbon Dioxide by Ionization in Bifurcation Flow", *Aerosol and Air Quality Research*, vol. 4, no. 1, pp. 91–104, 2004.
- [60] T.D. Märk and F. Egger, "Cross-section for single ionization of H_2O and D_2O by electron impact from threshold up to 170 eV", *International Journal of Mass Spectrometry and Ion Physics*, vol. 20, pp. 89–99, 1976.
- [61] A. Fridmen, *Plasma chemistry*, Cambridge University Press, 2008.
- [62] Michael A. Lieberman and A.J. Lichtenberg, *Principles of plasma Discharges and materials processing*, John Wiley & Sons, Inc., 2005.
- [63] T.J. Sommerer and M.J. Kushner, "Numerical investigation of the kinetics and chemistry of rf glow discharge plasmas sustained in He , N_2 , O_2 , $\text{He}/\text{N}_2/\text{O}_2$, $\text{He}/\text{CF}_4/\text{O}_2$, and SiH_4/NH_3 using a Monte Carlo-fluid hybrid model", *Journal of Applied Physics*, vol. 71, no. 4, pp. 1654–1673, 1992.
- [64] C. Lee, D.B. Graves, M.A. Lieberman, and D.W. Hess, "Global model of plasma chemistry in a high density oxygen discharge", *Journal of the Electrochemical Society*, vol. 141, no. 6, pp. 1546–1555, 1994.
- [65] D.A. Toneli, R.S. Pessoa, M. Roberto, and J.T. Gudmundsson, "On the formation and annihilation of the singlet molecular metastables in an oxygen discharge", *Journal of Physics D: Applied Physics*, vol. 48, p. 325202, 2015.
- [66] M. Jiménez-Redondo, E. Carrasco, V.J. Herrero, and I. Tanarro, "Chemistry in glow discharges of H_2/O_2 mixtures: Diagnostics and modelling", *Plasma Sources Science and Technology*, vol. 24, p. 015029, 2015.
- [67] A. Berthelot and A. Bogaerts, "Modeling of CO_2 plasma: effect of uncertainties in the plasma chemistry", *Plasma Sources Science and Technology*, vol. 26, p. 115002, 2017.
- [68] R. Aerts, W. Somers, and A. Bogaerts, "Carbon dioxide splitting in a dielectric barrier discharge plasma: a combined experimental and computational study", *ChemSusChem*, vol. 8, pp. 702–716, 2015.
- [69] D.X. Liu, P. Bruggeman, F. Iza, M.Z. Rong, and M.G. Kong, "Global model of low-temperature atmospheric-pressure $\text{He} + \text{H}_2\text{O}$ plasmas", *Plasma Sources Science and Technology*, vol. 19, p. 025018, 2010.
- [70] J.H. Park, E. Pfender, and C.H. Chang, "Reduction of chemical reactions in nitrogen and nitrogen-hydrogen plasma jets flowing into atmospheric air", *Plasma Chemistry and Plasma Processing*, vol. 20, no. 2, pp. 165–181, 2000.
- [71] M. Bosund, *Development of atomic layer deposition processes for nanotechnology applications*, Aalto University, 2018.
- [72] B. Han, Q. Zhang, J. Wu, B. Han, E.J. Karwacki, A. Derecskei, M. Xiao, X. Lei,

- M.L. O'Neill, and H. Cheng, "On the mechanisms of SiO₂ thin-film growth by the full atomic layer deposition process using bis(t-butylamino)silane on the hydroxylated SiO₂ (001) surface", *The Journal of Physical Chemistry C*, vol. 116, pp. 947–952, 2012.
- [73] E. Langereis, J. Keijmel, M.C.M. Van De Sanden, and W.M.M. Kessels, "Surface chemistry of plasma-assisted atomic layer deposition of Al₂O₃ studied by infrared spectroscopy", *Applied Physics Letters*, vol. 92, p. 231904, 2008.
- [74] A. Rahtu, T. Alaranta, and M. Ritala, "In situ quartz crystal microbalance and quadrupole mass spectrometry studies of atomic layer deposition of aluminum oxide from trimethylaluminum and water", *Langmuir*, vol. 17, no. 21, pp. 6506–6509, 2001.
- [75] Y. Widjaja and C.B. Musgrave, "Quantum chemical study of the mechanism of aluminum oxide atomic layer deposition", *Applied Physics Letters*, vol. 80, no. 18, pp. 3304–3306, 2002.
- [76] S.B.S. Heil, J.L. Van Hemmen, M.C.M. Van De Sanden, and W.M.M. Kessels, "Reaction mechanisms during plasma-assisted atomic layer deposition of metal oxides: A case study for Al₂O₃", *Journal of Applied Physics*, vol. 103, p. 103302, 2008.
- [77] K. Kanomata, P. Pansila, B. Ahmmad, S. Kubota, K. Hirahara, and F. Hirose, "Infrared study on room-temperature atomic layer deposition of TiO₂ using tetrakis(dimethylamino)titanium and remote-plasma-excited water vapor", *Applied Surface Science*, vol. 308, pp. 328–332, 2014.
- [78] K. Kanomata, P. Pansila, H. Ohbaa, B. Ahmmada, S. Kubotaa, K. Hiraharaa, and F. Hirosea, "RT atomic layer deposition of Al₂O₃ by using remote plasma excited water vapor", in: 227th ECS Meeting, Chicago, USA, 2015.
- [79] K. Kanomata, H. Ohba, P. Pansila, B. Ahmmad, S. Kubota, K. Hirahara, and F. Hirose, "Infrared study on room-temperature atomic layer deposition of HfO₂ using tetrakis(ethylmethylamino)hafnium and remote plasma-excited oxidizing agents", *Journal of Vacuum Science & Technology A: Vacuum, Surfaces, and Films*, vol. 33, no. 1, p. 01A113, 2015.
- [80] K. Kanomata, K. Tokoro, T. Imai, P. Pansila, M. Miura, B. Ahmmad, S. Kubota, K. Hirahara, and F. Hirose, "Room-temperature atomic layer deposition of ZrO₂ using tetrakis(ethylmethylamino)zirconium and plasma-excited humidified argon", *Applied Surface Science*, vol. 387, pp. 497–502, 2016.
- [81] R. Kohli and K.L. Mittal, *Developments in surface contamination and cleaning*, Elsevier, 2012.
- [82] J. Tiilikainen, J.M. Tilli, V. Bosund, M. Mattila, T. Hakkarainen, V.M. Airaksinen, and H. Lipsanen, "Nonlinear fitness-space-structure adaptation and principal component analysis in genetic algorithms: An application to x-ray reflectivity analysis", *Journal of Physics D: Applied Physics*, vol. 40, pp. 215–218, 2007.
- [83] O.M.E. Ylivaara, X. Liu, L. Kilpi, J. Lyytinen, D. Schneider, M. Laitinen, J. Julin, S. Ali, S. Sintonen, M. Berdova, E. Haimi, T. Sajavaara, H. Ronkainen, H. Lipsanen, J. Koskinen, S.P. Hannula, and R.L. Puurunen, "Aluminum oxide from trimethylaluminum and water by atomic layer deposition: The temperature dependence of residual stress, elastic modulus, hardness and adhesion", *Thin Solid Films*, vol. 552, pp. 124–135, 2014.
- [84] G.G. Stoney, "The tension of metallic films deposited by electrolysis", *Proceedings of the Royal Society A*, vol. 82, no. 553, pp. 172–175, 1909.
- [85] A.A. Sagade, A.I. Aria, S. Edge, P. Melgari, B. Gieseking, B.C. Bayer, J.C. Meyer, D. Bird, P. Brewer, and S. Hofmann, "Graphene-based nanolaminates as ultra-high permeation barriers", *npj 2D Materials and Applications*, vol. 1, p. 35, 2017.
- [86] H. Jung, H. Choi, H. Jeon, S. Lee, and H. Jeon, "Radio frequency plasma power dependence of the moisture permeation barrier characteristics of Al₂O₃ films deposited by remote plasma atomic layer deposition", *Journal of Applied Physics*, vol. 114, p. 173511, 2013.
- [87] T.O. Kääriäinen, P. Maydannik, D.C. Cameron, K. Lahtinen, P. Johansson, and J. Kuusipalo, "Atomic layer deposition on polymer based flexible packaging materials: Growth characteristics and diffusion barrier properties", *Thin Solid*

- Films*, vol. 519, pp. 3146–3154, 2011.
- [88] S.A. Starostin, W. Keuning, J.-P. Schalken, M. Creatore, W.M.M. (Erwin) Kessels, J.B. Bouwstra, M.C.M. (Richard) van de Sanden, and H.W. de Vries, "Synergy between plasma-assisted ALD and roll-to-roll atmospheric pressure PE-CVD processing of moisture barrier films on polymers", *Plasma Processes and Polymers*, vol. 13, 311–315, 2016.
  - [89] ASTM F-1249, "Standard Test Method for Water Vapor Transmission Rate Through Plastic Film and Sheeting Using a Modulated Infrared Sensor", ASTM International, West Conshohocken, PA, 2013.
  - [90] J.P. Thomas, M. Fallavier, D. Ramdane, N. Chevarier, and A. Chevarier, "High resolution depth profiling of light elements in high atomic mass materials", *Nuclear Instruments and Methods in Physics Research*, vol. 218, pp. 125–128, 1983.
  - [91] R. Groleau, S.C. Gujrathi, and J.P. Martin, "Time-of-flight system for profiling recoiled light elements", *Nuclear Instruments and Methods in Physics Research*, vol. 218, pp. 11–15, 1983.
  - [92] S. Giangrandi, K. Arstila, B. Brijs, T. Sajavaara, A. Vantomme, and W. Vandervorst, "Depth resolution optimization for low-energy ERDA", *Nuclear Instruments and Methods in Physics Research B*, vol. 261, pp. 512–515, 2007.
  - [93] K. Arstila, J. Julin, M.I. Laitinen, J. Aalto, T. Konu, S. Kärkkäinen, S. Rahkonen, M. Raunio, J. Itkonen, J.P. Santanen, T. Tuovinen, and T. Sajavaara, "Potku-New analysis software for heavy ion elastic recoil detection analysis", *Nuclear Instruments and Methods in Physics Research B*, vol. 331, pp. 34–41, 2014.
  - [94] D. Abou-Ras, R. Caballero, C.H. Fischer, C.A. Kaufmann, I. Lauermaier, R. Mainz, H. Mönig, A. Schöpke, C. Stephan, C. Streeck, S. Schorr, A. Eicke, M. Döbeli, B. Gade, J. Hinrichs, T. Nunnery, H. Dijkstra, V. Hoffmann, D. Klemm, V. Efimova, A. Bergmaier, G. Dollinger, T. Wirth, W. Unger, A.A. Rockett, A. Perez-Rodriguez, J. Alvarez-Garcia, V. Izquierdo-Roca, T. Schmid, P.P. Choi, M. Müller, F. Bertram, J. Christen, H. Khatir, R.W. Collins, S. Marsillac, and I. Kötschau, "Comprehensive comparison of various techniques for the analysis of elemental distributions in thin films", *Microscopy Microanalysis*, vol. 17, pp. 728–751, 2011.
  - [95] M. Wilke, G. Teichert, R. Gemma, A. Pundt, R. Kirchheim, H. Romanus, and P. Schaaf, "Glow discharge optical emission spectroscopy for accurate and well resolved analysis of coatings and thin films", *Thin Solid Films*, vol. 520, pp. 1660–1667, 2011.
  - [96] B.B. Burton, S.W. Kang, S.W. Rhee, and S.M. George, "SiO₂ atomic layer deposition using Tris(dimethylamino)silane and Hydrogen Peroxide studied by in situ transmission FTIR spectroscopy", *The Journal of Physical Chemistry C*, vol. 113, pp. 8249–8257, 2009.
  - [97] L.J. Ward, W.C.E. Schofield, J.P.S. Badyal, A.J. Goodwin, and P.J. Merlin, "Atmospheric pressure glow discharge deposition of polysiloxane and SiO_x films", *Langmuir*, vol. 19, no. 6, pp. 2110–2114, 2003.
  - [98] A.C. Dillon, A.W. Ott, J.D. Way, and S.M. George, "Surface chemistry of Al₂O₃ deposition using Al(CH₃)₃ and H₂O in a binary reaction sequence", *Surface Science*, vol. 322, pp. 230–242, 1995.
  - [99] J.L. van Hemmen, S.B.S. Heil, J.H. Klootwijk, F. Roozeboom, C.J. Hodson, M.C.M. van de Sanden, and W.M.M. Kessels, "Plasma and thermal ALD of Al₂O₃ in a commercial 200 mm ALD reactor", *Journal of The Electrochemical Society*, vol. 154, no. 7, pp. G165–G169, 2007.
  - [100] T.O. Kääriäinen and D.C. Cameron, "Plasma-assisted atomic layer deposition of Al₂O₃ at room temperature", *Plasma Processes and Polymers*, vol. 6, pp. S237–S241, 2009.
  - [101] J.M. Reyes, B.M. Perez Ramos, C.Z. Islas, W.C. Arriaga, P.R. Quintero, and A.T. Jacome, "Chemical and morphological characteristics of ALD Al₂O₃ thin-film surfaces after immersion in pH buffer solutions", *Journal of The Electrochemical Society*, vol. 160, no. 10, pp. B201–B206, 2013.
  - [102] V.R. Rai, V. Vandalon, and S. Agarwal, "Surface reaction mechanisms during ozone and oxygen plasma assisted atomic layer deposition of aluminum oxide",

- Langmuir*, vol. 26, no. 17, pp. 13732–13735, 2010.
- [103] D.N. Goldstein, J.A. McCormick, and S.M. George, "Al₂O₃ atomic layer deposition with trimethylaluminum and ozone studied by in situ transmission FTIR spectroscopy and quadrupole mass spectrometry", *The Journal of Physical Chemistry C*, vol. 112, no. 49, pp. 19530–19539, 2008.
- [104] N. Médard, J.C. Soutif, and F. Poncin-Epaillard, "CO₂, H₂O, and CO₂/H₂O plasma chemistry for polyethylene surface modification", *Langmuir*, vol. 18, no. 6, pp. 2246–2253, 2002.
- [105] A.P. Perros, H. Hakola, T. Sajavaara, T. Huhtio, and H. Lipsanen, "Influence of plasma chemistry on impurity incorporation in AlN prepared by plasma enhanced atomic layer deposition", *Journal of Physics D: Applied Physics*, vol. 46, p. 505502, 2013.

9 789526 088822

ISBN 978-952-60-8882-2 (printed)
ISBN 978-952-60-8883-9 (pdf)
ISSN 1799-4934 (printed)
ISSN 1799-4942 (pdf)

Aalto University
School of Electrical Engineering
Department of Electronics and Nanoengineering
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**