Structural materials corrosion testing and modelling assessment in supercritical water

Sami Penttilä

Structural materials corrosion testing and modelling assessment in supercritical water

Sami Penttilä

**The public defense on 22th May 2020 at 12:00 will be
organized via remote technology.**

Link: <https://aalto.zoom.us/j/65195807490>

Zoom Quick Guide: <https://www.aalto.fi/en/services/zoom-quick-guide>

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Chemical Engineering, at a public examination held at the lecture hall Ke 3 of the school on 22 May 2020 at 12 o'clock.

**Aalto University
School of Chemical Engineering
Department of Chemical and Metallurgical Engineering**

Supervising professor

Assistant Professor Mari Lundström, Aalto University, Finland

Thesis advisors

Dr. Petri Kinnunen, VTT, Finland

Professor Emeritus Olof Forsen, Aalto University, Finland

Preliminary examiners

Professor Todd Allen, University of Michigan, USA

Dr. Alina Aguero, Instituto Nacional de Tecnica Aeroespacial, Spain

Opponent

Professor Jörg Starflinger, University of Stuttgart, Germany

Aalto University publication series

DOCTORAL DISSERTATIONS 70/2020

© 2020 Sami Penttilä

ISBN 978-952-60-3866-7 (printed)

ISBN 978-952-60-3867-4 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-60-3867-4>

Images: Cover photo by VTT

Unigrafia Oy

Helsinki 2020

Finland

Author

Sami Penttilä

Name of the doctoral dissertation

Structural materials corrosion testing and modelling assessment in supercritical water

Publisher School of Chemical Engineering

Unit Department of Chemical and Metallurgical Engineering

Series Aalto University publication series DOCTORAL DISSERTATIONS 70/2020

Field of research Processing of Materials

Manuscript submitted 5 December 2019

Date of the defence 22 May 2020

Permission for public defence granted (date) 18 December 2019

Language English

☐ **Monograph**

☒ **Article dissertation**

☐ **Essay dissertation**

Abstract

Demands for improved sustainability, efficiency and safety require innovations in the field of nuclear technology and thus push forward the Generation IV (Gen IV) reactor systems. In general, Gen IV reactors use fuel more efficiently than current Light Water Reactors (LWR) due to a closed fuel cycle and/or higher fuel burn-up. Most systems also have enhanced safety features compared to present day reactors. One of the Gen IV type reactor concepts is called Supercritical Water Reactor (SCWR) that uses water as a coolant medium.

For components in SCWR designs, general corrosion is one of the most severe degradation modes. Numerous papers in the literature have considered the general corrosion of SCWR candidate materials. Unfortunately, tests have been conducted under various conditions. This work through Publications I - VI aims at identifying and decreasing knowledge gaps in the open literature especially at higher temperatures up to 700 °C with different material compositions by using different characterization methods. The most important variables affecting corrosion behaviour of the candidate materials in Supercritical Water (SCW) are alloy class, temperature and treatment of the sample surface.

Based on this work, it can be said that in the case of fuel cladding, zirconium alloys and steels with bulk Cr content < 16 - 20 wt-% have generally not sufficient corrosion resistance except possibly with special surface treatment. This observation rules out most of the available nuclear-grade materials in typical metallographic conditions. In terms of oxidation resistance, high-performance alloys like high-chromium steels (> 20 wt-% Cr), Ni-based alloys and Oxide Dispersion Strengthened (ODS) steels are applicable. However, there are some limitations regarding the adverse effect of high Cr and Ni contents in the bulk alloy or the material's joining possibilities. Thus, a study on cold worked Type 316L was performed by exposing specimens up to 3 000 h in SCW. Very promising general corrosion results were achieved at least in laboratory conditions. However, the effect of Stress Corrosion Cracking (SCC) susceptibility of cold-worked material and longer term behaviour (about 1 year or time period of equivalent to the fuel cycle) still need to be studied. In order to estimate the long-term corrosion penetration rate, the Mixed Conduction Model (MCM) was developed and applied to predict the behaviour of selected materials in SCW. The most promising results were found on the 20 wt-% Cr ODS steel. Based on the MCM calculations, the 20 wt-% Cr ODS steel showed slower corrosion penetration rate (mm/a) than the other alloys studied. By contrast, 316NG showed 2 times higher corrosion penetration rate compared to 20 wt-% Cr ODS steel. Modelling results gave new insight into the possible oxidation behaviour of structural materials in SCW and how it can be interpreted through modelling.

Keywords Supercritical water, corrosion, oxidation, steel, cladding, modelling, SCWR

ISBN (printed) 978-952-60-3866-7

ISBN (pdf) 978-952-60-3867-4

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Helsinki

Location of printing Helsinki **Year** 2020

Pages 178

urn <http://urn.fi/URN:ISBN:978-952-60-3867-4>

Tekijä

Sami Penttilä

Väitöskirjan nimi

Rakennemateriaalien korroosiotestaus ja mallintaminen ylikriittisessä vedessä

Julkaisija Kemian tekniikan korkeakoulu**Yksikkö** Kemiantekniikan ja metallurgian laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 70/2020**Tutkimusala** Materiaalien prosessointi**Käsikirjoituksen pvm** 05.12.2019**Väitöspäivä** 22.05.2020**Väittelyluvan myöntämispäivä** 18.12.2019**Kieli** Englanti☐ **Monografia**☒ **Artikkeliväitöskirja**☐ **Esseeväitöskirja****Tiivistelmä**

Ydinenergian tuotannossa esitetyt vaatimukset paremmalle polttoainetehokkuudelle ja turvallisuudelle edesauttavat uudenlaisien innovaatioiden esiintuloa edistämällä myös neljännen sukupolven (Gen IV) laitojen kehitystä. Yleisesti ottaen Gen IV reaktorit käyttävät polttoainetta tehokkaammin verrattuna nykyisiin kevytvesireaktoreihin johtuen suljetusta polttoainekierrrosta, korkeammasta palamasta, paremmasta termisestä hyötysuhteesta tai näiden yhdistelmästä. Näistä Gen IV konsepteista ylikriittisen veden reaktori (SCWR) on ainoa, joka käyttää vettä jäähdytteenä. Yleinen korrosio on yksi vakavimmista materiaalien vanhenemismekanismeista ylikriittisessä vedessä (SCW). Kirjallisuudessa käsitellään laajasti vaihtoehtoisia materiaaleja SCWR:n komponenteille. Yleensä kokeet ovat suoritettu hyvin erilaisissa olosuhteissa ja tuloksien vertaaminen on haastavaa. Tämä työ pyrkii selvittämään materiaalien käyttäytymistä SCW-olosuhteissa ja täydentämään tietoaaukkoja erityisesti korkeammissa lämpötiloissa aina 700 °C asti tutkien erilaisia materiaaliakoostumuksia (Julkaisut I-VI) erilaisilla karakterisointimenetelmillä. Yleisesti materiaalien käyttäytymiseen vaikuttavia tekijöitä yleisen korroosion näkökulmasta ovat perusaineen koostumus, lämpötila ja näytepinnan esikäsittely.

Tuloksien perusteella voidaan todeta, että Zr-seokset ja teräkset (< 16 - 20 paino-% Cr) eivät saavuta riittävää korroosiokestävyyttä polttoaineen suojakuoren tapauksessa, vaikka korroosiokestävyyttä voidaan mahdollisesti parantaa kylmämuokkaamalla materiaalin pintaa. Tämä havainto poissulkee useat ydinvoimalaitoskäyttöön jo lisensioituneet materiaalinvaihtoehdot niiden ollessa tyypillisessä lähtötilassaan. Toisaalta teräkset (> 20 paino-% Cr), nikkelipohjaiset seokset ja oksididispersioilujitetut teräkset (ODS) ovat osoittaneet käyttökelpoisuutensa. Joitakin rajoituksia näiden materiaalien käyttöön tulee liittyen perusaineen korkeaan kromi- ja nikkelipitoisuuteen sekä materiaalien liitettävyyteen. Pinnan kylmämuokkauksen vaikutusta hapettumisen kestävytyteen tutkittiin ruostumattomalle teräkselle 316L altistamalla näytteet 3000 h asti SCW olosuhteissa. Altistuskokeiden tulokset olivat lupaavia, mutta kylmämuokkauksen vaikutusta jännityskorroosioherkkyyteen kuten myös pidempiaikaisen altistumisen (> 5000 h) vaikutusta pitää edelleen tutkia. Yleisen korroosiokestävyyden arvioimiseksi kehitettiin ja sovellettiin ns. MCM-menetelmää (Mixed Conduction Model) määrittämään valittujen materiaalien pitkäaikaiskäyttäytymistä. Lupaavimpia tuloksia saatiin ODS teräksille, jotka sisälsivät yli 20 paino-% kromia perusaineessa. MCM laskennan perusteella tämä materiaali osoitti hitaampaa korroosiotunkeutumisnopeutta (mm/vuosi) kuin muut tutkitut metalliseokset. Toisaalta ruostumaton teräs 316NG osoitti n. 2 kertaa nopeampaa korroosiotunkeutumisnopeutta verrattuna 20 paino-% kromia sisältävään ODS teräkseen. Mallinnus antoi uutta ymmärrystä siihen, miten rakennemateriaalien hapettuminen ko. ympäristössä todennäköisesti tapahtuu ja miten sitä voidaan mallinnuksen kautta selittää.

Avainsanat Yliirittinen vesi, korrosio, hapettuminen, teräs, suojakuori, mallinnus, SCWR**ISBN (painettu)** 978-952-60-3866-7**ISBN (pdf)** 978-952-60-3867-4**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Helsinki**Painopaikka** Helsinki**Vuosi** 2020**Sivumäärä** 178**urn** <http://urn.fi/URN:ISBN:978-952-60-3867-4>

Acknowledgements

First, I am very grateful for Prof. Olof Forsen who gave me the opportunity to pursue PhD in his department. I warmly thank his valuable guidance and discussions especially in the beginning of my doctoral studies. Prof. Mari Lundström is also acknowledged for acting as thesis supervisor in the final phase. I want to thank all my colleagues at VTT who have enabled the experimental work in corrosion testing by using VTT's autoclave facility. Special thanks go to laboratory engineers and technicians; P. Väisänen, T. Lehtikuusi, M. Mattila, J. Lukin and S. Peltonen, who had to struggle with water chemistry issues and leaking autoclaves, and also A. Kukkonen for endless patience to perform oxide film characterizations by electron microscope; to P. Auerkari for the insight he provided concerning the general corrosion phenomena at high temperatures and associated experimental work done within the last 10 years or more. Special thanks go to my co-authors Prof. M. Bojinov and Prof. I. Betova for their valuable guidance and patience to discuss on aspects of materials modelling in supercritical water conditions. It's clear that without extensive international collaboration this thesis would never have been completed, so special thanks go to Dr. D. Guzonas for his valuable advice and comments on the work during the years, as well as my other GIF colleagues Prof. W. Zheng, Dr J. Li, Dr. L. Walters, Dr. L. Leung, Prof. T. Schulenberg, Prof. L. Zhang, Dr. A. Saez-Maderuelo, and also Prof. J. Szpunar, Dr. M. Nezakat and Dr. H. Akhiani for their information exchange and debates during the years. Special thanks go to Dr. R. Novotny who gave me the possibility to spend six months at JRC-IE in Petten, the Netherlands. Through that period, I learned much about myself and had a chance to strengthen my international network further. Special thanks go to my thesis advisor Dr. P. Kinnunen, as well as Dr. T. Saario and Dr. P. Moilanen who motivated and forced me to finish this thesis. Without their gentle push towards the right direction this would never have come to an end. Last but not least, Dr. A. Toivonen, who has influenced me the most during my career as a research scientist, especially through table hockey, but also by his endless willingness to answer my questions related to material science. I am very grateful to my parents and my family who have supported me during this long journey. As said in the most famous anthem, "you'll never walk alone".

Vantaa, 24.4.2020
Sami Penttilä

Contents

Acknowledgements	I
List of Symbols and Abbreviations.....	V
List of Publications	IX
Author's Contribution.....	XI
1. Introduction.....	1
1.1 Background	4
1.2 Objectives and Scope	8
1.3 Dissertation Structure.....	9
2. Theoretical Background	10
2.1 Properties of supercritical water	10
2.2 Materials research in SCWR development	15
2.3 SCWR in-core material requirements	15
2.4 Potential material options	17
2.5 Modelling approaches for oxide film growth	22
3. Experimental part.....	28
3.1 Materials and environment	28
3.2 Weight loss / gain experiments	30
3.3 Effect of surface modification.....	41
3.4 Oxidation mechanism	49
3.5 Reproducibility of test results.....	53
3.6 Electrochemical methods	56
4. Discussion and conclusions.....	60
References	73

List of Symbols and Abbreviations

Symbols

Latin alphabet

c_j	Molar concentration (mol cm^{-3} , $j = \text{Fe, Cr, Ni, Mn, Si, Cu, Nb, Ti, Al, Mo}$)
D_{eff}	Effective diffusion coefficient
D_{gb}	Diffusion coefficient in the grain boundary
D_{gi}	Diffusion coefficient in the grain interior
D_I	Diffusion coefficient of interstitial cations in the inner layer ($\text{cm}^2 \text{s}^{-1}$)
D_O	Diffusion coefficient of oxygen vacancies in the inner layer ($\text{cm}^2 \text{s}^{-1}$)
dpa	Displacement per atom
D_V	Diffusion coefficient of cation vacancies in the inner layer ($\text{cm}^2 \text{s}^{-1}$)
$\bar{E}$	Electric field strength (V cm^{-1})
F	Faraday constant (C mol^{-1})
f_{gb}	Fraction of grain boundaries
J_j	Flux of point defects of type j ($j=\text{I, O and V}$, i.e. interstitial cations, oxygen and cation vacancies)
k	Boltzmann constant
k_1	Rate constant of interstitial cation formation or cation vacancy consumption at the alloy/inner layer interface ($\text{mol cm}^{-2} \text{s}^{-1}$)
k_2	Rate constant of oxide formation via oxidation and injection of oxygen vacancies ($\text{mol cm}^{-2} \text{s}^{-1}$)
k_3	Rate constant of formation of outer layer at the inner layer/ outer layer interface (cm s^{-1})

k_4	Rate constant of oxygen incorporation via consumption of oxygen vacancies (cm s^{-1})
L_{in}	Thickness of the inner layer of oxide
L_{out}	Thickness of the outer layer of oxide
R	Ideal gas constant ($\text{J mol}^{-1} \text{K}^{-1}$)
T	Temperature (K)
T_c	Critical point
$V_{m,MO}$	Molar volume of the phase in the oxide layer ($\text{cm}^3 \text{mol}^{-1}$)
X	Nominal valence of an iron cation in the oxide
y_j	Atomic fraction of a cation in the oxide

Greek alphabet

α_2	Transfer coefficient of the oxidation reaction at the alloy/film interface
ε	Potential energy barrier
δ_{gb}	Grain boundary width
φ	Grain size of the oxide in question

Abbreviations

ASME	American Society of Mechanical Engineers
BWR	Boiling Water Reactor
CEI	Contact Electric Impedance
CER	Contact Electric Resistance
CNL	Canadian Nuclear Laboratories
CMAT	CanmetMATERIALS
EDM	Electric discharge Machine, EDM
EDS	Energy Dispersive X-ray Spectroscopy
EIS	Electrochemical Impedance Spectroscopy, EIS
EPR	European Pressurized Water Reactor
FA3	Flamanville 3 (EPR)

FFTF	Fast Flux Test Facility
FH1	Hanhikivi 1 (WWER)
F-M	Ferritic-Martensitic
FIB	Focused Ion Beam
GDOES	Glow Discharge Optical Emission Spectroscopy,
Gen III	Generation III
Gen IV	Generation IV
GFR	Gas-Cooled Fast Reactor
GHG	Greenhouse gas
GIF	Generation IV International Forum
HLMC	Heavy liquid metal coolant
HPLWR	High Performance Light Water Reactor
IGSCC	Intergranular stress corrosion cracking
JHR MTR	Jules Horowitz Materials Testing Reactor
JRC	Joint Research Centre
LBE	Pb-Bi eutectic
LFR	Lead-Cooled Fast Reactor
LWR	Light Water Reactor
MCM	Mixed Conduction Model
MOX	Mixed Oxide Fuel
MSR	Molten Salt Reactor
MW _e	Megawatts electrical
NPP	Nuclear Power Plant
ODS	Oxide Dispersion Strengthened Steel
OL3	Olkiluoto 3 (EPR)
PDM	Point Defect Model
PM	Powder Metallurgy
PWR	Pressurized Water Reactor
RCCM	Design and Construction Rules for the Mechanical Components of French PWR Nuclear Islands

SCC	Stress Corrosion Cracking
SCFFP	Supercritical Fossil-Fired Plant
SCW	Supercritical Water
SCWR	Supercritical Water-Cooled Reactor
SEM	Scanning Electron Microscopy
SFR	Sodium-Cooled Fast Reactor
SNETP	Sustainable Nuclear Energy Technology Platform
TEM	Transmission Electron Microscope
UNB	University of New Brunswick
VHTR	Very High Temperature Reactor
WWER	The Water-Water Power Reactor, PWR type design originally developed in the Soviet Union, and now Russia
XRD	X-Ray Diffraction

List of Publications

This doctoral thesis consists of a summary and of the following publications, which are referred to in the text by their respective Roman numerals:

I. Iva Betova, Martin Bojinov, Petri Kinnunen, Viivi Lehtovuori, Seppo Peltonen, Sami Penttilä, Timo Saario, 2006. Composition, structure, and properties of corrosion layers on ferritic and austenitic steels in ultrasupercritical water. ECS – The Electrochemical Society. Journal of the Electrochemical Society, volume 153, issue 11, pages B464–B473. DOI: 10.1149/1.2337166

II. Sami Penttilä, Aki Toivonen, Liisa Heikinheimo, Radek Novotny, 2010. Corrosion Studies of Candidate Materials for European HPLWR. Special Issue on the 2008 International Congress on Advances in Nuclear Power Plants. Journal of Nuclear Technology, Vol 170, issue 1, pages 261–271. DOI: 10.13182/NT10-A9463

III. Sami Penttilä, Aki Toivonen, Laura Rissanen, Liisa Heikinheimo, 2010. Generation IV Material Issues – Case SCWR. Fuji Technology Press Ltd. Journal of Disaster Research, volume 5, issue 4, pages 469–478. DOI: 10.20965/jdr.2010.p0469

IV. Sami Penttilä, Iva Betova, Martin Bojinov, Petri Kinnunen, Aki Toivonen, 2011. Estimation of kinetic parameters of the corrosion layer constituents on steels in supercritical water coolant conditions. Elsevier. Corrosion Science volume 53, issue 12, pages 4193–4203. DOI: <https://doi.org/10.1016/j.corsci.2011.08.029>

V. Sami Penttilä, Aki Toivonen, Jian Li, Wenyue Zheng, Radek Novotny, 2013. Effect of Surface Modification on the Corrosion Resistance of Austenitic Stainless Steels 316L in Supercritical Water. Elsevier. Journal of Supercritical Fluids, volume 81, pages 157–163. DOI: <https://doi.org/10.1016/j.supflu.2013.05.002>

VI. Sami Penttilä, Iva Betova, Martin Bojinov, Petri Kinnunen, Aki Toivonen, 2015. Oxidation model for construction materials in supercritical water – Estimation of kinetic and transport parameters. Elsevier. Corrosion Science, volume 100, pages 36–46. DOI: <https://doi.org/10.1016/j.corsci.2015.06.033>

It should be noted that in Publication I, the list of authors is based on alphabetical order as this was agreed at that time to be the normal procedure in joint publications. Starting from Publication II, the procedure was changed so that the main author was mentioned first.

Author's Contribution

The author's contributions to the included papers are described below:

Publication I: “Composition, structure, and properties of corrosion layers on ferritic and austenitic steels in ultrasupercritical water”

In **Publication I**, M.B and I.B were responsible for modelling part of the manuscript. T.S was responsible for the experimental design of electrochemical measurements under SCW conditions. S.P performed the experimental autoclave work including in-situ electrochemical measurements on F-M steel P91 and austenitic steel AISI 316LNG, as well as of their main constituents Fe, Cr, and Ni in supercritical water at 500 - 700 °C. This part was guided and supervised by P.K i.e. set-up of the system and electrochemical measurements. Operating of autoclave and water recirculation loop was done under supervision of S.Pel. Features observed in the measurements were substantiated by ex-situ results on the thickness, composition, and morphology of the formed oxide layers from weight change measurements and Glow Discharge Optical Emission Spectroscopy (GDOES) analyses. S.P contributed to the ex-situ data evaluation and the interpretation of the results and wrote the text related to the general corrosion part together with A.T. V.L and I.B wrote the manuscript part considering electrochemical measurements of the materials under SCW conditions. S.P took part in the overall manuscript writing together with co-authors under supervision of M.B.

Publication II: “Corrosion Studies of Candidate Materials for European HPLWR”

In **Publication II**, the screening tests on candidate material groups were performed in terms of general corrosion. S.P performed the major part of the planning and the experimental work, the evaluation, and the interpretation of the results including the Scanning Electron Microscope - Energy Dispersive X-ray Spectroscopy (SEM-EDS) analyses. R.N performed the X-ray Diffraction (XRD) analyses at the Joint Research Centre, Petten, the Netherlands. The paper was mainly compiled by S.P in support of A.T and was reviewed by L.H.

Publication III: “Generation IV Material Issues – Case SCWR”

Publication III deals with the material requirements regarding general corrosion resistance as well as their mechanical properties under Supercritical Water (SCW) conditions through Stress Corrosion Cracking (SCC) susceptibility tests and creep resistance. S.P performed the major part of the planning and the experimental part considering general corrosion autoclave tests. A.T performed

the SCC susceptibility and L.R creep resistance tests. The author performed the SEM-EDS evaluation and the interpretation of the general corrosion results. The paper was mainly compiled by S.P with support of A.T and R.L and reviewed by L.H.

Publication IV: “Estimation of kinetic parameters of the corrosion layer constituents on steels in supercritical water coolant conditions”

The first attempt to model oxide film formation and structure was performed in **Publication IV** based on the Mixed Conduction Model (MCM). M.B was responsible for the model development towards SCW conditions. S.P was responsible for planning the experimental part to support the modelling effort. S.P performed the major part of the modelling calculations under supervision of P.K. S.P performed all the experimental autoclave work in support of A.T including the SEM-EDS and GDOES data evaluation and the interpretation of the results. S.P was responsible of the overall manuscript under supervision of I.B and M.B.

Publication V: “Effect of surface modification on the corrosion resistance of austenitic stainless steels 316L in supercritical water”

Publication V focused on the effect of surface modification on oxidation resistance of austenitic stainless steel Type 316L. S.P was responsible for the experimental design together with A.T and R.N. J.L was responsible for the SEM/Focused Ion Beam (FIB) characterization of the studied materials at CANMET, Canada. S.P performed the major part of the experimental autoclave work and the interpretation of the results, and the SEM-EDS data evaluation together with J.L. The paper was mainly compiled by S.P together with J.L under supervision of W.Z.

Publication VI: “Oxidation model for construction materials in supercritical water – Estimation of kinetic and transport parameters”

The upgraded oxide film model was implemented on high-performance materials in **Publication VI**. M.B and I.B were responsible for the planning and execution of the upgraded model. All the modelling calculations were performed by M.B. S.P performed the major part of the planning related to experimental autoclave work together with A.T. S.P was responsible for the SEM-EDS and GDOES evaluation, and interpretation of the model calculation results under supervision of P.K. The overall paper was compiled by S.P in support of co-authors and supervised by M.B.

1. Introduction

Nuclear power makes a considerable contribution to diminishing Green House Gases (GHG) world-wide, since Nuclear Power Plants (NPP) produce almost no GHG emissions or other air pollutants during their operating life and actually very minimal emissions over an NPP's entire life cycle [1]. Nuclear accidents, e.g. at the Fukushima Daiichi nuclear power plant in Japan in 2011, however, raised some doubts, especially questions related to safety, and about the future of nuclear energy. Yet, in 2020, about 9 years after the accident, nuclear energy remains an important option for many countries to produce stable base load electricity. It is shown that, together with hydropower and wind-based electricity, nuclear power is one of the lowest GHG producers when taking into account emissions over the entire life cycle [1]. Nuclear power has been used to reduce human-caused climate change and air pollution since the 1950s, and it has been estimated that nuclear power prevented around 64 gigatons of CO₂-equivalent net GHG emissions world-wide between 1971 and 2009 [2]. This figure is comparable to the past 35 years of CO₂ emissions from burning coal in the USA or 17 years in China. This means that in the historical perspective, nuclear energy has so far prevented the construction of hundreds of harmful fossil-fired power plants.

Currently there are 451 nuclear power plants in operation in 31 countries, which provide about 12% of the total global electricity base load (390 GWe), around 2 500 TWh in 2017 [3, 4]. Most of them are Light Water Reactors (LWR), generally considered second- (Gen II) or third-generation systems (Gen III), which have been in use for decades due to a good safety record. The first-generation systems were shut down some time ago, but over 50 next generation NPPs are currently being constructed in 13 countries, most of them in China, South Korea, the United Arab Emirates and Russia [5].

Nuclear energy has been part of Finnish electricity production since the 1970s, and Finland is committed to nuclear energy for the next decades. Around one third of the electricity consumed in Finland is produced with nuclear energy [4], and it has the major role in the implementation of the Finnish climate and energy strategy. Olkiluoto 3 (OL3) nuclear power plant under construction in Finland (expected to come on-line in 2020) will operate until 2070. In addition, a nuclear power plant under preparation phase, Hanhikivi 1 (FH1), will operate for even longer. New capacity has also been achieved through uprating from the

original power level in Olkiluoto and Loviisa plants by 29% and 18%, respectively [5].

However, before the decommissioning of Gen III type nuclear power plants like OL3 and FH1, Europe is planning to deploy Generation IV (Gen IV) nuclear power plants. Demands for improved sustainability, efficiency and safety require new kinds of innovations in the area of nuclear technology and thus push forward the Gen IV reactor systems. In general, Gen IV reactors use the fuel more efficiently than current LWRs due to a closed fuel cycle, and most systems have enhanced safety features. According to the Generation IV International Forum (GIF), under the umbrella of Gen IV research, six different future reactor concepts are covered, as shown in Table 1 [6].

Within the GIF, the development work has been focused on future nuclear systems with high-safety features, enhanced resource use and minimization of waste production [6]. In 2001, six different systems were selected for Gen IV consideration, namely Gas-Cooled Fast Reactor (GFR), Very High Temperature Reactor (VHTR), Sodium-Cooled Fast Reactor (SFR), Lead-Cooled Fast Reactor (LFR), Molten Salt Reactor (MSR) and Supercritical Water Cooled Reactor (SCWR). In addition, Small Modular Reactors (SMR) have shown their potential as a future reactor concept with a cooling medium of either water, lead, or molten salts. Typically, SCWR concepts have been developed to generate electric powers at or greater than 1 000 MW_e except Japan's fast spectrum reactor. However, e.g. in Canada the need for smaller, lower power reactors in remote communities has been recognized, and for this purpose redesigning of the SCWR core size to meet local deployment needs of 10 to 300 MW_e is also under way.

Table 1. The six most promising Gen IV type reactors according to GIF [6].

Six nuclear energy systems for further development identified by GIF	
I.	Gas-Cooled fast reactor (GFR)
II.	Lead-Cooled fast reactor (LFR)
III.	Molten Salt Reactor (MSR)
IV.	Supercritical Water-Cooled Reactor (SCWR)
V.	Sodium-Cooled Fast Reactor (SFR)
VI.	Very High Temperature Reactor (VHTR)

Most of the GIF designs are generally not foreseen to be available for commercial construction before 2030. A demonstration of concepts, e.g., Myrrha (LFR) in Belgium is, however, foreseen around 2025 [7]. On the other hand, the latest news considering ASTRID (SFR) indicates that, due to heavy delays in construction of the Jules Horowitz Materials Testing Reactor (JHR

MTR) in France, the ASTRID project has been postponed for the moment. As stated above, the future types of nuclear power plant designs will take a long time to be utilized. However, there are several indications that they will be deployed faster than earlier anticipated. An 800 MW_e sodium-cooled reactor achieved full power in Russia in early 2016. Also, China is constructing a dual unit gas-cooled pebble bed reactor with estimated grid connection in 2021 [5].

When comparing Gen IV type reactor designs to present NPP technology, the presumable benefits for Gen IV reactors are [6, 7]:

- A. better sustainability,
- B. increased safety,
- C. more efficient use of fissile material,
- D. higher thermal energy to electricity conversion efficiency,
- E. minimal waste production,
- F. the ability to consume existing nuclear waste in the production of electricity,
- G. enhanced proliferation resistance.

In general, the Gen IV concept aims at closing the fuel cycle. The VHTR has an open fuel cycle and the SCWR can have an open or closed fuel cycle. The remaining four concepts have closed fuel cycles. Since most of the above concepts have high operational temperatures (GFR, LFR, MSR, VHTR, Canadian SCWR concept), they can be used for the cogeneration of hydrogen [8].

As an international effort on Gen IV development work, research is organized through the GIF. The participation of Europe in GIF activities takes place through EURATOM, focusing on the following concepts: GFR, SCWR, SFR and VHTR [8]. Research related to Gen IV reactors is also part of the European Sustainable Nuclear Energy Technology Platform (SNETP) agenda, whose actions aim to help reduce GHG emissions by 20% by 2020 (compared to 1990), make 20% energy savings and include a 20% share of renewable energies in the total energy mix [8].

Commercial deployment of Gen IV type reactors is not expected to occur before 2040 because major technological breakthroughs are still needed to solve some open questions. Thus, it is expected that three reactor generations - Gen II - IV - will coexist during the 21st century. New nuclear energy designs aim to push nuclear reactor technology to a completely new area of operating parameters, e.g., high temperatures and pressures, at the same time introducing different types of coolants not typically used in commercial nuclear power plants including sodium, lead, lead-bismuth and supercritical water. Lead and Lead-Bismuth Eutectic (LBE) were studied as coolants for fast reactor systems as early as in the 1950s (e.g. in the USA), but sodium were preferred over lead and LBE in the 1960s due to a higher achievable power density [9]. However,

LBE was selected as the coolant medium for many submarine reactors in the former Soviet Union. This led to a very large R&D programme on Heavy Liquid Metal Coolant (HLMC) technology and related materials. Extensive operating experience has been gained in the past in sodium fast reactors, e.g. in the Russian Federation by operating BOR-60, BN-350 and BN-600, in France by operating Rapsodie, Phenix and Superphenix, in the USA by operating EBR-II and Fast Flux Test Facility (FFTF), and in Japan by operating Joyo and Monju [9]. Based on this historical background, the level of technological experience for the use of sodium and lead as a coolant in a nuclear system is notable.

However, SCW as a coolant option was chosen as a subject of interest at VTT in the beginning of the 2000s due to the logical link between present LWRs and conventional Supercritical Fossil-Fired Plants (SCFFPs). The SCWR is the only Gen IV concept with water acting as a coolant and thus a more interesting option from a Finnish power company point of view. This concept is close to present LWRs and conventional supercritical power plants, and therefore has many features where cross-cutting research is beneficial, including the influence of water chemistry, mechanical properties of structural materials, and various corrosion phenomena at elevated temperatures and pressures.

1.1 Background

The SCWR has a thermal efficiency of roughly about 10% higher than existing LWRs. In addition, a plant simplification is achieved since the steam conversion process can be eliminated, i.e. the turbines are driven directly by using SCW. In general, SCWRs are LWRs that operate at higher pressure and temperatures, i.e. between 500 - 600 °C. The SCWR benefits from the two proven technologies, i.e., LWRs are the most commonly used power-generating reactors in the world, and supercritical fossil fuel fired boilers, a large number (around 400) of which are in use around the world [10]. SCFFPs do exist in the US, Japan and Germany where some of them date back to the early 1950s. This is the case, e.g., of the 1 000 MW_e plant in Germany (Niederaussem), which burns powdered lignite and heats water to 600 °C at a pressure of 26.5 MPa (thermodynamic efficiency of 45 %) [10]. Although SCWR concepts were studied in the 1950s and 1960s especially in US and former Soviet Union, no nuclear type reactors have ever been built. Beloyarsk Nuclear Power Plant (NPP) in Russia can be considered technically an SCWR since it operates at 500 °C. However, operating pressure is less than the critical pressure, i.e. 8 MPa. The main operating parameters of the Gen IV type reactors are shown in Table 2. For comparison the similar features of the European Pressurized water Reactor (EPR) is given as well (EPR Flamanville 3 (FA3) equivalent to OL3).

Table 2. Specific features of Gen IV concepts chosen by GIF [7].

	SFR	VHTR	GFR	LFR	MSR	SCWR	PWR (EPR FA3)
Neutron spectrum	Fast	Thermal	Fast	Fast	Fast or Thermal	Fast or Thermal	Thermal
Power density (MW/m ³)	300	5 to 10	100	100	330 (for fast spectrum)	100	92
Moderator	-	Graphite	-	-	Graphite for thermal spectrum	Water or heavy water for thermal spectrum	Water
Coolant	Sodium (liquid)	Helium (gas)	Helium (gas)	Lead or LBE (liquid)	Liquid salt (which is also the fuel)	Supercritical water	Water
Experience feedback	Approx. 20 reactors worldwide (400 reactor-years)	7 HTR already operated and 2 HTR under construction	None	No civilian reactors A few submarine propulsion units	Two thermal-spectrum reactors built	None	272 PWRs in operation worldwide, including 58 in France

Most future types of reactors will use very unique media as a coolant. However, as mentioned above, all of these reactor concepts are very well known from history, e.g., sodium- and lead-cooled fast reactors in France and Russia, respectively. The material choices for future types of reactors are cross-cutting topics that address the development needs of high-performance materials capable of working at a high temperature and in a harsh environment. At the same time, it is expected that the world will need additional capacity of coal- and gas-fired plants, especially in China and India. Thus, SCFFPs through advanced (ultra)supercritical technology with steam temperatures at 700 °C are currently one option for high-efficiency and low-emission electricity generation, which can benefit also from materials development effort related to the SCWR [10]. However, SCW presents many engineering challenges especially in material technologies. In order to solve existing material challenges, it is evident that reliable experimental data as well as the development and validation of modelling tools for material behaviour in the harsh SCW environment are needed. Materials in this type of reactor will be exposed to more severe conditions than faced in the current generation of LWRs, and to ensure higher efficiency of SCWR in energy production potential construction materials need to be studied.

The SCWR is an evolution from advanced LWR concepts and benefits from plant simplification compared to the current commercial LWRs. The European SCWR design, High Performance Light Water Reactor (HPLWR), is a thermal spectrum reactor using conventional LWR type oxide fuel that employs water rods as a moderator [11]. Table 3 summarizes the operating parameters of different SCWR designs under development world-wide [12]. The SCWR greatly differs from conventional LWRs by operating above the critical temperature and pressure of water. This means that the coolant does not boil while passing through the core. The operating pressure of the reactor is 25 MPa and the outlet temperature of the different type of SCWR designs varies between 500 and 625 °C. The combination of radiation (max. dose approx. 15 – 67 dpa), high-peak

cladding temperatures, even up to 850 °C, high pressure of 25 MPa and a rather harsh oxidizing environment make the SCWR one of the most challenging reactors from the standpoint of materials selection [11 - 13].

Table 3. Operating parameters of SCWR designs under development in EU (HPLWR), Japan (Super LWR / Super-Fast LWR) and Canada (Canadian-SCWR) [12]. CANDU-SCWR is known nowadays as the Canadian SCWR.

	SCWR target	HPLWR	Super LWR	Super-Fast LWR	CANDU-SCWR
Thermal/electrical power (MW)	3860/1700	2300/1000	2300/1000	2358/1000	2540/1220
Spectrum	Thermal/fast	Thermal	Thermal	Fast (breeder ratio≈1)	Thermal
Fuel	UO ₂ /MOX	UO ₂	UO ₂	MOX	UO ₂ /Th
Moderator	Light water	Light water	Light water	Light water	Heavy water
Reactor layout	RPV	RPV	RPV	RPV	Pressure tubes
Outlet core temperature (°C)	550	500	500	500	625
Core pressure (MPa)	25	25	25	25	25
Net electrical efficiency (%)	44	43.5	43.8	43.8	48
Economics	High	Higher than LWR	Higher than LWR	Higher than LWR	Higher than LWR

In the EU and Canada, the SCWRs are thermal neutron spectrum designs (HPLWR and Canadian SCWR, respectively), and in Japan both thermal and fast neutron spectrum reactor designs exist (Super LWR and Super-Fast LWR). In terms of material issues, the thermal spectrum introduces conditions with lower irradiation doses compared to the fast thermal spectrum design. Compared to other Gen IV concepts, the expected irradiation doses for the different SCWR concepts world-wide do not differ that much from the current LWRs, as seen in Fig. 1. In contrast, the expected operational temperature ranges are significantly higher compared to current LWRs.

The Super LWR and HPLWR are thermal designs with identical outlet core temperatures of 500 °C. These designs use UO₂ as a fuel. The main difference concerns the core layout: the HPLWR uses a three-pass core in contrast to the Super LWR which uses a simpler two-pass core [13, 14]. The Japanese Super-Fast LWR is based on the thermal design with a fast spectrum core fuelled with Mixed Oxide Fuel (MOX) [15, 16]. Fast reactors reduce the amount of spent LWR fuel and radioactive waste, and recycle plutonium. Thus, the advantages over thermal spectrum design are higher core power density and the usage of this design as a trans-uranic element burner [12 - 14]. However, the elevated irradiation doses, specifically in the case of fuel cladding, further increase the need for an advanced material solution for the fast spectrum core.

Figure 1. Temperature and dose ranges encountered by in-core structural materials of the SCWR designs and other five Gen IV reactor concepts including fusion compared to the current Gen II and Gen III LWRs [14].

The Canadian SCWR concept is continuing the international development effort on SCWR, which was initiated in the USA and Japan in the 1990s, and further R&D continued until 2010 by European and Japanese design teams [15]. The Canadian design concept presented in 2015 is based on previous studies and introduces new, innovative approaches to solve earlier issues challenging the material development, especially regarding fuel cladding materials with its ambitious target temperature up to 800 °C. The Canadian SCWR design differs from the two mentioned above in that it is a thermal pressure tube reactor fuelled with Pu/Th according to the latest reference design (i.e. differing from UO_2/Th in Table 3) [14]. In this design, the core outlet temperature is higher, even up to ~625 °C, allowing a medium temperature cogeneration application [12].

So far Canada, the EU and Japan have successfully completed the development of their SCWR concepts and they were reviewed by international peers [8]. China and the Russian Federation are also developing SCWR designs where core concepts are of the pressure-vessel type. The main difference between their concept approaches is that China is developing a thermal-spectrum core concept while the Russian Federation is working on a fast-spectrum core concept. China is also planning to host a review meeting of their SCWR concept with international peers in the near future [8].

1.2 Objectives and Scope

The scope of this thesis is to study the performance of selected candidate materials in SCW conditions by using experimental methods and available modelling tools to assess their usability as a construction material for expected service life in an SCWR. Potential construction materials, especially applicable to fuel claddings, were studied in terms of oxidation resistance. The materials' performance was evaluated by using weight change measurements and the applicable oxide film modelling method at different temperatures. This work was performed mainly between 2006 and 2016 as a part of the EU FP7 projects HPLWR Phase 2 (High Performance Light Water Reactor), GETMAT (Generation IV Transmutation Materials) and SCWR-FQT (Supercritical Water-Cooled Reactor - Fuel Qualification test), as well as the Academy of Finland projects NETNUC (New Type Nuclear Reactors) and IDEA (Interactive Modelling of Fuel Cladding Degradation Mechanisms). The work at VTT according to the original project plans focused mainly on experimental studies to elucidate the prevailing corrosion behaviour of the candidate materials in SCW conditions.

The objectives (1-3) in this study can be outlined as follows:

Objective 1: to investigate the corrosion performance of different material groups in SCW as a function of temperature and exposure time,

Objective 2: to study the effect of surface modification of austenitic stainless steels on corrosion resistance, and

Objective 3: to utilize the applicable modelling procedure to predict the behaviour of candidate materials in SCW conditions.

The structure of the work conducted in the publications related to the objectives is visually presented in Figure 2. It should be noted that irradiation was not considered as an environmental parameter in this study.

Figure 2. The structure of the work conducted in the publications of this thesis.

1.3 Dissertation Structure

This thesis consists of six scientific peer-reviewed journal publications (I-VI) and the present compendium. The publications are attached in the Appendixes. Chapter 2 of the thesis contains an overview of the SCWR R&D in terms of potential material options and requirements in the anticipated operating environment. It also contains a summary of the research results published in the literature on general corrosion resistance of candidate materials. Chapter 2 also contains the most relevant theoretical background of the modelling approaches for oxide film growth. A brief summary of SCW properties are also discussed. In Chapter 3, the experimental procedures and methods used in **Publications I - III** and **V** are described. Chapter 4 summarizes the obtained experimental and calculation results from **Publications I - VI**, and conclusions and recommendations for future work are given.

2. Theoretical Background

This chapter briefly presents the features of supercritical water and present potential material options for SCWR concepts. In addition, the theoretical background of modelling approach is introduced.

2.1 Properties of supercritical water

Water exhibits three well-known phases in the pressure-temperature-diagram: solid, liquid and steam. However, the fourth phase of water, namely supercritical water (SCW), is less well known. In the pressure-temperature diagram, water exhibits a critical point (T_c), T_c of 647.096 K at the pressure of 22.064 MPa [17], above which it is not possible to liquefy it by increasing/decreasing the pressure and thus no boiling occurs. A pressure-temperature diagram illustrating the critical point of water is shown in Fig. 3. Above T_c water is in the supercritical state and consists of small liquid-like hydrogen-bonded clusters within a gas-like phase [18]. Gas-like or liquid-like behaviour depends strongly on density variations, i.e. pressure.

Figure 3. Pressure-temperature diagram of water showing the critical point and pseudocritical line, which corresponds to the maximum value of the specific heat at particular pressure [19].

SCW has good heat transport properties and thus good ability to act as a coolant medium due to its relatively low viscosity and high specific enthalpy. It is also a very useful medium for different chemical processes due to excellent ionic transport properties and a complete solvency for most gases and organic compounds. The changes in physical and chemical properties at the critical point also affect rates of chemical reactions and thus control many important features such as corrosion reactions as well as deposition of radioactive species. When considering water radiolysis due to irradiation, water under conditions relevant to the SCWR is very different with respect to the stability of oxidizing species from water at 25 °C.

SCW has been an interesting medium for chemistry in the last two decades in relation to, e.g. accelerated chemical reactions, hydrothermal syntheses, waste oxidation, radioactive waste reduction, biomass conversion, plastic degradation, and synthesis of nano-particles [20]. Most of the applications benefit from the properties of SCW through the higher or lower solubility of organics, gases like oxygen, or monomers and salts. In addition, as a coolant medium for conventional fossil-fired power plants as well as nuclear

applications, i.e. different designs of SCWR, SCW has been the focus of research for the last 15 years, especially in China, Canada and Europe. However, measurement techniques in SCW conditions are challenging due to the high temperature and pressure, and in particular, in-situ experiments in autoclave environments are difficult to interpret without an understanding of the prevailing conditions. A reference electrode design is already available for SCW conditions but calibration of this system is still an open question. Experimental work in conjunction with modelling work, i.e. molecular dynamics and prediction of oxidation mechanism of materials during service lifetime, is a combination that can help to understand the characteristic of SCW as a coolant medium.

Since water consists of an extensive network of intermolecular hydrogen bonds, this network is responsible for its unique properties (e.g. boiling point, dielectric constant, density, ionic product). Hydrogen-bonding energy between molecules is relatively weak and the breaking of hydrogen bonds occurs when increasing temperature, which leads to increasing thermal motion of the water molecules. It is often described that a supercritical fluid such as SCW has both liquid- and gas-like characteristics. This is because in the supercritical region, this fluid typically consists of regions of high-density clusters of accumulated water molecules and low-density regions of individual water molecules [21]. When the thermal energy kT exceeds $\Delta\epsilon$ (k = Boltzmann constant, T = temperature in Kelvins, $\Delta\epsilon$ = potential energy barrier), the fluid molecules will always escape from the potential well and permanent liquid phase cannot form, as shown in Fig. 4 [22]. Accordingly, short-lived occasional molecular clusters form and disappear continuously, and this inhomogeneity in molecular distribution is one of the typically described characteristic properties of SCW.

Figure 4. Simplified presentation of potential versus separation distance for two interacting molecules in the liquid state. See text for details [22].

As shown in a range of studies [20], the properties of water exhibit dramatic changes when the critical point is exceeded. The fraction of hydrogen bonds between molecules decreases significantly above T_c compared to room temperature. However, the decrease in hydrogen bonding as well as dielectric constant from room temperature to 350 °C is about the same relation (factor of five) as the decrease through T_c . Changes in dielectric constant immediately after T_c are explained by pressure variations, as shown in Fig. 5. The dielectric constant of water drops from a value of 80 at 25 °C down to about 2 at 425 °C at 25 MPa. The low dielectric constant value favours the presence of uncharged species and ion association, and results in major changes in the ionic product of water. The density of high-temperature water and SCW is also shown in Fig. 5. In general, the drop of both physical properties is seen immediately after T_c at the critical pressure and the observed change moves towards higher temperatures with higher pressures.

Figure 5. a) Dielectric constant [21] and b) density of water [19] as a function of temperature and pressure.

It is very well known that oxidizing species produced by water radiolysis can significantly increase material degradation rates [20 - 22]. The key factor in controlling the effects of water radiolysis in an SCWR core is a well-defined water chemistry control, which is not yet decided by water chemistry experts. Bartels and Yurmanov [23, 24] proposed water chemistry with the addition of H_2 to an SCWR at a concentration of roughly ten times the current amount used in Pressurized Water Reactors (PWR). The idea of such an addition was a first attempt to minimize the effect of radiolysis by using a surplus amount of H_2 . The water chemistry strategy can eventually be confirmed experimentally in in-core test loops/reactor facilities, etc. However, modelling is the only option available now to predict material performance and coolant chemistry in in-core SCWR conditions. For this purpose, a Supercritical Water Loop (SCWL) in the Research Centre Řež, Czech Republic, was designed within the EU-funded

projects HPLWR Phase 2 and SCWR-FQT to give more insight about the water chemistry and material behaviour under simultaneous irradiation and SCW conditions. The primary goal of the SCWL is testing of materials for cladding and in-core applications at operational conditions of the European SCWR design HPLWR [13]. The maximum operational parameters (600 °C/25 MPa) are reached in the irradiation channel, which is also designed geometrically to fit into one rig of the research reactor LVR-15 [13, 25].

It should be noted that, although a very important issue was highlighted above, the present study does not consider irradiation as an environmental parameter, and thus it was left out of the focus of this thesis.

2.2 Materials research in SCWR development

Enhanced safety is one of the GIF technology goals, which is why SCWR safety characteristics have been improved compared to those of current reactors. Although many advantages compared to subcritical LWRs exist, in-core materials face specific challenges in terms of corrosion resistance, Stress Corrosion Cracking (SCC) susceptibility, creep / creep-fatigue resistance and last but not least, irradiation. According to the open literature, there is no commercially available material currently licensed for reactor applications that has shown good enough performance under SCW conditions at temperatures up to 650 °C [26 – 40].

The common issues for material challenges within future Gen IV reactor R&D are high temperature and irradiation, and thus cross-cutting topics are often included in different projects to maximize benefit from the project outcomes. Therefore, project plans are often determined by European-level road maps and other important documents to reach common objectives. This is also seen especially in the diversity of the tested materials and test parameters during this work performed at VTT. The experimental and modelling work performed within VTT projects had a general impact on the understanding of materials' behaviour in extreme environments, not only for Gen IV environments, but also other possible high-temperature applications like engines, e.g. nozzles. It should be noted that each project had its own work plan, scope and limitations and thus influenced the test matrices shown in this work. Consequently, the selected materials and testing parameters were typically a compromise from a bigger picture.

2.3 SCWR in-core material requirements

The development strategy of SCWR assumes that most required components can be adopted from present or future LWRs or from SCFFPs. However, components, in particular in-core components, will require dedicated tests due to differences in water chemistry and irradiation in SCWR service. In this study, the author has focused mainly on the European HPLWR design with the core

outlet temperature of 500 °C, estimated peak cladding temperature being in the range of 650 °C. The thin-walled components exposed to high temperatures, such as fuel claddings, set a combination of requirements that are more difficult to fulfil than those of SCFPPs. For the Canadian and European SCWR concepts, the allowable maximum corrosion penetration has been estimated to be around 130 - 140 µm after 20 000 h of service life [6, 14]. In comparison with the fire tubes of SCFPPs, which usually have a wall thickness of up to 10 mm, the thickness of nuclear fuel cladding is limited to about 0.5 – 0.6 mm (or 0.4 mm in EU HPLWR design) because of thermal conduction and neutron transparency requirements. In this case, as a rule of thumb, it can be said that such a thickness should allow a corrosion penetration depth of 25% of wall thickness at maximum, i.e. 0.13 – 0.14 mm, to prevent the collapsing of the fuel cladding. Although the entire fuel assembly is replaced typically every 3 years, the fuel cladding faces the greatest challenge for material selection due to the high radiation dose together with the peak cladding temperature of up to 800 °C depending on the design.

When taking into account the aforementioned issues, the material choices according to **Publications I - III** are mainly high-performance austenitic stainless steels, Ni-based alloys or novel Oxide Dispersion Strengthened (ODS) steels (F-M steels), as shown in Table 4. Other core components in the HPLWR, which are operating at 500°C may apply commonly used austenitic stainless steels. However, Ni-based alloys are not desirable for in-core components because nickel will produce He (neutron capture on Ni-58 produces Ni-59 and a gamma ray, followed by neutron capture on Ni-59 to produce Fe-56 and a helium atom). When considering the Canadian design, the estimated peak cladding temperature can be as high as 800 °C, which leaves little choice other than using Ni-based alloys or alloys with high Ni content like alloy 800H, even though they are not favourable for neutron economy. Such materials have shown the most promising margin against corrosion and creep in supercritical water [41 - 43]. However, as a drawback, the reactor core will need a higher enrichment due to neutron absorption in nickel, which was solved in the presented concept by using plutonium-thorium fuel (recyclable). It is evident, that more data on general corrosion are needed both on un-irradiated and irradiated materials before choosing the final in-core materials for different components. Stress Corrosion Cracking (SCC), and creep resistances are among the severest degradation modes which need to be understood and controlled, especially in the case of thin-walled components like fuel cladding.

Table 4. Some material choices considered in this work for SCWR design.

Alloy	Cr	Ni	Mo	Mn	Ti	Al/Nb	Other
1.4970	15	15.3	1.18	1.68	0.45		0.53Si
316NG	16.6	11.3	2.11	0.8			0.42Si
347H	17.6	10.7		1.84		0.56Nb	0.29Si
347HFG	18.1	11.8		1.65		0.8Nb ²⁾	0.42Si
HR3C	25.1	20		1.12			0.36Si
800H	20.5	30.8	0.13	0.67	0.36	0.26Al	0.36Si
Sanicro28	26.7	30.6	3.34	1.73			0.41Si
PM2000	20				0.5	6Al	0.5Y ₂ O ₃
MA956	19				0.3	4.5Al	0.5Y ₂ O ₃
690	30	58					10Fe

Currently, it is not quite evident which of the materials already licensed for in-core application in NPPs would be useful for thin-walled components in terms of the oxidation resistance at the highest design temperatures of the SCWR, although this issue has been extensively studied during recent years [14, 20, 26 - 48]. Austenitic stainless steels have been under consideration due to their corrosion resistance and improved irradiation resistance compared to Ni-based alloys. Different candidate materials for cladding solutions have been identified for different SCWR designs: Zr-modified versions of Type 316L and Type 310S austenitic stainless steels for Japan's pressure-vessel SCWR concept [15, 16], Ti-stabilized alloy 1.4970 austenitic stainless steel / high Cr ODS alloy PM2000 for the EU SCWR pressure vessel concept [14], and 800H for the Canadian SCWR [13, 14].

2.4 Potential material options

This chapter presents the potential material groups to be used in in-core component applications and the material requirements needed in the harsh SCWR environment.

Zirconium alloys

Zirconium (Zr) alloys were developed for use as nuclear fuel cladding in LWR conditions in the early 1950s. Owing to a low thermal neutron capture cross-section, reasonably good mechanical properties and adequate corrosion resistance in high-temperature water, Zr was selected for use in the cores of water-cooled nuclear reactors [44]. The good performance history has enhanced their wide use as fuel cladding and structural materials for nuclear reactors over

recent decades. However, Zr-based alloys cannot be utilized in SCW conditions at temperatures $> 400\text{ }^{\circ}\text{C}$. Different types of Zr-based alloys have been tested in SCW and test results in open literature [45 - 48] have shown that Zr-based alloys suffer from severe oxidation. Our autoclave test in SCW conditions confirmed this observation for Zr-2.5wt-%Nb and Zircaloy-4 at $600\text{ }^{\circ}\text{C}$ under a pressure of 25 MPa with $150\text{ }\mu\text{g/kg H}_2\text{O}$ dissolved oxygen (150 ppb) in the inlet water flow. Fig. 6 shows a Zr-2.5wt-%Nb (WWER pressure tube material) coupon specimen after exposure in SCW. The coupon sample ($25\times 15\times 5\text{ mm}^3$) was thoroughly oxidized after 100 h of exposure at $600\text{ }^{\circ}\text{C}/25\text{ MPa}$. The coupon sample remnants were collected from the bottom of the autoclave after the exposure.

Figure 6. Zr-2.5wt-%Nb coupon specimen ($25\times 15\times 5\text{ mm}^3$) after 100 h of exposure at $600\text{ }^{\circ}\text{C}/25\text{ MPa}$ in SCW (zirconia powder and pieces in a plastic container (diameter of 3.5 cm) after collecting from the bottom of the autoclave).

Since Zr-based alloys can be eliminated from the list of potential materials' solutions for a fuel cladding application in an SCWR, the remaining material groups are austenitic stainless steels, Ni-based alloys and ODS steels. Austenitic stainless steels are attractive due to their history in nuclear applications. Operating experience has been gained in the use of stainless steel fuel cladding in Boiling Water Reactors (BWR) and PWRs, and some stainless-steel alloys have been used at Beloyarsk NPP in Russia in superheated steam environments ($500\text{ }^{\circ}\text{C}/8\text{ MPa}$) [14]. The ODS alloys are promising in terms of high-temperature strength and irradiation resistance. However, their joining and manufacturing processes are still an open question and qualification of these materials for nuclear application would take many years.

Steel alloys and design criteria

The fuel assembly in the Canadian concept is planned to be changed every 3 – 3.5 years [48]. The change interval is one of the design criteria for the cladding material solution. The fuel cladding faces the highest possible temperature and irradiation dose, and cladding failure would be detrimental to the economics of plant operation. This is the reason why testing in autoclave conditions has been

focusing on fuel-cladding research mainly at 650 °C in Europe, which is the expected peak cladding temperature in the European HPLWR design. Guzonas et al. proposed design criteria for the fuel-cladding requirements in 2015 [48]. The starting point is that the fuel cladding cannot fail at the estimated peak cladding temperature. They listed several points when considering fuel cladding requirements in terms of corrosion resistance. The failure could occur by:

- 1) *through-wall penetration by general corrosion,*
- 2) *oxide build-up that can impede heat transfer or*
- 3) *stress corrosion cracking.*

Other issues must also be considered, such as mechanical strength and the very significant effects of irradiation, but these issues, including oxide build-up phenomena and SCC susceptibility, were excluded from the aim of this study, since the focus is on general corrosion challenges. In structures where the temperatures are higher than 300 °C or irradiation doses are above several dpa, suitable materials are expected to be either F-M steels or low-swelling austenitic stainless steels [26]. F-M steels (9 – 12 wt-% Cr) are more swelling resistant than austenitic alloys, i.e. an acceptable behaviour has been demonstrated at irradiation doses of 50 – 100 dpa. However, this material group cannot be utilized in SCW at temperatures higher than 500 °C due to the high oxidation rate [35]. The use of Fe-Cr-Ni alloys, i.e. austenitic stainless steels, is possible in terms of mechanical properties and dimensional stability, but more studies are needed to confirm their high-temperature oxidation resistance at temperatures higher than 600 °C, SCC resistance and IASCC behaviour under SCW conditions [14, 26, 45]. It is clear that a high-Cr content in the bulk material is needed for protective oxide film formation. The oxidation behaviour has been linked to the film formation typical for SCW conditions including an unprotective porous magnetite (Fe_3O_4) layer on top of a more protective inner Fe–Cr magnetite-type [$(\text{Fe,Cr})_3\text{O}_4$] and/or Fe–Cr spinel (FeCr_2O_4) layer [29 - 38].

To enhance the effectiveness of Cr in the material, surface modification may be needed for fuel cladding components using steels with bulk Cr content < 16 wt-% [28, 29, 42, 45]. According to **Publication V** and open literature, modification of a material's surface by changing the grain structure through cold working has shown a significant beneficial influence on the corrosion resistance of type 316L in SCW [28, 40]. This is due to the increased density of imperfections in the sample surface, e.g. dislocations and grain boundaries, further enhancing Cr diffusion to the alloy surface. However, the potentially adverse effect on SCC susceptibility resistance of cold-working is an open question and needs to be verified.

Austenitic stainless steels

One of the materials' required features is high neutron transparency. This is due to neutron economy, i.e. to minimize neutron losses and at the same time to maintain ongoing nuclear chain reactions [49]. Since Zr-alloys are not adequate under SCW conditions [45 - 51], focus has turned to austenitic stainless steels and Ni-based alloys as well as other possible materials like ODS steels [35]. The result is a compromise, since the aforementioned materials have more than 15 times lower neutron transparency compared to Zr-alloys, as seen in Table 5 [49]. For Ni-based alloys, their ability to form He in service conditions results in embrittlement and swelling, which makes them less favourable compared to austenitic stainless steels.

Based on the aforementioned facts, one of the most interesting material groups is the austenitic stainless steels due to their proven track record in current NPP applications [14, 52]. In general, austenitic stainless steels have good corrosion resistance in many process environments due to the formation of a protective Cr-rich oxide film. Molybdenum further increases the corrosion resistance but both elements are ferrite-forming elements and to maintain a fully austenitic structure, the amount of Ni must be increased.

Table 5. Calculated effective neutron absorption cross-section (neutron absorption cross-section per unit of yield strength compared to Zr alloys) and maximum service temperature for selected materials [49].

Material	Maximum service Temperature (°C)	Effective neutron absorption cross section in relation to Zr alloys
Zirconium alloys	400	1
FM stainless steels	500	15
Inconel	500	15
Austenitic stainless steels	600	15
ODS alloys	700	15
Nb-1Zr alloy	800	20
ZrC	900	0.20
SiC	900	0.10
Tantalum alloys	1000	50
Molybdenum alloys	1100	10
Tungsten alloys	1200	35

** Based on neutron irradiation between 10 and 50 dpa*

One of the most severe failure mechanisms in austenitic stainless steels is SCC [53, 54]. In particular, Intergranular Stress Corrosion Cracking (IGSCC) in oxidizing BWR environments has been observed to cause problems in the components' service life. Sensitization is the main factor affecting the appearance of IGSCC and it is, most often, a result of nucleation and growth of chromium-rich carbides on grain boundaries, resulting in grain boundary chromium depletion [53]. Grain boundaries with Cr-depleted areas are sensitive to general corrosion and in conjunction with stress and suitable environment also to IGSCC. In order to avoid this, the alloy's chemical composition is adjusted by reducing the carbon content to low enough levels. This is the case in Types 316L, 316LN and 316NG stainless steels with carbon content in the range of 0.02% [53]. Since carbon acts as a strengthening element, nitrogen is

added to these steels to compensate for the shortage of carbon content and thus achieve good mechanical properties. Nitrogen is also used to reduce chromium-rich carbide formation. This a concept that is utilized in the French RCCM guidelines (Design and Construction Rules for the Mechanical Components of French PWR Nuclear Islands), which allow a carbon content of 0.035% in their nitrogen-strengthened Type 316 stainless steel with 0.08% N. Another way to avoid sensitization is to tie up the carbon into precipitates. This approach is used in stabilized stainless steels like titanium- and niobium-stabilized stainless steels, Type 321 and 347, in which the carbon is tied into Ti(C,N) or Nb(C,N) precipitates [53].

Types 304L and 316L are the most used types in nuclear facilities and NPPs, i.e. PWRs and BWRs. Also type 321 is used in steam generator tubes and pressure vessel cladding in Water-Water Energetic Reactors (WWER), and Type 347 for many components in German reactors. The use of these stainless steels in nuclear applications is due to good corrosion resistance and good mechanical properties at operating temperatures [54]. In addition to their excellent behaviour in current NPP conditions, austenitic stainless steels have been reported to have adequate oxidation and creep resistance in SCW conditions with certain limitations [14, 26, 55–62]. The candidate fuel cladding alloys considered for the Canadian, EU and Japanese SCWR designs are shown in Table 6 [14]. These materials are being considered as claddings for fuel, which will be replaced at relatively short intervals. Other structural components require much longer lifetimes compared to the fuel cladding. In Table 6, most of the candidate fuel cladding materials are standardized austenitic stainless steels or modifications of them.

Table 6. Candidate cladding materials to be considered for the Canadian, EU and Japanese SCWR designs [14].

Alloy	Fe	Cr	Ni	Mo	Mn	Si	Al	Zr	C	Ti	Others
310	bal	24.5	20.2	0.29	1.17	0.33	-		0.048		
310S +Zr	bal	25.04	20.82	0.51		0.51		0.59	0.034		P: 0.016
310S FG	bal	24.74	21.92	-	-	0.25	-	-	0.099	0.81	N: 0.0006 P: <0.005 Nb: 0.26
310S FG	bal	25.03	22.81	2.38						0.41	N: 0.002 P: <
347	bal	18.0	11.0	-	2.0	1.0	-	-	0.08	-	Nb: 10xC*
800H	bal	22.5	34.8	-	1.59	0.95	0.45	-	0.08	-	
625	4.9	22.6	bal	9.8	0.43	0.47	0.47	-	0.09	0.45	Nb: 3.7 Cu: 0.68
214	3	16	75	-	0.5	0.2	4.5	0.1	0.05	-	Y: 0.01 B: 0.01
1.4970	bal	15	15.3	1.18	1.68	0.53			0.095	0.45	
ODS PM2000	bal	19					5.5			0.5	Y ₂ O ₃ : 0.5
316L	bal	16.6	10	2.0- 3.0	1.9	0.65			0.022		
316L(N)	bal	18	12	2.0- 3.0	2.0	1.0			0.030		N: 0.16
316Ti	bal	16.6	12.1	2.03	1.15	0.45			0.032	0.38	
316L + Zr	bal	16.54	10.71	2.22		0.46		0.56	0.006		P: 0.016

2.5 Modelling approaches for oxide film growth

The surfaces of many metals are covered by an oxide film under different process conditions. The oxide film can either be continuous and protective or discontinuous and un-protective. This is the case for many metals where the outer oxide is porous and less protective, and the inner layer is a barrier layer that hinders the corrosion processes. This assumption has been taken as a starting point for the modelling aspects in **Publications IV and VI** for candidate materials in SCW conditions.

To understand the long-term behaviour of oxide films and to estimate their anticipated service time in severe environments, the growth kinetics of these protective barrier films is of utmost importance. The composition and structure of the oxide film determines how anions and cations are transported through the oxides. These transport phenomena affect the corrosion rate of the material.

To present the oxide growth kinetics, knowledge about the transport processes in the oxide films is needed.

By combining data from experimental tests with a theoretical model, many important features, like rates of transport of ionic species or the effects of different anions on the oxidation rates of construction materials, can be evaluated. The prediction of the growth rate of oxide film and its general ability to resist SCW is typically described through experimental autoclave tests in conjunction with modelling. Therefore, modelling tools are needed in order to give some estimation about the materials performance after long-term exposure until the expected replacement of the entire component, e.g. a fuel assembly.

Models for predicting oxide film growth kinetics can be divided into empirical and deterministic models. Empirical models are based on observed corrosion rates, e.g. measured from coupons exposed in autoclaves, which are then fitted to the empirical formulae. However, they can seldom be generalized to describe the behaviour of a range of materials in a variety of operating conditions [63]. The deterministic models are based on the expected mechanisms of oxidation processes which can be translated into mathematical equations [64]. To understand the oxide growth kinetics of materials, information about the interfacial reactions at the inner layer / outer layer and outer layer / coolant medium interfaces, and the transport mechanisms are needed. Modelling of oxide growth through a deterministic model enables the prediction of oxide film growth as a function of time. Seyeux et al. [64, 65] discussed three main models that describe the oxide film growth on metals and alloys:

- *Cabrera-Mott model,*
- *Fehlner-Mott model and*
- *Point Defect model.*

The Point Defect Model (PDM) is a deterministic model for passive materials involving kinetic factors for oxide film dissolution parameters. Of the many models reviewed by Seyeux et al. [64], the PDM is the only one that considers the interfacial potential drops during the oxide growth. The PDM emphasizes the role of mobile charged point defects in conducting the current through the film. However, in this model, (i) no parameters relative to the substrate alloy are considered, and (ii) the growth is limited by the flow of oxygen vacancies through the film, i.e. transport via both cation interstitial and vacancy positions are not taken into account. Seyeux et al. [64, 65] presented a critical review on the existing model approaches and proposed an upgraded model for the oxide film growth. The phenomena identified to be involved in the formation of oxide films in liquid water are:

- 1) *the growth of the oxide layer,*

- 2) *the dissolution of the oxide film, and*
- 3) *the precipitation of dissolving species from the solution.*

Considering phenomena 2) and 3), the dissolution of oxides in SCW at temperatures above about 500 °C is expected to be minimal, although several studies report vaporization of Cr(VI) in sufficiently oxidizing conditions [66, 67]. Also, a direct chemical oxidation of elements by water/oxygen is assumed to form the outer oxide layer since ionic compounds are sparingly soluble in SCW. We also assume that the inner layer is the most important part of the oxide film system, since as a barrier layer it determines mainly its corrosion behaviour by controlling the transport of matter through this layer. The growth of the oxide layer 1) and its forming structure are of utmost importance to understand in order to predict the materials performance under SCW conditions.

Kinnunen [68] summarized the PDM and its deficiencies and modifications needed to develop it further. The PDM has been developed for electrochemically-formed oxide films. This led to the formulation of the so-called Mixed Conduction Model (MCM). The MCM represents the growth of the film as a combination of interfacial electrochemical reactions and transport of ionic point defects (interstitials and vacancies) [69-73]. MCM is an extension of the PDM allowing to assess quantitatively the electronic properties of the oxide layer. The roles of different types of defects (interstitials or vacancies) in the oxide film are a key to understand the mechanism of oxide film growth on construction materials. A more detailed description of MCM was presented by Bojinov and co-workers in refs. [69 - 73].

The MCM procedure is used in the current work to extract the vacancy and interstitial transport parameters of oxide films formed on candidate materials in SCW conditions. It should be noted that this modelling procedure does not consider parameters derived from the electrochemical properties of the oxide film as exploit in LWR conditions. This is because under SCW conditions, the conductivity of the coolant medium is negligible and measurement of the corresponding parameters is technically challenging. This led to the development of the calculation method, which is described in the following sections.

Deterministic modelling of the general corrosion of candidate materials in SCW conditions

The ultimate goal of this work was to increase our understanding of both general and localized corrosion mechanisms of candidate materials using a deterministic model of the oxide films in SCW conditions. The objective was that the model should be able to predict the rate of oxidation of a range of materials including ferritic-martensitic steels, austenitic stainless steels, Ni-based alloys and ODS alloys.

The first step towards the estimation of the kinetic and transport parameters of individual metallic constituents in the candidate materials was made in **Publication IV** by testing the validity of a quantitative model. This procedure was originally developed for LWR environments taking into account the in-depth composition of oxides on stainless steels, as proposed earlier by Bojinov et al. [68, 69-71]. Based on this, a calculation procedure was developed and verified using chemical composition data of the oxide film on ferritic-martensitic P91 and austenitic stainless steel 316L exposed for up to 100 h in SCW at temperatures between 500 and 700 °C. To predict the evolution of the inner layer thickness with the time of exposure, a logarithmic growth law previously employed at subcritical temperatures [69 - 73] was successfully employed. On the other hand, the discrete crystallites of the outer layer were assumed to grow via precipitation of material dissolved from the substrate through the inner layer of the oxide. This was formally modelled as a diffusion process and resulted in a parabolic growth law [72].

In Publication VI, the kinetic and transport parameters of inner and outer layer growth on austenitic steel and Ni-based alloy were estimated. This model presumes that the growth of the outer layer is dominated by the transport of cations through the inner layer via an interstitialcy mechanism. The updated model can accurately reproduce the depth profiles of individual metal constituents both in the inner and outer layers, and also in the diffusion layer of the alloy located between the inner layer and the substrate material. By using this calculation approach, kinetic and transport parameters of inner and outer layer growth were estimated for oxidation for longer exposure times, from 600 to 2 000 h, at 650 °C. The calculation procedure is described in more detail below.

Main processes and calculation procedure

According to the proposed approach as described in **Publications IV and VI**, the growth of the protective barrier layer (inner layer) of oxide progress via generation of normal cation positions and oxygen vacancies at the interface with the alloy. At the same time with this reaction, assuming materials with high-bulk chromium content, the growth of the oxide film can advance via chromium cation transmission through the inner layer where generation of cation vacancies at the outer interface is involved. Other minor constituents are presumed to proceed through the inner layer via an interstitialcy mechanism. It is assumed that the growth of the non-protective outer oxide layer forms through direct reaction with interstitial cations and water and/or oxygen at the inner layer / outer layer interface. A simplified picture of the processes described above is presented in Fig. 7. The proposed calculation procedure is described in **Publications IV and VI** in more detail.

Figure 7. A simplified scheme of the growth of the inner and outer layers of the film formed on Fe-Cr-Ni alloy according to the proposed approach. For details see text above.

As described in **Publication IV and VI**, the transfer of electrons through the inner layer to couple the oxidation of metal with the cathodic partial reaction of reduction of water is needed for film growth to proceed under free corrosion conditions. It is proposed that water molecules transfer through the non-protective outer layer with many defects and they are reduced to hydrogen gas, accepting electrons from oxidation of the metal constituents that are transported through the inner layer according to the overall reactions:

which introduces combinations of k_4 and $k_{3\text{Cr}}$ processes (according to Fig. 7) and the reaction of reduction of water to form gaseous hydrogen. This model approach does not consider electronic conduction to be a rate-limiting step. Within the MCM, it is assumed that ionic point defects play the role of electron donors and the electronic conduction is connected to the transport of ionic defects. The applicability of this assumption was demonstrated and confirmed by the CER/CEI measurements in SCW conditions. The specific conductivity of the oxide layer on alloy 316L was very close to magnetite, i.e. behaving like a good electronic conductor [74].

During oxidation in SCW, it is assumed that the large defect density in the oxide is not likely to support a high electric field as reported by several authors in subcritical conditions [68, 69 - 73]. Thus, the low-field approximation of the generalized transport equation of Fromhold and Cook [75] was utilized as a

starting point for the flux of point defects of type j ($j = \text{I, O and V}$, i.e. interstitial cations, oxygen and cation vacancies):

$$J_j(x, t) = -D_{i,j} \frac{\partial c_j(x, t)}{\partial x} - \frac{XF\vec{E}}{RT} D_{i,j} c_j(x, t) \quad (3)$$

The electric field strength in the oxide is assumed to be independent of distance within the oxide following previous treatments presented through the PDM and MCM [69 - 73]. The main reason for this is the so-called band-to-band tunnelling between electronic states that produces a separation of charge to compensate variations in the field strength. The concentration of a metallic oxide constituent is introduced as its atomic fraction, $y_j = c_j V_{m,MO}$, where $V_{m,MO}$ is the molar volume of the phase in the existing layer. It is assumed as a molar volume of spinel oxide ($47 \text{ cm}^3 \text{ mol}^{-1}$). This can be seen as a simplification because several other phases, like Fe_2O_3 , Cr_2O_3 , and spinel-oxides have been reported to form during high-temperature oxidation of ferritic and austenitic alloys. However, the differences between the molar volumes of different phases is in the order of 10%, and thus this presumption is reasonable.

To obtain the compositional profiles in the inner layer, the system of equations is solved subject to the initial and boundary conditions using a Crank-Nicholson method [76]. Further, to calculate the compositional profiles in the outer layer, a system of equations analogous to inner layer treatment was employed.

As a starting point, a growth law was adopted to estimate inner layer thicknesses derived from both the PDM and MCM. This approach was previously employed to predict oxide film growth on austenitic materials in LWR environments:

$$L_i(t) = L_i(t=0) + \frac{1}{b} \ln \left[1 + V_{m,MO} k_2 b e^{-bL_i(t=0)} t \right], \quad b = \frac{3\alpha_2 F \vec{E}}{RT} \quad (4)$$

Contrary to the estimation of inner layer thicknesses, a growth law for the outer layer was also proposed. As an assumption, the outer layer is formed via the reaction of interstitial cations transferring through the inner layer and reacting with water. A model for the growth of dual-layer films proposed by Sloppy et al. [77] was used as a starting point. In that model, Sloppy et al. assumed that the outer layer growth is due to the flux of interstitial cations through the inner layer. This equation is valid subject to the assumption that the transfer coefficients for all the reactions at the alloy / inner layer interface are equal. Integration of this equation from 0 to t (the actual oxidation time) and 0 to $L_{\text{out}}(t)$ gives the following growth law:

$$L_{\text{out}}(t) = \frac{\sum_j k_{1j} y_{j,a}}{k_2} (L_{\text{in}}(t) - L_{\text{in}}(t=0)) \quad (5)$$

3. Experimental part

The aim of the experimental part of this thesis is to evaluate the corrosion resistance of candidate materials under SCW conditions focusing on existing materials. For this purpose, a water-recirculating loop connected to a supercritical autoclave was employed and an assessment of corrosion resistance of the studied materials was carried out using weight loss/gain measurements and post-test analyses including Scanning Electron Microscopy (SEM) in conjunction with Energy Dispersive X-ray Spectroscopy (EDS) and Glow Discharge Optical Emission Spectroscopy (GDOES).

3.1 Materials and environment

In this part the focus is on the group of materials which comprises potential candidates for different SCWR components, as described in **Publications II and III**. At a later stage, a new set of materials is introduced for oxide film modelling purposes. The chemical compositions of the studied alloys for general corrosion tests are shown in Table 7. In the water-cooled reactors that are currently in operation worldwide, the strategy to mitigate component degradation is conducted using water chemistry parameters which reduce the aggressiveness of the fluid toward the material. The starting point is that the used water chemistry reduces the degradation rates to achieve the designed service life for each component. Equally, the water chemistry has an important role in terms of materials' selection for the SCWR design. This work has been conducted mainly in Canada, Ukraine and the Czech Republic [78 - 81]. So far, most of the experimental work available in the open literature has been performed using a combination of a normal BWR and SCFFP water chemistries. This includes a low-conductivity, neutral pH, added oxygen to a certain level (O_2 10 – 8 000 ppb, $\mu\text{g}/\text{kg H}_2\text{O}$) or added hydrogen (H_2 30 cc/kg H_2O , equivalent to 2 700 ppb of H_2) water chemistry [26, 45, 78 - 83]. This strategy was also the starting point at VTT in 2006, which widely determined the test matrices including water chemistry and studied alloys. Typically, oxidation exposure tests were performed at temperatures between 400 and 700 °C and using autoclave pressure of 25 MPa. Initially in 2006 - 2010, the applied pressure in the tests was kept at 30 MPa corresponding to the desired target pressures for better plant efficiency in future SCFFP designs. At that time, the development work on SCFFP was in focus and later this pressure was fixed to 25 MPa according to the EU FP7 project HPLWR Phase 2 work plan, i.e. applicable to nuclear design. The target ranges and measured values typically used in the test

campaigns at the temperature of 650 °C and pressure of 25 MPa are shown in Table 8.

Table 7. Chemical compositions of the studied alloy groups according to publications II and III: Ferritic-martensitic steels including ODS steels, austenitic stainless steels and Ni-based alloys in weight-% (“bal” is balance).

Alloy	C	Si	Mn	S	P	Cr	Ni	Mo
P91	0.11	0.41	0.43	0.005	0.012	8.3	0.11	0.96
P92	0.08	0.09	0.42	0.006	0.001	8.9	0.02	0.49
ODS (1)	0.021	0.12	0.36	0.007	0.002	9	0.05	0.02
ODS (2)	0.035	0.03	0.4	0.011	0.001	9.2	0.03	0.02
PM2000	0.005	0.02	0.08	0.001	0.007	20.1	0.03	0.09
316NG	0.014	0.42	0.8	0.001	0.032	16.6	11.3	2.11
1.4970	0.095	0.53	1.68	0.001	0.007	15	15.3	1.18
BGA4	0.11	0.49	6.1	0.024	0.02	22.9	15.4	0.14
800H	0.06	0.36	0.67	0.003	0.01	20.5	30.8	0.13
625	0.02	0.07	0.05	0.005	0.001	22.4	bal	9.1
Alloy	Cu	Al	W	V	Ti	Co	Nb	Fe
P91	0.02	0.01	<0.01	0.23	<0.003	<0.01	0.05	bal
P92	<0.01	<0.01	2.1	0.22	<0.01	<0.01	0.05	bal
ODS(1)	<0.01	<0.01	1.3	0.21	<0.003	0.01	<0.01	bal
ODS(2)	<0.01	<0.01	1.3	0.21	<0.003	0.01	<0.01	bal
PM2000	<0.01	5.5	<0.01	0.03	0.43	0.04	0.03	bal
316NG	0.23	0.007	0.02	0.04	0.004	0.07	0.01	bal
1.4970	0.02	0.05	<0.01	0.02	0.45	0.03	-	bal
BGA4	2.7	-	1.49	0.31	-	-	0.61	bal
800H	0.06	0.26	<0.01	0.04	0.36	0.09	0.01	bal
625	0.03	0.29	0.12	<0.01	0.25	0.06	3.3	2.6

Table 8. The realized test parameters in typical autoclave tests according to Publications II, III and V.

Quantity	Realized values (mean ± SD)
Temperature	Recorded mean 649 ± 1.0°C
Pressure	Recorded mean 250 ± 0.9 bar
Inlet conductivity	Recorded mean 0.055 ± 0.001 µS/cm
Outlet conductivity	Recorded mean 0.30 ± 0.11 µS/cm
Inlet dissolved O₂	Recorded mean 150 ± 0.5 ppb
pH of the inlet water	(Pure water)
Flow rate	~ 3-10 ml/min (Full renewal of autoclave volume about every 1 - 4 h)

Based on literature, the present candidates for European SCWR core internals are austenitic stainless steels with sufficient oxidation and creep resistance up to 500 - 550 °C. High-chromium (> 18 wt-%) austenitic steels and ferritic/martensitic ODS steels are considered, in the long term, for fuel cladding due to their good oxidation resistance and expected high mechanical strength up to 650 °C [14]. However, no single alloy with low enough Ni content in the bulk alloy has clearly satisfied the design criteria in terms of corrosion resistance at the temperature of 650 °C and under the pressure of 25 MPa. For this reason, the general corrosion, i.e. weight change, tests were conducted first on iron- and nickel-based alloys at temperatures of 400 °C, 500 °C, 650 °C and 700 °C in SCW using pure water chemistry with an oxygen concentration of 100 - 150 ppb.

3.2 Weight loss / gain experiments

A screening test was introduced as a starting point for this study to assess general corrosion rates on different material groups, including electrochemical characterization methods on selected materials, as described in **Publications I - III**:

- *F-M steels,*
- *austenitic stainless steels,*
- *nickel-based alloys and*
- *ODS steels.*

Some materials used in the general corrosion tests were selected for further studies. The effect of surface treatment on oxidation resistance was studied in **Publication V**, and oxide film growth modelling was attempted in **Publications IV and VI**, as presented later in this chapter. General corrosion tests were mostly done on 25x15x5 mm³ coupon specimens. Around 30 µm of the surface layer was removed by careful mechanical polishing to diminish the effects of the manufacturing procedure (cold working by grinding). The specimen geometry is shown in Fig. 8. The samples were placed on a specimen holder rack using electrically insulating ZrO₂ (Mg-stabilized) washer rings, as shown in Fig. 9. The specimen rack was also insulated from the autoclave body using ZrO₂ washer rings.

Figure 8. Coupon specimen geometry used in most of the weight change tests. The specimens were typically prepared either by a milling cutter or Electric Discharge Machine (EDM) and then ground with emery paper.

Figure 9. A specimen rack ($l = 150$ mm, $d = 50$ mm) for the coupon specimens used in autoclave with electrically insulating ZrO_2 (Mg-stabilized) washer rings.

A schematic presentation of the supercritical autoclave connected to a recirculation water loop, and a photograph of that autoclave, are shown in Fig. 10. The loop consisted of a high-pressure pump, a heat exchanger and a preheater. Water returning from the autoclave flowed through the heat exchanger and a cooler. The maximum working temperature and pressure of the system were 700 °C and 42 MPa, respectively. The loop was pressurized using a diaphragm pump and a back-pressure regulator. The maximum flow rate of the high-pressure loop was 85 ml min⁻¹. The flow rate was typically between ~3 and 10 ml/min, resulting in a refreshment of the autoclave volume roughly every 1 – 4 h. The applied flow rate was limited by the autoclave and preheater heating capacities and related risk for leakage. The main loop material was 316L and the autoclave was made of Nimonic 80A.

a)

b)

Figure 10. a) A schematic presentation of the water recirculation loop connected to a supercritical autoclave and b) photograph of supercritical autoclave. The main construction material of the supercritical autoclave is Nimonic 80A.

In the first stage, the exposure tests lasted up to about 600 hours. During the experiments, the inlet water conductivity was below $0.1 \mu\text{S}/\text{cm}$ and the pH at room temperature was, on average, around 8.4 (due to NH_3 feed in the inlet flow it is alkaline and not close to 7), as shown in Figs. 11 and 12, respectively. The outlet water conductivity in Fig. 11 indicates some impurities in the coolant in the beginning of the exposure test. This kind of measurement arrangement gives a reasonable measure of water purity before entering the autoclave test section. However, the water conductivity after the test section in the low-pressure part (at room temperature) most probably does not reflect the water's real aggressiveness due to corrosion product solubility in SCW. The water is cooled

down below the critical temperature and the part of dissolved cations precipitate back on the available surfaces and thus are not seen in the conductivity measurements. The dissolved oxygen content of the inlet water flow was maintained typically between 100 – 150 ppb in all tests unless otherwise mentioned, as seen in Fig. 13. The weight of the samples was measured before and after the corrosion tests and weight changes per unit area were calculated. A Mettler AT261 (accuracy 0.11 mg with 50 g mass) was used for weight measurement. After the weight change measurements, cross-section samples were prepared by cutting the coupons using a diamond saw. After cutting, the cut sections were moulded into electrically conductive resin and then mechanically polished with emery paper and diamond paste. The cross-section samples were then studied using SEM to determine mainly the oxide layer thickness and EDS to determine element distribution.

Figure 11. The measured inlet and outlet water conductivities during an exposure test at 650 °C/25 MPa.

Figure 12. The measured pH in the low-pressure part of the water-recirculating loop during an exposure test at 650 °C/25 MPa.

Figure 13. Dissolved oxygen content during an exposure test at 650 °C/25 MPa.

Figure 14 summarizes the weight loss/gain results on specimens polished with #1200 grit emery paper for up to 600 h (except in the case of 650 °C, at which exposure time was up to 578 h due to autoclave lid leakage). As discussed in **Publication II and III**, the tested materials showed generally similar trends, i.e. the weight gain increased with temperature. The results show that the best performers in terms of corrosion resistance under SCW conditions were high-chromium (> 18% Cr) and high-nickel (> 15% Ni) alloys, including ODS steel PM2000, stainless steel such as 800H and creep resistant laboratory heat BGA4, and Ni-based alloy 625. For austenitic stainless steel 316LNG, the weight change was relatively small up to 500 °C, but at 650 °C it was almost as high as in the F-M steels. Based on this, it seems that there is most probably a change in the oxidation mechanism of this material at temperatures higher than 500 °C.

Figure 14. Weight change test results for different candidate materials at temperatures of 400, 500 and 650 °C. Exposure time was 600 h and water chemistry was pure water with 100-150 ppb dissolved oxygen. PM = Powder metallurgy [35].

The change in oxide film composition on the outer oxide layer is depicted in Fig. 15. The disappearance of Cr_2O_3 from the outer layer at a higher temperature of 650 °C is confirmed by the SEM cross-sections and EDS analysis shown in Fig. 16 and Table 9, respectively. This can be tentatively explained in oxygenated water ($\text{DO}_2 > 10$ ppb) by the formation of a soluble Cr(VI) species, i.e. (CrO_4^{2-}) [84, 85]. On the other, Guo et al. reported that irregular oxide film of Cr_2O_3 might occur due to the low oxygen content in the SCW and/or, in general, the relatively low-Cr content in Type 316L (ca. 16 wt-% Cr) [86]. At higher temperatures (> 500 °C), it seems that the oxide structure on austenitic stainless steel 316NG resembles that on F-M steels, and the oxidation rate will increase significantly, as seen in Fig. 16. EDS-spot analyses on Type 316NG specimens after exposure in SCW at 500 and 650 °C for ~600 h are shown in Table 9. The film formed at 650 °C exhibits a double-layer structure with an inner layer containing Cr and Ni and enriched with small amount of Mn and Mo. In contrast, the outer layer can be identified as being almost pure iron oxide according to the EDS analysis. Both layers had significant porosity, and cracks are observed throughout the oxide scale, indicating that the protective ability of the oxides is most likely controlled by a very thin layer adjacent to the alloy/oxide interface, as hypothesized also for oxides formed in subcritical water [68]. The yellow translucent colour on the specimen exposed at 500 °C shown in Fig. 15 b) suggests a thin oxide layer enriched with Cr, as indicated also by the EDS analysis in Table 9. However, the cross-section SEM image shows that the Cr-rich layer is not continuous, and irregular Cr_2O_3 islands cover the surface, as shown in Fig. 16 b). In this case the formation of Cr_2O_3 leads to Cr depletion in the alloy substrate and might cause reduced oxidation resistance at longer exposure times as well as at higher temperatures [84], as shown in Figs. 15 c) and 16 d).

Figure 15. Visual inspection of Type 316NG coupon specimens (25x15x5mm) in SCW a) at 400 °C, b) at 500 °C and c) at 650 °C after around 600 h of exposure. The scale line below the coupon samples is in millimetres.

Figure 16. Surface morphology and cross-section of the oxide layer on austenitic stainless steel 316NG after 600 h of exposure with 100 - 150 ppb DO_2 : a) and b) at 500 °C, and c) and d) at 650 °C [35].

Table 9. EDS-spot analyses of oxide films formed on Type 316NG specimens after test in SCW conditions at 500 °C and 650 °C with 100 - 150 ppb dissolved oxygen in the inlet water flow.

Type 316NG	Chemical compositions (weight-%)					
Outer layer	O	Cr	Fe	Ni	Mn	Mo
500 °C	35.81	4.13	56.55	1.95	0.41	0.54
650 °C	28.11	0.46	71.35	-	-	-
Inner layer	O	Cr	Fe	Ni	Mn	Mo
500 °C	-	-	-	-	-	-
650 °C	22.95	22.66	35.08	14.84	1.23	2.6

For alloys in which the oxidation is diffusion limited, oxidation will follow parabolic kinetics. The experimental weight change (W^2) versus temperature dependence seems to follow an Arrhenius-type law as follows:

$$W^2 = Ae^{-\frac{E_a}{RT}}t \quad (6)$$

where A is a constant, E_a is the activation energy, R is the universal gas constant, T is the absolute temperature, and t is the exposure time. For constant time exposures, the slope of a plot of $\ln(W)$ versus $1/T$ is $E_a/2R$. However, for short exposure times, as represented in Fig. 17, it is assumed that the weight gain behaviour is linear, and in this case the slope of the plot of $1/T$ is then E_a/R . Using this expression, the weight change versus temperature seems to follow an

Arrhenius-type law for both conventional F-M steels P91 and P92, as shown in Fig. 17. This statement is, however, true only with the assumption that the oxide is homogeneous, or the diffusion is bulk diffusion such that the oxides grow only by Fe outward diffusion (and also by inward diffusion of oxygen). When taking this assumption into account, it can be assumed that the oxidation of conventional F-M alloys P91 and P92 are diffusion limited. Contrary to this, the austenitic stainless steel 316NG exhibited an increased oxidation rate above 500 °C possibly referring to a change in reaction mechanism. The mechanism observed on Type 316NG is most probably related to fast oxygen diffusion along grain boundaries or due to molecular oxygen permeation through defects in the outer oxide layer (micro cracks and pores) at temperatures > 500 °C, like those observed in Fig. 18, eventually leading to internal oxidation.

Figure 17. Oxide growth assuming linear growth law ($t = 100$ h) in F-M steels P91 and P92 and austenitic stainless steel 316NG over the temperature range of 400 to 650 °C in SCW conditions with 100 - 150 ppb oxygen [35].

All specimens undergo cyclic temperature variation because the autoclave is cooled down and reheated every time the specimens are removed, i.e. in this test campaign after 24, 168 and 600 h of exposure. The observed pore formation is related to the differences in transport mechanisms through the oxide scale during the heating and cooling of the autoclave as well as the presence of mechanical stresses. In Fig. 18, the internal oxidation zone on Type 316NG specimen is expected to be the sum of oxide film formed along the grain boundaries as well as precipitation of oxide particles in the grain interior (inter- and intragranular oxidation). The pores are most probably a result of the accumulation of vacancies formed during the oxidation process. It is assumed that the pore formation front is most probably next to the grain boundaries because of higher diffusivity compared to grain interior. In general, this feature is most probably associated with the tendency of oxide spallation, especially under cyclic thermal conditions. A discontinuous surface oxidation was typically

observed in our tests on high-Cr alloys like 800H at temperature > 550 °C, and this type of behaviour has been normally linked to spallation of the outer oxide layer.

Figure 18. a) SEM cross-section and b) surface morphology of the Type 316NG with polished surface using #1200 grit emery paper after 600 h exposure under SCW conditions at 650 °C/25 MPa with 100 - 150 ppb dissolved oxygen in the inlet water flow.

The Ni enrichment in Type 316NG specimen at 650 °C was located at the interface between bulk alloy and oxide film. The observed Ni content in the EDS analyses reflects enhanced Fe diffusion at 650 °C to the sample surface, since D_{Fe} is approximately $4x D_{Cr}$ in Ni [61], as shown in Table 9. Similar behaviour was observed in the tests on Type 316NG specimen exposed at 500 and 700 °C up to 100 h [87], as shown in Fig. 19. In this case, the applied pressure was 30 MPa, and the oxygen content was maintained at 0 ppb with nitrogen addition to the water mixing tank during the experiment. When applying higher-pressure values, fluid density increases, which in turn increases the liquid-like behaviour of the medium, as shown in Fig. 5. Although the applied pressure is higher, it is assumed that the difference in the oxidation test results is negligible.

Fig. 19 shows the depth profiles of the main metallic elements Cr, Ni, and Mn on Type 316NG after 100 h of exposure at the temperatures of 500 and 700 °C. GDOES analyses showed that at 700 °C, the amount of Cr in the outer layer is virtually zero. At 500 °C, a Cr-rich oxide film forms and protects the substrate against further oxidation by hindering ion transport through the oxide layer. At 700 °C, the oxide layer structure and thickness are similar to results at 650 °C with longer exposure times, as presented in Fig. 16 d.

Figure 19. GDOES analyses on austenitic stainless steel 316NG after 100 h of exposure a) at 500 °C and b) at 700 °C. The applied pressure was 30 MPa and dissolved oxygen content at 0 ppb in the inlet water flow [87].

The effect of dissolved oxygen content on the general corrosion resistance was also studied. It was observed to be relatively small in the tests with austenitic stainless steels and oxygen contents below about 200 ppb in the inlet water flow. The comparison test was performed on austenitic stainless steels 316NG and 347H at 0 and 150 ppb DO_2 , see Fig. 20. The parallel tests were performed at VTT and JRC-IET, the Netherlands. Although the observed weight change is negative on Type 316NG at 400 °C, the weight gain increases as a function of exposure temperature, and no significant effect of oxygen content on the results can be seen. This comparison test was performed using coupons from the same heats. However, the initial surface preparation was done by both institutions

independently, which may have affected the results. The observation was confirmed by performing Contact Electric Resistance (CER) measurements at 500 °C at a pressure of 30 MPa on austenitic stainless steel 316. The CER measurements were performed as a function of dissolved oxygen content on the steel and its main metallic constituents, showing that the effect of oxygen content on oxidation kinetics is negligible, at least up to 1.5 ppm DO₂ in the inlet water flow (Fig. 34 in the chapter below is dedicated to electrochemical measurements). This observation is discussed later in the “Electrochemical methods” chapter. However, it should be noted that in our test campaigns the applied inlet water flow rate typically varied between 3-10 ml min⁻¹ resulting in full refreshment of the autoclave volume roughly every 1 to 4 hours. Thus, the effect of oxygen content on the oxidation behaviour should be confirmed by higher flow rates in the autoclave system / test loops to simulate more realistic flow rates representative of operational NPP conditions. In flowing water conditions, all or some of the oxide layer can dissolve and be carried away by the coolant, or it can increase in thickness by deposition of oxide transported by the coolant from other corroding locations in the circuit. It is also proposed that in SCW conditions the corrosion mechanism changes from electrochemical to chemical at a density of 100 kg m⁻³ or at a temperature of about 500 – 550 °C / 25 MPa [43].

Figure 20. The effect of dissolved oxygen content on the weight change measurements for austenitic alloys Type 316NG and 347H as a function of temperature (25MPa). The comparison test was performed at VTT (DO₂ 0 ppb) and JRC-IET, the Netherlands, (DO₂ 150 ppb) using the same material heats up to 300 h of exposure.

The behaviour of different metallic elements in the oxide layer is discussed in more detail in **Publication IV**. Based on Fig. 19, the extent of the enrichment of the inner layer on 316NG with Cr seems to be independent from temperature. In general, the Cr enrichment shows the preferential oxidation of this element and also its slower transport rate through the inner oxide. Nickel is enriched

both in the inner layer and at the inner layer/alloy interface, which reflects both its slower oxidation rate and transport rate through the inner oxide. In contrast to Cr and Ni, Mn can be found in the outer layer of the oxides at both temperatures. According to this type of behaviour, the transport of Mn in the oxide is significantly higher than that of Cr or Ni. The enrichment of Mn in the inner layer, the possible formation of mixed Cr-Mn-Fe phases, and its beneficial or adverse effects are discussed later. Both Cr and Ni are practically absent in the outer layer on Type 316NG, which consists of Fe with a small amount of Mn. As discussed earlier, the loss of Cr from the outer layer can be tentatively explained by the formation of a volatile compound of Cr(VI) [61, 84, 85]. Alternatively, it could be because Cr and also Ni are retained in the inner layer due to their slower transport rate in comparison to Fe. The observed similarity between the shape of the Cr and Ni profiles in Fig. 19 supports the latter hypothesis.

The general corrosion rates measured by weight change and post-test analyses indicate that the traditionally used commercial austenitic stainless steels or F-M steels are not directly applicable in the case of core components at the highest temperatures of SCWR. This problem may possibly be solved by surface modification of the steels, although longer term tests are needed to confirm their high-temperature stability.

3.3 Effect of surface modification

As stated earlier in the design criteria discussion, surface modification could improve the corrosion resistance of steels used as fuel cladding whose bulk Cr content < 16 wt-% by enhancing Cr diffusion to the surface. It is well known in the literature that surface modification (e.g. using shot peening on the sample surface) has a beneficial effect on the oxidation resistance. This is a very common procedure for, e.g. fire tubes in conventional coal-fired plants [88]. Modification of the material surface by changing the grain structure through cold working has shown a significant beneficial effect on the corrosion resistance of austenitic stainless steels in SCW by increasing Cr transport to the sample surface [27, 28, 40, 45, 56]. A series of 316 stainless steel coupon and tube specimens were studied with different surface conditions as described in **Publication III and V**. To study further the effect of cold working and manufacturing procedure on Type 316 alloys, coupon and tube specimens with either polished or machined surfaces were prepared. The tube specimens were cut from a diameter of 10 mm tube used, e.g. in the piping of VTT's autoclave laboratory test loops. The length of the tube samples was approximately 10 mm and wall thickness was 1.5 mm. Different types of surface treatments were applied on the tube samples: one of the samples was left in the as-received state, one was machined, and two of the samples were ground using either #600 or #1 200 emery paper. Subsequent SCW exposure resulted in significantly different weight changes. The coupons with "machined" surfaces (2 and 3) were found to have the least weight change.

Figure 21 demonstrates the effect of surface condition, studied for the Type 316NG coupon specimens. The weight changes of 316NG samples with machined surfaces (samples #2 and #3) were significantly smaller compared to those of all other samples, despite the fact that Type 316NG has a lower bulk chromium concentration compared to, e.g. alloy HR3C, which is a modified Type 310, (16 weight-% Cr in 316NG vs. 24 weight-% Cr in HR3C). On the other hand, 316NG in the #1 200 polished condition (sample #1 in Fig. 21) showed the highest weight gain of all the tested specimens. The machined surface most likely produces a higher degree of cold work at the sample surface, which is generally removed by subsequent polishing with emery paper #1 200. The weight changes are shown in Fig. 22.

Figure 21. Photographs of Type 316NG coupon samples (25x15x5mm³) after 600 h of exposure at 650 °C/25MPa with 100 – 150 ppb dissolved oxygen content in the inlet water flow. 1) Coupon specimen polished up to #1 200 grit emery paper, 2) machined with normal sharp edge cutting tool, and 3) machined with blunt edge cutting tool to maximize the effect of cold work on the sample surface.

The weight change of Type 316NG samples with machined surfaces was considerably smaller than any other samples (except for Sanicro 25), despite their relatively low bulk Cr concentration. The cold work by machining produces a high dislocation density extending to much deeper surface layers than emery paper polishing, which helps Cr diffusion and effectively provides a higher Cr concentration on the surface. The protective effect was essentially similar for both machined surface roughness grades at least up to 600 h of testing. Although relatively poor oxidation properties have been observed previously for non-cold-worked Type 316 steel in SCW, it is not quite clear why HR3C, with its

higher Cr concentration, did not perform better in this study. Although the 347 HFG (17 wt-% Cr) and Super 304 (17 wt-% Cr) have clearly lower bulk Cr content than alloy HR3C, they also showed less weight gain, i.e. better oxidation resistance. A possible explanation could be that the grain size of Type 347 HFG and Super 304 is smaller (ASTM 7-8) than that of HR3C (ASTM 6-7), which leads to faster Cr diffusion to the surface. Table 10 shows the observed oxide film thicknesses and structures of Type 316NG with different surface modifications. Figures 18 and 23 show the SEM micrographs of the surface morphology and cross-sections of the Type 316NG with polished surface using grit #1 200 emery paper and machined specimen (#2), respectively. In Fig. 23, the formed uniform thin oxide layer is clearly discerned. The thicknesses of the oxide layers varied from about 0.6 to 1.0 μm in the machined specimens. The main constituents of the oxide films were Cr and Fe. By comparing Figs. 18 and 23, it can be stated that the oxide layer is almost 100 times thicker on the polished specimen.

Figure 22. The weight gain (mg cm^{-2}) of the selected materials for comparison to Type 316NG (with different surface finishes) after 600 h exposure at 650 °C under SCW conditions (25 MPa and dissolved oxygen content in the inlet water flow approximately 150 ppb).

Table 10. The maximum oxide film thicknesses and oxide structure on tested Type 316NG specimens with different surface finish after 600 h of exposure in SCW at 650 °C.

Materials	Initial surface finish	Max. oxide film thickness estimated from SEM cross-sections after 600 h exposure at 650 °C	Oxide structure and composition: outer / inner oxide layer
Type 316NG	#1 200 grit emery paper	92 μm	double layer, Fe-oxide / Fe-Cr-Ni spinel
Type 316NG	machined with normal sharp edge cutting tool	1 μm	thin and compact, Fe-Cr-oxide enriched with Mn
Type 316NG	machined with blunt edge cutting tool	0.6 μm	thin and compact, Fe-Cr-oxide

Figure 23. a) SEM cross-section and b) surface morphology of Type 316NG with machined surface using blunt edge cutting tool specimen (#3 in Fig. 21) after 600 h of exposure at 650 °C with 100 - 150 ppb dissolved oxygen in the inlet water flow. Note that the grinding traces are clearly seen on the sample surface after exposure test indicating a very thin oxide film formation.

To understand the material's long-term behaviour in SCW conditions, an exposure test was conducted on tube specimens at 650 °C for up to 3 000 h (125 days). The idea was to replicate the operation of fuel cladding in its original format as a tube component with machined and polished surfaces. Figure 24 shows the micro-hardness measurements of the tested specimens before exposure (tube specimens with machined and polished surfaces by using #600 & #1 200 grit emery papers, and a reference tube sample in the as-received condition). Accordingly, the hardness values increased with decreasing distance close to the sample surface on the machined surface. On the machined tube

specimen, a smooth and uniform oxide layer with occasional surface oxide crystals were observed after SCW exposure at 650 °C (Fig. 25 a), while the initially polished surface (#1 200 grit) appears to have been covered by a thick oxide layer (Fig. 25 b). To reveal the subsurface microstructure, a dual-beam Focused Ion Beam (FIB) in conjunction with SEM was used to perform ion beam cross-sections and further characterize the oxide film using a Transmission Electron Microscope (TEM), as discussed in **Publication V**.

Figure 24. Micro-hardness measurements and corresponding average surface roughness values R_a (μm) of different Type 316L tube specimens before exposure test.

Figure 25. SEM cross-section images after 3 000 h exposure at 650 °C for Type 316L tube specimens with a) machined surface, and b) with #1 200 emery paper finish.

According to **Publication V**, the following substantial differences in the morphology of the two samples were found:

- The machined surface only formed a very thin surface oxide layer and immediately beneath this surface oxide was a layer of fully recrystallized microstructure with mostly sub-micrometre sized grains.
- Severe internal oxidation was observed on the ground (#1 200 grit emery paper) specimen, which occurred beneath the oxide layer and extended deep into the substrate. The internal oxidation was also associated with the formation of voids at grain boundaries that would most probably affect the material's mechanical properties.

The machined surface exhibits significant residual strain near the surface due to severe deformation during machining. In the subsequent SCW exposure (in this case at 650 °C), this deformed structure becomes recrystallized to form a fine-grained microstructure near the surface. Below this recrystallized layer, the residual strain is not sufficient for recrystallization to occur at this temperature. However, there appears to have formed a recovered microstructure after the SCW testing. The substantial number of grain boundaries in the fine-grained layer can act as a short circuit path for outwards Cr diffusion from the bulk material. This helps to provide sufficient Cr near the surface to maintain a continuous protective Cr₂O₃ layer during SCW exposure. The high-dislocation density within the deformed layer beneath the fine recrystallized grains also facilitates Cr diffusion. This effect of machining on the corrosion rate should therefore be similar to the effects of grain refining in austenitic stainless steels, as reported by Tsuchiya et al. [40]. They found that the corrosion rates were very low at around 1/30 - 1/70 of those of the normal grain size Type 304L SS and Type 310S SS when exposed at 550 °C. It is evident that the formation of protective Cr₂O₃ is achievable when the bulk grain size is small enough and the bulk Cr content is high enough. This kind of behaviour was observed on austenitic stainless steel 347 with different bulk grain size, i.e. 347H has a grain size value of ASTM 9 equivalent to grain diameter of about 16 µm and 347HFG has ASTM 11 corresponding to a grain size of around 8 µm, as seen in Table 11 [89]. The same treatment was applied on 316L, as presented by Nezakat et al. [57]. They observed that the oxidation resistance of 316L can be enhanced up to four and five times by decreasing the bulk grain size below a critical value of 3 µm (corresponding to ASTM grain size number 14). They demonstrated that treated 316L samples provided a higher fraction of grain boundaries due to smaller grain size, which resulted in faster diffusion of chromium to the sample surface, and thus compensating for the shortage of chromium due to dissolution in the SCW at 600 °C.

Table 11. The measured ASTM bulk grain size of tested materials after 1 000 h of exposure and corresponding oxide film thicknesses after 2 000 h of exposure at 650 °C in SCW conditions [89].

Materials / surface finish	ASTM grain size No. (G) measured after 1 000 h of exposure	Nominal bulk Cr content in weight-%	Max. oxide film thickness observed from SEM characterization after 2 000 h
Sanicro 28 ground	4	27 wt-%	0.8 µm
HR3C ground	4-5	25 wt-%	20 µm
HR3C machined	4-5	25 wt-%	3 µm
347 HFG machined	11	18 wt-%	4.5 µm
347 H machined	9	18 wt-%	48 µm
316 NG machined	2-3	17 wt-%	75 µm

A visual inspection of the tube specimens revealed that a translucent colour of Cr-rich oxide is identifiable even after 3 000 h exposure, as shown in Fig. 26 [28]. For the machined specimen, it seems that the beneficial effect of cold work is sufficient at least up to 3 000 h exposure. For other specimens (grit #600 and #1 200 and “as-received”), oxide spallation is observed after 3 000 h exposure. This was also observed on the Type 347HFG specimen (note that the specimen was in as-received condition), which showed oxide exfoliation at the lower temperature of 550 °C with 8 000 ppb of dissolved oxygen (Fig. 27). This type of result is predictable because such a thick film (25 – 100 µm) is not adherent under cyclic temperature variations. Different thermal expansions of oxide phases between the magnetite and Fe-Cr-spinel will result in internal tensions and might cause scaling of the thick Fe-enriched oxide layer under the SCW conditions [59, 90]. On the other hand, the machined 316L sample surface is covered with a continuous, thin and uniform Cr-rich oxide, which leads to a relatively small variation in weight change measurement. The reason for the differences between treatments could be the oxide structure and composition. Thick oxide regions always show an iron-rich oxide layer with low-chromium concentration in the oxide. Again, the machined specimen showed relatively thin (< 1 µm) Cr-rich oxide with a peak Cr concentration of about 50% or more (depending on the location of where the line scan was performed). Consequently, it is obvious that different roughness grades of surface treatment result in different degrees of deformation of the surface layer, thus changing the diffusion characteristics of elements in the modified surface layer during exposure to SCW conditions.

As discussed in **Publication V**, typically austenite, magnetite/spinel and hematite phases have been observed on austenitic steels by X-Ray diffraction (XRD) after SCW exposure. The results of strain distribution studies obtained by Tan et al. [59] show that a strain accumulation close to the interface of

ingrown Cr-rich spinel and magnetite layer occurs for alloy 800H in as-received condition, i.e. without grain boundary or surface engineering. This might also be the case in this study for austenitic steels after long-term exposure where a thick oxide film forms on the sample surface with magnetite as the outer layer and a mixed spinel as the inner layer. Also, significant differences in the thermal expansion coefficients of magnetite and spinel may have led to the sharper strain change at the spinel-magnetite interface on the as-received and ground samples, while the smaller volume thermal expansion coefficient difference between the chromia and spinel may have alleviated the strain at the spinel-chromia interface on the 316L tube sample with machined surface. Differences between the volume thermal expansion coefficients support our experimental observations that the oxide exfoliation occurred mostly at the spinel-magnetite interface in the as-received and ground samples with a thick magnetite layer.

Figure 26. Type 316L tube specimens after exposure of 1 000 h (left) and 3 000 h (right) in SCW at 650 °C with machined (top) and #600 grit emery paper finish (bottom) [28].

Figure 27. a) SEM cross-section of oxide film and b) surface morphology of Type 347HFG specimen in SCW with 8 000 ppb of dissolved oxygen in the inlet flow at 550 °C after 1 000 h of exposure. The magnetite grows relatively quickly due to its porosity and can cause problems with exfoliation, as shown in c) with higher magnification.

The composition and structure of the scales forming on the materials depend mainly on the amount of Cr in the bulk alloy, the alloying elements, temperature, exposure time, heat flux, flow rate, and water chemistry. Grain size and initial surface condition will also play a crucial role in the whole picture. The beneficial effect of grain refining on the oxidation resistance of austenitic steels has been demonstrated. A typical example is alloy 347 HFG, which has been applied widely in the grain-refined condition, and favourable service experience up to 50 000 h has been achieved [88].

3.4 Oxidation mechanism

According to Kashif et al. [42], the formation of pores in the oxide is related to defects in the magnetite structure, which typically comprises two major defect types in magnetite: interstitial Fe^{2+} and cation / anion vacancies which may consolidate into pores when they are present in significant numbers located close to each other. As an outcome, the outer magnetite layer on austenitic stainless steels adheres poorly and can easily be detached from the substrate, as shown in Figs. 26 and 27.

Kofstad described [91] two major types of oxides that can develop on steels. Chromium oxide (Cr_2O_3 , rhombohedral corundum lattice) exhibits excellent protective properties. Chromium oxide typically forms solid solutions with hematite and as a result mixed oxide $(\text{Fe,Cr})_2\text{O}_3$ is observed. The other Cr-based oxide, $(\text{Fe,Cr})_3\text{O}_4$, has the cubic spinel structure and is less protective compared to Cr_2O_3 [91]. In most cases the inner spinel layer has Cr present in amounts that exceed the Cr concentration in the bulk alloy. In the spinel phase, Cr substitutes for trivalent Fe such that the compositions range from pure magnetite with zero Cr in the spinel $(\text{Fe,Cr})_3\text{O}_4$ with about 46% Cr [91]. The presence of Cr in the spinel lattice reduces the diffusion coefficients of metallic ions through the inner oxide by reducing the number of vacant sites and by increasing the energy of the diffusion jumps, resulting in lower oxidation rates [91].

Kashif et al. [43] proposed that in the beginning the corrosion process includes the reaction of both water and oxygen at the surface. A reaction at high energy on the surface site leads to the nucleation and formation of oxide cluster-type islands which expand and accumulate while releasing hydrogen into the water and consuming oxygen. In this way, the hydrogen release will continue until the islands coalesce to form a compact and uniform oxide layer which prevents the water access to the alloy surface. Hydrogen production decreases, and the only oxidant becomes oxygen, which must diffuse through the oxide layer to react at the metal-oxide interface [43].

Effertz and Meisel [92] presented the mechanism of scale formation where oxygen molecules are produced from steam by dissociation and are further adsorbed on the surface of an oxide. As such, this proposed approach can also be adopted in SCW conditions. They proposed that the following step involves dissociation of the oxygen molecules, ionization of oxygen atoms to oxygen ions, and chemisorption of the oxygen ions. The needed electrons are provided by the metal and are transported by diffusion through the oxide layer to the oxide/coolant interface. The chemisorbed oxygen ions are incorporated in the spinel lattice to form a new layer of magnetite with a high concentration of metal defects [92]. This mechanism is for the outer layer, i.e. then the cationic defects are filled with cations that migrate from the alloy substrate through the inner layer. At the metal-oxide interface, metal ions and electrons are transferred from the metal lattice into the scale and occupy interstitial positions in the spinel lattice of magnetite [92]. Oxygen ions from the scale enter the uppermost layers of the Fe lattice and start to form a spinel lattice. This is how two layers of scale grow from the original metal surface: one grows outward and the other inward [92]. This type of behaviour is shown in Fig. 28 where austenitic stainless steel 316L specimens have been exposed at 500, 600 and 700 °C revealing two separable oxide layers at higher temperatures (600 and 700 °C). Most probably, both specimens form of a spinel phase at higher temperatures. It is also assumed that the outer layer is rich in Fe vacant sites and the inner layer is featured by Fe excess and oxygen vacant sites. Typically, the inner layer

also contains most of the alloying elements from the steel. The oxide at the original location of the steel surface before exposure is often very porous because diffusion along vacant sites (outer scale) is faster compared to diffusion through interstitial sites (inner scale).

It has been shown that in steam the vaporization of Mn-enriched oxide is slower than that of pure Cr_2O_3 [93]. The diffusion of Mn is much faster in Cr_2O_3 than the diffusion of other elements like Fe, Ni and Cr. It is believed that initially Mn prevents the release of Cr from the film, but that over time the Mn dissolves into the coolant and is replaced by Fe. For 316L, the Mn content is not sufficient to maintain the required Mn concentration in the oxide. After the Mn concentration reduces to a critical value and the majority of Mn in the film is replaced by Fe, Cr release begins. It is also suggested that the effect of Mn is greater at higher temperatures due to lower solubility of Mn in SCW, although its diffusion rate through the layer is higher compared to lower temperatures. In the case of 316L, the data suggest that dissolution of Mn from the oxide into SCW results in the loss of the protective nature of oxide film. The high-energy sites in the coupon sample are typically located around the edges or near the sample surface defects where the oxidation reactions initiate, as shown in Fig. 29. This results from the oxidation of Cr(III) in the oxide to Cr(VI), which further enhances the dissolution of Cr(VI) into the solution and formation of an outer iron-rich oxide in the sample surface.

The distribution of main cationic constituents - Fe, Cr, Ni and Mn - in the oxide films are depicted as a function of depth at different temperatures in Fig. 30. According to **Publication IV**, it can be concluded that the most effective change in the element profile can be observed in Fe and Mn, the oxide film structure being completely different at 700 °C. Cr and Ni profiles behave in a similar fashion when considering different exposure temperatures.

Figure 28. Surface morphologies (a, b and c) and SEM cross-sections (d, e and f) on Type 316L after 100 h of exposure at 500, 600 and 700 °C in SCW conditions (30 MPa).

Figure 29. Type 316NG coupon specimen (25x15x5mm³) with machined surface condition a) before and b) after 2 000 h of exposure testing in SCW at 650 °C/25MPa with 150 ppb dissolved oxygen content in the inlet water flow. The scale line below the coupon sample is in millimetres.

Figure 30. The difference between main metallic constituents of a) Fe, b) Cr, c) Ni and d) Mn in the oxide film as a function of oxide film thickness and exposure temperature using GDOES on austenitic stainless steel Type 316NG after 100 h of exposure (30 MPa).

3.5 Reproducibility of test results

On examining the corrosion testing results available in the open literature, there are a lot of data on many material groups (e.g. ferritic-martensitic steels, austenitic stainless steels, Ni-based alloys, ODS alloys and Zr alloys) obtained with different testing parameters. Often the reported test parameters include temperature, pressure, exposure time, dissolved oxygen content and material composition. However, the information on flow rates and other important parameters from the testing facilities, like the total volume of the autoclave, are often missing. One of the most important factors, the initial surface finish of the tested specimens, is also regrettably not always part of the given information. The effect of surface finish is estimated to affect the material's corrosion resistance as much as the testing temperature itself [94]. Within the GIF SCWR (Materials & Chemistry (M&C) Project Management Board (PMB), it was realized that a major challenge in SCWR development was the lack of a consistent alloy database [94]. For this purpose, an international interlaboratory test campaign was arranged by the partners. In this international collaboration, a round-robin comparison test was organized to study the reproducibility of weight change data obtained from three identical alloys under similar conditions in different test facilities in different laboratories. The studied materials were austenitic stainless steels Type 800H, 310 and 321. An example of the results obtained is shown in Fig. 31, where the weight change data on austenitic stainless steel 321 is reported by the round-robin participants. In general, much more variation in weight change was

observed than expected. The scatter in weight change data was small within the same laboratory (typically less than $\pm 20\%$ of the average value) for the same material. However, large variations between different laboratories (typically greater than $\pm 100\%$ of the average value) were observed. The main reason for this variation appeared to result from differences in test facilities. This was not considered during development of the round-robin test procedures. Autoclave refresh time (i.e. water flow rate) appeared to play a significant role, although specific mechanism(s) were not proposed in this context. It should be noted that CNL and CMAT used static autoclaves, i.e., there was no water circulation through the autoclave volume. In addition to this, the CMAT specimens were cleaned after exposure test using an ultrasonic washer, which resulted in the very low weight change results compared to the other static autoclave.

Figure 31. Weight change data from the GIF round-robin exercise on austenitic stainless steel Type 321 [94]. Coupons are grouped by the international participants from left to right as following: Japan (Hitachi), Canada (Canadian Nuclear Laboratories (CNL)), CanmetMATERIALS (CMAT) and University of New Brunswick (UNB) and EU (Joint Research Centre, Petten (JRC), VTT and Ciemat) [94]. The group of coupon specimens were exposed simultaneously during one autoclave exposure test in each institution.

Most of the laboratories reported oxide spallation from the sample surfaces. This will, of course, reduce the measured weight gain and thus underestimate the measured values, at the same time as explain some of the differences reported between laboratories. Fig. 32 shows a specimen of Type 800H with oxide exfoliation after exposure in SCW at 550 °C with 8 000 ppb dissolved oxygen content in the inlet flow. This is one reason why the weight gain is not a reliable method to estimate the corrosion resistance. The oxide clusters formed on the sample surface are about 5 μm in thickness and most probably initiated on the middle of the grain interior due to limited availability of Cr ions. Dissolution of Cr(VI) from the specimen surfaces or deposition of elements dissolved from the autoclave or recirculation loop surfaces on the specimen may result in over- or underestimated values.

Figure 32. SEM cross-section and surface morphology of austenitic alloy Type 800H after 500 h of exposure in SCW conditions at 550 °C/25MPa with 8 000 ppb dissolved oxygen in the inlet water flow showing evidence of oxide exfoliation.

The temperature changes during cooling down and heating up of the autoclave for sample removal and at the end of the test produce thermal stresses due to the different thermal expansion coefficients between different oxide phases as well as substrate. This might result in a situation where a crack initiates and propagates to the surface, where oxide exfoliation could occur, and at the same time produces decohesion along the starting position. Since interconnected pores were observed, e.g. in Fig. 18 a) and Fig. 25 b), the tensile stresses most probably occur in the vicinity of such a defect and results in the growth of an interfacial crack.

The errors that can result from reporting only weight gain (instead of weight loss) are illustrated in Fig. 33, which shows the weight gain / loss measurements of austenitic alloy Type 321 (titanium stabilized austenitic stainless steel) in SCW at 550 °C with 8 000 ppb dissolved oxygen in the inlet water flow. A descaling procedure was conducted in order to measure weight loss using specific alkaline solution to dissolve oxides from the sample surface. The detailed descaling procedure for determining the weight loss results is presented elsewhere [94]. The autoclave was cooled down after 500 h of exposure and the coupons were removed and weighed. Selected coupons were kept for analysis and rest of them were placed back in the autoclave for the next exposure period up to 1 000 h. Based on the weight change data alone, one would assume that the corrosion rate of Type 321 at the two exposure times (500 and 1 000 h) is nearly the same. However, when the coupons are descaled to obtain the true weight loss, a considerable effect of exposure time on corrosion is observed. In this case, the total weight loss from the alloy is 6 times higher after 1 000 h of exposure than after 500 h.

Figure 33. Weight change measurement of Type 321 in SCW at 550 °C after 500 and 1 000 h of exposure. Different approaches were used when analyzing the weight change results of the coupon samples. See text for more detailed information.

The key conclusions can be summarized so that weight gain data must be interpreted with extra care, and especially caution must be taken when comparing experimental data from different laboratories/facilities. Also, the development of standard corrosion test methodologies is needed in order to create more reliable and comparable test data. The test coupons should be treated in the beginning to reduce the possible effects of machining-induced plastic deformation on the metal surface on corrosion, i.e. a surface layer of at least 30 μm in thickness should be removed from each side of the coupon. Based on the executed round-robin corrosion exercise, by descaling the coupons to obtain the true weight loss, not only is the oxygen effect more obvious but a stronger effect of temperature on the corrosion rate is also observed [94]. A follow-up test campaign with more detailed test parameters is ongoing by GIF SCWR M&C PMB partners to further reduce discrepancies between laboratories in general corrosion tests.

3.6 Electrochemical methods

The corrosion phenomena of alloys in aqueous electrolyte solutions follow electrochemical mechanisms [68]. The electrochemical process comprises two separate reactions, cathodic (reduction of an oxidant) and anodic (oxidation of an alloy constituent). Corrosion also includes other reactions, e.g. direct chemical reactions, but the process is fundamentally electrochemical. Electrochemical Impedance Spectroscopy (EIS) has shown great advantages compared to other electrochemical techniques as a non-destructive method for studying the corrosion phenomena of oxide films forming in liquids [95]. EIS is

capable of estimating the corrosion resistance of oxide film under different environmental conditions. Generally, a higher resistance at low frequency, describes processes depending on diffusion of reactants at surface (Warburg impedance) or high charge transfer resistance. In metal / oxide film / water configuration it has been shown in previous studies [68] that the response comes mainly from diffusion of reactants. Based on this, the impedance magnitude is proportional to the oxide resistance and inversely proportional to oxide capacitance, i.e. the larger the impedance value, the better is the corrosion resistance of forming oxide films, which has advantages in the study of interfacial phenomena. However, under SCW conditions, with unique fluid properties, there are some challenges in terms of electrochemical measurement techniques. The use of conventional electrochemical measurement methods in-situ, such as EIS, is not possible due to the very low ionic conductivity of SCW, as pointed out in Section 2.1 “Properties of supercritical water”. Fulger et al. [60, 96] performed post-test analyses on specimens exposed in SCW at 500 - 600 °C using EIS. However, the EIS measurements were performed ex-situ and are not comparable with in-situ measurements since oxide film properties are completely different at room temperature compared to the temperature range between 550 and 650 °C [91].

In-situ EIS measurements in SCW up to 600 °C have been very recently reported by Macak et al. in 2019 [39]. However, their data interpretation was subject to difficulties in performing the measurements, and therefore the data were occasionally encumbered by significant errors. In addition, some questions were raised by the authors on the optimal measurement conditions, especially electrode cell symmetry. Consequently, they concluded that more work needs to be done before EIS could be used as a reliable laboratory technique for in-situ studies of material behaviour in SCW. Thus, the only validated in-situ applicable electrochemical methods under SCW are Contact Electric Resistance (CER) and Contact Electric Impedance (CEI) techniques, which are described in detail in the PhD thesis by Kinnunen [68]. Several studies have shown that various electrochemical methods such as electrochemical polarization and electrochemical noise analysis can be used in SCW, although these techniques become more challenging as the SCW density decreases and the solution conductivity drops [21]. In the open literature there are only some available electrochemical studies performed in SCW, so far, e.g. by Zhou et al., Guan and MacDonald, Botella et al. & Delville et al. [54, 97, 98]. Zhou et al. as well as Guan and Macdonald monitored corrosion of Type 304 SS in dilute acidic water using the electrochemical noise technique (Electrochemical Emission Spectroscopy) up to 390 °C/25 MPa and 500 °C/40 MPa, respectively. Botella et al. & Delville et al. [97, 98] studied the behaviour of alloys C-276 and T60 titanium using polarization under steady-state and quasi-stationary conditions in oxidative chlorinated aqueous media. The tests were carried out at temperatures and pressures from room temperature to SCW conditions (400 °C, 28 MPa). It should be noted that the application of EIS under the conditions presented above was possible because the fluid density was

much higher (see Fig. 5) compared to typical conditions relevant to SCWR (500 - 650 °C, 25 MPa). This favours the use of conventional EIS measurements. In an SCWR concept, coolant will enter the core below the critical temperature and therefore electrochemical methods are still applicable in the core inlet (evaporator) region but at higher temperatures all parameters favouring the use of EIS measurements decrease rapidly. When non-contact impedance measurements are not possible due to the above-mentioned issues (and e.g. low ionic conductivity), the only applicable methods are CER/CEI measurements.

In **Publication I**, CER measurements were performed as a function of dissolved oxygen content on 316L steel and its main metallic constituents, as shown in Fig. 34 [74]. It seems that the effect of oxygen content on oxidation kinetics on 316L is negligible at least up to 1.5 ppm DO₂. The CER results of the main element of Type 316 steel, Fe, were identical to those of F-M steel P91 within the limit of the experimental error, and thus they were not included. When measuring the initial oxidation behaviour (in the range of minutes), the resistance of the oxide on pure Ni stabilizes relatively fast and settles above 100 $\Omega \text{ cm}^2$, close to the resolution limit of the CER device applied.

Figure 34. Oxide film resistance as a function of dissolved oxygen content for Type 316 and its main metallic constituents - Cr, Fe, Ni - during the initial stages of oxidation (up to a couple of minutes) in SCW at 500 °C/30 MPa [74].

According to **Publication I**, the oxide on Ni seems to behave as an insulator, whereas that on pure Cr as a p-type semiconductor under the applied SCW conditions. On the other hand, the resistance of the films on Fe and 316 stays very low, of the order of a few $\text{m}\Omega \text{ cm}^2$, indicating conductive behaviour, i.e., probably the presence of an oxide of the magnetite type. This result is in line with the conclusion from the surface analytical studies, e.g. EDS analyses. Here, the effect of Cr on the composition, structure, and properties of the films in SCW

is much less pronounced than during oxidation at subcritical temperatures in the case of austenitic stainless steels with less than 16 weight-% of Cr in the bulk alloy. In accordance with the fact that the oxides on Fe, P91, and Type 316 behave as conductors, no frequency response of the contact electric impedance (CEI) has been observed for these materials, where the measured values are equal to those obtained by CER within the experimental error. This observation was significant because modelling using quantitative interpretation of CEI results could not be realized, and alternative modelling approaches had to be considered, such as those discussed in the earlier chapters.

4. Discussion and conclusions

For thin-walled components in SCWR designs, the general corrosion is one of the most severe degradation modes which needs to be understood and controlled. It is evident that the oxidation rates of the candidate materials must be lower due to thinner wall thicknesses in SCWR core components compared to the materials used in SCFPPs. Numerous papers in the literature have considered the general corrosion of SCWR candidate materials [20, 30-52]. Tests have been conducted under wide-ranging conditions, but the temperatures used in the experiments have typically been lower than the estimated peak cladding temperature (620 – 630 °C). Based on literature data, the most important variables affecting corrosion behaviour of the candidate materials in SCW conditions are alloy class, temperature and surface treatment of the sample surface. The effect of dissolved oxygen content on corrosion resistance is not as significant as expected when the oxygen content is set below 300 ppb [22]. However, oxygen content near 300 ppb may slow the total oxide growth, as Bartels et al. suggested [23]. In contrast, the hydrogen water chemistry (HWC, H₂ 30 cc/kg H₂O) typically used in PWR plants may not be sufficient to suppress oxide growth rate of candidate materials in SCW. Thus, the effect of HWC with much higher H₂ content on oxidation rate is worth studying carefully in the future.

Based on the materials' screening performed in **Publications I - III and V**, the existing material choices for the European design HPLWR and especially for fuel cladding purposes need to be improved. One possible option is modification (e.g. decreasing bulk grain size or increasing defect density by cold working) or coating, otherwise new material needs to be developed. When considering HPLWR in the short term, another option is either to lower the core outlet temperature or compromise with higher Ni content in the material and respectively higher U-235 enrichment in the fuel. Since it is typically not cost-efficient to select the most alloyed material and in addition to this, the high Ni content in the bulk alloy is not favourable due to neutron economy as pointed out earlier, different techniques need to be considered in order to improve the oxidation resistance of relatively low alloyed austenitic steels. One possible method to reduce the oxidation rate is to introduce compressive stresses on the material's surface. Cold working is known to increase the dislocation density on the material surfaces. This increases diffusion rates in the affected zone. Whether this has a positive influence on oxidation/corrosion prevention or not

is dependent on the material composition and the environment to which it is subjected.

The influence of cold work and surface roughness on oxidation and corrosion has been studied widely, and the results vary depending on the material and temperature [99 - 103]. In **Publications III and V** this phenomenon was studied specifically on austenitic stainless steel Type 316L. Based on this study, thin and apparently protective oxide formed on the cold-worked 316L sample at 650 °C. The protectiveness lasted at least up to 3 000 h. The thin oxide film included a maximum chromium concentration of about 50% (or more) in the oxide. In samples with different treatments, locally thicker oxides had no such Cr-rich peaks in the oxide. In these cases, the oxide remained iron-rich throughout. It should be noted that the tests may not be representative of long-term service (> 5 000 h) in all respects. In particular, the protective nature of a high chromium diffusion rate in cold-worked layers could diminish in time, at least in the case of alloys with relatively low-Cr content in the bulk alloy such as in 316L. However, the beneficial effect of cold working on the early formation of an even and protective Cr-rich oxide can be seen as instructive. This could be applicable in the same manner as the typical initial treatment of in-core components to obtain thin and dense protective oxide layers by deliberate pre-oxidation. Such effects are enhanced by the relatively high testing temperature (650 °C) in addition to the high dislocation density of cold-worked (machined) metal and added diffusion paths resulting from small grain size. The same effect could not be observed on 15Cr-15Ni-Ti stabilized austenitic alloy 1.4970 [34, 35]. The difference is suspected to be related to the Cr content or the relative Cr and Ni content of the steels, i.e. the composition of the alloy seems not to be optimal due to its more stable austenitic structure.

In general, the results of this study showed that cold work of a surface layer by machining increases the oxidation resistance of 316L under SCW conditions. A combination of shot-peening and grain refinement might be an interesting solution as this has been reported to produce even greater benefit for austenitic alloys (304H and 347HFG), with the resulting oxidation resistance being nearly equivalent to high-Cr steels (25% Cr) under ultra-supercritical conditions [88]. Thus, it is recommended that cold-workable austenitic stainless steels, like Type 304, be studied under SCW conditions.

It has been reported that austenitic stainless steels form a double oxide layer under SCW conditions [30, 32, 33, 45] and this conclusion was confirmed in our tests as well. The non-protective magnetite outer oxide layer is assumed to grow by outward iron cation diffusion through the layers. The diffusion of oxygen to the metal-oxide interface is required to explain the observed weight gains for most of the austenitic alloys. Typically, the outermost layer consists of magnetite and hematite, and the inner layer a magnetite type spinel (FeCr_2O_4) and more protective chromia layer (Cr_2O_3). However, according to Kashif et al. [43], Cr-based oxide films are soluble in SCW conditions due to the formation

of Cr(VI) species. The diffusion coefficients of Fe and Cr in Cr_2O_3 have been reported to be in the same range, whereas Fe has three times higher value in spinel type FeCr_2O_4 oxide compared to Cr [43]. The formation of an Mn containing oxide layer is reported to be beneficial for the overall oxidation resistance in austenitic alloys since it limits the diffusion of iron to the sample surface and thus prevents the formation of unprotective magnetite. This was observed in our other studies on alloys 347H and 310 [89, 104]. An enriched Mn content was seen on alloys 347 and 310 specimens in the inner oxide layer after exposure at 600 and 650 °C. Both favourable and adverse effects of Mn on oxidation resistance have been reported [61, 105, 106]. In some cases, Mn has been found to form a spinel oxide of $\text{MnO} \cdot \text{Cr}_2\text{O}_3$ (MnCr_2O_4) rather than protective chromia. On the other hand, if MnCr_2O_4 occurs, it has been reported to reduce the Cr vaporization, since a Cr-Mn spinel is conductive which minimizes Cr evaporation from the protective oxide film at high-temperature steam conditions [84].

Not only the chemical composition, but also the microstructure of the material significantly contributes to its oxidation behaviour. Based on the study by Nezakat et al. [104], in air and SCW conditions, hot-rolled 316L (average grain size 20 μm) exhibited different oxides. When comparing test results in SCW after 100 h of exposure, magnetite (Fe_3O_4) and iron-chromium spinel (FeCr_2O_4) were the main oxide phases. The weight change of the alloy 316L during oxidation in SCW shows an enhancing trend with oxidation, but after 300 h of exposure weight loss occurred due to oxide exfoliation [104]. It is assumed that the oxide spallation is due to the stress induced by a temperature drop, i.e. during autoclave cooling. Based on the XRD pattern and EDS observations of the alloy 316L, magnetite (Fe_3O_4) and iron-chromium spinel (FeCr_2O_4) were observed after 1 000 h of exposure in SCW (i.e. the same oxides that were found after 100 h of exposure). Since the chromium content of this alloy is in general low (e.g. compared to AISI 310), a mixture of Fe-Cr-spinel is produced at the beginning of the oxidation. As the iron ions are much more mobile in this oxide scale than chromium ions (Cr^{3+}), quite pure iron oxide can be seen on the outer surface of the scale at longer times [104], as assumed also in our oxide film modelling procedure. This is not beneficial to corrosion resistance, because the formation of magnetite leads to spalling of the non-protective oxide layer. It is clear that oxidation rates are increased by the presence of water vapour due to more rapid dissociation of water compared to oxygen. Generally, the oxide films formed under SCW conditions are more porous than oxides formed in the absence of water, which was also as a starting point in our modelling procedure. This results most probably from increased cation diffusion in high temperature SCW conditions following vacancy condensation. In addition to this, volatilization of Cr oxides and hydrated oxides ($\text{CrO}_2(\text{OH})_2$, CrO_3) from the outer surface enhances this process further.

In Publications IV and VI, the kinetic and transport parameters of inner and outer layer growth on a range of candidate materials exposed in SCW

conditions were estimated using an upgrade of a model previously employed to predict the growth of oxide films in LWR conditions. The upgraded model features a new treatment of the growth of the outer layer which assumes that this process is limited by the transport of cations through the inner layer via an interstitialcy mechanism as described in **Publication VI**. The updated model is able to reproduce accurately (with certain limitations) the depth profiles of all constituent elements in the inner and outer layer, as well as in the diffusion layer situated between the inner layer and the bulk substrate. As a result of the calculations, kinetic and transport parameters of inner and outer layer growth and restructuring were obtained for five austenitic materials: AISI 316NG, AISI 347, DIN 1.4970, Sanicro 28, Alloy 690, and the ODS steels PM2000 and MA956 for oxidation times from 600 to 2 000 h at 650 °C.

Most of the rate constants and also the diffusion coefficients tend to decrease with time of oxidation at a constant temperature. Concerning the values of the rate constants, this might be related to the fact that the steady-state approximation that is used in the study for the boundary conditions needs a certain modification. Concerning the diffusion coefficients, in order to explain the effect of film aging on its properties, the effect of microstructure has to be considered.

To test the validity of the model, elemental profiles of oxide constituents estimated by Glow Discharge Optical Emission Spectroscopy (GDOES) were recalculated to represent the fractions of the metallic constituents normalized to the total concentration of metallic constituents and plotted versus the distance from the alloy / oxide interface. The comparison between the experimental and calculated profiles on MA956 [107] and Sanicro 28 alloys after 600 h of exposure at 650 °C is presented in Fig. 35. With the chosen values of the interfacial rate constants and diffusion coefficients, a good agreement is obtained both in terms of magnitude and depth distribution of the fractions of major (Fe, Cr, Ni, Mo, Al) and minor (Mn, Si, Nb, Ti, etc.) oxide constituents. The sigmoid fits to the oxygen and major metallic constituent profiles was used to determine the position of the alloy/oxide interface (e.g. in Fig. 35 (bottom) is shown with vertical line).

Figure 35. Comparison between the experimental (points) and calculated fractions of metallic constituents according to the model procedure (solid lines) at 650 °C (Fe, Cr, Al, Ni, Mn, Si, Ti and Nb) in the oxide formed on a) MA956 [107] and b) Sanicro 28 after 600 h of exposure with sigmoid fits to determine the position of the alloy/oxide interface shown with vertical line. M/F = metal substrate / oxide film interface.

Since the calculation method does not make use of a non-linear least square fitting procedure, to estimate the confidence intervals of the respective parameters, a sensitivity study was performed for each depth profile. As an example, the results of such a sensitivity study for the oxide formed on MA956 are shown in Fig. 36, which demonstrate that the confidence intervals for the rate constants and diffusion coefficients for the main alloy constituents are close

to $\pm 10\%$. This sensitivity study allowed us to define the parameters that most strongly affect the compositional profiles, namely, the rate constants at the alloy / inner layer interface, the rate constant of generation of chromium vacancies at the inner layer / fluid interface, and the diffusion coefficients of point defects in the inner layer.

Figure 36. Sensitivity study of the rate constants of oxidation at the alloy/inner layer interface (k_{1Fe} , k_{1Cr} , k_{1Al} , k_{1Mn} , k_{1Si} , k_{1Nb} , k_{1Ti} and k_2) as well as the rate constant of production of trivalent chromium vacancies (k_{3Cr}) for the oxide formed on MA956 for 1000 h [107]. Dashed lines represent variation of the respective parameters with 10%, respectively.

Another point worth noting is that most of the rate constants and the diffusion coefficients tend to decrease with time of oxidation. Concerning the values of the rate constants, this might be related to the fact that the steady-state approximation that is used for the boundary conditions at the interfaces is not entirely valid after only 600 h of oxidation. To explain the effect of film aging on its properties, the effect of microstructure should be considered, as pointed out earlier. The effective diffusion coefficient can be expressed as a combination of the diffusion coefficients in the grain interior and at the grain boundary

$$D_{eff} = (1 - f_{gb})D_{gi} + f_{gb}D_{gb} \quad (7)$$

where for the fraction of grain boundaries the following equation holds as a first approximation

$$f_{gb} \approx \frac{3\delta_{gb}}{\Phi} \quad (8)$$

in which δ_{gb} is the grain boundary width (of the order of 1 nm) and Φ is the grain size of the oxide in question. As a first approximation, if a linear grain growth is assumed, then combining equations (7) and (8) leads to

$$D(t) = D_{gi} + \frac{3\delta_{gb}}{\Phi_0 + kt} (D_{gb} - D_{gi}) \quad (9)$$

where Φ_0 is the grain size of the native oxide and k is a constant. Since the diffusion coefficient for grain boundary diffusion is much larger (about two orders of magnitude) than that through the grain interior, the term in the parentheses is approximately equal to D_{gb} . Then by fitting the estimated values of the effective diffusion coefficient in the inner layer to equation (9) under the assumption that the grain boundary width is 1 nm, indicative values of D_{gi} and D_{gb} can be obtained. An illustration of such fitting is shown in Fig. 37.

Figure 37. Diffusion coefficients of main constituents of the oxide on AISI 347H expressed vs. time of exposure in seconds (points) up to 2 000 h and best-fit calculations according to equation (9) (solid lines).

The average values of the fitting parameters are $D_{gi} = 4 \times 10^{-19} \text{ cm}^2 \text{ s}^{-1}$, $D_{gb} = 4 \times 10^{-17} \text{ cm}^2 \text{ s}^{-1}$, $\Phi_0 = 3.5 \text{ nm}$ and $k = 8 \times 10^{-13} \text{ cm s}^{-1}$. While more data are certainly needed to estimate the diffusion coefficients with sufficient confidence, the values obtained are in broad agreement with extrapolations from high-temperature gas oxidation of chromia-forming alloys [108 - 111].

Finally, the obtained rate constants are used to predict the oxide film thickness as a function of exposure time. The thicknesses of the oxides calculated by the model on high-Cr ODS alloys PM2000 and MA956, as well as Alloy 690 and Sanicro 28, as a function of exposure time are compared to the thicknesses

estimated from the experimental GDOES depth profiles in Fig. 38. The calculated values obtained for the oxide film thicknesses were in a good agreement with the results of the GDOES analyses. The good correspondence between the two sets of values furnishes additional proof for the validity of the proposed modelling approach.

Figure 38. Comparison between the oxide thicknesses calculated from the model (open symbols) and the thicknesses estimated from the experimental GDOES depth profiles (closed symbols) on high-performance materials a) PM2000 and MA956 [107] and b) Alloy 690 and Sanicro 28 at 650°C in SCW.

It should be noted that a change from liquid-like environment, i.e. where electrochemical reactions are prevailing, to a gas-phase environment, i.e. where direct chemical reactions (between alloy constituents and water molecules), is expected as the density drops monotonically after T_c [18, 21-24]. A mechanism involving separated cathodic and anodic sites changes to a direct chemical reaction between the metal surface and reactive species leading to a local

maximum corrosion rate in the vicinity of the critical point, as proposed by Guzonas et al. [48, 79]. Based on this, it seems that in the case of SCW with low ionic conductivity, the separation of anodic and cathodic sites at the surface is no longer possible and oxidation could be more localized and proceed in randomly-situated high-density water regions. This might initially favour the formation of a nodular type of oxide, as seen in many austenitic stainless steels after exposure to SCW, Fig. 39.

Figure 39. SEM cross-section (left) and surface morphology (right) of Alloy 800H after 1000 h of exposure in SCW at 700 °C.

Based on Fig. 39, in general, a thin chromium oxide covers the 800H specimen after 1 000 h of exposure at 700 °C. However, on the surface of the 800H specimen, clear nodule formation was visible already after 330 h of exposure, and at those points the oxide had a double layer structure. Based on the EDS analysis, the nodules consisted of an Fe-rich oxide and near the alloy surface a Cr-rich oxide layer was detected. No double layer formation was observed on the Alloy 800H at measurement points situated between the nodules, as shown in Fig. 40. This illustrates the complex behaviour of the austenitic alloy family in SCW conditions in terms of modelling approach, i.e. the need to include both nodule formation and possible spallation after long-term exposure.

Figure 40. SEM surface morphology on Alloy 800H after 660 h of exposure in SCW at 700 °C and EDS analyses locations #1 - #5.

To maintain a quasi-steady state in the system with a very low increment of thickness for most of the exposure time, Betova et al. [112] proposed that the film growth at the inner interface must be very nearly compensated for by dissolution at the outer interface, i.e. the oxidation rate constant must be almost equal to the dissolution rate constant of the corrosion layer (i.e. corrosion rate). However, in the case of SCW, cations will react directly with fluid and form the outer oxide layer. An estimate of the corrosion rate calculated under the assumption that the oxidation rate constant is equal to the rate constant of film dissolution is presented in Fig. 41. In the case that the dissolution rate of the oxide increases, in order to ensure the continuity of the ionic fluxes at the two interfaces and in the bulk oxide, a higher rate of film growth (and hence higher values of the rate constants at the inner interface) ensues. It should be noted that the relatively low oxidation rates of low Cr austenitic alloys in Fig. 41 is due to cold-worked sample surfaces that otherwise showed the highest average oxide thickness even up to 75 μm (see e.g. Fig. 29).

Figure 41. Comparison between the oxide thicknesses calculated from the model (open symbols) and the thicknesses estimated from the experimental GDOES depth profiles (closed symbols) after exposure test at 650 °C and 25 MPa with 150 ppb dissolved oxygen in the inlet flow. The experimental thicknesses were corrected by subtracting 0.05 - 0.1 μm of contamination layer depending on the alloy.

At the inner layer/water interface, restructuring of that layer occurs resulting in the formation of an outer layer [68]. This restructuring could proceed via dissolution or direct precipitation, but at higher temperatures due to low solubility of oxides, the restructuring is most likely due to direct reactions between oxidant and some components of metal oxide. The transport of matter and charge through the defective outer layer is assumed to take place via short circuit paths like imperfections and cracks, or interconnected porosity. Thus, no concentration gradient of oxygen vacancies is thought to be present in this layer and the transport mode through it is presumed to be pure migration [68].

The expected service lifetime for fuel cladding is from 25 000 to 30 000 h (3 – 3.5 years) depending on the design, which is roughly ten times longer than most autoclave tests have been. In order to have some estimate about the fuel cladding oxidation over the expected service lifetime, it is necessary to extrapolate data obtained from relatively short autoclave tests by assuming a particular model for the corrosion kinetics [113]. While this approach can be used to rule out proposed candidate alloys, longer tests are necessary to obtain the data needed to validate the extrapolations. It is often assumed that the corrosion rate has linear, parabolic, cubic or logarithmic behaviour. However, for double-layer oxide film structures it has been shown that mixed behaviour of mechanisms typically occurs, e.g. for austenitic alloys with an inner barrier layer and outer porous layer. An estimation of corrosion penetration rate for selected materials was done by using the calculation results from **Publications IV and VI**.

The maximum allowable corrosion penetration is specified to be less than 150 μm (0.15 mm) for the candidate cladding material after 20 000 h of service life. Concerning the estimate of corrosion penetration of the inner layer (mm / year), it can be calculated from the growth rate constant k_2 ($\text{mol cm}^{-2} \text{s}^{-1}$) estimated by the calculation procedure at 650 °C, as schematically presented in Fig. 7. As an example, for PM2000 after 600 h of exposure, the k_2 value is $2.2 \times 10^{-11} \text{ mol cm}^{-2} \text{s}^{-1}$ which translates into 0.0485 mm / year, and this decreases to 0.0286 mm / year after 2 000 h exposure. Corresponding figures on alloy 316NG estimated from the test at 650 °C after 1000 and 2000 h of exposures are 0.0441 mm / year and 0.0552 mm / year, respectively. Based on this the prediction the ODS alloys show slower corrosion penetration rate, i.e. the internal oxidation corresponds to a parabolic behaviour. Contrary to this, the alloy 316NG showed a linear behaviour when considering exposure test from 1 000 h to 2 000 h at 650 °C. In general, all materials showed k_2 values between $2 - 2.5 \times 10^{-11}$ except for PM2000 and Sanicro 28 which showed k_2 values 1.3 and $1.1 \times 10^{-11} \text{ mol cm}^{-2} \text{s}^{-1}$, respectively. This behaviour resulted in the best corrosion resistance according to our weight change measurements at 650 °C between 600 h and 2 000 h.

In the present version of the model, it is assumed that all the oxides that constitute the inner layer have the spinel structure. Certainly, this is an oversimplification considering the fact that several other phases (such as Fe_2O_3 , NiO or Cr_2O_3) have been reported to form during oxidation of ferritic and austenitic alloys in SCW. In this work we assumed that the surface oxide is magnetite (Fe_3O_4) since the molecular masses of Fe, Cr and Ni are very similar, and thus the assumption that the oxide is magnetite rather than a specific Fe-Cr spinel introduces only a small error in the model. Clearly, the interfacial rate constants and transport parameters of individual constituents would be different in different phases.

As a general conclusion, to increase the credibility of the present calculations, more data at different exposure times and temperatures would be needed in order to find at which exposure time the steady-state approximation starts to be strictly valid at the interfaces. In addition, structural data (e.g. phase composition, grain size of the inner layer) would be welcome in order for the model to be able to reproduce quantitatively the effect of aging of the oxide on its transport properties and thus be transformed into a predictive tool for oxidation and corrosion rates in SCW.

There are general corrosion data available in the open literature for many alloy groups including austenitic stainless steels, but comparing results to each other is extremely difficult due to different test parameters (flow rate, refresh times, heating / cooling rates, water chemistries etc.) and initial surface finishes of the specimen surfaces (polished, ground). This further increases the importance of international collaboration in order to provide proper guidelines for testing procedures in SCW. This is especially important in the case of austenitic stainless steels, which show a more severe tendency for oxide exfoliation in SCW compared to other material groups most probably due to differences in thermal expansion coefficients of the formed oxide phases.

If a new candidate material for SCWR components is needed, many criteria must be fulfilled before its introduction. First of all, the candidate material must fulfil certain properties, but also the economic point of view needs to be taken into account. It is clear that a new material or modification of a new material has to show sufficient improvement to earn acceptance, in spite of the added (often alloying-related) investment [113]. However, there could be some drawbacks, e.g. when adding new alloying elements to the bulk alloy or surface modification through coating or cold working. Although the criteria may be clear and competition from the existing solutions is well defined, it can be challenging to achieve significant improvement, e.g., because improving some property may require a disproportionately high level of additional expensive alloying, or because of conflicting trends in simultaneously required properties [113]. For example, it would be good for corrosion and oxidation resistance to have enough Cr in steels or increased defect density through cold working near the material external surface, since increasing Cr content in the bulk alloy or enhancing Cr diffusion to the material surface improves corrosion and oxidation resistance. However, the precipitation of unwanted secondary phases can compromise mechanical strength and/or ductility or increased defect density near material surface can increase stress corrosion cracking susceptibility, respectively.

An important requirement for the new materials at envisaged operating temperatures in Gen IV type reactors is the development of codes and standards. Current commercial codes like ASME and RCCM do not include the candidate materials under development and require specific rules and methods to be developed.

It is clear that certain challenges still exist in different alloy classes and especially in already nuclear-licensed material grades to adopt them as a candidate material for an SCWR, especially due to high oxidation rates. For this purpose, this work through **Publications I - VI** aims to identify and decrease knowledge gaps in the open literature, especially related to higher temperatures with different material compositions using the different characterization methods available.

References

- [1] IPCC, 2014: Climate Change 2014: Synthesis Report. Contribution of Working Groups I, II and III to the Fifth Assessment Report of the Intergovernmental Panel on Climate Change [Core Writing Team, R.K. Pachauri and L.A. Meyer (eds.)]. IPCC, Geneva, Switzerland, 151 pp.
- [2] P. Kharecha and J. Hansen, Science Briefs: Coal and Gas are Far More Harmful than Nuclear Power, NASA webpages, News April 23, 2013, Accessed on February 1st, 2017.
- [3] IAEA Power Reactor Information System (PRIS),
<https://www.iaea.org/PRIS/WorldStatistics/WorldTrendinElectricalProduction.aspx>, Accessed on December 27th, 2017.
- [4] World Nuclear Association, Nuclear Share Figures 2006–2016, <http://world-nuclear.org/information-library/facts-and-figures/nuclear-generation-by-country.aspx>, Accessed on December 27th, 2017.
- [5] World Nuclear Association, Plans for New Reactors Worldwide, Updated April 2016, <http://www.world-nuclear.org/information-library/current-and-future-generation/plans-for-new-reactors-worldwide.aspx>, Accessed on December 27th, 2017
- [6] A Technology Roadmap Update for Generation IV Nuclear Energy Systems, Issued by the OECD Nuclear Energy Agency for the Generation IV International Forum (GIF), 2014, <https://www.gen-4.org/gif/upload/docs/application/pdf/2014-03/gif-tru2014.pdf>
- [7] IRSN report, Review of Generation IV Nuclear Energy Systems, 2015, http://www.irsn.fr/EN/newsroom/News/Documents/IRSN_Report-GenIV_04-2015.pdf
- [8] 10th edition of the Generation IV International Forum (GIF) Annual Report, 2016, https://www.gen-4.org/gif/upload/docs/application/pdf/2017-07/gifannual_report_2016_final12july.pdf
- [9] Liquid metal coolants for fast reactors cooled by sodium, lead, and lead-bismuth eutectic. Vienna: International Atomic Energy Agency, 2012. p.; 29 cm. — IAEA nuclear energy series, ISSN 1995–7807; no. NG-T-1.6 STI/PUB/1567 978–92–0–131810–7
- [10] power-technology.com, News, views and contacts from the global power industry, Lean and clean: why modern coal-fired power plants are better by design, <http://www.power-technology.com/features/featurelean-and-clean-why-modern-coal-fired-power-plants-are-better-by-design-4892873/>, Accessed on February 7th, 2017
- [11] Status Report on Structural Materials for Advanced Nuclear Systems, Nuclear Science 2013, OECD NEA No. 6409, <https://www.oecd-nea.org/science/pubs/2013/6409-sr-smans.pdf>
- [12] G. Locatelli, M. Mancini, N. Todeschini, Generation IV nuclear reactors: Current status and future prospects, Energy Policy 61 (2013) 1503–1520
- [13] T. Schulenberg, L. Leung, Y. Oka, Review of R&D for supercritical water cooled reactors, Progress in Nuclear Energy 77 (2014) 282–299

- [14] D. Guzonas, R. Novotny, Supercritical water-cooled reactor materials – Summary of research and open issues, *Progress in Nuclear Energy* 77 (2014) 361–372
- [15] Y. Oka, S. Koshizuka, Y. Ishiwatari, A. Yamaji, *Super Light Water Reactors and Super Fast Reactors - Supercritical Pressure Light Water Cooled Reactors*, Springer ISBN 978-1-4419-6034-4 (2010) p. 651
- [16] Y. Oka et al., Super fast reactor R&D projects in Japan, *Proceedings of the ICONE19, 19th International Conference on Nuclear Engineering*, Chiba, Japan, 16–19 May, 2011, Paper 430702
- [17] B. Rukes, *Guideline on the Use of Fundamental Physical Constants and Basic Constants of Water*, The International Association for the Properties of Water and Steam Gaithersburg, Maryland, USA September 2001
- [18] H. Ohtaki, Effects of temperature and pressure on hydrogen bonds in water and in formamide, *J. Mol. Liq.* 103-104 (2003) 3-13
- [19] I. Pioro and S. Mokry, *Thermophysical Properties at Critical and Supercritical Pressures, Heat Transfer - Theoretical Analysis, Experimental Investigations and Industrial Systems*, Prof. Aziz Belmiloudi (Ed.), (2011) 573–592, ISBN: 978-953-307-226-5, In Tech, Available from:
<http://www.intechopen.com/books/heat-transfer-theoretical-analysis-experimental-investigations-and-industrial-systems/thermophysical-properties-at-critical-and-supercritical-pressures>
- [20] P. Kritzer, Corrosion in high-temperature and supercritical water and aqueous solutions: a review, *J. of Supercritical Fluids* 29 (2004) 1–29
- [21] D.A. Guzonas, W.G. Cook, Cycle chemistry and its effect on materials in a supercritical water-cooled reactor: A synthesis of current understanding, *Corrosion Science* 65 (2012) 48–66
- [22] D.A. Guzonas, *Extreme water chemistry – How Gen IV water chemistry research improves Gen III water cooled reactors*, Pacific Basin Nuclear Conference, Hyatt Regency Vancouver, (2014), PBCN2014-359.
- [23] D.M. Bartels, *Hydrogen Water Chemistry: Can it Work in a Supercritical Water Reactor?*, in: *Proceedings of the 8th Int'l Radiolysis, Electrochemistry & Materials Performance Workshop*, Quebec City, Canada, (2010)
- [24] V.A. Yurmanov; V.N. Belous; V.N. Vasina; E.V. Yurmanov, *Chemistry and Corrosion Issues in Supercritical Water Reactors*, *Proceedings of the Nuclear Plant Chemistry Conference*, October 3–8 (2010), Quebec City, Canada
- [25] M. Krykova, J. Macak, P. Sajdl, Z. Skoumalova, T. Popela, The influence of a start-up procedure on the corrosion behavior of selected stainless steels in supercritical water, *The 7th International Symposium on Supercritical Water-Cooled Reactors (ISSCWR-7)*, 15-18 March, Helsinki, Finland (2015), Paper #2098.
- [26] P. Yvon, *Woodhead Publishing Series in Energy: Number 106, Structural materials for Generation IV Nuclear Reactors* (2016)
- [27] X. Guoa, Y. Fan, W. Gao, R. Tang, K. Chen, Z. Shen, L. Zhang, Corrosion resistance of candidate cladding materials for supercritical water reactor, *Annals of Nuclear Energy* 127 (2019) 351–363
- [28] S. Penttilä, A. Horvath, A. Toivonen and Z. Zolnai, Effect of surface modification on the corrosion resistivity in supercritical water, the 5th Int. Sym. SCWR (ISSCWR-5), Vancouver, British Columbia, Canada, March 13-16 (2011) Paper 073

- [29] Y. Jiao a, W. Zheng b, D.A. Guzonas c, W.G. Cook d, J.R. Kish, Effect of thermal treatment on the corrosion resistance of Type 316L stainless steel exposed in supercritical water, *Journal of Nuclear Materials* 464 (2015) 356–364
- [30] G.S. Was, T.R. Allen, Time, temperature, and dissolved oxygen dependence of oxidation in austenitic and ferritic–martensitic alloys in supercritical water, in: *Proceedings of ICAPP’05, Seoul, Korea (2005)* Paper 5690
- [31] M. Bojinov, L. Heikinheimo, T. Saario, S. Tuurna, Characterisation of corrosion films on steels after long-term exposure to simulated supercritical water conditions, in: *Proceedings of ICAPP’05, Seoul, Korea (2005)* 1799–1807
- [32] G.S. Was, S. Teyseyre, Z. Jiao, Corrosion of austenitic alloys in supercritical water, *Corrosion* 62 (2006) 989
- [33] G.S. Was, P. Ampornrat, G. Gupta, S. Teyseyre, E.A. West, T.R. Allen, K. Sridharan, L. Tan, Y. Chen, X. Ren, C. Pister, Corrosion and stress corrosion cracking in supercritical water, *J. of Nuclear Materials* 371 (2007) 76
- [34] S. Penttilä, A. Toivonen, L. Heikinheimo, R. Novotny, SCC properties and oxidation behaviour of austenitic alloys at supercritical water conditions, in: *Proceedings of the 4th International Symposium on Supercritical Water Cooled Reactors, March 8–11, Heidelberg, Germany (2009)* Paper No. 60
- [35] S. Penttilä, A. Toivonen, L. Heikinheimo, R. Novotny, Corrosion studies of candidate materials for European HPLWR. in: *Proceedings of ICAPP ’08, Anaheim, CA USA, June 8–12 (2008)* Paper 8164
- [36] M. Sun, X. Wu, Z. Zhang, E.-H. Han, Oxidation of 316 stainless steel in supercritical water, *Corrosion Science* 51 (2009) 1069–1072
- [37] M. Sun, X. Wu, E.-H. Han, J. Rao, Microstructural characteristics of oxide scales grown on stainless steel exposed to supercritical water, *Scripta Mater.* 61 (2009) 996
- [38] Y. Maruno, J. Kaneda, S. Kasahara, N. Saito, T. Shikama, H. Matsui, Evaluation of weight loss of stainless steels in supercritical water, in: *Proceedings of ICAPP’09, Tokyo, Japan, May 10–14 (2009)* Paper 9289
- [39] J. Macak, R. Novotny, P. Sajdl, V. Bystriansky, L. Tuma, M. Novak, In-situ electrochemical impedance measurements of corroding stainless steel in high subcritical and supercritical water, *Corrosion Science* 150 (2019) 9–16
- [40] Y. Tsuchiya, F. Kano, N. Saito, M. Okawa, J. Kaneda, N. Hara, Corrosion and SCC properties of fine grain stainless steel in subcritical and supercritical pure water, in: *CORROSION/07, NACE International, Houston, TX (2007)* Paper 07415
- [41] H. Akhiani, M. Nezakat, M. Sanayei, J. Szpunar, The effect of thermo-mechanical processing on grain boundary character distribution in Incoloy 800H/HT, *Materials Science and Engineering* 626 (2015) 51–60
- [42] K. I. Choudhry, S. Mahboubi, G. A. Botton, J. R. Kish, I. M. Svishchev, Corrosion of engineering materials in a supercritical water cooled reactor: Characterization of oxide scales on Alloy 800H and stainless steel 316, *Corrosion Science* 100 (2015) 222–230
- [43] K. I. Choudhry, D. Guzonas, D. T. Kallikragas, I. M. Svishchev, On-line monitoring of oxide formation and dissolution on alloy 800H in supercritical, *Corrosion Science* 111 (2016) 574–582
- [44] B. Cox, Some thoughts on the mechanisms of in-reactor corrosion of zirconium alloys, *Journal of Nuclear Materials* 336 (2005) 331–368
- [45] T.R. Allen, Y. Chen, X. Ren, K. Sridharan, L. Tan, G.S. Was, E. West, D. Guzonas, Material performance in supercritical water, *Reference Module in Materials*

- Science and Materials Engineering, Comprehensive Nuclear Materials 5 (2012) 279–326, <http://dx.doi.org/10.1016/B978-0-08-056033-5.00100-2>
- [46] A. T. Motta, A. Yilmazbayhan, M. J. Gomes da Silva, R. J. Comstock, G. S. Was, J. T. Busby, E. Gartner, Q. Peng, Y. H. Jeong, J. Y. Park, Zirconium alloys for supercritical water reactor applications: Challenges and possibilities, *Journal of Nuclear Materials* 371 (2007) 61–75
- [47] G.S. Was, P. Ampornrat, G. Gupta, S. Teyseyre, E.A. West, T.R. Allen, K. Sridharan, L. Tan, Y. Chen, X. Ren, C. Pister, Corrosion and stress corrosion cracking in supercritical water, *Journal of Nuclear Materials* 371 (2007) 176–201
- [48] D. Guzonas, M. Edwards, W. Zheng, Assessment of candidate fuel cladding alloys for the Canadian supercritical water-cooled reactor concept, The 7th International Symposium on Supercritical Water-Cooled Reactors, Helsinki, Finland, 15-18 March (2015), Paper ISSCWR7-2090
- [49] C.R.F. Azevedo, Selection of fuel cladding material for nuclear fission reactors, *Eng. Fail. Anal.* 18 (2011) 1943–1962
- [50] A. Motta, A. Yilmazbayhan, M. J. Gomes da Silva, R. J. Comstock, G. S. Was, J. T. Busby, E. Gartner, Q. Peng, Y. H. Jeong, J. Y. Park, Zirconium alloys for supercritical water reactor applications: Challenges and possibilities, *Journal of Nuclear Materials* 371 Issues 1–3 (2007) 61–75
- [51] Y.H. Jeong, Corrosion of Zirconium-based Fuel Cladding Alloys in Supercritical Water, Proceedings of the 12th International Conference on Environmental Degradation of Materials in Nuclear Power System – Water Reactors – Edited by T.R. Allen, P.J. King, and L. Nelson (2005), The Minerals, Metals & Materials Society
- [52] K. Ehrlich, J. Konys, L. Heikinheimo, Materials for high performance light water reactors, *Journal of Nuclear Materials* 327 (2004) 140–147
- [53] U. Ehrnsten, Corrosion and stress corrosion cracking of austenitic stainless steels, Reference Module in Materials Science and Materials Engineering, Comprehensive Nuclear Materials 5 (2012) 93–104
- [54] D. Feron, Nuclear corrosion science and engineering, Woodhead Publishing Series in Energy: Number 22, 2012.
- [55] M. Sun, X. Wu, Z. Zhang, and E. Han, Oxidation of 316 Stainless Steel in Supercritical Water Corrosion Science 51(5) (2009) 1069–1072
- [56] J. Li, W. Zheng, P. Liu, M. Podlesny, Effect of Cold Work on the Corrosion Resistance of an Austenitic Stainless Steel, In: Ikhtayies S.J. et al. (eds), Characterization of Minerals, Metals, and Materials (2016), https://doi.org/10.1007/978-3-319-48210-1_15
- [57] M. Nezakat, H. Akhiani, S. Penttilä, S. Sabet, J. Szpunar, Effect of thermo-mechanical processing on oxidation of austenitic stainless steel 316L in supercritical water, *Corrosion Science* 94 (2015) 197–206
- [58] D. Gomez-Briceno, F. Blázquez, and A. Sáez-Maderuelo, Oxidation of Austenitic and Ferritic/Martensitic Alloys in Supercritical Water, *J. of Supercritical Fluids*, 78 (2013) 103–113
- [59] L. Tan, T. R. Allen, and Y. Yang, Corrosion Behavior of Alloy 800H (Fe–21Cr–32Ni) in Supercritical Water, *Corrosion Science* 53 (2011) 703–711
- [60] M. Fulger, M. Mihalache, D. Ohai, S. Fulger, and S. C. Valeca, Analyses of Oxide Films Grown on AISI 304L Stainless Steel and Incoloy 800HT Exposed to Supercritical Water Environment, *J. of Nuclear Materials* 415(2) (2011) 147–157

- [61] H. Akhiani, M. Nezakat, S. Penttilä, J. Szpunar, The Oxidation Resistance of Thermo-Mechanically Processed Incoloy 800HT in Supercritical Water, *J. of Supercritical Fluids* 101 (2015) 150–160
- [62] S. Mahboubi, G. A. Button, J. Kish, Oxide Scales Formed on Austenitic Fe-Cr-Ni Alloys Exposed to Supercritical Water: Role of Alloying Elements, The 19th Pacific Basin Nuclear Conference, PBNC, (2014) Canadian Nuclear Society
- [63] M. Bojinov, L. Heikinheimo, T. Saario, S. Tuurna, Characterisation of corrosion films on steels after long-term exposure to simulated supercritical water conditions, *Proceedings of ICAPP '05 Seoul, KOREA*, May 15–19 (2005) Paper 5349
- [64] A. Seyeux, V. Maurice, P. Marcus, Oxide Film Growth Kinetics on Metals and Alloys I. Physical Model, *Journal of The Electrochemical Society* 160 (6) (2013) C189-C196
- [65] K. Leistner, C. Toulemonde, B. Diawara, A. Seyeux, P. Marcus, Oxide Film Growth Kinetics on Metals and Alloys II. Numerical Simulation of Transient Behavior, *Journal of The Electrochemical Society* 160 (6) (2013) C197–C205
- [66] H. Asteman, J.-E. Svensson, M. Norell and L.-G. Johansson, "Influence of Water Vapor and Flow Rate on the High-Temperature Oxidation of 304L: Effect of Chromium Oxide Hydroxide Evaporation, *Oxid. Met.* 54 1/2 11(2000)
- [67] H. Asteman, J.-E. Svensson, and L.-G. Johansson, Evidence for Chromium Evaporation Influencing the Oxidation of 304L: The Effect of Temperature and Flow Rate, *Oxid. Met.* 57, 3/4, 193 (2002)
- [68] P. Kinnunen, Electrochemical characterization and modelling of passive films on Ni- and Fe-based alloys, PhD thesis, Espoo (2002), VTT Publications 472
- [69] M. Bojinov, P. Kinnunen, K. Lundgren, G. Wikmark, Mixed-Conduction Model for Stainless Steel in a High-Temperature Electrolyte: Estimation of kinetic parameters of oxide layer growth and restructuring, *J. Electrochem. Soc.* 152 (2005) B250
- [70] I. Betova, M. Bojinov, P. Kinnunen, K. Lundgren, T. Saario, Mixed-Conduction Model for Stainless Steel in a High-Temperature Electrolyte: Estimation of Kinetic Parameters of Inner Layer Constituents, *J. Electrochem. Soc.* 155 (2008) C81
- [71] I. Betova, M. Bojinov, P. Kinnunen, K. Lundgren, T. Saario, Influence of Zn on the oxide layer on AISI 316L(NG) stainless steel in simulated pressurised water reactor coolant, *Electrochim. Acta* 54 (2009) 1056
- [72] I. Betova, M. Bojinov, P. Kinnunen, K. Lundgren, T. Saario, A kinetic model of the oxide growth and restructuring on structural materials in nuclear power plants, in *Structural Materials and Engineering*, Chapter 3, Ference H. Hagy, Ed., Nova Publishers (2009) 91–133
- [73] I. Betova, M. Bojinov, V. Karastoyanov, P. Kinnunen, T. Saario, Estimation of kinetic and transport parameters by quantitative evaluation of EIS and XPS data, *Electrochim. Acta* 55 (2010) 6163
- [74] I. Betova, M. Bojinov, P. Kinnunen, S. Penttilä, T. Saario, Surface film electrochemistry of austenitic stainless steel and its main constituents in supercritical water. *J. Supercritical Fluids* 43 (2007) 333–340
- [75] A.T. Fromhold Jr., E. L. Cook, Diffusion currents in large electric fields for discrete lattices, *J. Appl. Phys.* 38 (1967) 1546–1551

- [76] J. Crank, P. Nicolson, A practical method for numerical evaluation of solutions of partial differential equations of the heat conduction type, *Proc. Camb. Phil. Soc.* 43 (1947) 50–61
- [77] J.D. Sloppy, Z. Lu, E.C. Dickey, D.D. MacDonald, Growth mechanism of anodic tantalum pentoxide formed in phosphoric acid, *Electrochimica Acta* 87 (2013) 82–91
- [78] S.A. Bakai, D.A. Guzonas, V.N. Boriskin, A.N. Dovbnya, S.V. Dyuldy, Supercritical Water Convection Loop for SCWR Materials Corrosion Tests under Electron Irradiation: First Results and Lessons Learned, The 6th International Symposium on Supercritical Water-Cooled Reactors ISSCWR-6 March 03-07, Shenzhen, Guangdong, China (2013), Paper ISSCWR6-13062
- [79] D.A. Guzonas, R. Novotny, S. Penttilä, A. Toivonen, W. Zheng, *Materials and Water Chemistry for Supercritical Water-cooled Reactors*, Woodhead Publishing Series in Energy (2018), ISBN: 978-0-08-102050-0
- [80] I. M. Svishchev, D. Guzonas, Supercritical water and particle nucleation: Implications for water chemistry control in a GEN IV supercritical water cooled nuclear reactor, *The Journal of Supercritical Fluids* 60 (2011) 121–126
- [81] J. Kysela, M. Ruzickova, J. Petr, Water chemistry specifications for supercritical water cooled reactors possible options. In: 4th International Symposium on Supercritical Water-cooled Reactors, Heidelberg, Germany (2009), Paper No. 68
- [82] EU FP6 High Performance Light Water Reactor (HPLWR) Phase2 Final report, (2010), https://www.cordis.europa.eu/result/rcn/52986_en.html
- [83] W. Zheng, J. Luo, M. Li, D. Guzonas, W. Cook, Stress corrosion cracking of SCWR candidate alloys: a review of published results. In: 5th International Symposium on SCWR (ISSCWR-5), Vancouver, BC, Canada (2011), Paper P095
- [84] A. Sabioni, A. Huntz, F. Silva, F. Jomard, Diffusion of iron in Cr₂O₃: polycrystals and thin films, *Materials Science and Engineering A* 392 (2005) 254–261
- [85] N. Zhang, Z. Zhu, G. Yue, D. Jiang, H. Xu, The oxidation behaviour of an austenitic steel in deaerated supercritical water at 600–700 °C, *Materials Characterization* 132 (2017) 119–125
- [86] X. Guo, K. Chen, W. Gao, Z. Shen, P. Lai, L. Zhang, A research on the corrosion and stress corrosion cracking susceptibility of 316L stainless steel exposed to supercritical water, *Corrosion Science* 127 (2017) 157–167
- [87] S. Penttilä, I. Betova, M. Bojinov, P. Kinnunen, A. Toivonen, Characterization of Candidate Materials in SCWR Conditions – Estimation of kinetic parameters of individual corrosion layer constituents, *Proceedings of ICAPP '10 San Diego*, CA, USA, June 13–17 (2010), Paper 10004
- [88] R. Viswanathan, J. Sarver, J. M. Tanzosh, Boiler materials for Ultra-Supercritical Coal Power plants - Steamside oxidation, *Journal of Materials Engineering and Performance* 15 (2006) 255–273
- [89] S. Penttilä, A. Toivonen, P. Auerkari, R. Novotny, Characterization of high performance austenitic and ODS alloys for SCWR conditions, *Proceedings of ICAPP '12, Chicago, USA*, June 24-28 (2012), Paper 12051
- [90] N. Zhang, Z. Zhu, G. Yue, D. Jiang, H. Xu, The oxidation behaviour of an austenitic steel in deaerated supercritical water at 600–700 °C, *Materials Characterization* 132 (2017) 119–125
- [91] P. Kofstad, *High Temperature Corrosion*, Springer, 1 edition (1988) p. 558

- [92] Effert & Meisel, Laboratory steam oxidation test results of shot-peened fine-grained and shot-peened coarse-grained austenitic stainless steel at 750 °C (Ref 58), *Journal of Materials Engineering and Performance*, 266 (2006)
- [93] G.R. Holcomb, D.E. Alman, The effect of manganese additions on the reactive evaporation of chromium in Ni–Cr alloys, *Scr. Mater.* 54 (2006) 1821–1825
- [94] D. Guzonas, S. Penttilä, W. Cook, W. Zheng, R. Novotny, A. Sáez-Maderuelo, J. Kaneda, The reproducibility of corrosion testing in supercritical water—Results of an international interlaboratory comparison exercise, *Corrosion Science* 106 (2016) 147–156
- [95] *Electrochemical Techniques for Corrosion Engineering*, NACE publication, Houston, Texas (1986) p. 332, ISBN 0-915567-23-7
- [96] M. Fulger, Oxidation behavior of Incoloy 800 under simulated supercritical water conditions, *Journal of Nuclear Materials* 385 Issue 2 (2009) 288–293
- [97] Ph. Botella et al., Experimental study, via current/potential curves, of the anodic behavior of Alloy C-276 and T60 titanium in chlorinated and oxygenated aqueous media under sub- to supercritical conditions, *J. of Supercritical Fluids* 25 (2003) 269–278
- [98] H. Delville et al., Electrochemical study of corrosion in aqueous high pressure, high temperature media and measurements of materials corrosion rates: applications to the hydrothermal treatments of organic wastes by SCWO, *J. of Supercritical Fluids* 26 (2003) 169–179
- [99] S. Uran et al. Effect of surface roughness on oxidation: changes in scale thickness, composition and residual stress, *Oxidation of metals* 54 (1999) 74–85
- [100] D. Caplan et al. Effect of cold work on the oxidation of nickel at high temperature, *Journal of the Electrochemical Society* 119 (1972) 1205–1214
- [101] D. Caplan et al., Effect of cold work on the oxidation of Fe-Cr alloys in water vapor at 600°C”, *Corrosion Science* 6 (1966) 509–512
- [102] A. S. Khanna, Effect of cold work on the oxidation resistance of 2 ¼ Cr-1Mo steel, *Oxidation of metals* 23 (1985) 17-33
- [103] S. Lozano-Perez, The role of cold work and applied stress on surface oxidation of 304 stainless steel, *Corrosion Science* 56 (2012) 78–85
- [104] M. Nezakat, H. Akhiani, S. Penttilä, J. Szpunar, Oxidation Behavior of Austenitic Stainless Steel 316L and 310S in Air and Supercritical Water, *Journal of Nuclear Engineering and Radiation Science* 2 / 021008-1 (2016)
- [105] V. Lepage, G. Louis, D. Allue, B. Lefebvre and B. Vanderberghe, Steam oxidation Resistance of New 12%Cr Steels: Comparison with Some Other Ferritic Steels, *Corrosion Science* 50 Issue 4 (2008)
- [106] J.M. Francis, Influence of Minor Alloying Elements on Structure of Surface Oxides Formed During High-Temperature Oxidation of an Austenitic Steel, *Journal of the Iron and Steel Institute* 204 (1966)
- [107] S. Penttilä, I. Betova, M. Bojinov, P. Kinnunen, A. Toivonen, Oxidation Parameters of Oxide Dispersion-Strengthened Steels in Supercritical Water, *Nuclear Engineering and Radiation Science* 2 / 011017-1 (2016), DOI: 10.1115/1.4031127
- [108] A. Sabioni, R. Ramos, V. Ji, F. Jomard, W. Macedo, P. Gastelois, V. Trindade, About the Role of Chromium and Oxygen Ion Diffusion on the Growth Mechanism of Oxidation Films of the AISI 304 Austenitic Stainless Steel, *Oxid. Met.* 78 (2012) 211–220, DOI 10.1007/s11085-012-9301-y

- [109] A. Sabioni, E. Malheiros, V. Ji, F. Jomard, W. Macedo, P. Gastelois, Ion Diffusion Study in the Oxide Layers Due to Oxidation of AISI 439 Ferritic Stainless Steel, *Oxid Met.* 81 (2014) 407–419, DOI 10.1007/s11085-013-9451-6
- [110] A. Sabioni, J. Souza, V. Ji, F. Jomard, V. Trindade, J. Carneiro, Study of ion diffusion in oxidation films grown on a model Fe–15%Cr alloy, *Solid State Ionics* 276 (2015) 1–8
- [111] E. Schmucker, C. Petitjean, L. Martinelli, P.-J. Panteix, S. Lagha, M. Vilasi, Oxidation of Ni-Cr alloy at intermediate oxygen pressures. I. Diffusion mechanisms through the oxide layer, *Corrosion Science* 111 (2016) 474–485
- [112] I. Betova, M. Bojinov, V. Karastoyanov, P. Kinnunen, T. Saario, Effect of water chemistry on the oxide film on Alloy 690 during simulated hot functional testing of a pressurised water reactor, *Corrosion Science* 58 (2012) 20–32
<https://doi.org/10.1016/j.corsci.2012.01.002>
- [113] P. Auerkari, S. Yli-Olli, S. Penttilä, S. Tuurna, R. Pohja, Performance of high temperature materials for efficient power plant: the water side challenge, *Journal of Nuclear Engineering and Radiation Science* 2 (2016), DOI: 10.1115/1.4032783

ISBN 978-952-60-3866-7 (printed)

ISBN 978-952-60-3867-4 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University

School of Chemical Engineering

Department of Chemical and Metallurgical Engineering

www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**