Utilization of Ti-containing microparticles on improved steel properties – Basic studies on inclusions control and interfacial phenomena

Miia Kiviö

Utilization of Ti-containing microparticles on improved steel properties – Basic studies on inclusions control and interfacial phenomena

Miia Kiviö

**The public defense on 12th June 2020 at 12:00 will
be available via remote technology.**

Link: <https://aalto.zoom.us/j/62968943922>

Zoom Quick Guide: <https://www.aalto.fi/en/services/zoom-quick-guide>

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Chemical Engineering, at a public examination held at the lecture hall Ke2 of the school on 12 June 2020 at 12.

**Aalto University
School of Chemical Engineering
Department of Chemical and Metallurgical Engineering
Metallurgy**

Supervising professor

Professor Ari Jokilaakso, Aalto University, Finland

Thesis advisor

Professor Emeritus Lauri Holappa, Aalto University, Finland

Preliminary examiners

Associate Professor Youn-Bae Kang, Pohang University of Science and Technology, Korea

Associate Professor Christian Bernhard, Montanuniversitaet Leoben, Austria

Opponent

Professor Timo Fabritius, University of Oulu, Finland

Aalto University publication series

DOCTORAL DISSERTATIONS 82/2020

© 2020 Miia Kiviö

ISBN 978-952-60-3900-8 (printed)

ISBN 978-952-60-3901-5 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-60-3901-5>

Unigrafia Oy

Helsinki 2020

Finland

Author
Miia Kiviö**Name of the doctoral dissertation**

Utilization of Ti-containing microparticles on improved steel properties – Basic studies on inclusions control and interfacial phenomena

Publisher School of Chemical Engineering**Unit** Department of Chemical and Metallurgical Engineering**Series** Aalto University publication series DOCTORAL DISSERTATIONS 82/2020**Field of research** Metallurgy**Manuscript submitted** 6 March 2020**Date of the defence** 12 June 2020**Permission for public defence granted (date)** 22 April 2020**Language** English☐ **Monograph**☒ **Article dissertation**☐ **Essay dissertation****Abstract**

Inclusions in steel are mostly regarded as harmful. However, if the size and chemistry of the inclusions are controlled, they can act as functional particles in improving the mechanical properties of the steel. Titanium as oxides or carbides can be used to control the microstructure and mechanical properties of steel. The composition, shape and size of the inclusions can vary depending on the conditions. Reactions and wetting between titanium inclusions and steel with different alloying elements are key phenomena in developing steel production processes. In this thesis the interfacial phenomena between liquid steel and titanium-containing inclusions were studied. The aim was to determine the inclusion types after additions of titanium and TiO₂, the effect and role of aluminium and manganese on the inclusions, the wetting between titanium carbide and steel and the effect of chromium, nickel and molybdenum on wetting and interfacial reactions.

The experiments in a vacuum furnace consisted of adding Ti and TiO₂ into liquid steel before and during casting. The inclusions formed after the additions of Ti/TiO₂ were comprehensively studied by scanning electron microscopy and energy-dispersive X-ray spectroscopy (SEM-EDS) and electron backscatter diffraction (EBSD), focusing on titanium oxide inclusions. The study examined inclusion types, and the composition and size of the inclusions existing in the cast ingots. Another experimental method used was wetting experiments between TiO₂/TiC and steel or iron alloys. The wetting experiments were performed using two different methods: conventional sessile drop technique and separate heating of the TiC substrate and metal droplet. During the wetting experiments the contact angles were recorded and evaluated. The samples from these experiments were investigated by SEM-EDS. The interface, particles and new phases were studied. Thermodynamic calculations (FactSage) of the formation of inclusions in low-alloyed steel in the melt and during solidification as well as carbide formation in stainless steel were performed to support the experimental part.

The results of the inclusion study after the addition of TiO₂ into liquid steel were novel at the time of publication of the articles. The extensive study on the effect of alloying elements on the wetting and interfacial reactions between stainless steel and TiC were unique and remains pioneering work. The results showed the complexity of the titanium-containing inclusions in steel. Mastering of the inclusions demands profound knowledge of the dominating phenomena. This thesis provides valuable information for developing the production processes of steels that have improved mechanical properties by using titanium-containing functional particles.

Keywords functional particles, wetting, titanium oxide, titanium carbide, mechanical properties**ISBN (printed)** 978-952-60-3900-8**ISBN (pdf)** 978-952-60-3901-5**ISSN (printed)** 1799-4934**ISSN (pdf)** 1799-4942**Location of publisher** Helsinki**Location of printing** Helsinki**Year** 2020**Pages** 128**urn** <http://urn.fi/URN:ISBN:978-952-60-3901-5>

Tekijä
Miia Kiviö**Väitöskirjan nimi**

Titaanioksidi- ja karbidi-mikropartikkelien hyödyntäminen teräksen ominaisuuksien parantamisessa – tutkimus sulkeumien hallinnasta ja rajapintailmiöistä

Julkaisija Kemian tekniikan korkeakoulu**Yksikkö** Kemian tekniikan ja metallurgian laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 82/2020**Tutkimusala** Metallurgia**Käsikirjoituksen pvm** 06.03.2020**Väitöspäivä** 12.06.2020**Väittelyluvan myöntämispäivä** 22.04.2020**Kieli** Englanti☐ **Monografia**☒ **Artikkeliväitöskirja**☐ **Esseeväitöskirja****Tiivistelmä**

Sulkeumia pidetään yleisesti haitallisina teräksessä. Kontrolloimalla sulkeumien kokoa ja koostumusta niitä voidaan kuitenkin hyödyntää myös funktionaalisina partikkeleina parantamaan teräksen mekaanisia ominaisuuksia. Titaanioksiedeja tai -karbideja voidaan hyödyntää halutun mikrorakenteen ja mekaanisten ominaisuuksien saavuttamisessa teräksessä. Sulkeumien koostumus, muoto ja koko riippuvat olosuhteista valmistusprosessissa. Titaania sisältävien sulkeumien ja erilaisia seosaineita sisältävän teräksen väliset reaktiot ja kostutus ovat avainasemassa valmistusprosesseja kehittäessä. Tässä väitöskirjassa on tutkittu sulan teräksen ja titaania sisältävien sulkeumien välisiä rajapintailmiöitä. Työn tavoitteena oli määrittää eri sulkeumatyypit teräksessä Ti ja TiO₂ lisäysten jälkeen sekä seosaineiden (alumiini ja mangaani) vaikutus sulkeumiin. Lisäksi tavoitteena oli selvittää TiC:n ja teräksen välinen kostutus ja reaktiot rajapinnalla sekä seosaineiden (kromi, nikkeli ja molybdeeni) vaikutus näihin.

Kokeellisessa osassa tehtiin sulatuskokeita vakuumiuunissa, joissa sulaan teräkseen tehtiin Ti ja TiO₂ lisäyksiä ennen valua ja valun aikana. Syntyneitä sulkeumia, erityisesti titaanioksiedeja, tutkittiin pyyhkäisyelektronimikroskoopilla ja energiadiispersiivisellä spektrometrillä (SEM-EDS) sekä elektronien takaisinsirontaan perustuvan diffraktion (EBSD) avulla. Näytteistä tehdyistä poikkileikkaushieistä tutkittiin sulkeumatyyppejä sekä sulkeumien koostumusta ja kokoa. Toinen osa kokeellisesta osasta koostui kostutuskokeista, joissa tutkittiin TiC- tai TiO₂-substraattien ja rautaseosten tai teräksen välistä kostutusta. Kostutuskokeissa käytettiin kahta eri menetelmää: 1. perinteinen sessile drop -menetelmä ja 2. substraatin ja sulan lämmitys toisista erillään. Kokeiden aikana seurattiin kostutusta ja määritettiin kostutuskulmat ja näytteet tutkittiin SEM-EDS -menetelmällä keskittyen rajapintaan, partikkeleihin ja mahdollisiin uusiin faaseihin. FactSage -ohjelmistolla tehtiin termodynaamisia laskelmia, jotka tukivat kokeellista osaa. Laskelmia tehtiin sulkeumien muodostumisesta sulassa matalaseosteisessa teräksessä ja jäähmettymisen aikana sekä karbidien muodostumisesta sulassa ruostumattomassa teräksessä ja jäähmettymisen aikana. Tulokset TiO₂:n lisäämisestä sulaan teräkseen ja siitä syntyvien sulkeumien tutkimuksesta olivat ensimmäiset julkaisut aiheesta. Laaja tutkimus seosaineiden vaikutuksesta kostutukseen ja rajapintailmiöistä TiC:n ja ruostumattoman teräksen välillä on ainutlaatuinen ja edelleen urauurtava. Tulosten perusteella titaania sisältävät sulkeumat teräksessä olivat hyvin moninaisia. Tämän väitöskirjan tulokset tarjoavat arvokasta tietoa, kun kehitetään mekaanisilta ominaisuuksiltaan entistä parempia teräksiä hyödyntämällä titaania sisältäviä sulkeumia funktionaalisina partikkeleina.

Avainsanat funktionaaliset partikkelit, kostutus, titaanioksidi, titaanikarbidi, mekaaniset ominaisuudet**ISBN (painettu)** 978-952-60-3900-8**ISBN (pdf)** 978-952-60-3901-5**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Helsinki**Painopaikka** Helsinki**Vuosi** 2020**Sivumäärä** 128**urn** <http://urn.fi/URN:ISBN:978-952-60-3901-5>

Acknowledgements

The research presented in this doctoral thesis was carried out at Aalto University School of Chemical Engineering within the research group of Metallurgy during the years 2007- 2011 (Helsinki University of Technology 2007-2009). Two research visits, in total approximately 3 months, to Osaka University, Japan took place in 2008 and 2010. I completed the thesis between 2012-2020 while working in the industry. This work was funded by Research Fund for Coal and Steel (RFCs) and TEKES-Finnish Funding Agency for Technology and Innovation (now Business Finland). Additionally, Emil Aaltonen Foundation and Finnish Foundation for Technology Promotion (TES) are gratefully acknowledged.

I would like to express my deepest gratitude to my first supervisor and thesis advisor, Professor Emeritus Lauri Holappa. He offered me the opportunity to start doctoral studies, introduced me to this research and continuously supported my work and pushed me to finish it through all these years (2007-2020). I would have never managed to finish the thesis without him. I would also like to thank my second supervisor, Professor Seppo Louhekilpi for supporting me during my studies. Finally, I would like to thank Professor Ari Jokilaakso my third supervisor. Thank you for all the support and encouragement in completing this thesis.

Most of the research work was carried out within the research group of Metallurgy. I would like to thank Erkki Heikinheimo, Hannu Heikkinen, Henrik Himberg and my colleagues in the research group of Metallurgy for assisting me in important parts of the research work. I also wish to thank Professor Toshihiro Tanaka, Assistant Professor Takeshi Yoshikawa, the students and research assistants for the experimental work and assistance at Osaka University, Japan. Special thanks to the Foundry Institute and Tomi Lano for the casting experiments. Many thanks to the research groups of Advanced and Functional Materials and Advanced Manufacturing and Materials at Aalto University for participating in the experimental work. SSAB Raahe Steelworks is acknowledged for chemical analyses of the steel samples.

I would like to thank my colleagues and friends in the research group of Metallurgy, especially my roommate and friend Heli, to my dear friend and fellow student Anu and all fellow doctoral students and friends at the Universities. Thank you also to Aurubis Finland Oy, my current employer, and my team and my colleagues for supporting the finalization of this thesis.

Finally, to my mother, brothers and all dear friends. Thank you for just being there and making me laugh. Last but not least, my men, my husband Janne and my little guy Kasper. It is finally done. This thesis is dedicated to my dad, who passed away in 2012. You would have been the first person I called after I finished this.

Pori, May 2020

Miia Kiviö

Contents

Acknowledgements.....	1
List of abbreviations and symbols	5
List of publications	7
Author's contribution	8
1. Introduction.....	11
1.1 Background.....	11
1.2 Scope and objectives of the thesis.....	12
1.3 Structure of the thesis	13
2. Theoretical background.....	15
2.1 Titanium oxides	15
2.2 Titanium carbides	17
2.3 Application of the materials.....	18
2.4 Thermodynamic studies	19
2.4.1 TiO _x systems	19
2.4.2 TiC systems.....	22
3. Experimental	24
3.1 Materials used in the experiments.....	24
3.1.1 Low-alloyed steel, stainless steel and Fe alloys used in the experiments	24
3.1.2 Ti and TiO ₂ materials added to low alloyed steel melt.....	25
3.1.3 TiC, TiCMo and TiO ₂ substrates for the wetting experiments.....	25
3.2 Addition of Ti and TiO ₂ to liquid steel	25
3.3 Wetting experiments between titanium-containing materials and liquid Fe alloys or steel	27
3.3.1 TiC wetting experiments	27
3.3.2 TiO ₂ wetting experiments.....	29
3.4 Analysis of the samples	29
3.4.1 Chemical analysis	29

3.4.2	Scanning electron microscopy, energy-/wavelength-dispersive X-ray spectroscopy (SEM-EDS/WDS) and electron backscatter diffraction (SEM-EBSD).....	29
4.	Summary of the results	31
4.1	Experiments with Ti and TiO ₂ additions into low-alloyed steel.....	31
4.1.1	Chemical composition	31
4.1.2	Inclusion analysis	32
4.1.3	TiO ₂ wetting experiments	36
4.2	TiC wetting experiments.....	39
4.2.1	Contact angles	39
4.2.2	SEM study of the wetting experiment samples	43
5.	Discussion	47
5.1	Thermodynamic calculations and experimental results	47
5.2	Behaviour of manganese after TiO ₂ additions.....	48
5.3	Wetting experiments with TiC.....	49
5.4	Formation of carbides	50
6.	Conclusions	54
6.1	Further Studies	55
	References	57

List of abbreviations and symbols

ABBREVIATIONS

BCC	Body-centered cubic structure of steel (ferrite)
BSE	Backscattered electron
EBSD	Electron backscatter diffraction
EDS	Energy-dispersive X-ray spectroscopy
EHT	Electron high tension
FCC	Face-centered cubic structure of steel (austenite)
FSstel	Steel database in FactSage
FToxid	Oxide database in FactSage
GRAINCONT	Grain size control in steel by means of dispersed non-metallic inclusions
i1, i2	ingot 1 and ingot 2
LIQ	Liquid
log	logarithm
M	Metal
Mag	Magnification
m1, m2	melt 1 and melt 2
NAMOS	Nanoparticle addition into molten steel
OES	Optical emission spectroscopy
QBSD	Backscattered electron detector
SEM	Scanning electron microscopy
SHS	Self-propagating high-temperature synthesis
SPS	Spark plasma sintering
SULA-TAJU	Solid-liquid interfaces in castings and development of

functionally graded structures

WD	Working distance
WDS	Wavelength-dispersive X-ray spectroscopy
X	Alloying element

SYMBOLS

A, B	types of wetting experiments
t	time
T	Temperature

SUBSCRIPTS

x	oxide with any oxidation state
y	sulphide with any oxidation state
tot	total content of oxygen or nitrogen

List of publications

This doctoral dissertation consists of a summary and the following publications, which are referred to in the thesis by the following Roman numerals.

I. Kiviö, Miia; Holappa, Lauri; Lung, Thierry. 2010. Addition of dispersoid titanium oxide inclusions in steel and their influence on grain refinement. Springer, Metallurgical and Materials Transactions B, Volume 41B, pages 1194-1204. ISSN 1073-5615. DOI: 10.1007/s11663-010-9416-y

II. Kiviö, Miia; Holappa, Lauri. 2012. Addition of titanium oxide inclusions into liquid steel to control nonmetallic inclusions. Springer, Metallurgical and Materials Transactions B, Volume 43B, pages 233-240. ISSN 1073-5615. DOI: 10.1007/s11663-011-9603-5

III. Kiviö, Miia; Holappa, Lauri; Tanaka, Toshihiro; Yoshikawa, Takeshi. 2012. Interfacial phenomena in Fe-TiC systems and the effect of Cr and Ni. De Gruyter, High Temperature Materials and Processes. Volume 31, pages 645-656. ISSN 2191-0324. DOI 10.1515/htmp-2012-0102

IV. Kiviö, Miia; Holappa, Lauri; Tanaka, Toshihiro; Yoshikawa, Takeshi. 2014. Interfacial phenomena in Fe/stainless steel-TiC systems and the effect of Mo. De Gruyter, High Temperature Materials and Processes. Volume 33, pages 571-584. ISSN 2191-0324. DOI 10.1515/htmp-2013-0082

Author's contribution

Publication I: Addition of dispersoid titanium oxide inclusions in steel and their influence on grain refinement.

MK compiled the literature review, performed the thermodynamic calculations, designed the experimental part and supervised the experiments performed by Tomi Lano at the Foundry Institute of Tampere University of Technology, conducted the inclusion analyses and prepared most of the manuscript under the supervision of LH. The OES analyses were performed by Rautaruukki Raahe Steelworks. The hot rolling, heat treatments and analyses were performed and written by TI (Arcelor Mittal Research Center). All authors contributed to the finalization of the article.

Publication II: Addition of titanium oxide inclusions into liquid steel to control non-metallic inclusions.

MK compiled the literature review, performed the thermodynamic calculations, designed the experimental part and supervised the experiments performed by Tomi Lano at Foundry Institute of Tampere University of Technology, conducted the inclusion analyses and prepared the manuscript under supervision of LH. SEM-EBSD was performed by Tapio Saukkonen (Aalto University). All authors contributed to the finalization of the article.

Publication III: Interfacial phenomena in Fe-TiC systems and the effect of Cr and Ni.

MK compiled the literature review, performed the thermodynamic calculations, planned the experimental part, performed type B wetting experiments and analyses and prepared the manuscript under the supervision of LH, TT and TY. Type A wetting experiments as well as some of the analyses were performed by Hannu Heikkinen (Aalto University) under the supervision of MK. All authors contributed to the finalization of the article.

Publication IV: Interfacial phenomena in Fe/stainless steel–TiC systems and the effect of Mo.

MK compiled the literature review, performed the thermodynamic calculations, planned and performed type B wetting experiments and analyses and prepared the manuscript under the supervision of LH, TT and TY. Type A wetting experiments and part of analyses were performed by Hannu Heikkinen

(Aalto University) under the supervision of MK. All authors contributed to the finalization of the article.

1. Introduction

New steel grades with improved mechanical and chemical properties are being developed all the time. Moreover, achieving these improvements with less energy consumption is of particular interest. The improved properties can be obtained by developing the production processes and by controlling the chemistry of the steels. A potential strengthening mechanism is to add a new phase into the steel. The new phase can for instance be in the form of small particles, ranging from a few hundred nm to a few μm in size. The new phase can be added to the steel in the form of particles (exogenous particles) or as components to form certain type of particles in the steel (endogenous particles). Usually, small particles in the steel microstructure are called inclusions and they are considered harmful or even detrimental to steel properties. However, if the size and chemistry of the inclusions is controlled properly, the inclusions can act as functional inclusions or particles in the steel instead of being harmful. The microstructure can in fact be controlled by inclusion engineering.

Titanium-containing particles can act as functional inclusions in steel. They can exist as oxide, nitride, carbide or complex particles and other conventional alloy metals can be present as well. In addition, the shape and the size of these particles can vary. By adding titanium-containing inclusions into liquid steel to control the resulting microstructure, grain size and mechanical properties, new materials with improved mechanical properties can be obtained. Titanium-containing particles can be either uniformly or locally distributed in the material. In many applications it is not necessary to add reinforcement into the whole material, but instead it is enough to have a locally reinforced material. Overall, in order to be able to control these particles the phenomena between the particles and the steel in liquid state, during solidification and during each step of the production process should be known. By identifying and controlling the interfacial phenomena between the particles and the steel, the manufacturing and processing methods as well as the final properties of the materials can be improved and optimised.

1.1 Background

The work in this thesis examines interfacial phenomena when adding titanium in different forms and ways into liquid steel: the phenomena involved in the addition of titanium oxides into low-alloyed steel and the phenomena involved in the wetting of titanium carbides by iron alloys and stainless steel. This thesis

is based on parts of two research projects. In the case of the former, the subject of the research project was Grain Size Control in Steel by Means of Dispersed Non-Metallic Inclusions (GRAINCONT; Andersson *et al.*, 2011). In the latter the title of the research project was Study on Solid-Liquid Interfaces in Castings and Development of Functionally Graded Structures (SULA-TAJU; Lagerbom *et al.*, 2010). The research work from these two projects was combined in this thesis because of the similar phenomena, materials and the concept of using particles to modify material properties.

1.2 Scope and objectives of the thesis

The two afore-mentioned research projects were chosen to form the thesis, because both dealt with the development of steel-based materials containing titanium particles. In the development and production of such particle-reinforced materials, it is important to understand the phenomena within the material during different processing stages. In particular, the interfacial phenomena between the matrix material (iron, iron alloys, steel and stainless steel) and titanium-containing particles are of great importance. The addition method and form of the additives play a significant role and affect the behaviour of the particles in the matrix material as well as the interfacial phenomena.

Figure 1 illustrates the scope of this thesis together with two parts from the research projects, the related publications (I-IV) as well as the two main reference articles related to this thesis.

Figure 1. Schematic presentation of the research projects.

The general objective of this thesis was to study the interfacial phenomena between titanium-containing inclusions and liquid steel. The prime focus was on the phenomena in liquid steel and to a lesser extent on the phenomena during cooling and solidification. The experimental part of the thesis was divided into two parts, as the original work resulted from two different research projects. Firstly, the aim was to study the addition of Ti and TiO_2 into liquid steel and the resulting Ti-containing inclusions with the emphasis on the TiO_x inclusions. Wetting and the reactions between the Ti/ TiO_2 and steel, and the composition and distribution of the final inclusions were also studied to understand the interfacial phenomena resulting from the addition of Ti and TiO_2 to liquid steel. (Publications I and II). Secondly, the aim was to study the wetting of TiC by liquid iron alloys and the resulting dissolution and formation of the Ti-containing particles to understand the interfacial phenomena in the addition of TiC to liquid iron-based alloys or stainless steel. Two different wetting experiments were performed. (Publications III and IV). Thermodynamic studies on the formation of the particles and different phases were used as a background and support for the experimental part (Holappa and Kiviö, 2012; Kiviö *et al.*, 2016). The article by Kiviö *et al.* (2016) also attempts to summarize and outline the results from Publications III and IV.

The main objectives of this work were:

- To study the types of Ti-containing inclusions in low-alloyed steel after additions of Ti and TiO_2 into the melt and during solidification.
- To determine the effect of the Al content and Ti/Al ratio in steel on the inclusions formed.
- To study the behaviour of manganese during inclusion formation.
- To determine the wetting between liquid steel and titanium carbide and the effect of Cr, Ni and Mo.
- To observe the reactions at the TiC and iron alloy interface and the effect of Cr, Ni and Mo.

1.3 Structure of the thesis

This thesis consists of four publications (I-IV) and this compendium. The publications attached in the appendices consist of four scientific peer-reviewed journal articles (I, II, III and IV).

This compendium consists of the following chapters. Chapter 2 includes the most relevant theoretical background for titanium-containing oxide and carbide particles and inclusions used as functional particles. The second chapter also includes related studies about the addition and usage of titanium-containing particles. Thermodynamic calculations done in relation to this thesis are summarized in the theoretical background as well. Chapter 3 summarizes the experimental part and methods used in this thesis, followed by a summary in chapter 4 of the most important results from Publications I-IV and some unpublished

results. Chapter 5 combines discussions of the results with the findings from previous studies. Finally, chapter 6 presents the conclusions of this dissertation including the author's recommendations for further studies.

2. Theoretical background

There are several phenomena related to titanium-containing inclusions in steel besides the well-known stabilizing effect of Ti in stainless steel. Titanium reacts with residual carbon forming titanium carbides and thus prevents the formation of Cr carbides (sensitization), which might deteriorate corrosion resistance. Titanium is also a rather strong deoxidizer in steels: not as strong as aluminium but stronger than silicon for example. On that account the appearance of titanium oxides has become of increasing interest. The concept of controlling the microstructure by means of oxide inclusions and the distribution of inclusions has been termed ‘Oxide Metallurgy in Steels’ (Takamura and Mizoguchi 1990).

Titanium-containing inclusions can promote grain refinement through constitutional supercooling during solidification (Jackson, 1972) and through the Zener pinning effect during solid-state transformations (Smith, 1948; Zener, 1949). In general, finely dispersed titanium oxides, nitrides and carbides are potential grain refiners for steels (Grong *et al.*, 2006; Lou and Holappa, 2001).

2.1 Titanium oxides

A uniform distribution of titanium oxide inclusions in steel promotes grain refinement and the formation of acicular ferrite, both of which have an effect on improving the strength and toughness of the material.

Besides grain refinement, titanium oxide inclusions can act as nucleation sites for acicular ferrite in the steel microstructure (Byun *et al.*, 2003; Gregg and Bhadeshia, 1997; Shim *et al.*, 1999; Shim *et al.*, 2001/1; Shim *et al.*, 2001/2). Acicular ferrite plates grow in many directions and prohibit the propagation of cracks in the microstructure, resulting in a good combination of toughness and strength (Bhadeshia, 2001). The utilization of titanium-containing inclusions in welds to create the acicular ferrite microstructure in the weld is well-known (Bhadeshia, 2001).

The mechanism for the nucleation of acicular ferrite on titanium oxide inclusions has not been confirmed. A small lattice registry (Bramfitt, 1970) between ferrite and the inclusion has been reported to play an important role. The formation of a Mn-depleted zone around the inclusions as a result of the presence of MnS or MnO_x in the inclusions is the most prevailing concept for the nucleation of acicular ferrite on titanium oxide inclusions (Byun *et al.*, 2003; Shim *et al.*, 1999; Shim *et al.*, 2001/1; Shim *et al.*, 2001/2; Jiang *et al.*, 2015).

Ti_2O_3 has been reported to absorb Mn from the surrounding matrix (Shim *et al.*, 1999; Shim *et al.*, 2001/2; Kang and Lee, 2010). Ti_2O_3 itself seems to be inert to ferrite nucleation in Mn-free steel (Shim *et al.*, 2001/2). Instead, the formation of $(\text{Mn,Ti})_2\text{O}_3$ inclusions is necessary for the nucleation of acicular ferrite. Microstructures rich in acicular ferrite have been observed in steels containing many TiO_x +Mn inclusions (Byun *et al.*, 2003; Gregg and Bhadeshia, 1997; Hossein Nedjad and Farzaneh, 2007; Jin *et al.*, 2003; Shim *et al.*, 2001/1; Yang *et al.*, 2008; Zhuo *et al.*, 2007). In contrast, TiO has also been found to be a more effective nucleation site for ferrite than Mn-containing TiO_x inclusions (Kikuchi *et al.*, 2011). The reason proposed was high lattice consistency. Several types of inclusions have been found active in acting as nuclei for acicular ferrite: $(\text{Ti,Mn})\text{O}_x$, $(\text{Ti,Mn})\text{O}_x\text{S}_y$, $(\text{Ti,Al})\text{O}_x$, $(\text{Ti,Al,Mn})\text{O}_x$ and $(\text{Ti,Al,Mn})\text{O}_x\text{S}_y$ depending on the composition of the steel (Loder *et al.*, 2016). A higher Mn content in the complex $(\text{Ti,Al,Mn})\text{O}_x$ might promote the formation of acicular ferrite. However, the presence of Ti in the inclusions is a prerequisite for acicular ferrite formation and inclusions with Ti, Mn and possibly also MnS are effective nuclei for acicular ferrite formation. In general, the inclusions formed in steels containing Ti and Mn can be very complex depending on the steel composition and conditions (Kang and Lee, 2005/1; Kang and Lee, 2005/2).

Due to the presence of alloying elements in steel and different processing conditions, these inclusions can be very complex regarding chemistry, shape and size distribution. The Al content and Al_2O_3 inclusions play a significant role in the formation of TiO_x inclusions. Titanium oxides can nucleate heterogeneously on existing Al_2O_3 inclusions (Byun *et al.*, 2003). The Al content and oxygen content in the melt prior to Ti addition play a significant role in Ti deoxidation. However, increasing the Ti content does not significantly affect the Ti deoxidation (Van Ende *et al.*, 2009). A higher oxygen content promotes titanium oxidation and increases the titanium content in Al-Ti oxide inclusions (Wang *et al.*, 2011). In another study, a low Al content and high Ti content have been emphasized in order to obtain a high number of TiO_x -rich inclusions (Xuan *et al.*, 2016/2). Several thermodynamic calculations depict the importance of a low Al content in obtaining TiO_x inclusions (Jung *et al.*, 2009; Ruby-Mayer *et al.*, 2000; Matsuura *et al.*, 2007). The optimum size range for the inclusions is from a few microns to a few hundred nanometres (Lee *et al.*, 2000; Shim *et al.*, 1999).

The idea of using Ti-containing inclusions throughout the material is becoming more attractive. The inclusions are usually created through deoxidation by adding Ti into the liquid steel, but this might result in coarsening of the inclusions (Van Der Eijk *et al.*, 2009). The inclusions are more easily controlled if they are added directly as exogenous particles. This might help in improving steel production steps (see 1.1.1). The direct addition of titanium oxide directly has been studied by adding it with the steel charge before meltdown (Gregg and Bhadeshia, 1997; Hossein Nedjad and Farzaneh, 2007; Mu *et al.*, 2014; Mu *et al.*, 2016). However, the idea of adding the inclusions directly into the melt as titanium oxides has not been reported earlier in the same way as in this work. Since the release of Publications I and II, a study on TiO_2 additions directly into the melt has been made (Xuan, 2016/1).

2.2 Titanium carbides

Titanium carbide, a group IV carbide, is a stable, hard and wear-resistant material with a high melting point and heat of formation (Samsonov *et al.*, 1968), due to which it is used as a reinforcement material in composites. When used in a metal matrix composite, it improves the hardness and wear resistance of the composite. TiC can exist with carbon contents varying between 34-50 at% (Okamoto, 2006). The wide composition range of TiC should be considered when using it as reinforcement material in metal-matrix composites. A uniform or gradual distribution of titanium carbide particles on a specific part of the material creates a hard and wear-resistant surface (Terry and Chinyanakobvu, 1991; Tiusanen *et al.*, 2009; Verezub *et al.*, 2003; Zhang, 1993). The reinforcement material can be added in powder processing or into the liquid metal before or during casting. Instead of adding the reinforcement into the whole material, it can also be added only locally to a certain surface in a casting where wear resistance is required. This leads to the combination of a hard surface and a tough matrix, for example in a stainless steel casting. Several studies have been published on adding TiC, (Ti,Mo)C or Ti/Mo and C directly to liquid low-alloyed or stainless steel or creating them in the melt (Chambers *et al.*, 1987; Chen *et al.*, 2009; Degnan and Shipway, 2002; Dogan *et al.*, 2006; Erauskin *et al.*, 2009; Funakawa *et al.*, 2004; Jang *et al.*, 2012; Jiang *et al.*, 2005; Parashivamurthy *et al.*, 2006; Razavi *et al.*, 2010; Terry and Chinyanakobvu, 1992/1; Terry and Chinyanakobvu, 1992/2; Verezub *et al.*, 2003; Wu *et al.*, 2008).

When adding a reinforcement material (ceramic) to liquid steel, wettability, stability and dissolution are key phenomena. Good wetting between the reinforcement material and the metal ensures good bonding and mechanical properties (Delannay *et al.*, 1987) and the desired distribution of the reinforcement particles in the melt. The size and shape of the particles is important as well. Fine particles provide better wear resistance and large, angular particles deteriorate toughness (Dogan *et al.*, 2006). The other alloying elements present in composite systems also play an important role. The elements affect the above-mentioned phenomena and might create new phases. The role of the main alloying elements in stainless steel on these phenomena have not been reported earlier to the extent that this thesis does.

Wetting is evaluated by measuring the contact angle. Wetting between the ceramic (substrate) and the liquid material is considered good when the contact angle is $<90^\circ$ and poor when it is $>90^\circ$. The interface between the ceramic and metal can be a reactive or non-reactive one (Eustathopoulos *et al.*, 1991). The wettability of a non-reactive interface can be improved by modifying the metallic phase through adding alloying elements that modify the interface. The alloying element can improve wetting by increasing the dissolution of the ceramic into the metal or by reacting with the ceramic to form a new product at the interface (Eustathopoulos and Coudurier 1992). The more metallic the new product, the more it improves wetting. Wetting between a transition metal carbide (such as TiC) and a metal is usually good. The metallic bonding at the interface results in low interfacial tension, dissolution of the ceramic into the

melt (and vice versa) and also in reactions between the melt and the ceramic (Delannay *et al.*, 1987; Parashivamurthy *et al.*, 2008; Warren, 1980). It is well-known that dissolved oxygen in a metal melt decreases the contact angle (Naidich, 1981). However, not all alloying elements or solutes improve wetting. The reaction product can in some cases also be detrimental to the mechanical properties (Delannay *et al.*, 1987). In the case of high-alloyed stainless steel the alloying elements (especially Cr, Ni and Mo) can significantly affect the wetting as well as other interfacial phenomena

To improve wetting the ceramic (substrate) can also be modified through alloying. Molybdenum is commonly added to reinforcement material to improve wettability and several studies about the addition of Mo to TiC containing composites and cermets have been made (Andrn, 2001; Cardinal *et al.*, 2009; Cutard *et al.*, 1996; Hussainova, 2003; Mari *et al.*, 2003; Samsonov *et al.*, 1972/1; Vallauri *et al.*, 2008; Zhang, 1993; Park *et al.*, 1999; Qian and Lim, 1999; Zhuo *et al.*, 2008). Mo can be added with the reinforcement material or with the binder/matrix metal. As a result of the Mo addition to the composites or cermets, the TiC or Ti(C, N) reinforcement particles tend to form core-rim type particles with TiC or Ti(C, N) in the core and (Ti, Mo)C or (Mo,Ti)(C,N) in the rim phase (Cutard *et al.*, 1996; Park *et al.*, 1999; Samsonov *et al.*, 1972/1; Zhang, 1993; Zhuo *et al.*, 2008). On the other hand, rim-core particles with a darker rim indicating a lower Mo content than the core have also been observed (Chen *et al.*, 2000; Liu *et al.*, 2006). Besides wetting, the addition of Mo to the reinforcement has been reported to result in improved hardness and yield strength, a more homogeneous structure, decreased size of the carbides, less dissolution of the carbides, more stable particles and smaller growth rate of the rim (Cutard *et al.*, 1996; Hussainova, 2003; Mari *et al.*, 2003; Samsonov *et al.*, 1972/1; Zhang, 1993). The addition of Mo to the binder has also been reported to improve the interface bond strength and wear resistance (Hussainova, 2003). In addition to Mo, nickel has also been found to improve wettability by decreasing the contact angle compared to iron (Samsonov *et al.*, 1972/2) and decreasing the particle size of the carbides (Jiang *et al.*, 2005).

In general, several phenomena have an effect on the functional inclusions or particles in steel. In most cases, the inclusions and particles formed are very complex and several other elements play important roles in the phenomena and behaviour of the particles as well.

2.3 Application of the materials

Steels having an acicular ferrite microstructure and a fine grain size as a result of titanium-containing inclusions, particularly oxide inclusions with a certain size range, can have superior mechanical properties - especially toughness - without compromising strength (Bhadeshia, 2001). These inoculated steels can be used for example in Arctic offshore applications. These steels retain their strength and toughness even at lower temperatures. Titanium-containing steels are also widely used in the automobile industry and pipelines.

The use of TiC-reinforced steel or stainless steel is concentrated in applications which require wear resistance. The material can also be only partly reinforced if wear resistance is only required of a certain part or surface of the component. This allows the rest of the material to be more ductile because it is not completely reinforced by the hard TiC particles.

2.4 Thermodynamic studies

Thermodynamic calculations were performed with FactSage 6.2 (for TiO_x systems) and 6.4 (for TiC systems) using the FSstel and FToxid databases in order to obtain information about the different phases formed in low-alloyed and stainless steel systems both in liquid state and during solidification related to this work (Bale *et al.*, 2016). The compositions used in the calculations represent the compositions used in the experiments of this work.

2.4.1 TiO_x systems

Titanium is very reactive with oxygen, nitrogen and carbon. Titanium oxides are of particular interest because Ti can exist in several oxidation states forming different oxides in steel, depending on the Ti and O contents, temperature and the presence of other elements especially Al (Babu *et al.*, 1995). Ti and O can form Ti_3O_5 , Ti_2O_3 , TiO_2 , Ti_4O_7 and TiO among others. As mentioned earlier, Ti_2O_3 seems to be the most beneficial of the oxides regarding the desired microstructure in the final solid steel.

Fig. 2 represents the predominance area diagram for oxides in low-alloyed steel containing Fe, Ti, Al, C, Mn, Si, O, N and S at 1600°C (Holappa and Kiviö, 2012). The dashed lines present the 2-phase region between slag and Al_2O_3 at 30ppm O_{tot} . At lower oxygen content, the region is very narrow and is thus not shown on the figure. Ti_3O_5 is the stable titanium oxide within a wide range of Ti content in the melt at 1600°C. The crosses represent the compositions of the experimental heats which are discussed later in conjunction with the experimental results. Industrial compositions have been added for reference. Based on several other studies and thermodynamic calculations of the Fe-Ti- (Al)-O system or low-alloyed steel, the stable titanium oxide in equilibrium with liquid steel is Ti_3O_5 at a Ti content of below 0.2-0.4 wt%, whereas at higher content the stable oxide is Ti_2O_3 (Jung *et al.*, 2009; Kang and Lee, 2010; Mutale *et al.*, 2004; Pak *et al.*, 2007; Wang *et al.*, 2009/2). In Fig. 2 the transition takes place at about 0.4 wt% Ti ($\log 0.4\text{wt}\% \text{ Ti} \approx -0.4$). It is worth noting that the other components in the steel may have a certain effect too. Based on the thermodynamic calculations, the Al content should be kept at a low level of <50ppm and the Ti/Al ratio should be at least around 15-20 to ensure the presence of titanium oxide dominant inclusions (Publications I and II). The predominance area diagram of oxides (Al_2O_3 , Ti_3O_5 , Ti_2O_3) and liquid oxide (slag) is shown as well as the respective oxygen isoactivity lines in the steel at equilibrium. Additionally, 2-phase regions can occur at total oxygen content higher than the equilibrium.

Figure 2. Predominance area diagram at 1600°C for oxides as a function of Al and Ti contents in steel with 0.15 wt% C, 0.2 wt% Si, 1.35 wt% Mn, 20 ppm S and 40 ppm Ntot (Holappa and Kiviö, 2012).

Figs. 3-5 represent the equilibrium formation of inclusions in steel containing Fe, Mn, Si, C, Ti, Al, O, N and S in the temperature range from 1600 to 1200°C. The effects of the Ti and Mn contents on inclusion formation can be observed from the figures. The slag phase represents mixed liquid oxide inclusions which consist mainly of Al_2O_3 (20-29 wt%), TiO_2 (26-28 wt%), Ti_2O_3 (39-48 wt%) and MnO (4-5 wt%). If Mn is not included in the calculations, the slag phase does not contain any MnO but only the three first mentioned. These inclusions are mostly liquid in liquid steel. In liquid steel the deoxidation product of Ti is Ti_3O_5 (Publication II). Ti_3O_5 is transformed to Ti_2O_3 during cooling. A similar transformation has been calculated in other studies (Kang and Lee, 2010). The transformation temperature range depends on the Ti and Mn contents of the steel. By increasing the Ti content from 0.05 to 0.07 wt% (Fig. 3 and Fig. 4), the formation of Ti_2O_3 starts already at higher temperatures during cooling and is much stronger. The Mn content also has a significant effect. In the system without Mn (Fig. 5), the formation of Ti_2O_3 starts at much lower temperatures than in the system containing Mn. Based on the calculations of the systems with Mn, the ilmenite phase (Ti_2O_3) consists mainly of Ti_2O_3 (>93%) with the rest being mainly MnTiO_3 . The increase in Ti content increases the Ti/Al ratio from 10 to 14 and the formation of Al_2O_3 is considerably reduced. According to the equilibrium calculations, the formations of Al_2O_3 , TiC and TiN increase at lower temperatures. This, however, is not very likely to take place in the experiments of this study as strongly as depicted in the thermodynamic calculations. The equilibrium calculations are discussed more below in conjunction with the experimental results.

Figure 3. Equilibrium calculation of 1.35 wt% Mn - 0.2 wt% Si - 0.15 wt% C - 0.05 wt% Ti - 50 ppm Al - 30 ppm O - 40 ppm N - 20 ppm S – balance Fe system between 1600 and 1200°C.

Figure 4. Equilibrium calculation of 1.35 wt% Mn - 0.2 wt% Si - 0.15 wt% C - 0.07 wt% Ti - 50 ppm Al - 30 ppm O - 40 ppm N - 20 ppm S – balance Fe system between 1600 and 1200°C (Holappa and Kiviö, 2012).

Figure 5. Equilibrium calculation of 0.2 wt% Si - 0.15 wt% C - 0.07 wt% Ti - 50 ppm Al - 30 ppm O - 40 ppm N - 20 ppm S – balance Fe system between 1600 and 1200°C (Holappa and Kiviö, 2012).

Most of the titanium in the calculations is present in the liquid steel at higher temperatures and in the austenite (FCC) phase at lower temperatures. The FCC phase includes the titanium as dissolved [Ti]FCC and TiC and TiN precipitates. The distribution of titanium into different phases and dissolved titanium is not shown in the figures above but was represented in the reference article (Holappa and Kiviö, 2012).

2.4.2 TiC systems

Fig. 6 represents the equilibrium carbide formations in stainless steel containing Fe, Cr, Ni, Mn, Si, Ti and C and Fig. 7 those in stainless steel containing Fe, Cr, Ni, Mo, Mn, Si, Ti and C in the temperature range of 1600-800°C (Kiviö 2016). The composition of the stainless steel is based on the experiments described later in this study. Ti and C are included in the calculations as 5 vol% TiC at 1600°C. At this temperature TiC is fully decomposed and dissolved as [Ti] and [C] (Ti-LIQ and C_LIQ respectively). TiC formation starts below 1550°C. In both calculations, a complex carbide is formed at lower temperatures around 1100°C (Figs. 6-7) with and without Mo.

In Fig. 6 the carbides are TiC and $M_{23}C_6$ type, consisting mainly of $Cr_{20}Fe_3C_6$ i.e. with some Fe and very little Ti. In Fig. 7 with Mo in the stainless steel the carbides are TiC and $M_{23}C_6$ type, consisting mainly of $Cr_{20}Mo_3C_6$ i.e. with some Mo and very little Ti. The calculations did not show any nickel in the carbides.

Figure 6. Equilibrium calculation of 19 wt% Cr- 8.5 wt% Ni - 0.48 wt% Si - 0.95 wt% Mn – 5 wt% TiC– balance Fe system between 1600 and 800°C (Kiviö *et al.*, 2016).

Figure 7. Equilibrium calculation of 19 wt% Cr- 8.5 wt% Ni - 0.48 wt% Si - 0.95 wt% Mn – 5 wt% TiC– 0.8 wt% Mo - balance Fe system between 1600 and 800°C (Kiviö *et al.*, 2016).

3. Experimental

The experimental part of this thesis consisted mainly of two types of experiments: the addition of Ti- and TiO₂-containing particles into liquid low-alloyed steel, and wetting experiments between TiO₂ or TiC and iron-based materials. These experiments were chosen because they simulated actual conditions in production processes and provided important results about the interfacial phenomena. All parameters related to the experiments were recorded. Samples resulting from the experiments were analysed and evaluated using mainly scanning electron microscopy and energy-dispersive X-ray spectroscopy (SEM-EDS) but also wavelength-dispersive X-ray spectroscopy (SEM-WDS), optical emission spectroscopy (OES), combustion analysis and electron backscatter diffraction (EBSD) methods. The experiments and analysis methods are presented in the following chapters.

3.1 Materials used in the experiments

Both metallic Ti and TiO₂ were added into a low-alloyed steel melt. They were added in different forms and in different amounts. TiC and TiO₂ substrates were used in the wetting experiments with pure Fe, Fe alloys (Fe-X), low-alloyed steel and stainless steel.

3.1.1 Low-alloyed steel, stainless steel and Fe alloys used in the experiments

Low-alloyed steel was used in the experiments with Ti/TiO₂ additions and in the wetting experiments with TiO₂. Pure Fe, Fe alloys and stainless steel (304) were used in the wetting experiments. The chemical compositions of the materials are presented in Table 1.

Table 1. Chemical composition of the low-alloyed steel and stainless steel (304) in wt% and ppm.

Material	C	Mn	Si wt%	Cr	Ni	Mo	Al	Ti ppm	S	N
Low-alloyed steel	0.11	1.46	0.22	0.65	-	-	290	20	10	38
Stainless steel	0.008	0.93	0.51	19.9	9.3	0.29	<170	-	300	181

The Fe₂O₃ and carbon used in the Ti/TiO₂ addition experiments were commercial powders.

The pure Fe used in the wetting experiments was electrolytic iron (99.95 wt%).

The alloys used in the wetting experiments were the following: FeCr23, FeCr22.8, FeCr18.2, FeNi9.5, FeNi9, FeNi6.5, FeMo5.2, FeMo3.7 and FeMo3.5, where the number indicates the alloying element content in wt%. These represent typical alloying element contents in stainless steels. These alloys were made from electrolytic iron or iron powder (99.5 wt%) and commercial alloying element powders with a purity of 99.9. The alloys were melted in argon atmosphere, soaked and left to solidify (Heikkinen, 2009; Publication III). Small pieces suitable for the wetting experiments were cut from the solidified ingots.

3.1.2 Ti and TiO₂ materials added to low alloyed steel melt

Metallic titanium was added as 5-30 mm sized FeTi flakes (72.6 % Ti, 2.7 % Al, and about 24 % Fe with some minor impurities) or as 10 mm thick Ti bar (99.999% Ti).

The TiO₂-containing materials were added either as pellets or cylinders. The approximately 10 mm sized pellets produced at Sintef Norway (Grong 2006) contained about 10 wt% TiO₂ and 5 wt% Al₂O₃ with the rest being metallic Fe. The cylinders (10 wt% TiO₂ and 90 wt% Fe) were prepared by mixing and compressing chemically pure TiO₂ (99.8 wt%) and carbonyl iron powders with minimum 99.5 wt% Fe (Publication I).

3.1.3 TiC, TiCMo and TiO₂ substrates for the wetting experiments

The TiC substrates used for the wetting experiments were made of commercial stoichiometric TiC powder (1-3µm, H.C. Starck Standard 120 titanium carbide, ≥ 19.2 wt% C) or by igniting commercial Ti and C powder to form TiC powder (<32 µm) by SHS technique (Tiusanen *et al.*, 2009). The TiCMo substrates were also prepared by the SHS technique by igniting Ti, C and Mo powders with 14 wt% Mo. The Ti/C or Ti+Mo/C atomic ratio was 1 in both powders. The TiC and TiCMo powders were then spark plasma sintered (SPS) to form cylindrical substrates with a density of 92-98 % (Publication III and IV). The TiO₂ substrates used were commercial, 3 mm thick TiO₂ sheets of 99.6% purity (TI603300 Goodfellow).

3.2 Addition of Ti and TiO₂ to liquid steel

Altogether seven experiments related to the addition of Ti and TiO₂ to low alloyed steel were done at the Foundry Institute of Tampere University of Technology. The experiments were performed inside a furnace chamber in argon atmosphere including heating, melting, temperature measurement and control, sampling, additions and casting (Publication I). The experimental procedures are described in Table 2, the amounts of additives are presented in Table 3 and the exact addition, sampling and casting times are given in Table 4. The charge consisted of 29 kg of low-alloyed steel (Table 1) and 56 g Fe₂O₃ to decrease the Al content of the melt. Carbon was added after meltdown to

increase the carbon content slightly. Metallic Ti was added first before the addition of TiO_2 to deoxidize the steel and to modify the inclusions into Ti bearing ones. Then TiO_2 was added to boost the number of Ti oxides in the steel. The Ti-containing additives were inserted with a special adding device which was submerged into the melt (Publication I). In experiments 3 and 4 TiO_2 was added later in the mould during casting with a similar adding device. The FeTi flakes, Ti bar and TiO_2 -containing cylinders dissolved well when added to the melt. However, the TiO_2 pellets did not disperse as desired. Instead they floated on the top of the melt and became attached to the walls of the crucible. In the mould additions neither the pellets nor the cylinders dissolved completely because of the lower temperature and the short time before solidification. The melt samples were taken inside the furnace chamber with a small crucible through an air-tight hatch. The sample was immediately placed into water to quench it and retain the melt conditions (Publications I and II).

Table 2. Experimental procedures and approximate times (Publication I).

Procedure	Time Approx. min
Start of heating in vacuum 0.3 to 0.4 Pa	0
Atmosphere change to argon 700 mbar	30
Charge completely molten	50-55
Temperature check	52-57
Melt sample 1	55-60
Carbon addition	58-63
Temperature check	61-66
FeTi/Ti addition into the melt	64-69
TiO_2 addition into the melt (experiments 5-7)	67-72
Melt sample 2	70-75
Temperature check	73-78
Casting (TiO_2 mould additions only in experiments 3-4)	~80

Table 3. Additions in the experiments (Publication I).

Experiment	Ti as FeTi (g)	Ti as bar (g)	TiO_2 pellets (g)	TiO_2 cylinders (g)	Location of TiO_2 addition	
					In the crucible	In the mould
1	27.6	-				
2	21.8	-				
3	-	20	4.75			x
4	-	20		5.0		x
5	-	20		5.0	x	
6	-	20	4.75		x	
7	-	28		9.86	x	

Table 4. Additions, sampling and casting times (Publication I).

Experiment	FeTi/Ti Addition (min)	TiO_2 Addition (min)	Melt 2 Sample (min)	Start of casting (min)
1	69	-	72	79
2	64	-	66	75
3	68	80	71	80
4	66	83	69	83
5	70	73	75	79
6	65	68	71	75
7	70	73	76	81

The target temperature for casting was 1570°C. The molten steel was cast into two ingots and the size of the moulds was the same in all experiments. The cooling of the ingot during casting was measured in experiment 7 (Publication I). The ingot samples were cut from the lower part of the ingot after removing an approximately 40-mm-long piece from the bottom and by cutting the sample from the middle of the cross section (Publications I and II).

3.3 Wetting experiments between titanium-containing materials and liquid Fe alloys or steel

The wetting experiments were done to determine the contact angle indicative of wetting, to study the interface and other particles and phases found in the system.

In all the wetting experiments the contact angle during the experiment was recorded by taking pictures of the specimens. The contact angle was measured from both sides of the droplet and calculated from the images using Image J software.

3.3.1 TiC wetting experiments

All the substrates were ground, polished and washed before each experiment to make sure the surface was flat and free of any debris. The TiC substrate was replaced by TiCMo in 3 experiments to study the effect of Mo addition into the substrate. Two types of wetting experiments with TiC were performed. Type A experiments were normal sessile drop experiments and type B were experiments with separate heating of the substrate and the metal. A summary of the TiC and TiCMo wetting experiments is presented in Table 5.

Table 5. Summary of the TiC and TiCMo wetting experiments (Publications III and IV).

Experiment No	Type	Abbreviation	Metal (alloy wt%)	Substrate	Substrate Density %	Holding Time (min)	Holding Temp. (°C)
1	A	Fe-TiC A	Fe	TiC	98	30	1550
2	A	FeCr22.8 A	FeCr22.8	TiC	98	30	1550
3	A	FeCr18.2 A	FeCr18.2	TiC	98	15	1550
4	A	FeNi9.5 A	FeNi9.5	TiC	98	15	1550
5	A	FeNi6.5 A	FeNi6.5	TiC	98	15	1550
6	A	FeMo5.2 A	FeMo5.2	TiC	98	15	1550
7	A	FeMo3.7 A	FeMo3.7	TiC	98	15	1550
8	B	Fe-TiC B	Fe	TiC	98	10	1550
9	B	Fe-TiC B5	Fe	TiC	98	5	1550
10	B	Fe-TiC B3	Fe	TiC	92	3	1550
11	B	FeCr23 B	FeCr23	TiC	98	10	1550
12	B	FeNi9 B	FeNi9	TiC	98	10	1550
13	B	FeMo3.5 B	FeMo3.5	TiC	98	10	1550
14	B	304-TiC B	304	TiC	92	10	1550
15	B	Fe-TiCMo B	Fe	TiCMo	92	10	1550
16	B	Fe-TiCMo B3	Fe	TiCMo	92	3	1550
17	B	304-TiCMo B	304	TiCMo	92	10	1550

Sessile drop experiments (Type A)

These experiments were done as part of a Master's thesis at Helsinki University of Technology (Heikkinen, 2009).

The substrate with a metal piece (to form the droplet) on the top were heated together in an Ar-1%H₂ atmosphere. The specimens were kept in the midway of the furnace until the hottest part of the furnace had reached about 1430°C. At that point, the specimens were moved slowly to the hottest part of the furnace to heat them up to the holding temperature. In the midway, the temperature reached a maximum of 727°C. This was done to minimize the reactions between the substrate and the metal during heating. To summarize, the specimen was heated to 727°C at a rate of 4.17°C/min and from 727°C up to the experiment holding temperature at 50°C/min.

The time when the metal had completely melted down and formed a droplet was the starting point ($t=0$) of the contact angle measurement. The holding time was 15 or 30 min. After the holding period the specimen was moved to the cooler end of the furnace to 800°C and left to solidify. Then the specimen was cooled down to room temperature at a rate of 4.17°C/min.

Wetting experiments with separate heating of the substrate and the metal (Type B)

Type B wetting experiments were performed at Osaka University, Japan (Publications III and IV).

In type B experiments, only the substrate was placed inside the furnace and the metal piece to be melted was kept outside the furnace. An alumina tube was placed inside the furnace through an air-tight lid and a rubber tube with the metal piece inside was attached to the other end of the alumina tube. The head of the alumina tube was placed on top of the substrate inside the furnace. The atmosphere inside the furnace was Ar-10%H₂ and the oxygen content around 30 ppm. The furnace with the substrate was heated up to 300°C at a rate of 13.8°C/min, from 300-800°C at 12.5°C/min, from 800-1400°C at 8.6°C/min and from 1400-1550°C at 7.5°C/min.

When the furnace had reached the holding temperature of 1550°C, the metal piece was dropped from the rubber tube to the lower end of the alumina tube. The metal piece was then inside the alumina tube, which was placed on top of the substrate. There, the metal piece melted in 1-2 minutes and fell from the tube on top of the substrate, forming a droplet. In these experiments the starting point ($t=0$) for the contact angle measurement was the point when the metal droplet fell onto the substrate. The holding times were 3, 5 and 10 minutes depending on the experiment. 10 minutes was the normal holding time and 3/5 minutes were chosen to study the dissolution of the substrate and infiltration of the melt. After holding, the furnace was cooled down rapidly to 1400°C at 50°C/min to avoid reactions during solidification, and then down to room temperature at 9.8°C/min.

In these experiments, reactions between the substrate and the metal were avoided during heating and the test resembled actual casting conditions more closely than type A.

3.3.2 TiO₂ wetting experiments

The TiO₂ wetting experiments were performed at Osaka University, Japan. The TiO₂ wetting experiments were similar to normal sessile drop experiments of type A. Both the substrate and the metal were placed inside a furnace. The atmosphere inside the furnace was changed to Ar-10%H₂. The furnace was heated up to 1550°C according to the same settings as in the type B wetting experiments. The holding time at 1550°C was 30 min. The furnace was allowed to cool down at a rate of 9.8°C/min. Three experiments are represented in Table 6.

Table 6. Wetting experiments between TiO₂ and pure Fe or steel.

Experiment No	Experiment		Metal (alloy wt%)	Substrate	Holding	
	Type	Abbreviation			Time (min)	Temp. (°C)
1	A	Fe-TiO ₂ A	Fe	TiO ₂	30	1550
2	A	Steel-TiO ₂ A	Steel	TiO ₂	30	1550
3	A	SteelTi-TiO ₂ A	Steel+Ti	TiO ₂	30	1550

The steel referred to in Table 6 is listed in Table 1 as low-alloyed steel. Steel+Ti is the same low-alloyed steel with 0.074 wt% titanium. The cross sections of the samples from the wetting experiments were studied by SEM-EDS and WDS.

3.4 Analysis of the samples

3.4.1 Chemical analysis

The chemical composition was analysed for all samples from the experiments using low-alloyed steel and additions of Ti/TiO₂. The chemical analyses were mostly performed using optical emission spectroscopy. Oxygen and nitrogen contents were analysed by combustion analysis. All chemical analyses were carried at an external laboratory.

3.4.2 Scanning electron microscopy, energy-/wavelength-dispersive X-ray spectroscopy (SEM-EDS/WDS) and electron backscatter diffraction (SEM-EBSD)

All samples from each experiment were studied with a scanning electron microscope (SEM) and by microanalysis. Before the SEM study the samples were mounted, ground and polished up to 1µm. The SEM used was a LEO SEM 1450. The microanalyses were done by energy- (EDS) and wavelength-dispersive (WDS) X-ray spectroscopy (Oxford Instruments) and using INCA software version 17b (Oxford Instruments). Wave dispersion was only used for studying the samples from the TiO₂ wetting experiments. An accelerating voltage of 12 keV was used in the study of low-alloyed samples and 15keV in the study of wetting experiment samples. It should be mentioned that the detection limit for EDS is approximately 0.1 wt% and content below 1 wt% should not be considered accurate.

In addition, INCA Feature, which is a part of the INCA software, was used for the TiO₂ inclusion study of low-alloyed steel. It automatically finds and analyses

the inclusions (features) in a predetermined area according to predetermined criteria. In this work the size of the predetermined area was 1mm^2 , the resolution 2048×2048 and magnification $2000\times$. Inclusions smaller than 150nm (2 pixels) were omitted from the analysis due to the fact that the uncertainty in the microanalysis was too high.

Two samples from the experiments with TiO_2 additions into low-alloyed steel were chosen for SEM-EBSD (Oxford Instruments Nordlys F+ camera and Channel 5 software) studies to determine the type of TiO_x inclusions (Publication II).

4. Summary of the results

4.1 Experiments with Ti and TiO₂ additions into low-alloyed steel

4.1.1 Chemical composition

Table 7 represents the chemical composition analyses by OES and combustion analysis of all samples from the Ti/TiO₂ experiments. The first number refers to the experiment number and the letter m and i to melt (m1 and m2) and ingot (i1 and i2) respectively (Table 2).

Table 7. Chemical composition of all samples from Ti/TiO₂ addition experiments (Publication I).

Sample	C	Mn	Si wt%	Cr	Ti	Al	O _{tot} ppm	N _{tot}	S
1 m1	0.1	1.41	0.21	0.65	0.005	60	55	30	13
1 m2	0.14	1.4	0.21	0.64	0.085	80	21	42	15
1 i1	0.15	1.41	0.21	0.64	0.074	70	19	49	15
1 i2	0.15	1.42	0.22	0.64	0.074	70	18	51	12
2 m1	0.09	1.39	0.21	0.65	0.009	50	42	27	22
2 m2	0.16	1.39	0.22	0.64	0.069	60	25	36	25
2 i1	0.16	1.41	0.22	0.64	0.053	60	21	51	27
2 i2	0.16	1.4	0.22	0.63	0.05	60	21	53	18
3 m2	0.16	1.35	0.19	0.63	0.057	50	29	34	20
3 i1	0.16	1.35	0.19	0.63	0.039	50	31	46	19
3 i2	0.16	1.35	0.19	0.63	0.038	50	35	51	20
4 m1	0.09	1.35	0.19	0.63	0.004	50	25	28	15
4 m2	0.17	1.37	0.2	0.64	0.062	40	19	41	20
4 i1	0.16	1.35	0.2	0.63	0.041	60	41	74	21
4 i2	0.16	1.35	0.2	0.63	0.04	60	40	83	21
5 m1	0.1	1.36	0.19	0.64	0.005	60	40	31	16
5 m2	0.17	1.35	0.19	0.63	0.049	50	33	44	20
5 i1	0.16	1.35	0.2	0.63	0.039	50	36	53	19
6 m1	0.1	1.35	0.19	0.63	0.006	60	32	31	13
6 m2	0.16	1.35	0.19	0.63	0.047	50	24	45	20
6 i1	0.16	1.36	0.2	0.63	0.038	50	31	50	19
6 i2	0.16	1.37	0.2	0.63	0.036	50	30	60	20
7 m1	0.1	1.34	0.19	0.63	0.005	50	39	30	13
7 m2	0.16	1.34	0.2	0.63	0.07	60	37	46	17
7 i1	0.16	1.35	0.2	0.63	0.057	60	30	57	17
7 i2	0.15	1.34	0.2	0.63	0.053	50	26	66	17

The Ti contents are highest in the m2 samples, because the samples were taken immediately after the addition of Ti and TiO₂. The overall yield for Ti additions was 55-75%. In experiments 3 and 6, as well as 4 and 5, the same amounts of Ti and TiO₂ were added but at different stages of the experiments. In experiments 3 and 6 TiO₂ was added as pellets and in 4 and 5 as cylinders. Even though in experiments 3 and 4 the TiO₂ was added later during casting the final Ti content in the ingot is not much higher. In other words, the yield is nearly the same. This

will, however, be discussed later in more detail in conjunction with the number and size of TiO_x inclusions. The Al content was decreased down to about 50ppm in the experiments with TiO_2 additions.

4.1.2 Inclusion analysis

Several types of inclusions were found in the samples. Inclusions containing titanium were divided into TiN-dominant and TiO_x -dominant inclusions. This study concentrates on TiO_x inclusions, but the presence of TiN inclusions cannot be avoided under these conditions. Ingots from experiment 1 and 2 had the lowest number of TiO_x inclusions, whereas ingots from experiments 3 and 4 had the highest. Addition of Ti+ TiO_2 instead of Ti alone seems to increase the number of TiO_x inclusions. The later the TiO_2 was added, the more TiO_x inclusions and the more Ti-containing inclusions found in the ingots. Especially in experiment 4, addition into the mould created significantly more TiO_x inclusions (Publication I).

The size of the inclusions was evaluated from the INCA Feature results (width and length) (Publication I). The biggest TiO_x inclusions were found in the ingots from experiment 1 and the smallest in experiments 3 and 4. The earlier the inclusions were added, the more time they had to grow in the melt. The size distribution of the inclusions in experiments 4 and 7 corresponded well with the size distribution of the TiO_2 powder used for the additives, suggesting successful addition.

The percentage of manganese and aluminium-containing TiO_x inclusions was also studied (Publication I). Most of the TiO_x inclusions (>74%) from experiments 3-7 contained Mn. The percentage of Al-containing TiO_x inclusions increased significantly between the melt 2 and the ingot samples in experiments 3-7. The average Al content in the TiO_x inclusions was 0.5-2.2 wt% (melt 2 samples) and 1.7-3.3 wt% (ingot samples) for experiments 3 and 5-7. Experiments 1, 2 and 4 had a higher (8.7-10.9 wt%) average Al content. Experiment 4 had the lowest Ti/Al ratio of the ingot samples and also the lowest Ti/Al ratio in the TiO_x inclusions (Table 8). The Ti/Al ratios of the steel in both the melt and ingot samples as well as the Ti/Al ratios of the inclusions in the melt and ingot samples are listed in Table 8. The Ti/Al ratio in the melt and ingot samples were calculated from the OES results in Table 7 as an average. The Ti/Al ratios of the inclusions were calculated from the SEM-EDS results of the inclusions as an average.

Table 8. Ti/Al ratios of melt and ingot samples and Ti/Al of TiO_x inclusions in melt and ingot samples

Experiment	Ti/Al in melt sample	Ti/Al in TiO_x inclusions in melt sample	Ti/Al in ingot sam- ples	Ti/Al in TiO_x inclusions in ingot sample
1	10.6	11.8	10.5	4.9
2	11.5	6.4	8.6	3.8
3	11.4	50.5	7.7	14.0
4	15.5	56.3	6.8	4.6
5	9.8	43.6	7.8	19.8
6	9.4	24.6	7.4	29.7
7	11.7	55.7	10.1	24.5

The Ti/Al ratios are higher in the melt samples and in the TiO_x inclusions in the melt samples compared to the ingot samples. The Ti/Al ratios of the steel show some variation between the experiments. In contrast, the inclusions have much more variation in terms of the Ti/Al ratio in both melt and ingot samples. The results are discussed in more detail in the discussion section of this thesis.

Based on the SEM-EDS studies using INCA Feature, the inclusions were divided into four types. The inclusion types found in the ingot samples are presented in Fig. 8. Many inclusions contained both Mn and Al. For this reason, some inclusions are present in two groups in Fig. 8, resulting in total percentages higher than 100%. For example, an inclusion containing Mn + S and some Al was found in both TiO_x+Mn(O,S) and TiO_x+Al₂O₃. The average composition of the TiO_x+MnO inclusions is presented in Fig. 9.

Figure 8. Different inclusions groups in ingot samples (Publication II).

Figure 9. Average composition of TiO_x+MnO inclusions in ingot samples (Publication II).

Examples of the four different inclusions types are presented in Figs. 10-15. It should be noted that elements such as Fe, Cr, Mg and C in the analyses originate from the surrounding steel matrix and crucible material (Mg). Light elements such as O, C, N and S cannot be analysed precisely by SEM-EDS. The presence of carbon in some of the inclusion analyses could mean that some inclusions also contain carbides. Small amounts of carbon could also be due to

contamination. Figure 13 is taken from the melt sample (before any addition of TiO_2) and the rest of the inclusion examples are from the ingot samples.

Figure 10. Example of a TiN+TiO_x inclusion with Al (18.3 wt% N, 19.4 wt% O, 8.6 wt% Al, 48.4 wt% Ti and 5.3 wt% Fe) in experiment 1 ingot sample.

Figure 11. Example of a Ti-Al oxide inclusion with MnS (27.9 wt% O, 10.5 wt% Al, 2.5 wt% S, 28.5 wt% Ti, 4.5 wt% Mn and 5.3 wt% Fe) in experiment 2 ingot sample.

Figure 12. TiO_x+Mn inclusion (30.1 wt% O, 0.4 wt% Al, 0.2 wt% S, 36.9 wt% Ti, 6.6 wt% Mn, 14.0 wt% Fe, 9.2 wt% C, 0.2 % Mg, 0.3 wt% Si, 0.3 wt% Ca and 1.8 wt% Cr) in experiment 3 ingot sample.

Figure 13. TiN+TiO_x inclusion (left with 12.9 wt% N, 7.0 wt% O, 76.3 wt% Ti, 2.4 wt% Fe and 1.4 wt% C) and TiO_x+MnS inclusion (right 20.4 wt% O, 0.3 wt% Al, 2.9 wt% S, 6.4 wt% Mn, 41.1 wt% Ti, 27.5 wt% Fe, 0.4 wt% Mg and 0.9 wt% C) in experiment 4 melt sample.

Figure 14. TiO_x+Mn inclusion (30.2 wt% O, 0.4 wt% Al, 48.1 wt% Ti, 7.6 wt% Mn, 12.2 wt% Fe, 0.6 wt% C, 0.3 % Mg and 0.6 wt% Cr) in experiment 4 ingot sample.

Figure 15. Example of a TiO_x+Mn inclusion (32.7 wt% O, 1.3 wt% Al, 51.1 wt% Ti, 4.9 wt% Mn, 7.6 wt% Fe, 1.2 wt% C, 0.7 wt% Mg and 0.6 wt% Cr) in experiment 7 ingot sample.

Experiments 3-7 with addition of TiO₂ contained far more TiO_x+MnO inclusions. As a result of this, the absolute amount of Mn found in the inclusions was

also higher in experiments with TiO_2 addition. Al was found in many TiO_x inclusions as well, but the amounts were small. Most of the inclusions contained Mn and/or Al, but TiO_x was clearly the main phase in the inclusions.

The Mn/S ratios in the inclusions were also compared. The results indicated that, in the $\text{TiO}_x + \text{Mn}(\text{O}, \text{S})$ inclusions, Mn was present as both sulphide and oxide. This would mean that at least 75% (Fig. 8) of the inclusions in experiments 3-7 contained Mn as oxide, either pure MnO or complex Ti-Mn oxides. In experiments 1 and 2, they accounted for approx. 30% and 50%, respectively.

Altogether five inclusions from the experiment 4 ingot sample and experiment 5 melt samples were studied by SEM-EBSD (Publication II). Only Ti_2O_3 was found in both ingot and melt samples and there was no TiO_2 or Ti_3O_5 . The absence of Ti_3O_5 in the melt samples could be explained by the fact that the cooling of the melt sample was too slow.

The titanium oxide inclusions found in the experiments were compared with inclusions found in industrial samples (Holappa and Kiviö, 2012). The inclusions in the industrial samples contained much more Al, with Al_2O_3 being the main phase in the inclusions. The Ti/Al ratio in the industrial samples was 7-8 and the Al content approx. 0.02 wt%. In the experiments carried out in this study, the ratio was 7-10 and the absolute Al content much lower. In addition, the Mn content of the inclusions in the industrial samples was lower, even though the Mn content of the steel was higher. The higher titanium oxide content of the inclusions resulted in a higher Mn content as well.

4.1.3 TiO_2 wetting experiments

The results concerning wetting and contact angles were published in the research project report (Andersson *et al.*, 2011). The wetting between TiO_2 substrate and the different melts was poor with a contact angle of 100° for pure Fe and $85\text{--}90^\circ$ for the two different steels. The most interesting results were found during the SEM-EDS and WDS studies of the samples after the wetting experiments.

The SEM-EDS analysis of the Fe- TiO_2 experiment did not reveal any significant findings. Very small amounts of Fe were found at the interface in the TiO_2 substrate. The origin cannot be confirmed on the basis of SEM-EDS analyses. The analyses of the experiments with steel revealed some interesting results. The low-alloyed steel contained 1.5 wt% Mn, but no trace of Mn was found in the steel droplets in the SEM-EDS analyses (Fig. 16). In contrast, the substrate contained up to 4.4 wt% Mn in the vicinity of the droplet (Fig. 17). Not even the steel droplets found inside the substrate contained any Mn (Fig. 18). Thus, all the Mn from the steel must have been absorbed into the TiO_x substrate. Aluminium was not found in any of the analyses despite the fact that there was some Al contained in the steel. The EDS analyses for each spectrum are presented in Table 9.

Figure 16. SEM-BSE image of the steel droplet (light) and substrate (dark) interface.

Figure 17. SEM-BSE image of the steel droplet (light) and substrate (dark) interface.

Figure 18. SEM-BSE image of the steel droplet (light) inside the substrate (dark).

Table 9. EDS analyses of the droplet, TiO₂ substrate and small steel droplet inside the substrate in wt%.

Spectrum	O	Ti	Cr	Mn	Fe
Fig. 16	-	-	0.5	-	99.9
Fig. 17	41.2	47.6	2.3	4.4	4.5
Fig. 18	-	1.0	0.4	-	85.7

The TiO₂ substrate sheets were white before the wetting experiments, which is a typical colour for TiO₂. After the experiments, the colour of the substrate sheets had turned to blueish and brownish. The change in colour suggested that a reduction of TiO₂ might have taken place during the experiment. SEM-WDS was used to analyse the TiO₂ substrate after the wetting experiments in the Fe-TiO₂ sample. The Ti and O contents were analysed to verify which titanium oxide the reduced substrate was. Some of the results are presented in Table 10 as at% with the SEM-BSE image presented in Fig.19.

Table 10. WDS and EDS analyses of the TiO₂ substrate after wetting experiments in at%.

Spectrum	O	Ti	V	Fe
1	61.0	33.7	0.3	5.1
3	59.1	35.7	0.2	5.0
4	66.1	32.9	0.2	0.8
5	62.9	36.0	0.3	0.9
6	65.2	33.8	0.2	0.7

Figure 19. SEM-BSE image of TiO₂ substrate after the experiment.

Ti and O were analysed by WDS and the rest by EDS. TiO₂ (rutile) and pure Ti were used as standards for the analyses. The origin of the vanadium remained unknown and iron came from the droplet material. The results indicate that the TiO₂ had been reduced partly to Ti₂O₃ (lighter phase), leaving some darker TiO₂ and possibly some Ti₃O₅. The lighter phase can be seen next to the pure Fe droplet.

These results strongly suggested that a Ti_2O_3 substrate was formed at the interface of the TiO_2 substrate and the metal droplet, and absorbing Mn from the steel causing the steel to be Mn depleted.

4.2 TiC wetting experiments

4.2.1 Contact angles

The contact angles discussed here are an average of the values from both sides of the substrate. The values did not differ significantly between different sides. The measured contact angles from all the experiments are presented in Figures 20-24.

Chromium did not have any significant effect on the wetting in type A experiments but in type B experiments Cr decreased the wetting somewhat. Ni increased the initial contact angle but decreased the minimum contact angles in type A experiments. Ni increased the initial contact angle in type B experiments as well, but did not have any significant effect on the minimum angles. Molybdenum alloying decreased the lowest contact angles in type A experiments, but increased them slightly in type B experiments. The replacement of TiC substrate with TiCMo substrate decreased the contact angle slightly in both pure Fe and 304 experiments. Using stainless steel instead of pure Fe did not have any significant effect on wetting.

Figure 20. Measured contact angles for type A experiments with Cr and Ni alloying (modified from Publication III).

Figure 21. Measured contact angles for type B experiments with Cr and Ni alloying (Publication III).

Figure 22. Measured contact angles for type A experiments with Mo alloying (modified from Publication IV).

Figure 23. Measured contact angles for type B experiments with Mo alloying (Publication IV).

Figure 24. Measured contact angles for type B experiments with stainless steel (modified from Publication IV).

The increase in the contact angles towards the end of the holding periods is due to the appearance of TiC at the surface of the droplet followed by solidification of the surface. This was also observed by the very uneven and rough surface appearance of the samples after the experiments (Fig. 25). Figure 25 summarizes the droplet behaviour during the holding in type B experiments. Only type B experiments are presented in Fig. 25, but samples in type A experiments behaved the same way. The behaviour was even more marked as a result of the longer holding period. Solidification of the surface was not observed in the experiments with short holding times. Droplets alloyed with Ni and Mo were in the liquid state and no solidified surface was clearly observed at the end of the holding period. However, during cooling the surface of the droplet also gained a rough appearance as well, although slightly less rough.

Figure 25. Droplets from type B experiments at different times (0, 2, 6 and 9 min) after start of holding period: on the right the substrate and solidified droplet at room temperature after the experiment (Kiviö *et al.*, 2016).

In general, the wetting was good with low contact angles in all experiments. The wetting behaviour in the different experiment types did not exhibit any major differences and the alloying had only minor effects on wetting.

Interface and penetration zone in the substrate

During the wetting experiments the melt penetrated the substrate strongly along the grain boundaries. Also, a high degree of interface roughness was observed in all the experiments. The penetration depths were calculated from the SEM-BSE images (Publications III and IV). In general, the penetration depths were greater in type A experiments due to the different experimental setup. Alloying increased the penetration: Ni having the strongest effect followed by Cr and Mo. In type B experiments, stainless steel had the shallowest penetration depths. The melt penetrated into the TiC substrate more than into the TiCMo

substrate. The shallowest penetrations could also be explained by the slightly different substrates (Table 5). The effect of holding time on the penetration depth could be seen from type B experiments with pure Fe and different holding times (experiments 9-11). The penetration depth decreased with shorter holding times. However, the dissolution of the substrate was very strong even in these experiments.

4.2.2 SEM study of the wetting experiment samples

A typical SEM-BSE image of the interface of the wetting experiment samples is presented in Figure 26. The dark area on the left is the substrate, next right from the substrate is the penetration zone, and the light phase on the right is the alloy droplet. The alloy droplet contains a lot of TiC particles having different shapes and sizes. Average SEM-EDS analyses of the wetting experiment samples for type B experiments are presented in Table 11. The results were first presented in Publications III and IV.

Figure 26. SEM-BSE image of the interface in experiment FeMo3.5 B.

The numbers (1-4) in Figure 26 refer to the substrate (1), TiC particles inside the alloy droplet (2), the alloy phase in the penetration zone (3) and the alloy droplet (4) in Table 11. As an example, in the FeCr23 B experiment the substrate (1) contained 0-2.2 wt% Fe, 75-81 wt% Ti and 0.6 wt% Cr. As a second example, in the FeMo3.5 B experiment the alloy phase in the penetration zone contained 0.9-2.8 wt% Ti, no Mo and of course Fe. The Fe content of the alloy is not included in Table 11.

Table 11. Average SEM-EDS analyses (wt%) of the substrate and alloy at the penetration zone and in the droplet (Kiviö *et al.*, 2016).

Experiment	Substrate	Contents in: Substrate / TiC particles inside Alloy Droplet/ Alloy Phase in Penetration Zone / Alloy Droplet	
	Fe	Ti	Cr/Ni/Mo
Fe-TiC B	0-1.4	75-81/81/0.8-3.5/0-1	0
FeCr23 B	0-2.2	74-77/ - /0.8-1.1 /0.3	Cr: 0.6/-/17.2-18/15.8
FeNi9 B	0	73-75/73-74/1-2.8/0-0.3	Ni: 0/0/6.1-6.8/6.2-6.8
FeMo3.5 B	0.3-4.4	72-81/62-82/0.9-2.8/0-0.3	Mo: 0-11/0-27/0/0
304-TiC B	0-1	80-82/69-79/0.8-2/0-0.5	Cr: 0-2/1-4/13-18/17-20 Ni: 0/0/8.9-9.6/8.4-9.2
Fe-TiC Mo B	0-2.7	63-82/63-71/1.1-2.1/0-0.7	Mo: 0-12.1/0-12/0/0-0.6
304-TiC Mo B	0-1.4	38-76/54-73/0.8-2/0-0.4	Cr: 0-1.4/1-3.4/17-19/17-25 Ni: 0/0/7.6-8.8/8.3-10.2 Mo: 0-36/4.6-12.6/0/0

The TiC found in the samples existed with different Ti and C contents. Also, the partly dissolved TiC and TiC Mo substrates had varying Ti and C contents. Some Fe and also Cr had dissolved into the substrates and into the TiC particles found in the metal droplet. In experiments including Cr, a lot of (Cr,Fe)C_x carbides and some sigma phase were found in the alloy droplet and in the penetration zone as well. Ni was not found in the substrate or TiC particles at all. In many cases, some dissolved Ti was found in the alloy. The Ti content was lower in the alloy droplet than in the alloy phase at the interface. The carbon content in the alloy was discussed in Publications III and IV. However, carbon analysis by SEM-EDS is unreliable. Nevertheless, dissolution of TiC in the alloy resulted in dissolved C in the alloy as well.

Molybdenum was not present in the alloy at all (Table 11). Instead, it was found only in the TiC particles both in the substrate and in TiC particles on the droplet side. The Mo content in the TiC varied a lot and the (Ti,Mo)C particles found in the experiments were very diverse. Figure 27 represents the (Ti,Mo)C particles found at the interface.

Figure 27. SEM-BSE of TiC particles at interface in experiment 304-TiC Mo B.

In the lower left corner a particle with a lighter rim can be observed (1 in Fig. 27). The Mo-rich parts appear lighter in the substrate particles and in the TiC particles found on the alloy side. In most of the (Ti,Mo)C particles the lighter phases are randomly distributed (2 in Fig. 27). Experiments including Mo and the (Ti,Mo)C particles were first discussed in Publication IV. Some particles with a lighter rim and some with a darker rim were found in experiment (13) FeMo_{3.5} B and in experiments with TiC Mo. However, most of the particles were more of the random type with lighter parts in them. Lighter rim particles were mostly found in the type A experiments, because the FeMo alloy had more time to react with TiC. The darker rim indicates a lower Mo content on the surface of the particle. Due to the small size of the rim, it could not be analysed precisely in this study. In the TiC Mo experiments, the Mo content of the TiC particles was lower than in the FeMo_{3.5} B experiments, but the number of Mo-containing TiC particles on the alloy droplet side was higher. In the 304-TiC Mo B experiment, some Cr and Fe were found in the substrate and in the (Ti,Mo)C particles. Ni was found in the alloy only.

TiC particle types

Besides the substrate, three different types of particles could be found in the systems (Fig. 28): small and more spherical, bigger and more angular, and very thin, longish particles (Fig. 28). All types were found in each experiment but in different amounts. Type A experiments were quite similar when it comes to the amounts of the different types. The type A experiments contained a lot of big, angular particles. The type B experiments were different, and they contained only a few big particles. Fe-TiC B had a lot of small spherical particles but almost no thin and longish particles. FeCr₂₃ B had mostly spherical and some thin and

longish particles. FeNi9 B had a lot of thin and longish particles. Of type B experiments, FeCr23 B had the highest number of big particles. The overall density of all kinds of particles was lower in the type B experiments. The experiments where Mo was involved had a large amount of spherical and longish particles.

Figure 28. Examples of different particle types found in the alloy droplet in the TiC wetting experiments (Publication IV).

5. Discussion

5.1 Thermodynamic calculations and experimental results

Thermodynamic calculations from the system equilibria in low-alloyed steel help to understand the experimental results of Ti/TiO₂ addition. The differences can be explained by local conditions and kinetics. Titanium oxide dominant inclusions seem to be more stable rather than Al₂O₃, which was highlighted by the thermodynamic calculations. The inclusion distribution (especially in relation to the low Al content in the TiO_x inclusions in Figs. 8 and 9) in experiments 3-7 deviates from the predominance diagram (Fig. 2). After the addition of the TiO₂, the local titanium concentration in the melt is higher and the local equilibrium is in the predominance area of Ti₃O₅ or even of Ti₂O₃. There was not enough time available to reach the equilibrium inclusion composition, because the TiO₂ was added sufficiently late (Publication I). In experiments with only the addition of metallic Ti, the equilibrium inclusion composition was more readily achievable, resulting in higher Al content in the TiO_x inclusions. Similar phenomena have been observed in several studies immediately after Ti addition when the local Ti content was very high compared to Al (Wang *et al.*, 2009/1; Pande *et al.*, 2013). It has been concluded that the TiO_x-containing inclusions would be formed as a result of the reduction of existing Al₂O₃ inclusions in Al-deoxidized steel with subsequent Ti addition. No increase in the number of inclusions after Ti addition was observed, which suggested that no new TiO_x inclusions were formed (Wang *et al.*, 2009/1). Ti and/or TiO₂ should be added as late as possible to prevent the re-formation of Al₂O₃. The greater amount of Al-containing TiO_x inclusions in the ingot samples indicated a partial transformation of TiO_x inclusions to Al-containing TiO_x inclusions over time after the addition of TiO₂.

On the basis of the thermodynamic calculations (Fig. 3-4) and the experimental results, the TiO₂ is first reduced to Ti₃O₅ in the melt, then later, during solidification, converted to Ti₂O₃. These spontaneous reactions release free oxygen, which then further reacts with the titanium. Later these inclusions and the free oxygen most likely react with manganese, resulting in a higher number of TiO_x+MnO inclusions, as observed in experiments 3-7. The addition of TiO₂ results in more Mn-containing TiO_x inclusions. During cooling at lower temperatures (below 1350-1200°C depending on the Ti content), Ti₂O₃ tends to transform partly to Al₂O₃ as predicted in Figs. 3 and 4. However, as a result of the low Al of the inclusions this happens only on a small scale due to slow kinetics. Many

of the inclusions in ingot samples, however, contain small amounts of Al (Publication I). The slower cooling rate of the ingot samples gave more time for the transformation to Al_2O_3 , as shown in Fig. 3. Ingot samples from experiments 4 had more Al-containing TiO_x inclusions and a higher Al content than the other TiO_2 experiments (Ti/Al ratio in TiO_x inclusions in the ingot sample, Table 8). This could be explained by the fact that experiment 4 had the lowest Ti/Al ratio of ≈ 7 . In addition, experiment 4 had by far the longest time between addition of Ti and casting, which might have given the Al more time to react with the TiO_x inclusions. Experiment 4 was the only experiment with a prolonged time between the addition of Ti and casting. The rest of the experiments had somewhat similar timings. Even though the Ti/Al ratios were too low in all of the experiments, the late addition of TiO_2 ensured that the inclusions were TiO_x rich. The Ti/Al ratios of the steel were not consistent with the Ti/Al ratios of the inclusions due to the late addition and kinetics, which has been observed in another study (Li *et al.*, 2018).

Based on the thermodynamic calculations, a liquid oxide would be present in the melt at higher temperatures. This is supported by the inclusion studies from the experimental part as well as by earlier studies (Ruby-Meyer *et al.*, 2000; Jung *et al.*, 2009). In particular, Figure 14 and Figure 15 represent spherical inclusions, whose shape evidently originated from the liquid state. The compositions of the inclusion, especially the Al contents, differ from the slag composition in the thermodynamic calculations in this case also. The Al content is clearly lower, which could be due to local conditions as well. According to more recent studies (Kang and Lee, 2017; Kang and Jung, 2018) the liquid phase should be less stable in the experimental conditions of this thesis. Manganese was included in most of the thermodynamic calculations. Based on the results manganese is expanding the liquid oxide (slag) region.

The thermodynamic calculations of TiC formation in a stainless steel system were in line with the results from the wetting experiments. Nickel does not react with carbides. On the other hand, chromium and molybdenum form carbides and react with the existing titanium carbides.

5.2 Behaviour of manganese after TiO_2 additions

The smaller amount of Mn-containing inclusions and the lower Mn/S ratio in experiments 1 and 2 indicate that the addition of Ti leads to TiO_x inclusions with less Ti-Mn oxides. Based on the difference between the inclusion types in experiments with Ti addition compared to the experiments with Ti+ TiO_2 addition, it can be concluded that many of the TiO_x inclusions originated from the addition of TiO_2 . The Mn content in the inclusions was much higher than indicated by the thermodynamic calculations (Holappa and Kiviö, 2012), which is most likely due to Mn reacting strongly with existing TiO_x inclusions during cooling. Based on the thermodynamic studies and SEM-EBSD study, the TiO_x inclusions can be shown to be Ti_2O_3 . This is supported by other studies in which the final inclusion type in similar conditions was Ti_2O_3 with Mn (Byun *et al.*, 2003; Mu *et al.*, 2014; Mu *et al.*, 2016).

Ti_2O_3 was found in the SEM-WDS studies of the TiO_2 -Fe/steel wetting experiment samples. These results suggest a reduction of the TiO_2 substrate to Ti_2O_3 at the interface. A similar observation about the reduction has been made in another study on Fe- TiO_2 wetting (Xuan, 2016/1). The results of inclusion studies from the experiments with addition of TiO_2 as well as the results of the steel- TiO_2 wetting experiments suggest a strong reaction between Ti_2O_3 and manganese. It is clear from these wetting experiments as well that Ti_2O_3 strongly interacts with the Mn from the surrounding matrix. Several other studies listed in the background described in chapter 2 have already presented similar results. Additionally, the transformation of Ti_3O_5 to Ti_2O_3 has been reported to enhance Mn absorption from the steel matrix (Kang and Lee, 2010). The findings from the inclusion study of industrial samples also indicated that inclusions richer in TiO_x have a higher Mn content (Holappa and Kiviö, 2012). No other reaction products besides the Mn absorption and reduction of TiO_2 were observed in the wetting experiments.

5.3 Wetting experiments with TiC

In order to have good bonding between the reinforcement particles and the substrate, good wettability is necessary. Good wetting results in good bonding between the reinforcement particles and the metal and in the desired distribution of particles. The contact angles measured in the TiC systems of this study were low indicating good wetting. Both the initial and the minimum contact angles measured are important. In this case, the initial contact angles were low in almost all of the experiments. Even in the experiments with somewhat higher initial contact angles the value dropped very quickly, and the minimum contact angle was low. Alloying did not have any significant effect on the wetting and the wetting behaviour was quite similar between type A and type B experiments. Mo and Ni alloying improved the wetting somewhat in type A experiments, whereas in type B experiments the effect of alloying elements was very small. The contact angle was decreased slightly by using a TiCMo substrate instead of TiC. Cr alloying did not affect the wetting significantly in type A experiments. In the type B experiments Cr alloying increased the contact angle somewhat. It should be noted that the solidification of the droplet surface was strong in the FeCr23 B. The experiments with stainless steel 304 showed similar contact angles as those with pure iron. The 304 had a low Mo content, but similar Ni and Cr contents as the alloys used in the other wetting experiments. It is likely that the Cr and Ni counteract the effects of each other. In almost all the wetting experiments the surface of the droplet solidified towards the end of the holding time and the surface became rough. This could be explained by the formation and transportation of TiC particles to the surface. Similar phenomena have been reported in another study as well (Liu and Fredriksson, 1997).

The repeatability of the contact angles in the experiments was very good and the results are consistent with each other, especially among the different types of alloys used. Previous studies regarding the wetting between Fe/Fe-alloys and TiC have been somewhat inconsistent (Naidich, 1981; Panasyuk *et al.*, 1981;

Panasyuk and Umanskii, 1987; Kiparisov *et al.*, 1976; Kiparisov *et al.*, 1979; Samsonov *et al.*, 1972/2). Complete wetting (contact angle 0°) between TiC and NiMo melt has been reported (Hussainova, 2003). In contrast, the current thesis provides consistent and comprehensive results for the contact angles between Fe/Fe-alloys and TiC (and TiCMo), especially regarding alloying elements in stainless steel. The differences regarding wetting between type A and B experiments can be explained by the different experimental setup and the reactions during heating.

In type A wetting experiments, the TiC substrate dissolved strongly into the metal already during heating. In general, dissolution of Ti and C results in good wetting (Parashivamurthy *et al.*, 2008). The low Ti content of the metal indicates a very strong formation of carbides, especially during cooling. The experiments with FeNi showed the strongest penetration of the melt into the substrate, the strongest dissolution of the substrate and strongest TiC appearance/formation on the droplet side, and also the lowest contact angles. Similar observations have been made in an earlier study (Samsonov *et al.*, 1972/2). The sudden drop in the initial contact angle values in the FeNi experiments is the result of fast and strong reactions between the melt and the substrate. However, dissolution of the substrate into the metal droplet and infiltration and dissolution of the melt into the substrate were observed in all experiments. The experiments with 304 had strong penetration of the melt into the substrate as well. Most likely because the 304 had a similar nickel content. 304 was followed by FeCr and FeMo. Based on the results the penetration of the melt was somewhat stronger into the TiC than into the TiCMo substrate. In general, the alloying of the melt improves the penetration compared to pure Fe. The penetration depths were greater in experiments with longer holding times, but otherwise the dissolution of the substrate was very fast and quite strong carbide formation was observed on the droplet side in all experiments.

5.4 Formation of carbides

The Fe-TiC (experiments 8-10) and Fe-TiCMo (experiments 15 and 16) experiments were performed with varied holding times to observe the dissolution of the substrate. The penetration depths were smaller in the experiments with shorter holding times. Nevertheless, the extent of TiC formation on the droplet side was very similar, regardless of the holding time. These observations mean that the dissolution of the substrate was quite vigorous, resulting in strong carbide formation on the droplet side as well.

Different types and shapes of particles were found in the samples from the TiC wetting experiments. Moreover, the origins and formation mechanisms of the particles were different. The TiC on the droplet side formed partly as a result of drifting from the substrate and partly from the dissolved Ti and C in the melt. Carbides can form on existing particles or as new particles (Terry and Chinyamakobvu, 1992/1; Terry and Chinyamakobvu, 1992/2). The number of larger particles was clearly higher in type A experiments. Due to the different setup, there was more time for substrate particles to drift to the alloy droplet

side. Based on the shape and size of the large angular particles on the droplet size, the particles had detached from the substrate surface. Some of the larger and angular particles might have been proeutectic TiC formed above 1500°C (Dogan *et al.*, 2006), instead of drifted substrate particles. The TiC particles formed earlier had angular shapes and the TiC particles formed later were more spherical (Parashivamurthy *et al.*, 2008). According to an earlier study (Dogan *et al.*, 2006), eutectic TiC is formed around 1400°C, which explains the high number of the longish eutectic TiC even in the type B wetting experiments. The presence of the longish type TiC is not desirable (Liu and Fredriksson, 1997). The higher the cooling rate, the thinner and longer the TiC particles are, leading to fine TiC particles at high cooling rates (Dogan *et al.*, 2006). The cooling rate has an effect on TiC particle types as well. An increased cooling rate results in smaller and finer particles (Dogan *et al.*, 2006), which can be observed in the type B experiments with higher cooling rates which had more particles that were small and spherical, as well as longer TiC particles.

The large angular particles are probably the first to appear. Proeutectic ferrite might also partly explain the solidified surface. Experiment 9 (Fe-TiC B) had the highest dissolved Ti content as well as the highest number of small spherical TiC particles in the metal phase. High supersaturation could lead to a large number of spherical TiC particles (Liu and Fredriksson, 1997). Great amounts of dissolved Ti and C have been found to lead to good dispersion of TiC in the melt (Parashivamurthy *et al.*, 2009; Terry and Chinyamakobvu, 1992/2). Experiment FeNi9 B had the highest number of longish eutectic and small spherical TiC particles, which could be related to the phenomenon of Ni acting as a diluent, preventing carbon diffusion and the growth of TiC (Jiang *et al.*, 2005). Based on another study, addition of Ni could lead to a shape change of the TiC from angular to spherical (Jie-Cai *et al.*, 2000), which could explain the low number of large angular TiC particles in the metal.

In the Mo-containing systems, additional particle types can be found: pure TiC, TiC with a lighter rim rich in Mo, TiC with a darker rim depleted in Mo and (Ti,Mo)C particles with randomly distributed lighter phases. These types existed in all the different shapes listed in the previous section. The Ti and Mo contents in the particles were very diverse. The small spherical particles and longish particles in the Mo-containing systems were formed during solidification directly from the eutectic melt and partly by Mo reacting with existing TiC particles. Molybdenum reacted very strongly with the melt and particles because, based on the analyses, the alloy did not contain dissolved Mo. It seems that molybdenum partly replaced titanium in the TiC particles.

Experiments with the FeMo alloy contained a great number of lighter rim particles. In contrast, experiments with TiCMo had only a few lighter rim particles. In particular, the TiC substrate particles at the interface had a lighter rim, although some particles were also found in the alloy droplet. It is most likely that molybdenum from the FeMo melt had reacted with the existing particles (especially the substrate), resulting in the lighter rim particles. This is in accordance with other studies (Qian and Lim, 1999; Andrén *et al.*, 1994). The formation of TiC particles with Cr, Mo and Fe in TiC-reinforced steel has been

reported to occur due to the melt surrounding the TiC becoming poorer in Ti and thus resulting in a lighter rim phase enriched in Cr, Mo and Fe (Bourithis *et al.*, 2003). The type A experiments with FeMo had plenty of lighter rim particles and the type B experiments less. This suggests that some of the reactions took place already during heating, but most likely the lighter rim particles were formed during solidification as the cooling rate was slower in the type A experiments.

Experiments with the TiCMo substrate had a higher number of small and homogeneous (Ti,Mo)C particles and TiC particles with randomly distributed lighter Mo-rich phases. Some of the TiC particles with random lighter phases most likely originated from the TiCMo substrate. The more homogeneous (Ti,Mo)C particles were usually the small spherical or longish type. Particles with a darker rim were observed in all Mo-containing experiments. The darker rim indicates Mo depletion compared to the lighter core phase. However, the thin rim could not be analysed precisely.

In general, the alloying elements affect the appearance of new phases in the TiC-Fe systems. If molybdenum is present in the system, it seems to react very strongly with TiC particles. All of the Mo reacts with the TiC or (Ti,Mo)C particles, resulting in the absence of Mo in the alloy phase. In contrast, if chromium is present in the system, small amounts of Cr can be found in most of the TiC and/or (Ti,Mo)C particles. Chromium also forms (Cr,Fe)C_x carbides, which can be detrimental to the properties of the materials. Chromium carbides were found in the penetration zone and in the vicinity of the TiC on the droplet side. The experiments with FeNi alloys did not contain any other phases besides TiC and FeNi, which means that no other reaction products were formed. Even the TiC particles or the substrate did not contain any Ni, which means that no nickel had dissolved into the TiC.

The addition of titanium to stainless steel (stabilization) is a well-known practice to bond the carbon and prevent the formation of chromium carbides. In addition to the formation of titanium carbides, the formation of molybdenum carbides also reduces the formation of chromium carbides (Kuzucu *et al.*, 1998; Pardo *et al.*, 2007). Mo replaces Cr in the TiC and stabilizes the TiC in stainless steel (Pardo *et al.*, 2007). This was, however, not the case in this study due to the formation of TiC with a carbon deficit and due to leaving extra carbon in the stainless steel. Based on a previous study (Jang *et al.*, 2012), the carbon in the (Ti,Mo)C is partly replaced by vacancies resulting in an increased carbon content of the metal, which might be the cause of the high carbon content of the metal in this study. In addition, in Mo-containing stainless steels the passivity of the material might be reduced as a result of the Mo depletion due to the formation of (Ti,Mo)C. The TiC particles contained a lot of Cr because the dissolution of Cr into TiC is very strong at high temperatures (Booker *et al.*, 1997). The formation of a Fe,Cr-rich layer on the surface of the TiC particle has been found to improve the bonding between the particles and the metal (Pagounis and Lindroos, 1998). The formation of a more metallic layer could also improve wetting (Eustathopoulos and Coudurier, 1992). In the casting experiments related to this thesis (Tiusanen *et al.*, 2009) strong chromium

carbide formation was observed around the TiC particles formed. This was most probably due to the same phenomena observed in this thesis: the carbon content in the vicinity of the TiC particle is decreased due to the formation of TiC with a carbon deficiency. The excess carbon in the metal around the particles reacts with the chromium from the stainless steel, leading to the formation of the detrimental chromium carbides.

The differences regarding wetting and TiC particle types between the type A and B experiments can be explained by the different experimental setup and the reactions during heating in type A experiments. The similar outcome in type A experiments concerning the shape of the particles is most likely the result of the long interaction time between the substrate and the alloys: reactions during heating, the longer holding period and the smaller cooling rate. Conversely, type B experiments had fewer particles in general. The main differences between type A and B experiments are the deeper penetration zone, stronger dissolution and transportation of substrate particles and the higher particle density in type A experiments. Type B experiments resemble the real casting process more.

6. Conclusions

The interfacial phenomena between Ti-containing oxide and carbide particles and liquid steel were the focus of this thesis. The results are useful in developing production processes for steels with improved mechanical properties by means of functional particles. The aim was to obtain information about the inclusions resulting from the addition of Ti and TiO_2 into liquid steel and wetting, and the reactions between the Ti/ TiO_2 and steel. Another aim was to gain information about wetting and particle dissolution and formation during and after addition of TiC into liquid iron-based alloys or stainless steel. More detailed conclusions of the objectives of this thesis are presented in the following paragraphs.

The formation of titanium-containing inclusions after the addition of Ti/ TiO_2 is complex. According to thermodynamic calculations and experimental studies, a low Al content ($\leq 50\text{ppm}$) promotes the occurrence of TiO_x -dominant inclusions. Even if the Ti/Al ratio is low, the local equilibrium moves towards the Ti_3O_5 predominance area promoting TiO_x -dominant inclusions when TiO_2 particles are added into the steel melt. Even liquid oxide inclusions seem to exist to some extent. If the additions are made late enough there is not enough time for conversion to Al_2O_3 -dominant inclusions. TiO_2 is reduced to Ti_3O_5 in the melt and later during solidification to Ti_2O_3 . During solidification the Ti_2O_3 inclusions react with Mn, Al and/or S, leading to complex Ti_2O_3 -rich inclusions with one or several of the following components: Al_2O_3 , MnTiO_x , AlTiO_x , MnS and TiN. The contents of the other components in the TiO_x inclusions remain much lower, with titanium oxide being the main component. Addition of TiO_2 into liquid steel increases the amount of titanium oxide dominant inclusions, leads to more $\text{Ti}_2\text{O}_3+\text{MnO}$ inclusions and decreases their size. Late addition of TiO_2 during casting further promotes these phenomena. The results of the TiO_2 wetting experiments supported the findings from the addition of TiO_2 , i.e. the Mn in steel strongly reacts with the existing titanium oxide.

The wettability between TiC and different Fe alloys and stainless steel was good. The effect of alloying elements on wettability was minor and mostly positive. Good wettability between the reinforcement particles and the metal should ensure good bonding and a good distribution of the reinforcement particles in the melt. The difference between the two types of wetting experiments was due to the reactions between the substrate and metal during heating. This resulted in improved wetting by Ni and Mo alloying of the Fe.

The good wettability was most probably ensured by the high reactivity of the interface, especially the dissolution of the TiC into the melt. However, as a

result of the dissolution and subsequent precipitation, the TiC formation was very complex with different shapes and compositions. The TiC existed with various Ti/C ratios and the presence of other elements like Fe, Cr and Mo were either as dissolved or separate phases. TiC was found to have precipitated with carbon deficiency, which means that the use of a stoichiometric TiC as reinforcement material may lead to too high a carbon content in the metal, which is especially detrimental to stainless steel such as 304.

Nickel seemed to increase the dissolution of the TiC at the interface. The presence of nickel did not create any new reaction products at the interface. However, due to the increased dissolution of the substrate, the amount of film-like eutectic TiC was higher, which is undesirable in composite materials.

The presence of Cr seemed to promote the formation of spherical TiC. In addition, Cr also dissolved into TiC which means that bonding should be improved due to the mutual dissolution. The mutual dissolution of the melt and substrate into each other should result in strong bonding between the metal and the reinforcement particles. This would be most advantageous without the formation of any new detrimental phases or reaction products.

Molybdenum strongly affected the TiC particles formed in the steel. It created particles with core-rim structures, homogeneous (Ti,Mo)C particles and TiC particles with randomly distributed Mo-rich phases. A long reaction time between the alloy and the substrate resulted in more core-rim particles. Mo reacted very strongly in the systems, because no dissolved Mo was found in the alloy phase.

Titanium-containing inclusions can exist in different sizes and shapes and with complex chemistries and multiple phases. Minor changes in the production process can change their appearance drastically. Some of these types are desirable in order to obtain improved mechanical properties while some are considered more harmful. The complexity of Ti-containing particles should be taken into account when utilizing Ti-containing particles to obtain desired mechanical properties and microstructures in steel.

6.1 Further Studies

The results of this thesis formed an important part of the research projects described in chapter 1.1. The research project “Grain size control in steel by means of dispersed non-metallic inclusions (GRAINCONT)” was continued with a slightly different approach in “Nanoparticle addition into molten steel (NAMOS)” (Lintunen et al., 2017). In the light of the results and conclusions of this thesis and all the previous work done in other studies, the utilization of titanium oxide inclusions in steel has great potential for use in industrial steelmaking on a larger scale. It is very likely that it is already being used in certain applications. For example, TiC and other types of particles are used in matrix materials as reinforcement particles. However, adding TiC or Ti+C directly into molten material during casting needs a significant amount of research to minimize or avoid detrimental effects. Nevertheless, the results of this thesis give a profound understanding of the phenomena, which is necessary for

the design and control of the steel manufacturing process (Kiviö et al., 2016). Some research topics are suggested in the following paragraphs.

Titanium-containing particles should be studied in more detail to determine the different phases that exist in the inclusions: which types of particles are better at acting as nucleation sites and pinning the grain boundaries: complex particles or the more homogeneous $(\text{Ti,Mn})_2\text{O}_3$? The same question goes for carbide particles. Which particles are better as reinforcement particles: the more complex core-rim particles or the more homogeneous $(\text{Ti,Mo})\text{C}$ particles?

The addition of TiO_2 into liquid steel could be studied with a different type of low-alloyed steel, with particular attention being paid to the Mn and S contents in order to make the acicular ferrite form on a larger scale.

In addition to the phases in the inclusions and the effect of the steel composition, the types of additives or inoculants and the ways of dispersing them in the melt should be studied. As depicted in Publication I the addition of TiO_2 containing inoculants is challenging.

The effect of Mo on the mechanical properties of TiC-reinforced stainless steel castings should be studied further. In addition, the reactions between TiC with carbon deficiency and Fe, FeCr alloy and stainless steel should be studied to verify whether the carbon deficiency in TiC could reduce the dissolution of carbon into the metal and the formation of chromium carbides. In general the stability of TiC in liquid steel in practical applications should be studied in more detail. As shown in this thesis the dissolution of TiC is very strong.

References

- Andersson, M., Janis, J., Holappa, L., Kiviö, M., Naveau, P., Brandt, M., Espinosa, D., Bellavia, L., Van den Eynde, X., de Courcy, E., Chapuis, L. and Iung, T. (2011). Grain size control in steel by means of dispersed non-metallic inclusions—GRAINCONT: Final Report, Publications Office of the European Union, Luxembourg, 2011
- Andrén, H. O., Rolander, U. and Lindahl, P. (1994). Atom-probe analysis of cemented carbides and cermets. *Applied Surface Science*, 76–77, pp. 278–284
- Andrén, H. O. (2001). Microstructures of cemented carbides. *Materials and Design*, 22, pp. 491–498
- Babu, S. S., David, S. A., Vitek, J. M., Mundra, K. and DebRoy, T. (1995): Development of macro- and microstructures of carbon–manganese low alloy steel welds: inclusion formation. *Materials Science and Technology*, 11(2), pp. 186–199
- Bale, C. W., Bélisle, E., Chartrand, P., Decterov, S. A., Eriksson, G., Gheribi, A. E., Hack, K., Jung, I. H., Kang, Y.-B., Melançon, J., Pelton, A. D., Petersen, S., Robelin, C., Sangster, J., Spencer, P. and VanEnde, M.-A. (2016): FactSage thermochemical software and databases, 2010–2016. *Calphad: Computer Coupling of Phase Diagrams and Thermochemistry*, 54, pp. 35–53
- Bhadeshia, H.K.D.H. (2001): Bainite in steels. pp. 237–76 (Institute of Materials: Minerals and Mining, London, UK)
- Booker, P. H., Kunrath, A. O. and Hepworth, M. T. (1997). Experimental determination of the ternary diagram of the Ti–Cr–C system. *Acta Materialia*, 45(4), pp. 1625–1632
- Bourithis, L., Milonas, A. and Papadimitriou, A. D. (2003). Plasma transferred arc surface alloying of a construction steel to produce a metal matrix composite tool steel with TiC as reinforcing particles. *Surface and Coatings Technology*, 165, pp. 286–295
- Bramfitt, B. L. (1970): The effect of carbide and nitride additions on the heterogeneous nucleation behaviour of liquid iron. *Metallurgical Transactions*, 1, pp. 1987–1995
- Byun, J. S., Shim, J.-D., Cho, Y.W. and Lee, D. N. (2003): Non-metallic inclusion and intragranular nucleation of ferrite in Ti-killed C–Mn steel. *Acta Materialia*, 51, pp. 1593–1606
- Cardinal, S., Malchere, A., Garnier, V. and Fantozzi, G. (2009). Microstructure and mechanical properties of TiC–TiN based cermets for tools application. *International Journal of Refractory Metals and Hard Materials*, 27, pp. 521–527
- Chambers, B.V., Kattamis, T.Z., Cornie, J.A. and Flemings, M.C. (1987), Solidification behaviour of particulate TiC–ferrous matrix composites. *Proceedings of 3rd International conference on Solidification Processing*, Sheffield, UK, pp. 435–438
- Chen, L., Lengauer, W., Ettmayer, P., Dreyer, K., Daub, H. W. and Kassel, D. (2000). Fundamentals of liquid phase sintering for modern cermets and functionally graded cemented carbonitrides (FGCC). *International Journal of Refractory Metals and Hard Materials*, 18, pp. 307–322

- Chen, C. Y., Yen, H. W., Kao, F. H., Li, W. C., Huang, C. Y., Yang, J. R. and Wang, S. H. (2009). Precipitation hardening of high-strength low-alloy steels by nanometer-sized carbides. *Materials Science and Engineering A*, 499(1-2), pp. 162–166
- Cutard, T., Viatte, T., Feusier, G. and Benoit, W. (1996). Microstructure and high temperature mechanical properties of $\text{TiC}_{0.7}\text{N}_{0.3}$ - Mo_2C - Ni cermets. *Materials Science and Engineering A*, 209, pp. 218–227
- Degnan, C.C. and Shipway, P.H. (2002). A comparison of the reciprocating sliding wear behaviour of steel based metal matrix composites processed from self-propagating high-temperature synthesised Fe–TiC and Fe–TiB₂ master alloys. *Wear*, 252 (9-10), pp. 832–841
- Delannay, F., Froyen, L., and Deruyttere, A. (1987). The wetting of solids by molten metals and its relation to the preparation of metal-matrix composites. *Journal of Materials Science*, 22, pp. 1-16
- Dogan, Ö.N., Hawk, J.A. and Schrems, K.K. (2006). TiC-reinforced cast Cr steels. *Journal of Materials Engineering and Performance*, 15 (3), pp. 320–327
- Erauskin, J. I., Sargyan, A. and Arana, J. L. (2009). Reinforcement of austenitic manganese steel with (TiMo) carbide particles previously synthesized by SHS. *ISIJ International*, 49(4), pp. 582–586
- Eustathopoulos, N., Chatain, D. and Coudurier, L. (1991). Wetting and interfacial chemistry in liquid metal-ceramic systems. *Materials Science and Engineering A*, 135, pp. 83–88
- Eustathopoulos, N. and Coudurier, L. (1992). Influence of alloying elements on wettability and adhesion energy in liquid metal-ceramic systems. *Journal of Adhesion Science and Technology*, 6(9), pp. 1011–1022
- Funakawa, Y., Shiozaki, T., Tomita, K., Yamamoto, T. and Maeda, E. (2004). Development of high strength hot-rolled sheet steel consisting of ferrite and nanometer-sized carbides. *ISIJ International*, 44(11), pp. 1945–1951
- Gregg, J.M. and Bhadeshia, H.K.D.H. (1997): Solid-state nucleation of acicular ferrite on minerals added to molten steel. *Acta Materialia*, 45, pp. 739–748
- Grong, Ø., Kolbeisen, L., Van der Eijk, C. and Tranell, G. (2006). Microstructure Control of steels through dispersoid metallurgy using novel grain refining alloys. *ISIJ International*, 46, pp. 824–831
- Heikkinen, H. (2009). Wetting of titanium carbide and iron alloys. Master's Thesis (In Finnish), Helsinki University of Technology
- Holappa, L. and Kiviö, M. (2012). Fundamentals of titanium deoxidation. In P Scheller (ed.), *Proceedings of the 5th International Congress on the Science and Technology of Steelmaking, ICS 2012*. October 1-3, 2012, Dresden, Germany. CD-ROM, ENGICOM GmbH Germany, Dresden, Pages 9. <http://urn.fi/URN:NBN:fi:aalto-202002122107>.
- Hossein Nedjad, S. and Farzaneh, A. (2007): Formation of fine intragranular ferrite in cast plain carbon steel inoculated by titanium oxide nanopowder. *Scripta Materialia*, 57, pp. 937–940
- Hussainova, I. (2003). Effect of microstructure on the erosive wear of titanium carbide-based cermets. *Wear*, 255(1-6), pp. 121–128
- Jackson W. J. (1972): Control of the grain structure in austenitic steel castings. *Iron and Steel*, 45(2), pp. 163–172
- Jang, J. H., Lee, C.-H., Heo, Y.-U. and Suh, D.-W. (2012). Stability of (Ti,M)C (M = Nb, V, Mo and W) carbide in steels using first-principles calculations. *Acta Materialia*, 60, pp. 208–217
- Jiang, M., Wang, X.H., Hu, Z.Y., Wang, K.P., Yang, C.W. and Li, S.R. (2015) Microstructure refinement and mechanical properties improvement by developing IAF on

- inclusions in Ti–Al complex deoxidized HSLA steel. *Materials Characterization*, 108, pp. 58–67
- Jiang, Q.C., Zhao, F., Wang, H.Y. and Zhang, Z.Q. (2005). In situ TiC-reinforced steel composite fabricated via self-propagating high-temperature synthesis of Ni–Ti–C system. *Materials Letters*, 59, pp. 2043–2047
- Jie-Cai, H., Zhang, X.-H. and Wood, J. V. (2000). In-situ combustion synthesis and densification of TiC–xNi cermets. *Materials Science and Engineering A*, 280, pp. 328–333
- Jin, H.-H., Shim, J.-H., Cho, Y. W. and Lee, H.-G. (2003): Formation of intragranular acicular ferrite grains in a Ti-containing low carbon steel. *ISIJ International*, 43, pp. 1111–11213
- Jung, I.-H., Eriksson, G., Wu, P. and Pelton, A. (2009). Thermodynamic modeling of the Al_2O_3 – Ti_2O_3 – TiO_2 system and its applications to the Fe–Al–Ti–O inclusion diagram. *ISIJ International*, 49 (9), pp. 1290–1297
- Kang, Y.-B. and Lee, H.-G. (2005/1). Experimental study of phase equilibria in the MnO– TiO_2 – Ti_2O_3 system. *ISIJ International*, 45 (1), pp. 1543–1551
- Kang, Y.-B. and Lee, H.-G. (2005/2). Experimental study of phase equilibria in the MnO– SiO_2 – TiO_2 – Ti_2O_3 system. *ISIJ International*, 45 (1), pp. 1552–156
- Kang, Y.-B. and Lee, H.-G. (2010). Thermodynamic analysis of Mn-depleted zone near Ti oxide inclusions for intragranular nucleation of ferrite in steel. *ISIJ International*, 50 (4), pp. 501–508
- Kang, Y.-B. and Lee, J.-H. (2017). Reassessment of oxide stability diagram in the Fe–Ti–Al–O system. *ISIJ International*, 57 (9), pp. 1665–1667
- Kang, Y.-B. and Jung, S.-H.. (2018). Oxide stability diagram of liquid steels – construction and utilization. *ISIJ International*, 58 (8), pp. 1371–1382
- Kikuchi, N., Nabeshima, S., Yamashita, T., Kishimoto, Y., Sridhar, S. and Nagasaka, T. (2011). Micro-structure refinement in low carbon high manganese steels through Ti-deoxidation, characterization and effect of secondary deoxidation particles. *ISIJ International*, 51 (12), pp. 2019–2028
- Kiparisov, S.S., Narva, V. K., Loshkareva, N. S. and Ivanov, A. D. (1976). Sintering of titanium-carbide-steel materials in various environments. *Powder Metallurgy and Metal Ceramics*, 15(8), pp. 618–621
- Kiparisov, S.S., Narva V. K., Shanaeva, D. A. and Shumenko, V. N. (1979). An experiment-planning investigation of the wetting of titanium carbide by Kh4N2M8 steel alloyed with manganese. *Powder Metallurgy and Metal Ceramics*, 18(5), pp. 322–325
- Kiviö, M., Holappa, L., Nakamoto, M. and Tanaka, T. (2016). Studies on interfacial phenomena in titanium carbide/liquid steel systems for development of functionally graded material. *Metallurgical and Materials Transactions B*, vol 47B, pp. 2114–2122
- Kuzucu, V., Aksoy, M. and Korkut, M. H. (1998). The effect of strong carbide-forming elements such as Mo, Ti, V and Nb on the microstructure of ferritic stainless steel. *Journal of Materials Processing Technology*, 82(1–3), pp. 165–171
- Lagerbom, J., Lintunen, P., Ritvonen, T., Turunen, E., Kiviö, M., Väyrynen, P., Niittynen, L., Heikkinen, H., Rauta, V., Cingi, C., Niini, E., Holappa, L., Louhenkilpi, S., Orkas, J., Oksanen, V., Niemi, M., Tiisanen, J., Rissa, K., Keskiäho, K., Itävuori, E., Tiainen, T., and Lepistö, T. (2010). Valujen sula-lujiterajapintojen ymmärtäminen ja hallittujen FG-rakenteiden kehittäminen SULA-TAJU (in Finnish). VTT-Research Report, <http://www.vtt.fi/inf/julkaisut/muut/2010/VTT-R-08817-10.pdf>

- Lee, T.-K., Kim, H.J., Kang, B.Y. and Hwang, S.K. (2000). Effect of inclusion size on the nucleation of acicular ferrite in welds. *ISIJ International*, 40(12), pp. 1260–1268.
- Li, M., Matsuura, H. and Tsukihashi, F. (2018). Investigation on the formation mechanism of Ti-bearing nonmetallic inclusions in Fe-Al-Ti-O-N alloy by inductive separation method. *Materials Characterization*, 136, pp. 358–366
- Lintunen, P., Idoyaga, Z., Callejo, L.M., Nakajima, K., Kytönen, H., Ekerot, S. and García-Mateo, C. (2017). Nanoparticle addition into molten steel (NAMOS). Final report – Study, European Commission, Research Fund for Coal and Steel, 2017
- Liu, N., Chao, S. and Huang, X. (2006). Effects of TiC/TiN addition on the microstructure and mechanical properties of ultra-fine grade Ti (C, N)–Ni cermets. *Journal of the European Ceramic Society*, 26, pp. 3861–3870
- Liu, Z. and Fredriksson, H. (1997). On the precipitation of TiC in liquid iron by reactions between different phases. *Metallurgical and Materials Transactions A*, 28A, pp. 471–483
- Loder, D., Michelis, S.K., Mayerhofer, A. and Bernhard, C (2016). On the capability of nonmetallic inclusions to act as nuclei for acicular ferrite in different steel grades. *Metallurgical and Materials Transactions B*, 48B, pp. 1992–2006
- Lou D. and L. Holappa, L. (2001): Microstructure and property control of steels with inclusions. SINTEF Materials Technology publications, Trondheim, Norway.
- Mari, D., Bolognini, S., Feusier, G., Cutard, T., Verdon, C., Viatte, T. and Benoit, W. (2003). TiMoCN based cermets: Part I. Morphology and phase composition. *International Journal of Refractory Metals and Hard Materials*, 21(1-2), pp. 37–46
- Matsuura, H., Wang, C., Wen, G. and Sridhar, S. (2007). The transient stages of inclusion evolution during Al and/or Ti additions to molten iron. *ISIJ International*, 47(9), pp. 1265–1274
- Mu, W., Shibata, H., Hedström, P., Jönsson, P. and Nakajima, K. (2016). Ferrite formation dynamics and microstructure due to inclusion engineering in low-alloy steels by Ti_2O_3 and TiN addition. *Metallurgical and Materials Transactions B*, 47B, pp. 2133–2147
- Mu, W., Jönsson, P. and Nakajima, K. (2014). Effect of sulfur content on inclusion and microstructure characteristics in steels with Ti_2O_3 and TiO_2 additions. *ISIJ International*, 54(12), pp. 2907–2916
- Mutale, C.-T., Tuling, A.S. and Verry, S.M.C. (2004). TEM study of solid titanium oxides inclusions in steel melt at 1600°C. VIII International Conference on Molten slags, fluxes and salts, The South Africa Institute of Mining and Metallurgy, pp. 293–297.
- Naidich, Y.V. (1981). The wettability of solids by liquid metals. *Progress in Surface and Membrane Science*, 14, pp. 353–386
- Okamoto, H. (2006). C-Ti (Carbon-Titanium). *Journal of Phase Equilibria*, 27(3), pp. 306–307
- Pagounis, E. and Lindroos, V. K. (1998). Processing and particulate reinforced steel matrix composites. *Materials Science and Engineering A*, 246, pp. 221–234
- Pak, J.-J., Oh, J.-O., Kim, S.-I., Kim, W.-Y., Chung, T.-I., Seo, S.-M., Park, J.-H. and Kim, D.-S. (2007). Thermodynamics of titanium and oxygen dissolved in liquid iron equilibrated with titanium oxides. *ISIJ International*, 47 (1), pp. 16–24.
- Panasyuk, A. D. and Umanskii, A.P. (1987). Interaction of structural components of a composite material based on titanium carbide. *Powder Metallurgy and Metal Ceramics*, 26(2), pp. 167–169
- Panasyuk, A. D., Kyubarsepp, Y. P., Dzykovich, I. Y. and Val'dma, L. E. (1981). Contact reactions of titanium carbide with iron-base alloys. *Powder Metallurgy and Metal Ceramics*, 20(4), pp. 291–296

- Pande, M.M., Guo, M. and Blanpain, B. (2013). Inclusion formation and interfacial reactions between FeTi alloys and liquid steel at an early stage. *ISIJ International*, 53(4), pp. 629–638
- Parashivamurthy, K. I., Chandrasekharaiah, M. N. , Sampathkumaran, P. and Seetharamu, S. (2006). Casting of TiC-reinforced steel matrix composite. *Materials and Manufacturing Processes*, 21, pp. 473–478
- Parashivamurthy, K. I., Sampathkumaran, P. and Seetharamu, S. (2008). In-situ TiC precipitation in molten Fe-C and their characterization. *Crystal Research and Technology*, 43(6), pp. 674–678
- Pardo, A., Merino, M. C., Coy, A. E., Viejo, F., Carboneras, M. and Arrabal, R. (2007). Influence of Ti, C and N concentration on the intergranular corrosion behaviour of AISI 316Ti and 321 stainless steels. *Acta Materialia*, 55(7), pp. 2239–2251
- Park, D. S., Lee, Y. D., Jung, T. and Kang, S. (1999). Effect of Mo₂C content on the microstructure and properties of Ti(CN)-Mo₂C ceramics. *Korean Journal of Ceramics*, 5(3), pp. 230–234
- Qian, M. and Lim, L. C. (1999). On the disappearance of Mo₂C during low-temperature sintering of Ti(C,N)-Mo₂C-Ni cermets. *Journal of Materials Science*, 34, pp. 3677–3684
- Razavi, M., Yaghmaee, M. S., Rahimpour, M. R. and Razavi Tousi, S. S. (2010). The effect of production method on properties of Fe–TiC composite. *International Journal of Minerals Processing*, 94, pp. 97–100
- Ruby-Meyer, F., Lehmann, J. and Gaye, H. (2000). Thermodynamic analysis of inclusions in Ti-deoxidised steels. *Scandinavian Journal of Metallurgy*, 29(5), pp. 206–212
- Samsonov, G.V., Panasyuk, A.D. and Kozina, G.K. (1968). Wetting of refractory carbides with liquid metals. *Powder Metallurgy and Metal Ceramics*, 7 (11), pp. 874–878.
- Samsonov, G. V., Dzodziev, G. T., Klyachko, L. I. and Vitryanyuk, V. K. (1972/1). Effect of molybdenum on the properties of sintered TiC-Ni hard alloys. *Powder Metallurgy and Metal Ceramics*, 11(4), pp. 300–302
- Samsonov, G.V., Panasyuk, A.D., Kozina, G.K. and D'yakonova, L.V. (1972/2). Contact reaction of refractory compounds with liquid metals. *Powder Metallurgy and Metal Ceramics*, 11(7), pp. 568–571
- Shim, J-H., Cho, Y.W., Chung, S.H., Shim, J.-D. and Lee, D.N. (1999): Nucleation of intergranular ferrite at Ti₂O₃ particle in low carbon steel. *Acta Materialia*, 47, pp. 2751–2760
- Shim, J-H., Oh, Y.J. Suh, J.Y., Cho, Y.W., Shim, J.-D., Byun, J. S. and Lee, D.N. (2001/1): Ferrite nucleation potency of non-metallic inclusions in medium carbon steel. *Acta Materialia*, 49, pp. 2115–2122
- Shim J-H., Byun J. S., Oh Y.J. Shim J.-D., and Lee D.N. (2001/2): Mn Absorption characteristics of Ti₂O₃ inclusions in low carbon steels. *Scripta Materialia*, 44, pp. 49–54
- Smith C.S. (1948): Grains, phases, and interfaces: an interpretation of microstructure. *Transactions of the Metallurgical Society of AIME*, 175, pp. 15–51
- Sumito, M., Tsuchiya, N., Okabe, K. and Sanbongi, K. (1981). Solubility of titanium and carbon in molten Fe-Ti alloys saturated with carbon. *Transactions ISIJ*, 21, pp. 414–421
- Takamura, J.I. and Mizoguchi, S. Roles of oxides in steels performance. *Proceedings of the 6th International Iron and Steel Congress*, 1990, pp. 591–597
- Terry, B. S. and Chinyamakobvu, O. S. (1991). In situ production of Fe-TiC composites by reactions in liquid iron alloys. *Journal of Materials Science Letters*, 10, pp. 628–629

- Terry, B. S. and Chinyamakobvu, O. S. (1992/1). Effects of cooling rate and heat treatment on the microstructure of iron-based titanium carbide composites. *Journal of Materials Science*, 27(20), pp. 5666–5670
- Terry, B. S. and Chinyamakobvu, O. S. (1992/2). Dispersion and reaction of TiC in liquid iron alloys. *Materials Science and Technology*, 8(5), pp. 399–405
- Tiusanen, J., Rissa, K., Ritvonen, T., Lagerbom, J., Keskiäho, K. and Lepisto, T. (2009). Characterization of functional gradient structures in duplex stainless steel castings. *Estonian Journal of Engineering*, 15(4), pp. 293–300
- Vallauri, D., Atias Adrian, I. C. and Crysanthou, A. (2008). TiC–TiB₂ composites: A review of phase relationships, processing and properties. *Journal of the European Ceramic Society*, 28(8), pp. 1697–1713
- Van Der Eijk, C., Grong, O., Haakonsen, F., Kolbeinsen, L. and Tranell, G. (2009): Progress in the development and use of grain refiner based on cerium sulfide or titanium compound for carbon steel. *ISIJ International*, 49, pp. 1046–1050.
- Van Ende, M.-A., Guo, M., Dekkers, R., Burty, M., Van Dyck, J., Jones, P.T., Blanpain, B. and Wollants, P. (2009). Formation and evolution of Al–Ti oxide inclusions during secondary steel refining. *ISIJ International*, 49(8), pp. 1133–1140
- Verezub, O.N., Kalazi, Z., Buza, G., Boross, P., Verö, B. and Kaptay, G. (2003). Surface metal matrix composite Fe–Ti–C/TiC layers produced by laser melt injection technology. *International Conference on Advanced Metallic Materials*, 2003, Smolenice, Slovakia, pp. 297–300
- Wang, C., Nuhfer, N.T. and Sridhar, S. (2009/1). Transient behavior of inclusion chemistry, shape and structure in Fe–Al–Ti–O melts: effect of titanium source and laboratory deoxidation simulation. *Metallurgical and Materials Transactions B*, 40B, pp. 1005–1021
- Wang, C., Nuhfer, N.T. and Sridhar, S. (2009/2). Transient behavior of inclusion chemistry, shape and structure in Fe–Al–Ti–O melts: effect of titanium/aluminum ratio. *Metallurgical and Materials Transactions B*, 40B, pp. 1022–1034
- Wang, C., Verma, N., Kwon, Y., Tiekink, W., Kikuchi, N. and Sridhar, S. (2011). A Study on the transient inclusion evolution during reoxidation of a Fe–Al–Ti–O melt. *ISIJ International*, 51(3), pp. 375–381
- Warren, R. (1980). Solid-liquid interfacial energies in binary and pseudo-binary systems. *Journal of Materials Science*, 15(10), pp. 2489–2499
- Wu, Q. L., Sun, Y. S., Xue, F. and Zhou, J. (2008). Microstructure, mechanical and wear properties of TiC particulate reinforced 2Cr13 steel by in situ reaction and electroslag remelting. *Ironmaking & Steelmaking*, 35(5), pp. 387–395
- Xuan, C. (2016/1). Wettability and agglomeration characteristics of non-metallic inclusions in the melt. *Doctoral Thesis*, KTH Royal Institute of Technology, Stockholm, 2015, pp. 7–8, 28–29
- Xuan, C., Mu, W., Olano, I., Jönsson, P. and Nakajima, K. (2016/2). Effect of the Ti, Al contents on the inclusion characteristics in steels with TiO₂ and TiN particle additions. *Steel Research International*, 87(7), pp. 911–20
- Yang, Z., Wang, F. and Song, B. (2008): Intragranular ferrite formation mechanism and mechanical properties of non-quenched-and-tempered medium carbon steels. *Steel Research International*, 79, pp. 390–395
- Zener, C. (1949): Theory of growth of spherical precipitates from solid solutions. *Journal of Applied Physics*, 20, pp.950–953
- Zhang, S. (1993). Titanium carbonitride-based cermets: processes and properties. *Materials Science and Engineering A*, 163, pp. 141–148
- Zhuo, X., Wang, X., Wang, W. and Lee, H.-G. J. (2007): Thermodynamic calculations and experiments on inclusions to be nucleation sites for intragranular ferrite in

- Si-Mn-Ti deoxidized steel. *Journal of University of Science and Technology Beijing*, 14, pp. 14-21
- Zhuo, S. Q., Zhao, W., Xiong, W. H. and Zhou, Y. N. (2008). Effect of Mo and Mo₂C on the microstructure and properties of the cermets based on Ti(C,N). *Acta Metallurgica Sinica (English Letters)*, 21(3), pp. 211-219

ISBN 978-952-60-3900-8 (printed)

ISBN 978-952-60-3901-5 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University
School of Chemical Engineering
Department of Chemical and Metallurgical Engineering
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**