Towards a Closed Loop Economy in Textile Industry: Separation, Dyeing and Re-Spinning of Cellulose Rich Textile Waste

Simone Haslinger

Towards a Closed Loop Economy in Textile Industry: Separation, Dyeing and Re-Spinning of Cellulose Rich Textile Waste

Simone Haslinger

**The public defense on 5th June 2020 at 12:00 will be
available via remote technology.**

Link: <https://aalto.zoom.us/j/65506626684>

Zoom Quick Guide: <https://www.aalto.fi/en/services/zoom-quick-guide>

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Chemical Engineering, at a public examination held at the lecture hall L1 of the school on 05 June 2020 at 12:00.

**Aalto University
School of Chemical Engineering
Department of Bioproducts and Biosystems
Biorefineries**

Supervising professor

Professor Herbert Sixta, Aalto University, Finland

Thesis advisor

Professor Michael Hummel, Aalto University, Finland

Preliminary examiner

Dr. Richard Blackburn, University of Leeds, United Kingdom, Dr. Frank Hermanutz, Deutsche Institute fuer Textil- und Faserforschung Denkendorf, Germany

Opponent

Professor Tung Pham, University of Innsbruck, Austria

Aalto University publication series

DOCTORAL DISSERTATIONS 73/2020

© 2020 Simone Haslinger

ISBN 978-952-60-3874-2 (printed)

ISBN 978-952-60-3875-9 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-60-3875-9>

Unigrafia Oy

Helsinki 2020

Finland

Author

Simone Haslinger

Name of the doctoral dissertation

Towards a Closed Loop Economy in Textile Industry: Separation, Dyeing and Re-Spinning of Cellulose Rich Textile Waste

Publisher School of Chemical Engineering**Unit** Department of Bioproducts and Biosystems**Series** Aalto University publication series DOCTORAL DISSERTATIONS 73/2020**Field of research** Biorefineries**Manuscript submitted** 6 March 2020**Date of the defence** 5 June 2020**Permission for public defence granted (date)** 22 April 2020**Language** English☐ **Monograph**☒ **Article dissertation**☐ **Essay dissertation****Abstract**

This thesis targeted to improve the waste management in textile industry in terms of material identification, waste valorization and implementation of sustainable alternatives to commercial dyes and finishing agents. A solid-state NMR method was developed to quantify the amount of cellulose in cotton polyester blends, employing a relationship between distinct peak ratios and the cellulose concentration. Furthermore, the Ioncell technology allowed to utilize both, cotton polyester blends and dyed cellulose waste, to spin new, textile grade cellulose fibers via an ionic liquid solvent system. The produced filaments displayed tensile properties superior to commercial Viscose and Tencel with titers down to the microfiber range (<1 dtex). It was also shown that the ionic liquid, 1,5-diazabicyclo[4.3.0]non-5-ene acetate, enabled to dissolve cellulose, while leaving behind a polyester residue, which could be recovered for conventional recycling procedures. Similarly, dyed pre- and post-consumer cotton waste was converted to pristine, colored staple fibers, which were used to manufacture a scarf and a baby jacket. In many cases, the original color of the waste fabrics translated to the new textile products, although a certain amount of leaching could be observed during the spinning process. This behavior was dependent on the nature of the dyes and was hence more pronounced for reactive dyes such as Remazoles than for vat dyes. Eventually, gold and silver nanoparticles were assessed to replace potentially polluting dyes and finishing agents. Via a hydrothermal *in-situ* synthesis approach, spherical nanoparticles were prepared on bleached prehydrolyzed kraft pulp, which was subsequently dry-jet wet spun to colored, UV protective man-made cellulose fibers. As a result of the incorporation technique, the fibers exhibited a better wash fastness than substrates coated via immersion or *in-situ* reduction only. This demonstrated that the Ioncell process offers versatile opportunities for waste reduction as it tolerates different raw materials and impurities such as synthetic fibers and colorants.

Keywords ionic liquid, NMR, cotton, polyester, reactive dyes, vat dyes, gold and silver nanoparticles**ISBN (printed)** 978-952-60-3874-2**ISBN (pdf)** 978-952-60-3875-9**ISSN (printed)** 1799-4934**ISSN (pdf)** 1799-4942**Location of publisher** Helsinki**Location of printing** Helsinki **Year** 2020**Pages** 188**urn** <http://urn.fi/URN:ISBN:978-952-60-3875-9>

Acknowledgements

This work was carried out from October 2015 until March 2020 under the supervision of Professor Herbert Sixta. The research was funded by Trash-2-Cash, an EU Horizon 2020 project, which gave me the unique opportunity to collaborate with experts from many different fields and countries. I would like to thank the Walter Ahlström Foundation, the Jenny and Antti Wihuri Foundation, the Tekniikan Edistämisyhdistys, and the Oskar Öflunds Stiftelse for providing me with additional financial support that elevated my motivation and allowed me travel to international conferences.

My intellectual debt is largely to Professor Herbert Sixta, who gave me the chance to deepen my knowledge in Finland and who introduced me to the world of cellulose. I have never had a supervisor, who understood that well to raise interest about his students' research among the broad public. Friends and family usually believe Chemistry related research is dull, but starting my studies in your group changed their perception. Herbert, I also appreciate your drive to push us to the limits; even though it sometimes made us struggle, it truly made our work more brilliant. Special thanks also to Professor Michael Hummel, who supported me with his positive attitude and commitment to science. Your sense of humor made long project meetings more bearable and showed me how to inspire people by science.

Moreover, I would like to offer my sincere gratitude to my co-authors and Master students. Above all, Xueyao Ge, Yuhang Ye, and Yingfeng Wang. Without your motivation and support, my work would not even be half as good. I was truly astonished by your determination and diligence. Your passion kept me motivated and made me enjoy coming to work every morning. Thank you, Professor Ali Harlin, Marjo Määtänen, Adina Anghelescu-Hakala, Sami Hietala, and Professor Sirkka Liisa Maunu. You immensely supported my research throughout the years with your profound scientific expertise and your assistance in various analyses. Special thanks also to Marja Rissanen, Marjaana Tanttu, and Elina Ilen, who helped me to convert my samples into pieces of art. I also owe gratitude to Miriam Beatrice Lossa, whose scientific findings certainly increased the value of this thesis.

I would also like to express my appreciation to the technical support staff in Puu I. While Seppo Jääskeläinen, Timo Ylönen, Hans Orassaari, and Jan Stang helped to solve any possible crisis evolving in the lab, Harri Koskinen was my savior when my laptop decided to stop working. I also want to thank Rita

Hatakka and Marja Kärkkäinen, who supported me with any lab related issues. Your kindness made working in Aalto a truly joyful experience.

Although both my thesis and publications only mention a few names, my studies could have never been successful without my colleagues who created a great working atmosphere. Eveliina Jutila, my longest and “oldest” office mate, you were the first one to talk to me after I had made my first acquaintances with Finnish silence. Annariikka Roselli and Eeva Lehtonen, I also loved to share an office with you. I liked your jokes and the way you took care of me when I was still new to Aalto. Terhi Toivari and Kyösti Ruuttunen, I enjoyed your lunch company a lot. No matter how frustrating work was, you could make me laugh again. I would also like to thank Anne Michud, Yibo Ma, and Shirin Asaadi. You had the patience to teach me everything I needed to know about spinning. Thank you so much Kaniz Moriam, Leena Katajainen and Hilda Zahra, who joined our group when work was truly stressful. Not only were you the best support I could have had in the lab, you have also become my good friends. I am also grateful to Marianna Granatier and Oona Korhonen, who always listened to me, when I needed someone to talk to. Special thanks also to Mikaela Trogen who helped me to write the final sentence of my dissertation. Of course, my deepest appreciation also goes to all my other colleagues and members of the spin team. Sanna Hellsten, Joanna Witos, Chamseddine Guizani, Inge Schlapp-Hackl, Kaarlo Nieminen and anyone else I may have not mentioned. I enjoyed working with everyone of you.

Eventually, I would like to express my gratitude to my friends and family. Sherif, thank you so much for withstanding my moods and desperation during the final phase of my thesis. Thanks for listening and supporting me when I needed it the most. Thank you, all my dear Austrian friends, Sandra, Caro, Anschl, Therri, Sarah, Alex, Barbara, Christian, David, and Michi who did not forget me while I was studying far away from home and came to visit me so often throughout the years. Thank you, my dear father, for your love and support. Finally, to my mother, who has always supported me in my decisions and raised me up to become the person who I am. You have stood by my side on every day of my life. I hope one day I can return part of what you have given to me.

Espoo, April 26th, 2020.

Simone Haslinger

Contents

1.	Introduction.....	15
2.	Research Questions	19
3.	Background.....	21
	3.1. Characterization of Textile Waste	21
	3.1.2. Near Infrared Spectroscopy	21
	3.2.2. Attenuated Total Reflection Spectroscopy	22
	3.2.3. 2D Barcodes and Radio Frequency Identification Tags	22
	3.2.4. ¹³ C Solid-state NMR.....	22
	3.2. Pulp and Cellulose Rich Waste Textiles as Substrates for Dry-Jet Wet Spinning	28
	3.2.1. Dissolving Pulp (PHK)	28
	3.2.2. Textile Fibers	29
	3.2.3. Textile Dyes.....	31
	3.3. Dissolution of Cellulose in Ionic liquids and Dry-Jet Wet Spinning	33
	3.3.1. Dissolution Mechanism.....	33
	3.3.2. Rheological Properties of Cellulose Ionic Liquid Solutions.....	35
	3.3.3. Factors Influencing the Spinning Process	36
	3.4. Surface Plasmon Resonance	38
	3.5. Cellulose Nanoparticle Composites	40
	3.5.1. Seed Mediated Synthesis and Dip Coating.....	40
	3.5.2. Electrostatic Assembly.....	41
	3.5.3. <i>In-situ</i> Reduction	42
	3.5.4. Incorporation via Dry-Jet Wet Spinning.....	44
4.	Materials and Methods.....	45
	4.1. Cellulose and Polyester Based Raw Materials	45
	4.1.1. NMR Standards.....	45
	4.1.2. Pretreatment of Cotton Polyester Blends.....	45

4.1.3. Pretreatment of Pre-Consumer Cotton.....	45
4.1.4. Viscosity Adjustment and Pretreatment of Samples (S16) from Unpublished Results.....	47
4.1.5. Vat Dyeing.....	47
4.1.6. Reactive Dyeing	48
4.1.7. Coating of PHK Pulp with Noble Metal Nanoparticles...	48
4.2. Dissolution of Cellulose in [DBNH] [OAc] and Dry-Jet Spinning	49
4.2.1. Synthesis of [DBNH] [OAc]	49
4.2.2. Separation of Cotton and Polyester	49
4.2.3. Dissolution of Colored Textile Waste and Nanoparticle Coated PHK Pulp	50
4.2.4. Dissolution Studies of Dyes and Dyed Textiles in [DBNH] [OAc]	50
4.2.5. Dry-Jet Wet Spinning	50
4.3. Yarn Spinning, Knitting and Demonstration Products.....	51
4.3.1. Spin Finishing	51
4.3.2. Yarn Spinning	51
4.3.3. Fabrics from Dyed Cotton Waste.....	51
4.3.4. Fabrics from Nanoparticle Containing Ioncell Fibers....	52
4.3.5. Fabric from Mixed Cellulose Waste (Unpublished) ...	52
4.4. Analytics	52
4.4.1. ¹³ C CP MAS NMR (A1)	53
4.4.2. Acid Hydrolysis of CO/PET Blends (A2)	53
4.4.3. Molar Mass Distribution of Cellulose Using Gel Permeation Chromatography (A3)	53
4.4.4. Molar Mass Distribution of Polyester (PET) Using Gel Permeation Chromatography (A4)	54
4.4.5. Rheology of Cellulose Solutions (A6).....	54
4.4.6. Birefringence of Cellulose Fibers (A8).....	54
4.4.7. Thermogravimetric Analysis of Cellulose and Polyester (A9)	54
4.4.8. Scanning Electron Microscopy (A10)	55
4.4.9. Transmission Electron Microscopy (A11)	55
4.4.10. Color Coordinates (CIELAB) (A12)	55
4.4.11. Inductively Coupled Plasma-Atomic Emission Spectrometry (A13)	56

4.4.12. Tensile Testing of Yarns (A14)	56
5. Results and Discussion	57
5.1. NMR-Analysis of Cotton Polyester Blends	57
5.1.1. Peak Deconvolution and Calibration Model for Quantification	59
5.1.2. Quantification Results.....	60
5.2. Raw Materials of Papers II-IV	61
5.2.1. Hydrothermal Synthesis of Gold and Silver Nanoparticles on Bleached PHK Pulp.....	61
5.2.2. Pretreatments of Cotton and Cotton Polyester Blends...	62
5.2.3. Viscosities and Molar Mass Distributions	64
5.3. Dissolution and Dry-Jet Wet Spinning	67
5.4. Polyester in the Ioncell Process	74
5.5. Dyes in the Ioncell Process	76
5.6. Gold and Silver Nanoparticles in the Ioncell Process.....	79
5.7. Yarn Spinning, Fabrics, and Demo Products	81
5.8. Wash and Rubbing Fastness of Dyed Fabrics and Nanoparticle Containing Yarns	82
5.9. UV Protection of Nanoparticle Containing Ioncell Fabrics	84
5.10. Unpublished Results: Recycling of Mixed Post-Consumer Cellulose Waste.....	85
6. Conclusions.....	89
References.....	90
Appendix 1	101
Appendix 2	102

List of Abbreviations and Symbols

$\varepsilon_1, \varepsilon_2$	real and imaginary variables of dielectric function
ε_m	dielectric constant of surrounding medium
[AMIM] [Cl]	1-allyl-3-methylimidazolium chloride
[BMIM] [Cl]	1-butyl-3-methylimidazolium chloride
[BMIM] [OAc]	1-butyl-3-methylimidazolium acetate
[DBNH] [OAc]	1,5-diazabicyclo[4.3.0]non-5-ene acetate
[EMIM] [OAc]	1-ethyl-3-methylimidazolium acetate
4-OH-TEMPO	4-hydroxy-2,2,6,6-tetramethylpiperidin-1-oxyl
A	acid washing, absorbance
a	slope
a*	redness
ACS	accessible crystallite surface
AFS	accessible fibril surface
AgAuNP	nanoparticle of gold and silver
AgNP	silver nanoparticle
ATR	attenuated total reflection
AuNP	gold nanoparticle
b	intercept
b*	yellowness
C2-3-5	peak of C2, C3, and C5 of cellulose in the NMR
Cell.	cellulose
CF	cover factor
CO	cotton

Cond.	conditioned
COP	crossover point
CP	crosspolarization
CrI [%]	crystallinity ratio
cryst.	crystalline
CTAB	cetrimonium bromide
DBN	1,5-diazabicyclo(4.3.0)non-5-ene
DBU	1,8-diazabicyclo(5.4.0)undec-7-ene
disk	disk refining
DMAc	N,N-dimethylacetamide
DMSO	dimethyl sulfoxide
DP	degree of polymerization
DP<100	degree of polymerization below 100
DP>2000	degree of polymerization above 2000
DR	draw ratio
DSC	differential scanning calometry
e-beam	electron beam irradiation
EG	endoglucanase
Elong.	elongation / %
Ew	alkaline washing
FTIR	fourier-transform infrared
f_{total}	total orientation factor
FW	fibril width
G'	storage modulus (Pa)
G''	loss modulus (Pa)
G'=G''	crossover point of storage and loss modulus
GPC	gel permeation chromatography
Hemicell.	hemicelluloses
HFIP	hexafluoroisopropanol
IACS	inaccessible crystallite surface

IAFS	inaccessible fibril surface
IC	inner-crystalline region
ICP	inductively coupled plasma
IL	ionic liquid
IR	infrared
I _α	cellulose I _α
I _β	cellulose I _β
L*	lightness
MAS	magnetic angle spinning
MMCFs	man-made cellulose fibers
MMD	molar mass distribution
Mn	number average molar mass (kDa)
<i>m_s</i>	spin quantum number
mTBD	7-methyl-1,5,7-triazabicyclo(4.4.0)dec-5-ene
Mw	weight average molar mass
NIR	near infrared
NMMO	N-methylmorpholinium-N-oxide
NMR	nuclear magnetic resonance
P	hydrogen peroxide
Paracryst.	paracrystalline
PDDA	poly (diallydimethylammonium chloride)
PDI	polydispersity index
PET	polyethylene terephthalate
PHK	prehydrolyzed kraft
PolyDADMAC	poly (diallydimethylammonium chloride)
q _{fibril}	fibril surface area fraction
R	reflectance
rf	radio frequency
RFID	radio frequency identification
SEM	scanning electron microscopy

SPB	surface plasmon band
Spin.	spinnable
TEM	transmission electron microscopy
TGA	thermogravimetric analysis
TM	yarn twist multiples
T _o	onset temperature
UPF	UV protection factor
UV	ultraviolet
UVA	ultraviolet light in the range of 290-315 nm
UVB	ultraviolet light in the range of 315-400 nm
v _e	extrusion velocity / (cm ³ /min)
V _{take-up}	take-up velocity of the godets / (m/min)
V _o	particle volume $\left(\frac{4\pi}{3}\right) R^3$
x	peak ratio
y	cellulose concentration (wt%)
Z	ozone
α	hydrogen bond acidity
β	hydrogen bond basicity
β-α	net basicity
ΔE	color difference
Δn	birefringence value
η	limiting viscosity / (ml/g)
η [*]	complex viscosity / (Pa s)
η _o [*]	zero shear viscosity / (Pa s)
π [*]	solvent polarizability
ω	angular frequency / (1/s)

List of Publications

This doctoral dissertation consists of a summary and of the following publications, which are referred to in the text by their numerals

I. Haslinger, Simone; Hietala, Sami; Hummel Michael; Maunu, Sirkka Liisa; Sixta, Herbert. 2019. Solid-State NMR Method for the Quantification of Cellulose and Polyester in Textile Blends. Elsevier. Carbohydrate Polymers, volume 207, page 11-16. Online ISSN: 0144-8617. DOI: 10.1016/j.carbpol.2018.11.052.

II. Haslinger, Simone; Hummel, Michael; Anghelescu-Hakala, Adina; Määttänen, Marjo; Sixta, Herbert. 2019. Upcycling of Cotton Polyester Blended Textile Waste to New Man-Made Cellulose Fibers. Elsevier. Waste Management, volume 97, page 88-96. Online ISSN: 0956-053X. DOI: 10.1016/j.wasman.2019.07.040.

III. Haslinger, Simone; Wang, Yingfeng; Rissanen, Marja; Lossa, Miriam Beatrice; Tanttu, Marjaana; Ilen, Elina; Määttänen, Marjo; Harlin, Ali; Hummel, Michael; Sixta, Herbert. 2019. Recycling of Vat and Reactive Dyed Textile Waste to New Colored Man-Made Cellulose Fibers. Royal Society of Chemistry. Green Chemistry, issue 21, page 5598-5610. DOI: 10.1039/C9GC02776A.

IV. Haslinger, Simone; Ye, Yuhang; Rissanen, Marja; Hummel, Michael; Sixta, Herbert. 2020. Cellulose Fibers for High-Performance Textiles Functionalized with Incorporated Gold and Silver Nanoparticles. ACS Publishing. ACS Sustainable Chemistry & Engineering, issue 8 (1), page 649-658. DOI: 10.1021/acssuschemeng.9b06385.

Author's Contribution

Publication I: Solid-State NMR Method for the Quantification of Cellulose and Polyester in Textile Blends

Simone Haslinger designed the study, conducted the experiments, and wrote the manuscript as a principal author. Sami Hietala and Sirkka Liisa Maunu performed the NMR relaxation delay experiments to determine the instrument parameters. Michael Hummel and Herbert Sixta supervised the research and reviewed the manuscript.

Publication II: Upcycling of Cotton Polyester Blended Textile Waste to New Man-made Cellulose Fibers

Simone Haslinger designed the study, conducted the experiments, and wrote the manuscript as a principle author. Adina Anghelescu-Hakala and Marjo Määttänen pretreated the raw material and performed the GPC analysis of polyester. Michael Hummel and Herbert Sixta supervised the research and reviewed the manuscript.

Publication III: Recycling of Vat and Reactive Dyed Textile Waste to New Colored Man-Made Cellulose Fibers

Simone Haslinger planned the study, conducted the experiments related to pre-consumer cotton, supervised the spinning trials of the post-consumer samples, and wrote the manuscript as a principal author together with Marja Rissanen. Yingfeng Wang performed the recycling experiments of post-consumer cotton. Miriam Beatrice Lossa recycled the denim garments under the supervision of Marja Rissanen. Marja Rissanen also conducted the wash and rubbing fastness tests, spun the yarns, and knitted the fabrics. Marjaana Tanttu dyed the raw material and produced the baby jacket together with Elina Ilen. Marjo Määttänen and Ali Harlin pretreated the pre-consumer fabrics. Michael Hummel and Herbert Sixta supervised the research and reviewed the manuscript.

Publication IV: Cellulose Fibers for High-Performance Textiles Functionalized with Incorporated Gold and Silver Nanoparticles

Simone Haslinger planned the study, conducted the experiments together with Yuhang Ye, and wrote the manuscript as a principal author together with Marja Rissanen. Moreover, Yuhang Ye performed all required optimization experiments prior to the spinning trials. Marja Rissanen also spun the yarns and manufactured the fabrics. Michael Hummel and Herbert Sixta supervised the research and reviewed the manuscript.

1. Introduction

The McDonaldization of fashion industry has created an interplay between the consumers' longing for instant gratification and high value (Bhardwaj & Fairhurst 2010). Despite the arising awareness of the environmental impacts associated with clothing industry, fast fashion consumers tend to prefer obsolescence over quality (Joy *et al.* 2015). "Here today, gone tomorrow" is the result of a continuous development of a societal attitude towards clothing as an emotional product rather than a valuable good (Weber, Lynes & Young 2017; Bhardwaj & Fairhurst 2010).

In the early 20th century, clothing was designed to foster a sustainable production that enabled to preserve valuable resources. Manufacturers tried to avoid unnecessary decorations and consumers would mend their clothes if needed. This led to a waste reduction of about 10% in the United States during World War I. With an increasing industrial development, the consumption of clothing per capita began to rise significantly (Claudio 2007). During the past two decades, the worldwide production of textiles doubled, whereas the average time of use decreased to less than a year for 50% of the fast fashion items (Ellen MacArthur Foundation 2017). Nowadays, an average Swedish consumer purchases 15 kg of clothing annually, of which 8 kg will be landfilled or incinerated ultimately (Carlsson *et al.* 2015). With 3% of the global greenhouse gas emissions (Laitala *et al.* 2012 in (Nørup *et al.* 2018)), the textile sector produces more carbon dioxide than both shipping and aircrafts combined (Ellen MacArthur Foundation 2017).

The textile industry mainly utilizes fibers from oil-based resources (63%) and cotton (26%) (Ellen MacArthur Foundation 2017). In particular, the demand for the latter is anticipated to grow because of the increasing wealth in emerging nations (Hämmerle 2011). 97% of the fibers produced globally are of virgin origin; less than 1% are manufactured via a closed-loop recycling technology (Ellen MacArthur Foundation 2017). However, cotton farming is expected to experience a decline due to the progressing depletion of natural resources and the competition with food for arable land. As cotton fibers show unique moisture up-take properties, they cannot entirely be replaced by synthetics, which represents an opportunity for man-made cellulose fibers (MMCFs) (Hämmerle 2011). The wood employed for MMCF production is hardly fertilized or irrigated, and thus fibers made thereof perform significantly better than cotton in terms of eco-toxicity, eutrophication, as well as water and land use (Shen & Patel 2010).

In 2008, a European Framework Directive (2008/98/EC) was introduced to improve the management of municipal waste. It targeted to recover up to 70% of the waste produced in the European Union by fostering prevention and preparation for reuse, facilitating recycling, and reducing ultimate disposal (Bukhari, Carrasco-Gallego & Ponce-Cueto 2018). With the change in legislation, research on the utilization of MMCF processes in textile recycling began to flourish. Many fiber manufactures filed patents on the exploitation of cotton waste as a feedstock for MMCFs (Eltz 1995; Serad 1993; Sun, Hongyu, Li, Chunguang *et al.* 2018). Processes such as SaXcell aim to convert cellulose rich textiles to dissolving pulp, which can be used in the Viscose or the Lyocell process (Oelerich *et al.* 2017). However, most of them are still in a development stage, and not yet accessible on an industrial scale. Employing the Lyocell technology, REFIBRA is currently the only fully commercialized approach that enables to transform pre-consumer cotton to new textile grade fibers (Lenzing AG 2019). For post-consumer garments, no processes are available yet in a similar extent.

It is evident that an orientation of textile industry to more sustainable alternatives can only take place if new recycling models offer a benefit to both the environment and the manufacturer. The collection and sorting of textile waste has so far been the most expensive step in the process chain (Hinkka, Heikkilä & Harlin 2018). Legislations in Europe do not consider worn out garments as problematic waste. Consequently, no uniform collecting strategies exist that could guarantee a steady supply of a certain waste feedstock. Currently, waste textiles are accumulated by different organizations including fashion retailers, municipalities, and charities. Once collected, they are sorted by hand, and baled in containers (Carlsson *et al.* 2015) to be resold in Europe, or in developing countries (Dahlbo *et al.* 2017). Therefore, the present system distinguishes between various levels of quality, but does not assess worn out clothing based on different fiber compositions, or on the vast spectrum of chemicals and dyes employed.

Therefore, facilitated sorting represents one of the cores in a new textile economy. Suggestions range from robotics to interwoven barcodes, but only a few have developed to a larger scale (Carlsson *et al.* 2015). Especially near infrared (NIR) spectroscopy has received considerable attention recently as it is non-destructive, and simple to integrate online into existing processes (Blanco *et al.* 1994; Cleve, Bach & Schollmeyer 2000; Tincher & Luk 1985). Technologies such as Fibersort (Circle Economy 2019) and SIPTex (Boer Group Recycling Solutions 2019) aim to apply NIR scanning to automate conveyor belt sorting based on material compositions. They operate according to a data set large enough to cover the majority of fiber types present on the market (Cleve, Bach & Schollmeyer 2000). Parameters such as moisture content, surface morphology, and color, nevertheless, tend to influence their output (Rodgers & Beck 2009). Theoretically, this makes it possible to detect different colors, fabric types, and finishing agents, although requiring baseline corrections to account for these factors. Unfortunately, the accuracy of NIR is limited to surface measurements, which can complicate the detection of multilayer clothing.

Moreover, the textile industry has not been equipped so far to handle the recycling of multicomponent garments. Blends of natural fibers with synthetics such as spandex or polyester have been referred to as “monstrous hybrids” as they are hardly recyclable and consume major amounts of energy and resources to be processed (Braungart & McDonough 2008). For example, the distinct chemical nature of cellulose and polyester has prevented them to be recycled within one process stream. To facilitate their valorization, approaches suggest the depolymerization of either component (Cowan 1981; Grunfest & Turner 1974; Oakley, Gorman & Mason 1992; Shen *et al.* 2013; Ouchi *et al.* 2010; Guo, Lindqvist & La Motte 2018), followed by repolymerization, or chain extension (Awaja & Pavel 2005). On the contrary, the dissolution of cellulose or polyester helps to ensure the molecular integrity of these waste substrates. Whereas dissolving the latter demands hazardous chemicals and elevated temperatures (Serad 1993), cellulose can be dissolved in non-derivatizing, “green” solvents such as NMMO (Haule, Carr & Rigout 2016; Björquist *et al.* 2017) and ionic liquids (Hauru *et al.* 2012; Pinkert *et al.* 2009). In particular, ionic liquids do not require the addition of any stabilizers and can dissolve cellulose at significantly lower temperatures, while at the same time allowing to use the resulting cellulose solution for the dry-jet wet spinning of MMCFs directly (Meksi & Moussa 2017). A few studies have also demonstrated that these properties can be employed to separate and recover cellulose from synthetic fiber blends, although none of them has yet been able to prove the feasibility of the concept by fiber spinning (Lv *et al.* 2015; Negulescu *et al.* 1998; Silva, Wang & Byrne 2014).

Another inherent problem in textile recycling is the enormous amount of chemicals employed in the manufacturing process. Textile dyeing is performed with more than 10 000 different dyes, of which 70 % amount potentially carcinogenic azo dyes. Because of incomplete dye exhaustion, 10-15% of these dyes are lost in the waterways during processing (Hassaan & El Nemr 2017). Most recycling approaches do not contribute to the reduction of these effluents. Recycling studies on the dissolution and respinning of cotton waste often imply to bleach the waste substrates during the pretreatment stage to obtain an uncolored fiber product, which is more favorable on a commercial scale (Björquist *et al.* 2017). Potentially, this leads to a cycle of bleaching, redyeing, and finishing, repeatedly eradicating and reintroducing desired material properties. However, to lower the consumption of both chemicals and water, it is essential to maintain dyes and treatments throughout the whole process chain. This requires colorants and finishing agents to tolerate the chemical environment of the recycling process so that the original color and other selective properties can be transferred from the waste material to the new textile product. In principle, it has been shown that in certain cases, dyes can resist the conditions of the Viscose and the Lyocell process (Haule, Carr & Rigout 2016; Eltz 1995), alkali/urea systems (Liu *et al.* 2019), or mixtures of ionic liquids and DMSO (Ma *et al.* 2019). Nonetheless, systematic studies on the recyclability of dyes within these fiber-spinning processes are still missing.

Finally, a lack of technological development, a scarcity of viable upcycling options, and a poor traceability of the global waste chain have so far impeded the

creation of a circular economy (Boiten, Han & Tyler 2017). Closing the loop in textile industry demands a large technological input over the entire process chain, ranging from facilitated material identification and sorting to adequate separation methods and upcycling processes, and eventually, to a redesign of clothing towards less complex material compositions and chemicals involved.

The obstacles described above can largely be overcome by the Ioncell technology. The process uses a superbase based ionic liquid 1,5-diazabicyclo[4.3.0]non-5-ene acetate ([DBNH][OAc]), which is able to dissolve considerably high amounts of cellulose at reasonable process temperatures (Sixta *et al.* 2015). The cellulose solution produced thereof can be utilized to dry-je wet spin textile grade fibers with superior tensile properties compared to commercial MMCFs originating from the Viscose or Lyocell process (Michud *et al.* 2015). Besides standard dissolving pulp, the ionic liquid also enables to dissolve cellulosic waste material including paper, cardboard, and cotton (Ma *et al.* 2016; Ma *et al.* 2018; Asaadi *et al.* 2016).

Similarly, this thesis demonstrates that [DBNH] [OAc] is suitable to separate cotton and polyester, yielding textile-grade cellulose fibers and a purified polyester residue (Paper II). To evaluate the success of the separation procedure, a solid-state NMR method was developed to determine the cellulose content in the blend before and after separation (Paper I). The ionic liquid also provided an adequate medium to process dyed textile waste to new colored fibers with excellent wash fastness and tensile properties (Paper III). Ultimately, the Ioncell technology was utilized to integrate noble metal nanoparticles into MMCFs, which exhibited promising wash fastness and UV protection properties (Paper IV). Apart from Paper I, all articles include a detailed analysis of the material properties before and after spinning, a rheological assessment of the spinning solutions, and a discussion of the fiber properties. Paper III and IV also contain the conversion of staple fibers into yarns and fabrics, which were studied in terms of color change, as well as wash and rubbing fastness. Paper IV also evaluates the UV protection properties of the manufactured fabrics and the yield of the nanoparticles on the cellulose fibers.

2. Research Questions

This thesis can be considered as continuation of Shirin Asaadi's and Yibo Ma's doctoral dissertations, who investigated different cellulose based raw materials for dry-jet wet spinning in the Ioncell process. Until this point, however, neither of them had studied the use of synthetic fiber blends or colored textile waste. The recycling of cotton and polyester, for example, has always been associated with substantial challenges due to a lack of characterization and separation methods. These problematics led to an in-depth study of potential characterization approaches via NMR and the development of a separation procedure for interwoven cotton polyester blends. In her Master's Thesis, Eugenia Smirnova initiated the idea that dyed waste garments can be transformed to new, colored textile grade fibers. She showed that certain colorants translated well to the new fiber product, while others substantially leached and impaired the spinnability. This demanded a more systematic study on the behavior of different dye classes during recycling. Moreover, this thesis also explored gold and silver nanoparticles as green alternatives to textile dyes and finishing agents to reduce the amount of chemicals in the textile chain. Accordingly, this research can be summarized by the following questions.

- i. How can solid-state NMR be used to characterize textile blends?
- ii. Can cotton and polyester be separated via the Ioncell technology? And can the cellulose fraction be used to dry-jet wet spin new staple fibers, while the recovered polyester maintains its molecular mass and structure?
- iii. Can dyed, cellulose rich textile waste be spun to new colored man-made cellulose fibers? How do different dyes affect the spinning process? Which sustainable pretreatments are suitable for this approach?
- iv. Can gold and silver nanoparticles be incorporated into Ioncell fibers via a green synthesis method? How do the nanoparticles change the fiber properties? Are gold and silver nanoparticles a sustainable alternative to currently used highly polluting textile dyes and finishing agents?

3. Background

3.1. Characterization of Textile Waste

Worn out textiles represent a very heterogeneous waste substrate. Apart from impurities such as buttons and zippers, textiles are composed of a multitude of different fiber types. As stated before, the current market situation yields mainly synthetic fibers (62.6%) interwoven with cotton (25.3%), MMCs (6.4%), natural fibers (4.7%), and wool (1.1%) (*The Fiber Year* 2019). To close the loop, these blends need to be characterized and sorted adequately in order to be recycled. Currently, material identification has focused either on improving textile labeling during manufacturing (i.e. RFID tags and barcodes), or on spectroscopic detection during recycling (i.e. NIR, ATR, and NMR).

3.1.2. Near Infrared Spectroscopy

Recently, several near infrared (NIR) based technologies have emerged to facilitate the online sorting of waste garments according to their composition and color. Several EU funded initiatives have been launched to incorporate NIR techniques into conveyor belt sorting, among them Textiles4Textiles, Fibersort, and REISKAtex (European Commission 2019; Valvan Bailing Systems 2019; REISKAtex 2017). Similarly, SIPTex is a Swedish undertaking supported by the BOER group, which targets to demonstrate a full year operation on a pilot scale (Boer Group Recycling Solutions 2019). Most of these projects started around 2010 and employ comparable technologies.

Near infrared spectroscopy relies on the detection of molecular oscillations induced by electromagnetic radiation in a wavelength range of 760-2500 nm. Overtones and combination vibrations lead to complex spectra, which cannot be processed based on single signals, but require an analysis of all spectral features (Schwedt 2007). Moreover, parameters such as moisture content, surface structure, color, and fiber composition tend to influence the obtained results. Fabrics composed of the same material, nonetheless, show similar key features that can be further elaborated by advanced chemometrical methods such as partial least squares or principal component analysis (Cleve, Bach & Schollmeyer 2000; Blanco *et al.* 1994; Rodgers & Beck 2009; Chen *et al.* 2018).

The success of these approaches is yet largely dependent on the size of the reference data set, which includes a library of the parameters intended to be

analyzed. For example, REISKAtex enables to detect single component materials ranging from cotton and Viscose to wool and polyester, and can also identify textile blends to some extent (Cura & Rintala 2019). Further refinement of mathematical operations also allows the determination of exact blend compositions (Chen *et al.* 2018). In principal, NIR technologies display a high recognition rate (97-100%), but they face limitations with small contaminants such as elastane (Cura & Rintala 2019; Zhou *et al.* 2019).

3.2.2. Attenuated Total Reflection Spectroscopy

ATR spectroscopy utilizes the interactions between the sample surface and evanescent waves generated by the total reflection of IR radiation on an ATR-crystal. Similar to NIR technologies, this method operates on the comparison of spectra to a library of reference data sets. If a spectrum cannot be found in the library, the most similar reference spectrum is subtracted from the signal. Subsequently, the remaining spectrum is compared to a database, and further validated by discriminant, or principal component analysis (Espinoza, Przybyla & Cox). Likewise, this method enables to distinguish between different cellulosic fibers such as cotton, linen, or Viscose and can give an estimate on the quantitative fiber composition. Its drawback lies in the considerably bad reproducibility of the generated data caused by the relatively small detection surface on the ATR-crystal (Peets *et al.* 2017).

3.2.3. 2D Barcodes and Radio Frequency Identification Tags

Both 2D barcodes and radio frequency identification (RFID) tags are intended to ensure product authenticity and traceability. Once attached during manufacturing, they can be used to retrieve information about chemical treatments and material composition. In either case, they are expected to withstand mechanical deformation induced by wearing and laundering. RFID tags can be read contactless, while barcodes need to be exposed to a scanner manually. However, the latter have the advantage that they are easily accessible, and can be read by anyone equipped with a smartphone (Humpston *et al.* 2014).

3.2.4. ^{13}C Solid-state NMR

Like NIR, solid-state NMR represents a non-destructive analysis technique, which can yield information about a sample's molecular structure, conformation, and its interface dynamics. Each nucleus with a spin quantum number of $m_s=1/2$ produces a sharp signal once exposed to an external magnetic field. Therein, the positively charged nucleus begins to rotate parallel to the induced field until it is disturbed by a rf puls. After the disturbance, the nucleus again strives for equilibrium. Its relaxation time depends on the chemical environment, which results in a distinct shift in the NMR spectrum. Chemically inequivalent nuclei evolve as separate peaks, while alike nuclei tend to overlap. In general, ^{13}C signals are less resolved than ^1H signals due to their lower environmental abundance (1.1%). However, it is possible to compensate for the higher signal

to noise ratio by signal enhancing techniques such as dipolar decoupling, magic angle spinning (MAS) and cross polarization (CP) (Martínez-Richa & Silvestri 2012).

Cellulose

In polymers, it is usually distinguished between amorphous and crystalline regions. The latter is characterized by highly ordered structures, while the former represents a more random arrangement of the polymer chains. Cellulose exists in various crystal structures dependent on its origin and undergone processing conditions. Native celluloses are combinations of triclinic I_α and the monoclinic I_β structures, which deviate in their hydrogen bonding pattern. The I_β form is chemically more stable and occurs more abundantly in higher plant species such as cotton, wood and ramie fibers (Heinze 2016). Moreover, cellulose I_α can be converted to cellulose I_β by thermal treatment (Liitiä, Maunu & Hortling 2000). In contrast, cellulose II is formed by the dissolution and coagulation of cellulose I (Heinze 2016).

As stated before, NMR analysis can differentiate between chemically inequivalent nuclei. Besides, it is also possible to distinguish between equivalent atoms that differ magnetically (Martínez-Richa & Silvestri 2012). This implies that the carbon signals of various crystal structures and amorphous regions appear at different shifts in the NMR spectrum. Figure 1 displays the labelled, molecular structure of cellulose. C1, C4, and C6 tend to appear as single peaks with shifts of 102-108 ppm, 81-83 ppm, and 60-70 ppm, respectively, whereas the signals of C2, C3, and C5 overlap around 81-93 ppm (Atalla & VanderHart 1999).

Figure 1. Molecular structure of cellulose.

In particular, the signals of C1, C4 and C6 exhibit visible contributions of both amorphous and crystalline regions. This enables to determine the quantitative composition of different crystallite structures through peak deconvolution (Larsson, Wickholm & Iverson 1997). For this procedure, it has commonly been agreed on that the C4 peak is more suitable than the C6 and C1 signals as it shows a better resolution of amorphous and crystalline regions (Maunu *et al.* 2000).

Larsson *et al.* proposed a combination of five Gaussian and three Lorentzian functions to integrate the C4 signal of native cellulose (s. Figure 2 and Table 1) (Larsson, Wickholm & Iverson 1997).

Figure 2. Deconvolution of the C4 region of cellulose in a NMR spectrum recorded from cotton linters (Zuckerstätter *et al.* 2009).

Table 1. Fit parameters for the C4 region of cellulose I samples. Adapted with permission from (Larsson, Wickholm & Iverson 1997). Copyright (2020) Elsevier.

Assignment	δ / ppm	FWHH / Hz	Line type
I_α	89.5	29	Lorentz
$I_{(\alpha+\beta)}$	88.7	30	Lorentz
Paracrystalline	88.4	153	Gauss
I_β	87.9	53	Lorentz
Amorphous / inaccessible fibril surface (IAFS)	84.9	479	Gauss
Fibril surface (AFS)	84.1	80	Gauss
Fibril surface (AFS)	83.2	60	Gauss
Hemicelluloses and cellulose oligomers	82.3	135	Gauss

The three Lorentzian functions describe the I_α and I_β contributions in the structure, while the Gaussian fits account for the paracrystalline and amorphous regions, as well as for the fibril surfaces and hemicelluloses. This assignment follows a fibril model established by Wickholm and Larsson. It is assumed that the paracrystalline regions between the inner crystalline cellulose (i.e. I_α , I_β , and $I_{(\alpha+\beta)}$) and the inaccessible fibril surface (IAFS) follow an ordered structure somewhat different from the I_α and I_β crystallites. In contrast, the inaccessible surface area is considered only as an amorphous contribution in the cellulose structure (s. Figure 3) (Wickholm, Larsson & Iverson 1998; Larsson, Wickholm & Iverson 1997). In any case, both peak position and width are fixed, whereas

the peak height can be varied according to the signal intensity. After integration, the crystallinity ratio CrI [%] can be calculated as follows,

$$CrI[\%] = \frac{(I_{\alpha} + I_{\beta} + I_{(\alpha+\beta)} + Paracryst.) * 100\%}{(I_{\alpha} + I_{\beta} + I_{(\alpha+\beta)} + Paracryst. + AFS + IAFS)} \quad (1)$$

where I_{α} and I_{β} describe the content of cellulose I_{α} and I_{β} , while $I_{(\alpha+\beta)}$ denotes a mixed peak of I_{α} and I_{β} . Paracryst., AFS, and IAFS refer to the paracrystalline regions, and to the accessible and inaccessible fibril surface (Zuckerstätter *et al.* 2009).

Figure 3. Model of fibril aggregates (left) and single cellulose fibrils according to Wickholm *et al.* 1998 and Larsson *et al.* 1997. IC denotes the inner-crystalline regions of cellulose such as I_{α} , I_{β} , and $I_{(\alpha+\beta)}$, while AFS and IAFS describe the accessible and inaccessible fibril surface area, respectively. The paracrystalline region can be found between IC and IAFS. Image copied with permission from (Zuckerstätter *et al.* 2009).

Moreover, the integrated functions can also be used to calculate the fibril width (FW) from the fibril surface area fraction (q_{fibril}),

$$q_{fibril} = \frac{AFS + IAFS}{I_{\alpha} + I_{\beta} + I_{\alpha+\beta} + para. + AFS1 + AFS2 + IAFS} \quad (2)$$

$$FW[nm] = \frac{0.57 \cdot (4 + \sqrt{16 - 16 \cdot q_{fibril}})}{2 \cdot q_{fibril}} \quad (3)$$

where 0.57 denotes the length of one glucan unit in nm (Wickholm, Larsson & Iverson 1998; Zuckerstätter *et al.* 2009).

According to Zuckerstätter *et al.*, Larsson's model only suits to describe the crystallinity of cellulose I samples. Higher amounts of cellulose II, such as in regenerated fibers, are more appropriately determined by using Newman's or Ibbett's approach. Both assigned four Gaussian functions to deconvolute crystalline, amorphous and partly ordered regions (Newman & Davidson 2004; Ibbett *et al.* 2010; Ibbett, Domvoglou & Fasching 2007). Signal enhancing methods such as the wetting of cellulose or the addition of 4-OH-TEMPO led to the discovery of two further sharp lines, which were identified as surface crystalline and short cellulose chain contributions (Zuckerstätter *et al.* 2013). Based on

these results, Zuckerstätter *et al.* proposed a deconvolution approach employing two Lorentzian and four Gaussian functions (s. Figure 4 and Table 2).

Figure 4. Highly resolved NMR spectrum of regenerated Lyocell fibers with deconvolution of the C4 region based on crystalline cores, accessible and inaccessible crystallite surfaces (ACS, IACS), hemicelluloses contribution, and C2-3-5 signal (Zuckerstätter *et al.* 2013).

Table 2. Fit parameters for the C4 region of cellulose II samples according to (Zuckerstätter *et al.* 2013).

Assignment	δ / ppm	FWHM / Hz	Line type
Crystalline core	88.7	51	Lorentz
Crystalline core + accessible crystallite surface (ACS)	87.5	57	Lorentz
Accessible crystallite surface I (ACS I)	86.1	84	Gauss
Accessible crystallite surface II (ACS II)	84.5	89	Gauss
Amorphous / inaccessible crystallite surface (IACS)	83.9	338	Gauss
Hemicelluloses and cellulose oligomers	81.7	89	Gauss

Like the deconvolution of cellulose I, the Lorentzian fits are attributed to the crystalline core, whereas the Gaussian lines describe the accessible and inaccessible crystallite surfaces (ACS, IACS), as well as the influence of possible hemicelluloses present in the sample. Furthermore, a seventh function was added to account for the contribution of the C2-3-5 signal (Zuckerstätter *et al.* 2013).

This implies that the crystallinity ratio CrI [%] for cellulose II is calculated from the sum of crystalline cores $\sum cryst.$ and the amount of accessible crystallite surfaces $\sum ACS$,

$$CrI [\%] = \sum cryst. + \sum ACS \quad (4)$$

$$\sum cryst. = \frac{cryst. + \left(cryst. \& ACS \cdot \frac{cryst.}{cryst. + ACS I} \right)}{cryst. + cryst. \& ACS + ACS I + ACS II + IACS.} \quad (5)$$

$$\sum FS = \frac{ACS I + \left(cryst. \& ACS \cdot \frac{ACS I}{cryst. + ACS I} \right) + ACS II}{cryst. + cryst. \& ACS + ACS I + ACS II + IACS.} \quad (6)$$

where $cryst.$ denotes the crystalline core, while $cryst.\&ACS$ describe the combined signals of crystalline regions and accessible crystallite surfaces. $ACS I$, $ACS II$, and $IACS$ represent the accessible and inaccessible crystallite surface areas, respectively. Accordingly, the resulting fibril surface area fraction q_{fibril} is determined by the sum of $ACS I$ and $ACS II$ divided by the added sum of crystalline cores and the sum of accessible crystallite surface contributions (Zuckerstätter *et al.* 2013).

$$q_{fibril} = \frac{ACS I + ACS II}{\sum cryst. + \sum ACS} \quad (7)$$

Insertion of q_{fibril} into equation (3) finally yields the fibril width FW as proposed by Wickholm *et al.* 1998 (Wickholm, Larsson & Iverson 1998).

Polyester

Comparable to cellulose, solid-state NMR studies of polyethylene terephthalate (PET) fibers tend to focus on molecular dynamics and structural investigations (English 1984). As shown in Figure 5, PET is composed of two carboxylic carbons (C1 and C8), an aromatic unit (C2, C3, C4, C5, C6, and C7), and an ethynyl group (C9 and C10). In the NMR spectrum, the latter appears at a shift of 62–64 ppm, while the carboxylic and aromatic lines can be found at 164–166 ppm and 130–134 ppm (Gabrielse *et al.* 1994).

Figure 5. Chemical structure of PET.

Crystalline regions usually exhibit an enhanced resolution, while amorphous areas are more prone to cause peak broadenings because of a higher isotropic distribution of the resonating nuclei (Bai *et al.* 1998). It is also known that a decrease in crystallinity can lead to a downward shift of the ethynyl and carboxyl

resonances (Gabrielse *et al.* 1994). Moreover, ^1H spin-lattice relaxation time experiments can be used to estimate crystallite sizes and the quantitative compositions of ordered and amorphous regions (Nascimento *et al.* 2004; Gabrielse *et al.* 1994). However, a more detailed description of the analytics of PET is beyond the scope of this thesis.

Composition Analysis of Cotton Polyester Blends

Only a very limited amount of research applies ^{13}C solid-state NMR to quantitatively characterize fiber compositions in textile blends. More frequently, NMR is employed to either detect the purity of recovered sample substrates (Silva, Wang & Byrne 2014), or to assess a change in crystallinity throughout laundering (Palme *et al.* 2014). However, Coletti and Mathias developed a quantification method for cotton polyester blends based on peak height relationships. When comparing the C1 peak of cellulose (104 ppm) and the carboxyl peak of polyester (162 ppm), it was found that their peak height ratio correlates with the blend ratio in textile samples. The establishment of a linear regression model then led to an accurate material composition. A correlation between the ratios of peak areas and fiber compositions had also been investigated, but was not found to yield as accurate information, presumably because of undefined integration areas and a too high signal to noise ratio (Colletti & Mathias 1988).

3.2. Pulp and Cellulose Rich Waste Textiles as Substrates for Dry-Jet Wet Spinning

Successful dry-jet wet spinning is a matter of the cellulose substrate. It requires being free of any impurities that could prevent the dissolution of cellulose or impede the formation of filaments during extrusion. Furthermore, the samples need to display distinct viscosities and appropriate molar mass distributions. Like the Lyocell process, the Ioncell technology relies on a broad molar mass distribution and a viscosity range close to 400-500 ml/g. During dissolution and regeneration, short polymer chains are supposed to serve as fillers, while long cellulose strains aim to provide fiber strength. Stable spinning is thus only possible with sufficient pulp purity and optimal macromolecular properties such as a PDI above 3.0 and a share of low and high molecular weight fractions ($\text{DP} < 100$, $\text{DP} > 2000$) above 3% and 22.5%, respectively (Michud, Hummel & Sixta 2015).

3.2.1. Dissolving Pulp (PHK)

Dissolving pulp shows a high cellulose content (>90%), which is mainly used for regenerated MMFCs or cellulose derivatives including ethers and esters. During pulping, harvested wood logs are converted into wood chips and are further broken down to cellulose fibers via various mechanical and chemical treatments. A prehydrolysis step removes the hemicelluloses, while kraft pulping separates the cellulose fibers from lignin. Bleaching finally tailors the substrate's purity by removing metallic contaminants, so that the pulp becomes applicable in various regenerated fiber processes (Sixta 2006).

3.2.2. Textile Fibers

Garments undergo many different processing steps followed by wearing and washing, until they eventually end up as textile waste. These conditions lead to very complex waste materials, which challenge any recycling process (Hinkka, Heikkilä & Harlin 2018). The subsequent sections aim to highlight the arising difficulties in the recycling of cellulosic textile fibers in respect to cotton, MMCFs, and cellulose polyester blends.

Cotton

As stated earlier, textile production yields two major waste streams composed of pre- and post-consumer material. Whereas pre-consumer cotton is generated during the production stage, the latter term refers to worn out clothing. In contrast to post-consumer cotton, pre-consumer fibers resemble a pristine cotton product (i.e. $\eta \approx 2000$ ml/g) with a traceable history (Muthu 2014). However, once a garment is purchased, it undergoes various degrading procedures ranging from sunlight exposure to abrasion triggered by wearing and laundering (Wedin *et al.* 2018; Palme *et al.* 2014). When recycled, these two types of cotton waste require different processing conditions. Especially pre-consumer cotton demands extensive pretreatments to reach a target viscosity between 400-500 ml/g to be used in dry-jet wet spinning (Silva & Byrne 2017). The adjustment of these properties can be attained through various treatments employing electron irradiation, ozone, peroxides, acids, and enzymes (Silva & Byrne 2017; Asaadi *et al.* 2016; Björquist *et al.* 2017; Haule, Carr & Rigout 2016; Ma *et al.* 2016). In contrast, the properties of post-consumer cotton are more scattered and largely dependent on wearing time and washing conditions, which can decrease its viscosity to a range already suitable for a spinning process (Wedin *et al.* 2018). Given an adequate removal of impurities, the recycling of post-consumer cotton may therefore demand less chemicals to obtain the desired material properties for a regenerated fiber production (Palme *et al.* 2014). As for any other textile fiber, the recyclability of cotton, however, also strongly depends on dyes, finishing agents, and the presence of other fiber types, whose impact will be further discussed in the following chapters.

Man-Made Cellulose Fibers

MMCFs show intrinsically lower limiting viscosities (150-450 ml/g), which arise from distinct processing conditions during manufacturing (cf. Viscose and Lyocell technology) (Woodings 1995). Moreover, dissolution and regeneration of cellulose cause MMCFs to form a thermodynamically more stable structure referred to as cellulose II (Heinze 2016). Both aspects, viscosity and macromolecular conformation, influence the recyclability of MMCFs. In particular, the latter may affect the solubility of cellulose in the solvent due to altered crystallinity levels and hornification caused by chemical operations and drying (Siller *et al.* 2014).

In principle, it can be assumed that textiles made from MMCFs are subjected to the same degradation mechanisms as cotton fibers. The difference lies in their distinct polymer chain lengths. It is widely known that longer polymer chains

are more susceptible to degradation than shorter ones. Despite these circumstances, degradation in MMCs occurs when worn, but in a smaller extent than in cotton fibers. This makes MMCs less suitable to be recycled in a dry-jet wet spinning process as their viscosities (100-340 ml/g) fall far below the target range of 400-500 ml/g (Wedin *et al.* 2018). An implementation of worn out MMCs into regenerated fiber processes seems hence only viable in combination with virgin pulp substrates.

Blends of Cotton and Polyester

Due to their different chemical nature, cotton and polyester cannot be recycled in one process stream. Polyester is thermoplastic and shows a high hydrophobicity, while cellulose is largely moisture absorbent and infusible even at elevated temperatures. Consequently, cotton polyester blends cannot be converted to value-added products without separation. As described in the introduction, their separation requires either the dissolution or the degradation of one of the two components to enable further processing.

Polyester can only be dissolved at high temperatures in hazardous solvents such as dimethyl sulfoxide or hexafluoro isopropanol, which also affect the molecular integrity of cellulose (Serad 1993; Farah *et al.* 2014). Therefore, most approaches have rather focused on the degradation of polyester employing various types of hydrolysis reactions (Barot & Sinha 2015; Oakley, Gorman & Mason 1992; Palme *et al.* 2017; Shen *et al.* 2013). These procedures leave the macromolecular properties of cellulose largely unaffected, while the cotton residue can be recovered for subsequent recycling processes (Palme *et al.* 2017). Nonetheless, the depolymerized building blocks of polyester need to undergo repolymerization or chain extension reactions to create a closed loop economy (Awaja & Pavel 2005; Sun *et al.* 2018).

Likewise, cellulose can be hydrolyzed in an acidic environment (Cowan 1981; Gruntfest & Turner 1974; Ouchi *et al.* 2010; Shen *et al.* 2013). Under adequate conditions, hydrochloric acid degrades cotton to a microcrystalline cellulose powder, which can be separated from the polyester residue. The latter can then be respun to PET yarns suitable for textile applications (Sun, Hongyu, Li, Chunguang *et al.* 2018). The drawback is that neither of the cellulose fractions remain applicable in dry-jet wet spinning processes due to their low degree of polymerization.

Preferably, cellulose is thus dissolved in non-derivatizing solvents such as ionic liquids and NMMO as they enable to ensure the preservation of its macromolecular structure (Brinks *et al.* 2013; Negulescu *et al.* 1998). After dissolution, polyester can be recovered through simple filtration procedures to be fed back into conventional recycling processes (Silva, Wang & Byrne 2014). This concept has yet been demonstrated utilizing 1-allyl-3-methylimidazolium chloride, 1-butyl-3-methylimidazolium chloride, 1-butyl-3-methylimidazolium acetate as well as NMMO (Silva, Wang & Byrne 2014; Lv *et al.* 2015; Negulescu *et al.* 1998; Brinks *et al.* 2013). Although these methods could show a successful separation of cotton and polyester, neither of them has so far been able to spin textile grade fibers from the separated cellulose solutions.

The absence of a proof of concept can mainly be attributed to the vast heterogeneity of blended textile waste. Similar to pure cotton, blended, cellulose rich waste garments demand appropriate pretreatment conditions, which should display a minor impact on the polyester fractions. Unfortunately, this aspect has not been incorporated sufficiently into recent studies.

3.2.3. Textile Dyes

The global production of textile dyes exceeds more than 80 000 tons annually, of which 70% amount potentially cancerogenic azo dyes that are hardly biodegradable, and detrimental to fauna and flora. 10-15% thereof disappear as effluents during the manufacturing of clothing (Hassaan & El Nemr 2017).

The chemical recycling of dyed waste garments offers two possible pathways including either the removal or the preservation of the colorant. On an industrial level, worn out garments are preferably bleached before being reprocessed to new textile fibers because of aesthetical and sanitary concerns. As subsequent redyeing is inevitable, this approach demands more processing steps causing a higher consumption of chemicals and water. In contrast, the translation of the color from the waste substrate to the new cellulose product can decrease the environmental footprint of upcycling substantially (Terinte *et al.* 2014).

The dry-jet wet spinning of colored cellulose waste resembles spin dyeing, a technology regularly employed for the mass coloration of synthetic fibers. Therein, the dye present in the substrate should neither impair the dissolution in the solvent, nor restrict the formation of filaments during extrusion (Tawiah & Asinyo 2016). Moreover, the dye is required to coagulate together with the formed filaments to prevent an extensive contamination of the spinbath. Accordingly, spun-dyed cellulose fibers have yet been colored with dyed cotton waste, inorganic pigments, and vat dyes (Ruef 2000; Bartsch & Ruef 1999; Bechtold & Manian 2006; Manian, Ruef & Bechtold 2007; Eltz 1995).

In particular, Indanthrenes exhibit a good thermal and chemical stability because of their aromatic structure (Mahapatra 2016). In general, vat dyes are water insoluble, but when converted to their reduced leuco form, they can be dissolved in water under alkaline conditions (s. Figure 6). Atmospheric oxygen or peroxides consequently precipitate the dyes on the cellulose structure (Chattopadhyay 2011).

Figure 6. Chemical reactions during vat dyeing as described in (Chattopadhyay 2011). Copyright (2020) Elsevier.

Although this results in an excellent substantivity and wash fastness in conventionally dyed textiles, this can represent a challenge in regenerated fiber processes. The redox activity of NMMO or certain ionic liquids can trigger a destabilization of the dyes accompanied by the formation of peroxides degrading the cellulose structure (Chattopadhyay 2011). Additionally, the limited solubility of vat dyes can also contribute to the formation of solid aggregates in the spin dope and the coagulation bath (Bartsch & Ruef 1999; Bechtold & Manian 2006).

Until the end of the post-war era, about one-half of the cellulose fibers were dyed with indigo and vat dyes. Nowadays, they have partly been replaced by cheaper and chemically more stable reactive dyes. Reactive dyes are composed of a solubilizing unit, a chromophore and a reactive group connected via a bridging unit (s. Figure 7). Dependent on the reactive group, they form covalent bonds with the hydroxyl groups of cellulose via nucleophilic substitution (i.e. halotriazines, or haloquinoxalines in Levafix dyes) or addition reactions (i.e. vinylsulfone groups in Remazol dyes) (Mahapatra 2016). Overall, reactive dyes can withstand color removal treatments better than direct dyes (Määttänen *et al.* 2019), and colorants with anthraquinone units in particular were shown to have a high tolerance towards commercial laundering and oxidative bleaches (Bigambo *et al.* 2018). To a certain degree, the strong covalent bonding of reactive dyes also tends to cross-link the cellulose structure, which can affect the final solubility of colored cellulose waste in ionic liquids or NMMO (Chattopadhyay 2011).

Figure 7. Chemical structure of C. I. Reactive Blue 109 with chromogen, bridging group, and reactive group as depicted by (Mahapatra 2016). Copyright (2020) Woodhead Publishing India.

The dye exhaustion of reactive dyes is influenced by the functionality of the dye structure. In an acidic environment, reactive dyes can undergo irreversible hydrolysis, which decreases the dyeing efficiency especially in the case of monofunctional dyes. Their hydrolyzed form usually remains unreacted on the cellulose surface, where it reduces the color fastness after an insufficient boil-off (Mahapatra 2016). The resulting poor wet fastness may be a drawback during dissolution and coagulation as the unreacted dye may leach into spinbath requiring a clean out after the recycling process.

A short description of other important cellulose dyes such as direct, sulphur and azoic dyes is given in Appendix 1.

3.3. Dissolution of Cellulose in Ionic liquids and Dry-Jet Wet Spinning

Ionic liquids (ILs) have emerged as sustainable alternatives to the Lyocell and the potentially polluting Viscose technology. As their anions and cations can be arranged in more than 10^{18} different combinations (Holbrey & Seddon 1999), ILs can be tailored efficiently according to their desired applications. Cellulose dissolving ILs are characterized through bulky, asymmetric cations, and smaller anions with delocalized charge. This arrangement prevents a dense packing of the crystallites, which is responsible for their considerably low melting points ($<100^{\circ}\text{C}$). Because of strong electrostatic interactions, ILs also show a negligible vapor pressure and a high thermal stability, which allows their recovery through simple recycling procedures such as distillation (Meksi & Moussa 2017).

The first steps towards cellulose dissolution and fiber regeneration were made by Laus *et al.* and Bentivoglio *et al.* using a variety of imidazolium-based chlorides. In particular, 1-allyl-3-methylimidazolium chloride [AMIM] [Cl] and 1-butyl-3-methylimidazolium chloride [BMIM] [Cl] were demonstrated to display promising properties for cellulose processing. Their application was yet accompanied by a considerable degradation of cellulose, which could only be prevented by the addition of stabilizers (Laus *et al.* 2005; Bentivoglio *et al.* 2006). In 2008, Hermanutz *et al.* proposed 1-ethyl-3-methylimidazolium acetate [EMIM] [OAc] as a non-corrosive alternative to the earlier suggested halide based ILs. The obtained fiber properties were similar to commercial Lyocell or Viscose dependent on the process conditions applied (Hermanutz *et al.* 2008). Similarly, Wendler *et al.* utilized [EMIM] [OAc], 1-butyl-3-methylimidazolium acetate [BMIM] [OAc], and their chlorine-based equivalents for fiber spinning reaching tensile strengths up to 53 cN/tex (Wendler *et al.* 2009). Overall, [EMIM] [OAc] represents the first-generation ionic liquid with the highest solvent power, but its spinnability is restricted by its relatively small spinning window for cellulose (Kosan, Michels & Meister 2008; Sixta *et al.* 2015).

Superbase-based ionic liquids have thus drawn considerable attention as they enable to compensate for these drawbacks. Developed by our collaborators at Helsinki University (Parviainen *et al.* 2014), especially 1-diazabicyclo[4.3.0]non-5-enium acetate [DBNH] [OAc] (i.e. Ioncell) was found to exhibit outstanding dissolution power for various cellulose substrates ranging from wood pulp, to paper, and waste cotton (Asaadi *et al.* 2016; Ma *et al.* 2018; Ma *et al.* 2016; Sixta *et al.* 2015; Michud *et al.* 2015). The spinning approach of the Ioncell process resembles the Lyocell technology, yet are its processing conditions milder and do not require any stabilizers (Sixta *et al.* 2015). In addition, its fibers properties were shown to exceed commercial Lyocell products (Michud *et al.* 2015; Asaadi *et al.* 2016), which places this technology in a high-quality sector with a large market potential.

3.3.1. Dissolution Mechanism

In a Lyocell-type process, cellulose dissolves according to different mechanisms based on the water content in the cellulose solvent mixture. At higher

concentrations of water (>19%) ballooning occurs before dissolution, while purer solvent fractions cause a direct, homogenous disintegration of the cellulose substrate (Cuissinat & Navard 2006).

The dissolution of cellulose relies on an increase of the intermolecular attraction forces between the solvent and the polymer, followed by a reduction of the interactions within the cellulose structure (Fink *et al.* 2001). In case of ionic liquids, this implies that hydrogen bonds between the polymer chains are disrupted, while an enhanced interaction between the anions and hydroxyl groups takes place. According to Novoselov *et al.*, the cation does not contribute to any direct interactions with the polymer, although it was found to compete for hydrogen bonds (Novoselov *et al.* 2007). On the contrary, Rabideau *et al.* suggested that the cation participates in the solvation process by establishing dispersion interactions between the apolar fractions of the polymer. In doing so, cations and anions can form larger chain networks along the cellulose strand, which eventually interact with both polar and non-polar domains in the molecule (Rabideau, Agarwal & Ismail 2014).

Subsequently, swelling induces a disruption of interchain hydrogen bonds between the hydroxyl groups of cellulose on the C3 and C6, accompanied by competitive hydrogen bonding within the cellulose structure and the protic cation (s. Figure 8).

Figure 8. Dissolution of cellulose with [DBNH][OAc] including competitive hydrogen bonding within the cellulose structure and the protic cation. Reprinted with permission from (Parviainen *et al.* 2013). Copyright (2020) Wiley.

A too pronounced acidity makes a cation a stronger hydrogen bond donor than the hydroxyl groups of cellulose, which weakens the enthalpy gain of the dissolution process, thereby reducing the solubility of cellulose in the respective IL. This is the reason why, for example, pyridine or Hunig Base based ILs fail to dissolve cellulose, while DBN, 1,8-diazabicyclo(5.4.0)undec-7-ene (DBU) or 7-methyl-1,5,7-triazabicyclo(4.4.0)dec-5-ene (mTBD) based ionic liquids solubilize cellulose efficiently (Parviainen *et al.* 2013).

This idea is further elaborated using solvent descriptors such as Kamlet Taft parameters. Therein, π^* highlights the polarizability of the solvent, whereas α and β describe its hydrogen bond acidity and basicity, indicating its ability to donate or accept hydrogen bonds, respectively. Hauru *et al.* found a linear correlation between the net basicity ($\beta-\alpha$) and β by investigating the solubility of cellulose in various solvent systems (s. Figure 9).

Figure 9. Solution window of various cellulose solvents and ionic liquids dependent on the net basicity ($\beta-\alpha$) and β according to (Hauru *et al.* 2012)

As mentioned before, the net basicity underlies the assumption that the hydrogen bond donor capacity of the cation influences the solubility of cellulose in the ionic liquid. Therefore, higher β values combined with lower acidity result in an increased solvent power yielding a solution window for cellulose in the range of $0.35 < \beta-\alpha < 0.9$, and $0.80 < \beta < 1.20$ (Hauru *et al.* 2012)

3.3.2. Rheological Properties of Cellulose Ionic Liquid Solutions

First of all, it is important to note that the rheological properties of cellulose IL solutions are determined by an interplay of solvent properties, cellulose concentration, and temperature. Dynamic strain sweep tests allow to determine the complex viscosity η^* as well as loss and storage modulus (G' , G'') dependent on the angular frequency (ω).

After extrapolation of η^* , the zero shear viscosity η_0^* can be obtained as a system descriptor employing the Cross or the Carreau model (Sammons *et al.* 2008). η_0^* increases with cellulose concentration and DP, while it is lowered by a rise in temperature (Chen *et al.* 2009; Sescousse *et al.* 2010). In a similar manner, less branched ILs tend to decrease the zero shear viscosity (Kosan, Michels & Meister 2008). Most IL solutions display a Newtonian plateau over a lower angular frequency range, while shear thinning occurs at elevated shear rates (Gericke *et al.* 2009) Therefore, with increased shear stress, the entanglements

between the polymer chains are diminished accompanied by a certain desolvation of the substrate. This can also be observed in the critical point for shear thinning, which shifts to lower frequencies with higher concentrations and DP (Chen *et al.* 2009).

Similarly, these factors influence the position of the crossover point of G' and G'' ($G'=G''$). In literature, $G'=G''$ is considered as the gelation point of a solution, indicating a change of its behavior from a viscous to an elastic state (Mezger 2018). For increased cellulose concentrations and lowered temperatures, this alteration takes place to lower shear rates as entanglements between the polymers are fostered (Sammons *et al.* 2008; Chen *et al.* 2009). The values of the dynamic moduli per se describe the nature of the molar mass distribution. High-values account for long, monodisperse polymer chains, while lower results indicate a broader distribution (Mezger 2006).

Concerning the Ioncell technology, cellulose solutions with broader molar mass distributions have been favored for fiber spinning, since a combination of short and long polymer chains provide fiber elasticity and high tensile strength (Michud, Hummel & Sixta 2015). In terms of rheology, this is embodied by $20\,000 < \eta_0^* < 30\,000$ Pa s, $2\,000 < G'=G'' < 4\,000$ Pa, and $0.5 < \omega < 1.3$ s⁻¹ (Michud *et al.* 2015; Ma *et al.* 2018; Ma *et al.* 2016; Asaadi *et al.* 2016).

3.3.3. Factors Influencing the Spinning Process

In 1964, Ziabicki *et al.* already concluded that any liquid can be drawn to filaments if appropriate process conditions are applied (Ziabicki & Takserman-Krozer 1964a). This hypothesis indicates that only two major factors limit the length of a filament, among them cohesion and capillary break. The latter is predominant in liquids with low viscosity, whereas the former primarily affects highly viscous solutions (Ziabicki & Takserman-Krozer 1964b). Cellulose solutions with spinnable concentrations are known to show a homogenous polymer distribution, which exhibit only negligible breaks of their microfluidic structure under increased shear stress (Haward *et al.* 2012).

During dry-jet wet spinning, a cellulose solution is extruded through a spinneret with small nozzles to form single liquid threads (s. Figure 10).

Figure 10. Scheme of lab-scale dry-jet wet spinning. Reprinted with permission from (Michud, Hummel & Sixta 2016). Copyright (2020) Wiley.

In the cylindrical capillaries of the nozzles, a pre-orientation of the cellulose chains occurs through shear forces, which is further enhanced when stretched in the air-gap. Therefore, the air-gap is crucial to structure formation. Along the liquid thread, downward from the spinneret until the coagulation bath, a temperature gradient is created that influences the diffusion of moisture into the filament structure. Due to considerably long relaxation times, the liquid thread adapts a gel like structure that fortifies the polymer orientation, which is finally locked in the coagulation bath (Fink *et al.* 2001).

The water triggers a phase separation, breaking down the interactions of the solvent and cellulose. Throughout diffusion, a lamellar nucleus is formed, eventually leading to a buildup of a crystalline, fibrillary structure (Fink *et al.* 2001). In NMMO and [DBNH] [OAc], this process starts with fast diffusion rates (93% and 77%) enhancing the creation of a polymer network. In contrast, poor dissolution states, as found in weak cellulose solvents or with high concentrations, lead to a gel-like character that prevents a reinforcement of the molecular orientation, eventually causing a bad spinnability of the substrate (Hauru *et al.* 2016).

Practically, this implies that the spinnability of cellulose solutions is determined by the extrusion velocity, the air-gap length, the draw ratio (DR), as well as by the humidity and temperature (Fink *et al.* 2001). Accordingly, Hauru *et al.* defined a spinning envelope for monofilament, dry-jet wet spinning (s. Figure 11)

Figure 11. Scheme of spinnable and unstable spinning conditions for monofilament dry-jet wet spinning with a length of diameter ratio of 2. Reprinted with permission from (Hauru *et al.* 2014). Copyright (2020) Springer.

High DRs are desirable in a spinning process, as they are accompanied with high fiber orientation and tensile strength, although no further enhancement happens after a certain benchmark (DR=6) (Michud, Hummel & Sixta 2016). Also the fiber crystallinity is marginally influenced by the take-up velocity, which is reflected in smaller alterations at lower DRs (Fink *et al.* 2001). As displayed, high DRs can neither be achieved by very fast extrusion speeds, nor by very low velocities. The latter induces a cohesive breakage of the filaments due to partial regeneration before entering the waterbath, whereas the former drives

the cylinder pressure over a critical limit (Hauru *et al.* 2016). However, it needs to be noted that the values displayed in Figure 11 only apply for a distinct experimental set-up and may vary once larger spinnerets are used. It is likely that an optimization of the length to diameter ratio may yield higher optimal extrusion velocities than discussed by Hauru *et al.*

Ultimately, temperature and type of the spinbath also contribute to the structure formation. In contrast to water, milder anti-solvents, such as ethanol or isopropanol, result in longer relaxation times, which positively affect the fiber elasticity (Fink *et al.* 2001), although they can decrease the tensile strength and promote technical problems due to explosive mixtures. A comparable effect is observed with low spin bath temperatures. Lower diffusion rates trigger the formation of a stronger liquid core in the filament that is able to withstand deformation forces better than fibers regenerated at elevated temperatures (Michud, Hummel & Sixta 2016).

3.4. Surface Plasmon Resonance

The utilization of surface plasmon resonance dates back to late antiquity, where the outstanding optical properties of noble metal nanoparticles were employed to introduce color in so-called “gold ruby glass” (Louis & Pluchery 2012). The most prominent example is the Lycurgus cup, an ancient Roman artefact, manufactured in the 4th century AC. When light penetrates its glass from the front, the cup appears green, while illumination from the back colors it red. These distinct appearance originates from an alloy of gold and silver nanoparticles in the artefact (Hornyak *et al.* 1997). It is questionable whether manufactures during this time were yet fully aware of how to prepare nanoparticles from silver or gold. Nowadays, surface plasmon resonance is well understood. Since the 1990s, this field has grown tremendously with 6572 articles published in 2019 (Louis & Pluchery 2012) (ISI Web of Knowledge, search word “plasmon” Feb. 13, 2020).

Localized surface plasmon resonance occurs when the size of a particle is much smaller than the wavelength of incident light. This usually applies to substrates in the nano range between 1-100 nm. Noble metals exhibit an electron cloud around their core, moving freely on the metal surface. The electromagnetic field induced by light causes a polarization of the surface electrons around the nanoparticles (s. Figure 12). The created surface charge is opposed to the electromagnetic field of the exciting radiation, which consequently triggers a restoration force due to Coulomb interactions between the electrons and the nuclei (Kelly *et al.* 2003). In case of particles larger than their atomic, mean free path, light scattering and heat emission may weaken the emerging oscillation. Below this size, no scattering takes places and the absorption peaks of the nanoparticles appear more pronounced (Eustis & El-Sayed 2006).

Figure 12. Schematic illustration of surface plasmon resonance occurring in spherical nanoparticles. Reprinted with permission from (Kelly *et al.* 2003). Copyright (2020) ACS Publishing.

The absorption of light also depends on the electron density, the dielectric constant of the surrounding medium, the type of metal, and the aspect ratio of the nanoparticles (Kelly *et al.* 2003; Hutter & Fendler 2004). This relation is expressed by a simplified version of the Mie theory describing the extinction cross section σ_{ext} of a particle with a size far below the wavelength of incident light.

$$\sigma_{ext}(\omega) = 9 \frac{\omega}{c} \varepsilon_m^{3/2} V_0 \frac{\varepsilon_2(\omega)}{[\varepsilon_1(\omega) + 2\varepsilon_m]^2 + \varepsilon_2(\omega)^2} \quad (8)$$

ω denotes the angular frequency of the exciting radiation, V_0 the particle volume $\left(\frac{4\pi}{3}\right)R^3$, ε_m the dielectric constant of the chemical environment, and ε_1 and ε_2 the real and imaginary contributions of the dielectric function (Kreibig & Vollmer 1995). A surface plasmon band becomes visible either when $\varepsilon_1(\omega) = -2\varepsilon_m$, $\varepsilon_2(\omega)$ is relatively low, or displays a weak dependency on ω . This equation does not account for the particle size, which thus requires to be compensated for with size dependent dielectric constants (Hutter & Fendler 2004).

However, the impact of the particle size on the apparent color of the nanoparticles is comparably small. Anisotropy has a significantly larger influence on the location of the surface plasmon band in the absorption spectrum. This phenomenon is described by Gan's dipole approximation, which is an extension of the Mie theory (Perez-Juste *et al.* 2005). The concept indicates that nanoparticles with a high aspect ratio tend to show two separate surface plasmon bands. As implied in Figure 13, the transverse surface plasmon band occurs at a similar position as the peak for spherical nanoparticles (i.e. around 520 nm for Au, and 420 nm for Ag), while the longitudinal signal can be found at longer wavelengths (Eustis & El-Sayed 2006; Rehan *et al.* 2015). As the latter shows a stronger resonance, anisotropic nanoparticles display a wider range of colors compared to spherical particles.

Figure 13. Collective oscillation of surface electrons in gold nanorods (a), and the resulting transverse and longitudinal surface plasmon band (b). Reprinted with permission from (Cao, Sun & Grattan 2014). Copyright (2020) Elsevier.

3.5. Cellulose Nanoparticle Composites

The demand for more sustainable alternatives in textile industry has also accelerated the research on composites of cellulose fibers and nanoparticles. For example, the UV protection factor (UPF) of cellulosic textiles per se is very low, so that clothing often represents an insufficient protection from sunlight (Gambichler *et al.* 2001). However, small amounts of nanogold or silver, usually in the lower ppm range, have been shown to render these textiles UV protective (Tang *et al.* 2014; Zheng *et al.* 2013). The same applies for the antibacterial activity of cellulosic textiles, where silver particles in particular have been proven effective against various stems of bacteria (He, Kunitake & Nakao 2003; Johnston & Nilsson 2012; Kim, Park & Lee 2011; Tsai *et al.* 2017).

Recently, studies have also focused on the use of nanogold and silver as textile dyes, employing anisotropic nanoparticles with a specific aspect ratio (Zheng *et al.* 2013; Tang *et al.* 2012). The current state of the art mainly involves four technologies to combine cellulose and noble metal nanoparticles. Among them, electrostatic assembly (Dong & Hinstroza 2009; Yu *et al.* 2018; Tang *et al.* 2012), seed mediated synthesis followed by dip coating (Zheng *et al.* 2013), *in-situ* reduction (Tang *et al.* 2014; Tang *et al.* 2015a; Boufi *et al.* 2011; Bumbudsanpharoke & Ko 2015; Cai *et al.* 2009), and the incorporation of nanoparticles via dry-jet wet spinning (Chen *et al.* 2015; Kulpinski 2007; Rac-Rumijowska *et al.* 2017; Smiechowicz *et al.* 2011; Smiechowicz *et al.* 2018; Smiechowicz *et al.* 2014; Wendler *et al.* 2008).

3.5.1. Seed Mediated Synthesis and Dip Coating

Gold nanorods are prepared via a growth and a seed solution. The latter consists of a cationic Au reagent (e.g. HAuCl_4 or NaAuCl_4), a reducing agent (e.g.

NaBH_4), and a surfactant (e.g. CTAB) (Nikoobakht & El-Sayed 2003). The surfactant is supposed to act as a template, and needs to stabilize the generated nanoparticles in the aqueous media (Smith & Korgel 2008). The growth solution contains noble metal ions, AgNO_3 for shape control, as well as CTAB, and ascorbic acid as a weak reducing agent. To initiate the synthesis of Au nanorods, the seed solution is combined with the growth solution (Nikoobakht & El-Sayed 2003). The particles' size and aspect ratio can be fine-tuned either by oxidation, or by the addition of more HAuCl_4 (Zheng *et al.* 2013), or by changing the choice and concentration of the surfactant (Gao, Bender & Murphy 2003; Jana, Gearheart & Murphy 2001; Nikoobakht & El-Sayed 2003; Smith & Korgel 2008).

Once prepared, the nanoparticle dispersions can be used to coat textile fabrics by immersion. The particles remain on the surface of the polymer due their electrostatic interactions with the functional groups of cellulose (s. Figure 14). The fabrics can be dyed with nanoparticles over the entire visible spectrum, providing shielding from UV light and antibacterial activity, unfortunately accompanied by mediocre wash fastness due to the relatively weak bonding forces to the polymer surface (Zheng *et al.* 2013).

Figure 14. SEM image of cotton (A-H) and silk (J-Q) fabrics with and without Au nanorods, as well as photographs of the respective cotton (I) and silk fabrics (R). Reprinted with permission from (Zheng *et al.* 2013). Copyright (2020) RSC Publishing.

3.5.2. Electrostatic Assembly

The electrostatic assembly of nanoparticles utilizes the interactions between a positively charged cellulose substrate and noble metal nanoparticles with negative zeta potential. Cellulose usually shows a negative surface charge, but can be

rendered cationic via grafting with polyelectrolytes (Yu *et al.* 2018; Dong & Hinestroza 2009; Tang *et al.* 2012). Figure 15 displays the coating mechanism as proposed by Tang *et al.* 2012.

Figure 15. Proposed mechanism of electrostatic assembly as conducted by (Tang *et al.* 2012). Reprinted with permission from (Tang *et al.* 2012). Copyright (2020) American Chemical Society.

In this method, cotton fibers were combined with anisotropic silver nanoparticles using poly (diallyldimethylammonium chloride) (PolyDADMAC) as a grafting agent. The synthesis procedure resembles an approach published by Métraux & Mirkin 2005, where Ag^+ is reduced to nanoparticles by adding NaBH_4 to an aqueous solution of AgNO_3 , sodium citrate, polyvinylpyrrolidone, and H_2O_2 , while achieving size and shape control by distinct amounts of reducing agent (Métraux & Mirkin 2005; Tang *et al.* 2012).

In a similar manner, Dong *et al.* assembled Au and Pd nanoparticles on cotton fabrics using (2,3-epoxypropyl) trimethylammonium chloride (Dong & Hinestroza 2009). A recent study also grafted regenerated Ioncell fibers spun from recycled waste paper, where the positive charge was introduced by glycidyltrimethylammonium chloride under strong alkaline conditions (Yu *et al.* 2018). Despite presumably stronger interactions, electrostatic assembly has not been demonstrated to significantly improve the wash fastness of nanoparticles compared to dip coating (Tang *et al.* 2012).

3.5.3. *In-situ* Reduction

An *in-situ* reduction combines both nanoparticle preparation and composite formation in one synthesis step. The advantages are evident. The formed nanoparticles show a considerably high stability, while saving time and resources. As the chemical environment limits their aspect ratio, samples prepared by this approach exhibit less variety in shape, size and color.

With Conventional Reduction Chemicals

As in the previous methods, reducing agents involving NaBH_4 (Shin *et al.* 2008; He, Kunitake & Nakao 2003; Cai *et al.* 2009; Koga *et al.* 2010), sodium

citrate (Rehan *et al.* 2015), sodium hydroxide (Emam *et al.* 2014), triethanolamine (Barud *et al.* 2008), or poly(ethyleneimine) (Zhang *et al.* 2010) are required to convert metal ions of silver and gold to their reduced form. However, this takes place while the respective textiles are immersed in the reaction mixture, where the functional groups of cellulose stabilize the metal ions through complexation.

The stabilization can be enhanced by the reducing agents, which can form crosslinks between the cellulose structure and the respective nanoparticles (cf. poly(ethyleneimine)) (Zhang *et al.* 2010). In an alkaline environment, swelling and subsequent shrinking of cellulose can also contribute to an entrapment of the nanoparticles in the polymer structure (Emam *et al.* 2014). These approaches have been conducted with cellulose nanofibers and crystals (Koga *et al.* 2010; Shin *et al.* 2008), bacterial cellulose (Barud *et al.* 2008; Zhang *et al.* 2010), cotton (Bacciarelli-Ulacha *et al.* 2014; Rehan *et al.* 2015), and Viscose (Emam *et al.* 2014) applying various metal substrates such as silver, gold, platinum and palladium. Most studies observed a noticeable loss of nanoparticles throughout laundering, which was nonetheless below the amounts described for dip coating and electrostatic assembly (Rehan *et al.* 2015).

With Cellulose as Reducing Agent

Under adequate process conditions, cellulose substrates can replace conventional reducing and stabilizing agents due to their ability to chelate nanoparticles in their polymer structure (Vigneshwaran *et al.* 2007; Tang *et al.* 2012). In a hydrothermal environment, cellulosic components can reduce metal ions to their elementary form, by using the terminal reducing end groups of cellulose. It has been argued about whether residual lignin plays a key role in this type of reaction as its hemiacetal and aldehyde groups are supposed to simultaneously reduce and stabilize the nanoparticles (Bumbudsanpharoke & Ko 2015). Other studies have highlighted the importance of sulphur and nitrogen containing units as they can provide additional binding centers for the metal ions during synthesis (Johnston & Nilsson 2012).

For low lignin substrates, the right pH seems crucial for quantitative nanoparticle yields. Whereas acidic conditions were shown to be beneficial for Au, Ag requires an alkaline environment to be converted to its reduced form (Tang *et al.* 2015b). The same applies for the mercerization of cotton, which was found to have a positive impact on both the color strength and yield of silver nanoparticles (Tang *et al.* 2013). In synthesis procedures, where a pH adjustment was avoided, higher nanoparticle yields were achieved through harsher reaction conditions, such as high pressure and elevated temperatures (Bumbudsanpharoke & Ko 2015; Vigneshwaran *et al.* 2007). For example, Tang *et al.* 2015a coated bamboo pulp with gold and silver nanoparticles under neutral conditions, but inferred that a change in the pH was observed to enhance the nanoparticle synthesis (Tang *et al.* 2015a). Overall, cellulose products coated with this procedure exhibited a better wash fastness than those obtained from the methods listed above, even after several washing cycles (Tang *et al.* 2013; Tang *et al.* 2015a).

3.5.4. Incorporation via Dry-Jet Wet Spinning

In fiber spinning, the incorporation of nanoparticles has so far been restricted to silver nanoparticles. In 2007, Wendler *et al.* for the first time discussed the addition of silver nanoparticles to a Lyocell type spin dope to obtain antimicrobial regenerated fibers (Wendler *et al.* 2007). This idea was also patented a year later (Wendler *et al.* 2008), and has recently been transferred to cellulose ionic liquid systems (Chen *et al.* 2015). Several other studies followed this approach indicating that silver nanoparticles could also be synthesized *in-situ* during the preparation of the spinning solution. This implies that AgNO_3 is added to an aqueous solution of NMMO, which is then left in a darkroom for several hours. Afterwards, the solution is used to dissolve cellulose pulp under standard conditions, which is then dry-jet wet spun to man-made cellulose fibers (Kulpinski 2007; Smiechowicz *et al.* 2011; Rac-Rumijowska *et al.* 2017; Smiechowicz *et al.* 2018; Smiechowicz *et al.* 2014). As dissolution and regeneration entraps the nanoparticles in the fiber matrix, the metal cellulose composites are assumed to release less silver than any other methods described before (Chen *et al.* 2015).

4. Materials and Methods

4.1. Cellulose and Polyester Based Raw Materials

Table 3 summarizes the cellulose and polyester based raw materials employed in this thesis according to a consecutive numbering. Birch prehydrolyzed kraft pulp (S1) was used for the preparation of cellulose fibers coated with noble metal nanoparticles (Paper IV). Virgin cotton fibers (S2) and polyester (S3) as well as cotton polyester blends (S4-9) contributed to the establishment of a quantification method for blended textile waste (Paper I). In Paper II, pretreated post-consumer cotton polyester blends (S10) were separated by the means of the Ion-cell technology, while PET fibers (S25) were suspended in [DBNH] [OAc] to study the degradation behavior of PET in the ionic liquid. Paper III utilized pre- and post-consumer cotton fabrics (S11-12) to investigate the impact of different vat and reactive dyes on the recyclability of cotton waste garments. Mixed post-consumer cotton waste (S16) was also recycled to new MMCFs in the unpublished results sections. Tencel (S13) and Viscose fibers (S14) were added as references to all studies.

4.1.1. NMR Standards

Ground, air-dried cotton (S2) and polyester (S3) were mixed in a rotavapor (3h) to obtain distinct blend concentrations (i.e. 2.5%, 10%, 25%, 50%, 75%, and 90% CO). The dry matter content was also taken into consideration.

4.1.2. Pretreatment of Cotton Polyester Blends

Post-consumer cotton polyester blends (S10) were shredded and pretreated according to an Ew-disk refining-Z-P-A sequence at VTT (Finland). Ew denotes an alkaline washing stage to remove residual silicate, while P and Z targeted to adjust the samples' DP and whiteness by hydrogen peroxide and ozone treatment. The letter A describes acid washing to reduce metal contaminations.

4.1.3. Pretreatment of Pre-Consumer Cotton

White pre-consumer cotton (S11) was subjected to three types of pretreatment including acid hydrolysis (A), a combination of acid washing and enzymes (EG-A, A-EG), and electron beam irradiation (e-beam).

Table 3. Summary of the cellulose and polyester based raw materials used in this thesis including supplier, cellulose and PET content, color and treatments.

	Sample	Supplier	Cell / wt%	PET / wt%	Color	Treatments	Paper
S1	PHK pulp	Stora Enso (Finland)	100	-	white	Au- and AgNP coatings	IV
S2	White CO	Söktas (Turkey)	100	-	white	-	I
S3	White PET	HT Sport Oy (Finland)	-	100	white	-	I
S4	IGALO	Tekstina (Slovenia)	50	50	white	-	I
S5	IGALO-TPPT	Tekstina (Slovenia)	50	50	white	-	I
S6	IGALO-KM	Tekstina (Slovenia)	65	35	white	-	I
S7	RED SHIRT	Second Hand (Finland)	17	83	red & white	-	I
S8	BROWN SHIRT	Second Hand (Finland)	60	40	brown	-	I
S9	WHITE SHIRT	Second Hand (Finland)	35	65	white	-	I
S10	Post-consumer CO/PET	Soex (Germany)	50	50	colored	Ew-disk-P-Z-A	II
S11	Pre-consumer CO	Iisalmen Kangastukku (Finland)	100	-	white	Indanthren Blue BC 3%, e-beam, A, EG-A, A-EG	III
S12	Post-consumer CO	Uusimaa Hospital Laundry (Finland)	100	-	white	Indanthren Brilliant Red FBB, Indanthren Brilliant Green FBB Coll, Remazol Black B gran 133%, Remazol Brilliant Blue R spec, Levafix Brilliant Red E-4BA, Levafix Blue E-GRN gran	III
S13	Tenocel 1.3 dtex	Lenzing AG (Austria)	100	-	white	-	I, II, III, IV
S14	Viscose 1.3 dtex	Kelheim (Germany)	100	-	white	-	I, II, III, IV
S15	PET fibers 3.3 dtex	Swerea IVF (Sweden)	-	100	white	-	II
S16	Post-consumer cellulose waste	Texaid	100	-	colored	A, or blending	Unpubl.

(A): Ground cotton was dispersed in a 0.27 M solution of sulphuric acid (H_2SO_4 , 95-97%, Merck or Sigma) and mixed vigorously at 82°C for 7-9 min. The sample to liquor ratio amounted 3:100. Once a viscosity of 450±50 ml/g was reached, the sample was filtered off and washed with cold water until a neutral pH was obtained.

(EG-A, A-EG): The pretreatment sequences EG-A and A-EG were performed at VTT (Finland). Accordingly, pre-consumer cotton was treated with Ecopulp R (Ecopulp R, 25 wt% endoglucanase, AB Enzymes, Finland) in an enzyme to pulp ratio of 10 mg/g (4h, 50°C). Similar to A, 2 wt% of shredded cotton (S11) were first soaked in water and then dewatered to increase the activity of the enzyme. The hydrolysis reaction was stopped by heating the cotton substrate to 90°C for 30 min followed by subsequent cooling and rinsing with deionized water. Concerning the acid treatment, both cotton and water were heated to 90°C separately and then mixed to obtain a consistency of 10 wt% (oven dry cotton/water). Subsequently, 0.45 wt% of 0.5 M H_2SO_4 (H_2SO_4 /oven dry cotton) were added to the mixture. After the dispersion had been stirred at 90°C for 2h, the reaction was stopped by reducing the sample's consistency to 5 wt% (oven dry cotton/water) followed by dewatering and rinsing with cold, deionized water.

(e-beam): Leoni Studer AG (Switzerland) conducted the electron irradiation treatments using a 10 MeV accelerator. Different e-beam dosages (5-30 kGy) were applied on an intact, stack of cotton fabrics to obtain a target viscosity of 450±50 ml/g.

4.1.4. Viscosity Adjustment and Pretreatment of Samples (S16) from Unpublished Results

(a) Two samples of high and low viscosity were mixed based on the following equation,

$$450 \frac{\text{ml}}{\text{g}} = \frac{\eta_n \cdot n + \eta_m \cdot m}{n + m} \quad (9)$$

where $450 \frac{\text{ml}}{\text{g}}$ represents the targeted viscosity for dry-jet wet spinning, η_n and η_m denote the initial viscosities of the raw materials, while n and m refer to the respective amounts of sample in wt%. (b) Three samples with a viscosity higher than the targeted viscosity were treated with 0.2 M H_2SO_4 with a liquor to pulp ratio of 100:3 at 60°C. The duration ranged from 15-30 min dependent on the respective starting viscosity. (c) Two samples obtained in (b) were blended with PHK pulp (50:50) to improve the spinnability.

4.1.5. Vat Dyeing

Indanthren Blue BC 3% was purchased from Wennström Oy (Finland), whereas Indanthren Red FBB coll and Indanthren Green FBB were supplied by DyStar (Germany). Vat dyeing was performed in 1 kg batches using white pre-

and post-consumer cotton fabrics (S11-12). Accordingly, 20 l of water were heated in a kettle (50°C) followed by the dissolution of $\text{Na}_2\text{S}_2\text{O}_4$ (3 g/ml), $\text{Na}_2\text{SO}_4 \cdot 10 \text{ H}_2\text{O}$, and 25 wt% of NaOH. Subsequently, 2 wt% of Indanthren dye (on the oven dry weight of the cotton substrates) were added to the mixture, which was stirred until the complete dissolution of all chemicals. The cotton fabrics were immersed in the dye bath (45 min) under continuous mixing. Once exposed to atmospheric oxygen, the dyes were oxidized to their water insoluble form and stabilized on the cotton fabric. Consequent washing of the samples with water and hydrogen peroxide (2 ml/l) further fortified the wash fastness of the dyes on the cellulose structure. Finally, the samples were dried at room temperature.

4.1.6. Reactive Dyeing

1 kg batches of post-consumer fabrics (S12) were dyed with Levafix Brilliant Red E-4BA, Levafix Blue E-GRN gran (both DyStar, Germany), Remazol Brilliant Black B gran 133%, and Remazol Brilliant Blue R Spec (both Wennström Oy, Finland). The dyeing procedure was performed in a laundering machine (Esteri Pesukoneet Oy, Finland) following a program of prewetting + gentle spin – dyeing – rinsing – boiling – rinsing – spin. The temperature was set to 60°C and the amount of water used was 20 l. In each case, the concentration of the dye was 2 wt% concerning the oven dry weight of the fabric, employing a sample to liquor ratio of 1:20 kg/l. The addition of $\text{Na}_2\text{SO}_4 \cdot 10 \text{ H}_2\text{O}$ (50 g/l) was supposed to enhance the interactions between the cellulose structure and the dye, while Na_2CO_3 (9 g /l) was applied to create alkaline conditions. As for the vat dyeing procedure, the samples were air-dried before further being processed.

4.1.7. Coating of PHK Pulp with Noble Metal Nanoparticles

50 mM aqueous seed solutions were prepared from $\text{HAuCl}_4 \cdot 3\text{H}_2\text{O}$ (99%, Sigma, USA) and AgNO_3 (99%, Sigma, USA). Air-dried PHK pulp (S1) was soaked in water in a sample to liquor ratio of 1:80 (ml/g) using 1 l, wide-neck Schott bottles. The pulp-water suspension was shaken for 15 min to guarantee a full disintegration of the pulp. Afterwards, the seed solutions (0.06 ml/g, 50 mM) were injected into the dispersion. To synthesize AgAu nanoparticles, a combination of AgNO_3 and HAuCl_4 (0.03 ml/g, 50mM, respectively) was added. The resulting samples were transferred to an oven (135°C) to generate noble metal nanoparticles (Bumbudsanpharoke & Ko 2015). The efficiency of the reaction was estimated by the progressing color change from white to yellow (Ag: 15h), or white to purple (Au: 2h and AgAu: 2h). After the mixture was cooled to room temperature, the nanoparticle-coated pulp was filtered off, rinsed with water, and dried in an oven at 45°C.

4.2. Dissolution of Cellulose in [DBNH] [OAc] and Dry-Jet Spinning

4.2.1. Synthesis of [DBNH] [OAc]

[DBNH] [OAc] was synthesized via a neutralization reaction of 1,5-diazabicyclo(4.3.0)non-5-ene (DBN, 99%, Fluorochem, UK) and glacial acetic acid (HOAc, 100%, Merck, Germany). DBN was poured into a thermally controlled reactor (30°C) and HOAc was added dropwise under constant stirring. Afterwards, the mixture was slowly heated to 70°C (30 min) to further promote the conversion of the reactants to [DBNH] [OAc].

4.2.2. Separation of Cotton and Polyester

The separation of cotton and polyester was composed of three process steps (s. Figure 16). 13 wt% ground and pretreated post-consumer cotton polyester fabrics ((S10), 50% CO) were dispersed in [DBNH] [OAc] in a vertical kneader system (80°C). After mixing for 1 h, the cellulose component had dissolved in the IL yielding a 6.5 wt% cellulose solution, which could be separated from the solid polyester residue via filtration (70 °C, 1–8 MPa, metal filter mesh with 5–6 µm absolute fineness, Gebr. Kufferath AG, Germany). The cellulose solution was molded into cylindrical shape and stored in a refrigerator (8°C) upon solidification. The PET fraction was extracted with [DBNH] [OAc] twice to lower its contamination with residual cellulose and was then washed with water to remove the IL. To prepare a spin dope with a higher cellulose concentration, the obtained 6.5 wt% solution was transferred back to the kneader and suspended with additional raw material to yield a 10.5 wt% cellulose solution after stirring (1h, 80°C). Filtering and washing of the mixture were conducted as explained before.

Figure 16. Simplified process scheme for the separation of cotton and polyester in the loncell process. Image copied from Paper II (Haslinger *et al.* 2019b).

As further elaborated in the following sections, [DBNH] [OAc] can degrade the molecular structure of PET. This degradation could be reduced by replacing [DBNH] [OAc] by a 1:1.3 mixture of DBN and HOAc, which however had a negative impact on the spinnability of the resulting cellulose solution.

4.2.3. Dissolution of Colored Textile Waste and Nanoparticle Coated PHK Pulp

Ground cotton and Viscose fabrics (S10-11, S16) or nanoparticle coated PHK pulp (S1) were dissolved in [DBNH] [OAc] under standard conditions (vertical kneader, 13-14 wt%, 80°C, 90 min). Afterwards, the resulting cellulose solutions were filtered and stored as stated in 4.2.2.

4.2.4. Dissolution Studies of Dyes and Dyed Textiles in [DBNH] [OAc]

Small amounts of the dyes described in 4.1.5 and 4.1.6 were dispersed in [DBNH] [OAc] and stirred for 1 h at elevated temperatures (80°C). A small amount of the obtained suspension was transferred to a glass slide and evaluated under a heating stage microscope (80°C, Zeiss Axio Scope A1, Zeiss AG Germany). In a similar manner, small samples of the spin dopes prepared from colored cotton waste (cf. 4.2.4.) were placed onto glass slides and analyzed for undissolved material.

4.2.5. Dry-Jet Wet Spinning

The cellulose solutions were transferred into a lab-scale piston-spinning unit (Fourné Polymertechnik, Germany) and heated to temperatures between 60-80°C based on their rheological properties. The dopes were extruded through multihole spinnerets (36 holes for CO/PET separation, 200 holes for dyed cotton waste and nanoparticle coated pulp, or 18, 36, and 200 holes for mixed cellulose based textile waste in the Unpublished Results section) with a diameter of 0.1 mm and a capillary length of 0.02 mm. After extrusion, the liquid threads were extended in a 1 cm air-gap ($DR = v_{\text{take-up}}/v_{\text{extr.}} = 4-12$, cf. Table 4) before they were coagulated in water ($\sim 10^\circ\text{C}$).

Table 4. Summary of the spinning conditions such as draw ratio (DR), number of holes, extrusion velocity ($v_{\text{extr.}}$) and take-up velocity ($v_{\text{take-up}}$).

Sample	DR	Holes	$v_{\text{extr.}}$	$v_{\text{extr.}}$	$v_{\text{take-up}}$
			/ cm^3/min	/ m/min	/ m/min
COPET_6.5	8.0	36	1.6	5.7	45.5
COPET_6.5_HOAc	4.0	36	5.0	17.7	71.0
COPET_10.5	8.8	36	1.6	5.7	50.0
Indanthren Blue BC 3%	12	200	5.5	3.5	42.0
Dyed Post-consumer Cotton	12	200	5.5	3.5	42.0
Pulp with Nanoparticles	12	200	5.5	3.5	42.0
Mixed Cellulose Waste	12	18, 36, 200	0.4-5.5	1.4-5.6	17.0-68.0

In case of lower cellulose concentrations (i.e. 6.5 wt%), it was found beneficial to maintain higher extrusion speeds than under standard conditions (13-14%) to avoid aggregate formation or adhesion of the spinning solution on the spinneret surface. The spun filaments were shortened to 4 cm staple fibers, disentangled by hand, and immersed in water (80°C, 2h).

4.3. Yarn Spinning, Knitting and Demonstration Products

4.3.1. Spin Finishing

A 0.25 wt% spin finish (Leomin PN/Aflian CVS (80:20), Achroma, Switzerland) was applied onto the fibers produced from the solutions described in 4.2.5. After the finishing chemicals (20 ml/ g of oven dry fibers) had fully dissolved in water (50°C), the staple fibers were immersed in the solution followed by vigorous stirring of the mixture (5 min). Consequently, the fibers were separated from the finishing solution and dewatered to reach 400 % of their oven dry weight. After drying at room temperature, the single fibers were separated with a fiber opening device (Trash Analyzer 281C Mesdan Lab, Mesdan S. p. A. Italy).

4.3.2. Yarn Spinning

Before the actual yarn spinning process, all staple fibers (spin-finished) were exposed to a relative humidity of 65% (20°C) overnight. Afterwards, carding (Carding Machine 337A, Mesdan, Italy for the fibers spun from post-consumer cotton, and AgNP coated pulp, or Automatex, Italy for the fibers spun from pre-consumer cotton, mixed cellulose waste, PHK pulp, AuNP-, and AgNP- coated pulp) produced a thin fiber web that was further drafted to a sliver (Stiro Roving Lab 3371, Mesdan Lab, Mesdan S.p. A, Italy for the fibers spun from pre-consumer cotton, mixed cellulose waste. PHK pulp, AuNP- and AgAuNP- coated pulp, or Ring Lab 82BA, Ser.Ma.Tes Srl, Italy for the fibers spun from post-consumer cotton, and AgNP coated pulp). The sliver was then twisted in Z direction with 700 twists per meter to obtain yarns with target linear densities of 18-22 tex.

4.3.3. Fabrics from Dyed Cotton Waste

After plying, the yarns from pre- and post-consumer cotton waste were knitted to single jersey fabrics (150 g/m², Stoll CMS ADF 32W E7.3 multi gauge, Stoll, Germany). The same machinery was used to produce a baby-jacket demonstrator from regained, Indanthren Blue BC 3% dyed pre-consumer cotton yarn. The fabric was knitted in an interlock structure (127 g/m²) with a single thread yarn (18 tex Z 700). For the sleeve cuffs, a 2x1 rib-knit was used, which employed a plied yarn composed of two single threads (18 tex Z700 x t_o). The fabrics were steam ironed and bound on the edges with commercially knitted Viscose shaped into a narrow band. The sewing was conducted with lab-scale prototyping equipment. Furthermore, a scarf was knitted from plied Remazol Brilliant Blue R spec yarn (22 tex Z/00 X 2 S 300) using a mixed purl and lace structure.

4.3.4. Fabrics from Nanoparticle Containing Ioncell Fibers

Concerning the demo fabrics, three single threads were plied together using 300 twists per m in S direction (DirectTwist, Agteks, Turkey, 22 tex, Z 700 X 3 S 300). The obtained yarn was converted to a knitted jersey fabric. The machinery was a flatbed weft knitting machine (Stoll CMS ADF 32 W E7.3 multi gauge, Stoll, Germany) employing the following knitting parameters: 7 courses per cm, 8 wales per cm, and 56 stitches per cm².

The plied yarns were also woven to fabrics using a 3D printed handloom. Weaving parameters: Weft densities of 24 or 30 yarns/cm, and warp density of 6 yarns/cm.

4.3.5. Fabric from Mixed Cellulose Waste (Unpublished)

Two strands were plied and twisted together (DirectTwist, Agteks, Turkey). The ply twist direction was S using 300 twists/m. The designation of the yarn was 20 tex Z 700 x 2 S 300. The two-fold yarn was then knitted into two-color jacquard and interlock fabric with a weft knitting machine (Stoll CMS ADF 32W E7.3 multi gauge, Stoll, Germany). The mass per unit area was 265 g/m². The number of stiches per unit length was 7 wales/cm (width) and 6.5 courses/cm (length).

4.4. Analytics

Table 5 depicts a concise summary of the analytical methods used in this thesis based on a sequential numbering. The subsequent sections aim to further elaborate the listed procedures unless mentioned together with the respective standard norms.

Table 5. Summary of the analytical methods employed in this thesis.

	Method	Standard	Paper
A1	¹³ C CP MAS NMR	-	I, II
A2	Acid Hydrolysis of CO/PET Blends	Modified procedure of EU 1007/2011, 2011.	I
A3	GPC / MMD of Cellulose	-	II, III, IV
A4	GPC / MMD of PET	-	II
A5	Intrinsic Viscosity of Cellulose	SCAN-CM 15:88	II, III, IV
A6	Rheology of Cellulose Solutions	-	II, III, IV
A7	Tensile Testing of Fibers	DIN 53816 or ISO 5079, Young's Modulus ASTM D2256/D2256.	II, III, IV
A8	Birefringence	-	II, III, IV
A9	TGA	-	II
A10	SEM	-	II, IV
A11	TEM	-	IV
A12	CIELAB and ΔE	-	III, IV
A13	ICP-Analysis	-	III

A14	Tensile Testing of Yarns	-	III, IV
A15	Color Fastness to Washing	EN ISO 105-C06	III, IV
A16	Color Fastness to Rubbing	EN ISO 105-X12:2016	III
A17	UV Protection	EN 13758-1:2001 + A1	IV

4.4.1. ^{13}C CP MAS NMR (A1)

All samples in Paper I (i.e. NMR quantification method for CO/PET blends) and the PET samples in Article II (i.e. separation of CO/PET blends) were measured on a Bruker AVANCE III device equipped with an UltraShield Plus 400 MHz magnet. Its operating frequency was 100.6 MHz. Settings: 4 mm probe size, 8000 scans, 8 kHz spinning speed, 2 ms CP contact time, 34 ms acquisition time, and proton SPINAL-64 ^1H decoupling. Since the spectra of pure cellulose samples are commonly recorded with a CP contact time of 1 ms (Zuckerstätter *et al.* 2009), 2 ms represented a compromise between the signal intensity of cotton and polyester. During contact time, the cross-polarization amplitude was increased from 50% to a maximum of 85 kHz.

Viscose and Tencel fibers (Cellulose II) were soaked in water before the analysis. The measurements thereof were conducted on a Bruker Avance III 500 MHz spectrometer. Settings: 4 mm probe size, 8000-10000 scans, 5s relaxation delay, 10 kHz spinning speed, 1 ms CP contact time, 27 ms acquisition time, and proton SPINAL-64 ^1H decoupling. The crosspolarization amplitude was varied from 70% to reach a maximum of 80 kHz throughout contact time.

4.4.2. Acid Hydrolysis of CO/PET Blends (A2)

For the determination of the exact blend composition, cotton polyester fabrics were hydrolyzed in 10 M H_2SO_4 (95°C) according to a modified procedure as stated in the EU norm 1007/2011. The treatment time was 20-30 min with a sample to liquor ratio of 0.02:100. The harsh acidic conditions dissolved the cotton component completely, while the polyester residue remained unaffected in the solution. After hydrolysis, the remaining PET fibers were recovered through filtration, rinsed with water and acetone, and dried in vacuum (50°C, 6h). The initial blend concentration could then be calculated from the mass of the dried PET fraction (1007/2011, 2011).

4.4.3. Molar Mass Distribution of Cellulose Using Gel Permeation Chromatography (A3)

The molar mass distribution (MMD) of cellulose was analyzed by gel permeation chromatography. The five-column system consisted of one pre-column (PLgel Mixed-A, 7.5 × 50 mm) and four analytical columns (PLgel Mixed-a, 7.5 × 300 mm) and a refractive index detector (Shodex RI-101). The samples were dissolved in 90 g/l LiCl/N,N-dimethylacetamide (DMAc) using a solvent exchange sequence of water, acetone, and DMAc. The sample solution was diluted to a 0.9 wt% LiCl/DMAc solution and transferred into an eluent phase of the same concentration. The flow rate was adjusted to 0.75 ml/min at an operation

temperature of 25°C. To obtain the detector constants, the system was calibrated with Pullulan standards ($M_w=343\text{--}708$ kDa) using a $\partial n/\partial c$ value of 0.136 mL/g for cellulose dissolved in LiCl/DMAc (0.9 wt%) (Potthast *et al.* 2015).

4.4.4. Molar Mass Distribution of Polyester (PET) Using Gel Permeation Chromatography (A4)

VTT (Finland) measured the MMD of PET using a 3-column unit combined with a RI-detector (40°C) operating on an 1,1,1,3,3,3-hexafluoro-2-propanol (HFIP)/5mM salt (sodium trifluoroacetate) eluent and a flow rate of 0.5 ml/min. The columns comprised of one pre-column (Styragel WATTo54405) and two analytical columns (Styragel HR 4E 7.8×300 mm and Styragel HR5 7.8×300 mm). The calibration was conducted with polymethyl methacrylate standards.

4.4.5. Rheology of Cellulose Solutions (A6)

The complex viscosity η^* and the dynamic moduli (G' , G'') of the prepared cellulose dopes were recorded as a variable of the angular frequency (ω) using Anton Paar rheometers (Physica MCR 300 & 302, Anton Paar, Austria). Prior to the actual analysis, dynamic strain sweep tests were conducted to determine a strain of 0.5%. The device geometry was a plate to plate set-up with 25 mm diameter and 1 mm gap size. The measurements were performed over a temperature range of (40-100°C) dependent on the concentration of the cellulose solutions. In agreement with the Cox-Merz rule, the zero shear viscosity η_o^* could be estimated via the Carreau or Cross model (Sammons *et al.* 2008). The cross-over point of storage and loss modulus (G' , G'') provided further information on the elastic and viscous domains of the cellulose solutions. Appendix 2 also summarizes the mastercurves of all parameters.

4.4.6. Birefringence of Cellulose Fibers (A8)

The birefringence of the spun cellulose fibers was observed under a polarized light microscope (Zeiss Axio Scope, Zeiss Ag, Germany). Accordingly, single filaments were fixed onto a glass slide and their birefringence value Δn was measured on three different positions (i.e. top, middle, and bottom). This procedure was repeated three times yielding the total orientation factor f_i after dividing Δn by 0.062, which represents the maximum birefringence value for cellulose with a density of 1.5 g/cm³ (Lenz, Schurz & Wrentschur 1994).

4.4.7. Thermogravimetric Analysis of Cellulose and Polyester (A9)

The thermal degradation behavior of cellulose and polyester was measured with a Q500 TGA (TA Instruments, Germany) under a N₂ atmosphere. The temperature was increased gradually from 25-800°C with a heating rate of 10°C/min. The sample amounts ranged from 5-10 g per analysis.

4.4.8. Scanning Electron Microscopy (A10)

For cross-sectional measurements, small fiber strands were taped into an aluminium cup, which was filled with water and frozen in a freezer. The sample set-up was then dipped into liquid nitrogen and broken into two pieces along the center of the fiber strand. The obtained cross-sections were fixed on a carbon tape facing an upright position (ca. 1 mm of fiber sticking out from the edge of the carbon tape). Alternatively, the filaments could be taped on a paper surface, soaked in water and cryofractured. All other samples were ground and applied horizontally on a carbon tape coated surface. The specimens were consequently sputter coated with Au or Pt/Pd and measured by a Zeiss Sigma VP, Zeiss field emission-scanning electron microscope operating at an acceleration voltage of 1.5 kV.

4.4.9. Transmission Electron Microscopy (A11)

The TEM images were taken by FELMI-ZFE (Austria). Single cellulose filaments, coated with noble metal nanoparticles, were submerged in an Epoxfix resin and sliced with an Ultramicrotome UC6 (Leica Microsystems Austria) equipped with a 35° diamond knife (Diatome, Switzerland). Once placed on a copper grid, the thin sample slices were observed under a Tecnai T12 (FEI) operating at an acceleration voltage of 120 kV.

4.4.10. Color Coordinates (CIELAB) (A12)

The color coordinates (L^* , a^* , b^*) of pre- and post-consumer cellulose waste before and after spinning and of nanoparticle coated pulp and fibers were determined with a 10° observer equipped with a standard illuminant D65 (SpectroScan, GretagMacbeth, Germany). While spun fibers and fabrics were measured without further modification, the pulp samples were ground and dispersed in water to collect a homogenous filter cake, which was air-dried subsequently. To avoid irregularities in the measurements, the sample surfaces were compressed with a glass slide used for light microscopy. Applying the following equation, the absorbance spectra could be generated from the reflectance values,

$$A = \log \frac{1}{R} \quad (9)$$

where A and R represent absorbance and reflectance at distinct wavelengths, respectively. The color difference ΔE is composed of the square root of the sum of the absolute values of all color coordinates.

$$\Delta E = \sqrt{(\Delta L^*)^2 + (\Delta a^*)^2 + (\Delta b^*)^2} \quad (10)$$

Therein, ΔL^* describes the variation in lightness, whereas Δa^* and Δb^* denote the color change on the red-green axis and on the yellow-blue axis.

4.4.11. Inductively Coupled Plasma-Atomic Emission Spectrometry (A13)

The ICP-analysis was conducted with a Perkin Elmer ICP-optical emission spectrometer (Optima 7100, DV). During sample preparation, pulp and yarns were dissolved in Aqua regia (7.5 ml HCl conc. and 2.5 ml HNO₃ conc.) using a microwave oven (Milestone Ethos, Italy, 200°C, 50 min). The device was calibrated by element specific standard solutions.

4.4.12. Tensile Testing of Yarns (A14)

Prior to the analysis, the samples were conditioned overnight ($65\pm 2\%$ relative humidity, $20\pm 2^\circ\text{C}$), and their titers were calculated from the average weight of a 10 m hank. For tensile testing, the two ends of a single yarn strand were compressed either with 1 cm slices of conventional printing paper or covered with tape to reduce breakage induced by the clamps of the tensile tester (MTS 400). Gauge length and test speed were then adjusted to 250 mm and 250 mm/min to measure breaking tenacity (cN/tex) and elongation at break (%) using a 50 N load cell.

5. Results and Discussion

5.1. NMR-Analysis of Cotton Polyester Blends

If calibrated accurately, solid state NMR allows, besides molecular conformation and interface dynamics, to determine material compositions such as in textile blends. Figure 17 depicts ^{13}C -NMR spectra of virgin cotton and polyethylene terephthalate (PET).

Figure 17. NMR Spectra of cotton (blue) and PET (black) with assignments of the respective nuclei. Image copied from Paper I (Haslinger *et al.* 2019a).

As initially explained, magnetically inequivalent nuclei can appear as separate peaks in the NMR spectrum (Martínez-Richa & Silvestri 2012). In cellulose, C1, C4, and C6 thus evolve as distinct signals (107-109 ppm, 87-89 ppm, and 66-68, ppm), while the lines of C2, C3, and C5 remain partially unresolved (74-78 ppm). In particular, the lower ppm regions of C4 and C6 also account for amorphous structures in the polymer, which implies that signal size and shape can vary according to the crystallinity and type of cellulose present in the sample (Atalla & VanderHart 1999; Zuckerstätter *et al.* 2009; Park *et al.* 2009).

Cotton consists of cellulose I, which, if dissolved and regenerated, can transform to cellulose II. Therefore, single peaks around 87-89 ppm indicate cellulose I, whereas two separate lines at 89 and 88 ppm result from cellulose II. The former is composed of I_α and I_β , paracrystalline and amorphous contributions,

while the latter displays two crystalline cores, as well as accessible and inaccessible fibril surface areas. Correspondingly, Zuckerstätter *et al.* developed a deconvolution model for the C4 region to estimate fibril and aggregate width (FW, AW), crystallinity ratio (Crl), and sum of crystalline and fibril surface areas (Σ cryst., Σ FS) in natural and regenerated cellulose fibers (Zuckerstätter *et al.* 2009; Zuckerstätter *et al.* 2013). Table 6 displays the respective parameters calculated for the samples in Paper I.

Table 6. Cellulose content, fibril and aggregate width (FW, AW), crystallinity ratio (Crl), sum of crystalline areas (Σ cryst.), and sum of fibril surface areas (Σ FS). Table adapted from Paper I (Haslinger *et al.* 2019a).

Sample	Cell. / wt%	FW / nm	AW / nm	Crl / %	Σ cryst. / %	Σ FS / %
IGALO TPPT	50	3.3	56	43	-	-
IGALO KM	65	3.0	-	39	-	-
IGALO	50	3.5	-	45	-	-
RED SHIRT	17	3.1	25	40	-	-
BROWN SHIRT	60	3.9	50	50	-	-
WHITE SHIRT	35	3.2	40	41	-	-
Cotton	100	4.0	57	51	-	-
Viscose	100	5.1	-	46	28	18
Tencel	100	3.2	-	65	27	38

In general, it is known that dissolution and dry-jet wet spinning in NMMO lead to higher crystallinity ratios (65 %) than derivatization via CS₂ (46 %) (Fink *et al.* 2001). This is also reflected in the smaller amount of fibril surface areas in Viscose fibers (18 %) as compared to Tencel (38 %). Pure cellulose I yielded a crystallinity ratio of 50 % with a fibril and aggregate width of 5.1 nm and 57 nm, respectively. The remaining samples represented cotton polyester blends with varying concentrations (17-65 wt% CO). Besides IGALO KM (FW=3 nm, Crl=39 wt%), fibril width, aggregate dimensions, and crystallinity decreased with the cotton content (FW=3.9-3.1 nm, AW=25-56, Crl=50-41 %). This corresponds to literature, where resolution and intensity were reported to affect the output of the deconvolution method (Zuckerstätter *et al.* 2009). Accordingly, it can be assumed that with decreasing cotton concentrations the analyses became less accurate.

PET showed three peaks in the NMR spectrum. The largest signal was caused by the carbons of the aromatic unit (C2-3-4-5-6-7), which appeared at 130-134 ppm, followed by the carboxyl groups (C1-8) at 164 ppm. The ethynyl groups (C9-10) overlapped with the C2-3-4 nuclei of cellulose as they evolved at 62 ppm. The remaining signals represented spinning side bands of PET. Similar to cellulose, the resolution of the NMR spectrum can be an indicator of the ratio of amorphous and crystalline regions in the polymer. Sharp lines imply a highly crystalline structure, while an increased signal to noise ratio with softer lines refers to less ordered areas (Gabrielse *et al.* 1994).

5.1.1. Peak Deconvolution and Calibration Model for Quantification

The establishment of the subsequent calibration model relied on the assumption that the intensities of certain NMR signals correlate to the quantitative composition of textiles. This has been confirmed by Colletti and Mathias, who successfully employed peak height relationships to characterize cotton polyester blends. To avoid overlaps, their model utilized the C1 line of cellulose and the carboxyl peak of PET (C1-8) (Colletti & Mathias 1988).

Similarly, this study compared C1, C1-8, and C2-3-4-5-6-7, subsequently labelled as C1(C), C1-8(P), and C_{arom.}(P), to estimate the composition of cellulose and polyester in textile blends using ratios of peak areas. Already Colletti and Mathias had attempted to follow the same approach, but failed as they forgot to set accurate integration limits (Colletti & Mathias 1988). Likewise, Peterson implied that NMR based quantification methods could face difficulties due to their dependency on distinct instrument parameters required by different fiber types (Peterson 2015).

However, these problematics can be overcome by the optimization of contact time and adequate peak constraints (cf. supporting information of Paper I).

Table 7. Constraints and number of Gaussian functions of the peaks integrated for the quantification of cotton and polyester. Table copied from Paper I (Haslinger *et al.* 2019a).

Abbrev.	Fiber	Peak No.	Constraints / ppm	No. f(x)
C1(C)	Cellulose (Cotton)	1	100-110	4
C1-8(P)	PET	1,8	160-175	2
Carom.(P)	PET	2, 3, 4, 5, 6, 7	120-140	3

As shown in Table 7, all peaks were integrated with 2-4 Gaussian functions dependent on the complexity of the signal. While the deconvolution of C1(C) accounted for cellulose I_α and I_β, as well as amorphous contributions and baseline corrections, C1-8(P) and C_{arom.}(P) were fitted with two and three curves, respectively. Constraints aimed to reduce errors caused by manual integration procedures.

The calibration curves were generated by the analysis of six sample standards containing 2.5-90 wt% CO. After integration, the division of the C1(C) area by the PET signals yielded relative values (C1(C):C1-8(P) and C1(C):C_{arom.}(P)), which could be expressed as cotton content (wt%) vs. peak ratios. As the functions are undefined at 0 and 100 wt%, their behavior is described as sigmoidal (cf. Figure 18),

$$y = \frac{a x}{1 + |x|^b} \quad (11)$$

Figure 18. Calibration and confidence intervals generated from the measurement of distinct cotton concentrations and integration of C1(C), C1-8(P), and Carom.(P). Image copied from Paper I (Haslinger *et al.* 2019a).

where distinct cotton contents are expressed as a function of the peak ratios x , whereas the variables a and b denote slope and intercept of the calibration functions. The standard deviations were approximated by the elimination of single calibration points from the overall data set. Their accuracy is dependent on the cotton concentration, and can be improved by inversion if necessary.

5.1.2. Quantification Results

The quality of the calibration model was tested with six pre- and postconsumer cotton polyester blends. Among them, three white cotton fabrics (IGALO TPPT, IGALO KM, and IGALO) from a fabric supplier and three colored shirts (RED SHIRT, BROWN SHIRT, and WHITE SHIRT) from a secondhand store. Figure 19 and Table 8 summarize their composition according to textile labels, acid hydrolysis, and solid-state NMR.

Figure 19. Cotton content (wt%) of pre- and post-consumer cotton polyester blends according to the textile labels, acid hydrolysis and NMR. Image copied from Paper I (Haslinger *et al.* 2019a).

Table 8. Cotton content (wt%) of pre- and post-consumer cotton polyester blends according to the textile labels, acid hydrolysis and NMR (i.e. C1(C):C_{arom.}(P) and C1(C):C1-8(P)).

Sample	Label / wt%	Acid Hydr. / wt%	C1(C):C _{arom.} (P) / wt%	C1(C):C1-8(P) / wt%
IGALO TPPT	50	48.4±0.3	45.6±6.7	46.9±6.7
IGALO KM	65	60.7±0.2	62.1±7.0	63.6±6.9
IGALO	50	48.8±1.5	53.2±7.0	55.2±7.0
RED SHIRT	17	17.7±0.1	16.6±3.8	21.0±4.0
BROWN SHIRT	60	54.8±1.1	53.7±7.0	55.2±7.0
WHITE SHIRT	35	30±0.1	31.7±5.4	33.3±5.7

In five out of six cases, the cellulose concentrations stated on the label were higher than determined by acid hydrolysis. Solid-state NMR supported this conclusion four times, whereas two measurements led to ambiguous results. The deviations ranged from 0.7-5.2 wt% for the former, and from 0.4-5.2 wt% for the latter. It can be assumed that these differences arise from lax EU regulations. When it comes to the manufacturing of clothing, textile labels are, in principal, not allowed to state compositions that deviate more than 3 wt% from the actual blend ratio, although fibers amounting less than 5 wt% in total are not required to be mentioned at all (EU 1007/2011). Overall, C1(C):C2-8(P) provided values closer to acid hydrolysis, while C1(C):C_{arom.}(P) exhibited a tendency to higher cotton concentrations. Neither dyes nor finishing agents, nor wearing and laundering had a noticeable effect on the obtained results. It is obvious that both, the number of data points and the heterogeneity of the samples, affected the robustness of the calibration method, which led to higher standard deviations as compared to acid hydrolysis. With further development, however, solid-state NMR could potentially qualify as an accurate technique for textile analysis.

5.2. Raw Materials of Papers II-IV

5.2.1. Hydrothermal Synthesis of Gold and Silver Nanoparticles on Bleached PHK Pulp

The synthesis procedure of gold and silver nanoparticles followed a hydrothermal method reported by Bumbudsanpharoke *et al.*, where diluted, aqueous solutions of HAuCl₄ were applied on wet, unbleached kraft pulp to form nanometal particles (121°C, 101.35 kPa, 30 min) (Bumbudsanpharoke & Ko 2015). Under adequate conditions, cellulose can stabilize metal ions to convert them to their reduced form using its half acetal groups on the anomeric carbon (Boufi *et al.* 2011; Bumbudsanpharoke & Ko 2015). Several studies also indicated that reduction reactions of this type are governed by an appropriate pH (Tang *et al.* 2015b), and the presence of lignin (Bumbudsanpharoke & Ko 2015).

In this study, we adjusted the reported protocol to higher temperatures and longer reaction times (135°C, 2-15 h) to generate quantitative yields on bleached PHK pulp. Figure 20 displays the sample substrates before and after coating with Au, AgAu, and AgNPs.

Figure 20. SEM images of the PHK pulp surface before and after coating with Au, AgAu, and AuNPs. Image modified from Paper IV (Haslinger *et al.* 2020).

It is evident that the size and distribution of the nanoparticles differed according to the metal type. While larger Au and AgNPs aggregated on distinct areas, the smaller AgAuNPs were distributed uniformly on the cellulose surface.

Table 9 summarizes the yields of gold and silver after the respective coating procedures. The reaction times were solely estimated based on the color change occurring during the synthesis. After 2h, 71-84 % of the Au employed had precipitated on the cellulose surface, whereas Ag required more than a sevenfold to reach a yield of 94 %. Further optimization may have provided conditions that are more efficient.

Table 9. Yield of Au and Ag on the pulp samples according to ICP analysis before and after coating with Au, AgAu, and AuNPs. Data retrieved from Paper IV (Haslinger *et al.* 2020).

Sample	Time / 2h	Au Yield / %	Ag Yield / %
Uncoated Pulp	0	-	-
Pulp with AuNPs	2	71±1	-
Pulp with AgAuNPs	2	84±1	65±1
Pulp with AgNPs	15	-	94±2

5.2.2. Pretreatments of Cotton and Cotton Polyester Blends

This thesis attempted to solve several pressing problems concerning the recyclability of cotton waste in textile industry. Among them, the exploitation of blended, cellulose rich textile waste for staple fiber spinning, and the translation of dyestuff from waste sources to new fiber products.

In principal, the Ioncell technology allows to upcycle cellulose from various waste streams, if their macromolecular properties correspond to a certain target

range ($\eta=400\text{--}500$ ml/g) (Asaadi *et al.* 2016; Ma *et al.* 2018; Ma *et al.* 2016). However, natural fibers such as cotton display much higher viscosities ($\eta=2000$ ml/g), which can be lowered for MMCF processes by DP adjustment. The same applies for post-consumer cotton if the degradation caused by wearing and laundering was insufficient (cf. domestic and industrial laundering) (Wedin *et al.* 2019). When a second fiber component comes into play, it further enhances the complexity of the process.

The challenges addressed above bring about different pre-requisites in terms of pretreatment. The utmost aim of any recycling strategy is to promote sustainability, i.e. to reduce the consumption of chemicals and resources. In case of blended textile waste, this implies that all material components are intended to be re-used without a major amount of processing steps.

The cotton polyester blend studied herein represented a mixture of post-consumer waste obtained from a textile recycling company (SOEX, Germany). Prior to processing, impurities such as buttons and zippers were removed, and the waste fractions were blended to obtain a cotton content of 50 wt%. A pretreatment sequence of Ew-disk refining-P-Z-A subsequently bleached and decreased the viscosity of the substrate. Alkaline washing (Ew) aimed to eliminate silicates, while disk refining adjusted the particle size of the sample. Hydrogen peroxide (P) and ozone (Z) lowered the DP and increased the brightness, whereas acid washing (A) removed metal contaminations.

Both peroxide and ozone treatments tend to have a negligible effect on the MMD of cellulose. Similarly, acid washes lead to a PDI (~ 2.0), which is close to the original MMD of cotton (Flory 1953 (1969)). In this respect, it appears natural to investigate also the pretreatment's impact on the PET fraction. In Table 10, the number average molar mass (M_n), weight average molar mass (M_w), and PDI of the sample were evaluated according to the different pretreatment steps.

Table 10. Number average molar mass M_n , weight average molar mass M_w , and PDI of PET before and after the pretreatment steps. Table copied from Paper II (Haslinger *et al.* 2019b).

Sample	M_n / kDa	M_w / kDa	PDI
PET before Treatment	9.8 ± 0.3	21.4 ± 0.2	2.1 ± 0.2
PET after Alkali (E)	9.8 ± 0.3	22.4 ± 0.2	2.3 ± 0.2
PET after Disk Refining (disk)	10.1 ± 0.3	22.5 ± 0.2	2.2 ± 0.2
PET after Ozone (Z)	9.4 ± 0.3	21.8 ± 0.2	2.3 ± 0.2
PET after Peroxide (P)	9.3 ± 0.3	21.6 ± 0.2	2.3 ± 0.2
PET after Acid (A)	9.5 ± 0.3	21.6 ± 0.2	2.3 ± 0.2

The pretreatment sequence caused a negligible alteration in the MMD. While M_n experienced a minor decline from 9.8 to 9.5 kDa, M_w remained unchanged. This triggered a small increase in the PDI (2.1–2.3), suggesting a slight broaden-

ing of the molar mass distribution of PET. However, the obtained results indicate a certain heterogeneity in the waste substrate, rather than a degradation induced by the pretreatment of cellulose.

In Paper III, pure pre- and post-consumer cotton was dyed with vat and reactive dyes to study their fastness during dissolution and respinning. Before dyeing, 50 worn out hospital bed sheets were assessed according to their limiting viscosities. Among them, 32 (62%) classified as suitable to be used without pretreatment. Bed sheets with values below 350 ml/g and above 550 ml/g were excluded from the study. Subsequently, the samples were divided into sets of 1 kg and dyed with Indanthren Brilliant Red FBB, Indanthren Brilliant Green FBB Coll, Remazol Black B gran 133%, Remazol Brilliant Blue R spec, Levafix Brilliant Red E-4BA, and Levafix Blue E-GRN.

Indanthren Blue BC 3% was applied onto a white, pre-consumer cotton fabric. For DP adjustment, we tested four types of pretreatment including high energy electron beam dosages (e-beam), acid hydrolysis (A), and combinations of acids and endoglucanase (EG-A, A-EG). Mechanical treatments and bleaches such as Z and P were evaded to preserve the original dye structure.

E-beam treatments rely on high-energy electrons (10 MeV), which are fired at stacks of cotton fabrics to induce a homogenous cleavage in the polymer. The procedure generates free radicals and labile carbonyl groups, which can continue the degradation of cellulose beyond the actual treatment (Sixta 2006). In contrast, enzymes render the structure of cellulose more polydisperse as they favor amorphous over crystalline regions and tend to act mostly on the cellulose surface due to their limited mass transfer through the pores. Besides depolymerisation, they also enable to increase the reactivity of the sample, which translates to an enhanced dissolution in the solvent (Pérez *et al.* 2002). Combinations of both acid washing and enzymes reduce costs and contaminants, while they broaden the MMD of cellulose to support the formation of filaments during dry-jet wet spinning (Michud, Hummel & Sixta 2015).

5.2.3. Viscosities and Molar Mass Distributions

As illustrated in Figure 21 and Table 11, viscosity and MMD depended on the origin and pretreatment of the cellulose substrate. Wood pulp inherently shows a broader MMD ($M_n=71.5$ kDa, $M_w=255.2$ kDa, $PDI=3.6$, s. Figure 21d) than pre-consumer cotton ($M_n=423.1$ kDa, $M_w=1417.3$ kDa, $PDI=2.4$, Figure 21b), despite a significantly lower intrinsic viscosity ($\eta=464$ ml/g). This is also displayed in the high proportions of low and high molecular weight fractions ($DP<100=4.1\%$, $DP>2000=22.0\%$) that allowed a stable dry-jet wet spinning (Michud, Hummel & Sixta 2015). With the introduction of nanoparticles into the system, the MMD negligibly shifted to lower molecular weight fractions over treatment time and metal type employed ($DP<100=4.1-4.3\%$, $DP>2000=19.2-21.3\%$), while the PDI slightly narrowed to 3.4-3.5. However, it is assumed that these alterations were rather arbitrary, since this trend could not be observed for sample blanks subjected to the same treatment conditions (cf. Paper IV).

Table 11. Summary of pretreatments, limiting viscosity (η), number average molar mass (M_n), weight average molar mass (M_w), polydispersity index (PDI), and percentage of degree of polymerization (DP) below 100 and over 2000. The raw materials listed display the samples of Papers II-IV.

	Sample	Pretreatment	η / (ml/g)	M_n / kDa	M_w / kDa	PDI	DP<100 / %	DP>2000 / %
Paper II	Post-Consumer Cotton Polyester							
	Cotton from CO PET Blend ¹	Ew-disk-P-Z-A	450±50	68.3±0.7	193.2±5.1	2.8±0.04	2.9±0.01	14.4±0.2
	Polyester from CO PET Blend	Ew-disk-P-Z-A	-	9.8±0.3	21.4±0.2	2.1±0.2	-	-
Paper III	Pre-Consumer Cotton							
	Untreated Cotton	-	2032±50	423.1±1.0	1417.3±57.7	2.4±1.4	0	78.1±0.8
	Indanthren Blue BC 3%	e-beam	545±11	147.3±3.2	391.1±10.6	2.7±0.1	0.3±0.1	37.8±0.4
	Indanthren Blue BC 3%	EG-A	496±15	67.1±7.6	304.5±13.4	4.6±0.7	3.6±1.3	24.8±0.5
	Indanthren Blue BC 3%	A-EG	470±12	75.9±1.2	380.0±55.9	5.0±0.8	2.7±0.2	28.1±0.5
	Indanthren Blue BC 3%	A	454±11	114.5±14.5	314.9±6.1	2.8±0.4	0.9±0.9	29.4±0.7
	Post-Consumer Cotton							
	Undyed Cotton	-	396±16	94.1±4.2	193.8±2.6	2.1±0.1	1.5±0.4	15.3±0.2
	Indanthren Brilliant Red FBB	-	461±78	93.7±1.5	206.5±3.5	2.2±0.02	1.4±0.06	17.7±0.3
	Indanthren Brilliant Green FBB Coll	-	435±33	100.1±4.0	210.5±1.0	2.1±0.1	1.3±0.3	18.5±0.02
	Remazol Black B gran 133%	-	448±113	91.8±0.1	255.3±0.1	2.8±0.003	1.9±0.08	23.1±0.2
	Remazol Brilliant Blue R spec	-	422±63	91.9±2.5	204.0±0.5	2.2±0.1	1.8±0.2	17.5±0.04
	Levafix Brilliant Red E-4BA	-	465±28	102.4±5.3	308.3±1.5	3.0±0.1	1.6±0.4	29.1±0.2
	Levafix Blue E-GRN gran	-	426±56	89.1±1.8	186.8±0.3	2.1±0.04	1.7±0.3	14.3±0.01
Paper IV	Bleached PHK Pulp with NP Coatings							
	Uncoated Pulp		464±0.2	71.5±7.7	255.2±6.3	3.6±0.3	4.1±0.1	22.0±0.8
	Pulp with AuNPs	2h, hydrothermal	461±8	72.1±4.3	248.3±3.8	3.4±0.2	4.1±0.3	21.3±.2
	Pulp with AgAuNPs	2h, hydrothermal	477±2	69.6±0.7	246.2±1.1	3.5±0.1	4.2±0.04	20.7±0.1
	Pulp with AgNPs	15h, hydrothermal	478±9	68.6±1.1	232.4±4.5	3.4±0.1	4.3±0.1	19.2±0.02

¹ The considerably low values in the MMD in case of the cotton polyester blend may result from different GPC runs with distinct calibrations.

Figure 21. Molar mass distributions of the cellulose substrates in Papers II-IV. (a) MMD of cotton from a pretreated, post-consumer cotton polyester blend,² (b) MMD of Indanthren Blue BC 3 % dyed pre-consumer cotton before and after pretreatment with e-beam, EG-A, A-EG, and A, (c) MMD of untreated, vat and reactive dyed post-consumer cotton, (d) MMD of bleached PHK pulp before and after coating with Au, AgAu, and AgNPs. Graphs edited and merged from Papers II-IV.

In contrast, the MMD of dyed pre-consumer cotton changed noticeably throughout the different pretreatment procedures. Both e-beam and A resulted in narrow MMDs ($PDI=2.4-2.8$) with proportionally high amounts of long polymer chains ($DP>2000=29.4-37.8$), whereas A-EG and EG-A increased the PDI (4.6-5.0) to better match the properties of PHK pulp. In either case, M_n and M_w decreased to 67.1-75.9 kDa and 304.5-380.0 kDa as compared to e-beam and acid treated pulp ($M_n=114.5-147.3$ kDa, $M_w=314.9-391.1$ kDa). This also corresponds to the higher percentage of shorter cellulose chains ($DP<100=2.7-3.6$ %) combined with less fractions above $DP>2000$ (24.8-28.1%). In spite of these alterations, most limiting viscosities ($\eta=454-545$ ml/g) still complied with the set target range of 400-500 ml/g. The same applied for the cellulose component

² Note: The MMD data of the cotton polyester blend before the pretreatment is missing due to an unavailability from the supplier (VTT), who conducted the pretreatment.

assessed in the pretreated, post-consumer cotton polyester blend ($\eta=450$ ml/g, s. Figure 21a). The sample exhibited a M_n of 68.3 kDa and M_w of 193.2 kDa, which was similar to the A and e-beam treated samples in terms of PDI (2.8). Nonetheless, it showed a higher amount of low molecular weight fractions ($DP<100=2.9\%$) accompanied by a smaller number of longer polymer chains ($DP>2000=14.4\%$).

Apart from Remazol Black B gran 133% and Levafix Brilliant Red E-4BA (PDI=2.8-3.0), all untreated, dyed post-consumer cotton samples displayed uniform macromolecular properties (cf. Figure 21c) with considerably small PDIs (2.1-2.2). While their high molecular weight fractions ($DP>2000=14.3-18.5\%$) resembled the cotton polyester substrate, their amount of shorter polymer chains was evidently lower ($DP<100=1.5-1.8\%$). This deviation is also embodied by the distinct molar masses M_n and M_w ($M_n=89.1-94.1$ kDa, $M_w=186.8-210.5$ kDa), which largely differed from pre-consumer cotton concerning their weight average molar masses. In contrast, Levafix Brilliant Red E-4BA and Remazol Black B gran 133% exhibited substantially higher M_w values in the range of 255.3-308.3 kDa translating to a greater presence of longer polymers ($DP>2000=23.1-29.1\%$). These differences are only marginally represented in the limiting viscosities of the samples ($\eta=396-465$ ml/g) and can largely be attributed to the heterogeneity of the waste substrate.

5.3. Dissolution and Dry-Jet Wet Spinning

As stated in the previous chapters, the dissolution of cellulose in ionic liquids involves various factors such as the IL's solvent power, the polymer concentration and DP, as well as the dissolution time and temperature (Fink *et al.* 2001; Parviainen *et al.* 2014).

All samples discussed herein were dissolved via a standard procedure (kneader, 1-2h, 70-80°C, ~10 mbar, press filtration at 80°C) that was developed earlier (Michud *et al.* 2015; Sixta *et al.* 2015). Solution time and temperature mainly depended on the cellulose substrate. In particular, the cotton polyester samples demanded shorter dissolution times (1h) and milder filtration temperatures (70°C) to hinder the degradation of PET in the mixture. For the same reason, it was also attempted to add a surplus of HOAc (30%) to the IL to render the pKa value of the system less alkaline. In case of dyed pretreated, pre-consumer cotton, partially longer dissolution times were employed (2h) to compensate for the hornification created by repeated wetting and drying throughout the pretreatment stage. Despite this, the resulting solutions still showed aggregates of undissolved particles, which lowered the final concentration of the mixtures. In contrast, dyed post-consumer cotton and the nanoparticle-coated pulp could be dissolved without any difficulties (80°C, 1.5 h).

This practical discrepancy is also highlighted by the rheological behavior of the solutions (Figure 22a-d and Table 12). As described in the experimentals, the samples were subjected to frequency sweep measurements at distinct temperatures to assess their complex viscosity η^* and dynamic moduli (G' , G'') as a function of the angular frequency (ω).

Table 12. Summary of all spun samples from Papers II-IV including cellulose concentrations (Cell.), rheological parameters (η_0^* , ω , $G' = G''$) at the spinning temperature (T), fiber properties (titer, tenacity, and elongation) in conditioned and wet stated, as well as birefringence measurements (Δn , f_{total}). Note: Samples marked with * display average values due to multiple trials with the same parameters.

	Spin Dope Rheology						Fiber Properties / Cond.				Wet			Birefringence	
	Sample	Cell. /wt%	T /°C	η_0^* / Pa s	ω / s ⁻¹	$G' = G''$ / Pa	DR	Spin.	Titer / dtex	Tenacity / cN/tex	Elong. / %	Tenacity / cN/tex	Elong. / %	Δn	f_{total}
Paper II	Cellulose Solutions from Pretreated Post-Consumer Cotton Polyester Blends														
	COPEt_6.5	6.5	60	1400	6.90	1495	8	yes	0.8±0.1	34.8±5.3	7.3±1.4	36.6±5.2	8.5±0.7	0.044±0.005	0.71±0.08
	COPEt_6.5_HOAc	6.5	60	175700	-	-	4	bad	2.7±0.3	26.9±2.1	9.0±1.3	20.5±1.3	10.8±1.8	0.036±0.012	0.59±0.19
	COPEt_10.5	10.5	60	13300	1.40	3224	8.8	yes	1.7±0.1	47.7±3.4	8.7±0.8	44.6±3.3	11.3±1.0	0.042±0.008	0.67±0.12
Paper III	Cellulose Solutions from Pretreated Dyed Pre-Consumer Cotton														
	Indanthren Blue BC 3% e-beam*	13-14	70	31100	1.07	6996	12	no	1.4±0.2	40.3±2.7	7.4±1.4	33.7±3.3	7.3±1.0	0.048±0.007	0.78±0.12
	Indanthren Blue BC 3% EG-A*	13-14	70	31100	0.53	2179	12	yes	1.2±0.1	44.3±1.4	10.8±0.6	39.5±3.2	12.5±0.7	0.048±0.007	0.78±0.11
	Indanthren Blue BC 3% A-EG	13	70	16400	0.61	1630	12	no	1.0±0.1	45.5±2.8	8.9±1.1	45.0±3.5	11.5±1.3	0.044±0.017	0.72±0.27
	Indanthren Blue BC 3% A*	13	70	26500	0.90	3905	12	no	1.2±0.1	48.5±4.1	12.8±1.3	47.4±4.1	12.4±3.1	0.044±0.004	0.71±0.06
	Cellulose Solutions from Dyed Post-Consumer Cotton														
	Undyed Cotton	13	65	47500	0.42	4554	12	yes	1.2±0.2	56.4±4.3	13.0±1.4	53.4±4.0	13.7±1.1	0.043±0.004	0.70±0.07
	Indanthren Brilliant Red FBB	13	65	37200	0.76	4913	12	yes	1.4±0.4	54.4±8.4	14.3±1.0	54.3±2.3	14.3±1.1	0.045±0.006	0.72±0.09
	Indanthren Brilliant Green FBB Coll	13	65	41200	0.37	3484	12	yes	1.3±0.2	54.7±4.4	12.3±1.9	51.2±6.0	13.2±1.5	0.044±0.005	0.71±0.09

Paper IV	Remazol Black B gran 133%	13	65	78200	0.29	4319	12	yes	1.4±0.4	50.7±8.8	13.1±1.4	51.4±2.6	14.2±1.5	0.038±0.010	0.61±0.16
	Remazol Brilliant Blue R spec	13	65	55900	0.18	3131	12	yes	1.2±0.2	59.8±4.1	13.1±1.6	57.0±4.4	15.1±2.1	0.047±0.004	0.75±0.07
	Levafix Brilliant Red E-4BA	13	65	812200	-	-	12	no	-	-	-	-	-	-	-
	Levafix Blue E- GRN gran	13	65	32700	0.51	4317	12	yes	1.2±0.2	56.0±4.7	13.1±1.9	54.3±4.3	13.8±1.8	0.047±0.015	0.76±0.22
	Cellulose Solutions from Nanoparticle Coated PHK Pulp														
Paper IV	Uncoated pulp	13	80	26100	0.42	2343	12	yes	1.2±0.1	49.9±4.6	12.5±2.0	47.3±4.5	14.2±2.1	0.040±0.005	0.65±0.09
	AuNP pulp*	13	80	23900	1.20	4774	12	yes	1.3±0.1	49.0±3.7	11.5±1.9	45.0±3.0	13.9±1.7	0.045±0.010	0.73±0.12
	AgAuNP pulp	13	80	30900	0.88	4540	12	yes	1.4±0.1	49.5±3.1	13.0±1.3	46.8±3.3	15.0±1.4	0.047±0.008	0.76±0.12
	AgNP pulp*	13	80	20500	1.30	4242	12	yes	1.2±0.1	46.6±3.2	13.1±2.0	47.8±4.0	15.5±2.2	0.046±0.008	0.73±0.13

Figure 1. Rheological parameters of cellulose solutions prepared from CO PET blends (a), dyed, pretreated pre-consumer cotton (b), dyed post-consumer cotton (c), and nanoparticle coated pulps (d) at their spinning temperatures (60°C , 70°C , 65°C , and 80°C). Complex viscosity (η^*) and dynamic moduli (G' , G'') were measured as a function of the angular frequency (ω). An asterisk (*) was added to curves that represented average results of multiple trials. Figures adapted from Papers II-IV.

η^* can subsequently be fitted with the cross model to obtain an apparent zero shear viscosity η_0^* at minimum shear rates (Sammons *et al.* 2008). Previous studies suggest that η_0^* values of 20 000–30 000 indicate optimal spinning conditions if standard substrates are employed (i.e. 13 wt% PHK pulp) (Michud, Hummel & Sixta 2016; Michud *et al.* 2015; Sixta *et al.* 2015), while cotton demands higher zero shear viscosities (32 700–78 200 Pa s) to be spun to filaments (Asaadi *et al.* 2016). This is also reflected in the lower spinning temperatures for cotton (65–70°C), and therefore requires adjusted processing conditions.

Cellulose solutions usually behave as Newtonian fluids at lower angular frequencies. With increased shear stress, however, the polymer network disconnects, and shear thinning occurs, leading to a decrease in the complex viscosity of the samples (Haward *et al.* 2012; Chen *et al.* 2009; Gericke *et al.* 2009). This becomes particularly evident for lower cellulose concentrations such as obtained from the separation of cotton and polyester (i.e. 6.5 wt%, 10.5 wt%, cf. Figure 22a), where the Newtonian plateau is maintained for a longer frequency range. At higher cellulose concentrations (cf. 13–14 wt%), the critical point for shear thinning shifts to lower shear rates as the disentanglement of the polymer chains is increased faster under increased shear stress (Chen *et al.* 2009). Accordingly, all samples prepared from nanoparticle-coated pulp showed a similar trend for η^* , since the coating procedure left the pulps' MMD unaffected. The complex viscosities of dyed pre- and post-consumer waste were influenced by the choice of the colorant and the differences in their MMDs. Although Indanthren Brilliant Red FBB did not dissolve in [DBNH] [OAc], it did not impair the dissolution of the dyed cotton substrate. In contrast, dyeing with Levafix Brilliant Red E-4BA lowered the solubility of the sample so that gelation could be observed (s. Figure 22c). This phenomenon is depicted by the linear decrease of η^* and can also be found for COPET_6.5_HOAc, where an excess amount of acetic acid impeded the full dissolution of cotton.

The gel formation is also portrayed by the missing crossover point (COP) of storage and loss modulus (G' , G'') (cf. Table 12), which usually indicates a transformation of the solution state from liquid to solid. Similar to η^* , it is determined by the cellulose' concentration and DP, but it is only marginally influenced by the temperature (Mezger 2006). When a gel is formed, no COP exists because G' remains higher than G'' throughout the whole shear rate range, which implies the presence of interlinked ordered cellulose clusters (Mezger 2018).

As a benchmark, spinnable solutions of virgin PHK pulp ($\eta=482\pm3$ ml/g, $PDI=3.6\pm0.3$, cf. Table 11) display a COP of around $\omega=0.42$ s⁻¹ and $G'=G''=2343$ Pa (cf. Uncoated Pulp in Table 12). On the contrary, virgin cotton exhibits an intrinsically much narrower MMD ($\eta=2032\pm50$ ml/g, $PDI=2.4\pm1.4$, cf. Pre-consumer cotton Table 11) than dissolving pulp, which can even be further decreased by wearing and laundering (Palme *et al.* 2014; Wedin *et al.* 2019). At similar concentrations, this translates to cellulose solutions with comparable angular frequencies ($\omega=0.18$ – 1.07 s⁻¹), but with significantly higher moduli ($G'=G''=3131$ – 6996 Pa). This also applies for pre-consumer cotton pretreated with acids or e-beam irradiation ($\omega=0.90$ – 1.07 s⁻¹, $G'=G''=3905$ – 6996 Pa) (Sixta

2006; Flory 1953 (1969)), while enzymatic treatments rendered cellulose more polydisperse ($\omega=0.53-0.61\text{ s}^{-1}$, $G'=G''=1630-2179\text{ Pa}$) (Pérez *et al.* 2002). Lower cellulose concentrations induce similar rheological effects. The viscous domain of the sample solutions is extended to higher shear rates ($\omega=1.40-6.90\text{ s}^{-1}$), whereas the moduli gradually decline ($G'=G''=1495-3224\text{ Pa}$) as DP and concentration decrease (cf. samples COPET_6.5, and COPET_10.5 in Table 12). Besides, the COP can be altered by changing the interactions between cellulose and the solvent. Nanomaterials, such as silica particles or carbon nanotubes, are known to affect the storage modulus of cellulose solutions, as they modify the hydrogen bonding pattern in the system (Czarnecki 2007; Rahatekar *et al.* 2009; Song *et al.* 2013). Presumably, the addition of noble metal nanoparticles had a comparable effect on the spin dope, which made the dynamic moduli undergo a noticeable elevation from 2343 Pa to 4242-4774 Pa.

The deviations in the rheological behavior also translated to the spinnability of the respective solutions. When filaments are extruded, the polymer chains pre-orientate in the spinneret, and further align once stretched in the air-gap (Fink *et al.* 2001). The success of this process again depends on the spinning temperature and the cellulose concentration employed as the liquid thread requires to withstand the forces created by the spinning process during extrusion (Ziabicki & Takserman-Krozer 1964a; Ziabicki & Takserman-Krozer 1964b). Therefore, lower concentrations (cf. COPET_6.5, COPET_6.5_HOAc, and COPET_10.5) and narrower MMDs (cf. dyed post-consumer cotton) were spun at lower spinning temperatures ($60-65^{\circ}\text{C}$) than samples with greater variation in their molecular weight fractions and higher cellulose content ($70-80^{\circ}\text{C}$, cf. pre-consumer cotton and nanoparticle coated pulp). These conclusions were not relevant for COPET_6.5_HOAc and Levafix Brilliant Red E-4BA due to their gel character. Their spinnability was unsatisfactory at all temperatures as their pre-defined network structure prevented further enhancement of the filament strength during spinning (Hauru *et al.* 2016). These circumstances consequently transferred to poor yields and fiber properties.

Under certain prerequisites, previous studies described the spinnability of cotton-based raw material dependent on the maximum draw ratio (DR) obtained: $\text{DR} < 2$ non-spinnable, 2-8 poor, 8-14 good, >14 excellent (Asaadi *et al.* 2016). However, these criteria only apply if the cellulose concentration is maintained in a standardized range (13-14 wt%). Once lowered, new categories need to be defined. For cotton spun from cotton polyester blends, we thus assigned $\text{DR} < 2$ as non-spinnable, 2-4 poor, 4-8 good, >8 excellent. As implied in Table 12, the solutions of COPET_6.5 and COPET_10.5 both showed good to excellent spinnability, which resulted in staple fibers with linear densities of 0.8 dtex and 1.7 dtex, respectively. As the former value already falls into the microfiber range, fibers thereof would qualify for speciality applications, while 1.7 dtex fibers could be used in common clothing. COPET_6.5_HOAc only exhibited a poor spinnability ($\text{DR}=4$), which led to weak 2.7 dtex staple fibers. Using a DR of 12, the remaining samples were converted to 1.0-1.4 dtex fibers dependent on their solubility and concentration in the IL.

Figure 23 illustrates their tenacities as a function of the Young's modulus.

Figure 23. Summary of all fibers spun in Papers II-IV ranging from pre- and post-consumer cotton to cotton polyester blends and nanoparticle coated wood pulp. The samples were plotted dependent on their tenacities and elastic moduli. Viscose, Tencel, and standard Ioncell fibers were added as a reference.

It is evident that the narrow MMD of dyed post-consumer cotton emerged into the highest tenacities (50.7-59.8 cN/tex) and elasticities (12.3-14.3 %) apart from Levafix Brilliant Red E-4BA, which was not spinnable at all. Fibers from nanoparticle coated pulp displayed similar properties (45.0-46.6 cN/tex, 11.5-13.1) to standard Ioncell fibers (49.9 cN/tex, 12.5%) although Ag containing samples appeared slightly more elastic. Concerning pre-consumer cotton, neither e-beam nor A allowed stable fiber spinning, which partially manifested in lower tenacities. In particular, the former caused substantially weaker filaments (40.3 cN/tex, 7.4%) as compared to A, EG-A, and A-EG (44.3-48.5 cN/tex, 8.9-12.8%). This difference can be attributed to the prevailing degradation triggered by radicals occurring during e-beam irradiation (Sixta 2006). In contrast, cotton obtained from textile blends led to stiffer fibers (7.3-9.0 %) with tenacities dependent on the cotton concentration employed. A cellulose concentration of 10.5 wt% raised the fiber strength to 44.6 cN/tex, while 6.5 wt% resulted in 20.5-36.6 cN/tex. Especially, the lower value is a result of an excess amount of acetic acid present in the solvent, which impeded the dissolution of cellulose and the reinforcement of a fibril structure during fiber spinning. The properties in wet state corresponded to this pattern, although no trend could be observed for the birefringence value Δn and total orientation factor f_t . This is also confirmed by Michud et al, who found that the fibril orientation in the fibers tends to stabilize above DRs higher than 6 (Michud, Hummel & Sixta 2016).

Eventually, this section demonstrated that both dissolution and fiber spinning are dependent on the same variables such as the dye and pretreatment type,

viscosity, MMD, concentration and temperature. As also indicated by Figure 23, especially the properties of the fibers regenerated from CO/PET blends could further be enhanced by increasing the spin dope concentrations through improved filtration procedures. This would enable a denser packing of the cellulose chains along the spinning direction, which would finally result in higher tenacities. Despite these obvious alterations, all fibers produced herein showed properties similar or even superior to commercial MMCFs, thus offering more sustainable pathways to textile industry.

5.4. Polyester in the Ioncell Process

At elevated temperatures, literature proposes various imidazolium based ILs as catalysts for the dissolution and degradation of PET (Wang *et al.* 2009). It is assumed that the choice of the anion affects the corrosiveness of the IL (Liu *et al.* 2009). As a powerful cellulose solvent, [BMIM] [OAc], for example, has been reported to dissolve small fractions of PET (3.4 wt%, 150°C), whereas [BMIM] [Cl] also enabled the hydrolysis of the polymer (Liu *et al.* 2009). Uncatalyzed, PET can be hydrolyzed in an aqueous environment at temperatures above 100°C (Buxbaum 1968).

When it comes to the separation of cotton polyester blends, ILs have yet been considered to preserve the molecular integrity of PET. Negulescu *et al.* and Brinks *et al.* were among the first ones to study the preparation of cellulose solutions from blends of synthetic fibers, but neither of them investigated the behavior of PET in the solvent (NMMO) (Brinks *et al.* 2013; Negulescu *et al.* 1998). Da Silva *et al.* utilized both, [AMIM] [Cl] and [BMIM] [OAc], to dissolve cellulose of cotton polyester yarns. The recovered PET fractions were characterized with a combination of DSC, TGA, FTIR and NMR. Although residual cellulose could be observed, neither of these methods detected any degradation of PET. The TGA even suggested an intact polymer structure as the melting point of PET remained unaffected throughout processing (Silva, Wang & Byrne 2014).

In this thesis, cotton polyester blends were treated with [DBNH] [OAc] to obtain a cellulose solution and a PET residue. In a similar manner, the TGA experiments did not indicate any influence of the separation procedure on the PET fractions. As shown in Figure 24a and Table 13, their onset temperatures (T_o) stayed largely unchanged ($T_o=393-397^\circ\text{C}$), although their molar mass distributions were altered significantly by the processing conditions employed (cf. Figure 24b). Therefore, it is a matter of the right analytical toolkit whether the degradation of PET can be observed.

Figure 24. TGA (a) and molar mass distribution of polyester before (Reference) and after separation with [DBNH] [OAc]. Images adapted from Paper II (Haslinger *et al.* 2019b).

Table 13. Polyester before (Reference) and after separation: Residual cellulose content, number average molar mass (Mn), weight average molar mass (Mw), polydispersity index (PDI), and onset temperature (T_o) dependent on the time (h) in [DBNH] [OAc]. Table adapted from Paper II (Haslinger *et al.* 2019b).

Sample	Time in IL / h	Cellulose / wt%	Mn / kDa	Mw / kDa	PDI	T_o / °C
Reference	0	48.8±6.7	9.2±0.3	23.5±0.2	2.6±0.2	-
PET from COPET_6.5	2	2.5±0.5	6.2±0.2	17.4±0.1	2.6±0.2	397
PET from COPET_6.5	3	1.7±0.4	4.4±0.1	12.0±0.1	2.8±0.2	398
PET from COPET_6.5_HOAc	3	2.0±0.4	7.1±0.2	19.5±0.1	2.7±0.2	393
PET from COPET_10.5	3	1.9±0.5	5.9±0.1	16.5±0.1	2.8±0.2	397

After 2h (80°C, cf. PET from COPET_6.5), Mn and Mw had already noticeably decreased from 9.2 kDa to 6.2 kDa and from 23.5 kDa to 17.4 kDa. This reduction amounted one third of the molecular weight and was further continued throughout the second washing step (80°C, 1h, Mn=4.4 kDa, Mw=12.0 kDa). A comparable decline also occurred for the PET regained from COPET_10.5, which was lowered to Mn=5.9 kDa and Mw=16.5 kDa. This is also represented by its bimodal MMD in Figure 24b, resulting from the consecutive addition of two different sample fractions. In contrast, an excess amount of HOAc (30%) in the mixture allowed to decrease the corrosiveness of the IL (Mn=7.1 kDa, Mw=19.5 kDa), while impeding the formation of cellulose filaments during dry-jet wet spinning. Unlike the MMD, the PDI of the samples (2.6-2.8) remained unchanged by the treatment in [DBNH] [OAc], which implies a uniform cleavage of the polymer structure.

Solid-state NMR, as described in chapter 5.1., determined the content of residual cellulose in the PET fractions (s. Table 13). The separation procedure could lower the cellulose concentration from 48.8 wt% to 2.5 wt% after one

washing step. With a repetition of the same protocol, the cellulose content further decreased to 1.7-2.0 wt% even if acetic acid was present.

Without a doubt, both mechanical and chemical stability are essential for PET to be reprocessed to new value-added products. Especially, melt spinning of textile grade fibers demands high quality substrates. Virgin PET exhibits a Mw above 30 kDa, but undergoes substantial hydrolysis once spun to filaments (Samperi *et al.* 2004). Similar to cellulose, the degradation continues during wearing and laundering. In post-consumer garments, the MMD of PET thus falls below the required criteria for respinning already before any processing is applied. Unfortunately, the method discussed herein further contributes to this process, although shorter dissolution times of cellulose in large scale reactors might reduce this effect to a minimum. Therefore, the recovered PET might rather be reused in depolymerization-repolymerization concepts (Sun *et al.* 2018) or in chain extension approaches (Awaja & Pavel 2005).

5.5. Dyes in the loncell Process

In Paper III, three vat (Indanthren Blue BC 3%, Indanthren Red FBB coll, and Indanthren Brilliant Green FBB coll) and four reactive dyes (Levafix Brilliant Red E-4BA, Levafix Blue E-GRN gran, Remazol Brilliant Blue R spec, and Remazol Black B gran 133%) were evaluated for their durability on pre- and post-consumer cotton throughout recycling (cf. Figure 25). Accordingly, we dyed white cotton fabrics, shredded, and dissolved them in [DBNH] [OAc] to spin new MMCFs.

Recyclable colorants need to survive a whole lifecycle of sunlight exposure, washing, and wearing. When clothing is disposed, it should still exhibit enough color strength, which can be transferred to a new textile product. Throughout dry-jet wet spinning, dyes should neither influence the solubility of the waste substrate nor impair the spinnability of the resulting solution (Tawiah & Asinyo 2016). Their chemical structure should also be resistant to the conditions of the process to avoid leaching into the spin bath, and contamination of the equipment (Bechtold & Manian 2006).

As stated earlier, the stability of dyes largely depends on their chemical structure. Vat dyes are composed of anthraquinone units that can be rendered water-soluble by reduction in an alkaline medium. Re-oxidation precipitates the colorants on the cellulose surface, where they are stabilized through electrostatic interactions. On the contrary, reactive dyes link to cellulose via covalent bonding, leading to a high stability of the chromophores (Mahapatra 2016). Similar to Indanthrens, it is also known that reactive dyes with anthraquinone groups are more tolerant to laundering and chemical bleaches (Bigambo *et al.* 2018).

Figure 25. Chemical structures of the vat and reactive dyes tested in this thesis. Image copied from Paper III (Haslinger *et al.* 2019c).

Accordingly, a similar correspondence can be expected for dyed waste garments recycled within the Ioncell technology. Table 14 displays the color coordinates (L^* , a^* , b^*) of dyed, post-consumer cotton fabrics, and the regenerated fibers produced thereof. L^* indicates the lightness of the samples, while a^* and b^* denote the red-green and yellow-blue values in the CIELAB space. ΔE represents the vector amount of the coordinates before and after recycling. Values of $\Delta E=0-0.5$ describe an unnoticeable color difference, while $\Delta E=0.5-1.0$ implies the smallest difference by visible human eye. $\Delta E=1.0-5.0$ represents a color change with increasing visibility, while results above 5.0 refer to a different color.

Table 14. Summary of the CIELAB parameters (L^* , a^* , b^*) of the dyed waste fabrics and the recycled, regenerated fibers produced thereof. Table adapted from Paper III (Haslinger *et al.* 2019c).

Samples	Waste Fabrics			Regenerated Fibers			ΔE
	L^*	a^*	b^*	L^*	a^*	b^*	
Indanthren Blue BC 3%	69.0 ± 0.3	-4.9 ± 0.3	-22.2 ± 1.1	56.6 ± 1.1	-6.6 ± 0.1	-14.0 ± 0.3	14.9
Indanthren Brilliant Red FBB	40.5 ± 1.0	49.1 ± 0.6	6.9 ± 0.4	39.5 ± 0.8	38.1 ± 0.7	12.9 ± 0.3	12.6
Indanthren Brilliant Green FBB Coll	37.0 ± 0.5	-46.9 ± 0.4	-1.4 ± 0.1	34.5 ± 0.4	-38.4 ± 0.1	-0.9 ± 0.1	8.8
Remazol Black B gran 133%	18.7 ± 0.3	-5.0 ± 0.1	-16.2 ± 0.2	35.6 ± 1.2	15.6 ± 0.3	6.2 ± 0.2	25.6
Remazol Brilliant Blue R spec	43.0 ± 0.6	-1.8 ± 0.1	-39.7 ± 0.3	56.9 ± 3.1	0.7 ± 0.7	-20.7 ± 0.4	23.6
Levafix Brilliant Red E-4BA	41.9 ± 0.3	62.0 ± 0.3	0.01 ± 0.2	-	-	-	-
Levafix Blue E-GRN gran	37.5 ± 0.9	-1.5 ± 0.1	-31.97 ± 0.3	35.3 ± 1.4	-3.5 ± 0.5	-23.3 ± 0.6	9.2

Besides Indanthren Brilliant Red FBB coll., all dyes dissolved in [DBNH] [OAc] at elevated temperatures. On the cellulose substrate, this led to uniform spinning solutions, which formed, apart from Levafix Brilliant Red E-4BA, strong, colored filaments with consistent amounts of dye throughout the fiber matrix. Nonetheless, all samples experienced a pronounced color change ($\Delta E=8.8$ -25.6) induced by the recycling process.

Under adequate conditions, [DBNH] [OAc] causes an alkaline environment, which can reduce vat dyes to their water-soluble form. This may weaken the interactions between the cellulose structure and the dyes, eventually resulting in a decrease of substantivity. On the contrary, Levafix dyes show two functional groups that can covalently bind to cellulose via nucleophilic substitution. Although hydrolysis might occur, it is more likely that these dyes remain linked to cellulose due to the presence of two dye-fiber bonds (Mahapatra 2016). Consequently, both Indanthren and Levafix dyes displayed color differences in a comparable range ($\Delta E=8.8$ -14.9), while the Remazol derivatives leached into the spinbath substantially ($\Delta E=23.6$ -25.6).

The leaching is also confirmed by UV spectra of pure dye in water and the spin bath after the respective spinning procedures (s. Figure 26). The absorption maxima of Remazol Brilliant Blue R spec in water and in the spinbath appeared at similar positions (590 nm, 587 nm), indicating a wash-off of unreacted dye. In contrast, the signal of Remazol Black B gran 133% shifted to shorter wavelengths (597-574 nm) when subjected to the spinning process, which may be attributed to a certain degree of degradation in the chromophore.

Overall, the spinning of dyed cotton waste led to an increase in the yellowness (b^*) of all samples, whereas the leaching of the Remazol derivatives enhanced their lightness (L^*). The rest of the fibers exhibited a decrease in L^* with no conclusive change in redness (a^*).

Figure 26. UV spectra of the Remazol Brilliant Blue R spec and Remazol Black B gran 133% dissolved in deionized water and when leached into the spinbath. Image copied from Paper III (Haslinger *et al.* 2019c).

It is evident that the documented alterations are a consequence of an incomplete dye removal through laundering, changes in the interactions between the dyes and cellulose, as well as surface phenomena. In particular, the latter is affected by the dissolution and regeneration of the polymer substrate altering fiber shininess and distribution of the dyes in the cellulose matrix.

5.6. Gold and Silver Nanoparticles in the Ioncell Process

In particles smaller than 100 nm, electromagnetic irradiation can induce a collective oscillation of the electrons on the metal surface (Kelly *et al.* 2003). The absorption of light depends on the particle size and shape, and can lead to a large spectrum of vivid colors (Eustis & El-Sayed 2006). Due to a restricted aspect ratio, spherical nanoparticles can only show colors from brown to yellow (Ag) (Chen *et al.* 2015; Cai *et al.* 2009; Smiechowicz *et al.* 2011), or purple to orange (Jain *et al.* 2006).

Figure 27 depicts the absorbance spectra and color coordinates of Au, AgAu, and AgNP coated pulps and the regenerated fibers made thereof. The position of the surface plasmon band correlates with the size of the nanoparticles (Eustis & El-Sayed 2006). During hydrothermal synthesis, the reducing end groups of cellulose reduce metal ions to their elemental form. In particular, Ag tends to form aggregates in the cellulose matrix, which can result into a widening of the absorption maximum at 420 nm (Su *et al.* 2003). With the dissolution of cellulose, the agglomeration is broken up, and the SPB becomes narrower at similar wavelengths. At 420 nm, the shift indicated a particle diameter of 20-25 nm (Lee *et al.* 2008), while Au and AgAuNPs showed a distinct redshift. Therefore, their SPBs could be found at 540 and 510 nm, indicating a particle size of 40-60

nm (Au) (Njoki *et al.* 2007) and 10-20 nm (AgAu) (Shin *et al.* 2008), respectively. Moreover, the absence of a second SPB regarding the AgAuNPs confirmed the formation of an alloy of gold and silver rather than element specific nanoparticles (Shin *et al.* 2008).

Figure 27 (a) Absorbance spectra and (b) color coordinates L^* , a^* , and b^* of AuNP, AgAuNP, and AgNP coated pulp and fibers. Image copied from Paper IV (Haslinger *et al.* 2020).

After dry-jet wet spinning, the Lab values of all samples decreased, which represented a fading of color in all respects. However, as discussed in the wash fastness section below, the nanoparticle yield remained constant throughout the spinning process. Accordingly, it can be assumed that dissolution and regeneration removed parts of the nanoparticles from the cellulose surface and incorporated them more homogeneously in the fiber matrix (s. Figure 28), which led to a decline in color and luster. Despite this, size and shape of the substrates were not affected by the spinning technology.

Figure 28. (a) TEM images of a fiber cross section containing AuNPs, (b) SEM image of AuNPs on the fiber surface. Images merged from Paper IV (Haslinger *et al.* 2020).

5.7. Yarn Spinning, Fabrics, and Demo Products

The success of yarn spinning relies on appropriate spin finish, sufficient fiber strength, and frictional resistance to slippage (Oxtoby 2014). Treatment in Lemin PN and Aflin CVS intended to lower both cohesion and electrostatic interactions between the single fibers to allow facilitated processing. As moisture serves as lubricant, conditioning overnight (23°C, 65% relative humidity) further improved the spinnability of the yarns. Overall, it is known that up to 70% of the fiber strength can translate to the yarn (Klein 1998). Although twisting reduces slippage, it challenges the fiber tenacity as the angle of fiber inclination increases (Oxtoby 2014). However, high yarn strength may be relinquished in favor of homogeneity and improved touch.

In this thesis, the fibers of Papers III and IV were spun to yarns and further converted to different fabrics and various demo products. Table 15 depicts linear density, yarn twist multiples (TM), tenacity and elongation at break of the respective samples.

Table 15. Linear density (titer), yarn twist multiples (TM), tenacity, and elongation at break of the yarns spun from the regenerated fibers of dyed, pre- and post-consumer cotton, as well as from nanoparticle coated pulp. Yarns from commercial cotton, Viscose and Tencel, as well as a yarn from loncell fibers produced under standard conditions (Uncoated Yarn) were added as references. Tables merged and modified from Papers III and IV (Haslinger *et al.* 2019c; Haslinger *et al.* 2020).

	Sample	Titer / tex	TM	Tenacity / (cN/tex)	Elong. / %
Paper III	Pre-Consumer				
	Indanthren Blue BC 3%	17.8±1.5	3.09	25.0±4.7	7.6±0.9
	Post-Consumer				
	Indanthren Brilliant Red FBB	21.7±1.7	3.41	28.8±3.8	6.9±0.5
	Indanthren Brilliant Green FFB Coll	20.8±1.8	3.34	28.9±3.6	6.4±0.5
	Remazol Black B gran 133%	25.3±0.5	3.68	29.0±3.4	7.1±0.5
	Remazol Brilliant Blue R spec	21.2±1.0	3.37	32.7±3.9	6.9±0.5
Paper IV	Levafix Blue E-GRN gran	21.5±0.9	3.39	31.4 ± 4.4	6.7±0.6
	Uncoated Yarn	22.9±1.1	3.50	30.9±3.4	8.1±0.9
	Yarn with AuNPs	20.5±1.1	3.31	20.5±6.2	6.0±0.9
	Yarn with AgAuNPs	21.8±0.5	3.42	26.2±3.4	7.1±0.5
	Yarn with AgNPs	22.3±1.0	3.46	26.9±4.0	8.0±0.5
	Commerical Yarns				
	Tencel TM	19.9±0.3	-	22.3±1.7	7.7±0.7
	Cotton	21.1±0.5	-	14.4±1.2	5.9±0.3
	Viscose	20.5±0.2	-	13.9±1.0	13.7±0.9

Despite distinct pretreatments, all fibers of Indanthren Blue BC 3% were merged, and spun to one batch of yarn to produce a baby jacket (s. Figure 29a). The remaining fibers were processed in separate batches, which were used to manufacture a blue scarf (b), several colored, single jersey fabrics (c), and a knit structure of Au, AgAu, and AgNP coated fibers (d). Although a target count of 22 tex was pursued, the yarns' titers varied from 21.2-25.3 tex due to the use of lab-scale equipment.

Figure 29. On the left: Baby jacket knitted from recycled Indanthren Blue BC 3% (a), scarf manufactured from Remazol Brilliant Blue R spec. (b), and dyed post-consumer fabrics before recycling, and fabrics made thereof after dissolution and re-spinning (c). On the right: Fabric made from nanoparticle coated fibers, with AuNPs on the left, with AgAuNPs on the stripe in the middle, and with AgNP in the yellow section on the right (d). Pictures copied from Paper III and Paper IV (Haslinger *et al.* 2019c; Haslinger *et al.* 2020).

In case of Indanthren Blue BC 3%, a lower linear density (17.8 tex) was targeted to enable the knitting of a denser interlock structure. Its reduced titer evolved into lower yarn strength (25.0 cN/tex) and increased elongation (7.6 %) as compared to the regenerated fibers from dyed post-consumer cotton (28.8-31.4 cN/tex, 6.4-7.1%). The properties of the yarns with noble metal nanoparticles (20.5-26.9 tex, 6.0-8.0%) were similar to Indanthren Blue BC 3% despite higher linear densities (20.5-22.3 tex). This deviation resulted from the utilization of different raw materials, which emerged as weaker filaments during dry-jet wet spinning. In addition, also the twist influences the yarn properties. With increased TM values, the yarn becomes stronger, while its softness declines (Lord 2003). This could be observed for ‘Uncoated Yarn’ (TM=3.50), which showed a significantly higher tenacity (30.9 cN/tex) than the other samples in Paper IV (TM=3.31-3.46). In contrast, dyes and nanoparticles were assumed to have a negligible impact on the yarn properties.

5.8. Wash and Rubbing Fastness of Dyed Fabrics and Nanoparticle Containing Yarns

Dyes and finishes are supposed to exhibit high durability to laundering to keep the environmental impact of textiles low, while maintaining their quality. Accordingly, the assessment of wash and rubbing fastness helps to estimate the potential color stability of fabrics and their staining onto other garments based on a standardized procedure (cf. EN ISO 105-C06 and EN ISO 105-X12:2016).

In general, vat dyes (Indanthrenes) and reactive dyes (Remazol and Levafix) display good wash fastness properties. While the former are water insoluble, the latter establish covalent bonds to cellulose. Remazol Brilliant Blue R spec attaches to the hydroxyl groups of cellulose via a nucleophilic addition reaction on its vinyl sulphone group (Mahapatra 2016). During dyeing, this type of dye is likely to undergo hydrolysis reactions, which can lower the final dye exhaustion.

The same applies for Remazol Black B 133%, but the effect is less pronounced due to the presence of a bifunctional system (Lewis 2014). In a similar manner, the functional groups of Levafix dyes have been observed to be susceptible to competing hydrolysis in aqueous media (Clark 2011). However, a sufficient boil-off of unreacted dyes after dyeing can reduce this phenomenon.

Therefore, all dyes tested in this thesis showed excellent wash fastness properties ranging from 4-5 on a greyscale rating (s. Table 16). In contrast, their lower rubbing fastness could be attributed to the superficiality of the coloring process. The largest amount of dye is usually applied on the fiber surface, where a more facile abrasion is possible. In wet state, some dyes can also partly dissolve in water, further reducing the rubbing fastness of the fabrics.

However, dissolution and regeneration distributed the dyes more evenly along the fiber cross section, leading to enhanced fastness properties in all aspects.

Similar results were obtained from the incorporation of noble metal nanoparticles into Ioncell fibers. Their entrapment in the polymer matrix resulted in the preservation of NP-yield and color throughout the laundering process (s. Table 16). Overall, it is known that AuNPs tend to have a higher affinity to cellulose than AgNPs (Tang *et al.* 2015b; Ilić *et al.* 2009). Especially in dip coating or *in-situ* reduction approaches, substantial release of nanoparticles occurs after the first few laundering steps. Subsequently, the leaching stabilizes and a residual amount remains on the garment (Tang *et al.* 2015b; Tang *et al.* 2014; Tang *et al.* 2013). Inevitably, this loss is accompanied by a decrease in functionality and thus needs to be compensated for using higher starting amounts. On the contrary, the incorporation of nanoparticles minimizes leaching, of both AgNPs and AuNPs, so that the functionalized fibers can withstand laundering without any loss in performance.

5.9. UV Protection of Nanoparticle Containing Ioncell Fabrics

One important feature of clothing is to protect human skin from excessive exposure to potentially dangerous UV radiation (Muthu 2017). A fabric's capability to shield UV light depends on the fiber type, garment structure, and color employed (Louris *et al.* 2018). Moreover, additives such as noble metal nanoparticles or titanium oxide enable to alter its UV protection properties (Louris *et al.* 2018; Tang *et al.* 2015a; Vigneshwaran *et al.* 2007; Tang *et al.* 2014; Zheng *et al.* 2013). Among all fibers, polyester shows the lowest transmission of UV light, whereas cotton allows more light to pass (Louris *et al.* 2018). With UPFs lower than 5, most summer clothing is an insufficient barrier to sunlight (Gambichler *et al.* 2001). The UPF describes how many times a fabric enhances the human's skin ability to withstand sunlight without damage. Excellent shielding is provided by clothing with a UPF higher than 40, whereas values between 25-39 imply very good, 15-24 good, and 0-14 poor protection.

In this thesis, Ag, AgAu, and AuNP containing Ioncell fibers were knitted or woven to fabrics and evaluated according to their transmission to UVA (290-

315 nm) and UVB light (315-400 nm). The results are summarized in Table 17 (cf. EN 13758-1:2001 + A1).

Table 17. Summary of Ag, AgAu, and AgNP containing knits and wovens including their cover factor (CF), T(UVA) (%), T(UVB) (%), and UPF. The table was copied from Paper IV (Haslinger *et al.* 2020).

Sample		CF ³	T(UVA) / %	T(UVB) / %	UPF
Knitted fabric	Uncoated Fabric	3.4	25.8±2.7	19.6±2.6	4.9±0.7
	Fabric with AuNPs	3.2	22.9±1.9	19.8±1.9	4.9±0.5
	Fabric with AgAuNPs	3.3	23.2±2.2	19.9±2.2	4.9±0.5
	Fabric with AgNPs	3.3	23.3±2.3	21.3±1.7	4.6±0.4
Woven fabric ⁴ (24 threads/cm)	Uncoated Fabric	19.9	8.8±0.6	3.7±0.4	22.5±2.1
	Fabric with AuNPs	18.8	4.2±1.0	2.1±0.7	43.2±14.6
	Fabric with AgAuNPs	19.4	3.6±1.1	1.8±0.6	49.6±12.4
	Fabric with AgNPs	19.6	5.7±2.7	3.5±1.1	26.8±8.2

The use of noble metal nanoparticles did not have any influence on the UV protection properties of the knitted fabrics. As their cover factors were intrinsically low (3.2-3.4), significantly more UV light penetrated their structure than what could be shielded by Au, AgAu and AgNPs (UPF=4.6-4.9). Similar research on single jersey cotton fabrics reported UPF values below 15 with comparable machinery (Louris *et al.* 2018). In contrast, the woven fabrics showed higher cover factors initially (18.8-19.9), which led to a more pronounced shielding effect. Au containing wefts resulted in the highest UPF values (UPF=43.2-49.6) absorbing UV light over the entire spectrum (T(UVA)=3.6-4.2, T(UVB)=1.8-2.1). The incorporation of AgNPs mainly reduced the transmission of UV light in the UVA range (UPF=26.8, T(UVA)=5.7, T(UVB)=3.5, UPF=26.8). It is likely that higher nanoparticle amounts could have further enhanced the UV resistance of the fabrics tested, as commercial sun protective clothing employs more than a hundredfold of TiO₂ to obtain UPF values above 50 (Roshan 2015).

5.10. Unpublished Results: Recycling of Mixed Post-Consumer Cellulose Waste

The aim of the study below was to upcycle post-consumer cellulose-based textile waste of unknown origin and composition to new MMCs via the Ioncell technology. The fabrics displayed different colors such as white, grey, blue and purple and were assumed to be manufactured either from Viscose or cotton fibers. The idea was to avoid as many unnecessary pretreatment steps as possible, while testing different eco-friendly methods to adjust the cellulose' degree of polymerization. This study represented the basis for the investigations conducted in Paper III and pinpointed some major obstacles in textile recycling.

³ The cover factor was calculated as described in Horrocks & Anand (2000).

The cellulose based textile waste was supplied by a textile recycling company (Texaid, Switzerland). Texaid sorts textile waste according to quality. While well-preserved garments are resold, clothing of worse condition is converted to cleaning rags or insulation material. The waste fraction obtained for this study had a quality below these criteria and would have been burned under other circumstances. Prior to recycling, the samples were sorted according to color and texture, which led to five different species to be identified (i.e. 1 Viscose and 4 cotton).

As stated earlier, the optimum limiting viscosity of a cellulose substrate spun in the Ioncell process ranges from 400-500 ml/g (Sixta *et al.* 2015). Virgin cotton samples usually show viscosities a fourfold beyond this range, whereas Viscose fibers commonly display viscosities around 200 ml/g. Table 18 depicts the limiting viscosities η , mass average molar mass M_w , and PDI of the raw materials (1-5). Compared to cotton in 3 and 5 (η =1465-1729 ml/g), 1 and 4 showed considerably low viscosities (η =805-1050 ml/g). Therefore, they were blended with the Viscose sample 2 (η =188 ml/g) to obtain an overall viscosity of about 450 ml/g. Moreover, parts of samples 1, 3, 5 were treated with 0.2 M H_2SO_4 to lower their degree of polymerization. In previous studies, we found that cotton samples, which undergo acid hydrolysis, tend to show considerably narrow MMDs potentially unsuitable for dry-jet wet spinning (Asaadi *et al.* 2015). Standard dissolving pulp was hence added to parts of sample 3 and 5. Subsequently, all DP-adjusted samples were dissolved in [DBNH] [OAc] and spun to staple fibers as implied in the experimental section.

The spinnability of the blended samples (1+2 and 2+4) was limited, also resulting in lower tensile strength (32.4 cN/tex) as compared to virgin pulp (50.5 cN/tex) and the substrates pretreated with H_2SO_4 (45.6-54.3 cN/tex) (cf. Table 18). In the case of sample 2+4, this is explained by the gel like behavior of the spinning solution indicated by the high apparent zero shear viscosity (97 500 Pa s) and the absence of the crossover point of storage and loss modulus close to the spinning temperature (80°C) (Mezger 2006). These results agree with Papers II-III, where gelled solutions were accompanied by bad spinnability. In contrast, the mixing of H_2SO_4 pretreated cotton (3b and 5b) with virgin dissolving pulp did not affect the spinnability significantly despite an increased PDI (2.7-3.3), which however contributed to an improved elongation (9.2-11.0 %).

Similar to Paper III, another target of this study was to avoid bleaching before respinning, while maintaining the original color of the samples throughout upcycling. Nonetheless, all samples leached dyestuff during dissolution and regeneration leading to a decrease in redness and an increase in yellowness. The lightness L^* was altered inconclusively (s. Figure 30a).

The successfully produced fibers were ring spun and knitted to a jacquard fabric, which is presented in Figure 30b. Besides of Viscose, it could be demonstrated that the Ioncell process even allows to upcycle cellulose based post-consumer waste of unknown origin with a minor amount of chemicals employed, still enabling the production of high-quality products. However, the stability of the dyes was affected during dissolution and re-spinning, implying that the recyclability of garments is also a factor of the colorant (cf. Paper III).

Table 18. Summary of the raw material properties such as limiting viscosity (η) and weight average molar mass Mw, pretreatment conditions, dope parameters including zero shear viscosity (η_0^*) and storage and loss modulus (G' , G''), and fiber properties.

Raw Material			Dope / 80°C				DR12 Fibers (cond.)			
Sample	Pretreatment	η / ml/g	Mw	PDI	η_0^* / Pa*s	G'=G'' / Pa	ω / s ⁻¹	Titer / dtex	Tenacity / (cN/tex)	Elongation / %
1	no	1050	693.0		2.3	-	-	-	-	-
2	no	188	96.7		2.0	-	-	-	-	-
3	no	1465	972.2		2.2	-	-	-	-	-
4	no	805	451.0		3.7	-	-	-	-	-
5	no	1729	940.7		2.7	-	-	-	-	-
1+2	mixing	493	697.4		3.7	24900	815	0.22	1.5	32.4
2+4	mixing	479	195.3		2.4	97500	-	-	-	7.9
1b	H ₂ SO ₄ , 30 min	558	296.9		2.2	29800	2399	0.24	1.1	54.3
3b	H ₂ SO ₄ , 15 min	425	252.6		1.9	-	-	-	-	9.5
5b	H ₂ SO ₄ , 15 min	490	301.8		2.3	37500	2547	0.31	1.3	45.6
3b+pulp	50:50	n.a.	294.9		3.3	24200	2897	0.63	1.9	45.0
5b+pulp	50:50	n.a.	308.5		2.7	26800	2005	0.33	1.3	40.3
pulp	no	502	262.9		3.6	26100	3558	0.79	1.2	50.5
										12.7

Figure 30. (a) CIELAB data for the samples with high spinnability before and after spinning, (b) jacquard fabric knitted from the recycled fibers.

6. Conclusions

The creation of a circular economy in textile industry represents a complex venture, which demands adequate sorting and characterization equipment, approaches to recycle textile blends and colored waste material, and green alternatives to reduce the amount of chemicals and resources used in textile products. This thesis attempted to tackle these problematics at different stages of the value chain to provide a sustainable pathway towards waste reduction.

A closed loop economy begins with a viable method for material identification. In this work, it could be demonstrated that solid-state NMR reliably quantifies cellulose in polyester blends, if an appropriate calibration model is applied. This knowledge offers a useful analytical toolkit for lab-scale analyses or future, commercial at-line measurements. More importantly, the Ioncell technology enabled, besides cardboard and wastepaper, to upcycle cotton polyester blends and various streams of colored cotton waste. The spun fibers showed properties superior to commercial MMCFs such as Viscose and Tencel and could reach titers down to the microfiber range. Their tensile strength was largely dependent on the origin of the waste substrate, as post-consumer samples evolved to higher tenacities than pretreated, pre-consumer waste. It was also found that Viscose substrates impeded the spinning process and decreased the tensile properties. Contrary to Remazols, Indanthren and Levafix derivatives proved to be stable dyes, which could be translated to pristine staple fibers. This was also confirmed by wash fastness testing and various demonstration products. Eventually, gold and silver nanoparticles incorporated into Ioncell fibers achieved UV resistance and coloring simultaneously, thereby reducing the overall input of chemicals into the process chain.

Nonetheless, further optimizations are needed to transfer these approaches to a commercial scale. Unfortunately, polyester degraded to some extent, when treated with [DBNH] [OAc], which limits its recyclability to depolymerization or chain extension concepts. The recycling of textile waste also demands a steady supply chain and technologies that can distinguish between colors, quality and obsolescence. Moreover, the synthesis methods for noble metal nanoparticle restrict either their sustainability or their appearance. More eco-friendly approaches for shape control would thus promote their versatility in textile products.

References

- Asaadi, S, Hummel, M, Hellsten, S, Härkäsalmi, T, Ma, Y, Michud, A & Sixta, H 2016, 'Renewable High-Performance Fibers from the Chemical Recycling of Cotton Waste Utilizing an Ionic Liquid', *ChemSusChem*, vol. 9, no. 22, pp. 3250–3258.
- Atalla, RH & VanderHart, DL 1999, 'The Role of Solid State ^{13}C NMR Spectroscopy in Studies of the Nature of Native Celluloses', *Solid State Nuclear Magnetic Resonance*, vol. 15, pp. 1–19.
- Awaja, F & Pavel, D 2005, 'Recycling of PET', *European Polymer Journal*, vol. 41, no. 7, pp. 1453–1477.
- Bacciarelli-Ulacha, A, Rybicki, E, Matyjas-Zgondek, E, Pawlaczyk, A & Szyrkowska, MI 2014, 'A New Method of Finishing of Cotton Fabric by in Situ Synthesis of Silver Nanoparticles', *Industrial & Engineering Chemistry Research*, vol. 53, no. 11, pp. 4147–4155.
- Bai, S, Hu, JZ, Pugmire, RJ, Grant, DM, Taylor, CMV, Rubin, JB & Peterson, EJ 1998, 'Solid State NMR and Wide Angle X-ray Diffraction Studies of Supercritical Fluid CO_2 -Treated Poly(ethylene terephthalate)', *Macromolecules*, vol. 31, no. 26, pp. 9238–9246.
- Barot, AA & Sinha, VK 2015, 'Chemical Scavenging of Post-Consumed Clothes', *Waste Management (New York, N.Y.)*, vol. 46, pp. 86–93.
- Bartsch, P & Ruef, H, *Method for Producing Cellulosic Moulded Bodies* 1999, Austria WO 99/46434.
- Barud, HS, Barrios, C, Regiani, T, Marques, RFC, Verelst, M, Dexpert-Ghys, J, Messaddeq, Y & Ribeiro, SJL 2008, 'Self-Supported Silver Nanoparticles Containing Bacterial Cellulose Membranes', *Materials Science and Engineering: C*, vol. 28, no. 4, pp. 515–518.
- Bechtold, T & Manian, AP, *Verfahren zur Herstellung eines Gefärbten Cellulosischen Formkörpers* 2006, Austria WO2007070904A1.
- Bentivoglio, G, Röder, T, Fasching, M, Buchberger, M, Schottenberger, H & Sixta, H 2006, 'Cellulose Processing with Chloride-Based Ionic Liquids', *Lenzinger Berichte*, vol. 86, 154–161.
- Bhardwaj, V & Fairhurst, A 2010, 'Fast fashion. Response to Changes in the Fashion Industry', *The International Review of Retail, Distribution and Consumer Research*, vol. 20, no. 1, pp. 165–173.

- Bigambo, P, Liu, H, Broadbent, PJ, Carr, CM & Rigout, M 2018, 'Surface Chemical and Colorimetric Analysis of Reactively Dyed Cellulosic Fabric. The Effect of ISO 105 CO9 Laundering and the Implications for Waste Cellulosic Recycling', *Dyes and Pigments*, vol. 148, pp. 91–98.
- Björquist, S, Aronsson, J, Henriksson, G & Persson, A 2017, 'Textile Qualities of Regenerated Cellulose Fibers from Cotton Waste Pulp', *Textile Research Journal*, vol. 88, no. 21, pp. 2485–2492.
- Blanco, M, Coello, J, Iturriaga, H, Maspoch, S & Bertran, E 1994, 'Analysis of Cotton-Polyester Yarns by Near-infrared Reflectance Spectroscopy', *Analyst*, vol. 119, pp. 1779–1785.
- Boer Group Recycling Solutions 2019, *SIPTex. Swedish Innovation Platform for Textile Sorting*, Boer Group Recycling Solutions. Available from: <http://boergroup-recyclingsolutions.com/projects/siptex-swedish-innovation-platform-for-textile-sorting/> [13 November 2019].
- Boiten, VJ, Han, SL-C & Tyler, D 2017, *Textile Collection Strategies to Support Material Circularity*, Online. Available from: http://www.resyntex.eu/images/downloads/ValrieJBoiten_Textile_collection_strategies.pdf [13 November 2019].
- Boufi, S, Ferraria, AM, do Rego, AMB, Battaglini, N, Herbst, F & Vilar, MR 2011, 'Surface Functionalisation of Cellulose with Noble Metals Nanoparticles through a Selective Nucleation', *Carbohydrate Polymers*, vol. 86, no. 4, pp. 1586–1594.
- Braungart, M & McDonough, W 2008, *Cradle to Cradle. Remaking the Way we Make Things* / Michael Braungart & William McDonough, Jonathan Cape, London.
- Brinks, GJ, Bouwhuis, GH, Agrawal, PB & Gooiher, H, *Processing of Cotton-Polyester Waste Textile* 2013, Netherlands WO 2014/081291 A1.
- Bukhari, MA, Carrasco-Gallego, R & Ponce-Cueto, E 2018, 'Developing a National Programme for Textiles and Clothing Recovery', *Waste Management & Research: The Journal of the International Solid Wastes and Public Cleansing Association, ISWA*, vol. 36, no. 4, pp. 321–331.
- Bumbudsanpharoke, N & Ko, S 2015, 'In-situ Green Synthesis of Gold Nanoparticles using Unbleached Kraft Pulp', *BioResources*, vol. 10, no. 4.
- Buxbaum, LH 1968, 'The Degradation of Poly(ethylene terephthalate)', *Angewandte Chemie International Edition in English*, vol. 7, no. 3, pp. 182–190.
- Cai, J, Kimura, S, Wada, M & Kuga, S 2009, 'Nanoporous Cellulose as Metal Nanoparticles Support', *Biomacromolecules*, vol. 10, no. 1, pp. 87–94.
- Cao, J, Sun, T & Grattan, KTV 2014, 'Gold Nanorod-Based Localized Surface Plasmon Resonance Biosensors: A review', *Sensors and Actuators B: Chemical*, vol. 195, pp. 332–351.
- Carlsson, J, Torstensson, H, Pal, R & Paras, MK 2015, *Re:Textile - Planning a Swedish Collection and Sorting Plan for Used Textiles*, Online. Available from: <https://pdfs.semanticscholar.org/5ed7/e31584bad9ed116ca3e1f27a64940e6fd661.pdf> [13 November 2019].
- Chattopadhyay, DP 2011, 'Chemistry of dyeing' in *Handbook of Textile and Industrial Dyeing*, Elsevier, pp. 150–183.

- Chen, H, Tan, C, Lin, Z & Wu, T 2018, 'Rapid Determination of Cotton Content in Textiles by Near-Infrared Spectroscopy and Interval Partial Least Squares', *Analytical Letters*, vol. 51, no. 17, pp. 2697–2709.
- Chen, JY, Sun, L, Jiang, W & Lynch, VM 2015, 'Antimicrobial Regenerated Cellulose/Nano-Silver Fiber without Leaching', *Journal of Bioactive and Compatible Polymers*, vol. 30, no. 1, pp. 17–33.
- Chen, X, Zhang, Y, Cheng, L & Wang, H 2009, 'Rheology of Concentrated Cellulose Solutions in 1-Butyl-3-methylimidazolium Chloride', *Journal of Polymers and the Environment*, vol. 17, no. 4, pp. 273–279.
- Circle Economy 2019, *Fibersort*, Circle Economy. Available from: <https://www.circle-economy.com/case/fibersort/#.Xcv1z1cza70> [13 November 2019].
- Clark, M 2011, *Handbook of Textile and Industrial Dyeing*, Woodhead Publishing, Cambridge, UK.
- Claudio, L 2007, 'Waste Couture. Environmental Impact of the Clothing Industry', *Environmental Health Perspectives*, vol. 115, no. 9, A 448-A 454.
- Cleve, E, Bach, E & Schollmeyer, E 2000, 'Using Chemometric Methods and NIR Spectrophotometry in the Textile Industry', *Analytica Chimica Acta*, vol. 420, no. 2, pp. 163–167.
- Colletti, RF & Mathias, LJ 1988, 'Solid State C-13 NMR Characterization of Textiles: Qualitative and Quantitative Analysis', *Journal of Applied Polymer Science*, vol. 35, pp. 2069–2074.
- Cowan, JC, *Method of Recovering Polyester Fibers and Cellulosic Powder from Polyester/Cotton Textile Waste* 1981, United States 4345039.
- Cuissinat, C & Navard, P 2006, 'Swelling and Dissolution of Cellulose Part 1: Free Floating Cotton and Wood Fibres in N-Methylmorpholine-N-oxide–Water Mixtures', *Macromolecular Symposia*, vol. 244, no. 1, pp. 1–18.
- Cura, K & Rintala, N 2019, 'Using NIR Technology to Identify Value in Waste Textile Streams', *AUTEX 2019*.
- Czarnecki, P 2007, 'Thermal and Rheological Characterization of Cellulose Spinning Dopes Modified with Nanosilica and Antibacterial Agents', *Polymers for Advanced Technologies*, vol. 18, no. 10, pp. 845–852.
- Dahlbo, H, Aalto, K, Eskelinen, H & Salmenperä, H 2017, 'Increasing Textile Circulation—Consequences and Requirements', *Sustainable Production and Consumption*, vol. 9, pp. 44–57.
- Dong, BH & Hinestroza, JP 2009, 'Metal Nanoparticles on Natural Cellulose Fibers: Electrostatic Assembly and In Situ Synthesis', *ACS Applied Materials & Interfaces*, vol. 1, no. 4, pp. 797–803.
- Ellen MacArthur Foundation 2017, 'A New Textiles Economy: Redesigning Fashion's Future'. Available from: <http://www.ellenmacarthurfoundation.org/publications>.
- Eltz, A von der, *Recycling of Dyed Cellulosic Waste* 1995, United States.
- Emam, HE, Mowafi, S, Mashaly, HM & Rehan, M 2014, 'Production of Antibacterial Colored Viscose Fibers Using In Situ Prepared Spherical Ag Nanoparticles', *Carbohydrate Polymers*, vol. 110, pp. 148–155.

- English, AD 1984, 'Macromolecular Dynamics in Solid Poly(ethylene terephthalate): Proton and Carbon-13 Solid-State NMR', *Macromolecules*, vol. 17, pp. 2182–2192.
- Espinoza, E, Przybyla, J & Cox, R 2006, 'Analysis of Fiber Blends Using Horizontal Attenuated Total Reflection Fourier Transform Infrared and Discriminant Analysis', *Applied Spectroscopy*, vol. 60, no. 4, pp. 386–391.
- European Commission 2019, *Textiles for Textiles*, European Commission. Available from: <https://ec.europa.eu/environment/eco-innovation/projects/en/projects/t4t>.
- Eustis, S & El-Sayed, MA 2006, 'Why Gold Nanoparticles are More Precious than Pretty Gold: Noble Metal Surface Plasmon Resonance and Its Enhancement of the Radiative and Nonradiative Properties of Nanocrystals of Different Shapes', *Chemical Society Reviews*, vol. 35, no. 3, pp. 209–217.
- Farah, S, Tsach, T, Bentolila, A & Domb, AJ 2014, 'Morphological, Spectral and Chromatography Analysis and Forensic Comparison of PET Fibers', *Talanta*, vol. 123, pp. 54–62. Available from: <http://www.sciencedirect.com/science/article/pii/S0039914014000526>.
- Fink, H-P, Weigel, P, Purz, HJ & Ganster, J 2001, 'Structure Formation of Regenerated Cellulose Materials from NMMO-Solutions', *Progress in Polymer Science*, vol. 26, no. 9, pp. 1473–1524.
- Flory, PJ 1953 (1969), *Principles of Polymer Chemistry*, Cornell University Press, S.I.
- Gabrielse, W, Angad Gaur, H, Feyen, FC & Veeman, WS 1994, '13C Solid-State NMR Study of Differently Processed Poly(ethylene terephthalate) Yarns', *Macromolecules*, vol. 27, no. 20, pp. 5811–5820.
- Gambichler, T, Rotterdam, S, Altmeyer, P & Hoffmann, K 2001, 'Protection Against Ultraviolet Radiation by Commercial Summer Clothing: Need for Standardised Testing and Labelling', *BMC Dermatology*, vol. 1, no. 1, p. 6. Available from: <https://doi.org/10.1186/1471-5945-1-6>.
- Gao, J, Bender, CM & Murphy, CJ 2003, 'Dependence of the Gold Nanorod Aspect Ratio on the Nature of the Directing Surfactant in Aqueous Solution', *Langmuir*, vol. 19, no. 21, pp. 9065–9070.
- Gericke, M, Schlufte, K, Liebert, T, Heinze, T & Budtova, T 2009, 'Rheological Properties of Cellulose/Ionic Liquid Solutions: From Dilute to Concentrated States', *Biomacromolecules*, vol. 10, no. 5, pp. 1188–1194.
- Gruntfest, I & Turner, R, *Treatment of Textile Waste Formed from Polyester and Cellulosic Fibers* 1974, United States 3937675.
- Guo, Z, Lindqvist, K & La Motte, H de 2018, 'An efficient recycling process of glycolysis of PET in the presence of a sustainable nanocatalyst', *Journal of Applied Polymer Science*, vol. 135, no. 21, p. 46285.
- Haslinger, S, Hietala, S, Hummel, M, Maunu, SL & Sixta, H 2019a, 'Solid-State NMR Method for the Quantification of Cellulose and Polyester in Textile Blends', *Carbohydrate Polymers*, vol. 207, pp. 11–16.
- Haslinger, S, Hummel, M, Anghelescu-Hakala, A, Määttänen, M & Sixta, H 2019b, 'Upcycling of Cotton Polyester Blended Textile Waste to New Man-Made Cellulose Fibers', *Waste Management (New York, N.Y.)*, vol. 97, pp. 88–96.

- Haslinger, S, Wang, Y, Rissanen, M, Lossa, MB, Tantt, M, Ilen, E, Määttä, M, Harlin, A, Hummel, M & Sixta, H 2019c, 'Recycling of Vat and Reactive Dyed Textile Waste to New Colored Man-Made Cellulose Fibers', *Green Chemistry*, vol. 21, no. 20, pp. 5598–5610.
- Haslinger, S, Ye, Y, Rissanen, M, Hummel, M & Sixta, H 2020, 'Cellulose Fibers for High-Performance Textiles Functionalized with Incorporated Gold and Silver Nanoparticles', *ACS Sustainable Chemistry & Engineering*, vol. 8, no. 1, pp. 649–658.
- Hassaan, MA & El Nemr 2017, 'Health and Environmental Impacts of Dyes: Mini Review', *American Journal of Environmental Science and Engineering*, vol. 1, no. 3, pp. 64–67.
- Haule, LV, Carr, CM & Rigout, M 2016, 'Preparation and Physical Properties of Regenerated Cellulose Fibres from Cotton Waste Garments', *Journal of Cleaner Production*, vol. 112, pp. 4445–4451.
- Hauru, LKJ, Hummel, M, King, AWT, Kilpeläinen, I & Sixta, H 2012, 'Role of Solvent Parameters in the Regeneration of Cellulose from Ionic Liquid Solutions', *Biomacromolecules*, vol. 13, no. 9, pp. 2896–2905.
- Hauru, LKJ, Hummel, M, Michud, A & Sixta, H 2014, 'Dry Jet-Wet Spinning of Strong Cellulose Filaments from Ionic Liquid Solution', *Cellulose*, vol. 21, no. 6, pp. 4471–4481.
- Hauru, LKJ, Hummel, M, Nieminen, K, Michud, A & Sixta, H 2016, 'Cellulose Regeneration and Spinnability from Ionic Liquids', *Soft Matter*, vol. 12, no. 5, pp. 1487–1495.
- Haward, SJ, Sharma, V, Butts, CP, McKinley, GH & Rahatekar, SS 2012, 'Shear and Extensional Rheology of Cellulose/Ionic Liquid Solutions', *Biomacromolecules*, vol. 13, no. 5, pp. 1688–1699.
- He, J, Kunitake, T & Nakao, A 2003, 'Facile In Situ Synthesis of Noble Metal Nanoparticles in Porous Cellulose Fibers', *Chemistry of Materials*, vol. 15, no. 23, pp. 4401–4406.
- Heinze, T 2016, 'Cellulose: Structure and Properties' in *Cellulose Chemistry and Properties: Fibers, Nanocelluloses and Advanced Materials*, ed OJ Rojas, Springer International Publishing, Cham, pp. 1–52.
- Hermanutz, F, Gähr, F, Uerdingen, E, Meister, F & Kosan, B 2008, 'New Developments in Dissolving and Processing of Cellulose in Ionic Liquids', *Macromolecular Symposia*, vol. 262, no. 1, pp. 23–27.
- Hinkka, V, Heikkilä, P & Harlin, A 2018, *Logistical Preconditions for Economical Reuse of End-of-life Textiles*, Online. Available from: https://cris.vtt.fi/ws/portal-files/portal/20305661/Hinkka_Heikkil_Harlin_Reuse_of_End_of_life_Textiles_hicl_2018.pdf [13 November 2019].
- Holbrey, JD & Seddon, KR 1999, 'Ionic Liquids', *Clean Products and Processes*, vol. 1, pp. 223–236.
- Hornyak, GL, Patrissi, CJ, Oberhauser, EB, Martin, CR, Valmalette, J-C, Lemaire, L.: Dutta, J. & Hofmann, H 1997, 'Effective Medium Theory Characterization of Au/Ag Nanoalloy-Porous Alumina Composites', *NanoStructured Materials*, vol. 9, pp. 571–574.

- Horrocks, AR & Anand, S 2000, *Handbook of Technical Textiles*, CRC Press; Cambridge: Woodhead Pub, Boca Raton, Fla.
- Humpston, G, Willis, P, Tyler, D & Han, S 2014, *Technologies for Sorting End of Life Textiles*, ResearchGate. Available from: <https://www.researchgate.net/publication/293487871> [21 December 2019].
- Hutter, E & Fendler, JH 2004, 'Exploitation of Localized Surface Plasmon Resonance', *Advanced Materials*, vol. 16, no. 19, pp. 1685–1706.
- Hämmerle, FM 2011, 'The cellulose gap. The future of cellulose fibers', *Lenzinger Berichte*, vol. 89, pp. 11–21.
- Ibbett, R, Domvoglou, D, Wortmann, F & Schuster, KC 2010, 'Carbon-13 Solid State NMR Investigation and Modeling of the Morphological Reorganization in Regenerated Cellulose Fibres Induced by Controlled Acid Hydrolysis', *Cellulose*, vol. 17, no. 2, pp. 231–243.
- Ibbett, RN, Domvoglou, D & Fasching, M 2007, 'Characterisation of the Supramolecular Structure of Chemically and Physically Modified regenerated cellulosic fibres by Means of High-Resolution Carbon-13 solid-state NMR', *Polymer*, vol. 48, no. 5, pp. 1287–1296.
- Ilić, V, Šaponjić, Z, Vodnik, V, Potkonjak, B, Jovančić, P, Nedeljković, J & Radetić, M 2009, 'The influence of Silver Content on Antimicrobial Activity and Color of Cotton Fabrics Functionalized with Ag Nanoparticles', *Carbohydrate Polymers*, vol. 78, no. 3, pp. 564–569.
- Jain, PK, Lee, KS, El-Sayed, IH & El-Sayed, MA 2006, 'Calculated Absorption and Scattering Properties of Gold Nanoparticles of Different Size, Shape, and Composition: Applications in Biological Imaging and Biomedicine', *The Journal of Physical Chemistry B*, vol. 110, no. 14, pp. 7238–7248.
- Jana, NR, Gearheart, L & Murphy, CJ 2001, 'Evidence for Seed-Mediated Nucleation in the Chemical Reduction of Gold Salts to Gold Nanoparticles', *Chemistry of Materials*, vol. 13, no. 7, pp. 2313–2322.
- Johnston, JH & Nilsson, T 2012, 'Nanogold and Nanosilver Composites with Lignin-Containing Cellulose Fibres', *Journal of Materials Science*, vol. 47, no. 3, pp. 1103–1112.
- Joy, A, Sherry, JF, Venkatesh, A, Wang, J & Chan, R 2015, 'Fast Fashion, Sustainability, and the Ethical Appeal of Luxury Brands', *Fashion Theory*, vol. 16, no. 3, pp. 273–295.
- Kelly, KL, Coronado, E, Zhao, LL & Schatz, GC 2003, 'The Optical Properties of Metal Nanoparticles. The Influence of Size, Shape, and Dielectric Environment', *The Journal of Physical Chemistry B*, vol. 107, no. 3, pp. 668–677.
- Kim, SS, Park, JE & Lee, J 2011, 'Properties and Antimicrobial Efficacy of Cellulose Fiber Coated with Silver Nanoparticles and 3-Mercaptopropyltrimethoxysilane (3-MPTMS)', *Journal of Applied Polymer Science*, vol. 119, no. 4, pp. 2261–2267.
- Klein, W 1998, *The Technology of Short-Staple Spinning*.

- Koga, H, Tokunaga, E, Hidaka, M, Umemura, Y, Saito, T, Isogai, A & Kitaoka, T 2010, 'Topochemical Synthesis and Catalysis of Metal Nanoparticles Exposed on Crystalline Cellulose Nanofibers', *Chemical Communications (Cambridge, England)*, vol. 46, no. 45, pp. 8567–8569.
- Kosan, B, Michels, C & Meister, F 2008, 'Dissolution and Forming of Cellulose with Ionic Liquids', *Cellulose*, vol. 15, no. 1, pp. 59–66.
- Kreibig, U & Vollmer, M 1995, *Optical Properties of Metal Clusters*, Springer, Berlin.
- Kulpinski, P 2007, 'Bioactive Cellulose Fibres with Silver Nanoparticles', *e-Polymers*, vol. 068, pp. 1–12.
- Larsson, PT, Wickholm, K & Iverson, T 1997, 'A CP/MAS ^{13}C NMR Investigation of Molecular Ordering in Celluloses', *Carbohydrate Research*, vol. 302, pp. 19–25.
- Laus, G, Bentivoglio, G, Schottenberger, H, Kahlenberg, V, Kopacka, H & Sixta, H 2005, 'Ionic Liquids: Current Developments, Potentials and Drawbacks for Industrial Applications', *Lenzinger Berichte*, vol. 84, pp. 71–85.
- Lee, K-C, Lin, S-J, Lin, C-H, Tsai, C-S & Lu, Y-J 2008, 'Size Effect of Ag Nanoparticles on Surface Plasmon Resonance', *Surface and Coatings Technology*, vol. 202, pp. 5339–5342.
- Lenz, J, Schurz, J & Wrentschur, E 1994, 'On the Elongation Mechanism of Regenerated Cellulose Fibres', *Holzforschung*, vol. 48, s1, pp. 72–76.
- Lenzing AG 2019, *TENCEL x REFIBRA Technology*. Available from: <https://www.tencel.com/refibra> [13 November 2019].
- Lewis, DM 2014, 'Developments in the Chemistry of Reactive Dyes and their Application Processes', *Coloration Technology*, vol. 130, no. 6, pp. 382–412.
- Liittä, T, Maunu, SL & Hortling, B 2000, 'Solid State NMR Studies on Cellulose Crystallinity in Fines and Bulk Fibres Separated from Refined Kraft Pulp', *Holzforschung*, vol. 54, no. 6, p. 186.
- Liu, F, Cui, X, Yu, S, Li, Z & Ge, X 2009, 'Hydrolysis Reaction of Poly(ethylene terephthalate) Using Ionic Liquids as Solvent and Catalyst', *Journal of Applied Polymer Science*, vol. 114, no. 6, pp. 3561–3565.
- Liu, W, Liu, S, Liu, T, Liu, T, Zhang, J & Liu, H 2019, 'Eco-Friendly Post-Consumer Cotton Waste Recycling for Regenerated Cellulose Fibers', *Carbohydrate Polymers*, vol. 206, pp. 141–148.
- Lord, PR 2003, *Handbook of Yarn Technology. Science, Technology and Economics*, CRC; Woodhead, Boca Raton, Fla., Cambridge.
- Louis, C & Pluchery, O 2012, *Gold Nanoparticles for Physics, Chemistry and Biology*, Imperial College Press; Distributed by World Scientific Pub. Co, London, Singapore, Hackensack NJ.
- Louris, E, Sfiroera, E, Priniotakis, G, Makris, R, Siemos, H, Efthymiou, C & Assimakopoulos, MN 2018, 'Evaluating the Ultraviolet Protection Factor (UPF) of Various Knit Fabric Structures', *IOP Conference Series: Materials Science and Engineering*, vol. 459, p. 12051.

- Lv, F, Wang, C, Zhu, P & Zhang, C 2015, 'Isolation and Recovery of Cellulose from Waste Nylon/Cotton Blended Fabrics by 1-Allyl-3-Methylimidazolium Chloride', *Carbohydrate Polymers*, vol. 123, pp. 424–431.
- Ma, Y, Hummel, M, Kontro, I & Sixta, H 2018, 'High Performance Man-Made Cellulosic Fibres from Recycled Newsprint', *Green Chemistry*, vol. 20, no. 1, pp. 160–169.
- Ma, Y, Hummel, M, Määttänen, M, Särkilahti, A, Harlin, A & Sixta, H 2016, 'Upcycling of Waste Paper and Cardboard to Textiles', *Green Chemistry*, vol. 18, no. 3, pp. 858–866.
- Ma, Y, Zeng, B, Wang, X & Byrne, N 2019, 'Circular Textiles: Closed Loop Fiber to Fiber Wet Spun Process for Recycling Cotton from Denim', *ACS Sustainable Chemistry & Engineering*, vol. 7, pp. 11937–11943.
- Mahapatra, NN 2016, *Textile dyes*, WPI Publishing, New Delhi.
- Manian, AP, Ruef, H & Bechtold, T 2007, 'Spun-dyed lyocell', *Dyes and Pigments*, vol. 74, no. 3, pp. 519–524.
- Martínez-Richa, A & Silvestri, R 2012, 'Determination of Phase Content in Multiphase Polymers by Solid-State NMR Techniques', *Materials Science Forum*, vol. 714, pp. 51–56.
- Maunu, S, Liitiä, T, Kauliomäki, S, HORTLING, BO & SUNDQUIST, J 2000, '¹³C CPMAS NMR Investigations of Cellulose Polymorphs in Different Pulps', *Cellulose*, vol. 7, no. 2, pp. 147–159.
- Meksi, N & Moussa, A 2017, 'A Review of Progress in the Ecological Application of Ionic Liquids in Textile Processes', *Journal of Cleaner Production*, vol. 161, pp. 105–126.
- Métraux, GS & Mirkin, CA 2005, 'Rapid Thermal Synthesis of Silver Nanoprisms with Chemically Tailorable Thickness', *Advanced Materials*, vol. 17, no. 4, pp. 412–415.
- Mezger, TG 2006, *The Rheology Handbook*, Hannover.
- Mezger, TG 2018, *Applied rheology. With Joe Flow on rheology road*, Anton Paar, Graz.
- Michud, A, Hummel, M & Sixta, H 2015, 'Influence of Molar Mass Distribution on the Final Properties of Fibers Regenerated from Cellulose Dissolved in Ionic Liquid by Dry-Jet Wet Spinning', *Polymer*, vol. 75, pp. 1–9.
- Michud, A, Hummel, M & Sixta, H 2016, 'Influence of Process Parameters on the Structure Formation of Man-Made Cellulosic Fibers from Ionic Liquid Solution', *Journal of Applied Polymer Science*, vol. 133, no. 30, p. 177.
- Michud, A, Tanttu, M, Asaadi, S, Ma, Y, Netti, E, Kääriäinen, P, Persson, A, Berntsson, A, Hummel, M & Sixta, H 2015, 'Ioncell-F. Ionic Liquid-Based Cellulosic Textile Fibers as an Alternative to viscose and Lyocell', *Textile Research Journal*, vol. 86, no. 5, pp. 543–552.
- Muthu, SS (ed.) 2014, *Roadmap to Sustainable Textiles and Clothing: Eco-Friendly Raw Materials, Technologies, and Processing Methods*, Springer Singapore, Singapore.
- Muthu, SS (ed.) 2017, *Textiles and Clothing Sustainability. Sustainable Textile Chemical Processes*, Springer, Singapore.

- Määttänen, M, Asikainen, S, Kamppuri, T, Ilen, E, Niinimäki, K, Tanttu, M & Harlin, A 2019, 'Colour Management in Circular Economy: Decolourization of Cotton Waste', *Research Journal of Textile and Apparel*, vol. 23, no. 2, pp. 134–152.
- Nascimento, CR, Dias, ML, Menezes, SM:C & Silva, NM 2004, '¹³C Solid State Characterization of Recycled Poly(ethylene terephthalate)-PET', *Ann. Magn. Reson.*, vol. 3, no. 3, pp. 93–95.
- Negulescu, II, Kwon, H, Collier, BJ, Collier, JR & Pendse, A 1998, 'Recycling Cotton from Cotton/Polyester Fabrics', *Textile Chemist and Colorist*, vol. 30, no. 6, pp. 31–35.
- Newman, RH & Davidson, TC 2004, 'Molecular Conformations at the Cellulose-Water Interface', *Cellulose*, vol. 11, pp. 23–32.
- Nikoobakht, B & El-Sayed, MA 2003, 'Preparation and Growth Mechanism of Gold Nanorods (NRs) Using Seed-Mediated Growth Method', *Chemistry of Materials*, vol. 15, no. 10, pp. 1957–1962.
- Njoki, PN, Lim, I-IS, Mott, D, Park, H-Y, Khan, B, Mishra, S, Sujakumar, R, Luo, J & Zhong, C-J 2007, 'Size Correlation of Optical and Spectroscopic Properties for Gold Nanoparticles', *The Journal of Physical Chemistry C*, vol. 111, no. 40, pp. 14664–14669.
- Novoselov, NP, Sashina, ES, Petrenko, VE & Zaborsky, M 2007, 'Study of Dissolution of Cellulose in Ionic Liquids by Computer Modeling', *Fiber Chemistry*, vol. 39, no. 2, pp. 153–158.
- Nørup, N, Pihl, K, Damgaard, A & Scheutz, C 2018, 'Development and Testing of a Sorting and Quality Assessment Method for Textile Waste', *Waste Management (New York, N.Y.)*, vol. 79, pp. 8–21.
- Oakley, EO, Gorman, FJ & Mason, JD, *Process for Recycling Polyester/Cotton Blends* 1992, United States 5236959.
- Oelerich, J, Bijleveld, M, Bouwhuis, GH & Brinks, GJ 2017, 'The life Cycle Assessment of Cellulose Pulp from Waste Cotton via the SaXcell™ Process', *IOP Conference Series: Materials Science and Engineering*, vol. 254, p. 192012.
- Ouchi, A, Toida, T, Kumaresan, S, Ando, W & Kato, J 2010, 'A New Methodology to Recycle Polyester from Fabric Blends with Cellulose', *Cellulose*, vol. 17, no. 1, pp. 215–222.
- Oxtoby, E 2014, *Spun Yarn Technology*, Elsevier Science, Kent.
- Palme, A, Idström, A, Nordstierna, L & Brelid, H 2014, 'Chemical and Ultrastructural Changes in Cotton Cellulose Induced by Laundering and Textile Use', *Cellulose*, vol. 21, no. 6, pp. 4681–4691.
- Palme, A, Peterson, A, La Motte, H de, Theliander, H & Brelid, H 2017, 'Development of an Efficient Route for Combined Recycling of PET and Cotton from Mixed Fabrics', *Textiles and Clothing Sustainability*, vol. 3, no. 1, p. 53.
- Park, S, Johnson, DK, Ishizawa, CI, Parilla, PA & Davis, MF 2009, 'Measuring the Crystallinity Index of Cellulose by Solid State ¹³C Nuclear Magnetic Resonance', *Cellulose*, vol. 16, no. 4, pp. 641–647.

- Parviainen, A, King, AWT, Mutikainen, I, Hummel, M, Selg, C, Hauru, LKJ, Sixta, H & Kilpeläinen, I 2013, 'Predicting Cellulose Solvating Capabilities of Acid-Base Conjugate Ionic Liquids', *ChemSusChem*, vol. 6, no. 11, pp. 2161–2169.
- Parviainen, H, Parviainen, A, Virtanen, T, Kilpeläinen, I, Ahvenainen, P, Serimaa, R, Grönqvist, S, Maloney, T & Maunu, SL 2014, 'Dissolution Enthalpies of Cellulose in Ionic Liquids', *Carbohydrate Polymers*, vol. 113, pp. 67–76.
- Peets, P, Leito, I, Pelt, J & Vahur, S 2017, 'Identification and Classification of Textile Fibres Using ATR-FT-IR Spectroscopy with Chemometric Methods', *Spectrochimica acta. Part A, Molecular and biomolecular spectroscopy*, vol. 173, pp. 175–181.
- Pérez, J, Muñoz-Dorado, J, La Rubia, T de & Martínez, J 2002, 'Biodegradation and Biological Treatments of Cellulose, Hemicellulose and Lignin: An Overview', *International Microbiology: The Official Journal of the Spanish Society for Microbiology*, vol. 5, no. 2, pp. 53–63.
- Perez-Juste, J, Pastoriza-Santos, I, Liz-Marzan, L & MULVANEY, P 2005, 'Gold Nanorods. Synthesis, Characterization and Applications', *Coordination Chemistry Reviews*, vol. 249, 17–18, pp. 1870–1901.
- Peterson, A 2015, *Towards Recycling of Textile Fibers. Separation and Characterization of Textile Fibers and Blends*. Master's Thesis, Gothenburg, Sweden. Available from: <https://odr.chalmers.se/bitstream/20.500.12380/218483/1/218483.pdf> [29 January 2020].
- Pinkert, A, Marsh, KN, Pang, S & Staiger, MP 2009, 'Ionic liquids and their interaction with cellulose', *Chemical Reviews*, vol. 109, no. 12, pp. 6712–6728.
- Potthast, A, Radosta, S, Saake, B, Lebioda, S, Heinze, T, Henniges, U, Isogai, A, Koschella, A, Kosma, P, Rosenau, T, Schiehser, S, Sixta, H, Strlič, M, Strobin, G, Vorwerg, W & Wetzl, H 2015, 'Comparison Testing of Methods for Gel Permeation Chromatography of Cellulose. Coming Closer to a Standard Protocol', *Cellulose*, vol. 22, no. 3, pp. 1591–1613.
- Rabideau, BD, Agarwal, A & Ismail, AE 2014, 'The Role of the Cation in the Solvation of Cellulose by Imidazolium-Based Ionic Liquids', *The Journal of Physical Chemistry. B*, vol. 118, no. 6, pp. 1621–1629.
- Rac-Rumijowska, O, Fiedot, M, Karbownik, I, Suchorska-Woźniak, P & Teterycz, H 2017, 'Synthesis of Silver Nanoparticles in NMMO and Their In Situ Doping into Cellulose Fibers', *Cellulose*, vol. 24, no. 3, pp. 1355–1370.
- Rahatekar, SS, Rasheed, A, Jain, R, Zammarano, M, Koziol, KK, Windle, AH, Gilman, JW & Kumar, S 2009, 'Solution Spinning of Cellulose Carbon Nanotube Composites Using Room Temperature Ionic Liquids', *Polymer*, vol. 50, no. 19, pp. 4577–4583.
- Rehan, M, Mashaly, HM, Mowafi, S, Abou El-Kheir, A & Emam, HE 2015, 'Multi-Functional Textile Design Using In-Situ Ag NPs Incorporation into Natural Fabric Matrix', *Dyes and Pigments*, vol. 118, pp. 9–17.
- REISKAtex 2017, *Tekstiilien tunnistus- ja lajittelulaitteisto – REISKAtex®*, REISKAtex. Available from: <https://www.reiska.info/tekstililajitin> [21 December 2019].

- Rodgers, J & Beck, K 2009, 'NIR Characterization and Measurement of the Cotton Content of Dyed Blend Fabrics', *Textile Research Journal*, vol. 79, no. 8, pp. 675–686.
- Roshan, P 2015, *Functional Finishes for Textiles. Improving Comfort, Performance and Protection*, Elsevier, Amsterdam.
- Ruef, H, *Colored Cellulosic Shaped Bodies* 2000, Austria EP121463B1.
- Sammons, RJ, Collier, JR, Rials, TG & Petrovan, S 2008, 'Rheology of 1-Butyl-3-Methylimidazolium Chloride Cellulose Solutions. I. Shear Rheology', *Journal of Applied Polymer Science*, vol. 110, no. 2, pp. 1175–1181.
- Samperi, F, Puglisi, C, Alicata, R & Montaudo, G 2004, 'Thermal Degradation of Poly(ethylene terephthalate) at the Processing Temperature', *Polymer Degradation and Stability*, vol. 83, no. 1, pp. 3–10.
- Schwedt, G 2007, *Taschenatlas der Analytik*, Wiley-VCH Verl., Weinheim.
- Serad, SL, *Polyester Dissolution for Polyester/Cotton Blend Recycle* 1993, United States 5342854.
- Sescousse, R, Le, KA, Ries, ME & Budtova, T 2010, 'Viscosity of Cellulose-Imidazolium-Based Ionic Liquid Solutions', *The Journal of Physical Chemistry. B*, vol. 114, no. 21, pp. 7222–7228.
- Shen, F, Xiao, W, Lin, L, Yang, G, Zhang, Y & Deng, S 2013, 'Enzymatic Saccharification Coupling with Polyester Recovery from Cotton-Based Waste Textiles by Phosphoric Acid Pretreatment', *Bioresource Technology*, vol. 130, pp. 248–255.
- Shen, L & Patel, MK 2010, 'Life Cycle Assessment of Man-Made Cellulose Fibers', *Leuzinger Berichte*, vol. 88, pp. 1–59.
- Shin, Y, Bae, I-T, Arey, BW & Exarhos, GJ 2008, 'Facile Stabilization of Gold-silver Alloy Nanoparticles on Cellulose Nanocrystal', *The Journal of Physical Chemistry C*, vol. 112, no. 13, pp. 4844–4848.
- Siller, M, Ahn, K, Pircher, N, Rosenau, T & Potthast, A 2014, 'Dissolution of Rayon Fibers for Size Exclusion Chromatography: A Challenge', *Cellulose*, vol. 21, no. 5, pp. 3291–3301.
- Silva, R de & Byrne, N 2017, 'Utilization of Cotton Waste for Regenerated Cellulose Fibres: Influence of Degree of Polymerization on Mechanical Properties', *Carbohydrate Polymers*, vol. 174, pp. 89–94. Available from: <http://www.sciencedirect.com/science/article/pii/S0144861717306793>.
- Silva, R de, Wang, X & Byrne, N 2014, 'Recycling Textiles. The Use of Ionic Liquids in the Separation of Cotton Polyester Blends', *RSC Adv*, vol. 4, no. 55, pp. 29094–29098.
- Sixta, H 2006, *Handbook of pulp*, Wiley-VCH, Weinheim, Chichester.
- Sixta, H, Michud, A, Hauru, L, Asaadi, S, Ma, Y, King, AWT, Kilpeläinen, I & Hummel, M 2015, 'Ioncell-F: A High-Strength Regenerated Cellulose Fibre', *Nordic Pulp & Paper Research Journal*, vol. 30, no. 1, pp. 43–57.
- Smiechowicz, E, Kulpinski, P, Niekraszewicz, B & Bacciarelli, A 2011, 'Cellulose fibers modified with silver nanoparticles', *Cellulose*, vol. 18, no. 4, pp. 975–985.

- Smiechowicz, E, Kulpinski, P, Niekraszewicz, B, Bemska, J & Morgiel, J 2014, 'Effect of Silver on Cellulose Fibre Colour', *Coloration Technology*, vol. 130, no. 6, pp. 424–431.
- Smiechowicz, E, Niekraszewicz, B, Kulpinski, P & Dzitko, K 2018, 'Antibacterial Composite Cellulose Fibers Modified with Silver Nanoparticles and Nanosilica', *Cellulose*, vol. 25, no. 6, pp. 3499–3517.
- Smith, DK & Korgel, BA 2008, 'The Importance of the CTAB Surfactant on the Colloidal Seed-Mediated Synthesis of Gold Nanorods', *Langmuir: The ACS Journal of Surfaces and Colloids*, vol. 24, no. 3, pp. 644–649.
- Song, H-Z, Luo, Z-Q, Wang, C-Z, Hao, X-F & Gao, J-G 2013, 'Preparation and Characterization of Bionanocomposite Fiber Based on Cellulose and Nano-SiO₂ Using Ionic Liquid', *Carbohydrate Polymers*, vol. 98, no. 1, pp. 161–167.
- Su, K-H, Wei, Q-H, Zhang, X, Mock, JJ, Smith, DR & Schultz, S 2003, 'Interparticle Coupling Effects on Plasmon Resonances of Nanogold Particles', *Nano Letters*, vol. 3, no. 8, pp. 1087–1090.
- Sun, C-h, Chen, X-p, Zhuo, Q & Zhou, T 2018, 'Recycling and Depolymerization of Waste Polyethylene Terephthalate Bottles by Alcohol Alkali Hydrolysis', *Journal of Central South University*, vol. 25, no. 3, pp. 543–549.
- Sun, Hongyu, Li, Chunguang, Sheng, C, Wang, J, Deng, H, Jia, R, Xia, Y, Tian, F, Lu, Q & Guo, D, *Method for separating and preparing microcrystalline cellulose from polyester-cotton fabric* 2018, CN 108424466 A.
- Tang, B, Kaur, J, Sun, L & Wang, X 2013, 'Multifunctionalization of Cotton Through In Situ Green Synthesis of Silver Nanoparticles', *Cellulose*, vol. 20, no. 6, pp. 3053–3065.
- Tang, B, Sun, L, Kaur, J, Yu, Y & Wang, X 2014, 'In-situ Synthesis of Gold nanoparticles for Multifunctionalization of Silk Fabrics', *Dyes and Pigments*, vol. 103, pp. 183–190.
- Tang, B, Sun, L, Li, J, Kaur, J, Zhu, H, Qin, S, Yao, Y, Chen, W & Wang, X 2015a, 'Functionalization of Bamboo Pulp Fabrics with Noble Metal Nanoparticles', *Dyes and Pigments*, vol. 113, pp. 289–298.
- Tang, B, Yao, Y, Li, J, Qin, S, Zhu, H, Kaur, J, Chen, W, Sun, L & Wang, X 2015b, 'Functional Application of Noble Metal Nanoparticles In Situ Synthesized on Ramie Fibers', *Nanoscale Research Letters*, vol. 10, no. 1, p. 366.
- Tang, B, Zhang, M, Hou, X, Li, J, Sun, L & Wang, X 2012, 'Coloration of Cotton Fibers with Anisotropic Silver Nanoparticles', *Industrial & Engineering Chemistry Research*, vol. 51, no. 39, pp. 12807–12813.
- Tawiah, B & Asinyo, BK 2016, 'Advances in Spun-dyeing of Regenerated Cellulose Fibers', *International Journal of Management, Information, Technology and Engineering*, vol. 4, no. 2, pp. 65–80.
- Terinte, N, Manda, BMK, Taylor, J, Schuster, KC & Patel, MK 2014, 'Environmental Assessment of Coloured Fabrics and Opportunities for Value Creation. Spin-dyeing Versus Conventional Dyeing of Modal Fabrics', *Journal of Cleaner Production*, vol. 72, pp. 127–138.
- The Fiber Year. World Survey on Textiles & Nonwovens* 2019, Speicher, Switzerland.

- Tincher, WC & Luk, A 1985, 'NIRS Analysis of Cotton/Polyester Yarns', *Spectroscopic Analysis*, vol. 17, no. 10, pp. 25–29.
- Tsai, T-T, Huang, T-H, Chang, C-J, Yi-Ju Ho, N, Tseng, Y-T & Chen, C-F 2017, 'Anti-Bacterial Cellulose Paper Made with Silver-Coated Gold Nanoparticles', *Scientific reports*, vol. 7, no. 1, p. 3155.
- Valvan Bailing Systems 2019, *Fibersort*, Valvan Bailing Systems. Available from: <http://www.valvan.com/products/equipment-for-used-clothing-wipers/sorting-equipment/fibersort/> [21 December 2019].
- Wang, H, Li, Z, Liu, Y, Zhang, X & Zhang, S 2009, 'Degradation of Poly(ethylene terephthalate) Using Ionic Liquids', *Green Chemistry*, vol. 11, no. 10, p. 1568.
- Weber, S, Lynes, J & Young, SB 2017, 'Fashion Interest as a Driver for Consumer Textile Waste Management: Reuse, Recycle or Disposal', *International Journal of Consumer Studies*, vol. 41, no. 2, pp. 207–215.
- Wedin, H, Lopes, M, Sixta, H & Hummel, M 2019, 'Evaluation of Post-Consumer Cellulosic Textile Waste for Chemical Recycling Based on Cellulose Degree of Polymerization and Molar Mass Distribution', *Textile Research Journal*, vol. 10, 004051751984815.
- Wedin, H, Niit, E, Mansoor, ZA, Kristinsdottir, AR, La Motte, H de, Jönsson, C, Östlund, Å & Lindgren, C 2018, 'Preparation of Viscose Fibres Stripped of Reactive Dyes and Wrinkle-Free Crosslinked Cotton Textile Finish', *Journal of Polymers and the Environment*, vol. 26, no. 9, pp. 3603–3612.
- Wendler, F, Kolbe, A, Buettner, R & Markwitz, H, *Method for the Production of Bioactive Cellulose Fiber with a High Degree of Whiteness* 2008, US US 2010/0124861 A1.
- Wendler, F, Kosan, B, Krieg, M & Meister, F 2009, 'Possibilities for the Physical Modification of Cellulose Shapes Using Ionic Liquids', *Macromolecular Symposia*, vol. 280, no. 1, pp. 112–122.
- Wendler, F, Meister, F, Montigny, R & Wagener, M 2007, 'A New Antimicrobial ALCERU Fibre with Silver Nanoparticles', *FIBRES & TEXTILES in Eastern Europe*, vol. 15, pp. 41–45.
- Wickholm, K, Larsson, PT & Iverson, T 1998, 'Assignment of Non-Crystalline Forms in Cellulose I by CP/MAS ^{13}C NMR Spectroscopy', *Carbohydrate Research*, vol. 312, pp. 123–129.
- Vigneshwaran, N, Kathe, AA, Varadarajan, PV, Nachane, RP & Balasubramanya, RH 2007, 'Functional Finishing of Cotton Fabrics Using Silver Nanoparticles', *Journal of Nanoscience and Nanotechnology*, vol. 7, no. 6, pp. 1893–1897.
- Woodings, CR 1995, 'The Development of Advanced Cellulosic Fibers', *Int. J. Bio. Macromol.*, vol. 17, no. 6.
- Yu, Q, Kong, X, Ma, Y, Wang, R, Liu, Q, Hinestroza, JP, Wang, AX & Vuorinen, T 2018, 'Multi-Functional Regenerated Cellulose Fibers Decorated with Plasmonic Au Nanoparticles for Colorimetry and SERS Assays', *Cellulose*, vol. 25, no. 10, pp. 6041–6053.
- Zhang, T, Wang, W, Zhang, D, Zhang, X, Ma, Y, Zhou, Y & Qi, L 2010, 'Biotemplated Synthesis of Gold Nanoparticle-Bacteria Cellulose Nanofiber Nanocomposites and

- Their Application in Biosensing', *Advanced Functional Materials*, vol. 20, no. 7, pp. 1152–1160.
- Zheng, Y, Xiao, M, Jiang, S, Ding, F & Wang, J 2013, 'Coating Fabrics with Gold Nanorods for Colouring, UV-protection, and Antibacterial Functions', *Nanoscale*, vol. 5, no. 2, pp. 788–795.
- Zhou, C, Han, G, Via, BK, Song, Y, Gao, S & Jiang, W 2019, 'Rapid Identification of Fibers from Different Waste Fabrics Using the Near-Infrared Spectroscopy Technique', *Textile Research Journal*, vol. 89, no. 17, pp. 3610–3616.
- Ziabicki, A & Takserman-Krozer, R 1964a, 'Effect of Rheological Factors on the Length of Liquid Threads', *Kolloid-Zeitschrift und Zeitschrift für Polymere*, vol. 199, no. 1, pp. 9–13.
- Ziabicki, A & Takserman-Krozer, R 1964b, 'Mechanism of Breakage of Liquid Threads', *Kolloid-Zeitschrift und Zeitschrift für Polymere*, vol. 198.
- Zuckerstätter, G, Schild, G, Wollboldt, P, Röder, T, Weber, HK & Sixta, H 2009, 'The Elucidation of Cellulose Supramolecular Structure by ^{13}C CP-MAS NMR', *Leinzinger Berichte*, vol. 87, pp. 38–46.
- Zuckerstätter, G, Terinte, N, Sixta, H & Schuster, KC 2013, 'Novel Insight into Cellulose Supramolecular Structure through ^{13}C CP-MAS NMR Spectroscopy and Paramagnetic Relaxation Enhancement', *Carbohydrate Polymers*, vol. 93, no. 1, pp. 122–128.

Appendix 1

Figure A1. (a) Chemical Structure of C. I. Direct Red 14, which is water soluble and remains on the cellulose surface due to electrostatic interactions, (b) C. I. Sulphur Black, which is solubilized in water through a reduction reaction and subsequently precipitated on the fiber structure by oxidation, (c) mechanism of azoic dyeing, which represents an in-situ synthesis of dye in the cellulose matrix (Chattopadhyay 2011).

Appendix 2

Figure A2. Mastercurves: Rheological parameters of cellulose solutions prepared from CO PET blends (a), dyed, pretreated pre-consumer cotton (b), dyed post-consumer cotton (c), and nanoparticle coated pulps (d) at their spinning temperatures (60°C, 70°C, 65°C, and 80°C). Complex viscosity (η^*) and dynamic moduli (G' , G'') were measured as a function of the angular frequency (ω). An asterisk (*) was added to curves that represented average results of multiple trials.⁵

⁵ Note: The curves for COPET_6.5_HOAc and Indanthren Brilliant Red FBB could not be calculated.

ISBN 978-952-60-3874-2 (printed)

ISBN 978-952-60-3875-9 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University
School of Chemical Engineering
Department of Bioproducts and Biosystems
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**