Morphometric Study of Bio-Based Particles and Their Interactions

Tero Kämäräinen

Morphometric Study of Bio-Based Particles and Their Interactions

Tero Kämäräinen

**The public defense on 15th June 2020 at 19:00 (7 p.m.)
will be available via remote technology.**

Link: <https://aalto.zoom.us/j/66338220319>

Zoom Quick Guide: <https://www.aalto.fi/en/services/zoom-quick-guide>

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Chemical Engineering, at a public examination held via remote connection (<https://aalto.zoom.us/j/66338220319>), on 15 June 2020 at 7 pm.

**Aalto University
School of Chemical Engineering
Department of Bioproducts and Biosystems
Bio-Based Colloids and Materials (BiCMat)**

Supervising professor

Professor Orlando J. Rojas, Aalto University, Finland

Thesis advisors

Dr. Blaise L. Tardy, Aalto University, Finland

Dr. Mariko Ago, Aalto University, Finland

Professor Orlando J. Rojas, Aalto University, Finland

Preliminary examiners

Associate Professor Audrey H. Moores, McGill University, Canada

Professor Jeffrey P. Youngblood, Purdue University, USA

Opponent

Professor J. Carson Meredith, Georgia Institute of Technology, USA

Aalto University publication series

DOCTORAL DISSERTATIONS 94/2020

© 2020 Tero Kämäräinen

ISBN 978-952-60-3927-5 (printed)

ISBN 978-952-60-3928-2 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-60-3928-2>

Unigrafia Oy

Helsinki 2020

Finland

Author

Tero Kämäräinen

Name of the doctoral dissertation

Morphometric Study of Bio-Based Particles and Their Interactions

Publisher School of Chemical Engineering

Unit Department of Bioproducts and Biosystems

Series Aalto University publication series DOCTORAL DISSERTATIONS 94/2020

Field of research Bioproduct Technology

Manuscript submitted 6 March 2020

Date of the defence 15 June 2020

Permission for public defence granted (date) 20 May 2020

Language English

☐ **Monograph**

☒ **Article dissertation**

☐ **Essay dissertation**

Abstract

Particle morphology plays many important roles in any technological application. This thesis introduces new protocols to prepare bio-based particles (including those based on lignin, tannin and chitin) and explores their morphological parametrization and colloidal interactions.

In Paper I, colloidal lignin particles were prepared by using an aerosol flow reactor, which enabled a size-dependent production of particle surfaces encompassing smooth and corrugated morphologies. Three-dimensional particle morphology characterization was carried out using cryo-electron tomography and harmonic analysis to give insights on their frequency domain characteristics, surface area distribution and volume. These descriptions were used in Paper IV to assess the influence of surface corrugation networks present in crumpled particles on the interaction energy, which consisted of van der Waals and electric double layer forces. The results revealed a highly anisotropic interaction energy depending on the local morphological features near the direction of approach. We identified surface regions that acted either stronger or weaker compared to an equivalent-volume, smooth spherical particle with contact area.

In Paper II, crystalline polyphenol-based particles were self-assembled using a simple, green method from alkaline aqueous tannic acid. Attained particle morphologies included rod-like, planar and cuboidal shapes. The process condition-morphology relations were unveiled by using principal component analysis, which indicated the main factors that influence the particle formation. For example, increasing the initial pH produced more elongated particles; base strength increased particle yield and increasing base counter cation size diminished particle size.

In Paper III, never-dried chitin nanocrystals were isolated from crab exoskeleton residues. The chirality of these particles was analysed using cryo-electron tomography by utilizing a method based on principal component analysis. No dominant chiral handedness was found for the never-dried nanomaterials. Comparison with the results found in the literature allowed us to suggest that the drying history could influence the chiral twist formation. This is hypothesized to take place through the inhibition of hydrogen bonding networks within and across chitin chains.

Overall, this thesis sheds light on the complex morphological details of various colloidal particles prepared from bio-based materials, which we considered for their high valorisation potential. Improved understanding of particle morphology and interactions is expected to facilitate the adoption of bio-based materials in a number of applications, including particulate coatings, composites and Pickering emulsions, among many others.

Keywords Colloidal lignin, Wrinkling, Colloidal interactions, Tannic acid, Chitin nanocrystals, Chirality, Morphology

ISBN (printed) 978-952-60-3927-5

ISBN (pdf) 978-952-60-3928-2

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Helsinki

Location of printing Helsinki **Year** 2020

Pages 162

urn <http://urn.fi/URN:ISBN:978-952-60-3928-2>

Tekijä

Tero Kämäräinen

Väitöskirjan nimi

Tutkielmia biopohjaisten partikkelien morfologiasta ja kolloidaalisista vuorovaikutuksista

Julkaisija Kemian tekniikan korkeakoulu**Yksikkö** Biotuotteiden ja biotekniikan laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 94/2020**Tutkimusala** Biotuotetekniikka**Käsikirjoituksen pvm** 06.03.2020**Väitöspäivä** 15.06.2020**Väittelyluvan myöntämispäivä** 20.05.2020**Kieli** Englanti☐ **Monografia**☒ **Artikkeliväitöskirja**☐ **Esseeväitöskirja****Tiivistelmä**

Kiintoainepartikkelien morfologialla on tärkeä rooli eri teknologisissa sovelluksissa. Tässä väitöskirjassa esitellään biopohjaisten kiintoainepartikkelien uusia valmistusmenetelmiä käyttäen lähtöaineina luonnossa runsaasti esiintyviä materiaaleja, kuten ligniiniä, tanniinia ja kitiiniä. Työssä tutkittiin partikkelien morfologiaa sekä vuorovaikutuksia tavoitteena edistää biopohjaisten materiaalien laajempaa hyödyntämistä.

Julkaisuissa I ja IV tutkimuksen kohteena olivat poimumaiset ligniinipartikkelit. Julkaisu I käsittelee niiden aerosolipohjaista valmistusmenetelmää ja morfologian kolmiulotteista karakterisointia kryoelektronitomografian avulla. Partikkelien pinta-alan ja tilavuuden lisäksi analyysimenetelmällä määritettiin pinnanmuodon poimuttumisen jakautuminen eri aallonpituuksille. Julkaisussa IV tuloksia hyödynnettiin partikkelien kolloidaalisten vuorovaikutusten laskennassa. Pinnan epätasainen muoto tuottaa suuruudeltaan vahvempia tai heikompia vuorovaikutuksia riippuen partikkelipinnan paikallisesta muodosta verrattuna samankokoiseen pyöreään partikkeliin. Tulokset korostavat morfologian suunnittelun tärkeyttä poimumaisia partikkeleita hyödyntävien sovellusten lähtökohtana.

Julkaisussa II tutkittiin tanniinihapon emäksisestä liuoksesta valmistettujen partikkelien morfologioiden ja prosessiparametrien välisiä suhteita. Yksinkertainen, vihreä valmistusmenetelmä mahdollisti laajan morfologisen kirjon sisältäen sauva-, laatta- ja särmiömäisiä muotoja. Pääkomponenttianalyysi osoittaa, että liuoksen pH ja käytetyn emäksen vahvuus vaikuttavat partikkeleiden sauvamaisuuteen ja reaktiotuotteen saantoon, kun taas suurempi emäksen kationin koko pienentää partikkelikokoa.

Julkaisussa III tutkittiin ravun kuoresta eristettyjen kuivumattomien kitiininanokiteiden kierteisyyttä kryoelektronitomografian ja pääkomponenttianalyysiin perustuvan menetelmän avulla. Morfologian kierteisyydellä ei havaittu olevan yksiselitteistä kätisyyttä, mikä voi viitata materiaalin kuivumishistorian merkittävyyteen kierteisyyden syntymekanismeissa. Tämän oletetaan johtuvan nanokiteiden kitiinimolekyylien välisten ja sisäisten vetysidosverkostojen muodostumisen estymisestä läsnäolevan veden seurauksena.

Tässä väitöskirjassa saadut tulokset partikkelien morfologiasta ja niiden vuorovaikutuksista odotetaan edesauttavan biopohjaisten materiaalien käyttöönottoa monissa sovelluskohteissa kuten muun muassa partikkelipinnoitteissa, komposiiteissa ja Pickering-emulsioidissa.

Avainsanat Ligniinipartikkelit, Rypistyminen, Kolloidaaliset vuorovaikutukset, Tanniinihappo, Kitiininanokiteet, Kierteisyys, Morfologia

ISBN (painettu) 978-952-60-3927-5**ISBN (pdf)** 978-952-60-3928-2**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Helsinki**Painopaikka** Helsinki**Vuosi** 2020**Sivumäärä** 162**urn** <http://urn.fi/URN:ISBN:978-952-60-3928-2>

Preface

This doctoral dissertation presents work carried out in the Bio-Based Colloids and Materials group (BiCMat) at the Department of Bioproducts and Biosystems in Aalto University School of Chemical Engineering between 2015 and 2020. I gratefully acknowledge the funding by Business Finland through the projects World of Cellulose (WoC) and Design Driven Value Chains in the World of Cellulose (DWoC) during 2015, the Academy of Finland's Centre of Excellence Programme under the project Molecular Engineering of Biosynthetic Hybrid Materials Research (HYBER) during 2016–2019 and the European Research Council Advanced Grant under the project BioELCell (Prof. Orlando J. Rojas) during 2020.

As the greatest hurdles have now passed, I've found myself drifting in thought to that confused electrical engineering student, who years ago set foot in the Department of Forest Products Technology, as it was known back then, and started learning about the science of natural materials. It was refreshing to be surrounded with people who studied and thought deeply about trees and other bio-based materials, subjects so ubiquitous yet foreign to me. The experiences I've had during these years have been very eye-opening. Looking back to my winding path through the different schools of thought and the challenges I encountered, I can state in content that I would not have it any other way. This has only been possible with the help of many people to whom I want to extend my greatest admiration and best wishes.

I'd like to express my utmost appreciation to Prof. Orlando J. Rojas for giving me the opportunity to work in his group. His open, educational personality and willingness to always dispense guidance and thought-provoking perspective, while still cultivating the development of his students as individuals, has been a great experience to be part of.

I'm very grateful for having such insightful advisors who carried out their role admirably and I hope to be as good of a mentor someday. My warmest thanks to Dr. Blaise L. Tardy, Dr. Mariko Ago, Dr. Maryam Borghei and Dr. Hannes Orelma. I would also like to thank Dr. Long Bai for giving me the chance to participate in his project and for his kind direction along the way. I feel especially indebted to Dr. Jani Seitsonen for his tireless guidance and spirit during our collaborations.

I would like to also warmly thank our co-authors Prof. Esko I. Kauppinen, Prof. Janne Ruokolainen, Prof. Yimin Fan, Dr. Maria Sammalkorpi, Dr. Sousa

Javan Nikkhah, Dr. Piotr Batys, Dr. Markus Müllner, Dr. Janne Raula, Dr. Johanna Majoinen, Dr. Wenchao Xiang, Dr. Leena-Sisko Johansson, Dr. Rafael Grande, Dr. Siqi Huan, Dr. Liang Liu and Mr. Luiz G. Greca for their hard work. It was always a pleasure to work with you.

My heartfelt gratitude goes to all the past and current members of the BiCMat family for creating a cooperative spirit that made work such a joy. Special thanks to Dr. Joseph Campbell for the language check of this thesis. I want to thank everybody of the department for being always willing to help and the friendly atmosphere that they have developed. I would also like to acknowledge everybody involved in HYBER for their work in making the meetings, get-togethers, symposiums and workshops a wonderful experience.

I want to thank the pre-examiners Prof. Audrey H. Moores and Prof. Jeffrey P. Youngblood. Their insightful comments have greatly improved the quality of this thesis. I would also like to thank Prof. J. Carson Meredith for taking the time to act as my opponent. I'm already looking forward to the day of our discussion.

Lastly, this would have been a much more difficult task if it weren't for my parents, brother, sister and friends. I remain forever grateful for their support and thoughtful views that have always been very welcomed during the ups and downs of life.

Helsinki, May 5th, 2020
Tero Kämäräinen

Contents

Preface	v
List of Abbreviations and Symbols.....	ix
List of Publications	xi
Author Contributions	xiii
1. Introduction.....	1
1.1 Scope and outline of the thesis	2
2. Background.....	3
2.1 Role of morphology in particle technology	3
2.2 Corrugated lignin particles and their interactions	4
2.2.1 Lignins.....	5
2.2.2 Surface corrugation in drying solute-laden droplets	6
2.2.3 Particle morphology and DLVO interactions.....	7
2.3 Morphological control of crystalline particles from tannic acid	7
2.3.1 Tannins.....	8
2.3.2 Particle morphology control	8
2.4 Chirality of never-dried chitin nanocrystals isolated from crustacean residue	9
2.4.1 Chitin.....	9
2.4.2 Deconstruction of a crustacean exoskeleton.....	10
2.4.3 Chiral twist in chitin nanocrystals	11
3. Experimental	13
3.1 Materials.....	13
3.2 Preparative methods	13
3.2.1 Preparation of lignin particles.....	13
3.2.2 Preparation of crystalline polyphenol-based particles	14
3.2.3 Preparation of never-dried chitin nanocrystals	14
3.3 Characterization methods	15

3.3.1	Scanning electron microscopy	15
3.3.2	Cryo-electron tomography.....	15
3.3.3	Frequency domain description of particle morphology	16
3.3.4	Calculation of colloidal interaction energies	17
3.3.5	Analysis of process condition-morphology relations	19
3.3.6	Analysis of chitin nanocrystal chirality.....	20
4.	Results and Discussion	23
4.1	Corrugated lignin particles	23
4.1.1	Morphological characterization with scanning electron microscopy.....	23
4.1.2	Three-dimensional morphological characterization with electron tomography.....	25
4.1.3	Influence of surface corrugations on colloidal interactions .	28
4.2	Morphological control of crystalline polyphenol-based particles	31
4.3	Chirality of never-dried chitin nanocrystals	34
5.	Concluding Remarks.....	39
	References	41
	Publications	51

List of Abbreviations and Symbols

ChNC	Chitin nanocrystal
CNC	Cellulose nanocrystal
CP	Corrugated particle
DE-ChNC	Deacetylated chitin nanocrystal
DLVO	Derjaguin-Landau-Verwey-Overbeek
EDL	Electric double layer
ET	Electron tomography
EVS	Equivalent-volume sphere
OTA	Oxidized tannic acid
PCA	Principal component analysis
SEI	Surface element integration
SEM	Scanning electron microscopy
SVD	Singular value decomposition
TEM	Transmission electron microscopy
vdW	van der Waals

Symbols

A	Surface area
h	Crust thickness
k_B	Boltzmann constant
ℓ	Harmonic degree
λ_D	Debye length
λ_ℓ	Angular length
ψ	Surface potential

R_{env}	Spherical envelope radius
R_V	Equivalent-volume sphere radius
r, θ, ϕ	Spherical coordinates
T	Temperature
U	DLVO interaction energy
U_{max}	Energy barrier height
U_{min}	Secondary minimum depth
V	Volume

List of Publications

This doctoral dissertation consists of a summary of the following publications which are referred in the text by their Roman numerals.

- I Kämäräinen, Tero**; Ago, Mariko; Seitsonen, Jani; Raula, Janne; Kauppinen, Esko I.; Ruokolainen, Janne; Rojas, Orlando J. Harmonic analysis of surface instability patterns on colloidal particles. *Soft Matter*, 2018, 14 (17), 3387–3396. DOI 10.1039/C8SM00383A

- II Kämäräinen, Tero**; Ago, Mariko; Greca, Luiz G.; Tardy, Blaise L.; Müllner, Markus; Johansson, Leena-Sisko; Rojas, Orlando J. Morphology-controlled synthesis of colloidal polyphenol particles from aqueous solutions of tannic acid. *ACS Sustainable Chemistry & Engineering*, 2019, 7 (20), 16985–16990. DOI 10.1021/acssuschemeng.9b02378

- III** Bai, Long; **Kämäräinen, Tero**; Xiang, Wenchao; Majoinen, Johanna; Seitsonen, Jani; Grande, Rafael; Huan, Siqi; Liu, Liang; Fan, Yimin; Rojas, Orlando J. Chirality from cryo-electron tomograms of nanocrystals obtained by lateral disassembly and surface etching of never-dried chitin. Accepted to the journal *ACS Nano* in 2020.

- IV Kämäräinen, Tero**; Tardy, Blaise L.; Javan Nikkhah, Sousa; Batys, Piotr; Sammalkorpi, Maria; Rojas, Orlando J. Effect of particle surface corrugation on colloidal interactions. *Submitted*, 2020.

Author Contributions

Paper I: Harmonic analysis of surface instability patterns on colloidal particles.

TK created the particle reconstructions from cryo-TEM images acquired by JS, analysed the particle morphologies and wrote the preliminary manuscript under the supervision of MA and OJR. MA prepared the particles in collaboration with JRaula and EIK. All authors critically reviewed the results and participated in the discussion and writing of the final manuscript.

Paper II: Morphology-controlled synthesis of colloidal polyphenol particles from aqueous solutions of tannic acid.

MA, TK, BLT, LCG and MM carried out particle syntheses and SEM imaging. TK analysed the process condition-morphology relations and wrote the preliminary manuscript under the supervision of BLT and OJR. MA developed the particle preparation method and performed thermochemical measurements. MM performed GPC and LSJ carried out XPS measurements. All authors critically reviewed the results, discussed and participated in the writing of the final manuscript.

Paper III: Chirality from cryo-electron tomograms of nanocrystals obtained by lateral disassembly and surface etching of never-dried chitin.

TK created the particle reconstructions from cryo-TEM images acquired by JS and WX. TK analysed the particle morphologies and wrote the corresponding section in the manuscript under the supervision of OJR. LB wrote the preliminary manuscript. LB, WX, JM, RG, and SH carried out the experimental work, physicochemical measurement and data interpretation. All authors critically reviewed the results and discussion and participated in the writing of the final manuscript.

Paper IV: Effect of particle surface corrugation on colloidal interactions.

TK carried out the colloidal interaction energy calculations and wrote the preliminary manuscript under the supervision of BLT and OJR. TK, SJN, PB and MS designed, and TK performed the Langevin dynamics simulations. All authors critically reviewed the results and discussions and participated in the writing of the final manuscript.

1. Introduction

The limits of our ability to manipulate the physical world determines how well we can address the most pressing global challenges that we face in areas related to healthcare,¹ the environment² and climate change,³ among others. These seemingly dissimilar aspects are connected by the workings of the atomic world, which through nanotechnology play a pivotal role in enabling sustainable life in the 21st century and beyond. Oversight of these matters has manifested in a wasteful use of resources that now populate our landfills and sea floor, while contributing to the decline of the biome.^{4,5} Such shortcomings have recently promoted the disapproval of single-use fossil-based plastics, which account for a large portion of the existing microplastics in the marine environment⁶ and our drinking water,⁷ provoking governmental bodies to legislative action.⁸ The growing juxtaposition between renewable and fossil-based materials and the ensuing demand in multidisciplinary research in environmentally friendly solutions has instigated funding institutions to support collaborations such as the FinnCERES Materials Cluster in Finland.⁹

Among the formidable challenges in materials science, is the development of competitive, sustainable alternatives to conventional, state-of-the-art technologies, as utilization of natural products often requires that material performance is forfeited. However, through evolutionary pressure, nature has gone much beyond our current technological capabilities by assembling atoms and molecules with high reproducibility and precision, yielding materials that display micro- and nano-architectures with great mechanical strength, such as the nacre shell,¹⁰ crustacean exoskeleton,¹¹ avian egg shell¹² and sponge spicules,¹³ while often demonstrating self-healing properties. These impressive structures found in living things have increasingly inspired the direction of natural sciences. The future materials engineer will adapt tools and materials via biomimicry in a quest for peak material performance.^{14,15} The exploration is at an early stage and many valuable lessons still lie ahead. Thus, the preservation of animal and plant life is of direct technological utility, and in turn, bears broad economic and societal benefits.

Traditionally, when imitation of natural materials has not been economically feasible, engineers have resorted to direct utilization of the embedded structural constituents by means of deconstruction and purification, as exemplified, e.g., by the paper industry. Isolation of wood nanostructures has further opened new possibilities for the application of plant biomass.¹⁶ Decreasing the physical di-

mensions of the fibre components in paper, for example, by using cellulose nanofibrils, makes the resulting nanopaper stronger and tougher due to a smaller intrinsic defect size and increased hydrogen bonding between the fibrils.¹⁷ Nanopaper also offers improved optical transmission¹⁸ and barrier properties.¹⁹ The deconstructionist route of material preparation continues to offer significant opportunities for biomass valorization,²⁰ while playing a concurrent role with biomimicry in elevating our technological feats to a new, higher standard.

1.1 Scope and outline of the thesis

The work presented in this thesis broadly concerns the use of renewable, plant-based materials and their embedded nanostructures. More specifically, we introduce new preparative protocols for bio-based particles and clarify their quantitative, morphological character and interactions. Additional results obtained by the author not found in the publications are discussed when they offer valuable information.

In **Papers I** and **IV**, we explore the implications of using wrinkling, present in many natural physiological systems,^{21–23} as a morphology and colloidal interaction modifier for colloidal lignin particles. In **Paper I**, we introduce a new protocol for creating corrugated particles (CPs) from lignin using an aerosol flow reactor method and study their morphology using electron tomography (ET). Frequency domain methods were used to analyse the three-dimensional particle reconstructions to yield information on how the corrugations are distributed on different length scales. The resulting particle models were utilized in **Paper IV** as generalized descriptions to assess the influence of surface corrugations on colloidal interactions compared to smooth, spherical particles of similar volume.

In **Paper II**, we propose a novel, green particle preparation method that is capable of producing many different particle shapes including rod-like, planar and cuboidal crystals from tannic acid. The process condition-morphology relationships were illuminated using principal component analysis (PCA), while chemical composition and thermal stability were also studied.

In **Paper III**, we study never-dried chitin nanocrystals (ChNCs) isolated from an abundant crustacean residue using a one-step acid hydrolysis aided by surface deacetylation. We study their morphology using ET and numerical shape analysis based on PCA. The analyses provide insights into the effect of drying history and aggregation on the measurement of ChNC chirality.

In Section 2, the relevance of morphology is discussed from the particle technological perspective. The materials employed in this thesis are introduced and remarks on the mechanisms that underlie particle formation in the utilized preparation methods are provided. Section 3 outlines the particle preparation protocols and gives an account on the main characterization and analysis methods used to derive the central results presented in the publications. Section 4 contains an exposition of the main results, while Section 5 gives concluding remarks and future prospects.

2. Background

This section gives a panoramic view of some of the roles that morphology plays in the broader particle-technological context and how the work in this thesis relates to established research directions. The main materials are introduced with some general remarks on the particle preparation processes employed in this thesis. These comprise the two bottom-up approaches, namely the aerosol flow reactor method that was used to create corrugated colloidal lignin particles and the solution precipitation method that yielded crystalline polyphenol-based particles from tannic acid, as well as the top-down deconstruction method used to extract never-dried chitin nanocrystals from crab residues.

2.1 Role of morphology in particle technology

Important characteristics of particulate systems include their intrinsic properties and interactions with the surrounding environment. Exploring the attainable morphological variety is motivated by the many size, structure and morphology-dependent physicochemical properties that particles can possess.²⁴ As particle interactions are typically surface-dominated and the chemical reactions they partake occur at their interfaces, increasing the specific surface area of a particulate system generally leads to improvement, e.g., in catalytic,²⁵ electrochemical²⁶ or combustion²⁷ performance. As a result, a large body of work has been carried out to elucidate the mechanisms that underlie the morphological control of inorganic and organic materials such as gold,²⁸ silver,²⁹ titanium dioxide,^{30,31} zinc oxide,³² carbon^{33,34} and calcium carbonate^{35,36} due to their technological and biological significance.

More specifically, in electrochemical, photovoltaic and photocatalytic applications, hierarchical or fractal-like³⁷ architectures, that embody unique or repeating structural elements at multiple length scales, can outperform simpler crystalline shapes by providing a platform with enhanced light scattering capability, larger dye adsorption area, higher percolation and packing density, leading to improved electron transport and ion diffusion properties.^{38–40} In surface wetting, a well-known biological example of a hierarchical surface involves the self-cleaning property of superhydrophobic *Nelumbo nucifera* (sacred lotus) leaves, i.e. the Lotus effect,⁴¹ which arises from the interplay of surface chemistry and surface morphology.⁴² Commercial particulate analogies have been introduced, where morphology of the spray-coated hydrophobic powder films modify the

wetting properties of the target surface.⁴³ Further refined surface morphological control has even enabled the effect to appear in surfaces that are chemically hydrophilic.⁴⁴

In biological systems, the conformability of red blood cells is partly afforded by their non-rigid, biconcave shape, allowing them to transverse through capillaries narrower than their own diameter.^{45,46} Similarly in drug delivery systems, particle shape affects their movement in the body in addition to their degradation kinetics, passage through filtering organs, targeting ability and uptake by macrophages.⁴⁷ Therefore, an important aspect particle technologists must understand prior to the introduction of new materials, is the possible adverse health effects that are associated with the utilization of particulate matter in contact with people, livestock and the environment as size and shape dependent interactions of nanoparticles can work against their safe usage as bulk macroscale material behaviour does not guarantee similar biological activity at the nanoscale.^{48–50} With cellulose nanomaterials, the research fortunately indicates low toxicity.^{51,52}

Hence, the morphometric characterization of particulate systems is of considerable importance in studying structure-property relations in multitude of circumstances ranging from physicochemical to biological. Often a simple imaging technique might suffice as shown with the regular crystalline shapes analysed in **Paper II**, while with more complex morphologies, methods yielding three-dimensional information might be warranted as emphasized by the work presented in **Paper I** and **Paper III**. The changes that morphology can impart on colloidal interactions is exemplified by the results of **Paper IV**.

2.2 Corrugated lignin particles and their interactions

Understanding morphological influences, such as surface roughness, on colloidal interactions can elucidate the kinetic and thermodynamic fate of particulate systems. In colloidal suspensions, particles with acute geometries have been associated with improved colloidal stability.^{53,54} In membrane separation processes, avoiding particle attachment on the membrane surface is required to insure prolonged separation efficiency, necessitating the evaluation of colloidal interactions.⁵⁵ In pulmonary drug delivery, where inhaled particles travel through an increasingly narrow respiratory tract, the delivery efficiency and aerosolization performance is greatly influenced by the particle morphological dependencies of their aerodynamics and colloidal interactions.⁵⁶ Utilization of submicron particles brings challenges due to their high specific surface area, which can show as a strong interparticle cohesion and poor aerosolization performance. To improve the pulmonary deposition at this size range, non-spherical morphologies, such as corrugated particles, are being considered.^{57–59} While it is known that too large surface corrugations can in fact enhance agglomeration,⁶⁰ the characterization of colloidal interactions of particles bearing surface corrugations is lacking and realistic particle models are needed to take into account the complex morphology of such particles.

In **Paper I**, we expand the available preparation protocols of colloidal lignin particles to include such corrugated shapes and study their morphology using tomographic 3D reconstructions. We utilize this detailed morphometric knowledge of these particles in **Paper IV** as means to assess the colloidal interactions of corrugated particles, and thereby, shed light to this broadly interesting topic.

2.2.1 Lignins

Lignins are the second most abundant biopolymers in the world after cellulose, accounting for roughly 25–30 % of all biosphere carbon.⁶¹ Lignin is found in many plants, where its main role is to act as a binder between the other major components, i.e. cellulose and hemicelluloses (**Figure 1a**).⁶² The chemical structure of lignin displays regional and source-based variations of a heterogeneous aromatic compound formed through the polymerization of three monolignol building blocks, *p*-coumaryl alcohol, coniferyl alcohol and sinapyl alcohol (**Figure 1b–d**), linked through –O– and C–C bonds.⁶³ A commercial lignin was used in **Paper I**, which was extracted from a softwood species (pine) through the Kraft process, wherein lignin is depolymerized, solubilized and precipitated to delignify cellulose.⁶⁴ Softwood contains mostly coniferyl units, which makes it generally more abundant in C–C crosslinks compared to hardwood lignin that contains sinapyl units in greater proportion.^{65,66}

Over 50 million tons of lignins are produced annually, mostly via the Kraft process, of which around 98 % is estimated to be used for the production of energy.⁶⁷ Around 10–15 % of Kraft lignin could be viably isolated,⁶⁸ which cre-

Figure 1: (a) Schematic representation of wood structure: (i) transection of wood cell network, (ii) cell wall layers, (iii) microfibrils and (iv) the lignin-carbohydrate complex. Adapted from Nishimura et al. (2018)⁶² with permission from Nature Publishing Group under Creative Commons license (CC BY 4.0). Monolignols: (b) *p*-coumaryl alcohol, (c) coniferyl alcohol and (d) sinapyl alcohol.

ates a great opportunity and economic incentive to find new value-added products for lignin. Having a high carbon content of over 60 % makes lignin a viable candidate for the creation of activated carbon and carbon fibres, for instance.⁶⁹ To curtail the increasing processing costs associated with the chemical modification of their highly heterogeneous structure, feasible competition with established commercial products have been proposed through their use as colloidal units, e.g., for interfacial stabilization in Pickering emulsions,^{70–74} adhesives⁷⁵ and biomaterials.⁷⁶ Different colloidal lignin preparation routes are actively being investigated,^{71–80} which rely on aerosol- or solution-based methods. In **Paper I**, we prepared corrugated lignin particles using an aerosol flow reactor (Section 3.2.1) that utilizes the drying of aerosolized lignin solution droplets in an elevated atmosphere to yield solid colloidal particles.

2.2.2 Surface corrugation in drying solute-laden droplets

Particle preparation processes utilizing the drying of aerosolized solution droplets, such as the aerosol flow reactor method, spray-drying and electrospraying,^{81–83} can be used to produce corrugated morphologies (**Figure 2**). During drying, the net solvent content of the droplet is evaporatively decreased, which leads to an increase in solute concentration near the receding air-solution interface. When the evaporation rate-to-solute diffusion rate (Péclet number) ratio is large,⁸² the solute concentration can reach the critical supersaturation near the free interface early during the drying process, instigating the precipitation of the solute in the form of a spherical shell. As the drying proceeds, this precipitate shell is subject to drying-induced capillary stresses, which can buckle a sufficiently thin, pliable shell.⁸⁴

Buckling instability produces a morphology characterized by surface corrugations and dimples. Studies on elastic spherical shells have shown that the particle radius (R) and the spherical shell thickness (h) influence the subsequent pattern formation, whereby decreasing h/R yields a transition in the surface pattern.⁸⁵ A similar transition has been also observed when the magnitude of the buckling stress is increased at constant h/R .^{86,87} In collapsing shells, the number of indentations that is produced has been linked to the volume change that occurs as a result of buckling, favouring one indentation (bowl-shape) for small and large volume changes, while larger indentation numbers take intermediate

Figure 2: Schematic representation of the main stages of corrugated particle morphology formation. (a) Initial aerosolized precursor solution droplet. (b) Solute precipitation at the free interface forming a spherical shell. (c) Precipitate shell buckling under drying-induced capillary stresses. (d) Dry, corrugated particle morphology.

values.⁸⁸ Additionally, the compression rate, due to capillary or osmotic pressure, also influences the number of attained indentations as shown computationally for the compression of spherical capsules, wherein slow compression rates allowed the system to relax to local elastic energy minimum configurations during the crumpling, yielding surfaces with fewer indentations compared to higher compression rates.⁸⁹

2.2.3 Particle morphology and DLVO interactions

The theoretical framework of Derjaguin, Landau, Verwey and Overbeek (DLVO) is a widely used to evaluate colloidal interactions quantitatively by considering the electric double layer and van der Waals interactions. Particle morphology affects colloidal interactions by altering the physical size, contact area and contact radius of curvature of the interacting bodies. The effect of surface morphology on the nature of interparticle and particle-surface interactions has been extensively studied due to shortcomings of established model systems based on spherical particle shapes. The studies often utilize various surface roughness models, including hemispherical, conical and cylindrical protrusions and depressions,^{90–95} or fractal-like^{96–98} surface topographies, whereby generally, the introduction of topographic heterogeneities tends to weaken the DLVO interactions, resulting in a decrease in energy barrier height as well as the secondary and primary minimum depths. Due to the statistical nature of many heterogeneous surface patterns, they can also locally contribute to the inversion of this tendency.⁹⁹ In particles bearing large protrusions with a characteristic length, colloidal interactions are greatly influenced by the morphological feature radius of curvature due to the diminished contact radius.^{53,100} In corrugated particles, the characteristic dimensions include the radius of curvature of the ridges (crust thickness), ridge lengths and the sizes of the flat polygonal regions that they form. We address these complications in **Paper IV** by assessing the DLVO interactions in a spatially uniform manner around realistic particle models and by labelling the different morphological features associated with surface corrugations with the respective interaction direction to give a comprehensive picture of the distribution of interaction energies as detailed in Section 3.3.4.

2.3 Morphological control of crystalline particles from tannic acid

Finding processes that allow the control over synthesized particle morphologies is advantageous for the development of high surface area functional materials. The usage of biofunctional particulates could benefit from additional preparative freedom in designing their morphological and structural properties to further tailor their action. A novel tannic acid-based system allowing particle morphological control is introduced in **Paper II**, wherein galloyl-rich moieties were assembled into various crystalline shapes ranging from rod- and plate-like to cuboidal.

2.3.1 Tannins

Tannins are a class of polyphenolic plant secondary metabolites found in many parts of the plant, where they are active in protecting the plant from pathogens, insects and herbivores.¹⁰¹ Natural polyphenols are consequently known for their many favourable biological activities including antioxidative, anti-inflammatory, antimicrobial, antimutagenic and anticarcinogenic properties.^{102–105} Tannins are categorized into hydrolysable and condensed tannins. The former are further divided to ellagitannins and gallotannins by the nature of the galloyl residue linkages.¹⁰¹ The tannin employed in **Paper II** was tannic acid, a gallotannin, comprised of galloyl moieties linked through ester bonds (**Figure 3b**).

Historically, tannins have been associated with dyeing of textiles by utilization of their metal complexation ability¹⁰⁶ and with leather-making (tanning) by their capacity to crosslink animal skin proteins.¹⁰⁷ More recently, these properties have been exploited in creating sustainable alternatives to conventional adhesives and coatings.¹⁰⁸ Although tannins are less available than the major plant-based materials, with around 200 000 tons produced commercially each year,¹⁰⁹ hydrolysable tannins like tannic acid contain a phenolic unit suitable for bottom-up preparation methods (**Figure 3a**).

Figure 3: (a) Gallic acid and (b) a representative structure of commercial tannic acid from Sigma-Aldrich.

2.3.2 Particle morphology control

Tannins and other plant secondary metabolites are often incorporated in organic or inorganic platforms as additives and coatings for functional purposes.^{110–114} Developing template-free methods entails the control over the precipitate formation process that occurs through the attainment of solute supersaturation and the resulting nucleation and growth via agglomeration and secondary nucleation.¹¹⁵ As a general rule, surfaces of the slowest growing faces control the ensuing crystal shape.¹¹⁵ The presence of impurities can have a catalytic effect on nucleation by providing surfaces that act as favourable nucleation sites, which can have a large influence on the final precipitate shape. Often in practise, particle morphological control is studied simply through incorporation of impurities, varying stirring conditions, changing pH and temperature in an

effort to alter, e.g., the supersaturation, agglomeration tendency, degree of dissociation of chemical groups or nucleation rate.

Recently, Bhangu et al. (2018)¹¹⁶ reported on the morphological control of plate-like ellagic acid particles prepared from tannic acid, wherein the radical formation, responsible for the oxidative coupling of tannic acid hydrolysis products, was modulated by using sonochemical parameters. They observed a decrease in particle size and increase in yield with an increase in ultrasonic power, which they attributed to increased radical formation and nucleation rate. The particle aspect ratio was shown to correlate with the ultrasonic frequency, likely through reducing radical formation resulting in a lower ellagic acid supersaturation and nucleation rate.

Ellagic acid has been previously precipitated into a variety of morphologies, e.g., rod-like, planar, and cuboidal shapes,^{117–119} but a one-pot synthesis method capable of producing an analogous morphological variety from tannic acid seem to not have been developed until now.

2.4 Chirality of never-dried chitin nanocrystals isolated from crustacean residue

Optically active nanostructures are found, e.g., in insects, which employ the assembly of structural elements into regular arrangements in an effort to display colour.^{120,121} Some rod-like particles, such as cellulose nanocrystals (CNCs) and chitin nanocrystals (ChNCs), can be made to self-assemble into a chiral nematic order, which exhibits similar interaction with an incident light reproducing the structural colour effect.¹²² These architectures have a large commercial potential as they could provide a more sustainable alternative to conventional dyes and pigments in art and design.¹²³ The chirality of cellulose and chitin chains have been hypothesized to influence the self-assembly of nanorods such as CNCs into chiral nematic phases.^{124–128} Molecular dynamics simulations^{129,130} and experimental^{131–135} investigations have shown evidence of a right-handed chiral twist. The chirality of chitin, although a related polysaccharide, has been much less studied, with only computational studies being available.^{136,137}

In **Paper III**, we explore experimentally ChNCs using tomographic 3D reconstructions to yield insights in their aggregation and chirality properties. As drying-induced forces can influence the material's morphological characterization,^{132,133,138} we utilize never-dried ChNCs to preserve their hydrated morphology.

2.4.1 Chitin

Chitin is the second most common naturally occurring polysaccharide after cellulose, found in fungi, insect cuticles, algae and crustacean shells.¹³⁹ Chitin is a linear polymer of *N*-acetylglucosamine units (**Figure 4b**), with a deacetylation degree generally around 10–20 % in crustacean shells,¹⁴⁰ where it constitutes around 15–40 % of the material, while the other major components, calcium carbonate and proteins, account ca. 20–50 and 20–40 %, respectively.¹⁴¹ The

Figure 4: (a) Schematic illustration of the structure of the American lobster (*Homarus americanus*) exoskeleton: (i) Cuticle cross-section showing the biomineralized nanocomposite. (ii) Helical Bouligand structure composed of proteins, minerals and chitin. (iii–iv) Chitin nanofibril bundles. (v) Chitin nanofibrils formed from aggregates of α -chitin crystals surrounded by proteins. (vi) The most common polymorph, α -chitin, crystal structure composed of antiparallel chitin molecules. Adapted from Raabe et al. (2005)¹⁴⁶ with permission from Elsevier. (b) *N*-acetylglucosamine, the repeating unit of chitin.

relative amounts of these components vary greatly between species and the location in the exoskeleton, e.g. the calcium carbonate content of oysters shells can be up to 96 %, ^{142,143} while insect cuticles are composed mainly of chitin and proteins.¹⁴⁴ Seasonal variations might exist in biomass chitin content due to, e.g., moulting phases.¹⁴⁵ The chitin sourced in **Paper III** was isolated from crab shells, where it partakes in the formation of a specific chiral nanoarchitecture as shown in **Figure 4a**.¹⁴⁶

Chitin is perhaps most conveniently sourced from crustacean and mollusc residues with high chitin content, such as crabs, lobsters, prawns, krill, shrimps, mussels and scallops, due to their utilization by the food processing industry. The annual production of molluscs and crustaceans shell waste is around 6–8 million tons worldwide, which presents a great opportunity for valorization.^{141,147} Besides having the capacity to create structural colour, chitin, or its deacetylated form (chitosan), could compete with synthetic materials in high value products, e.g., in cosmetic and biomedical applications, where their biodegradability and biocompatibility weigh in their favor.¹⁴⁸

2.4.2 Deconstruction of a crustacean exoskeleton

When particles are isolated from biological sources, such as plants and food waste, the morphologies are predetermined. Many of the morphological needs are addressed in choosing the source material and the degree to which it is deconstructed, which in practice pertains to the duration and strength of chemical

or mechanical treatments. Moreover, this approach allows particles to be utilized that are currently challenging to create synthetically from bottom up, such as large highly crystalline polymeric particles of chitin or cellulose.

As shown in **Figure 4**, chitin is embedded in a biomineralized composite structure in a crustacean shell, containing chitin nanofibril bundles surrounded by proteins and minerals. The isolation of chitin nanofibrils and nanocrystals proceeds typically through three main steps: demineralization and deproteinization with acid and alkali treatments followed by decolourization with an organic solvent or a bleaching agent.¹⁴⁹ Finally, the chitin is disintegrated into nanosized elements by acid hydrolysis^{150–152} or mechanical action using high-pressure homogenization^{153–156} or microfluidization.^{157,158}

2.4.3 Chiral twist in chitin nanocrystals

The chiral twist of chitin and ChNCs has been comparatively less studied than cellulose and CNCs. For CNCs, molecular dynamics simulations have suggested a length-independent right-handed twist with an inverse proportionality to cross-sectional area, yielding values roughly between 1–10 °/nm, when lengths ≤ 60 glucose units were studied.¹³⁰ Previously, similar ca. 1.5° twist per cellobiose unit (1.038 nm¹⁵⁹) had been acquired.¹²⁹ The experimental evidence based on imaging techniques of cellulose micro and nanofibrils have shown comparable values,^{133,135} while considerably lower helical twists have been observed for CNCs.^{132,134} Evidence for a right-handed twist in CNCs isolated from Whatman® filter paper has been acquired using electron tomography,¹³⁴ which by estimating from two publication images gives values roughly around 0.17–0.20 °/nm, from approximately 25–30° total twist along the ca. 150 nm length of the nanocrystals. Recently, Ogawa (2019)¹³² observed a twist between 0.04–0.13 °/nm along never-dried tunicate CNCs using electron microdiffraction measurements, wherein differences in the twist magnitude were ascribed to differences in the cross-sectional shape of the CNCs. Further, dried samples displayed regions devoid of twist separated by sudden twisted segments likely due to either the drying capillary forces between the CNCs and the substrate causing untwisting of the structure or an intrinsic property of the CNCs.

For ChNCs, in the molecular dynamics study of Beckham & Crowley (2011),¹³⁶ agreement on the reported ChNC crystal structure in water was achieved but without any helical twisting. On the other hand, Střelcová et al. (2016)¹³⁷ studied the twisting of hydrated 20 *N*-acetylglucosamine units long ChNCs (ca. 10.6 nm) finding values roughly between 1–22 °/nm and an increase in twist with increasing number of adjacent chitin chains. To the author's knowledge, no experimental investigations have been published in relation to ChNC chirality but extrapolating the results of CNCs would suggest smaller twist angles than predicted by molecular dynamics studies.

3. Experimental

This section introduces the particle preparation protocols and the experimental and numerical methods used to carry out the morphometric analyses.

3.1 Materials

The lignin used in **Paper I** was softwood (pine) Kraft lignin (Indulin AT®) acquired from MeadWestvaco (USA). The tannic acid used in **Paper II** was purchased from Sigma-Aldrich (USA). The chitin used in **Paper III** was extracted from fresh crabs (*Callinectes sapidus*) purchased from Helsinki harbour in Finland.

3.2 Preparative methods

3.2.1 Preparation of lignin particles

The preparation of smooth and corrugated colloidal lignin particles using the aerosol flow reactor method in **Paper I** was adapted from Ago, M. et al. (2016).⁷¹ The method comprises four items depicted in **Figure 5**, namely a precursor solution, an atomizer, a heating element and a particle collector. Lignin (1 wt%) was dissolved in 50/50 vol% water/ammonium hydroxide solution (25 %). When an equivalent mass of ammonium hydrogen carbonate (blowing agent) was included to the precursor solution, corrugated particle morphologies were formed, while its omission produced smooth, spherical particles. The atomizer creates a fine droplet spray from the precursor, which is carried under laminar nitrogen flow through a tube heated to 80 °C, whereby the droplets dry. Subsequently, part of the dry particle aerosol stream is diverted through a collector, wherein the particles are segregated based on their average size by the action of a tortuous flow path containing 10 intermittent arrays of nozzles with decreasing size and nominal cut-off diameters ranging from 31 nm to 7.8 µm. During their passage, the particles are deposited to impaction surfaces at each stage (**Figure 5a**), from where they are collected after the production run by disassembling the collector. The overall yield of the process was around 30–40 %.

Figure 5: (a) Collector comprising of multiple stages, each having a different effective particle cut-off radius as determined by the aerosol flow geometry and acceleration nozzle diameter. (b) Schematic representation of the aerosol flow reactor unit. The lignin precursor solution is atomized and transported to an elevated temperature using nitrogen carrier gas. The precursor droplets dry and are subsequently captured at the collector impaction surface. Adapted from Ago, M. et al. (2016)⁷¹ with permission from American Chemical Society.

3.2.2 Preparation of crystalline polyphenol-based particles

In **Paper II**, the polyphenol-based particles were prepared from aqueous tannic acid solutions (2 wt%) adjusted to pH 7.8–11 using potassium hydroxide (KOH, 1 M), lithium hydroxide (LiOH, 1 M), sodium hydroxide (NaOH, 1 M), trisodium phosphate (Na_3PO_4 , 0.5 M) and ammonium hydroxide (NH_4OH , 25 %). The flask was sealed with perforated Parafilm® and put under continuous agitation (orbital shaker, 200 min^{-1}). A change in colour of the initially yellow tannic acid solution to light brown was noted during the initial period following the pH adjustment. This further changed to dark greenish colour when the reaction was allowed to continue between 14 h and one week.

3.2.3 Preparation of never-dried chitin nanocrystals

ChNCs were isolated from fresh crab shells in **Paper III**. The crab shells were subjected to alternating acid (1 M HCl) and alkaline (1 M NaOH) treatments at least three times, each treatment lasting one day, followed by a 2 h treatment with sodium chlorite solution (acetic acid, pH 5.0) at $70\text{ }^{\circ}\text{C}$. The resulting purified chitin was washed with distilled water and disintegrated into smaller pieces using a blender and stored at $4\text{ }^{\circ}\text{C}$. Part of the chitin was then partially deacetylated (27.3 %)¹⁵⁸ using a 25 mL/g liquid-to-solid ratio with a 3.5 h NaOH solution (12.4 M, ca. 33 wt%) treatment at $90\text{ }^{\circ}\text{C}$, followed by washing to neutral pH and removal of excess water by pressing. Deacetylated chitin nanocrystals (DE-ChNCs) were acquired from deacetylated chitin using acid hydrolysis (3 M HCl) with a 30 mL/g liquid-to-solid ratio at $95\text{ }^{\circ}\text{C}$ for 30–90 min under stirring, after which the reaction was quenched with Milli-Q water and washed using a centrifugation cycle (10000 rpm, 15 min) three times. The sediment was then dialyzed in Milli-Q water until pH 4.0 was reached and redispersed using pulsed

tip sonication (3 min, 5/2 s on/off), followed by centrifugation (8000 rpm, 5 min) to separate larger particulates and storing at 4 °C. Non-deacetylated ChNCs were acquired from non-deacetylated chitin as described for DE-ChNCs, whereby an acetylation degree of at least 97 % was acquired.¹⁶⁰ The DE-ChNCs and ChNCs analysed with ET were selected from samples hydrolysed for 90 min, while an additional sample hydrolysed for 30 min was used for DE-ChNC.

3.3 Characterization methods

3.3.1 Scanning electron microscopy

Particle morphologies were characterized in **Papers I** and **II** with a field emission scanning electron microscope (SEM, Zeiss Sigma VP, Germany) using an acceleration voltage of ca. 1.5 kV. The samples were prepared by drop-casting a dilute suspension on a cleaned silicon wafer piece, which was then allowed to dry in ambient laboratory conditions. A ca. 3–5 nm thick platinum or palladium/gold alloy film was thereafter sputtered on the sample. Images were analysed with the ImageJ software.¹⁶¹

3.3.2 Cryo-electron tomography

Cryo-ET was employed to elucidate the three-dimensional morphology of corrugated lignin particles (**Paper I**) and never-dried ChNCs (**Paper III**).¹⁶² The principle of the tomographic reconstruction can be depicted through a two-dimensional analogue shown in **Figure 6**. After the particle suspension was transferred to the imaging grid and blotted to remove excess suspension, the sample was quickly cooled to cryogenic temperatures and maintained at –187 °C during the imaging, which guarantees a never-dried, hydrated morphology of the ChNCs. Tilt series were acquired using JEOL JEM 3200FSC transmission electron microscope (TEM) operated at 300 kV under zero energy loss conditions. The tilt series spanned roughly $\pm 65^\circ$ with increments of ca. $2\text{--}4^\circ$. Gold

Figure 6: Two-dimensional analogue of the image generation principle in electron tomography. The “Aalto” image represents the sample, which is imaged (Radon transform) from different angles and summed together as indicated by the orientation of the red lines. As the number of images increases, the original features can be recovered with increasing precision.

nanoparticles were also deposited to the TEM grid to facilitate the image alignment process and reconstruction using the simultaneous iterative reconstruction technique (SIRT, 8 iterations) carried out in the IMOD Etomo,¹⁶³ while feature extraction and visualization was performed with the UCSF Chimera.²⁸ Gaussian filtering and binning were used to reduce noise and data size.

3.3.3 Frequency domain description of particle morphology

In **Paper I**, spherical harmonic descriptions of particle morphologies were used to further elucidate the complex, corrugated surface topography. This approach is particularly attractive as it allows the decomposition of the shape into frequency domain components analogous to Fourier series.¹⁶⁴ Similar descriptors have been used in, e.g., studies of powders^{165–167} and celestial objects.^{168–170} The surface topographies, as given by their tomographical 3D reconstructions, were expanded in terms of spherical harmonics using the Fortran libraries of the Hierarchical Equal Area Isolatitude Pixelization of a sphere (HEALPix) software package.¹⁷¹ The particle model was transferred into a HEALPix tessellation with a resolution parameter $N_{\text{side}} = 32$ by choosing for each pixel the largest radial value of the topography in centre-of-mass coordinates. As this neglects multi-valued surface regions, the spherical harmonic model can be larger in volume than the reconstruction.

Spherical harmonics form a basis for bounded functions on a sphere, and thus, the particle topographies can be expanded (in HEALPix) as

$$r(\theta, \phi) = \sum_{\ell=0}^{2N_{\text{side}}} \sum_{m=-\ell}^{\ell} a_{\ell m} Y_{\ell}^m(\theta, \phi), \quad (1)$$

where r , θ , ϕ are spherical coordinates of the particle surface, $a_{\ell m}$ are the expansion coefficients of spherical harmonic functions Y_{ℓ}^m of degree ℓ and order m . Spherical harmonics can be visualized, e.g., by using their real-valued forms[†] depicted in **Figure 7**, which show their decreasing angular resolution with increasing ℓ , expressible using¹⁷²

$$\lambda_{\ell} = \frac{2\pi r_0}{\sqrt{\ell(\ell+1)}}, \quad (2)$$

where $r_0 = a_{00}/\sqrt{4\pi}$ is the average value of $r(\theta, \phi)$. As a rotation-invariant descriptor of how the topography is distributed to different length scales, we use the angular power spectrum given by¹⁷³

$$C_{\ell} = \frac{1}{2\ell+1} \sum_{m=-\ell}^{\ell} |a_{\ell m}|^2. \quad (3)$$

The Mollweide projection was used because it preserves area proportions, which is convenient concerning the nature of the particle topographies with a characteristic surface corrugation length. Relative angles between surface features are not conserved, however.

[†] Defined as $Y_{\ell m}(\theta, \phi) = \begin{cases} \frac{i}{\sqrt{2}} [Y_{\ell}^m - (-1)^m Y_{\ell}^{-m}] & , m < 0 \\ Y_{\ell}^0 & , m = 0 \\ \frac{1}{\sqrt{2}} [Y_{\ell}^{-m} + (-1)^m Y_{\ell}^m] & , m > 0. \end{cases}$

Figure 7: Mollweide projection of real spherical harmonics $Y_{\ell m}(\theta, \phi)$ up to harmonic degree $\ell = 3$ and order $m \leq \ell$ showing the decrease in angular length λ_ℓ with increasing ℓ .

3.3.4 Calculation of colloidal interaction energies

Colloidal interaction energies were calculated in **Paper IV** within the DLVO framework, which accounts the electric double layer (EDL) and van der Waals (vdW) interactions. The electric potential of ions near a planar surface immersed in an electrolyte solution is governed by the Poisson-Boltzmann equation, which for small surface potentials, $|\psi_0| \leq 25$ mV, and a symmetric electrolyte can be written as¹⁷⁴

$$\frac{d^2\psi}{dx^2} = \kappa^2\psi, \quad (4)$$

where $\kappa = 1/\lambda_D$ is the inverse Debye length, given for a monovalent salt by

$$\kappa = \sqrt{\frac{2e^2 N_A c_0}{\varepsilon_0 \varepsilon_r k_B T}}, \quad (5)$$

where e is the elementary charge, N_A is the Avogadro constant, c_0 is the bulk ion concentration in mM, ε_0 is the vacuum permittivity, ε_r is the continuous medium relative permittivity, k_B is the Boltzmann constant and T is the temperature. For two infinite parallel planar surfaces with constant surface potential (ψ_A and ψ_B) separated by a distance x , the EDL interaction energy per unit area is given by¹⁷⁵

$$E_{\text{EDL}}(x) = \frac{1}{2} \varepsilon_0 \varepsilon_r \kappa \{ (\psi_A^2 + \psi_B^2) [1 - \coth(\kappa x)] + 2\psi_A \psi_B \operatorname{csch}(\kappa x) \}. \quad (6)$$

The corresponding non-retarded vdW interaction energy per unit area is¹⁷⁶

$$E_{\text{vdW}}(x) = -\frac{A_H}{12\pi x^2}, \quad (7)$$

where A_H is the Hamaker constant. At long distances, the finite speed of light shows as an attenuation of the vdW interaction. This retardation effect can be taken into account by using the phenomenological retarded Hamaker constant¹⁷⁷

$$A_{\text{RH}} = \frac{A_H}{1 + bx/\lambda}, \quad (8)$$

where $b = 5.32$ and $\lambda = 100$ nm are parameters conjoining the non-retarded and retarded regimes.

The surface element integration (SEI) method¹⁷⁸ was used to calculate the DLVO interaction energies of corrugated lignin particles with respect to a flat

plate. SEI method gives an exact interaction energy in situations when the other surface is flat,^{93,178} while extended-DLVO interactions can also be incorporated, notably the Born repulsion^{94,95,179} and Lewis acid/base interactions.^{99,180} Thus, SEI can be used to analyse many important colloidal interactions in conjunction with surface morphology and chemical heterogeneity.

In the SEI method, the interaction energy is given by an integral over the particle surface¹⁷⁸

$$U = \iint_S E(x)(\hat{n} \cdot \hat{z})dS, \quad (9)$$

where x is the surface element distance to the plate, $\hat{n}$ and $\hat{z}$ are the surface element and plate outward normal vectors, respectively. In **Paper IV**, $E(x)$ comprised the retarded vdW and EDL interaction energies as given above. Monovalent ionic concentrations were chosen such that the Debye length took values $\lambda_D = h/8$, $h/4$ and h relative to the particle crust thickness (h) (**Figure 8b**), while the lignin-lignin Hamaker constant of 17×10^{-21} J ($T = 298$ K)¹⁸¹ was used for the vdW term. The spherical harmonic models were used to define the surface topographies over which the SEI was evaluated by implementing a quadrature routine in Matlab (MathWorks, USA) that utilized a 37-point rule,¹⁸² which iteratively refined the surface triangulation until the relative (10^{-3}) or absolute ($10^{-6} k_B T$) tolerance was met.

Two types of plate configurations were used in the centre-of-mass frame of the particle defined as follows (**Figure 8a**). Type I configurations consisted of concentric arrangements of plate locations given by the HEALPix pixel centre angular coordinates above the particle's spherical envelope radius (R_{env}) with a resolution parameter $N_{\text{side}} = 8$ corresponding to an angular resolution of

Figure 8: (a) Corrugated lignin particle labelled CP-2 and the difference between Type I and Type II interaction energy profiles, showing schematically the spherical envelope radius as a dotted line (R_{env}) bounding the plate location for Type I profiles and the convex hull shown as a red solid line, which was used to define Type II profiles. (b) Particle crust thickness (h) shown from a cut-off. (c) Labelling of different Type II profiles based on the local morphological feature. The convex hull is shown as purple solid lines with black arrows pointing to the direction of the plate outward normal. (d) Morphological features associated with corrugated morphologies: (i) Flat-sided ridges that bound typically a polygonal-shaped ridge network. (ii) Ridges merging in a vertex region. (iii) Surface creasing, whereby adjacent ridges come into contact, making the surface area between them inaccessible.

7.33°. ¹⁷¹ Thereby, the interaction energies can be expressed in the frequency domain similar to the topography according to Equation 1. In Type II configurations, the plate orientation was determined from the convex hull of the particle shape determined in Matlab. Additionally, the locations were labelled vertex, ridge and ridge network depending on the local morphological feature near the plate (**Figure 8c,d**). The surface potential of the particle was fixed at -20 mV for both profile types, whereas the plate surface potential was varied between -15, -20 and -25 mV for Type II profiles, while for Type I, it was set to -20 mV.

3.3.5 Analysis of process condition-morphology relations

Principal component analysis (PCA) was used in **Paper II** as a dimensional reduction aid to yield insights into how process conditions affect the ensuing particle morphology. The PCA was carried out in Matlab, which uses the singular value decomposition (SVD) of a user-defined data matrix X :

$$X = USV^T, \quad (10)$$

where U and V are unitary and S is a diagonal singular value matrix with entries s_i^2 corresponding to the principal direction variances and T denotes matrix transpose. Standard deviations along the principal directions are given by the singular values

$$\sigma_i = \frac{s_i}{\sqrt{n-1}}. \quad (11)$$

As the crystalline particles displayed a homogeneous structure, mainly differing by the magnitude of crystal habit lengths, SEM images were used to assess the mean particle dimensions. Each process condition yielding particle-like precipitates was associated with its process conditions comprising the base counter cation ionic radius (R_+), base conjugate acid dissociation constant (pK_a) and initial solution pH, while the reaction time and tannic acid concentration were held constant at 14 h and 2 wt%, respectively. The morphology was characterized by using the mean physical dimensions, denoted by d_1 , d_2 and d_3 in descending order, volume ($V = d_1 d_2 d_3$) and yield after one week (Y_{wk}). This data was collated in row vectors of the form

$$x_i = [R_+ \quad pK_a \quad pH \quad d_2/d_1 \quad d_3/d_2 \quad V \quad Y_{wk}], \quad (12)$$

from which the data matrix was then constructed as

$$X = \begin{bmatrix} x_1 \\ \vdots \\ x_n \end{bmatrix} \quad (13)$$

and decomposed as per Equation 10 after normalization (zero mean and unit variance along columns). The number of principal components (PCs) was selected such that their explained variance was larger than the unit variance of $1/7 \approx 14\%$, which included the first three PCs. Varimax rotation was used to facilitate the interpretation process. ^{183,184}

3.3.6 Analysis of chitin nanocrystal chirality

In **Paper III**, PCA was used to analyse the twisting of ChNCs along their longest, axial dimension. The method utilizes PCA in two steps. First to define a coordinate system, where one axis aligns with the ChNC axial direction, and second, to determine the direction of anisotropy perpendicular to the axial direction (**Figure 9a–b**). Primed symbols are here used for the variables associated with the second PCA.

First, the data matrix was constructed from the ET reconstruction 3D model Cartesian surface coordinates (x, y, z) as

$$X = \begin{bmatrix} x_1 & y_1 & z_1 \\ \vdots & \vdots & \vdots \\ x_n & y_n & z_n \end{bmatrix} \quad (14)$$

and subjected to SVD (Equation 10). The surface points are then given in the principal component coordinate frame by the columns of the matrix US , while the columns (v_1, v_2, v_3) of matrix V give the principal directions of the ChNC, of which the first principal direction (v_1) gives the direction of the largest spread, i.e. the axial direction. The respective standard deviations of the ChNC surface points along v_1, v_2 and v_3 are given by σ_1, σ_2 and σ_3 (Equation 11). The particle was then divided into thin $0.5\sigma_3$ wide segments along v_1 (**Figure 9c**). The second PCA was then carried out for each segment, after which the first principal direction (v'_1) of the segment was used as an indicator of the local directional tendency of the ChNC from the angles α and β that v'_1 creates with v_2 and v_3 (see coordinate schematic in **Figure 9d**). As the segments are generally thinner than their lateral size, the directions v'_1 and v'_2 lie roughly in the plane defined

Figure 9: (a) Electron tomography reconstruction of deacetylated chitin nanocrystal and (b,c) its representation in the principal component coordinate frame (PCCF). Red and black arrows correspond to the first principal component vectors (v'_1) of the respective coloured segments. (d) Coordinate schematic showing the angles α and β used to define the orientation of the segments perpendicular to the nanocrystal axial direction shown in (b,c). (e,f) Angles α and β as a function of the segment centre coordinate along v_1 of the PCCF. The linear regression line in (e) is shown in black. The β mean ± 3 times its standard deviation is shown in (f) as dotted lines. The crosses in (e,f) and red arrows in (b,c) denote segments that were excluded from the linear regression.

by v_2 and v_3 , therefore large β indicates deviation from this general behaviour (**Figure 9c**).

The chirality was then determined using an iterative reweighted least squares linear regression model with 0.01 significance in Matlab based on α and its corresponding segment mean coordinate value along v_1 (**Figure 9e**). The first and last segments were automatically excluded from the analysis, as were segments with β over three standard deviations above and below the ChNC mean (**Figure 9f**). In some cases, only a subsection of the ChNC was utilized in the regression model due to kinks and morphological defects (red arrows in **Figure 9b,c** and crosses in **Figure 9e,f**).

4. Results and Discussion

The main findings of **Papers I–IV** are presented in this section. Additional results produced by the author, which are not part of the publications, are also discussed where available.

4.1 Corrugated lignin particles

This section contains an exposition of the main results related to particle shapes possessing corrugated surface patterns. The preparation method (Section 3.2.1) was reported in **Paper I** along with their morphological characterization with SEM and ET. In **Paper IV**, DLVO interaction energies were calculated for two particle models obtained in **Paper I** to compare the effect that local morphological features, i.e. vertices, ridges and ridge networks, have on colloidal interactions using the SEI method (Section 3.3.4).

Frequent reference will be made to the smooth, equivalent-volume sphere (EVS) with radius R_V . Although the spherical envelope radius (R_{env}), i.e. the smallest sphere that fully encloses the particle, is experimentally easier to estimate from SEM images, R_V is a more well-defined quantity as it is directly related to the particle volume, whereas R_{env} depends on the surface corrugation pattern. Naturally, $R_{\text{env}} = R_V$ only for smooth, solid particles, otherwise $R_{\text{env}} > R_V$.

4.1.1 Morphological characterization with scanning electron microscopy

At the size range that the collector operates, the corrugated particles (CPs) display a size-dependent morphological character (**Figure 10d–f**). More corrugated morphologies are attained in the smaller size ranges as evidenced by the characteristic ridge network that decorates the particle surfaces, while some level of surface creasing (self-contact) is also visible in the SEM images. Due to their non-convex morphology, drop-cast CP films of particles at this size range attain an apparently dense, interlocked packing (**Figure 10i**). At larger sizes, the surface corrugations decrease in amplitude and in the degree of surface creasing, until disappearing altogether for a part of the population at the largest size ranges (**Figure 10f**). As all the particle size fractions were produced during a single, continuous operation of the aerosol flow reactor, this attenuation of the ridge structure is likely related to an increase in the ratio between the crust

Figure 10: Scanning electron microscopy images of (a–c) smooth and (d–f) corrugated lignin particles (CPs) prepared under identical conditions with different precursor solution compositions. The particle size increases from left to right displaying the captured particles in collector stages 1, 5 and 9, respectively. (g) Close-up of CPs from stage 1. (h) CP with a spherical envelope radius (R_{env}) of approximately 170 nm, ridge length around 250–300 nm and crust thickness of ca. 50 nm. (i) Surface of a drop-cast CP suspension displaying their close-packing behaviour. (j) CP showing intermediate surface morphology between corrugated and rough. (k,l) Qualitatively similar morphologies between CPs with R_{env} of ca. 280 nm and 1.7 μm and crust thicknesses of ca. 40 nm and 260 nm, respectively. (m,n) CPs from stage 9 that contain a surface depression.

thickness and the particle radius at the buckling transition, h/R_B , making the shells more resilient towards buckling.⁸⁶

When the ratio of the particle size to crust thickness attain relatively similar values as shown in **Figure 10k,l**, with $h/R_{env} \approx 0.13$ and 0.15, respectively, the resulting morphology has an apparent similarity, though at larger particle sizes the particles possess a more pronounced, hierarchical, roughness-on-ridge morphology (**Figure 10l**). The SEM images further indicate that the crust thickness has a tendency to increase with respect to R_{env} as the particle size gets smaller. This might have a further crease-reducing effect as exemplified by the highly symmetric crumpled particle in **Figure 10h**, with $h/R_{env} \approx 0.28$.

Because the morphology has such a large variation between different sizes, size fractionation is essential to acquire morphologically homogeneous samples. Not present in **Paper I**, experiments were later carried out by the author to investigate the size fractionation properties of the collector. Extensive SEM image analysis was performed to assess the size distributions in different stages of the collector using ImageJ¹⁶¹ by measuring particles by their largest horizontal dimension. This approximates the spherical envelope radius of the particles, and thus yields a value larger than the smooth spherical particle size at the small particle size range, wherein large surface corrugations are observed. This discrepancy is illustrated by the size distribution median R_{env} differences (**Figure 11**), which suggest corrugated-to-smooth median R_{env} ratio of 1.7 and 1.3 for the collector stages 1 and 5, respectively (**Figure 10a,b,d,e**).

Figure 11: Spherical envelope radius (R_{env}) size distributions of (a) smooth and (b) corrugated colloidal lignin particles determined from scanning electron microscopy images of collector stages 1 and 5. The distribution medians are (a) stage 1: 100 nm, stage 5: 335 nm and (b) stage 1: 171 nm, stage 5: 442 nm.

4.1.2 Three-dimensional morphological characterization with electron tomography

ET allows a quantitative, three-dimensional characterization of the particle morphologies. The labelling CP-1, CP-2 and CP-3 is used to refer to the acquired 3D reconstructions of different CPs that were selected for the ET analysis (**Figure 12a**). Of these, CP-1 and CP-2 possess a more severely corrugated morphology compared to CP-3, which contains undulations of much smaller amplitude. The morphological details given by the ET shape analysis include the final surface area (A_F), final volume (V_F), final crust thickness (h_F) and surface coordinates.

From a particle engineering perspective, the surface area distribution (**Figure 12b**) and its accessibility is of interest. In each case, no disjoint surface regions were found. Later studies in the group suggested that hollow particles are present at certain size ranges. Particle diameters larger than around 600–700 nm were deemed too large for hollowness assessment with cryo-TEM due to the limited electron beam tolerance of lignin. As an outcome of crumpling, an increase in surface area-to-volume ratio (compared to a smooth, spherical particle) of around 100, 120 and 50 % was observed with CP-1, CP-2 and CP-3, respectively. A redistribution of the spherical shell into regions spanning near the centre-of-mass up to ca. $1.5R_V$ was observed with CP-1 and CP-2. For the CP-3

Figure 12: (a) Electron tomography reconstructions of corrugated colloidal lignin particles (shown parted roughly from the middle) and (b) their surface area distributions as a function of radial distance (r) from the particle centre-of-mass scaled with the equivalent-volume radius (R_V).

particle, the surface area distribution is more Gaussian in shape, centred roughly at R_V . The distribution tail in CP-3 is due to a surface depression locating on the side of the cryo-TEM sample holder (**Figure 14c**). A plausible explanation is that it is a form of surface instability^{185,186} as similar surface invaginations were observed, albeit rarely, in SEM images (**Figure 10m,n**). This is likely related to inhomogeneous precipitation⁸⁴ or a display of the shape favoured at smaller volume changes.¹⁸⁵ Of the buckled morphologies, the singly-indented, bowl shape^{187–189} was not observed when crumpling led to large volume changes, which is likely due to the high drying rates associated with the aerosol process.⁸⁹

The stages of droplet drying discussed in Section 2.2.2 are shown schematically in **Figure 13a,b** to illuminate the morphological parameters that can be deduced from A_F , V_F and h_F . During the particle shape formation, the pre-buckled spherical crust surface area (A_B) is decreased by the amount of surface creasing (A_C), i.e. $A_B = A_F + A_C$. Assuming that the volume remains roughly constant, i.e. the remaining solute solvated in the liquid core contributes relatively little to the final volume, and that possible viscous relaxation and isotropic shrinking

Figure 13: Schematic representation of the variables associated with corrugated particles: final surface area (A_F), buckling transition spherical surface area (A_B), inaccessible surface area due to creasing (A_C), buckling transition radius (R_B), final crust thickness (h_F) and crust thickness (H_F) with zero creasing. (a) Precipitate shell at the buckling transition point and (b) dry particle. (c) Plots of crust thickness $h = R - [R^3 - 3V_F/(4\pi)]^{1/3}$ and sphere surface area $A = 4\pi R^2$ at constant volume as a function of sphere radius (R). The grey annuli represent the shape transition as R is varied while the volume is kept constant.

remain negligible during and after the crumpling process, then A_C can be estimated from the spherical crust thickness (H_F) with volume V_F and surface area A_F . In the presence of creasing, $H_F > h_F$, and therefore h_F indicates roughly the deficiency in measured final area caused by creasing (**Figure 13c**). Using the 95 % confidence interval for the measurement of h_F yields values for the inaccessible surface area to be at most 19 % and 10 % in CP-1 and CP-2, respectively.

The ET results show that $R_{\text{env}}/R_V \approx 1.5$ for CP-1 and CP-2 ($R_{\text{env}} < 200$ nm), which suggests that the median R_V in the collector stage 1 is around 110 nm (**Figure 11b**). Therefore, the corrugated-to-smooth median R_V ratio is 1.1, i.e. much lower than the R_{env} ratio determined with SEM, as expected. The CP-3 reconstruction yields $R_{\text{env}}/R_V \approx 1.3$ at $R_{\text{env}} \approx 280$ nm, giving a corrugated-to-smooth median R_V ratio of 1.0. These results supplement the SEM size characterization, as the extent of the difference between R_{env} and R_V is difficult to estimate accurately from SEM images especially for highly corrugated particles. This also suggest that at the aerosol flow conditions used, the morphology does not likely influence their attachment on the collector impaction surface when judged based on the median R_V , though the difference in distribution spread is somewhat larger with CPs in collector stage 1.

Finally, the particle surfaces were analysed in the frequency domain to illuminate how the surface topographical variations are distributed to different length scales as explained in Section 3.3.3. The main differences between the particles lie in the angular lengths larger than the crust thickness ($\lambda_\ell > 4h$), wherein CP-3 spectrum is greatly attenuated compared to CP-1 and CP-2, due its drastically smaller corrugation amplitude (**Figure 14d**). Also, as a result, CP-3 is more spherical in shape, which is reflected in a small $\ell = 2$ term (ellipsoidal variation). The differences are possibly further enhanced by the presence of surface creasing in CP-1 and CP-2, which acts to increase the length at which the surface corrugates by merging adjacent ridges together. This also likely accounts some

Figure 14: Maps of spherical harmonic particle models of (a) CP-1, (b) CP-2, (c) CP-3 and (d) their normalized angular power spectra (C_ℓ/C_0 for $\ell \geq 2$) as a function of angular length-to-crust thickness ratio (λ_ℓ/h). Smaller λ_ℓ corresponds to larger ℓ .

of the differences observed between CP-1 and CP-2. Note that as CP-3 lacks a clear ridge structure, the estimation of h was based on spherical shell thickness with an equivalent outer surface area (H_F in **Figure 13a**).

In summary, ET greatly complements the morphological view given by SEM imaging with detailed quantitative information on their surface area distribution, volume and frequency domain character. Although ET is time-consuming and cannot yet reach such statistically meaningful numbers as SEM, details such as crust thickness are plausibly related to particle size similarly over a range of values, and therefore holds broad applicability. Describing the surface in a quantitative way is further justified as it allows the determination of the DLVO interaction energy distribution as discussed in the following section.

4.1.3 Influence of surface corrugations on colloidal interactions

In **Paper IV**, we explore the span of interactions that CPs form with respect to a flat plate by using the CP-1 and CP-2 particle models. Although the employed particles have a characteristic repeating length encoded in their topography by the crust thickness (h), their overall shapes are highly anisotropic and non-periodic, and thus, use of realistic particle shapes is advantageous. We investigated the influence of local morphological features on the interaction energy (Type II profiles) as well as the near-field interaction energy behaviour (Type I profiles). As described in Section 3.3.4, these morphological features were taken into account by categorising profiles into vertices, ridges and ridge networks (**Figure 8d**), while the ionic concentrations were selected such that the Debye lengths took values $\lambda_D \leq h$.

For Type I profiles, the CP-2 results show that depending on the orientation of the particle with respect to the plate, the magnitude of the interaction energy varies greatly based on the local surface topographic height between the interacting bodies (**Figure 15a–d**). Compared to a smooth sphere with equivalent volume (U_V) and surface potential, the interaction energy of CPs is on average larger in absolute magnitude at the same distance from the particle centre-of-mass. At high ionic concentrations, 4 and 45 % of the interaction energy profiles acquire a secondary minimum when $\lambda_D = h/8$ and $h/4$, respectively, corresponding to locations with small surface-to-surface distance (**Figure 15e–g**). At $\lambda_D = h$, the interaction is EDL dominated and thus repulsive at the studied range. Results for CP-1 were qualitatively similar.

Type II profiles permit the secondary minimum depth ($U_{\min}$) and energy barrier height ($U_{\max}$) to be determined for each local morphological category (**Figure 16**). The results indicate a similar trend in absolute magnitudes of $U_{\min}$ and $U_{\max}$ given by ridge network > ridge > vertex region. The most apparent distinction between these regions is their widely varying allowable contact area, which corroborates the observed trend. The interaction energy magnitude is higher with ridges and ridge networks as they come in more varied lengths and sizes, whereas vertices represent a more pointed surface motif. Variations in the interaction energies could also arise from creasing, whereby two ridges come into contact, effectively filling the concave domain in the middle of the bounding

Figure 15: DLVO interaction energy (U) profiles of Type I for CP-2 particle as a function of radial distance (r) from the particle centre-of-mass scaled with the equivalent-volume sphere radius (R_V) when Debye length (λ_D) is given with respect to crust thickness (h) by (a) $\lambda_D = h/8$, (b) $\lambda_D = h/4$ and (c) $\lambda_D = h$. The profiles are plotted with a cubic interpolant for clarity. U_0 corresponds to the DLVO monopole ($\ell = 0$) term, while U_V and $\tilde{U}_V$ denote the DLVO interaction energy of equivalent-volume spheres determined from the spherical harmonic particle model and the tomographic reconstruction, respectively. The labelling (i–iv) is used in subsequent panels. The profiles containing secondary minimum have been plotted separately in the insets of (a) and (b) for visual clarity, while the inset of (c) shows the energy distributions of (a–c) at the (i) position. (d) Maps of van der Waals (vdW) and DLVO interaction energy at increasing radial distance from the particle as indicated by (i)–(iv). (e, f) Locations of profiles with a secondary minimum (with depth $U_{\min}$) overlaid on the topography and smallest surface-to-surface distance (d_{env}) evaluated at the spherical envelope radius on the left and right, respectively. (g) Probability distribution of the $U_{\min}$ radial coordinate ($r_{\min}$).

ridge network. Whereas profiles near vertices are likely affected by the conical angle between the ridges that meet at the vertex region, whereby larger apex angles correspond to larger interaction energies. The tendency of the analysed particles to display morphological variations of these kind, results in ridges and their networks being more affected by changes in the plate surface potential. Another feature of corrugated, crumpled morphologies is that ridge networks allow the plate to approach closer to the particle centre-of-mass compared to

Figure 16: Values determined from Type II DLVO profiles for CP-2 particle at the indicated Debye length (λ_D) represented relative to the particle crust thickness (h) when particle (ψ_p) is held fixed and plate (ψ_s) surface potential is varied. (a) Secondary minimum depth ($U_{\min}$) and (b–d) energy barrier height ($U_{\max}$) as a function of radial distance (r) scaled by the equivalent-volume sphere radius (R_V). The lines are guides for the eye.

the more distant vertices. As $U_{\max}$ of the equivalent-volume sphere is roughly the magnitude of an average ridge network feature, most ridges and vertices act to weaken the interaction, whereas ridge networks can incur an opposite effect. A plausible outcome of the interaction energy distribution is that adsorption is favoured at vertex regions due to their smaller energy barrier, while ridge networks are likely more stable towards desorption due to their higher energy barrier. This is supported by experimental findings that too highly corrugated surfaces can increase the tendency towards particle aggregation.^{60,190}

In conclusion, the morphological character of corrugated colloidal lignin particles was analysed based on realistic models of their particle surfaces. Both stronger and weaker regions of interaction were present compared to a spherical particle with equivalent volume, depending on the local morphological character of the surface, which raises the question of the possible morphological parameters that could bring strictly stronger or weaker interactions to better control, e.g., their aggregation and deposition behaviour. The results suggest that a systematic approach along the lines herein used could provide means to achieve an improved comprehension of when corrugated particles are most suitably used. With additional preparative controls for, e.g., morphological homogeneity and symmetry, this could significantly contribute to the use of corrugated particles in advanced functional materials.

4.2 Morphological control of crystalline polyphenol-based particles

This section outlines the main findings of **Paper II**, where a simple, green solution precipitation method (Section 3.2.2) was applied for the formation of crystalline polyphenol-based particles from tannic acid under alkaline conditions. We will refer to the resulting particulate precipitates as oxidized tannic acid (OTA) particles. The influence of process conditions on particle characteristics, namely dimensions and yield, was investigated based on SEM images using PCA as described in Section 3.3.5. Further analyses were performed to investigate their thermal stability and chemical composition.

Some of the great variety of OTA particle morphologies is displayed in **Figure 17**. These contain clear angular features suggestive of crystalline structure. The morphologies include rod-like particles (**Figure 17a–d**), platelets and flower-like shapes (**Figure 17e–h**, see also the inset of **Figure 17i** with a close-up of the twinned plate-like constructs that was found among the predominantly almond-like morphology), cuboidal particles (**Figure 17j–n**) and large spheroidal oblate shapes (**Figure 17o**). Each morphology comes with varying degree of crystal twinning or aggregation possibly due to presence of impurities or low agitation levels,¹⁹¹ while some of the apparent aggregate structures might be due to drying-induce capillary forces during the SEM sample preparation. A rod-like microstructure was emblematic to many morphologies illustrative of a general morphogenetic tendency across multiple process conditions. An example is shown in the inset of **Figure 17n**, visible as a ca. 50 nm microstructure found in the tapering sides of the OTA-LiOH particles.

The PCA was based on principal components (PCs) with roughly 81 % total explained variance (**Figure 18b**). PCA results underline three main correlations between particle morphological variables, i.e. ratios of physical dimensions d_1 , d_2 , d_3 (in descending order) given by d_2/d_1 and d_3/d_2 , volume V , yield Y_{wk} and process conditions comprising initial pH, base conjugated acid pK_a and base counter cation ionic radius R_+ . These results warrant the interpretations collated in **Figure 18c** by observing the three main correlated pairs comprising: (1) R_+ and V , i.e., increasing the counter cation ionic radius diminishes the particle volume. As the pyrogallol residues found in tannic acid can effectively chelate metal ions,¹⁹² a possible explanation is that increasing R_+ suppresses secondary nucleation via metal complexation (X-ray photoelectron spectroscopy elemental analysis indicated sodium in OTA-NaOH), while remaining largely ineffective in influencing the primary nucleation as R_+ does not markedly correlated with the overall yield (R_+ and Y_{wk} in **Figure 18a** are roughly orthogonal). (2) pK_a and Y_{wk} , i.e. increasing base strength increases yield. Stronger bases facilitate tannic acid hydrolysis and therefore accounts for the improvement in particulate product (decreasing pH with time, **Figure 19a**). (3) pH, d_2/d_1 and d_3/d_2 , i.e. increasing the initial pH results in elongated particle morphologies. The initial pH could influence the crystal habit formation by increasing the concentrations of reaction products, which in conjunction with concentration-dependencies of different crystal face growth rates could inhibit the crystal

Figure 17: Examples of particle morphologies produced in different conditions: (a) KOH at initial pH 9, 2 wt% in tannic acid, 14 h duration. (b) NH_4OH pH 11, 2 wt%, 14 h. (c) LiOH pH 11, 2 wt%, 14 h. (d) KOH pH 11, 2 wt%, 14 h. (e) NaOH pH 11, 2 wt%, 14 h. (f) NaOH pH 7.8, 2 wt%, 14 h. (g) Na_3PO_4 pH 7.8, 2 wt%, 1 week. (h) NH_4OH pH 9, 2 wt%, 14 h. (i) Na_3PO_4 pH 11, 2 wt%, 14 h. (j) KOH pH 7.8, 2 wt%, 14 h. (k) LiOH pH 7.8, 2 wt%, 1 week. (l) NaOH pH 7.8, 0.4 wt%, 1 week. (m) LiOH pH 9, 2 wt%, 14 h. (n) LiOH pH 9, 2 wt%, 1 week. (o) LiOH pH 7.8, 2 wt%, 14 h.

growth on the slowest growing faces, thereby increasing the elongation of the particle shape.

The apparent crystallinity of the OTA-NaOH particles was confirmed with powder X-ray diffraction (**Figure 19c**). Matrix-assisted laser desorption/ionization (MALDI) indicated that the particle constituents include species carrying galloyl moieties as indicated by the inter-peak mass-to-charge ratios of 152 m/z ,^{193,194} which was corroborated by Fourier-transform infrared spectroscopy. Although the reaction mechanism was not investigated in any detail, it can be hypothesized that it takes a similar path to what has been proposed for a sonochemical protocol by Bhangu et al. (2018),¹¹⁶ i.e. tannic acid ester linkages are first hydrolysed creating hexahydroxydiphenic acid after oxidative C–C coupling, which is then converted to ellagic acid by lactonization. The morphologies obtained by Bhangu et al. (2018)¹¹⁶ at neutral pH resemble those produced herein with NaOH (**Figure 17e,f**), while they similarly observed a galloyl-moiety in MALDI. Ellagic acid has been reported in multiple different solvatomorphs, such as anhydrous,¹⁹⁵ dihydrate¹⁹⁶ and acid solvate¹⁹⁷ forms, which could facilitate the morphological variety that was observed by permitting different hydrogen bonding configurations.

The method proposed in **Paper II** has some favourable properties such as simplicity and improved scalability. The adoption of the proposed method could be further facilitated by the good stability of the particles under organic solvents. The OTA-NaOH particles were found to be poorly soluble in water, ethanol, dimethyl sulfoxide (DMSO), dimethylformamide, chloroform, toluene and acetone. OTA-KOH (pH 7.8) showed similarly poor solubility, except with DMSO, wherein it was fully dissolved. Additionally, improved thermal stability was observed in thermogravimetric analysis under nitrogen atmosphere, showing

Figure 18: (a) Correlation circles of first three varimax-rotated principal components (RPCs). (b) Explained and cumulative variance of principal components. Unit explained variance is shown as a dashed line (1/7 $\approx$ 14 %). (c) Schematic interpretation of the results. The arrow connects the effect of increasing its associated variable, namely pH–elongation; base conjugate acid pK_a –yield; base counter cation ionic radius, R_+ –volume.

Figure 19: (a) pH and yield with different bases as a function of reaction time. (b) Thermogravimetric analysis of tannic acid and OTA-NaOH particles (pH 7.8, 2 wt%) with heating rate of 10 °C/min under nitrogen atmosphere. (c) Powder X-ray diffraction spectra of tannic acid and oxidized tannic acid particles (OTA-NaOH, pH 7.8, 2 wt% in tannic acid, 14 h). The background signal is likely affected by residual water.

thermal conversion shift to around 450–550 °C from ca. 200–300 °C of tannic acid (**Figure 19b**). Some open questions remain as to the mechanical strength of the particles. The high aspect-ratio OTA-KOH particles were disintegrated as a result of a washing step (**Figure 17d** inset), possibly necessitating additional chemical treatments to improve their mechanical strength.

In summary, the evidence from these experiments show large differences in morphology which were correlated with process conditions. For future studies on the structural and morphological aspects of the protocol, likely the most important issue is to control evaporation during long-lasting experiments. Also, the crystalline structure of different morphologies remains unexplored. This could have great practical utility, as the crystal structure can have a significant influence on the biological and chemical activity.

4.3 Chirality of never-dried chitin nanocrystals

In **Paper III**, crab shell residues were deconstructed to yield ChNCs using the protocol described in Section 3.2.3. ET was employed to assess the chiral twist along the ChNC axial direction using a numerical procedure detailed in Section 3.3.6. As the resulting particle reconstructions could be affected by the chemical treatments used to isolate the ChNCs, electron beam damage occurring during

imaging, reconstruction artefacts and noise, general trends are herein emphasized over individual characteristics.

Generally, the non-deacetylated nanocrystals (ChNC90) were larger in size, with a considerable portion consisting of bundled nanocrystals as determined with atomic force microscopy and ET (**Figure 20**), which points to irregular etching of the chitin surface during hydrolysis. The presence of kinks was addressed by excluding the associated regions from the linear regression model. These kinds of defects were noted for both DE-ChNCs and ChNCs. Other shapes of the anisotropy profile that are not readily analysed as a constant twist, such

Figure 20: Atomic force microscopy images of (a) DE-ChNC90 and (b) ChNC90. (c) Examples of tomographic reconstructions shown in grey with the corresponding anisotropy characterization profile (arrows depict the orientation of the segments' first principal direction; red arrows denote segments that were excluded from the twist analysis) with left-handed (LH) and right-handed (RH) twists as indicated. The lower angle denotes the total twist along the analysed segments. The asterisk (*) marks the nanocrystals with a parabolic profile.

as parabolic profiles were also present (**Figure 20c**). The twist along the ChNC axial direction showed left- and right-handed chiralities, both of which were found in reconstructions generated from the same cryo-TEM image stack, but mostly they were found to have a non-chiral morphology (**Figure 21a**). No significant differences in the average magnitude of the twist was found between left/right-handed ChNCs in DE-ChNC30, DE-ChNC90 and ChNC90 samples. The average twist of $0.3^\circ/\text{nm}$ was observed for single nanocrystals of both handedness in the whole sample set with slightly larger twists being present in the shortest nanocrystals. Contrary to the molecular dynamics study of Střelcová et al. (2016),¹³⁷ the mean cross-sectional aspect ratio, when measured from the cross-sectional dimensions of each analysed segment, did not influence the twist magnitude significantly.

Though in a majority of the samples no twist was observed, the resulting average twist is similar in magnitude to what has been measured experimentally for CNCs,^{132,134} while being slightly smaller than the molecular dynamics results predict for ChNCs.¹³⁷ If twisting was present, the handedness remained inconclusive. In all cases where the regression model suggested chiral twisting, the total absolute twist angle along the ChNC was within error bounds below 90° (**Figure 21b**). As the nanocrystals have been acquired under a harsh chemical environment and the existence of other factors influencing the morphology cannot be excluded, it cannot be guaranteed that visual identification of bundling should result in a decisive categorization, only an apparent one. This invites a comparison to a simple model comprising of two non-parallel, straight rods as shown in **Figure 21b**, whereby the clustering of random relative ChNC orientations produces an apparent, ambivalent handedness in the data set. The maximum total twist along a bundle is then limited to between $\pm 90^\circ$ depending on the relative angle between the constituent rods, while the twist per unit length depends on the bundle length. Chiralities of both handedness could thereby result from the random alignment of the individual rods. Though based on the

Figure 21: Chirality determination for deacetylated (DE-ChNC) and non-deacetylated (ChNC) chitin nanocrystals (30 or 90 min treatment): (a) twist rate and (b) absolute total twist as a function axial length and their distributions.

average twist value, only over ca. 300 nm long nanocrystals would show above 90° total twist, and hence, this cannot be used to make a distinction between single and bundled morphologies.

A remaining plausible explanation is that the hydrogen bonding network is compromised in never-dried ChNCs. This is corroborated by the lack of separation of a DE-ChNC90 suspension (1.2 wt%) into anisotropic and isotropic phases after an extended period of time. In ChNC90, such a separation was present without birefringence. These results raise the possibility that the drying history influences the chiral twisting of ChNCs comparable to the twisting of CNCs.¹³² Extensive hydrogen bonding networks of never-dried ChNCs might adversely affect the chirality-inducing hydrogen bonding of amine and hydroxyl groups of the chitin chains.^{137,198} As shown by a reduction in hydrolysis time necessary to yield comparable particle sizes with a method utilizing once-dried chitin,¹⁶⁰ the smaller specific surface area of once-dried ChNCs and reduced chemical access could enhance the inter and intra chain hydrogen bonding,¹⁹⁹ thereby promoting the development of a chiral twist.

5. Concluding Remarks

Experimental aspects of importance to colloidal science and the use of bio-based materials were investigated in this thesis from a morphometric perspective. The main outcomes of the work are summarized below with thoughts on future research directions.

In **Papers I** and **IV**, an aerosol flow reactor method was used to prepare corrugated lignin particles, which showed size-dependent morphological features. Quantitative three-dimensional analysis yielded information on the level of surface creasing, surface area distribution and surface area-to-volume ratio. Frequency domain methods elucidated the dominant angular lengths associated with the corrugated topographies. These surface models were further utilized in the calculations of colloidal interaction energies, which indicate great directional dependency based on the local surface topography, resulting in weaker and stronger interactions compared to a spherical particle with equivalent volume. To provide additional insights, future studies could address the effect of surface corrugations in the extended DLVO setting. Perhaps most notably, the depletion interaction could be of interest wherein the interaction is further dependent on the depletant size. Albeit the analysis of real surface topographies afforded by ET is very appealing, more statistically robust approaches would likely adopt computationally generated, random particle surfaces to assess interactions with a range of morphological parameters. This could further illuminate the morphological parameters and conditions wherein the corrugated particles produce interactions that are strictly stronger or strictly weaker compared to spherical particles, and thereby, give practical targets for the particle preparation process to produce such colloidal systems with more tailored and precise behaviour.

In **Paper II**, a promising route to produce a vast library of crystalline, polyphenolic particle morphologies was reported. The thermochemical analyses showed an improved thermal stability, while maintaining the galloyl-rich composition of their source material. The correlations uncovered by the process condition-particle morphology relation analysis suggested that increasing the base strength and initial solution pH likely play a role in increasing precipitate yield and shape elongation, respectively, while an increase in base counter cation size generally decreases the particle size. Future studies could address the sensitivity of process conditions with respect to solvent evaporation and stirring conditions. Also, the elucidation of possible differences in crystal structures could further promote the use of such polyphenolic particles by allowing more tailorable

functionalities. Such constructs could find use, for example, as absorbents in wastewater treatment due to their insolubility in water and likely inheritance of the general affinity for organic and heavy metal contaminant uptake.²⁰⁰ The sheer complexity of phenomena involved in crystal engineering likely sees the field employing more artificial intelligence and machine learning approaches in future.

In **Paper III**, never-dried chitin nanocrystals were isolated from crab exoskeletons and their chiral twisting was investigated. No major differences were found between the non-deacetylated and partially deacetylated samples besides the apparent lack of aggregation due to deacetylation. Chiralities of both handednesses were observed, while on average the nanocrystals were non-chiral. The twist was slightly larger for shorter nanocrystals, while the cross-sectional aspect ratio did not influence the twist magnitude significantly. This could point to the possibility of non-apparent aggregation or that the drying history of the sample may affect the chiral twist formation. It is hypothesized that the loose, never-dried structure adversely affects the chiral twist formation by altering the intra and inter chain hydrogen bonding in ChNCs, thereby influencing the twist formation. The obtained results give evidence of a possibility that water interactions may influence particle systems derived from this abundant resource, and thus, are of definite practical utility to materials engineers wishing to control such properties. Further research on the chirality of never-dried and once-dried ChNCs is required to improve the understanding of chitin at the nanoscale. Other methodologies are needed to yield more definite answers.

References

1. Khalil, A. S. & Collins, J. J. Synthetic biology: Applications come of age. *Nat. Rev. Genet.* **11**, 367–379 (2010).
2. Anastas, P. T. & Kirchhoff, M. M. Origins, current status, and future challenges of green chemistry. *Acc. Chem. Res.* **35**, 686–694 (2002).
3. Rockström, J. *et al.* A safe operating space for humanity. *Nature* **461**, 472–475 (2009).
4. Bull, J. W. & Maron, M. How humans drive speciation as well as extinction. *Proc. R. Soc. B Biol. Sci.* **283**, 20160600 (2016).
5. Pimm, S. L. *et al.* The biodiversity of species and their rates of extinction, distribution, and protection. *Science* **344**, 1246752 (2014).
6. Andrady, A. L. Microplastics in the marine environment. *Mar. Pollut. Bull.* **62**, 1596–1605 (2011).
7. Koelmans, A. A. *et al.* Microplastics in freshwaters and drinking water: Critical review and assessment of data quality. *Water Res.* **155**, 410–422 (2019).
8. European Parliament and Council. Directive (EU) 2019/904 of the European Parliament and of the Council of 5 June 2019 on the reduction of the impact of certain plastic products on the environment. *Off. J. Eur. Union* **155**, 1–19 (2019).
9. FinnCERES Materials Cluster website. <https://finnceres.fi>. Accessed March 6, 2020.
10. Nudelman, F. Nacre biomineralisation: A review on the mechanisms of crystal nucleation. *Semin. Cell Dev. Biol.* **46**, 2–10 (2015).
11. Weaver, J. C. *et al.* The stomatopod dactyl club: A formidable damage-tolerant biological hammer. *Science* **336**, 1275–1280 (2012).
12. Meyers, M. A. *et al.* Nature's technical ceramic: The avian eggshell. *J. R. Soc. Interface* **14**, 20160804 (2017).
13. Sethmann, I. & Wörheide, G. Structure and composition of calcareous sponge spicules: A review and comparison to structurally related biominerals. *Micron* **39**, 209–228 (2008).
14. Fayemi, P. E., Wanieck, K., Zollfrank, C., Maranzana, N. & Aoussat, A. Biomimetics: Process, tools and practice. *Bioinspiration Biomim.* **12**, 011002 (2017).
15. Hwang, J. *et al.* Biomimetics: Forecasting the future of science, engineering, and medicine. *Int. J. Nanomedicine* **10**, 5701–5713 (2015).
16. Klemm, D. *et al.* Nanocelluloses: A new family of nature-based materials. *Angew. Chemie - Int. Ed.* **50**, 5438–5466 (2011).
17. Zhu, H. *et al.* Anomalous scaling law of strength and toughness of cellulose nanopaper. *Proc. Natl. Acad. Sci. U. S. A.* **112**, 8971–8976 (2015).
18. Nogí, M., Iwamoto, S., Nakagaito, A. N. & Yano, H. Optically transparent nanofiber paper. *Adv. Mater.* **21**, 1595–1598 (2009).
19. Fukuzumi, H., Saito, T., Iwata, T., Kumamoto, Y. & Isogai, A. Transparent and high gas barrier films of cellulose nanofibers prepared by TEMPO-mediated oxidation. *Biomacromolecules* **10**, 162–165 (2009).
20. García, A., Gandini, A., Labidi, J., Belgacem, N. & Bras, J. Industrial and crop wastes: A new source for nanocellulose biorefinery. *Ind. Crops Prod.* **93**, 26–38 (2016).
21. Shyer, A. E. *et al.* Villification: How the gut gets its villi. *Science* **342**, 212–218 (2013).
22. Lavrentovich, M. O., Horsley, E. M., Radja, A., Sweeney, A. M. & Kamien, R. D. First-order patterning transitions on a sphere as a route to cell morphology. *Proc. Natl. Acad. Sci. U. S. A.* **113**, 5189–5194 (2016).

23. Prothero, J. W. & Sundsten, J. W. Folding of the cerebral cortex in mammals. A scaling model. *Brain. Behav. Evol.* **24**, 152–167 (1984).
24. Burda, C., Chen, X., Narayanan, R. & El-Sayed, M. A. Chemistry and properties of nanocrystals of different shapes. *Chem. Rev.* **105**, 1025–1102 (2005).
25. Schlögl, R. Heterogeneous catalysis. *Angew. Chemie - Int. Ed.* **54**, 3465–3520 (2015).
26. Simon, P. & Gogotsi, Y. Materials for electrochemical capacitors. *Nat. Mater.* **7**, 845–854 (2008).
27. Pivkina, A., Ulyanova, P., Frolov, Y., Zavyalov, S. & Schoonman, J. Nanomaterials for heterogeneous combustion. *Propellants, Explos. Pyrotech.* **29**, 39–48 (2004).
28. Pettersen, E. F. *et al.* UCSF Chimera - A visualization system for exploratory research and analysis. *J. Comput. Chem.* **25**, 1605–1612 (2004).
29. Wiley, B., Sun, Y., Mayers, B. & Xia, Y. Shape-controlled synthesis of metal nanostructures: The case of silver. *Chem. - A Eur. J.* **11**, 454–463 (2005).
30. Chen, X. & Mao, S. S. Titanium dioxide nanomaterials: Synthesis, properties, modifications and applications. *Chem. Rev.* **107**, 2891–2959 (2007).
31. Roy, P., Berger, S. & Schmuki, P. TiO₂ nanotubes: Synthesis and applications. *Angew. Chemie - Int. Ed.* **50**, 2904–2939 (2011).
32. Wang, Z. L. Zinc oxide nanostructures: Growth, properties and applications. *J. Phys. Condens. Matter* **16**, (2004).
33. Tasis, D., Tagmatarchis, N., Bianco, A. & Prato, M. Chemistry of carbon nanotubes. *Chem. Rev.* **106**, 1105–1136 (2006).
34. Lim, S. Y., Shen, W. & Gao, Z. Carbon quantum dots and their applications. *Chem. Soc. Rev.* **44**, 362–381 (2015).
35. Morse, J. W., Arvidson, R. S. & Lüttge, A. Calcium carbonate formation and dissolution. *Chem. Rev.* **107**, 342–381 (2007).
36. Meldrum, F. C. Calcium carbonate in biomineralisation and biomimetic chemistry. *Int. Mater. Rev.* **48**, 187–224 (2003).
37. Shenker, O. R. Fractal geometry is not the geometry of nature. *Stud. Hist. Philos. Sci.* **25**, 967–981 (1994).
38. Zhang, Q. & Cao, G. Hierarchically structured photoelectrodes for dye-sensitized solar cells. *J. Mater. Chem.* **21**, 6769–6774 (2011).
39. Sun, Z. *et al.* Rational design of 3D dendritic TiO₂ nanostructures with favorable architectures. *J. Am. Chem. Soc.* **133**, 19314–19317 (2011).
40. Zhu, F. *et al.* Hierarchical TiO₂ microspheres: Synthesis, structural control and their applications in dye-sensitized solar cells. *RSC Adv.* **2**, 11629–11637 (2012).
41. Barthlott, W. & Neinhuis, C. Purity of the sacred lotus, or escape from contamination in biological surfaces. *Planta* **202**, 1–8 (1997).
42. Quéré, D. Non-sticking drops. *Reports Prog. Phys.* **68**, 2495–2532 (2005).
43. Simpson, J. T., Hunter, S. R. & Aytug, T. Superhydrophobic materials and coatings: A review. *Reports Prog. Phys.* **78**, 086501 (2015).
44. Wang, J., Liu, F., Chen, H. & Chen, D. Superhydrophobic behavior achieved from hydrophilic surfaces. *Appl. Phys. Lett.* **95**, 084104 (2009).
45. Diez-Silva, M., Dao, M., Han, J., Lim, C.-T. & Suresh, S. Shape and biomechanical characteristics of human red blood cells in health and disease. *MRS Bull.* **35**, 382–388 (2010).
46. Li, J., Lykotrafitis, G., Dao, M. & Suresh, S. Cytoskeletal dynamics of human erythrocyte. *Proc. Natl. Acad. Sci. U. S. A.* **104**, 4937–4942 (2007).
47. Champion, J. A., Katare, Y. K. & Mitragotri, S. Particle shape: A new design parameter for micro- and nanoscale drug delivery carriers. *J. Control. Release* **121**, 3–9 (2007).
48. Nel, A., Xia, T., Mädler, L. & Li, N. Toxic potential of materials at the nanolevel. *Science* **311**, 622–627 (2006).
49. Albanese, A., Tang, P. S. & Chan, W. C. W. The effect of nanoparticle size, shape, and surface chemistry on biological systems. *Annu. Rev. Biomed. Eng.* **14**, 1–16 (2012).
50. Lewinski, N., Colvin, V. & Dreze, R. Cytotoxicity of nanopartides. *Small* **4**, 26–49 (2008).
51. Ong, K. J. *et al.* A 90-day dietary study with fibrillated cellulose in Sprague-

- Dawley rats. *Toxicol. Reports* **7**, 174–182 (2020).
52. Seabra, A. B., Bernardes, J. S., Fávoro, W. J., Paula, A. J. & Durán, N. Cellulose nanocrystals as carriers in medicine and their toxicities: A review. *Carbohydr. Polym.* **181**, 514–527 (2018).
 53. Xi, W., Phan, H. T. & Haes, A. J. How to accurately predict solution-phase gold nanostar stability. *Anal. Bioanal. Chem.* **410**, 6113–6123 (2018).
 54. Bahng, J. H. *et al.* Anomalous dispersions of ‘hedgehog’ particles. *Nature* **517**, 596–599 (2015).
 55. Adamczyk, Z. & Weroński, P. Application of the DLVO theory for particle deposition problems. *Adv. Colloid Interface Sci.* **83**, 137–226 (1999).
 56. Crowder, T. M., Rosati, J. A., Schroeter, J. D., Hickey, A. J. & Martonen, T. B. Fundamental effects of particle morphology on lung delivery: Predictions of Stokes’ law and the particular relevance to dry powder inhaler formulation and development. *Pharm. Res.* **19**, 239–245 (2002).
 57. Costa, E., Neves, F. & Moura, C. Design of composite particles via spray drying for DPI formulations. *ONdrugDelivery* 16–23 (2014).
 58. Chew, N. Y. K. & Chan, H. K. Use of solid corrugated particles to enhance powder aerosol performance. *Pharm. Res.* **18**, 1570–1577 (2001).
 59. Chew, N. Y. K., Tang, P., Chan, H. K. & Raper, J. A. How much particle surface corrugation is sufficient to improve aerosol performance of powders? *Pharm. Res.* **22**, 148–152 (2005).
 60. Cui, Y. *et al.* Moisture-resistant co-spray-dried netilmicin with l-leucine as dry powder inhalation for the treatment of respiratory infections. *Pharmaceutics* **10**, 252 (2018).
 61. Bozell, J. J. *et al.* Lignin isolation methodology for biorefining, pretreatment and analysis. in *Lignin valorization: Emerging approaches. RSC energy and environment series* 21–61 (Royal Society of Chemistry, 2018).
 62. Nishimura, H., Kamiya, A., Nagata, T., Katahira, M. & Watanabe, T. Direct evidence for α ether linkage between lignin and carbohydrates in wood cell walls. *Sci. Rep.* **8**, 6538 (2018).
 63. Demuner, I. F., Colodette, J. L., Demuner, A. J. & Jardim, C. M. Biorefinery review: Wide-reaching products through kraft lignin. *Bioresources* **14**, 7543–7581 (2019).
 64. Azadi, P., Inderwildi, O. R., Farnood, R. & King, D. A. Liquid fuels, hydrogen and chemicals from lignin: A critical review. *Renew. Sustain. Energy Rev.* **21**, 506–523 (2013).
 65. Notley, S. M. & Norgren, M. Lignin: Functional biomaterial with potential in surface chemistry and nanoscience. in *The nanoscience and technology of renewable biomaterials* 173–205 (Blackwell Publishing Ltd, 2009).
 66. Sjöström, E. *Wood chemistry fundamentals and applications*. (Academic Press Inc., 1993).
 67. Gosselink, R. J. A., De Jong, E., Guran, B. & Abächerli, A. Co-ordination network for lignin - Standardisation, production and applications adapted to market requirements (EUROLIGNIN). *Ind. Crops Prod.* **20**, 121–129 (2004).
 68. Hu, Z., Du, X., Liu, J., Chang, H. M. & Jameel, H. Structural characterization of pine Kraft lignin: BioChoice lignin vs Indulin AT. *J. Wood Chem. Technol.* **36**, 432–446 (2016).
 69. Puziy, A. M., Poddubnaya, O. I. & Sevastyanova, O. Carbon materials from technical lignins: Recent advances. *Top. Curr. Chem.* **376**, (2018).
 70. Abbati De Assis, C. *et al.* Techno-economic assessment, scalability, and applications of aerosol lignin micro- and nanoparticles. *ACS Sustain. Chem. Eng.* **6**, 11853–11868 (2018).
 71. Ago, M. *et al.* High-throughput synthesis of lignin particles (~30 nm to ~2 μ m) via aerosol flow reactor: Size fractionation and utilization in Pickering emulsions. *ACS Appl. Mater. Interfaces* **8**, 23302–23310 (2016).
 72. Sipponen, M. H., Smyth, M., Leskinen, T., Johansson, L. S. & Österberg, M. All-lignin approach to prepare cationic colloidal lignin particles: Stabilization of durable Pickering emulsions. *Green Chem.* **19**, 5831–5840 (2017).
 73. Nypelö, T. E., Carrillo, C. A. & Rojas, O. J. Lignin supracolloids synthesized from (W/O) microemulsions: Use in the interfacial stabilization of Pickering systems

- and organic carriers for silver metal. *Soft Matter* **11**, 2046–2054 (2015).
74. Silmore, K. S., Gupta, C. & Washburn, N. R. Tunable Pickering emulsions with polymer-grafted lignin nanoparticles (PGLNs). *J. Colloid Interface Sci.* **466**, 91–100 (2016).
 75. Mattinen, M. L. *et al.* Colloidal lignin particles as adhesives for soft materials. *Nanomaterials* **8**, 1001 (2018).
 76. Leskinen, T. *et al.* Adsorption of proteins on colloidal lignin particles for advanced biomaterials. *Biomacromolecules* **18**, 2767–2776 (2017).
 77. Qian, Y., Deng, Y., Qiu, X., Li, H. & Yang, D. Formation of uniform colloidal spheres from lignin, a renewable resource recovered from pulping spent liquor. *Green Chem.* **16**, 2156–2163 (2014).
 78. Gilca, I. A., Popa, V. I. & Crestini, C. Obtaining lignin nanoparticles by sonication. *Ultrason. Sonochem.* **23**, 369–375 (2015).
 79. Mishra, P. K. & Wimmer, R. Aerosol assisted self-assembly as a route to synthesize solid and hollow spherical lignin colloids and its utilization in layer by layer deposition. *Ultrason. Sonochem.* **35**, 45–50 (2017).
 80. Lievonen, M. *et al.* A simple process for lignin nanoparticle preparation. *Green Chem.* **18**, 1416–1422 (2016).
 81. Mezhericher, M., Levy, A. & Borde, I. Theoretical drying model of single droplets containing insoluble or dissolved solids. *Dry. Technol.* **25**, 1025–1032 (2007).
 82. Vicente, J., Pinto, J., Menezes, J. & Gaspar, F. Fundamental analysis of particle formation in spray drying. *Powder Technol.* **247**, 1–7 (2013).
 83. Vehring, R., Foss, W. R. & Lechuga-Ballesteros, D. Particle formation in spray drying. *J. Aerosol Sci.* **38**, 728–746 (2007).
 84. Charlesworth, D. H. & Marshall, W. R. Evaporation from drops containing dissolved solids. *AIChE J.* **6**, 9–23 (1960).
 85. Stoop, N., Lagrange, R., Terwagne, D., Reis, P. M. & Dunkel, J. Curvature-induced symmetry breaking determines elastic surface patterns. *Nat. Mater.* **14**, 337–342 (2015).
 86. Breid, D. & Crosby, A. J. Curvature-controlled wrinkle morphologies. *Soft Matter* **9**, 3624–3630 (2013).
 87. Yin, J., Han, X., Cao, Y. & Lu, C. Surface wrinkling on polydimethylsiloxane microspheres via wet surface chemical oxidation. *Sci. Rep.* **4**, 5710 (2014).
 88. Quilliet, C. Depressions at the surface of an elastic spherical shell submitted to external pressure. *Phys. Rev. E - Stat. Nonlinear, Soft Matter Phys.* **74**, 046608 (2006).
 89. Vliegthart, G. A. & Gompper, G. Compression, crumpling and collapse of spherical shells and capsules. *New J. Phys.* **13**, 045020 (2011).
 90. Suresh, L. & Walz, J. Y. Effect of surface roughness on the interaction energy between a colloidal sphere and a flat plate. *J. Colloid Interface Sci.* **183**, 199–213 (1996).
 91. Bhattacharjee, S., Ko, C. H. & Elimelech, M. DLVO interaction between rough surfaces. *Langmuir* **14**, 3365–3375 (1998).
 92. Hoek, E. M. V., Bhattacharjee, S. & Elimelech, M. Effect of membrane surface roughness on colloid-membrane DLVO interactions. *Langmuir* **19**, 4836–4847 (2003).
 93. Shen, C. *et al.* Application of DLVO energy map to evaluate interactions between spherical colloids and rough surfaces. *Langmuir* **28**, 14681–14692 (2012).
 94. Bradford, S. A., Kim, H., Shen, C., Sasidharan, S. & Shang, J. Contributions of nanoscale roughness to anomalous colloid retention and stability behavior. *Langmuir* **33**, 10094–10105 (2017).
 95. Shen, C., Bradford, S. A., Li, T., Li, B. & Huang, Y. Can nanoscale surface charge heterogeneity really explain colloid detachment from primary minima upon reduction of solution ionic strength? *J. Nanoparticle Res.* **20**, (2018).
 96. Hong, H. *et al.* Membrane fouling in a membrane bioreactor: A novel method for membrane surface morphology construction and its application in interaction energy assessment. *J. Memb. Sci.* **516**, 135–143 (2016).
 97. Zhang, M. *et al.* Quantitative evaluation of the interfacial interactions between a randomly rough sludge floc and membrane surface in a membrane bioreactor based on fractal geometry. *Bioresour. Technol.* **234**, 198–207 (2017).

98. Wang, H. *et al.* Interactions between nanoparticles and fractal surfaces. *Water Res.* **151**, 296–309 (2019).
99. Hoek, E. M. V. & Agarwal, G. K. Extended DLVO interactions between spherical particles and rough surfaces. *J. Colloid Interface Sci.* **298**, 50–58 (2006).
100. Lin, H., Gomez, I. & Meredith, J. C. Pollenkitt wetting mechanism enables species-specific tunable pollen adhesion. *Langmuir* **29**, 3012–3023 (2013).
101. Khanbabaee, K. & van Ree, T. Tannins: Classification and definition. *Nat. Prod. Rep.* **18**, 641–649 (2001).
102. Meydani, M. & Hasan, S. T. Dietary polyphenols and obesity. *Nutrients* **2**, 737–751 (2010).
103. Chung, K. T., Wong, T. Y., Wei, C. I., Huang, Y. W. & Lin, Y. Tannins and human health: A review. *Crit. Rev. Food Sci. Nutr.* **38**, 421–464 (1998).
104. Zhou, Y. *et al.* Natural polyphenols for prevention and treatment of cancer. *Nutrients* **8**, 515 (2016).
105. Badhani, B., Sharma, N. & Kakkar, R. Gallic acid: A versatile antioxidant with promising therapeutic and industrial applications. *RSC Adv.* **5**, 27540–27557 (2015).
106. Chattopadhyay, D. P. Chemistry of dyeing. in *Handbook of Textile and Industrial Dyeing: Principles, Processes and Types of Dyes* vol. 1 150–183 (Woodhead Publishing, 2011).
107. Covington, T. Vegetable tanning. in *Tanning chemistry: The science of leather* 281–314 (The Royal Society of Chemistry, 2009).
108. Shirmohammadi, Y., Efhamisizi, D. & Pizzi, A. Tannins as a sustainable raw material for green chemistry: A review. *Ind. Crops Prod.* **126**, 316–332 (2018).
109. Pizzi, A. Natural phenolic adhesives derived from tannins and lignin. in *Handbook of adhesive technology, Third Edition* 263–282 (William Andrew, 2017).
110. Mahajan, P. G., Dige, N. C., Vanjare, B. D., Hong, S. K. & Lee, K. H. Gallotannin functionalized gold nanoparticles for rapid, selective and sensitive colorimetric detection of Ag⁺ in aqueous medium: Approach to eco-friendly water analysis. *Sensors Actuators, B Chem.* **281**, 720–729 (2019).
111. Tang, C., Amin, D., Messersmith, P. B., Anthony, J. E. & Prud'homme, R. K. Polymer directed self-assembly of pH-responsive antioxidant nanoparticles. *Langmuir* **31**, 3612–3620 (2015).
112. Hu, C. *et al.* Tannin as a gatekeeper of pH-responsive mesoporous silica nanoparticles for drug delivery. *RSC Adv.* **5**, 85436–85441 (2015).
113. Barrett, D. G., Sileika, T. S. & Messersmith, P. B. Molecular diversity in phenolic and polyphenolic precursors of tannin-inspired nanocoatings. *Chem. Commun.* **50**, 7265–7268 (2014).
114. Chen, Z., Wang, C., Chen, J. & Li, X. Biocompatible, functional spheres based on oxidative coupling assembly of green tea polyphenols. *J. Am. Chem. Soc.* **135**, 4179–4182 (2013).
115. Mullin, J. W. Crystallization and precipitation. in *Ullmann's encyclopedia of industrial chemistry* 581–630 (Wiley-VCH, 2003).
116. Bhangu, S. K., Singla, R., Colombo, E., Ashokkumar, M. & Cavalieri, F. Sono-transformation of tannic acid into biofunctional ellagic acid micro/nanocrystals with distinct morphologies. *Green Chem.* **20**, 816–821 (2018).
117. Montes, A., Wehner, L., Pereyra, C. & Martínez De La Ossa, E. J. Generation of microparticles of ellagic acid by supercritical antisolvent process. *J. Supercrit. Fluids* **116**, 101–110 (2016).
118. Wang, L. *et al.* Optimization of ellagic acid purification from Pomegranate husk by antisolvent recrystallization. *Chem. Eng. Technol.* **41**, 1188–1198 (2018).
119. Li, Y. *et al.* Preparation and characterization of micronized ellagic acid using antisolvent precipitation for oral delivery. *Int. J. Pharm.* **486**, 207–216 (2015).
120. Prum, R. O., Quinn, T. & Torres, R. H. Anatomically diverse butterfly scales all produce structural colours by coherent scattering. *J. Exp. Biol.* **209**, 748–765 (2006).
121. Vukusic, P. & Sambles, J. R. Photonic structures in biology. *Nature* **424**, 852–855 (2003).
122. Gray, D. G. Recent advances in chiral nematic structure and iridescent color of

- cellulose nanocrystal films. *Nanomaterials* **6**, 213 (2016).
123. Klockars, K. W. *et al.* Asymmetrical coffee rings from cellulose nanocrystals and prospects in art and design. *Cellulose* **26**, 491–506 (2019).
 124. Stroobants, A., Lekkerkerker, H. N. W. & Odijk, T. Effect of electrostatic interaction on the liquid crystal phase transition in solutions of rodlike polyelectrolytes. *Macromolecules* **19**, 2232–2238 (1986).
 125. Xue, M. D., Kimura, T., Revol, J. F. & Gray, D. G. Effects of ionic strength on the isotropic-chiral nematic phase transition of suspensions of cellulose crystallites. *Langmuir* **12**, 2076–2082 (1996).
 126. Honorato-Rios, C. *et al.* Equilibrium liquid crystal phase diagrams and detection of kinetic arrest in cellulose nanocrystal suspensions. *Front. Mater.* **3**, (2016).
 127. Wensink, H. H. & Jackson, G. Cholesteric order in systems of helical Yukawa rods. *J. Phys. Condens. Matter* **23**, 194107 (2011).
 128. Varga, S. & Jackson, G. Simulation of the macroscopic pitch of a chiral nematic phase of a model chiral mesogen. *Chem. Phys. Lett.* **377**, 6–12 (2003).
 129. Matthews, J. F. *et al.* Computer simulation studies of microcrystalline cellulose I β . *Carbohydr. Res.* **341**, 138–152 (2006).
 130. Zhao, Z. *et al.* Cellulose microfibril twist, mechanics, and implication for cellulose biosynthesis. *J. Phys. Chem. A* **117**, 2580–2589 (2013).
 131. Usov, I. *et al.* Understanding nanocellulose chirality and structure-properties relationship at the single fibril level. *Nat. Commun.* **6**, 7564 (2015).
 132. Ogawa, Y. Electron microdiffraction reveals the nanoscale twist geometry of cellulose nanocrystals. *Nanoscale* **11**, 21767–21774 (2019).
 133. Hanley, S. J., Revol, J. F., Godbout, L. & Gray, D. G. Atomic force microscopy and transmission electron microscopy of cellulose from *Micrasterias denticulata*; evidence for a chiral helical microfibril twist. *Cellulose* **4**, 209–220 (1997).
 134. Majoinen, J. *et al.* Supracolloidal multivalent interactions and wrapping of dendronized glycopolymers on native cellulose nanocrystals. *J. Am. Chem. Soc.* **136**, 866–869 (2014).
 135. Arcari, M. *et al.* Nanostructural properties and twist periodicity of cellulose nanofibrils with variable charge density. *Biomacromolecules* **20**, 1288–1296 (2019).
 136. Beckham, G. T. & Crowley, M. F. Examination of the α -chitin structure and decrystallization thermodynamics at the nanoscale. *J. Phys. Chem. B* **115**, 4516–4522 (2011).
 137. Štřelcová, Z. *et al.* The structure and dynamics of chitin nanofibrils in an aqueous environment revealed by molecular dynamics simulations. *RSC Adv.* **6**, 30710–30721 (2016).
 138. Mattos, B. D., Tardy, B. L. & Rojas, O. J. Accounting for substrate interactions in the measurement of the dimensions of cellulose nanofibrils. *Biomacromolecules* **20**, 2657–2665 (2019).
 139. Roberts, G. A. F. Structure of chitin and chitosan. in *Chitin chemistry* 1–53 (The MacMillan Press Ltd, 1992).
 140. Zhu, K. Y., Merzendorfer, H., Zhang, W., Zhang, J. & Muthukrishnan, S. Biosynthesis, turnover, and functions of chitin in insects. *Annu. Rev. Entomol.* **61**, 177–196 (2016).
 141. Yan, N. & Chen, X. Sustainability: Don't waste seafood waste. *Nature* **524**, 155–157 (2015).
 142. Yoon, G. L., Kim, B. T., Kim, B. O. & Han, S. H. Chemical-mechanical characteristics of crushed oyster-shell. *Waste Manag.* **23**, 825–834 (2003).
 143. Hamed, I., Özogul, F. & Regenstein, J. M. Industrial applications of crustacean by-products (chitin, chitosan, and chitooligosaccharides): A review. *Trends Food Sci. Technol.* **48**, 40–50 (2016).
 144. Rudall, K. M. The chitin/protein complexes of insect cuticles. *Adv. In Insect Phys.* **1**, 257–313 (1963).
 145. Cauchie, H. M., Jaspar-Versali, M. F., Hoffmann, L. & Thomé, J. P. Analysis of the seasonal variation in biochemical composition of *Daphnia magna* Straus (Crustacea: Branchiopoda: Anomopoda) from an aerated wastewater stabilisation pond. *Ann. Limnol.* **35**, 223–231 (1999).

146. Raabe, D., Sachs, C. & Romano, P. The crustacean exoskeleton as an example of a structurally and mechanically graded biological nanocomposite material. *Acta Mater.* **53**, 4281–4292 (2005).
147. FAO. The state of world fisheries and aquaculture 2018 - Meeting the sustainable development goals. Rome. (2018).
148. Shamshina, J. L., Berton, P. & Rogers, R. D. Advances in functional chitin materials: A review. *ACS Sustain. Chem. Eng.* **7**, 6444–6457 (2019).
149. Younes, I. & Rinaudo, M. Chitin and chitosan preparation from marine sources. Structure, properties and applications. *Mar. Drugs* **13**, 1133–1174 (2015).
150. Ji, Y. L., Wolfe, P. S., Rodriguez, I. A. & Bowlin, G. L. Preparation of chitin nanofibril/polycaprolactone nanocomposite from a nonaqueous medium suspension. *Carbohydr. Polym.* **87**, 2313–2319 (2012).
151. Paillet, M. & Dufresne, A. Chitin whisker reinforced thermoplastic nanocomposites. *Macromolecules* **34**, 6527–6530 (2001).
152. Lu, Y., Weng, L. & Zhang, L. Morphology and properties of soy protein isolate thermoplastics reinforced with chitin whiskers. *Biomacromolecules* **5**, 1046–1051 (2004).
153. Wu, J., Zhang, K., Girouard, N. & Meredith, J. C. Facile route to produce chitin nanofibers as precursors for flexible and transparent gas barrier materials. *Biomacromolecules* **15**, 4614–4620 (2014).
154. Salaberria, A. M., Fernandes, S. C. M., Diaz, R. H. & Labidi, J. Processing of α -chitin nanofibers by dynamic high pressure homogenization: Characterization and antifungal activity against *A. niger*. *Carbohydr. Polym.* **116**, 286–291 (2015).
155. Fan, Y., Saito, T. & Isogai, A. Individual chitin nano-whiskers prepared from partially deacetylated α -chitin by fibril surface cationization. *Carbohydr. Polym.* **79**, 1046–1051 (2010).
156. Liu, L. *et al.* Salt-induced colloidal destabilization, separation, drying, and redispersion in aqueous phase of cationic and anionic nanochitins. *J. Agric. Food Chem.* **66**, 9189–9198 (2018).
157. Mushi, N. E., Nishino, T., Berglund, L. A. & Zhou, Q. Strong and tough chitin film from α -chitin nanofibers prepared by high pressure homogenization and chitosan addition. *ACS Sustain. Chem. Eng.* **7**, 1692–1697 (2019).
158. Bai, L. *et al.* Self-assembled networks of short and long chitin nanoparticles for oil/water interfacial superstabilization. *ACS Sustain. Chem. Eng.* **7**, 6497–6511 (2019).
159. Gardner, K. H. & Blackwell, J. The structure of native cellulose. *Biopolymers* **13**, 1975–2001 (1974).
160. Narkevicius, A. *et al.* Controlling the self-assembly behavior of aqueous chitin nanocrystal suspensions. *Biomacromolecules* **20**, 2830–2838 (2019).
161. Abràmoff, M. D., Magalhães, P. J. & Ram, S. J. Image processing with imageJ. *Biophotonics Int.* **11**, 36–41 (2004).
162. Midgley, P. A. & Dunin-Borkowski, R. E. Electron tomography and holography in materials science. *Nature Materials* vol. 8 271–280 (2009).
163. Kremer, J. R., Mastronarde, D. N. & McIntosh, J. R. Computer visualization of three-dimensional image data using IMOD. *J. Struct. Biol.* **116**, 71–76 (1996).
164. Kaula, W. M. Theory of statistical analysis of data distributed over a sphere. *Rev. Geophys.* **5**, 83–107 (1967).
165. Taylor, M. A., Garboczi, E. J., Erdogan, S. T. & Fowler, D. W. Some properties of irregular 3-D particles. *Powder Technol.* **162**, 1–15 (2006).
166. Cnudde, V. & Boone, M. N. High-resolution X-ray computed tomography in geosciences: A review of the current technology and applications. *Earth-Science Rev.* **123**, 1–17 (2013).
167. Garboczi, E. J. & Bullard, J. W. 3D analytical mathematical models of random star-shape particles via a combination of X-ray computed microtomography and spherical harmonic analysis. *Adv. Powder Technol.* **28**, 325–339 (2017).
168. Smith, D. E. *et al.* Mars orbiter laser altimeter: Experiment summary after the first year of global mapping of Mars. *J. Geophys. Res. E Planets* **106**, 23689–23722 (2001).
169. Rappaport, N. J., Konopliv, A. S., Kucinskis, A. B. & Ford, P. G. An improved

- 360 degree and order model of Venus topography. *Icarus* **139**, 19–31 (1999).
170. Araki, H. *et al.* Lunar global shape and polar topography derived from Kaguya-LALT laser altimetry. *Science* **323**, 897–900 (2009).
 171. Gorski, K. M. *et al.* HEALPix: A Framework for high-resolution discretization and fast analysis of data distributed on the sphere. *Astrophys. J.* **622**, 759–771 (2005).
 172. Wieczorek, M. A. Gravity and topography of the terrestrial planets. in *Treatise on geophysics: Second Edition* vol. 10 153–193 (Elsevier, 2015).
 173. Gorski, K. M., Wandelt, B. D., Hansen, F. K., Hivon, E. & Banday, A. J. The HEALPix Primer. (1999).
 174. Butt, H.-J., Graf, K. & Kappl, M. The electric double layer. in *Physics and chemistry of interfaces* 42–56 (Wiley-VCH, 2004).
 175. Hogg, R., Healy, T. W. & Fuerstenau, D. W. Mutual coagulation of colloidal dispersions. *Trans. Faraday Soc.* **62**, 1638–1651 (1966).
 176. Hamaker, H. C. The London-van der Waals attraction between spherical particles. *Physica* **4**, 1058–1072 (1937).
 177. Gregory, J. Approximate expressions for retarded van der Waals interaction. *J. Colloid Interface Sci.* **83**, 138–145 (1981).
 178. Bhattacharjee, S. & Elimelech, M. Surface element integration: A novel technique for evaluation of DLVO interaction between a particle and a flat plate. *J. Colloid Interface Sci.* **193**, 273–285 (1997).
 179. Shen, C. *et al.* Influence of surface chemical heterogeneity on attachment and detachment of microparticles. *Colloids Surfaces A Physicochem. Eng. Asp.* **433**, 14–29 (2013).
 180. Huang, X., Bhattacharjee, S. & Hoek, E. M. V. Is surface roughness a ‘scapegoat’ or a primary factor when defining particle-substrate interactions? *Langmuir* **26**, 2528–2537 (2010).
 181. Hollertz, R. *et al.* Dielectric properties of lignin and glucomannan as determined by spectroscopic ellipsometry and Lifshitz estimates of non-retarded Hamaker constants. *Cellulose* **20**, 1639–1648 (2013).
 182. Berntsen, J. & Espelid, T. O. Algorithm 706: DCUTRI: An algorithm for adaptive cubature over a collection of triangles. *ACM Trans. Math. Softw.* **18**, 329–342 (1992).
 183. Kaiser, H. F. The varimax criterion for analytic rotation in factor analysis. *Psychometrika* **23**, 187–200 (1958).
 184. Jolliffe, I. T. *Principal component analysis. Second Edition. Springer Series in Statistics* (Springer, 2002).
 185. Pauchard, L. & Couder, Y. Invagination during the collapse of an inhomogeneous spheroidal shell. *Europhys. Lett.* **66**, 667–673 (2004).
 186. Park, J. Y. *et al.* Facile fabrication of superhydrophobic coatings with polyimide particles using a reactive electrospraying process. *J. Mater. Chem.* **22**, 16005–16010 (2012).
 187. Zoldesi, C. I., Van Walree, C. A. & Imhof, A. Deformable hollow hybrid silica/siloxane colloids by emulsion templating. *Langmuir* **22**, 4343–4352 (2006).
 188. Nagao, D., Ohta, T., Ishii, H., Imhof, A. & Konno, M. Novel mini-reactor of silicone oil droplets for synthesis of morphology-controlled polymer particles. *Langmuir* **28**, 17642–17646 (2012).
 189. Cao, J. *et al.* Controlling sol-gel polymerization to create bowl-shaped polysilsesquioxane particles with a kippah structure. *Polymer (Guildf)* **54**, 2493–2497 (2013).
 190. Adi, S. *et al.* Micro-particle corrugation, adhesion and inhalation aerosol efficiency. *Eur. J. Pharm. Sci.* **35**, 12–18 (2008).
 191. Jones, A. G. Crystal agglomeration and disruption. in *Crystallization Process Systems* 155–189 (Butterworth-Heinemann, 2002).
 192. Scalbert, A. *et al.* Polyphenols, metal ion complexation and biological consequences. in *Plant Polyphenols 2. Basic Life Sciences Series* vol. 66 545–554 (Springer, 1999).
 193. Li, B., Bhandari, D. R., Römpf, A. & Spengler, B. High-resolution MALDI mass spectrometry imaging of gallotannins and monoterpene glucosides in the root of

- Paeonia lactiflora*. *Sci. Rep.* **6**, 36074 (2016).
194. Xiang, P. *et al.* Effect of cationization reagents on the matrix-assisted laser desorption/ionization time-of-flight mass spectrum of chinese gallotannins. *J. Appl. Polym. Sci.* **105**, 859–864 (2007).
195. McL Mathieson, A. & Poppleton, B. J. The crystal structure of ellagic acid. *Acta Crystallogr. Sect. B Struct. Crystallogr. Cryst. Chem.* **24**, 1456–1461 (1968).
196. Rossi, M., Erlebacher, J., Zacharias, D. E., Carrell, H. L. & Iannucci, B. The crystal and molecular structure of ellagic acid dihydrate: A dietary anti-cancer agent. *Carcinogenesis* **12**, 2227–2232 (1991).
197. Źesławska, E. & Skórska-Stania, A. The role of solvent in hydrogen bonding pattern of ellagic acid crystals. *J. Chem. Crystallogr.* **43**, 285–291 (2013).
198. Adamcik, J. & Mezzenga, R. Adjustable twisting periodic pitch of amyloid fibrils. *Soft Matter* **7**, 5437–5443 (2011).
199. Agarwal, U. P., Ralph, S. A., Reiner, R. S. & Baez, C. Probing crystallinity of never-dried wood cellulose with Raman spectroscopy. *Cellulose* **23**, 125–144 (2016).
200. Bacelo, H. A. M., Santos, S. C. R. & Botelho, C. M. S. Tannin-based biosorbents for environmental applications - A review. *Chem. Eng. J.* **303**, 575–587 (2016).

ISBN 978-952-60-3927-5 (printed)

ISBN 978-952-60-3928-2 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University
School of Chemical Engineering
Department of Bioproducts and Biosystems
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**