On thermal and mechanical behavior of cast irons at elevated temperatures

Kalle Jalava

On thermal and mechanical behavior of cast irons at elevated temperatures

Kalle Jalava

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Engineering, Remote connection via Zoom, on 6 November 2020 at 12pm.

**Aalto University
School of Engineering
Department of Mechanical Engineering
Advanced Manufacturing and Materials**

Supervising professor

Professor Juhani Orkas, Aalto University, Department of Mechanical Engineering

Preliminary examiners

Associate Professor Marcin Górny, AGH University of Science and Technology, Poland

Professor Pasi Peura, Tampere University, Finland

Opponent

Professor Attila Diószegi, Jönköping University, Sweden

Aalto University publication series

DOCTORAL DISSERTATIONS 148/2020

© 2020 Kalle Jalava

ISBN 978-952-64-0060-0 (printed)

ISBN 978-952-64-0061-7 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-64-0061-7>

Unigrafia Oy

Helsinki 2020

Finland

Printed matter
4041-0619

Author
Kalle Jalava

Name of the doctoral dissertation
On thermal and mechanical behavior of cast irons at elevated temperatures

Publisher School of Engineering

Unit Department of Mechanical Engineering

Series Aalto University publication series DOCTORAL DISSERTATIONS 148/2020

Field of research Mechanical Engineering

Manuscript submitted 6 April 2020

Date of the defence 6 November 2020

Permission for public defence granted (date) 18 August 2020

Language English

☐ **Monograph**

☒ **Article dissertation**

☐ **Essay dissertation**

Abstract

Casting is a production process that lends itself superbly to creation of complex shapes in many scales. To get every sliver of performance from a casting, one needs to combine the knowledge of shaping methods to a deep understanding of properties and behaviour. Cast irons in particular are widely used in thermally loaded applications, where both mechanical and physical properties are required. Spheroidal graphite cast irons hold potential in becoming a replacement for lamellar graphite alloys with certain combination of microstructure and alloying.

In this work, thermal and mechanical properties of select cast iron types are explored at elevated temperatures, from room temperature (RT) to around 400 °C. A Transient Plane Source-measurement system is used to characterize thermal conductivities of lamellar, compacted and spheroidal graphite irons. Secondly, the effects of silicon alloying in the range of 1.5 to 4.3 w-% and different ferrite-pearlite fractions to spheroidal graphite thermal conductivity at elevated temperatures are tested and models for estimation purposes are made. Mechanical property side of this work concentrates on evaluating the occurrence of Dynamic Strain Aging (DSA) in ferritic to pearlitic microstructures of spheroidal graphite cast iron. DSA testing consisted of tensile and cyclic load cases with various strain rates and amplitudes from RT to 450 °C.

The results in this thesis indicate that the used TPS measurement system is capable of characterizing cast irons at elevated temperatures, when care is taken in analysis and certain operator related challenges are considered. Additionally, spheroidal graphite cast iron thermal conductivities can be optimized or estimated with the chosen test parameters as the contribution of graphite in spheroids is relatively minimal. The mechanical property experiments show that DSA related phenomena are evident in all tested ferritic and pearlitic microstructures with certain combination of strain rates and temperatures. As DSA effects include negative strain rate sensitivity, ductility minimums and positive temperature dependence for flow stress and work hardening, it should be considered in analysis of components that are used in the range of 200-400 °C.

This work fills gaps in knowledge regarding cast irons at elevated temperatures. However, taking the outlined approaches further remains a topic for future research. Additional testing is required to cover the full production window of spheroidal graphite cast irons to be fully usable in production simulation, optimization tools and local property approaches

Keywords Cast iron, thermal conductivity, dynamic strain aging, elevated temperatures

ISBN (printed) 978-952-64-0060-0

ISBN (pdf) 978-952-64-0061-7

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Helsinki

Location of printing Helsinki **Year** 2020

Pages 101

urn <http://urn.fi/URN:ISBN:978-952-64-0061-7>

Tekijä

Kalle Jalava

Väitöskirjan nimi

Valurautojen termisestä ja mekaanisesta käyttäytymisestä korotetuissa lämpötiloissa

Julkaisija Insinööritieteiden korkeakoulu**Yksikkö** Konetekniikan laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 148/2020**Tutkimusala** Konetekniikka**Käsikirjoituksen pvm** 06.04.2020**Väitöspäivä** 06.11.2020**Väittelyluvan myöntämispäivä** 18.08.2020**Kieli** Englanti☐ **Monografia**☒ **Artikkeliväitöskirja**☐ **Esseeväitöskirja****Tiivistelmä**

Valaminen on valmistusmenetelmä, joka mahdollistaa monimutkaisten komponenttien tuotannon monessa kokoluokassa. Valutuotteiden tehokas käyttö vaatii kattavaa tietoutta niin tuotantotekniikoista kuin seosten materiaaliominaisuuksista. Valuraudat ovat keskeisiä konstruktiomateriaaleja käyttökohteissa, joissa yhdistyy tarpeet hyvistä termisistä ja mekaanisista ominaisuuksista. Pallografiittiraudat ovat valurautojen alatyyppejä, jonka tiettyjen mikrorakenteen ja seostuksen yhdistelmällä on potentiaalia korvata suomugrafiittirautoja termisesti kuormitetuissa käyttökohteissa.

Tässä työssä tutkittiin tiettyjen valurautatyyppien termistä ja mekaanista käyttäytymistä korotetuissa lämpötiloissa huoneenlämmöstä noin 400 °C asti. Transient Plane Source-tekniikkaan perustuvaa mittaustekniikkaa käytettiin karakterisoimaan suomu-, tylppä- ja pallografiittirautojen lämmönjohtavuutta. Pallografiittirautojen lämmönjohtavuutta tutkittiin tarkemmin piiseostuksen välillä 1.5 - 4.3 p-% ja eri ferriitti-perliittisuhteilla. Testien tuloksia käytettiin regressiomallien luomisessa, joka mahdollistaa termisten ominaisuuksien arvioimisen. Mekaanisen testauksen puoli tässä työssä keskittyy dynaamisen myötövanhenemisen vaikutusten esiintymiseen ferriittisperliittisillä pallografiittiraudoilla. Myötövanhenemiseen liittyvät testit koostuivat vetokokeista ja venymäohjatuista syklistä testeistä useilla venymänopeuksilla ja -amplitudeilla huoneenlämpötilasta 450 °C:seen asti.

Työn tulosten perusteella voidaan sanoa, että käytetty lämmönjohtavuuden mittaustekniikka soveltuu valurautojen karakterisoimiseen, kunhan tietyt käyttäjään ja mittaustulosten analyysin haasteet otetaan kunnolla huomioon. Pallografiittirautojen lämmönjohtavuuksia voidaan optimoida tai arvioida testiparametrien ja luodun regressiomallin avulla. Tämä on mahdollista, koska grafiittipallojen vaikutus lämmönjohtavuuteen on suhteellisen pieni. Myötövanhenemiseen liittyvät testit osoittavat, että siihen liittyviä ilmiöitä esiintyy kaikilla testatuilla ferriittisperliittisillä mikrorakenteilla tiettyjen venymänopeuksien ja lämpötilojen yhdistelmillä. Koska myötövanhenemiseen liittyy mm. negatiivinen muodonmuutosnopeusherkkyys, venymäarvojen heikentyminen ja positiivinen lämpötilakorrelaatio myötymisjännitykseen, on se otettava huomioon termomekaanisen jännityksen alaisten komponenttien suunnittelussa.

Tämä työ lisää tietoa valurautojen käyttäytymisestä korotetuissa lämpötiloissa, jättäen sen hyötykäytön tulevaisuuden tutkimuskohteeksi. Lisää materiaalitestausta ja dataa tarvitaan kattamaan ferriittisperliittisten pallografiittirautojen tuotantoikkuna, jonka kautta mahdollistuu

Avainsanat Valurauta, lämmönjohtavuus, dynaaminen myötövanheneminen, korotetut lämpötilat

ISBN (painettu) 978-952-64-0060-0**ISBN (pdf)** 978-952-64-0061-7**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Helsinki**Painopaikka** Helsinki**Vuosi** 2020**Sivumäärä** 101**urn** <http://urn.fi/URN:ISBN:978-952-64-0061-7>

Acknowledgements

The work presented in this doctoral dissertation was conducted at the Department of Mechanical Engineering at the Aalto University School of Engineering. I am grateful for all the support I have received during these long years from colleagues, co-authors, friends and family. I would like to specifically thank professor Juhani Orkas, for all the supervision, as well as for the opportunity to work in this project along with many other casting related topics unrelated to my dissertation. I would also like to thank my co-authors at Wärtsilä for all the engaging research collaboration done during the years. Financial support has been provided by Business Finland and Aalto University School of Engineering.

Espoo, 14.9.2020
Kalle Artturi Jalava

Contents

Acknowledgements.....	1
List of Abbreviations and Symbols.....	5
List of Publications	6
Author's Contribution.....	7
1. Introduction.....	9
1.1 Background and research gap.....	9
1.2 Objectives and scope of research	10
1.3 Outline of thesis	12
1.4 Main contributions of this thesis	12
2. Theoretical background.....	13
2.1 Failure prevention of cast irons at elevated temperatures	13
2.2 Theory of thermal conduction and measurement methods	14
2.3 Thermal conduction in cast irons	16
2.4 Spheroidal graphite irons in thermally loaded applications ...	19
2.5 Dynamic strain aging	20
2.6 Dynamic strain aging in cast irons	22
2.7 Summary of literature.....	24
3. Experimental work and methods	25
3.1 Thermal conductivity testing with TPS-approach	25
3.2 Static and cyclic mechanical property testing	28
4. Results	29
4.1 Lamellar -, compacted and spheroidal graphite cast irons at elevated temperatures (Article I)	29
4.2 Effect of ferrite, pearlite and silicon alloying on elevated temperature thermal conductivity of spheroidal graphite cast irons (Article II)...	33
4.3 Effects of ferrite and pearlite on dynamic strain aging behavior of spheroidal graphite irons at elevated temperatures (Article III)	37
5. Discussion.....	46
5.1 Theoretical implications	46

5.1.1	Thermal properties of spheroidal graphite cast irons	46
5.1.2	Mechanical properties	48
5.2	Practical implications	50
5.3	Reliability and validity.....	51
6.	Conclusions	58
6.1	Research questions.....	58
6.2	Recommendations for further research	60
	References	61
	Publications	66

List of Abbreviations and Symbols

ADI	Austempered Ductile Iron
CE%	Carbon equivalent, percentage
CGI	Compacted Graphite Iron, also GJV
DSA	Dynamic Strain Aging
HCF	High Cycle Fatigue
L	Lorenz number
LCF	Low Cycle Fatigue
LFA	Laser Flash Analysis
LGI	Lamellar Graphite Iron, also GJL
P	Probability value
PLC	Portevin-Le Chatelier effect
R_{eH}	Upper yield point
R_{eL}	Lower yield point
R_m	Ultimate tensile strength
$R_{p0,2}$	0,2 % offset yield point
RT	Room temperature
R^2	Coefficient of determination
SGI	Spheroidal Graphite Iron, also GJS
SSF	Solution Strengthened Ferritic
TMF	ThermoMechanical Fatigue
TPS	Transient Plane Source
λ	Thermal conductivity
C_p	Specific heat
τ	Characteristic time
ε	Strain, strain rate, strain amplitude ($\Delta\varepsilon$)
σ	Electrical resistivity

List of Publications

This doctoral dissertation consists of a summary and of the following publications, which are referred to in the text by their numerals

- I. Jalava, Kalle;** Soivio, Kaisu; Laine, Jarkko; Orkas, Juhani. 2018. Elevated temperature thermal conductivities of some as-cast and austempered cast irons. *Materials Science and Technology*, volume 34, issue 3, pages 327-333. 1743-2847. DOI: 10.1080/02670836.2017.1389117
- II. Jalava, Kalle;** Soivio, Kaisu; Laine, Jarkko; Orkas, Juhani. 2018. Effect of Silicon and Microstructure on Spheroidal Graphite Cast Iron Thermal Conductivity at Elevated Temperatures. *International Journal of Metalcasting*, volume 12, issue 3, pages 480-486. 2163-3193. DOI: 10.1007/s40962-017-0184-1
- III. Jalava, Kalle;** Laine, Jarkko; Vaara, Joona; Frondelius, Tero; Orkas, Juhani. 2019. Investigation on dynamic strain aging behavior of ferritic-pearlitic ductile irons. *Materials Science and Technology*, volume 36, issue 2, pages 160-167, DOI: 10.1080/02670836.2019.1685760

Author's Contribution

Publication 1: Elevated temperature thermal conductivities of some as-cast and austempered cast irons.

In this study, first author contribution consists of thermal conductivity testing, design of experiments and data analysis. Co-authors took part in design of experiments, heat treatments and alloy production. The results were interpreted and commented together by the co-authors.

Publication 2: Effect of Silicon and Microstructure on Spheroidal Graphite Cast Iron Thermal Conductivity at Elevated Temperatures.

In this study, first author contribution consists of thermal conductivity testing, design of experiments, heat treatments and regression modelling. Co-authors took part in design of experiments, heat treatments and alloy production. The results were interpreted together by the co-authors.

Publication 3: Investigations on dynamic strain aging behavior of ferritic-pearlitic ductile irons.

In this study, first author contribution consists of data analysis and interpretation. Co-authors took part in design of experiments, heat treatments, alloy production and experimental setup. The results were interpreted and commented together by the co-authors.

1. Introduction

1.1 Background and research gap

Casting is a production process that lends itself superbly to creation of complex shapes in many scales. To get every sliver of performance from a casting, an engineer needs to combine the knowledge of shaping methods to deep understanding of cast alloy properties and behaviour. With regards to increasing the performance of cast alloys at specific applications, broadly applicable material standards are often not enough. Thus, end-users and suppliers need to co-operate on tailoring properties. However, this is not possible without proper tools and knowledge. Alloys can be tuned to specific applications and production methods, necessitating additional research and development.

Elevated temperatures, thermal cycles and variable mechanical loads, among others, create challenges in cast component design. Trends in part design have also increasingly shifted from using assumptions of a mostly homogenous material behavior to a localized property approach. Profound understanding and data of materials is a key aspect for any computational approach to be usable and accurate. Higher demands from cast component users increase the need for better mechanical and thermal property combinations. Fine-tuning compositions and microstructures could prove successful in attaining those goals. In thermomechanically stressed applications, difference between good and bad combinations will have a large impact on component lifetime and actual operating conditions.

As materials, cast irons are composite structures, including graphite in various forms. Cast irons are well known for their good manufacturability and castability, especially when compared to cast steel. They are widely used in applications that combine the need for good thermal transport and mechanical properties. Positive effects arise from the graphite in their microstructures, ranging from vibrational damping, and easy machinability to thermal transport. Microstructural differences due to multitude of production steps and component geometries necessitate gaining more knowledge of corresponding properties. Regarding design of complex thermally stressed components, like those in internal combustion engines, all too little of certain key parameters is currently known in detail. E.g. how different material parameters affect elevated temperature behavior of cast irons.

Although cast irons are known for good thermal transport properties and research on these materials have been widely undertaken since their invention,

the bigger picture seems somewhat fractured in the light of modern needs. Design data of mechanical properties are available in abundance compared to detailed thermal properties, which naturally complicates the design of thermally stressed components and forces one to make assumptions about unknown parameters. Data is available from literature, but often notations of important parameters, such as microstructural composition and alloying levels, are left ambiguous. Similar case is with mechanical properties at elevated temperatures. General data on standard alloys exist to a certain extent, while minute data on alloying and microstructural variations is not always readily available. To be able to optimize materials for future applications, one quite certainly needs to consider an approach where properties are decided at the start and material specifications are tweaked until they fulfil those requirements. The current available scientific literature does not completely support such an approach.

1.2 Objectives and scope of research

The main motivation for this thesis was to investigate elevated temperature behavior of cast irons, with most attention given to spheroidal graphite cast irons. The main research themes of the dissertation are as follows:

*How do parameters such as **alloying**, **microstructure** and **temperature** change cast iron thermal conductivity and mechanical behavior at elevated temperatures? Are the results promising enough to continue onto component level optimization with tested parameter space? Does thermal or mechanical behavior somehow deteriorate at elevated temperatures?*

More specifically, given that:

- **Silicon (Si)** is one of the main alloying elements in spheroidal graphite irons, being between ~1,5-4,5 w-% in the current industrial production window. Alloying elements, especially in solid solution, are known to affect both thermal and mechanical properties strongly. Does control of Si in this range allow for equivalent or better thermal conductivities compared to lamellar graphite alloys?
- **Graphite morphology** is known to affect thermal conductivity in various forms.
- **Ferrite and pearlite** are typical microstructures in cast irons and their mixture can be affected through casting process control and heat treatments, changing both mechanical and thermal properties. Use of otherwise unalloyed pearlitic cast irons is often limited to around **400 °C**.
- In standard practise, higher silicon and pearlite contents are used in foundry processes to ease attainment of mechanical property requirements set by material standards. This approach is counteractive for thermal properties.

- Aging effects are known to happen to iron-based alloys under elevated temperature straining. Such are also observed for cast irons, where most research interest has been on fully ferritic microstructures. Does the same happen with ferritic-pearlitic and pearlitic structures?

Thus, if material selection viewpoint is taken from the design need perspective rather than levels given by standards, one can postulate that modifying alloying and ferrite/pearlite structures might allow for increased performance of spheroidal graphite cast irons at elevated temperatures. This type of a viewpoint has recently been discussed regarding mechanical properties of spheroidal graphite cast irons[1]. Similar classification could be done when design needs are more thermal than mechanical.

Figure 1 Approach of optimizing thermomechanically loaded cast components

The importance of these aspects is outlined through Figure 1. Spheroidal graphite cast irons are materials with future potential in thermomechanically loaded applications. Performance of materials in such applications are not dictated by a single parameter, rather being a complex combination of many. Only through local property approach can one know what combinations truly work. However, such approaches are not possible without comprehensive base data. This thesis aims to fill parts of the materials science gap in Figure 1. More studies on mechanical properties, implementation of simulations and optimization loops fall outside this thesis. However, they are outlined for further research continuing the approach postulated in this work, as this dissertation was designed to be the first of two forming a greater whole.

1.3 Outline of thesis

The dissertation consists of three original research papers and this compiling part. Publication 1 considers three main groups of cast irons, lamellar, compacted and spheroidal, and thermal conductivity testing benchmarking. Publication 2 considers silicon alloying, ferrite-pearlite microstructures and temperature effects on spheroidal graphite cast iron thermal conductivity. Publication 3 considers elevated temperature mechanical properties of ferritic-pearlitic spheroidal graphite irons in cyclic loading, mainly the occurrence of dynamic strain aging (DSA).

1.4 Main contributions of this thesis

Transient plane source measurement of three different types of cast irons

In this dissertation, the fitness of the transient plane source thermal conductivity measurement system is benchmarked. Practically no relevant data on cast iron thermal conductivities at elevated temperatures measured with Transient Plane Source-method exists. Thus, if the different cast iron types would behave differently to established literature done with other measurement systems at elevated temperatures, the used TPS-system fitness would be questionable when measuring cast irons. Comparisons to established literature and current results are made in this work.

Unalloyed spheroidal graphite cast iron thermal conductivity data and modelling for engineering use

Data for cast iron thermal conductivity is available from literature but often notations of important parameters such as microstructural composition is left somewhat ambiguous. Literature is consistent to an extent, but uncertainties still exist. A great many previous work studies relationships between graphite morphology and thermal conductivity, but microstructural variations, such as ferrite pearlite contents, are not tested in multitude. This work takes more of a microstructure-based view on the topic and provides estimation models for engineering purposes.

Ferrite – pearlite microstructural effects on occurrence of dynamic strain aging

Strain aging of ferritic-pearlitic microstructures of cast irons have not previously been studied extensively enough to understand how strain aging may influence ductility in thermomechanical conditions. Relatively little data on the influence of microstructure on DSA behaviour of spheroidal graphite cast iron exists. Many a work on the topic focuses on fully ferritic microstructures, offering little on how similar conditions on mixed pearlitic and ferritic structures behave at similar conditions. This work provides data to fill the research gap.

2. Theoretical background

2.1 Failure prevention of cast irons at elevated temperatures

Components that are used at elevated temperatures often undergo various heating and cooling cycles. For example, with combustion engines such cycles come about from startups, running and cooling phases. The thermal loads inflict expansion and contraction at different stages and magnitudes. This results in combined thermo-mechanical loads, effectively bringing the whole assembly into thermomechanical fatigue (TMF) regime. Variable temperature fields not only determine critical locations but also are decisive in limiting number of cycles to failure, both in high and low cycle fatigue regimes. Fast ramp-ups and downs result in high thermal gradients and stresses, generally making the low cycle fatigue the limiting factor in final component life [2]. In many cases material optimization is one of the only ways to radically change the scenario, as component geometries are largely decided based on other factors.

TMF of cast irons is not a particularly new field of research, having been part of great many publications in the past decades. Most of previous research concentrates on lamellar graphite cast irons [3-7] as they have been the prime materials in applications such as cylinder heads for a long time. Some common views on the topics are evident. If one is to design against thermal loads, *high thermal conductivity, low thermal expansion, low modulus of elasticity, good strength properties and low creep tendencies* are key parameters in the analysis. Analyzing base properties without context means rather little in the end. Specifics of applications have large impacts on the result. For example, Szmytka et al. [8] have developed a TMF analysis approach where specific use cases are considered. Traditional TMF tests do not necessarily consider thermal conductivities and expansions when thermal flux into the component stays the same. E.g. thermal energy inputs into cylinder heads and exhaust manifolds are not material based, rather than being constants arising from engine running parameters. In other words, the thermal energy that needs to be transferred to cooling systems stays the same. However, stresses in components are dependent on material properties. Thermal gradients are not as severe with materials with better thermal transports properties. Thus, isothermal tests with materials differing in physical properties do not correspond to same applicational states. TMF is a complex phenomenon, where actual strains are dependent on local material properties. In the heat-flux controlled approach [8], adjusted TMF tests are made based on the thermal flux. In their example, the differences resulted in

final temperature deviation of 50 °C and 60 % higher strain amplitude. The higher strength material was ultimately worse in their analysis. In short, temperature loading is a significant influence on TMF life. Temperature fields not only determine critical areas in components but also are key in cycles to failure. For the same applied thermal loads, the number of cycles to failure increases with increasing strength. Temperatures for the same applied thermal load differ due to varying thermal conductivities. Thus, there are no all-encompassing guidelines, but each design should be investigated in its own to end up with accurate results.

In summary, striving for thermal field modification rather than strengthening materials may prove to be an effective approach in increasing performance and component life at elevated temperatures. The approach is investigated in the following sections.

2.2 Theory of thermal conduction and measurement methods

Metals are solid materials that commonly conduct heat and electricity well. Theories of conduction phenomena are complex and not too easy to apply in engineering level analyses. Fundamentals of thermal and electrical conduction are well known, however. Main heat carriers are electrons and phonons, also known as crystal/lattice vibrations. Metals have so-called free electrons in their crystal structures, which in most cases contributes most in conduction phenomena. Thermal conduction in solids through crystal vibrations/phonon interactions are of lesser magnitude. Bulk thermal conductivity can be expressed as a combination of both, magnitudes depending on many interaction processes and hindrances. In the case of lattice vibrations, such hindrances arise from interactions between phonons, phonon scattering due to crystal imperfections, solute atoms, impurities, and interaction between electrons and phonons. For the electron component, the same style of scattering in crystals and interactions between electrons apply.

The contribution of phonons first decreases with increase in temperature, but at higher temperatures the phonon scattering of electrons saturates and the effective thermal conductivity stabilizes to a minimum state. For metals with good thermal conductivities, the conductivity is mostly from the electron contribution. In some cases, like pure metals or very diluted alloys, phonon interaction can be even neglected from estimations. Additionally, possibilities to affect phonon interactions in bulk are rather minimal, as they are fundamental atom level behaviors. In pure metals, the contribution of electrons is dominant and little hindrance to conduction exists. Alloys are another matter, as differently sized elements are mixed together, increasing scattering effects[8]. Thermal transport in a material can be described with

$$\lambda = \kappa \rho c \quad (1)$$

where λ is thermal conductivity, κ thermal diffusivity, ρ density and c specific heat.

For metals and their alloys, thermal and electrical conductivities are related, as free electrons transfer both electric current and heat. This empirical relation is known as Wiedemann-Franz law. If electrical resistivity of a material is known, thermal conductivity can be estimated by using the relation;

$$\frac{\lambda}{\sigma} = LT, \quad (2)$$

where λ is thermal conductivity, σ electrical resistivity, L known as Lorenz number and T temperature. Although the relation works well in general, it has limitations. The Lorenz number can have differing values for systems with scattering effects, for example. Another relation used to approximate resistivity, known as Matthiessen's rule, states that total resistivity of a crystalline metallic alloy is the sum of resistivity due to thermal agitation of a lattice, imperfections and defects in an alloy. Imperfections with the largest contribution are alloying elements in solid solution followed by precipitated inclusions.

From all the above, it is not surprising that thermal conductivities in metallic alloys display a wide variation, in magnitude and as a function of temperature. Ultimately, the rate of heat transfer in a component is determined by material's thermal conductivity and the temperature gradient the component is exposed to. Several measurement techniques for thermal properties exist. Generally, these can be divided into steady-state and non-steady state methods, each fit for use with different materials, temperature and thermal property ranges, with inherent limitations in sample geometries. The challenges with most techniques regard control of heat losses/thermal stability and heat flow direction. These result in limitations of total measurement accuracy.

Steady state methods exist for both solids and fluids. Often, experimental set-ups are made in a way to reduce the calculations to one-dimensional cases, simplifying the whole. Guarded hot-plate method is one of them, where material samples are placed between a heated and a cooled plate, resulting in a temperature gradient in the sample after equilibrium is attained. The temperature difference between the plates and sample geometry can be used to calculate thermal conductivity values. The method can be used for relatively low thermal conductivities, up to $5 \text{ Wm}^{-1}\text{K}^{-1}$, and thus not applicable to metals with high conductivities. The same principle is used in a comparative fashion in heat flow meters, where samples are placed in series with a material of known thermal conductivity. This method of measurement is similarly limited in range of thermal conductivity. Some steady-state methods can be used to measure metals and their alloys, although accuracies of such measurements can vary up to tens of percent[9].

Non-steady state methods, also known as transient methods, use measuring response of a material to heat input to calculate thermal properties instead of relying on an equilibrium in heat flow. Laser Flash (LFA) is a widely used transient method, where a short laser pulse is used to heat one side of a sample and the temperature response is measured on the other side as a function of time. This method enables measurement of thermal diffusivity at high and low tem-

peratures, with short measurement times. After separate measurements of specific heat and sample density are done, calculation of thermal conductivity is possible, using equation (1). Hot-wire and hot-strip methods measure rise in temperature set distance from a heat source. An evolution of these is Transient Plane Source (TPS) method, where a protected spiral placed between samples acts as both the heat source and temperature sensor. The advantage of the TPS-method is measurement of both thermal diffusivity and conductivity at the same time, while limitations in sample geometry are not overly constraining. The use of TPS method is presented in more detail in **section 3.1**.

2.3 Thermal conduction in cast irons

Estimating thermal conductivities for multi-component systems without experimental data is challenging. Simple alloys can be estimated with rule-of-mixtures type of calculations, which however only work with materials that contain distinct separate phases. In the case of cast irons, similar alloying can result in various microstructures such as ferrite, pearlite, martensite, ausferrite etc. Various alloying elements also can also exist in solid solution, complicating the matter. The various morphologies and microstructures in cast irons enable their use in great amounts of applications, but at the same time make accurate modeling of their properties a challenge. Atoms in solid solution distort crystals, which results in strengthening effects, like in precipitation hardening. Strength and conductivity are most often inversely related to each other. Combinations of pure metal conductivities and highly alloyed strengths would be ideal, but unfortunately impossible to attain, necessitating compromises in material development. Cast irons not only differ in microstructures, but also in graphite morphologies. Differing forms of graphite effect strength and conduction in various ways. Three common base forms of graphite in cast irons are lamellar, compacted and spheroidal. Other morphologies also exist but are in most cases classified as degenerated graphite with regards to cast iron production. Effectively, thermal properties in this materials group are affected by atleast the type of matrix, the amount and form of graphite and abundance of alloying elements.

Graphite itself is an excellent conductor and can be manipulated with the goal of increasing thermal conductivity. Having been studied extensively, graphite conducts heat very well in certain basal planes and poorly in others. Due to this, lamellar graphite is the most efficient form for conduction and spheroidal the worst. Thus, increasing the volume of graphite in the matrix can be used to increase conductivity of especially lamellar alloys. However, at around 4,5 – to 4,8-% carbon equivalent (CE%) graphite flotation defects start to appear due to differences in densities [10]. In [11], the differences in graphite thermal conduction and basal planes are outlined. A schematic representation of the differences is shown in Figure 2. For a very low alloy steel, or near pure iron, no carbon precipitates exist, and the conduction is purely based on the metallic matrix. In lamellar form, conduction happens in addition to the metallic matrix largely along the advantageously oriented [001] basal plane. In spheroidal graphite

Figure 2 Schematic representation of heat propagation based on graphite morphology and favourable basal planes for thermal conduction. From left: iron matrix without graphite inclusions, spheroidal graphite and lamellar graphite. Adapted from [11]

nodules, the same basal planes are not oriented to significantly aid conduction, effectively giving only a minor boost compared to pure iron and steels. Thus, spheroidal graphite cast iron behaves almost like similarly alloyed steels, conduction being dominated by the matrix. Compacted graphite, being an in-between morphology of lamellar and nodular, has some characteristics of both. Elongated graphite precipitates mixed with spheroidal graphite increases conductivity but does not allow as good mechanical properties, e.g. ductility and ultimate tensile strength, as with fully spheroidal nodules. Effect of graphite shape on conductivity in a pearlitic matrix is presented in Figure 3, based on models of Helsing, et al[12]. The model illustrates that shape differences in the most spherical range affect bulk conductivity rather little, while small deviations in shape matter a lot in the other extreme. In cast iron standards like EN 1563: Spheroidal graphite cast irons, material quality is partly defined by a measure called nodularity. The nodularity of spheroidal graphite cast irons is defined as the percentage of graphite particles that are spheroidal or nodular in shape (form V and VI of EN ISO 945-1). As an informative guideline, nodularity of 80 % or more generally ensures the minimum tensile properties specified. Thus, in shape factor ranges that graphite could be classified as spheroidal, very little gain in conductivity is possible even if such shape control could be done in practise. Ultimately, the morphology of graphite matters a lot, but just controlling the shape of it is not an answer to the challenges ahead regarding thermally loaded applications. Just based on thermal conductivity, lamellar graphite alloys would be the best choice but unfortunately practically all grades of lamellar cast irons are considered low strength materials. In the end, increasing carbon content and controlling graphite does not come without negative effects.

Figure 3 Effect of graphite shape on bulk thermal conductivity in a pearlitic matrix. Shape factor in this case is defined by ellipsoid axes R and eR . Adapted from [12]

As outlined earlier, thermal conductivity of cast irons is not purely based on graphite morphology. The contribution of the metallic matrix can be influenced by alloying and process treatments affecting microstructure. Unalloyed ferrite, pure iron, is a decent thermal conductor with a conductivity of around $80 \text{ Wm}^{-1}\text{K}^{-1}$ [13-15]. Pearlite is a lamellar composition of ferrite and cementite, iron carbide Fe_3C . Having lots of boundaries that hinder conduction, along with having a lot of badly conducting carbide compounds, $\lambda(\text{Fe}_3\text{C}) \approx 8 \text{ Wm}^{-1}\text{K}^{-1}$ [12] makes pearlite an ineffective thermal conductor. The effective thermal conductivity in pearlitic microstructures thus depend largely on how much hindrance to ferrite conduction exist. Naturally, the form of pearlite, spacing, coarseness and other shape related factors influence the magnitude of hindrance from cementite. Other types of iron microstructures have similar downsides to pearlite, being either highly alloyed to be stable at normal operating temperatures or having a lot of hindrances for conduction in the form of grain boundaries etc. Thinking naively, one could postulate that adding highly conductive elements, such as copper and aluminium to less conductive materials should increase thermal conductivity. However, in multi-element systems with complex interactions that is rarely the case. Table 1 lists a few elements and their main effects on cast irons, collected from [10]. Elements often have both positive and negative effects, depending on alloying levels and points-of-view. E.g. copper stays mostly in solution in ferrite until 3,5 w-% and precipitates out of solution after that. Alloying levels of less than 1 w-% are enough to result in completely pearlitic microstructures. At levels above 1 w-%, copper can precipitate out of solution during heat treatments and other thermal processing steps. In standard cast iron grades, aluminium is an unwanted element in considerable contents as it inhibits nodularization, for one.

Table 1 Some elements and their general effects on cast irons [10]

Element	Effect
Silicon (Si)	Graphitization, ferrite stabilization and solution strengthening
Nickel (Ni)	Ferrite strengthening, pearlitization
Copper (Cu)	Pearlitization, sensitization of graphite degenerative elements
Manganese (Mn)	Pearlitization, strengthening
Aluminium (Al)	Graphite spheroidization inhibitor

Most alloying elements affect cast iron microstructures in some way. Their effects can generally be divided into carbide inducing or graphitizing groups. For example, silicon, phosphorus, aluminium, titanium, nickel and copper are graphitizing and manganese, molybdenum, chromium and vanadium are carbide inducing. Graphitizing elements promote the growth of graphite and increase the hardness of ferrite through solution strengthening. Carbide inducing elements form compounds with carbon and promote the formation of iron carbide, cementite. Thus, they are also often pearlite promoters. Nickel and copper are pearlitizing elements, although they do not promote growth of cementite rather than stabilize pearlite through slowing the diffusion of carbon in the matrix. Nickel is a strong austenite stabilizer, being used in production of austenitic and ausferritic cast irons. Pure copper thermal conductivity is in the range of $400 \text{ Wm}^{-1}\text{K}^{-1}$ [16], being widely used in electronics and applications that require good electrical and thermal conductivity. Copper is a strong pearlitizing element and starts to precipitate as a separate phase in quantities in excess of 1-%. Regarding thermal conductivity, a fully pearlitic matrix is prohibitive. Tin, Sn, is one other pearlitizing element and is mostly detrimental in more than minute amounts in cast iron compositions. Practically all alloying elements decrease thermal conductivity one way or the other, ultimately making it rather impossible to increase conductivity by just dumping a certain element into a melt. Evidently, if a simple radical way of increasing cast iron thermal conductivities existed, it most likely would have already been introduced into industrial use. As improving both thermal and mechanical properties at the same time seems rather improbable, optimization of properties at applicational level looks to be a more fruitful approach in solving modern industrial challenges.

2.4 Spheroidal graphite irons in thermally loaded applications

Trends in component design have also increasingly shifted from using assumptions of a mostly homogenous material behavior to local property approaches [17-21]. To use such approaches, proper data of materials is needed for any computational approach to be usable and accurate. Data on some levels exists but not as a whole, which naturally complicates design of thermally stressed components and forces one to assume magnitudes of some parameters. Grey and compacted graphite alloys' thermal property optimization is often done through graphite control, while in contrast the nature of spheroidal graphite forces one to focus more on microstructural and compositional control.

Heat treatments and controlled cooling systems are widely used to change material microstructures to improve and tune mechanical properties. For cast irons, heat treatments can be used to control ferrite and pearlite ratios or change the microstructure entirely, e.g. austempering treatments (ADI). Ferrite is a much better thermal conductor than pearlite but results in lower strength if not solution strengthened with proper alloying elements. Higher alloying levels, for example high silicon in standardized (ISO 1083:2004, EN 1563:2011) solution strengthened ferritic ductile irons (SSF), give better mechanical properties combined with a homogenous ferritic microstructure [22-24], but will have more disruptive effects to thermal transport properties compared to low alloy ferrite. Changes in microstructure also naturally arise from cast part geometries, like wall thicknesses. A part might also have multitude of ferrite and pearlite compositions in the geometry due to different internal cooling rates alone. This heterogeneity can be a challenge or a possibility for design engineers. Proper material data is of utmost importance especially in simulation and general design of components.

Spheroidal graphite cast irons offer a potential approach for increasing performance in thermally loaded applications. Spheroidal nodules offer little to no benefit in thermal conduction, but at the same time do not decrease mechanical properties, like strength and elongation, nearly as much as other forms of graphite. Optimization of matrix thermal properties while not forgetting strength is a possible avenue for progress. From a microstructural point of view, ferritic low silicon alloy should be the best for thermal conduction. This naturally results in lower strength. Pearlite increases the strength of metallic matrix, leading to a possible production window of silicon and pearlite fractions. Thus, it can be postulated that there should exist a sweet spot in lowering the amount of silicon and controlling the amount of pearlite in the matrix, depending on components and application environments. Not much discussion of using spheroidal graphite cast irons in thermally loaded applications exists in scientific literature. One of the aims of this work is to address that.

2.5 Dynamic strain aging

Elevated temperature behavior is not dominated only by changes in thermal properties. Strength evolution is also a key parameter. For iron-based materials, some often detrimental effects are known to exist, but a complete image is yet to be made for certain alloy systems. One of these relatively less investigated areas of research, specifically regarding cast iron properties, is related to aging effects grouped under the term strain aging. Strain aging is an effect where hardening happens under plastic deformation. At certain elevated temperatures in aging occurs due to interaction of solutes with dislocations, pinning of dislocations by solutes, thus increasing needed stress for dislocation movement. As with other aging processes, changes in strength and hardness can be observed. At elevated temperatures, such effects can manifest themselves in the form of dynamic strain aging (DSA). DSA can be defined as aging processes in alloys

containing solutes, which can rapidly and strongly segregate to dislocations and lock them during active straining.

Generally, DSA is observed in multiple different forms, such as loss of ductility at elevated temperatures and Portevin-Le Chatelier effect (PLC) [25]. PLC is a form of inhomogeneous deformation, seen as serrations in stress-strain curves, as deformation bands and is associated with DSA [26, 27]. In PLC, stress and plastic strain oscillate. During oscillations, average stress may remain constant or increase either steadily or in steps, corresponding to crossing of the specimen length by the bands. Several types of serrations are classified in established literature [28]. Another occurrence type of instability are Lüders fronts [29, 30]. They are defined as delineation between plastically deformed and undeformed material during tensile strain, appearing at one place and propagating through the material. With Lüders fronts, stress-strain curves in tensile tests appear smooth during propagation, but the localization is preceded by yield point behaviour. Yield point behaviour is observed as stress reaching a peak, then quickly dropping to a lower value. However, these are not the sole forms of occurrence, as mechanical properties can change in DSA regimes even without the occurrence of serrated yielding.

Known strain aging effects include negative strain rate sensitivity, ductility minimums and positive temperature dependence for flow stress and work hardening [28]. The main contributing factor in dynamic strain aging in most research is attributed to interaction of various solute elements [26, 27] like nitrogen and carbon with movement of dislocations. Interaction with solutes is dependent on diffusion rates of said elements. Thus, aging effects occur more strongly at elevated temperatures, as increase in temperature results in faster diffusion. Strain localisation and higher strain hardening observed during inhomogeneous plastic flow, affect performance of materials in thermomechanically loaded applications. Instabilities in straining can occur from strain induced phase transformation, twinning, order-disorder transformation interaction with dislocations in alloys.

Cottrell and Bilby [31] proposed that strain aging effects are due to segregation of interstitial solutes to form atmospheres around dislocations requiring increased force to break away and become mobile, known as the 'solute dragging'-model. This model predicts aspects of serrated yielding correctly, however the model has been shown to predict critical strain for their onset in error [32]. McCormick proposed an arrest model, where motion of dislocations on their slip planes is described as discontinuous process. Dislocations meet obstacles that need to be passed, after which a rapid jump happens to the next obstacle. In the model, pinning of dislocations is dependent on combination of solute diffusion and average waiting times before obstacles are passed. Another alternative model, known as 'pair reorientation'-model, was proposed by Rose and Glover [33]. In that model, motion of dislocations is slowed by vacancy-solute pairs. Recent studies still clarify and discuss the actual mechanisms behind DSA in iron-based materials [34, 35], although the effects and challenges created by the phenomenon have been known a long time. In Caillard et al. observations indicate that dynamic strain aging in pure iron involves the locking of pure

screw dislocations. Tests with carbon in solution, shows Cottrell interaction between carbon atoms and dislocations and the carbon-screw interaction by what they describe as a new “high-temperature Peierls mechanism”.

In summary, multiple models for DSA effects exist and most attest those to solute atom interaction with dislocations at elevated temperatures in various mechanisms. DSA is observed in multiple forms during straining and should be considered in thermomechanically loaded component design. Cast irons exhibit properties that make them attractive in such applications, and thus their DSA behavior needs to be investigated.

2.6 Dynamic strain aging in cast irons

In general, cast iron stress-strain behaviour differs from those of many steels. For example, cast irons do not generally have clear yield points, which also affects flow behaviour. For ductile irons, yield strength is taken as the stress corresponding to 0.2 % plastic strain. In the case of strain aging, effects can be observed when solute element diffusivity is high enough compared to the movement of dislocations. Thus, temperature is a clear driving factor in the occurrence of strain aging effects, as solute atom diffusivity rises with temperature. As the effect is dependent on a combination of strain, diffusion and temperature, the effects manifest themselves in certain elevated temperature regimes. Relatively little data on the influence of microstructure on dynamic strain aging behaviour of ductile cast iron exists. Many a work on the topic focuses on fully ferritic microstructures [36-39]. Studies have shown that DSA induced effects are evident in pearlitic steels at the temperature range of 100 – 400 °C [40-42]. Strain aging effects, both static and dynamic, are reported with both ferritic and pearlitic microstructures, although the mechanisms have been analysed to differ in causes. The more commonly discussed form takes place with carbon and nitrogen dissolved in ferrite, and the other is attributed to carbon atoms released during the decomposition of cementite in pearlite during plastic deformation [42]. Static strain aging refers to cases where diffusion at elevated temperature happens without simultaneous load and ultimately leads to increase in properties such as yield strength when the structure is ultimately strained. One clear difference between the matrix structure between steels and cast irons is the amount of silicon. For example, increasing silicon content is associated with increasing activation energies for the appearance of serrated flow [37], as silicon in solution lowers the diffusivity of carbon in ferrite. Naturally, the carbon contained in graphite nodules is a clear difference between steels and ductile irons. Hot strength of various cast irons at elevated temperatures have been noted to plateau near 200- 400 °C [43], although much more for lamellar than spheroidal graphite irons.

In low alloy steels with varying microstructures, changes in yield and tensile properties due to dynamic strain aging and effects on fatigue life has been observed at elevated temperatures [44-48]. In ferritic ductile cast irons, studies

have shown the same tendencies, but with the difference that their embrittlement temperatures are at higher temperatures [36]. The reason for this is at least partly that silicon contents are higher, suppressing diffusion and graphite is present in the microstructure [36, 37]. Microstructural changes are built up by dynamic strain aging under recurring tension and compression strains, which affect materials' mechanical behaviour and ultimately fatigue life. Studies on ferritic ductile irons have shown that DSA related phenomena have effects on low cycle fatigue (LCF) properties [38, 39]. E.g. higher peak stresses have been attributed to be the cause of reduction in LCF life. However, in some other studies, high cycle fatigue (HCF) lifetimes have been observed to increase when a material is loaded at elevated temperatures under DSA inducing conditions [49]. Similar findings and temperature related changes have been noted for cast iron types with different graphite morphologies [50-52], such as compacted graphite. Effectively, the contribution of temperature, strain rates, alloying and microstructure need to be understood better if they are to be considered in thermomechanically-loaded component design.

2.7 Summary of literature

There are several approaches to modify the behaviour of cast irons at elevated temperatures. A lot of research has been done on alloying and strengthening of high thermal conductivity types of cast irons. A great deal of works also study the effects of graphite shape on thermal conductivity. In a sense, high matrix strength lamellar graphite cast irons are at the end of their line with regards to performance increase. One other approach, where increased priority is given to a thermally conductive matrix and graphite shape conducive to better mechanical properties is a path rarely trodden. This potential approach drives the need of gathering knowledge on the effects of microstructure and alloying. Ferrite and pearlite are the main constituents in iron-based materials, with also the most potential in finding a compromise between thermal conductivity and strength. Silicon is one of the main alloying elements in cast irons and being in solution in ferrite, has the most effect on matrix conductivity. Ferritic-pearlitic cast irons that have not been heavily alloyed to withstand high temperatures are commonly limited to about 400 °C, as tensile strengths rapidly decrease at temperatures above this. All these narrow down the possible parameter space that is of interest in engineering design:

- Silicon alloying dictated by limits in base foundry process and carbon equivalent
- Temperature from room temperature up to ~400 °C
- Microstructure from fully ferritic to fully pearlitic

This temperature range puts the potential material into the range of dynamic strain aging, where sudden loss of ductility is possible with certain load combinations. Practically all available data on the topic is for ferritic microstructures. Thus, it is of great interest to know whether going the above-mentioned direction will pose greater risk with regards to DSA.

3. Experimental work and methods

A brief summary of the most important experimental methods and techniques used in this dissertation is given here. Descriptions of standard practises like metallography and material production can be found in the appended publications.

3.1 Thermal conductivity testing with TPS-approach

‘Hot Disk TPS 2500 S’-thermal constants analyzer, capable of measuring high thermal conductivities of metals like copper and aluminum alloys [53-56], was used to measure thermal conductivities of test alloys from room temperature up to 400 °C. Transient plane source method relies on mathematical modelling to derive thermal transport properties with a single measurement. Other methods to measure thermal conductivities, like laser flash analysis (LFA), often require additional measurement of parameters like specific heat (C_p). The fundamentals and background of the method are portrayed in the work of Gustafsson et al[53, 57]

Figure 4 Important Transient Plane Source sample parameters

In the TPS-method used in this work, a transient plane source sensor is placed between the surfaces of one or two pieces of sample(s) to be measured, shown in Figure 4. During measurement, a constant current passes through a nickel (Ni) foil spiral in the sensor, which in turn creates an increase in temperature. The heat generated in the sensor flows through the sample at a rate dependent on thermal transport characteristics of the studied material, creating a temperature transient. By recording the temperature versus time response, transient, in the sensor, thermal transport characteristics including thermal conductivity can be calculated. The heat propagated needs to be confined within the sample boundaries, or be insulated properly and be of known height, and thus in property calculations the material can be assumed as infinite bulk. The method has been shown to be useful for measuring engineering materials with high thermal conductivity [53-56]. Represented in a simplified manner, thermal properties can be identified from a single transient measurement using the following equations;

$$\lambda = \kappa \rho c \quad (1)$$

$$\tau = \frac{\sqrt{\kappa t}}{a} \quad (3)$$

where λ is thermal conductivity, κ thermal diffusivity, ρ density, c specific heat and τ a dimensionless parameter called characteristics time, including time t and sensor radius a . Thermal property values are calculated from slope of a complex time function $D(\tau)$ and average temperature increase $\Delta T(\tau)$ plot. As many of the parameters are not known beforehand, measurement software is used to optimize a solution of a model until a linear fit is achieved. A good fit in this case means that the data makes a linear slope, corresponding to steady increase in temperature in a sample based on constant heating power. If the temperature increase does not form a constant slope, seen as large residuals to a linear model, the experimental setup can be suspected to be poor and thus the accuracy of the measurement should too. However, if the experimental setup is handled correctly, the approach ultimately makes it possible to measure a property like thermal conductivity without measuring specific heat independently. Examples of the parameters used in the measurements are illustrated in Figure 5. Figure 5a shows a transient temperature graph, which corresponds to heat propagation in the sample. For the measurement quality to be good, the sample temperature needs to be stable before the transient measurement is made. This requirement is fulfilled by analysing sample temperature drift results, illustrated in Figure 5b. If either a positive or a negative trend is evident in the results, the sample is yet to reach ambient temperature. If the transient graph does not show anomalies and the temperature drift is minor, a part of the transient can be used to make the linear fit shown in Figure 5c, ultimately resulting in thermal properties of the sample. Usually, the start of the transient is not used, as that part corresponds to thermal resistance between sensor and sample. Data points from ends of transients are taken out of calculation based on probing depth, sensor and sample dimension. If the linear fit is poor or the fit residuals,

example shown in in Figure 5d, are large, the calculated results can be expected to be inaccurate. Ultimately, the TPS method can be a very efficient tool in thermal property assessment but can also result in high uncertainty if the operator is inexperienced in setting parameters, performing measurements or analysing the results.

Figure 5 Examples of a) temperature transient measurement b) sample temperature drift c) calculated linear fit d) calculated fit result residuals

All room temperature measurements in this work were made in stainless steel sample holders with a Kapton insulated sensor. Elevated temperature tests were made with an automatically controlled muffle furnace, which contained a high temperature sample holder with Mica insulated sensors. Test samples were stabilized at selected temperatures for at least 30 minutes before conducting measurements to lessen the effect and probability of temperature drift and other variation sources in thermal property calculations. Elevated temperature tests consisted of a single cycle that went in steps from lower temperatures to higher, e.g. 100-200-300-400 °C to minimize potential effect of heating cycles and microstructural changes in samples. All samples were made after other processing steps, e.g. heat treatment, to minimize degradation of material in the surface region.

3.2 Static and cyclic mechanical property testing

Figure 6 DSA test bar geometry and dimensions in mm

Basic tensile test samples were manufactured from separately cast cylindrical bars according to EN 1561 "Founding. Grey cast irons", EN 16079 "Founding. Compacted (vermicular) graphite cast irons" and EN 1563 "Founding. Spheroidal graphite cast irons". For GJL, cylindrical blanks were cast in 30mm diameter and machined into 10 mm gauge diameter samples. For GJV, cylindrical blanks were cast in 25 mm diameter and machined into 10 mm gauge diameter samples. For GJS, cylindrical blanks were cast in 25 mm diameter and machined into 10 mm gauge diameter samples.

In studying dynamic strain aging, basic tensile tests were performed at different temperatures ranging from room temperature (RT) up to 450 °C. Cyclic strain-controlled tests with triangular waveform were performed on a MTS machine according to test program presented in Table 2, and were conducted at five different temperatures. The tests contained three different strain rates ranging from 0.00001 s^{-1} to 0.01 s^{-1} and strain amplitudes (%) from 0,3 to 0,7. Strains were measured with extensometers, elevated temperature tests using high temperature versions. In cyclic load tests, three to five samples were tested at each temperature following the full program. The samples were not strained to fracture with the objective to limit the number of samples needed in testing. Additional tensile tests, one that contained an interrupted test, were done with fully ferritic samples to investigate changes in general yield behaviour. The interrupted test contained the following cycle; strain at 250 °C until 1% elongation, restart of test at room temperature and strain until fracture. All tests in the DSA study used tensile test samples in the shape and dimensions outlined in Figure 6.

Table 2 Cyclic plasticity test program used for all microstructures

Strain amplitude, $\pm\epsilon$, %	Strain rate, $1/\text{s}$	Number of cycles
0,3	1,00E-02	100
	1,00E-03	6
	1,00E-05	3
0,5	1,00E-02	60
	1,00E-03	3
	1,00E-05	3
0,7	1,00E-02	30
	1,00E-03	3
	1,00E-05	3

4. Results

This chapter summarises the results of the three publications that were done during this thesis. The main findings of this study broaden the knowledge about the effects of microstructure and alloying on elevated temperature behaviour of cast irons. First, **article I** studies the material group of cast irons more generally, having a wider base of as-cast test materials and seeks to benchmark the fitness of the thermal conductivity measurement system. Practically no data on cast iron thermal conductivities at elevated temperatures measured with Transient Plane Source-method exists. Thus, if the different cast iron types behave according to established literature done with other measurement systems at elevated temperatures, the HotDisk TPS should be fit also for the measurement of cast irons. **Articles II and III** study spheroidal graphite cast iron properties in more detail with respects to thermal and mechanical behaviour as outlined in previous sections.

4.1 Lamellar -, compacted and spheroidal graphite cast irons at elevated temperatures (Article I)

Table 3 Chemical composition, carbon equivalent (CE %) of the studied alloys

#	C	Si	Mn	P	S	Cu	CE %	Graphite type	Alloy designation
1	3,15	1,80	0,75	0,025	0,070	0,51	3,75	Lamellar	GJL 250
2	3,81	1,84	0,22	0,024	0,009	0,82	4,42	Compacted	GJV 450
3	3,93	1,61	0,09	0,022	0,009	0,03	4,47	Spheroidal	Low Si
4	3,69	2,33	0,40	0,037	0,012	0,15	4,47	Spheroidal	GJS 500-7
5	3,43	3,79	0,39	0,037	0,012	0,09	4,69	Spheroidal	GJS 500-14
6	2,74	4,39	0,29	0,018	0,003	0,02	4,21	Spheroidal	GJS 600-10

Alloys in the first study consisted of lamellar, compacted and spheroidal graphite cast irons listed in Table 3. Nodularisation of spheroidal graphite irons was done with sandwich method, with FeSiMg, and were inoculated with FeSi in pouring stream. Residual magnesium levels were ~0,04-0,05% and compositions were checked for elements that are detrimental to nodularisation (Pb, Sb, Sn, Bi). Micrographs of as-cast and austempered structures are shown in Figure 7. Microstructural percentages calculated using image analysis can be found in Table 4. Measured temperature dependencies on thermal conductivities of the studied alloys are shown in Figure 8. The tested lamellar graphite cast irons, alloys 1 and 1A, exhibit an almost linear decreasing

Figure 7 Example micrographs of as-cast (a) alloy 1 LGI, (c) alloy 2 CGI, (e) alloy 4 SGI, (g) alloy 6 SGI, (h) alloy 3, SGI and austempered versions (b) alloy 1A (d) alloy 2A (f) alloy 4A.

Figure 8 Thermal conductivity results of materials described in Table 3

trend at elevated temperatures normal for many iron-based materials. All other tested materials show varying increase and peak thermal transport properties at an intermediate temperature, at approx. 200 - 300 °C, and a decrease after the attained peak. The low silicon alloy ductile iron, alloy 3, shows the highest elevated temperature thermal conductivity within the studied materials with λ of 49 Wm⁻¹K⁻¹ at 200 °C. At room temperature, the lamellar graphite cast iron alloy 1 has the best thermal conductivity. The results of compacted graphite irons, alloys 2 and 2A, fall in the middle of the tested alloys. In line with theoretical aspects of graphite effect on conductivity, the spheroidal graphite irons generally have the lowest measured conductivities in the set. The high silicon variants, alloys 5 and 6 exhibit the lowest conductivities of the tested materials.

Austempered versions of the base alloys, 1A, 2A, 4A and 5A all exhibit a drop in conductivity compared to the as-cast variants. As the austempering process mainly affects microstructure, there is only a rather minor drop in conductivity for lamellar graphite alloy 1, while the biggest decrease in thermal conductivity between as-cast and austempered states is evident with the high silicon spheroidal graphite irons. Ausferritic compacted graphite alloy 2A thermal conductivity peaks at almost the same level compared to the as-cast version of the same alloy at around 300 °C, while the difference is more evident at all other tested temperatures. The tested austempered samples have additional drops in thermal conductivities at the highest tested temperature, 400 °C, which is above the salt bath temperatures used in the treatment. In actual components, a safety buffer between operating and austempering temperatures is essential to minimize the risk of unwanted microstructural changes and unforeseen changes in mechanical behavior.

Mechanical properties at room temperature are listed in Table 4 along with notation of ferrite-pearlite area fractions of the mixed microstructure variants. All ausferritic variations show expected increase in mechanical properties. Compared to thermal conductivity results, the trend between the different graphite types is generally inverted when mechanical properties are compared. LGI alloys ultimate tensile strength increased only little, while the difference for the tested CGI alloy was larger. SGI alloys were strengthened much more. The largest improvement in mechanical properties coincides with the lowest thermal conductivity. In line with established literature [58-60], no studied alloy shows improvement in both mechanical and thermal properties with the used treatment parameters. However, the results show that spheroidal graphite cast irons can rival lamellar graphite alloys, if the main optimization parameter is thermal conductivity. The main trends of the three different cast iron groups is evident in Figure 8, which matches those in established literature [58-60]. Lamellar graphite conductivity only decreases with increasing temperature, while compacted and spheroidal graphite variant conductivity increase up to a certain point and starts to decrease in the final test temperatures. Thus, if the measurement system would systematically give bad results or there would be major operator errors, these trends should not be visible.

Table 4 Properties and microstructures of alloys presented in Table 3

#	Treatment	R _{p0.2} (Mpa)	R _m (Mpa)	A %	Hardness (HB)	Microstructure	Base alloy
1	As cast	-	319	-	228	Pearlitic, lamellar graphite	GJL 250
1A	Austempered	-	422	-	285	Ausferritic, lamellar graphite	GJL 250
2	As cast	386	560	2	261	Dominately pearlitic (5 % Ferrite), compacted graphite	GJV 450
2A	Austempered	690	782	1	350	Ausferritic, compacted graphite	GJV 450
3	As cast	256	414	21	143	Ferritic-Pearlitic (12 % Pearlitic), spheroidal graphite	Low Si
4	As cast	380	626	8	211	Ferritic-Pearlitic (48 % Pearlitic), spheroidal graphite	GJS 500-7
4A	Austempered	763	1072	6	336	Ausferritic, spheroidal graphite	GJS 500-7
5	As cast	436	553	20	200	Fully ferritic, spheroidal graphite	GJS 500-14
5A	Austempered	1005	1364	7	415	Ausferritic, spheroidal graphite	GJS 500-14
6	As cast	493	613	18	220	Fully ferritic, spheroidal graphite	GJS 600-10

4.2 Effect of ferrite, pearlite and silicon alloying on elevated temperature thermal conductivity of spheroidal graphite cast irons (Article II)

Table 5 Chemical compositions of alloys (w-%) and some nearest corresponding grades according to standard EN 1563 for the ones applicable

Alloy	C	Si	Mn	P	S	CE %	Note
1	3,9	1,3	0,1	0,02	0,009	4,43	Low Silicon
2	3,6	2,3	0,5	0,03	0,015	4,37	GJS 500-7
3	3,4	3,8	0,4	0,03	0,008	4,67	GJS 500-14
4	2,8	4,3	0,3	0,02	0,003	4,23	GJS 600-10

In the most used forms, spheroidal graphite cast irons are microstructurally some combination of ferrite and pearlite. Silicon alloying levels are dependent on application and required strength levels. Studied compositions shown in Table 6 covers most of the standard silicon alloying ranges for spheroidal graphite cast irons, varying silicon (Si) between 1,3-4,3 w-%. Alloy 1 is near the easily attainable lower limit of silicon alloying, as some silicon is in most cases introduced to a melt from important metallurgical treatments like spheroidizing and inoculation. Carburizing a low silicon melt also becomes increasingly difficult when trying to offset the decrease in carbon equivalent (CE%). Alloy 2 is an intermediate composition, which corresponds to a common ferritic-pearlitic variant in the standard EN 1563, namely EN GJS 500-7. Alloy 3 is a solution strengthened composition in the higher range of silicon alloying, corresponding to EN GJS 500-14 standard and alloy 4 a bit higher still in silicon alloying, corresponding to EN GJS 600-10. Silicon alloying levels of over 4,5 w-% are not normally used due to embrittlement[61]. Decrease in elongation at fracture is associated with chemical ordering of ferritic matrix, known as embrittlement of cast irons as their silicon content is increased. Nodularisation for all the alloys were done with sandwich method, with FeSiMg, and were inoculated with FeSi in pouring stream. Residual magnesium levels were ~0,04-0,05% and compositions were checked for elements that are detrimental to nodularisation (Pb, Sb, Sn, Bi).

Measured thermal conductivities and corresponding microstructural compositions are presented in Figure 9 and Figure 10. Temperature, silicon and pearlite all have clear effects on resulting thermal conductivity. The low silicon alloy 1 shows the best elevated temperature thermal properties of the studied materials with thermal conductivity of $59 \text{ Wm}^{-1}\text{K}^{-1}$ at around 200°C with a mostly ferritic microstructure. On the other hand, the highest alloyed material (alloy 4) has the lowest conductivity results with high amounts of pearlite in the microstructure. Generally, with all the tested alloys, an increase in thermal conductivity can be seen with rising temperature until a peak is attained. A decrease in conductivity is seen with increase in silicon alloying levels and pearlite fraction in the microstructure.

Figure 9 Thermal conductivities of a) alloy 1, 1,5 w-% Si, b) alloy 2, 2,3 w-% Si with different ferrite-pearlite ratios

Figure 10 Thermal conductivities of a) alloy 3, 3,8 Si w-%, b) alloy 4, 4,3 w-% Si with different ferrite-pearlite ratios

The results shown in Figure 9 and Figure 10 were used to make a multi-parameter regression model in Minitab – statistical analysis software. Regression resulted in the following equation

$$\lambda \left(\frac{W}{mK} \right) = 72,56 + 0,06721x_1 - 21,67x_2 - 0,2458x_3 - 0,000161x_1^2 + 2,173x_2^2 + 0,00414x_1x_2 + 0,0541x_2x_3 \quad (4)$$

where x_1 = Temperature (°C), x_2 = Silicon (%) and x_3 = Pearlite (% abs.) $R^2=0,92$ $P<0,001$. The reliability of the data and analysis of the multiple regression is discussed later in section 5.3. Main effect plots of the thermal conductivity regression are illustrated in Figure 11. Conductivity increases up to a point as a function of temperature, while increasing silicon only decreases conductivity. Pearlite effect on conductivity is rather linear, conductivity decreasing with increasing pearlite fraction.

Figure 11 Main effect plots for studied parameters

4.3 Effects of ferrite and pearlite on dynamic strain aging behavior of spheroidal graphite irons at elevated temperatures (Article III)

In this section, tendencies of ferritic and pearlitic microstructures to dynamic strain aging at elevated temperatures is investigated. The alloy composition for these tests was GJS 500-7, with 2,3 w-% Si, like the ones in previous sections.

Figure 12 Example micrographs of 41 vol.% (left) and 100 vol.% pearlitic (right) microstructures used in analysis

Table 6 Chemical composition of the studied alloy (wt.%), carbon equivalent (CE%) and corresponding grade according to standard EN 1563

C	Si	Mn	P	S	CE %	Note
3,6	2,3	0,5	0,03	0,015	4,37	EN-GJS 500-7

Table 7 Heat treatments and resulting microstructures of the test material

Austenization	Cooling	Pearlite (%)	Note
900 °C, 2 h	Cooling 20 °C/h to 400°C, air cool to RT	0	As-cast
900 °C, 2 h	690 °C/4 h, air cool to RT	41	
-	-	52	
900 °C, 2 h	690 °C/0.5 h, air cool to RT	70	
900 °C, 2 h	Air cool to RT	100	

Tensile stress–strain curves for fully ferritic and pearlitic microstructures for all test temperatures are shown in Figure 13 a - b, and the results are collected separately in Figure 14. Serrations were present for the fully ferritic microstructure at 250 °C. Ultimate tensile strengths and yield strengths ($R_{p0,2}$) plateau between 100 – 350 °C for both tested microstructures. A minimum in elongation at elevated temperatures is observed for other than a single isolated test for a fully ferritic microstructure, where it had a local maximum at 350 °C. All tested variations exhibit a decrease in strength properties at 450 °C. Increase in elevated temperature stresses at certain strains, hardening, combined with a loss of elongation is an effect attributed to dynamic strain aging.

Figure 13 Tensile test results for a) 0 vol.% pearlite, b) 100 vol.% pearlite.

Figure 14 Tensile test results from Fig. 13 collected separately. Elongation follows the left vertical axis, R_m and $R_{p0.2}$ axis on the right

Figure 15 shows stress-strain curves for tensile test samples with fully ferritic microstructures using the interrupted test cycle. A test at room temperature, which contains a sample without additional processing, is included in the graph for comparison. The test at 250 °C shows serrated yielding, the PLC effect, while the room temperature test is typical for ductile cast irons with no yield point behaviour. In contrast, the restarted test exhibits clear upper and lower yield points, typical for materials like mild steels. Discontinuous

yielding due to existence of solute interstitials manifests itself as a sharp yield point and subsequent yield plateau in the stress-strain curve, associated with the appearance of deformation bands described already in the 19th century [29, 62]. The 0.2% offset yield strength ($R_{p0.2}$) for the room temperature variant is 302 MPa, while the restarted version has an upper yield point (R_{eH}) of 367 MPa and lower yield point (R_{eL}) of 346 MPa having been strained at DSA inducing conditions.

Figure 15 Stress-strain behaviour of fully ferritic samples in the interrupted test cycle

Figure 16 to Figure 17 show select hysteresis loops from the cyclic materials test program presented in Table 2. Figure 16 shows hysteresis loops for a fully pearlitic microstructure at room temperature and at 350 °C in a low strain rate case (0.00001 s^{-1}). Hardening behaviour is evident, indicated by higher peak stresses for the same strain. Figure 17 shows single, final cycle loops at all the test temperatures for a fully ferritic (a), 52 vol.% pearlitic (b) and fully pearlitic (c) microstructures. For all microstructures, the resulting peak stresses for 100 °C are lower than at room temperature. Stresses in 250 and 350 °C are either near or higher than at room temperature. However, at 450 °C a clear drop in stress levels is evident. Figure 18 shows the same microstructures at the highest strain rate (0.01 s^{-1}) used in this study. The high strain rate results in almost identical behaviour, other than at 250 °C. The stresses do not reach the levels of those done at room temperature, which is a strong indication towards the influence of solute atoms and rate of strain/dislocation movement interaction.

Figure 16 Example hysteresis loops for a 100 vol.% pearlitic microstructure at two different temperatures, low strain rate (0.00001 s^{-1})

a)

b)

c)

Figure 17 Magnified tips of single loops for low strain rate (0.00001 s^{-1}) a) 0 vol.% pearlite b) 52 vol.% pearlite c) 100 vol.% pearlite at 0.5% strain amplitude

a)

b)

c)

Figure 18 Magnified tips of single loops for highest tested strain rate (0.01 s^{-1}) a) 0 vol.% pearlite b) 52 vol.% pearlite c) 100 vol.% pearlite, at 0.5% strain amplitude

Figure 19 to Figure 21 show final loop peak stresses from all the cyclic load cases in an averaged form to highlight how microstructure, temperature, strain amplitude and strain rate affects the occurrence of strain aging on the test alloy. The data has been modified according to equation (5) to ease readability;

$$\text{Peak Stress} = \frac{\sigma_{T(x)}}{\sigma_{T(RT)}} * 100, \quad (5)$$

where x is the test temperature. Room temperature (RT) final loop peak stress is fixed to 100 in each graph, and all the peak stresses at other temperatures are shown relative to it. Thus, absolute stress levels in the different microstructures do not start at the same baseline, as microstructural hardening, through pearlite increases stresses at similar strain levels. Hardening at elevated temperatures shows as deviation from a decreasing stress trend in the graphs with increase in temperature, indicating dynamic strain aging conditions.

All the test cases show an increasing stress behaviour at either 250 °C, 350 °C or both, depending on strain rate. Tested strain amplitudes varied from 0.3 % to 0.7 %. The striking effect at 250 °C and 350 °C exists in all of them and the behaviours in Figure 19 to Figure 21 are invariable between the different amplitude levels. The tested strain rates varied from 0.00001 s⁻¹ to 0.01 s⁻¹, which affect the resulting behaviour. The effects connect strongly to temperature. Higher strain rates suppress hardening at 250 °C, while a peak in stress evolution is evident in all tested samples at 350 °C. Low strain rate cases in Figure 19 to Figure 21 exhibit very similar peak levels at both 250 and 350 °C. The intermediate strain rate of 0.001 s⁻¹ is enough to suppress hardening at 250 °C, although even the highest used strain rate does not stop it occurring at 350 °C. With the higher used strain rates, the stress levels at 250 °C do not reach the levels seen at room temperature, rather staying near the levels at 100 °C. Stress levels peak beyond those at RT with the lowest tested strain rate at 250 °C at all strain amplitudes. In other words, negative strain rate sensitivity, one of the phenomena commonly associated with DSA, can be observed from the compiled data. For example, increase in strain rate normally increases stresses, as is evident for all microstructures at 450 °C. At 100 °C, the sensitivity of all microstructures is almost neutral. For all strain amplitudes at 250 °C, the sensitivity is clearly negative. At 350 °C, increase in strain rate results in slightly negative behaviour.

All the tested microstructures behave similarly when temperature and strain rate vary, as shown in Figure 19 to Figure 21. Absolute stress levels are different, e.g. hardening effect of pearlite compared to ferrite and resulting change in stress levels for given strains. Thus, the occurrence of DSA in spheroidal graphite cast iron is not specific to a microstructural composition of ferrite or pearlite. In fact, when absolute stress values are considered, in many tests the fully pearlitic variants harden the most compared to the room temperature baseline than others. As hardening results in loss of ductility, at elevated temperatures this is particularly risky for pearlitic microstructures where such properties are lower to begin with.

Figure 19 Indexed hysteresis final loop peak stresses at different temperatures, strain rates (ϵ), at strain amplitude $\Delta\epsilon=0,3\%$ and as a function of pearlite content (0-100%) in microstructure

Figure 20 Indexed hysteresis final loop peak stresses at different temperatures, strain rates (ϵ), at strain amplitude $\Delta\epsilon=0,5\%$ and as a function of pearlite content (0-100%) in microstructure

Figure 21 Indexed hysteresis final loop peak stresses at different temperatures, strain rates (ϵ), at strain amplitude $\Delta\epsilon=0,7\%$ and as a function of pearlite content (0-100%) in microstructure

5. Discussion

In this chapter, the results provided in **Articles I-III** are discussed. First, theoretical implications that contribute to the scientific community are presented. Second, practical implications that are beneficial for manufacturing companies and organizations are presented. Third, the reliability and validity of the research that was conducted is discussed.

5.1 Theoretical implications

5.1.1 Thermal properties of spheroidal graphite cast irons

Increasing silicon alloying decreases thermal conductivities with all microstructures. Even in a fully ferritic state, measured thermal conductivity of the highest alloyed variant is far from the low silicon variant. High amounts of silicon in solid solution has many benefits for cast irons in regards of mechanical properties, manufacturability and microstructural homogeneity [22-24] but is clearly not beneficial for thermal properties. Thus, tuning chemical compositions for better mechanical properties through solution strengthening will worsen thermal properties and vice versa. However, the general effect of silicon on thermal conductivity is not linear, as shown in the main effect plots in Figure 11 calculated from the aggregate data. The decrease in conductivity is initially rapid in the low silicon ranges, while increasing alloying has a clear saturating behavior showing as a change in the slope at around ~3-4 % silicon. Similar kind of saturating behavior can be seen in mechanical behavior, as increasing silicon alloying to over 4,3 % has been shown to deteriorate properties like elongation in solution strengthened spheroidal graphite cast irons [23] making them unusable for structural use after the silicon embrittlement range has been reached.

The general shape of the elevated temperature curve shown in Figure 11 is consistent for all the tested alloys and microstructures. The results indicate that the temperature dependence is not linear in nature, seen as some initial increase towards higher temperatures, which peaks at around 200 – 300 °C, and with a final decrease towards higher temperatures. Generally, the main effect plot shows a peak at 250 °C. Highest silicon alloys peak at a slightly higher temperature than the others do, which is not truly surprising as it is farthest from being a pure material, containing the most hindrances to conduction in terms of silicon alloying combined with pearlite. The temperature effect happens with all

microstructures from ferritic to pearlitic along with all tested silicon alloying levels, which indicates that it is not only a property of a specific matrix composition, like ferrite. Similarly, this happens with silicon-alloyed steel without precipitated graphite [63], which in turn indicates that the effect is not based on conduction in graphite nodules. Precipitation out-of-solution as an explanation is also very unlikely in cast irons due to the non-supersaturating nature of silicon solution in iron. Carbon is also precipitated as graphite nodules or for example trapped in the matrix in the form of pearlite or other carbide compositions. In addition, normal cast iron chemical compositions contain very little additional elements that can be considered alloying elements rather than minor trace occurrences from the production process or scrap material. There is also no indication of deviation from the general trend when low cooling rates of ferritic and faster cooled pearlitic versions of the same alloys are concerned. The peak at an intermediate temperature for spheroidal graphite irons has been noted in studies and data gathered from multiple sources [58, 63] and is noted also in established literature on the matter [43] but is not really explained or not often even speculated upon in any meaningful manner. Definite conclusions cannot be drawn on the matter from the results and work in this study, but the findings suggest that the behavior is not exclusive to a certain microstructure rather than more a property of iron-silicon system.

Increase in pearlite fraction decreases thermal conductivities in all tested alloys. The relation between microstructure and thermal conductivity shows as a linear decrease, illustrated in the effect plot in Figure 11. The phenomena behind the results can at least partly be accredited to hindering of conduction due to distortion of lattices with solution elements [14] and the lamellar composite form of pearlite. Pearlite, being a composite form of ferrite and iron carbide, cementite (Fe_3C), has many interfaces and directions that hinder conduction along the fact that cementite in general has poor conductivity [12, 63, 64]. The general theory of thermal conduction in metallic materials states that purer and more homogenous a crystal lattice is; less disruption is imposed upon thermal energy carriers like electrons and phonons. In the case of cast irons, silicon is an element that forms a solid solution with iron matrix. Carbon being out-of-solution as precipitated graphite particles does not have such effects and has little effect on thermal properties due to its' morphology compared to graphite in compacted or flake form. If only good thermal conductivity is concerned in spheroidal graphite irons, low silicon ferritic matrix is the best choice and seems to even rival the conductive properties of some lamellar graphite cast irons [58]. The results in this work highlight the difference between ferritic-pearlitic grades and the newer silicon solution strengthened ferritic (SSF) grades. The new GJS 500-14 and GJS 600-10 are used as direct replacements to ferritic-pearlitic grades, so these differences should be kept in mind. Mechanically, the new grades surpass the older ones by quite a wide margin [22-24], but thermal properties do not improve in the same way as seen from literature and the results of this study. This in turn might create some unforeseen behavior if not taken into proper consideration in component design. Knowledge of true material behavior is thus of utmost importance as previously mentioned.

Conductivities estimated from the regression equation (4) ($R^2=0.92$) agree well with appropriate measured data. The estimation also works for well for a test material with added copper alloying. The addition of copper will influence microstructure through pearlitizing, in addition to increasing the total alloying level. The results show that the model will give good estimations even on ferrite-pearlite microstructures that are controlled with alloying in small amounts, rather than with heat treatments. Naturally, a simple regression model cannot fully cover all aspects of complex composites such as graphitic cast irons. However, in the case of spheroidal graphite irons where large deviations in nodularity are unacceptable in production, these kinds of models that exclusively estimate properties through matrix behavior should work accurately. Modeling thermal conductivities of steels and cast irons have been made with different kinds of techniques ranging from microstructural approaches to composition analysis with artificial neural networks [12, 65, 66]. These studies highlight a few important additional aspects, like the need for fundamental data on microstructural constituents and the complex effect of key alloying elements. For example, silicon studied in this work, is easy to account for being an element just in solid solution, not as a precipitating supersaturated element like in aluminium-silicon cast alloys. However, others like copper or tin, do not have such straight forward interactions. Cast iron alloying and subversive elements can act as pearlitizing, pearlite stabilizing, ferrite stabilizing, graphitizing and the like due to their more complex interactions in iron-carbon systems. Thus, taking a similar regression approach as taken in this study with a larger number of alloying elements as parameters without analyzing their final effect on things like microstructure, is a recipe for disaster.

5.1.2 Mechanical properties

In many engineering materials, dynamic strain aging most evidently shows as serrations in stress-strain curves. Lots of research has been devoted to characterizing serration types along with general yield behaviour. However, DSA is not only limited to this kind of yielding behaviour. Mechanical properties and load bearing behaviours show changes near DSA-inflicting conditions even in the absence of serrated flow. In this work, a tensile test stress-strain curve showed PLC serrations for a fully ferritic microstructure at 250 °C. Yield and ultimate tensile strengths had were at similar levels in the range 100 – 350 °C for both ferritic and pearlitic microstructures, while a ductility minimum was observed at 250 – 350 °C. For an interrupted tensile test with a fully ferritic microstructure, serrations were observed when the test bar was strained at 250 °C. When the test was continued after relaxation and cooling down back to room temperature, the resulting state behaves very differently with a clear yield point behaviour unlike cast irons in general. Serrations and ductility minima at elevated temperatures are DSA associated behaviours.

Strain rates are one of the key factors in the occurrence of DSA. Dislocation pinning by solute concentration and diffusion at low strain rates create a suitable situation for hardening. At higher strain rates, dislocation movement is not impeded as much by this pinning effect, which shows as lower stresses and less

aging effects in macroscopic scale. As solute elements are a main factor in pinning, temperature related changes in diffusion plays as big a role as strain rates. In cyclic load cases where strain rates were varied, such behaviour was observed. The tested strain rates varied from 0.00001 s^{-1} to 0.01 s^{-1} , and clear changes at the stress-strain behaviour is observed at elevated temperatures, mainly between $250 - 350 \text{ }^{\circ}\text{C}$. The slowest strain rate allows solute diffusion to contribute at $250 \text{ }^{\circ}\text{C}$, while hardening is more suppressed at the same temperature when strain rate is increased. The increase in strain amplitude increases the effects at elevated temperatures as plastic deformation increases.

Studies that have analysed fatigue properties of ferritic spheroidal graphite cast irons have distinguished three clearly differing temperature ranges. Low temperatures where diffusion speed is low and no DSA is evident ($20 - 125 \text{ }^{\circ}\text{C}$), intermediate temperatures where dislocation speed is compatible with diffusion and DSA occurs ($125 - 300 \text{ }^{\circ}\text{C}$), and at high temperatures where the two are again not compatible and no strain aging is seen ($>300 \text{ }^{\circ}\text{C}$) has been previously reported [8]. Three different ranges are also evident in this study. Strain aging effects are seen both in tensile and cyclic tests between $100 - 350 \text{ }^{\circ}\text{C}$. Temperatures between $100 - 250 \text{ }^{\circ}\text{C}$ were not included in the test program, where the specific onset temperature of DSA falls. DSA effects has been reported in fatigue of ferritic bearing steels with the aim of increasing fatigue lifetimes through thermomechanical treatments [49]. Kerscher et al. used cyclic loading during thermomechanical treatment to produce a more stable dislocation structure by increasing the mobile dislocation density and dislocation pinning. The result was a higher fatigue limit proportional to higher hardness and yield strength as well as a higher high cycle lifetime. The low cycle lifetime on the other hand remained constant because high stress amplitudes and the corresponding plastic strain amplitude in the low cycle regime destroyed the beneficial dislocation structure in first few loading cycles. Jost et al. [67] studied temperature dependence on fatigue life of predominately pearlitic cast iron EN-GJS 600-3. In that study, fatigue life minimum was attained at $175 \text{ }^{\circ}\text{C}$, a maximum at $300 \text{ }^{\circ}\text{C}$ with DSA related effects and a significant reduction in fatigue life was seen at temperatures over $300 \text{ }^{\circ}\text{C}$. Most current studies on spheroidal graphite cast irons do not comprehensively analyse ferritic-pearlitic microstructures. The cyclic test data in Figure 19 to Figure 21 show that all ferritic-pearlitic microstructures exhibit DSA effects. Changes in fatigue properties should thus be seen in all forms of ferritic-pearlitic spheroidal graphite irons at elevated temperatures.

One parameter not investigated in detail in this study is alloying. Commonly used spheroidal graphite cast iron grades have various levels of silicon in solution. The tested alloy in this study conforms to an intermediate level by current standards, having around $2.3 \text{ wt.}\%$ silicon, which is already very high compared to most steel alloys. Solution strengthened ferritic cast irons (SSF) are a relatively new additions to the spheroidal graphite iron standard family, having as much as $4.3 \text{ w-}\%$ silicon. Silicon affects solubility and diffusion rates of other solutes in ferrite, which in turn should influence dynamic strain aging. As DSA occurs at specific combinations of temperature and strain, this kind of a difference in alloying should slow solute diffusion and thus suppress the window

where effects are observed. Chen et. al investigated silicon alloying effects on DSA in the range 2.0 to 4.1 w-% [37]. Increasing activation energies of carbon diffusion with increasing silicon contents were reported. Silicon was analysed to have a major role on the onset of DSA effects, e.g. serrations appeared at higher temperatures when compared to mild steel. Ultimately, to be able to assess the elevated temperature behaviour of ferritic-pearlitic ductile cast irons at local property level, more testing and data is needed. E.g. silicon alloying in the levels studied in thermal conductivity part of this work and other than ferritic-pearlitic microstructures are still to be fully researched.

5.2 Practical implications

The results presented in work have several practical implications for industries using cast iron components. Improving thermal conduction and thus lowering temperature gradients and ultimate peak temperatures under loading is a particularly potent way of preventing failures. Historically, lamellar graphite irons have been widely used in applications that require good thermal conductivity. A lot of research has been dedicated to quantifying the effects of graphite morphology. As demands for components rise, the lamellar grades are starting to fall short in certain applications. The lamellar morphology is efficient in thermal transport but is not good for ductility nor strength. One of the most common ways of strengthening lamellar graphite irons is to promote pearlite which is done using various alloying elements. However, the increase in strength comes at a cost in matrix thermal conductivity. More ferritic structures combined with lamellar graphite results in quite low strengths as far as common engineering materials go. The work done on ferritic pearlitic ductile irons in this work can offer an alternative approach for applications where lamellar graphite alloys are not sufficient any longer. **Articles I and II** show that certain combinations of silicon alloying and ferrite-pearlite fractions in ductile irons result in materials that have higher thermal conductivities at elevated temperatures. Nodular graphite alloys are more ductile and in almost all cases have higher ultimate tensile strengths compared to lamellar alloys. Thus, control of silicon alloying levels and ferrite-pearlite fractions in the foundry process can give design engineers a powerful tool to really push the envelope in thermally loaded component design. With the models made in this work, one could turn the design process upside down from the current approaches. Rather than simply specifying material grades with only strength requirements and letting the microstructure be something that fulfils those, one could start off with a requirement of thermal conductivity and derive an acceptable window of alloying and microstructure. Essentially, this approach requires use of more simulational tools, but is in no way impossible to attain with current technology. However, in practise foundries have the freedom to tweak alloying with the goal of attaining requirements set by materials standards. An approach where acceptable boundaries in structure and alloying are given by the end-user requires more discourse and data sharing between parties.

In addition to thermal conduction, knowledge of mechanical properties at elevated temperatures and materials' stress response behaviour changes are also

very important in the design of thermally loaded components. Results from **article III** indicate that dynamic strain aging affects the behaviour of both ferritic and pearlitic microstructures and is not exclusive to ferrite. As strain aging is a hardening phenomenon, microstructures containing high amounts of pearlite are particularly susceptible to failure by ductility loss. Essentially, in a design where strength requirements have been set at room temperature and a certain level of softening is assumed at elevated temperatures, DSA induced hardening and its' effects on fatigue life might result in sudden catastrophic failures. As such in certain applications, a choice of a softer variant at room temperature with higher thermal conductivity and more ductility might prove a much better combination. However, to reach such a conclusion one needs to assess properties based on the actual application, as supported literature. Only through simulation of the complete use-case can one decide whether this kind of material optimization is applicable or not. As a sidenote, in certain applications DSA has been even used to improve fatigue life [49, 67].

5.3 Reliability and validity

In scientific endeavours, it is always prudent to critically assess the reliability and validity of made work. This is especially important when the work and results are used to optimize systems. The complexity of the microstructural constituents in cast irons pose challenges especially for generalizing between material properties and testing variables. Thus, it's important to review the results.

The most obvious form of error is in measurement. This dissertation relies heavily on measuring thermal conductivities and uses a lesser used technique at that. Thus, it is important to assess the results from this angle. Figure 22 illustrates measured general behavior of different cast iron types as a function of temperature. The three different thermal conductivity evolutions can be sum-

Figure 22 General behavior of the three different cast iron types studied in this dissertation

marized as follows; 1) lamellar graphite iron conductivity decreases almost linearly 2) spheroidal graphite irons exhibit an initial rise, a subsequent peak and a final decrease towards higher temperatures 3) compacted graphite irons behave similarly to spheroidal, while their conductivity is higher for the same matrix composition. Earlier research that study thermal conductivity of cast irons show quite similar trends and findings [58]. In line with the theory of thermal conduction in cast irons, lamellar graphite cast irons include a heavy emphasis on graphite conduction and only decrease in conductivity towards elevated temperatures. Compacted graphite irons, having partly spheroidized graphite structure, are intermediate forms between fully lamellar and spheroidal graphite irons. All the tests done with lamellar graphite irons at elevated temperatures exhibit the linear trend in thermal conductivity behavior, one test cycle shown in Figure 22, (**LGI**). In the same figure, both the compacted graphite (**CGI**) and spheroidal graphite (**SGI**) test alloy thermal conductivities rise from room temperature until reaching a peak and finally adopting a decreasing trend as with lamellar graphite alloys. If the thermal conductivity test system would be showing similar behaviors for all three, there would naturally be doubts about the accuracy and fitness of the transient plane source method. The test results agree with other studies [58], where spheroidal graphite iron thermal conductivities increase in intermediate temperatures while all tested lamellar graphite iron conductivities decrease with increase in temperature. Thus, no obvious gross errors in the use of the system or method is evident. The general trends for the cases where microstructures completely changed to ausferrite also apply. Drops in conductivity for lamellar graphite irons is smaller than for spheroidal graphite irons. These results are in line with theories of graphite morphology effect on bulk conductivity. Additionally, the accuracy of the measurements themselves should be given thought. The used TPS system standard accuracy is reported to be less than 5%, with repeatability being around 1%. Figure 23 shows compari-

Figure 23 Comparison of measured thermal conductivities and models of Helsing and Grimvall[11], fully ferritic microstructure, spheroidal graphite, at room temperature ($\sim 22^\circ\text{C}$)

son of some measurements from this work, compared with theoretical framework and spheroidal graphite models made by Helsing and Grimvall[12]. The measurements fit very well to the model at room temperature.

One important factor in the reliability of the work presented, is to critically assess the modelling in Article II. The presented equation (4) is a regression model. By definition, regression analysis is based on statistical *estimations* between independent predictor variables and dependent output variables. The

Table 8 Chemical and microstructural composition of alloys used to test equation 4

Alloy	C	Si	Mn	P	S	Cu	CE %	Pearl. (%)	Note
A	3.7	2.5	0.4	0.03	0.009	0.1	4.5	15	GJS 400-15
B	3.6	2.3	0.4	0.03	0.009	0.4	4.4	88	GJS 600-3

Figure 24 Test of regression model (eqn. 4) with alloys in Table 8

predictions are heavily dependent on the range of used variables in the initial modelling. The estimates that fall within the value range are called *interpolations*, while everything that is outside the range are *extrapolations*. Extrapolation is inherently prone to errors and model failures, as differences between the base assumptions in regression analysis, sampled data and behaviour of variables outside the sample range are not known. The model made in this work covers most of the production window of ferritic-pearlitic spheroidal graphite cast irons, so rather small amount of possible combinations fall outside the scope.

Equation 4 was additionally tested with two materials outside of the base input data. Those materials and their microstructural compositions are shown in Table 8, while the deviations between model estimations and measurements are shown in Figure 24. In these cases, the pearlite contents were controlled with small Copper (Cu) additions in the melt. The main function of Copper in cast iron metallurgy is matrix modification, seen as a strong pearlitizing effect. For

the test materials, the estimates and measurements agreed well. The test materials were inside the compositional ranges used in regression modelling, which places the test materials in bounds of interpolation. The model appears to reliably estimate microstructures that have been controlled with minute alloying.

As mentioned earlier, extrapolation outside sample data is often challenging and prone to errors and bias. However, testing a model with variables outside the sample can be an effective way of seeking information of model validity. A particularly usable case for this work is pure iron, for which reference data exists. Using equation 4 for pure iron [$x_1 = 27\text{ }^\circ\text{C}/300\text{ K}$, $x_2 = 0\text{ \% Si}$, $x_3 = 0\text{ \% pearlite}$] yields a result of $\lambda = 74,3\text{ Wm}^{-1}\text{K}^{-1}$. Data from literature for unalloyed iron, practically ferrite, has a thermal conductivity range of around $70\text{--}80\text{ Wm}^{-1}\text{K}^{-1}$ at room temperature [13-15]. Additionally, a function modelled after literature data for carbon steels[68] exists;

$$\lambda_{steel\ 0\% C} = 72,45 \frac{W}{mK} - 0,0563T(^{\circ}C). \quad (5)$$

The base values for unalloyed iron from literature sources and the results from this work are close one another. Although the models differ at elevated temperatures being different in compositions, both agree well on pure iron thermal conductivity at room temperature. Figure 25 - Figure 27 show some of the regression statistics for the thermal conductivity data and equation (4). Broadly taken, the significance of temperature, alloying levels, microstructure is already well established in scientific literature and as such the P-value of the fit is small. R^2 -value of 92% also supports the quality of the data, although does not rule out systematic errors made in measurements. The main effects of parameters shown in Figure 11 and Figure 26 show expected trends and significance. Figure 27 shows the residuals of the regression model. Generally, the residuals are spread out rather evenly, although minor clustering exists. A few large residuals can be seen from the data in the high thermal conductivity side.

Figure 25 Regression summary

Figure 26 Regression model and summary

Figure 27 Regression residual analysis

Mechanical properties, like yield and tensile strength of cast irons, have inherent variability due to their structure. For spheroidal graphite cast irons, properties such as nodularity, nodule count, nodule size and distribution, ferrite and pearlite content, possible micro-porosity etc. affect stress-strain behaviour. Thus, it is critical that analysis and conclusions are not based on single test bars. In the cyclic dynamic strain aging study made in this work, three to five samples were tested for each load-case with the aim to improve statistical quality. With the set test program, this led to roughly 900 separate hysteresis loop sets and data points. The data was averaged for each 'microstructure-temperature-strain rate-strain amplitude'-load case. Standard deviations of peak-to-peak stresses of all the load cases are illustrated in Figure 28. In Figure 28a, most of the higher standard deviations correspond to load cases at the highest test temperatures, which are naturally more challenging experiments to carry out. Figure 28b collects the same data distribution in a slightly different manner. More than 50% of the data points have standard deviations less than 10 MPa and 90% of the data less than 30 MPa. This amount of variability is not a threat to the validity of the trends shown in Figure 19 nor the final conclusions put forward in **article III**. Clear differences are also seen in single tests shown in Figure 13 and Figure 15.

Figure 28 Standard deviation of peak to peak stress by parameter set a) and distribution of standard deviations b)

6. Conclusions

In this chapter, results of the work and their implications are summarized, and future work is outlined. Cast irons have been well researched throughout decades, although certain gaps in knowledge still exists. This thesis took a closer look in thermomechanical regime. Estimation tools for spheroidal graphite cast iron thermal conductivity were made and compared to theory. Straight aging effects on ferritic-pearlitic microstructures were investigated and similar behavior to fully ferritic structures in referenced research was found. The work is viewed through the research questions outlined in section 1.

6.1 Research questions

*How do parameters such as **alloying**, **microstructure** and **temperature** change cast iron thermal conductivity at **elevated temperatures**?*

The results from research done in this work are in line with the general consensus of previous research and literature. The three different thermal conductivity evolutions with temperature can be summarized as follows; 1) lamellar graphite iron conductivity decreases almost linearly, having high starting points 2) spheroidal graphite irons exhibit an initial rise, a subsequent peak and a final decrease towards higher temperatures 3) compacted graphite irons behave similarly to spheroidal, while their conductivities are higher for similar matrix compositions.

Regarding alloying, this work concentrated on Silicon in spheroidal graphite irons and clear differences can be seen in that front. Being in solid solution, it is one of the main parameters affecting bulk thermal conductivity. Silicon alloying being between 1 – 4.5 w-% in standard foundry process gives a large window of conductivity and strength control. Pearlite is a hindrance to thermal conduction, while giving boost to strength. The effect of pearlite on thermal conduction is rather linear. These general trends are discussed in earlier studies, but this work gives a more in-depth tool to estimate properties based on silicon content, ferrite-pearlite contents and temperature.

*Are the results of spheroidal graphite irons promising enough to consider component level optimization with tested parameter space? Does **control of Si in this range allow for equivalent or better thermal conductivities** compared to lamellar graphite alloys?*

Figure 11 neatly summarizes the potential. Silicon alloying levels between 1 – 4.5 w-% in standard foundry process are possible while the effects on graphitization and carbide formation is taken into consideration at metallurgical level. Less silicon results in a promising level of thermal conductivity. Use of cast irons at elevated temperatures is often limited to around 400 °C due to loss of strength and gradual changes in microstructure. At the range of 200 – 300 °C spheroidal graphite irons exhibit a peak in thermal conductivity, which is beneficial for components that are used at elevated temperatures. Some loss of strength due to silicon strengthening might be possible to be counteracted with pearlite, as the effect of pearlite on bulk thermal conductivity is not as high in minor amounts. Thus, an alloy can be tuned to required properties when these parameters are considered in depth. There is clear potential in using spheroidal graphite irons, although gauging the fitness of materials requires a lot more analysis than is commonly done. Such an approach needs to contain many separate inputs from computation fluid analysis to strength calculations to know whether the load-case reflects reality.

Does thermal or mechanical behavior somehow deteriorate at elevated temperatures? Are DSA effects with ferritic-pearlitic and pearlitic structures same with the ones previously shown for ferritic microstructures?

The loss of conductivity towards higher temperatures is evident in all test series done within the scope of this work, being in line with established literature on the matter. However, this work gives new insights on occurrence of dynamic strain aging with mixed ferrite-pearlite microstructures while earlier data on DSA consisted mainly of tests on ferritic matrices. The results clearly show that DSA related effects with certain combinations of temperatures and strain rates is not specific to ferritic structures. As such, DSA needs to be considered in cast iron components that are used at temperatures between 200 – 400 °C. It is case dependent if DSA is fatal or advantageous. Pearlitic structures are at most risk, as loss of elongation can be critical to alloys with less capacity for it in the first place.

6.2 Recommendations for further research

This work gave insights into the field of cast irons at elevated temperatures. However, the made tests naturally didn't cover every portion of the approach outlined in Figure 1. To have a more complete view of the situation, the following topics should be addressed;

Mechanical behaviour at elevated temperatures with different alloying levels

Current data pool of mechanical properties of high and low silicon spheroidal graphite cast irons at elevated temperatures is currently fragmented and work is still required to fill that gap.

Complete DSA tests for different alloying levels

The DSA tests done in this work contained a test alloy in the mid-ranges of silicon composition. Silicon affects diffusion rates of elements tied to DSA and as such to have a more complete view on the topic, test should be conducted also at the low and high ranges of silicon alloying.

Combining everything to FEM – local property approach

As tweaking alloying and microstructure have effects both on physical and mechanical properties, local property approach should be considered as the next step.

Casting simulations and further validation

As even the name implies, cast irons are made with casting processes. To take a local property approach, one needs to know how microstructures evolve inside a component during manufacturing and treatment processes. This is made possible with casting simulation and optimization. An approach where casting parameters, material and component is optimized with a certain objective in mind holds a lot of potential in the future. As noted, a lot of data is needed to completely realise this.

References

1. Zanardi F, Mapelli C, Barella S. Reclassification of Spheroidal Graphite Ductile Cast Irons Grades According to Design Needs. *International Journal of Metalcasting*. 2020;14(3):622-55.
2. Remy L. Fatigue and Thermomechanical Fatigue at High Temperature. In: *Encyclopedia of Materials: Science and Technology* (Second Edition). Oxford: Elsevier; 2001. p. 2866-77.
3. Gundlach RB. Thermal Fatigue Resistance of Alloyed Gray Irons for Diesel Engine Components. *Transactions of the American Foundry Society*. 1979;87:551-60.
4. Roehrig K. Thermal Fatigue of Gray and Ductile Irons. *Transactions of the American Foundry Society*. 1978;86:75-88.
5. Park YJ, Janowak JF. Effects of Molybdenum on Thermal Fatigue Resistance of Ductile and Compacted Graphite Irons. *Transactions of the American Foundry Society*. 1987;95:267-72.
6. Wu M, Campbell J. Thermal Fatigue in Diesel Engine Cylinder Head Castings. *Transactions of the American Foundry Society*. 1998;106:485-95.
7. Park YJ, Gundlach RB, Thomas RG, Janowak JF. Thermal Fatigue Resistance of Gray and Compacted Graphite Irons. *Transactions of the American Foundry Society*. 1985;93:415-22.
8. Szmytka F, Michaud P, Rémy L, Köster A. Thermo-mechanical fatigue resistance characterization and materials ranking from heat-flux-controlled tests. Application to cast-irons for automotive exhaust part. *Int J Fatigue*. 2013;55:136.
9. Numan Y. The Review of Some Commonly Used Methods and Techniques to Measure the Thermal Conductivity of Insulation Materials. In: *Insulation Materials in Context of Sustainability*. Rijeka: IntechOpen; 2016. p. Ch. 6.
10. Autere E, Ingman Y, Tennilä P. *Valimotekniikka 1*. Insinööritieto Oy; 1982.
11. Kempers H. Steelplant ingot molds of nodular iron. *Giesserei*. 1966;53(1):15-8.
12. Helsing J, Grimvall G. Thermal conductivity of cast iron: Models and analysis of experiments. *J Appl Phys*. 1991;70.

13. Williams RK, Yarbrough DW, Masey JW, Holder TK, Graves RS. Experimental determination of the phonon and electron components of the thermal conductivity of bcc iron. *J Appl Phys.* 1981;52(8):5167-75.
14. Williams RK, Graves RS, Weaver FJ, Yarbrough DW. Effect of point defects on the phonon thermal conductivity of bcc iron. *J Appl Phys.* 1987;62(7):2778-83.
15. Smithells CJ, Gale WF, Totemeier TC. *Smithells metals reference book*. 8th ed. / edited by W.F. Gale, T.C. Totemeier. ed. Amsterdam: Elsevier Butterworth-Heinemann; 2004.
16. Gale WF, Totemeier TC, editors. *Smithells Metals Reference Book*. 8th ed. Elsevier; 2004.
17. Olofsson J, Svensson IL. Casting and stress-strain simulations of a cast ductile iron component using microstructure based mechanical behavior. *IOP Conference Series: Materials Science and Engineering.* 2012;33(1):012051.
18. Olofsson J, Svensson IL. Incorporating predicted local mechanical behaviour of cast components into finite element simulations. *Mater Des.* 2012;34(0):494-500.
19. Olofsson J. *Microstructure-based Mechanical Behaviour in Structural Analyses of Cast Components [dissertation]*. Jönköping University School of Engineering; 2012.
20. Olofsson J, Svensson IL. The effects of local variations in mechanical behaviour – Numerical investigation of a ductile iron component. *Mater Des.* 2013;43(0):264-71.
21. Cenni R, Cova M, Bertuzzi G. A methodology to consider local material properties in structural optimization. *Proc Inst Mech Eng Part C.* 2016:2822-34.
22. Larker R. Solution strengthened ferritic ductile iron ISO 1083/JS/500-10 provides superior consistent properties in hydraulic rotators. *China Foundry.* 2009;4(12):343-51.
23. Löblich H, Stets W, Gassner G, Schumacher P. Hoch siliciumhaltiges Gusseisen mit Kugelgraphit toleriert größere Anteile an carbidbildenden Elementen. *Giesserei.* 2012;3:28-32.
24. Stets W, Löblich H, Gassner G, Schumacher P. Solution Strengthened Ferritic Ductile Cast Iron Properties, Production and Application. *Int J Metalcast.* 2014;8(2):35-40.
25. Portevin A, Le Chatelier F. Sur un phénomène observé lors de l'essai de traction d'alliages en cours de transformation. *C R Acad Sci.* 1923;176:507-10.
26. McCormick PG, Ling CP. Numerical modelling of the Portevin—Le Chatelier effect. *Acta Metall Mater.* 1995;43(5):1969-77.
27. Jiang H, Zhang Q, Chen X, Chen Z, Jiang Z, Wu X, et al. Three types of Portevin—Le Chatelier effects: Experiment and modelling. *Acta Mater.* 2007;55(7):2219-28.
28. Rodriguez P. Serrated plastic flow. *Bull Mater Sci.* 1984;6(4):653-63.

29. Lüders W. Über die äusserung der elasticität an stahlartigen eisenstäben und stahlstäben, und über eine beim biegen solcher stäbe beobachtete molecular-bewegung. *Dingler's Polytech J.* 1860;155:18-22.
30. Lomer WM. The yield phenomenon in polycrystalline mild steel. *J Mech Phys Solids.* 1952;1(1):64-73.
31. Cottrell AH, Bilby BA. Dislocation Theory of Yielding and Strain Ageing of Iron. *Proceedings of the Physical Society, Section A.* 1949;62(1):49-62.
32. McCormick PG. A model for the Portevin-Le Chatelier effect in substitutional alloys. *Acta Metallurgica.* 1972;20(3):351-4.
33. Rose KSB, Glover SG. A study of strain-ageing in austenite. *Acta Metallurgica.* 1966;14(11):1505-16.
34. Caillard D, Bonneville J. Dynamic strain aging caused by a new Peierls mechanism at high-temperature in iron. *Scr Mater.* 2015;95:15-8.
35. Caillard D. Dynamic strain ageing in iron alloys: The shielding effect of carbon. *Acta Mater.* 2016;112:273-84.
36. Lui TS, Chao CG. High-temperature properties of ferritic spheroidal graphite cast iron. *J Mater Sci.* 1989;24(7):2503-7.
37. Chen SF, Lui TS, Chen LH. Dynamic Strain Ageing of Ferritic Spheroidal Graphite Cast Iron in the Temperature Range 300 K -700 K. *J Jpn Foundrymen's Soc.* 1993;65(7):535-40.
38. Mouri H, Hayashi M, Wunderlich W. Effect of Dynamic Strain Aging of High Temperature Low Cycle Fatigue of Ferritic Ductile Cast Iron. *Mater Trans.* 2009;50(8):1935-40.
39. Mouri H, Wunderlich W, Hayashi M. New aspects about reduced LCF-life time of spherical ductile cast iron due to dynamic strain aging at intermediate temperatures. *J Nucl Mater.* 2009;389(1):137-41.
40. Watté P, Van Humbeeck J, Aernoudt E, Lefever I. Strain ageing in heavily drawn eutectoid steel wires. *Scr Mater.* 1996;34(1):89-95.
41. Languillaume J, Kapelski G, Baudalet B. Evolution of the tensile strength in heavily cold drawn and annealed pearlitic steel wires. *Mater Lett.* 1997;33(3):241-5.
42. Gonzalez B, Marchi L, Fonseca E, Modenesi P, Buono V. Measurement of Dynamic Strain Aging in Pearlitic Steels by Tensile Test. *ISIJ Int.* 2003;43(3):428-32.
43. Nechtelberger E. The properties of cast irons up to 500 °C. *Technicopy Ltd;* 1980.
44. Huang Z, Wagner D, Bathias C. Some metallurgical aspects of Dynamic Strain Aging effect on the Low Cycle Fatigue behavior of C-Mn steels. *Int J Fatigue.* 2015;80:113-20.

45. Taheri AK, Maccagno TM, Jonas JJ. Dynamic Strain Aging and the Wire Drawing of Low Carbon Steel Rods. *ISIJ Int.* 1995;35(12):1532-40.
46. Calado W, dos Santos O, Castro C, Barbosa R, Gonzalez B. Effect of finishing rolling temperature on fire resistance and dynamic strain aging behavior of a structural steel. *J Mater Sci.* 2008;43(17):6005-11.
47. Queiroz RRU, Cunha FGG, Gonzalez BM. Study of dynamic strain aging in dual phase steel. *Mater Sci Eng, A.* 2012;543:84-7.
48. Bayramin B, Simsir C, Efe M. Dynamic strain aging in DP steels at forming relevant strain rates and temperatures. *Mater Sci Eng, A.* 2017;704:164-72.
49. Kerscher E, Lang K, Vöhringer O, Löhe D. Increasing the fatigue limit of a bearing steel by dynamic strain ageing. *Int J Fatigue.* 2008;30(10):1838-42.
50. Qiu Y, Pang JC, Yang EN, Li SX, Zhang ZF. Transition of tensile strength and damaging mechanisms of compacted graphite iron with temperature. *Mater Sci Eng, A.* 2016;677:290-301.
51. Zou CL, Pang JC, Zhang MX, Qiu Y, Li SX, Chen LJ, et al. The high cycle fatigue, deformation and fracture of compacted graphite iron: Influence of temperature. *Mater Sci Eng, A.* 2018;724:606-15.
52. Qiu Y, Pang JC, Zhang MX, Zou CL, Li SX, Zhang ZF. Influence of temperature on the high-cycle fatigue properties of compacted graphite iron. *Int J Fatigue.* 2018;112:84-93.
53. Gustavsson M, Karawacki E, Gustafsson SE. Thermal conductivity, thermal diffusivity, and specific heat of thin samples from transient measurements with hot disk sensors. *Rev Sci Instrum.* 1994;65(12):3856-9.
54. He Y. Rapid thermal conductivity measurement with a hot disk sensor. *Thermo-chim. Acta.* 2005;436:122.
55. Cingi C, Rauta V, Suikkanen E, Orkas J. Effect of heat treatment on thermal conductivity of aluminum die casting alloys. *Adv Mater Res.* 2012;538-541:2047-52.
56. Rauta V, Cingi C, Orkas J. Effect of annealing and metallurgical treatments on thermal conductivity of aluminium alloys. *Int J Metalcast.* 2016;10(2):157-71.
57. Gustafsson E. Transient plane source techniques for thermal conductivity and thermal diffusivity measurements of solid materials. *Rev. Sci. Instrum.* 1991;62(3):797.
58. Holmgren D. Review of thermal conductivity of cast iron. *Int. J. Cast Met. Res.* 2005;18(6):331-45.
59. Holmgren DM, Diószegi A, Svensson IL. Effects of transition from lamellar to compacted graphite on thermal conductivity of cast iron. *Int. J. Cast Met. Res.* 2006;19(6):303-13.

60. Holmgren D, Diószegi A, Svensson IL. Effects of nodularity on thermal conductivity of cast iron. *Int. J. Cast Met. Res.* 2007;20(1):30-40.
61. González-Martínez R, de la Torre U, Ebel A, Lacaze J, Sertucha J. Effects of high silicon contents on graphite morphology and room temperature mechanical properties of as-cast ferritic ductile cast irons. Part II – Mechanical properties. *Materials Science and Engineering: A.* 2018;712:803-11.
62. Piobert G, Morin AJ, Didion I. Commission des principes du tir. *Mémorial de l'artillerie.* 1842;5:501-52.
63. Okamoto T, Kagawa A, Kamei K, Matsumoto H. Effects of Graphite Shape on Thermal Conductivity, Electrical Resistivity, Damping Capacity and Young's Modulus of Cast Iron Below 500 C. *Trans. Jpn. Foundrymen's Soc.* 1985;4:32-6.
64. Donaldson JW. Mechanical and physical properties of high-duty alloy cast irons. *Foundry Trade J.* 1940;63:141-4.
65. Peet MJ, Hasan HS, Bhadeshia HKDH. Prediction of thermal conductivity of steel. *Int J Heat Mass Transf.* 2011;54(11-12):2602-8.
66. Chen JK, Chen SF. On Thermal Conductivity of an In-Situ Metal Matrix Composite - Cast Iron. *InTech.* 2011.
67. Jost B, Klein M, Beck T, Eifler D. Temperature dependent cyclic deformation and fatigue life of EN-GJS-600 (ASTM 80-55-06) ductile cast iron. *Int J Fatigue.* 2017;96:102-13.
68. Browne KM. ASME International Mechanical Engineering Congress and Exposition on 'Recent advances in heat transfer and microstructure modelling for metal processing'; November 1995; San Francisco, CA. San Francisco, CA: ASME International; 1995.

ISBN 978-952-64-0060-0 (printed)

ISBN 978-952-64-0061-7 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University
School of Engineering
Department of Mechanical Engineering
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**