Electrochemical Studies on Degradation Mechanisms of Electrode Materials in Lithium-Ion Batteries

Taina Rauhala

Electrochemical Studies on Degradation Mechanisms of Electrode Materials in Lithium-Ion Batteries

Taina Rauhala

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Chemical Engineering, at a public examination held via remote technology on 3 December 2020 at 16.

Aalto University
School of Chemical Engineering
Department of Chemistry and Materials Science
Research Group of Electrochemical Energy Conversion

Supervising professor

Professor Tanja Kallio, Aalto University, Finland

Thesis advisor

Professor Tanja Kallio, Aalto University, Finland

Preliminary examiners

Professor Daniel Brandell, Uppsala University, Sweden

Professor Johan Hjelm, Technical University of Denmark, Denmark

Opponent

Professor Ann Mari Svensson, Norwegian University of Science and Technology, Norway

Aalto University publication series

DOCTORAL DISSERTATIONS 177/2020

© 2020 Taina Rauhala

ISBN 978-952-64-0117-1 (printed)

ISBN 978-952-64-0118-8 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-64-0118-8>

Images: Photography (cover, figures 4a, 4c) by Valeria Azovskaya

Unigrafia Oy

Helsinki 2020

Finland

Author

Taina Rauhala

Name of the doctoral dissertation

Electrochemical Studies on Degradation Mechanisms of Electrode Materials in Lithium-Ion Batteries

Publisher School of Chemical Engineering

Unit Department of Chemistry and Materials Science

Series Aalto University publication series DOCTORAL DISSERTATIONS 177/2020

Field of research Physical Chemistry

Manuscript submitted 14 August 2020

Date of the defence 3 December 2020

Permission for public defence granted (date) 21 October 2020

Language English

☐ **Monograph**

☒ **Article dissertation**

☐ **Essay dissertation**

Abstract

Li-ion batteries are the primary power source in small consumer electronics, and they are becoming common in larger systems, such as (hybrid) electric vehicles and stationary energy storage, as well. In the large-scale applications, especially the safety and reliability requirements are strict, and the gradual degradation of Li-ion cell materials over time and use should be prevented. The aim of this thesis was to study the aging of Li-ion battery electrode materials and to investigate different strategies to improve their stabilities.

The aging mechanisms in commercial graphite/LiFePO₄ battery cells were studied at different temperatures. A *post-mortem* analysis of the aged cells revealed that the cell performance decline originated from side reactions at the graphite negative electrode. Furthermore, cycling at low temperatures was found to promote surface and intergranular cracking of the graphite particles, which likely originated from mechanical stress caused by large Li concentration gradients within the particles.

In addition to the graphite negative electrode, the positive electrode materials can be a major source of cell aging. While commercial LiFePO₄ was shown to be stable towards prolonged cycling, the most commonly used transition metal oxides (LiMO₂, *M*=Co, Ni, Mn) are known to degrade especially at high potentials. In this work, small amounts of Mg and Ti co-doping (<1 mol-%) were shown to improve the electrochemical performance and to increase the durability of LiCoO₂ by suppressing the impedance increase during cycling. On the other hand, Li overstoichiometry was found to be detrimental to the performance of LiCoO₂ when cycled at relatively low potentials.

To replace the expensive and often toxic transition metal oxides, organic electrode materials such as conducting polymers have been studied extensively, but a poor cycling stability restricts their use in commercial applications. In the present work, the addition of carbon nanotubes as a support for a common conducting polymer, polyaniline, was shown to improve its cycling stability. The carbon nanotube support inhibited mechanical changes of the electrode, and suppressed the deterioration of the electrical properties of the composite electrodes during cycling.

Cell design also affects the aging of Li-ion batteries. Side reactions related to the faradaic Li-intercalation reaction are a major source of aging in Li-ion cells. By replacing one of the Li-intercalation electrodes with a capacitor-type electrode showing a purely capacitive charge-storage mechanism, the aging rate can be reduced. In this work, the preparation of this type of Li-ion capacitor cells was considered, and the electrode balancing, pre-lithiation of the intercalation electrode and different material combinations were considered.

Keywords lithium-ion battery, electrode material, aging, degradation mechanism, post-mortem analysis, conducting polymer, lithium-ion capacitor

ISBN (printed) 978-952-64-0117-1

ISBN (pdf) 978-952-64-0118-8

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Helsinki

Location of printing Helsinki **Year** 2020

Pages 155

urn <http://urn.fi/URN:ISBN:978-952-64-0118-8>

Tekijä

Taina Rauhala

Väitöskirjan nimi

Elektrodimateriaalien ikääntymismekanismit litiumioniakuissa: Tutkimus sähkökemiallisin menetelmin

Julkaisija Kemian tekniikan korkeakoulu**Yksikkö** Kemian ja materiaalitieteen laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 177/2020**Tutkimusala** Fysikaalinen kemia**Käsikirjoituksen pvm** 14.08.2020**Väitöspäivä** 03.12.2020**Väittelyluvan myöntämispäivä** 21.10.2020**Kieli** Englanti☐ **Monografia**☒ **Artikkeliväitöskirja**☐ **Esseeväitöskirja****Tiivistelmä**

Li-ioniakut ovat yleisin akkutyypin kannettavassa elektroniikassa, ja niiden käyttö on yleistynyt myös suuremmissa sovelluskohteissa, kuten sähkö- ja hybridautoissa sekä stationäärisissä energiavarastoissa. Suuren kokoluokan sovelluksissa akkujen tulee täyttää tiukat vaatimukset turvallisuudesta sekä luotettavuudesta, ja akkumateriaalien heikkeneminen käytössä tulisi estää. Tässä työssä tutkittiin litiumioniakkujen elektrodimateriaalien ikääntymistä sekä keinoja sen ehkäisemiseksi.

Kaupallisten grafiitti/LiFePO₄-akkukennojen ikääntymismekanismeja tutkittiin avaamalla eri lämpötiloissa käytettyjä kennoja. Työssä havaittiin, että kennojen suorituskvyn heikkeneminen johtui pääasiassa sivureaktioista akun grafiittinegatiivielektrodilla. Lisäksi akun latauksen ja käytön matalassa lämpötilassa huomattiin johtavan grafiittipartikkelien pintojen halkeiluun sekä rakeiden väliseen halkeiluun. Tämä aiheutui partikkelien sisäisistä Li-konsentraatioeroista johtuvasta mekaanisesta rasituksesta.

Grafiittinegatiivielektrodin lisäksi myös positiivielektrodimateriaalit voivat olla merkittävä syy kennon ikääntymiseen. Kaupallisen LiFePO₄-materiaalin todettiin olevan stabiili pitkäaikaisessakin käytössä, kun taas yleisimmin käytettyjen siirtymämetallioksidien (LiMO₂, M=Co, Ni, Mn) on huomattu ikääntyvän nopeasti varsinkin korkeissa potentiaaleissa. Tässä työssä osoitettiin, että pieni määrä (<1 mol-%) Mg:ia ja Ti:a seostettuna LiCoO₂:iin parantaa sen sähkökemiallista suorituskvyyä ja kestävyttä sekä vähentää materiaalin impedanssin kasvua kennon käytön aikana. Li-ylimäärä sen sijaan heikensi LiCoO₂:n suorituskvyyä matalissa potentiaaleissa.

Koska siirtymämetallioksidit ovat kalliita ja usein myrkyllisiä, orgaanisia elektrodimateriaaleja kuten sähköä johtavia polymeerejä on tutkittu paljon, mutta huono stabiilius rajoittaa niiden käyttöä kaupallisissa sovelluksissa. Tässä työssä osoitettiin, että lisäämällä hiilinanoputkia tukimateriaaliksi sähköä johtavan polyaniliinin sekaan materiaalin kestävyttä käytössä voidaan parantaa. Hiilinanoputket estivät mekaanisia muutoksia elektrodissa käytön aikana sekä hidastivat materiaalin sähköisten ominaisuuksien heikkenemistä.

Li-ioniakkujen ikääntymiseen voidaan vaikuttaa myös kennon suunnittelun kautta. Faradisen Li-interkalaatioreaktion kanssa samanaikaisesti tapahtuvat sivureaktiot ovat tärkeä Li-ioniakkukennojen ikääntymisen syy. Korvaamalla toinen akun interkalaatioelektrodeista materiaalilla, jonka energianvarastointikyky perustuu puhtaasti kapasitiivisiin ilmiöihin, voidaan ikääntymistä hidastaa. Tällaista kennoa kutsutaan Li-ionikondensaattoriksi, ja tässä työssä perehdyttiin niiden valmistukseen, elektrodien tasapainotukseen sekä interkalaatioelektrodien esilittioimiseen ja testattiin erilaisia materiaaliyhdistelmiä.

Avainsanat litiumioniakku, elektrodimateriaali, ikääntyminen, ikääntymismekanismi, post mortem-analyysi, sähköä johtava polymeeri, litiumionikondensaattori

ISBN (painettu) 978-952-64-0117-1**ISBN (pdf)** 978-952-64-0118-8**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Helsinki**Painopaikka** Helsinki**Vuosi** 2020**Sivumäärä** 155**urn** <http://urn.fi/URN:ISBN:978-952-64-0118-8>

Acknowledgements

The work presented in this thesis was conducted in the Research Group of Electrochemical Energy Conversion at the Department of Chemistry and Materials Science of Aalto University between 2014 and 2019. Financial support from Aalto CHEM, Fortum Foundation and Walter Ahlström Foundation is gratefully acknowledged.

During the years, I had the privilege to work with a number of exceptional scientists. First of all, I want to express my great gratitude to my thesis advisor and supervisor, Prof. Tanja Kallio, for her guidance and for offering me the opportunity to do this thesis in the fascinating and challenging field of lithium-ion batteries. In addition, I would like to acknowledge late Prof. Emer. Kyösti Kontturi, my supervisor in the beginning of this project, who encouraged me to pursue a doctorate in the first place.

I also want to thank all of my co-authors and others who have contributed to the work presented in this thesis. I am especially grateful to my fellow battery researchers Dr. Elina Pohjalainen, Dr. Kirsi Jalkanen, Dr. Mikko Nisula and Ms. Katja Lahtinen for the advice, support and help they have given me. Moreover, a sincere thank you belongs to Adjunct Prof. Kai Vuorilehto for sharing his endless knowledge about batteries and supercapacitors with me during our collaboration. In addition, I want to thank Dr. Olli Sorsa for all the insightful feedback and the many fruitful scientific discussions (as well as the non-scientific ones). Prof. Annukka Santasalo-Aarnio is also acknowledged for introducing me to the world of lithium-ion batteries before the actual thesis project. Moreover, I had the opportunity to instruct several enthusiastic master's thesis workers and research assistants, and I wish to thank all of them for their help with the experiments and for teaching me a lot through their difficult questions.

The warmest thanks belong to my fellow doctoral candidates for the countless fun memories. I am grateful for the interesting discussions and all the laughter during the lunches, coffee breaks and outside of work. Especially, I want to thank my office mate Dr. Timo Weckman for sharing the highlights and struggles of doctoral studies. In addition, thank you Olli, Timo and Lauri for the wonderful introduction to the world of whiskies.

The nice working environment at FyKe was also highly appreciated and for that I'd like to thank all the people, past and present, working there. In addition, I would like to thank Anita Pirhonen for her help in acquiring the equipment and chemicals for the experiments and for knowing the location of anything a researcher might ever need in the building.

Last, but certainly not least, I want to thank all my friends and family for their support and for reminding me that life is much more than just work. Kiitos isälleni kannustuksesta, tuesta ja siitä, että opetit minutkin arvostamaan tietoa ja tiedettä. Kiitos myös kaikista rakennusprojekteista, jotka teorian vastapainoksi ovat opettaneet minulle paljon käytännön taitoja. Kiitos siskolleni Tarulle kaikesta unohtumattoman hauskaista, mitä olemme yhdessä tehneet. Suurin kiitos kaikista miehelleni Antille, joka on tukenut minua silloin, kun asiat ovat olleet vaikeita, ja jonka kanssa olen onnekas saadessani jakaa elämäni. Kiitos!

Taina Rauhala

Houston, TX, October 2020

Contents

List of Abbreviations and Symbols.....	i
List of Publications	iii
Author's Contribution.....	iv
1. Introduction.....	1
1.1 Principles of Li-Ion Batteries.....	2
1.2 Electrode Materials for Li-Ion Batteries.....	3
1.2.1 Negative Electrode Materials	4
1.2.2 Positive Electrode Materials.....	6
1.3 Other Cell Components and Cell Construction.....	8
1.4 Scope of the Thesis.....	9
2. Methods	11
2.1 Electrode Preparation.....	11
2.2 Electrochemical Characterization.....	11
2.3 Material Characterization	13
2.4 <i>Post-Mortem</i> Analysis of Commercial Cells	14
3. Aging of Li-Ion Battery Cells	16
3.1 Aging Mechanisms in Li-ion Cells	17
3.1.1 Negative Electrode Materials	17
3.1.2 Positive Electrode Materials.....	19
3.1.3 Other Cell Components	20
3.2 Temperature Effects on Aging Mechanisms.....	20
4. Doping of Layered Transition Metal Oxides	26
4.1 Cation Doping of LiCoO_2	27
4.2 Comparison of Doping and Variation of Li/Co Ratio.....	28
4.2.1 Electrochemical Performance	28
4.2.2 Cycling Stability.....	30
5. Conducting Polymers as Electrode Materials.....	32
5.1 Conducting Polymers in Electrochemical Energy Storage	32
5.2 Polyaniline as Electrode Material in Li-ion Cells	34

5.3	Stability of Polyaniline in Organic Electrolytes.....	35
5.4	Composites of Polyaniline and Carbon Nanotubes.....	36
5.4.1	Electrochemical Performance.....	37
5.4.2	Cycling Stability and Degradation Mechanisms.....	38
6.	Li-Ion Capacitors.....	41
6.1	Principles of Li-Ion Capacitors.....	42
6.2	Faradaic Materials for Li-Ion Capacitors	43
6.3	Capacitive Materials for Li-ion Capacitors.....	44
6.4	Cells with Carbide-Derived Carbon as Positive Electrode	45
6.5	Effects of Pre-lithiating $\text{Li}_4\text{Ti}_5\text{O}_{12}$	48
7.	Conclusions	50
	References	53

List of Abbreviations and Symbols

BET	Brunauer-Emmett-Teller theory of adsorption
CDC	Carbide-derived carbon
CEI	Cathode electrolyte interface
CMC	Carboxymethyl cellulose
CV	Cyclic voltammetry
DMC	Dimethyl carbonate
EDLC	Electrochemical double-layer capacitor
EDX	Energy dispersive X-ray spectroscopy
EIS	Electrochemical impedance spectroscopy
EV	Electric vehicle
ICP-OES	Inductively coupled plasma optical emission spectroscopy
MWNT	Multi-walled carbon nanotubes
NMP	N-methylpyrrolidone
OCV	Open circuit voltage
PANI	Polyaniline
PVDF	Polyvinylidene fluoride
RT	Room temperature
SBR	Styrene butadiene rubber
SEI	Solid electrolyte interphase
SEM	Scanning electron microscopy
SOC	State of charge
XPS	X-ray photoelectron spectroscopy
XRD	X-ray diffraction

A	Surface area
C	Capacitance
d	Thickness or length
E	Energy
U	Potential, Voltage
ε	Dielectric constant

List of Publications

This doctoral dissertation consists of a summary and of the following publications which are referred to in the text by their Roman numerals

- I** T. Rauhala, K. Jalkanen, T. Romann, E. Lust, N. Omar and T. Kallio, Low-temperature aging mechanisms of commercial graphite/LiFePO₄ cells cycled with a simulated electric vehicle load profile—A post-mortem study, *Journal of Energy Storage* **20** (2018) 344–356. DOI: 10.1016/j.est.2018.10.007

- II** K. Lahtinen, T. Rauhala, S. Räsänen, E. Rautama and T. Kallio, The effect of synthesis modifications on the lithium cobalt oxide using commercial precursors, *Electrochimica Acta* **327** (2019) 135012. DOI: 10.1016/j.electacta.2019.135012

- III** T. Rauhala, F. Davodi, J. Sainio, O. Sorsa and T. Kallio, On the stability of polyaniline/carbon nanotube composites as binder-free positive electrodes for electrochemical energy storage, *Electrochimica Acta* **336** (2020) 135735. DOI: 10.1016/j.electacta.2020.135735

- IV** T. Rauhala, J. Leis, T. Kallio and K. Vuorilehto, Lithium-ion capacitors using carbide-derived carbon as the positive electrode – A comparison of cells with graphite and Li₄Ti₅O₁₂ as the negative electrode, *Journal of Power Sources* **331** (2016) 156–166. DOI: 10.1016/j.jpowsour.2016.09.010

Author's Contribution

Publication I: Low-temperature aging mechanisms of commercial graphite/LiFePO₄ cells cycled with a simulated electric vehicle load profile—A post-mortem study

The author defined the research plan together with the co-authors and carried out the electrochemical half-cell characterizations, SEM and EDX analyses. The XRD, Raman, and ICP-OES analyses were performed by K.J., T. Romann and Mr. Hannu Revitzer, respectively. The full-cell experiments, cell disassembling and sample preparation were carried out together with K. J. (equal contributions). The author interpreted the results and wrote the manuscript, refining it to its final form according to comments from the co-authors.

Publication II: The effect of synthesis modifications on the lithium cobalt oxide using commercial precursors

The author defined the research plan together with the co-authors and performed the SEM experiments. The author planned the electrochemical measurements with K.L. and instructed K.L. in the experiments. EELS measurements were conducted by Dr. Hua Jiang and the Rietveld refinements by E.R. XRD and Raman measurements as well as the analysis of EELS data were conducted by K.L. The manuscript was written by K.L., and the author had an active role in interpreting the electrochemical results and refining the manuscript to the final published form.

Publication III: On the stability of polyaniline/carbon nanotube composites as binder-free positive electrodes for electrochemical energy storage

The author defined the research plan with F.D., O.S. and T.K. and performed the electrochemical measurements, SEM and EDX characterizations. Composite synthesis and Raman spectroscopy were performed by F.D. The XPS measurements, analysis of the results, and the writing of the corresponding chapters of the manuscript were conducted by J.S. The author interpreted the other results and wrote the rest of the manuscript with inputs from F.D. The author refined the manuscript based on comments from the co-authors.

Publication IV: Lithium-ion capacitors using carbide-derived carbon as the positive electrode – A comparison of cells with graphite and $\text{Li}_4\text{Ti}_5\text{O}_{12}$ as the negative electrode

The author had a supporting role in defining the research plan. The author carried out most of the experimental work with help from Mr. Matti Nuutinen, excluding the CDC synthesis and the preparation of the CDC and graphite electrodes. The author interpreted the results together with K.V. and wrote the manuscript under the supervision of K.V. and T.K., with inputs from J.L. The author refined the manuscript based on comments from the co-authors.

1. Introduction

The invention of lithium-ion (Li-ion) batteries can be credited for revolutionizing the use of portable consumer electronics. Their commercialization by Sony in 1991 came after almost two decades of research by scientists including M. Stanley Whittingham, John B. Goodenough and Akira Yoshino, who were awarded the 2019 Nobel Prize in Chemistry for their contributions to the development of the technology.^{1,2} After the market introduction, Li-ion batteries quickly became a standard power source in small devices, such as mobile phones, laptop computers and power tools, due to their superior energy density and long lifetime in comparison to other rechargeable batteries.

At present, Li-ion batteries are utilized also in large-scale applications like electric vehicles (EVs) and stationary energy storage. Concerns about climate change have caused governments all over the world to introduce policies to reduce carbon emissions by decreasing the use of fossil fuels. These policies are driving the electrification of vehicles and the implementation of renewable energy sources. However, the feasibility of both technologies depends on efficient energy storage. EVs require a mobile energy storage system to power them, and the integration of renewables, such as wind and solar power, to the power grid requires reliable energy storage solutions to level the intermittent nature of their power output. In the absence of a more energy-dense technology, Li-ion batteries have become the standard power source in EVs. Moreover, they are becoming more common also in stationary energy storage systems for renewable energy, especially in areas with limited space.

The large-scale applications have brought new requirements for the batteries, and some of them are not yet met by the current Li-ion technology. The cells in small consumer electronics must have a high energy density but they are not that sensitive to cost or lifetime. For EV batteries, energy density, price, safety, durability and fast-charge capability are all essential and need further improvement.^{3,4} In stationary energy storage, in turn, cost, sustainability and reliability are the most critical qualities, whereas the energy density can be lower. Overall, the rapidly growing demand for large batteries has increased concerns about their environmental impacts, as mitigation of climate change requires that the energy storage technologies actually have a positive effect on the climate.

A key parameter affecting especially the cost and the environmental impacts of storing energy in batteries is the lifetime of the cells. Even if the initial price of the system is high, the cost per total energy stored during the life span of the system ($\$ \text{Wh}^{-1}$) might be low if the cells are very durable. Similarly, the lifecycle

emissions arising from e.g. mining the materials, cell production, recycling, etc., are lower if the useful life of the system is high. Furthermore, the safety of the cells too can be affected by the degradation that takes place throughout their service life. Therefore, increasing the lifetime of current Li-ion batteries could mitigate some of the major bottlenecks of the technology in large-scale applications.

The present thesis investigates electrode materials for Li-ion batteries from the perspective of cell lifetime. The characteristics and the durability of Li-ion batteries are largely determined by the electrode materials and the cell design. Therefore, the basic operating principles and material choices for Li-ion batteries are discussed in the following.

1.1 Principles of Li-Ion Batteries

A battery is a device capable of converting chemical energy contained in its active materials directly into electrical energy and vice versa if the battery is rechargeable. In its simplest form it consists of two electrodes in an electrolyte solution and external wiring connecting the electrodes (i.e. an electrochemical cell). Reduction and oxidation of the electrode materials are responsible for the energy storage, while ion transfer in the electrolyte completes the electrical circuit. The operation of a Li-ion battery is based on the shuttling of Li ions between two intercalation electrodes, which can reversibly store the Li ions in their lattices. When the battery is discharged, the negative electrode (the electrode with the lower potential) oxidizes and simultaneously releases Li ions into the electrolyte in order to maintain its electroneutrality. Meanwhile, the positive electrode is reduced and Li ions are inserted into its lattice (Figure 1).⁵ During charging, the reactions occur in the opposite direction.

Figure 1. The operating principle of a Li-ion battery cell with graphite (C_6) as the negative electrode and LiCoO_2 as the positive electrode.

The theoretical energy of the cell is the product of the open circuit voltage (OCV) and the cell capacity i.e. the amount of charge it can store. It is usually reported per the weight of the cell as specific energy (Wh kg^{-1}) or per volume as energy

density (Wh l^{-1}). The cell OCV corresponds to the difference between the equilibrium potentials of the electrochemical reactions on each of the electrodes

$$U_{\text{cell}} = U_{\text{positive}} - U_{\text{negative}}, \quad (1)$$

and hence it depends on the electrode materials. The cell capacity, in turn, is determined by the amount and type of electrode materials. The amount of charge an electrode material can store per weight i.e. the specific capacity of the material (usually measured in Ah kg^{-1}) is determined by the quantity of electrons transferred in the electrode reaction (i.e. the feasible oxidation states of the electrode material) through Faraday's law. Thus, to produce a cell with high specific energy, the redox potential of the positive electrode should be high, the potential of the negative electrode low, and the specific capacities of both materials high. A practical cell also contains several electrochemically inactive components (Section 1.3) that add to the weight and volume of the system, decreasing the energy content.⁵

When current is drawn from the cell, energy losses are caused by polarization from overcoming activation overpotentials, transport phenomena and ohmic losses, which reduces the usable energy. In addition to the choice of electrode materials, these overpotentials are strongly affected by cell engineering and factors such as electrode thickness, particle size and the choice of an electrolyte.

1.2 Electrode Materials for Li-Ion Batteries

The first Li-ion batteries produced by Sony in the early 1990s utilized a LiCoO_2 positive electrode and petroleum coke as the negative electrode.⁵ Since then, the Li-ion technology has seen a steady improvement. The cell level energy density has improved from 200 to 680 Wh l^{-1} , and the specific energy has more than tripled from 80 to 250 Wh kg^{-1} .^{6,7} These advances are mainly the result of developments in the electrode materials (e.g. the introduction of graphite instead of petroleum coke at the negative electrode), but advances in the other cell components, like the electrolyte, as well as the engineering and manufacturing of the cells have had a significant effect, too.^{6,8}

In contrast to other types of batteries, Li-ion cells currently utilize a variety of different electrode materials. Most of the materials used in commercial cells are based on intercalation reactions, during which Li ions are inserted into or removed from a solid host matrix without major changes to the structure of the host. The intercalation compounds are often further classified into one-, two-, and three-dimensional host materials, based on the dimensionality of Li^+ diffusion in the structure.⁹ Materials utilizing alloying and conversion reactions, which involve major structural rearrangements of the host, have also been studied. These materials provide potentially very high specific capacities, but they are currently not durable enough to function as the sole electrode material in commercial cells.

1.2.1 Negative Electrode Materials

Graphitic carbon is currently the most commonly used negative electrode material in Li-ion batteries because it is cheap, non-toxic, has good electrical conductivity and provides cells with relatively high specific energy.⁸ Li ions can be intercalated between the graphene sheets in the graphite structure to yield the end composition LiC_6 (Figure 2b), which corresponds to a specific capacity of 372 mAh g^{-1} . During lithiation (charging), graphite potential changes as a function of the lithiation degree (state of charge, SOC) in a stepwise manner (Figure 2c).^{9,10} This is caused by the reaction mechanism called staging, in which Li ions fill the gaps between the graphene planes in an ordered, stepwise way instead of randomly distributing between all the layers. As the lithiation proceeds, regular numbers of graphene layers are left between the Li layers, giving rise to different intercalation phases. The phases are described with a stage index describing the number of graphene layers between two nearest Li layers. As a simplified description, the plateaus seen in the graphite potential profile correspond to two-phase regions where two different stage intercalation phases coexist, whereas the single-phase areas are seen as a changing potential as a function of the SOC.^{9,10}

Figure 2. Structures and experimental voltage profiles of common negative electrode materials. (a) $\text{Li}_4\text{Ti}_5\text{O}_{12}$ ¹¹ (adapted with permission, under CC BY 3.0, Published (2013) by Elsevier), (b) lithiated graphite¹² (adapted with permission, copyright (2018) American Chemical Society) and (c) half-cell voltage profiles of $\text{Li}_4\text{Ti}_5\text{O}_{12}$ and graphite measured against metallic Li. In (a) and (b), red spheres represent O, green spheres Li, blue spheres Ti and grey spheres C.

The operating potential of graphite is 0.1–0.2 V vs. Li^+/Li , which enables high cell voltages but lies outside of the electrochemical stability window of the organic electrolytes used in the cells, causing the electrolyte to be reduced on the graphite surface. The key invention that allows graphite to still operate as the negative electrode in practical cells was the discovery of suitable electrolytes, which passivate the surface. The passivating layer of electrolyte reduction products formed on the surface of graphite electrodes is known as the solid electrolyte interphase (SEI).^{8,13–15} It is a complex mixture of inorganic (e.g. LiF , Li_2CO_3) and organic (e.g. Li-alkyl carbonates) compounds, and it allows Li ions to migrate through it while blocking the flow of electrons.^{15,16} Ideally, the SEI should

form during the first lithiation of the graphite electrodes (formation cycle) and prevent any further reduction reactions of the electrolyte during the subsequent use of the cells. However, in practice, some reformation and growth of the SEI occurs during the use of graphite-based batteries, which decreases their lifetime. Furthermore, the low operating potential of graphite leads to safety issues. The potential is very close to the reduction potential of Li, causing a risk of Li deposition on the surface of the electrode. Metallic Li poses a safety hazard, because it can cause an internal short circuit within the cell, and it decreases the thermal stability of the system.^{17,18} These issues have led to research to find safer and more durable alternatives for graphite.

At present, the only other negative electrode material in commercial use is lithium titanate, $\text{Li}_4\text{Ti}_5\text{O}_{12}$.^{8,19} It has a spinel structure, in which Li ions can diffuse inside a three-dimensional network of interconnected channels (Figure 2a). The potential profile of $\text{Li}_4\text{Ti}_5\text{O}_{12}$ is extremely flat over almost the entire range of lithiation degrees (Figure 2c), which is considered to result from a two-phase reaction mechanism between the $\text{Li}_4\text{Ti}_5\text{O}_{12}$ phase and the lithiated $\text{Li}_7\text{Ti}_5\text{O}_{12}$ phase.^{19–21} $\text{Li}_4\text{Ti}_5\text{O}_{12}$ shows negligible volume change (less than 0.2%)^{20,21} during the Li insertion and extraction, and its operating potential (1.55 V vs. Li^+/Li)¹⁹ is within the stability window of the commonly used organic electrolytes. Therefore, SEI formation on the surface of $\text{Li}_4\text{Ti}_5\text{O}_{12}$ is diminished and a long cycle life can be expected. Moreover, the high operating potential prevents the risk of Li deposition, making $\text{Li}_4\text{Ti}_5\text{O}_{12}$ a highly safe material and well-suited for high-power applications. However, the specific capacity of $\text{Li}_4\text{Ti}_5\text{O}_{12}$ is only 175 mAh g^{-1} and together with the relatively high operating potential it leads to low cell-level specific energy.

To find negative electrode materials with higher specific capacity, a lot of research has concentrated on materials utilizing alloying and conversion reactions instead of Li intercalation. Alloying materials include for example Al, Sn and Si, from which Si is sometimes mixed in small amounts (typically <5 wt-%) with graphite in commercial cells to increase the specific energy.^{22–24} The specific capacity of Si is potentially very high with a theoretical value at 3500–4200 mAh g^{-1} , and Si has an operating potential range similar to that of graphite. Conversion materials, in turn, include metal oxides such as Fe_2O_3 and Co_3O_4 . The lithiation of these materials leads to the formation of metal nanoparticles in a matrix of Li_2O , yielding theoretical capacities above 1000 mAh g^{-1} .²⁵ However, both of these material types suffer from prohibitively large volume changes during lithiation (for example, around 300% for Si)²³ and show large potential hysteresis during galvanostatic cycling, often leading to poor energy efficiencies.

The ideal negative electrode material in terms of specific energy would be Li metal. Without the host material structure and due to the low operating potential, the energy content of the resulting cells would be very high. The first rechargeable Li-based cells actually used metallic Li as the negative electrode, but safety problems related to uneven deposition of Li (formation of Li dendrites) led to the replacement of metallic Li with graphite.⁸ In addition to the risk of short circuit, the large surface area of the dendrites also caused excessive buildup of SEI, limiting the lifetime of the cells.

1.2.2 Positive Electrode Materials

The positive electrode materials are currently limiting in terms of the gravimetric capacity of Li-ion cells. Modern cells are manufactured in the discharged state, meaning that the positive electrode is in the lithiated form. However, developing materials showing a high capacity for Li storage and good environmental stability in the lithiated state has proven difficult. Lithium cobalt oxide, LiCoO_2 , the original positive electrode introduced by Goodenough *et al.*²⁶ in 1980, is still widely used in consumer electronics today. LiCoO_2 has a layered structure, where Li ions occupy alternating layers between CoO_2 layers (Figure 3a).²³ It has several advantages: it shows good electronic and ionic conductivity, relatively high operating potential (average 3.9 V vs. Li^+/Li), high (volumetric) energy density and relatively simple synthesis process. Moreover, the theoretical specific capacity of the material is high (274 mAh g^{-1}), although only roughly half of the value can be utilized in practice (Figure 3c). If more than 50–60% of the Li in LiCoO_2 is extracted, the structure becomes unstable and releases oxygen, which reacts with the organic electrolyte, potentially leading to a battery fire.^{27,28} Exposure to elevated temperatures may also lead to oxygen release from LiCoO_2 , making it the least thermally stable of the commercially used positive electrode materials.²⁹

Figure 3. Structures and experimental voltage profiles of common positive electrode materials. (a) LiCoO_2 ,³⁰ (b) LiFePO_4 ,³⁰ (adapted with permission, under CC BY 3.0, Published (2014) by The Royal Society of Chemistry) and (c) half-cell voltage profiles of LiCoO_2 and LiFePO_4 measured against metallic Li. In (a) and (b) green spheres represent Li, blue octahedra CoO_6 , brown octahedra FeO_6 and purple tetrahedra PO_4 .

Due to a high price and sourcing issues of Co as well as the stability concerns, other metal oxides with the same layered LiMO_2 ($M = \text{metal}$) structure have been studied. Especially LiNiO_2 was initially investigated as a cheaper, high-capacity alternative to LiCoO_2 , but it was quickly learned to be even less stable.^{8,23} However, substituting part of the Ni with other metals can stabilize the structure.^{29,31,32} This has led to the development of $\text{Li}(\text{Ni}_{1-y-z}\text{Co}_y\text{Mn}_z)\text{O}_2$ and $\text{Li}(\text{Ni}_{1-y-z}\text{Co}_y\text{Al}_z)\text{O}_2$ materials, which have improved safety properties compared to LiCoO_2 .^{29,33} The typical composition of the former is $\text{Li}(\text{Ni}_{1/3}\text{Co}_{1/3}\text{Mn}_{1/3})\text{O}_2$, which is currently the most commonly used positive electrode material in EV

applications.^{8,24} During delithiation of the structure, Ni^{2+} is oxidized to Ni^{4+} , followed by Co^{3+} to Co^{4+} , whereas Mn^{4+} is inactive, providing structural stability for the material.³⁴ The average operating potential is 3.7 V vs. Li^+/Li and the specific capacity is 150–200 mAh g^{-1} depending on the applied potential window.³⁵ The current trend in the development of $\text{Li}(\text{Ni}_{1-y-z}\text{Co}_y\text{Mn}_z)\text{O}_2$ materials is to further reduce the amount of Co in the structure to lower the price of the positive electrodes.⁸ On the other hand, the typical composition of the Al-substituted $\text{Li}(\text{Ni}_{1-y-z}\text{Co}_y\text{Al}_z)\text{O}_2$ materials is $\text{Li}(\text{Ni}_{0.8}\text{Co}_{0.15}\text{Al}_{0.05})\text{O}_2$, which already has a low Co content. The material has an operating potential of 3.7 V vs. Li^+/Li and a usable capacity of roughly 200 mAh g^{-1} enabled by the $\text{Ni}^{3+}/\text{Ni}^{4+}$ and $\text{Co}^{3+}/\text{Co}^{4+}$ redox pairs, whereas Al is electrochemically inactive.^{23,33,36} However, the thermal stability of $\text{Li}(\text{Ni}_{0.8}\text{Co}_{0.15}\text{Al}_{0.05})\text{O}_2$ is rather poor, causing safety concerns.³³

Recently, so-called Li-rich layered oxides have received wide attention due to their potentially high specific capacities ($>200 \text{ mAh g}^{-1}$). Their structure can be described either as a solid solution where some of the extra Li ions are incorporated into the transition metal layer³⁷ or as a nanocomposite of Li_2MnO_3 and LiMO_2 .^{24,38} However, these materials have several disadvantages, such as high first charge irreversible capacity and poor cycling stability.²⁴

In addition to the transition metal oxides, cheaper and safer “three-dimensional” host structures have been developed. Spinel LiMn_2O_4 is an environmentally friendly, non-toxic, low-cost material with three-dimensional interstitial pathways for Li-ion diffusion and improved thermal stability.^{29,39,40} It shows a specific capacity of 120 mAh g^{-1} at 4 V vs. Li^+/Li , but suffers from poor cycling stability. The capacity fade is caused by slow dissolution of Mn^{2+} from the electrode due to the disproportionation reaction of Mn^{3+} to form Mn^{2+} and Mn^{4+} .^{40,41} The reaction is induced by small amounts of HF in the electrolyte produced by reactions between the electrolyte salt LiPF_6 and trace amounts of water impurities. Moreover, deep discharging can cause the material to become unstable due to Jahn-Teller distortion related to Mn^{3+} .^{40,41} Cation doping has been shown to improve the stability,⁴¹ but the use of LiMn_2O_4 in commercial applications has still been limited to mostly blends with transition metal oxides, in which they reduce the overall cost and improve the safety.⁸

Olivine LiFePO_4 is another low-cost, environmentally benign host material, in which Li diffusion occurs within one-dimensional channels (Figure 3b).⁴² It is extremely safe, showing the best thermal stability of the current positive electrode materials:²⁹ due to the strong P–O bond, O_2 release from the material does not occur even at high temperatures.⁴² LiFePO_4 has a relatively high theoretical capacity of 170 mAh g^{-1} , but the operating potential of 3.4 V vs. Li^+/Li is significantly lower compared to the layered transition metal oxides (Figure 3c). Similarly to $\text{Li}_4\text{Ti}_5\text{O}_{12}$, Li extraction from LiFePO_4 proceeds through a two-phase mechanism of the lithiated LiFePO_4 and delithiated FePO_4 phases, resulting in a very flat potential profile. In addition to the rather low specific energy, the drawback of LiFePO_4 is its poor electronic and ionic conductivity.⁴² However, the problem can be mitigated by decreasing the particle size and carbon coating

the particles, and LiFePO_4 has found applications in power tools and electric buses as well as some electric vehicles.²⁴

1.3 Other Cell Components and Cell Construction

In addition to the electrochemically active electrode materials, Li-ion batteries contain several other components that are crucial to the operation of the cells. To produce the electrodes, the active material particles, usually with a size in the micrometer or nanometer scale, are attached to each other and to a metallic current collector using a polymeric binder. The most commonly used binder is polyvinylidene fluoride (PVDF), which requires organic solvents such as N-methylpyrrolidone (NMP) for electrode preparation. Other alternatives that allow aqueous processing have also been developed. For example, water-based mixtures of carboxymethyl cellulose (CMC) and styrene butadiene rubber (SBR) are popular in the preparation of graphite electrodes. The current collectors, in turn, are typically Al foil on positive electrodes and Cu foil on negative electrodes. If the potential of the negative electrode is sufficiently high to avoid the formation of Li-Al alloys, such as that of $\text{Li}_4\text{Ti}_5\text{O}_{12}$, an Al foil can also be used. In addition, the composite electrodes contain conductive additives, most often carbon black or carbon fibers, to improve the electrical conductivity. To maximize the energy density of the cells, the amounts of the conductive carbon and the binder are kept as low as possible, around 2% each in commercial cells.⁴³ The typical thickness of an electrode ranges from few tens to a hundred micrometers.

To prepare a cell, positive and negative electrodes are sandwiched together with a porous separator in between them to prevent a short circuit. The separator is typically a microporous film of a polyolefin such as polyethylene or polypropylene or both, and it is impregnated with a liquid electrolyte. The electrolyte, in turn, is most commonly LiPF_6 salt dissolved in a mixture of organic carbonates, such as ethylene carbonate and dimethyl carbonate (DMC). In addition, commercial electrolytes usually contain additives, such as vinylene carbonate or fluoroethylene carbonate, which react on the surface of lithiated graphite to improve the stability of the SEI.^{44,45} The conductivity of the organic electrolytes is poor compared to most aqueous electrolyte solutions, and therefore, the typical separator thicknesses are in the range of a few tens of micrometers to keep the distance between the positive and negative electrodes low. Furthermore, intensive research efforts have been made towards the realization of solid electrolytes, which could replace the liquid electrolyte-separator combination. As the realization of solid electrolytes with sufficient conductivity has been difficult, some manufacturers have started producing so-called Li-polymer batteries, where the liquid electrolyte is mixed with polymers to form a gel in order to eliminate the free liquid in the cells.⁸ Finally, the electrodes and the separator or gel-electrolyte are wound or stacked to form different types of battery cells, usually of cylindrical or prismatic form.

By connecting the Li-ion cells in series or in parallel, batteries with different output voltage and capacity are obtained. Moreover, Li-ion batteries need external circuitry to protect them from overcharge, overdischarge and harmful temperatures. These battery management systems often monitor also the state-of-health of the battery and determine when the battery has reached the end of its useful life in the specific application.

1.4 Scope of the Thesis

The present thesis investigates electrode materials for Li-ion batteries from the perspective of cell lifetime. Especially, the degradation mechanisms occurring on the electrodes during the use of the battery cells and methods to mitigate performance deterioration were examined. Both commercially available electrode materials (Publications I and II) and novel alternatives (Publication III) were studied, and cell design effects were considered through the preparation of battery-supercapacitor hybrids (Publication IV). The experimental methods used included mainly electrochemical techniques, which were complemented by materials characterization methods.

First, to identify the limitations of the current Li-ion technology, the cycling-induced aging of commercial Li-ion cells was studied. In order to improve the lifetime, it is necessary to understand the aging mechanisms taking place in the cells. In Publication I, the changes induced by electrochemical cycling on the electrodes of commercial graphite/LiFePO₄ cells were investigated through *post-mortem* analysis of aged cells. Because low-temperature performance and tolerance to abusive conditions have been identified as major bottlenecks for EV batteries,³ Publication I concentrated on the degradation of the Li-ion cells occurring during simulated EV usage below room temperature.

In Publications II and III, ways to diminish some of the aging mechanisms of different positive electrode materials were investigated. Doping has been identified as an effective method to improve the cycling stability and enhance the performance. Therefore, the effects of cation doping and variation in the Li/Co ratio (Li doping) on the performance and cycle aging behavior of LiCoO₂ were investigated in Publication II. On the other hand, environmentally friendly alternatives to the transition metal oxides are needed as the demand for large batteries increases. To this end, conducting polymers are an interesting group of materials with potentially high gravimetric capacities and almost metallic conductivity. However, they suffer from stability issues when used as electrode materials in Li-ion cells. In Publication III, the addition of carbon nanotubes as a support for conducting polymers as well as heat treatments of the resulting composite were studied as possible methods to improve the stability. Moreover, the cycling-induced changes on the polymer electrodes were analyzed through a *post-mortem* analysis of cycled half-cells.

In the last part of the work (Publication IV), Li-ion battery-supercapacitor hybrids (Li-ion capacitors) were studied. The motivation of building Li-ion capacitors is to improve the power performance and cycle life in comparison to Li-ion batteries. This is accomplished through changing the energy storage mechanism

of one of the electrodes from a faradaic intercalation reaction to a purely capacitive process. As the capacitive process occurs only on the surface of the electrode, many of the complications of faradaic processes, such as activation overpotentials and volume changes, can be avoided on the capacitive electrode, theoretically reducing the cell resistance and cutting the degradation rate.

To summarize, the present thesis investigates degradation mechanisms in Li-ion batteries and prevention strategies thereof from multiple perspectives ranging from commercial materials to novel alternatives and the effects of cell design.

2. Methods

The experiments presented in this thesis are primarily based on electrochemical techniques, which are complemented and supported by materials characterization methods. An overview of the experimental approaches is given here, while further details can be found in the appended articles. *Post-mortem* analysis as a method to study the aging mechanisms in Li-ion cells is discussed in slightly more detail due to its less standard nature in Li-ion battery research.

2.1 Electrode Preparation

The electrode preparation was mainly accomplished through the standard doctor blade coating technique (Publications II and IV). During the process, the active material, conductive additive (carbon black) and polymer binder (PVDF/CMC-SBR) were dissolved in a solvent (NMP/water) to form a slurry, which was then coated on a metal foil (Al/Cu). The coating thickness was adjusted to obtain the desired electrode loadings, and the calendaring pressure was optimized for best electrochemical performance. Punched electrodes were dried under vacuum (≥ 100 °C) overnight before transferring into an Ar-filled glove box, where the test cells were assembled.

The electrodes in Publication I were collected from disassembled commercial cells (graphite/LiFePO₄, cylindrical, 2.3 Ah), as described in Section 2.4. In Publication III, in turn, electrodes were prepared without any additives through spray painting with an air brush on graphite foil. This method is common in the preparation of catalyst layers for fuel-cell applications and is known to produce layers with high uniformity. Therefore, it was used for the polymer-carbon nanotube composites studied in Publication III to avoid the bundling of the nanotubes and its adverse effects on electrode performance. Regardless of the coating method, care was taken to keep the electrode thicknesses constant to allow meaningful comparison of the studied materials.

2.2 Electrochemical Characterization

The electrochemical methods utilized in this work include galvanostatic charging/discharging, cyclic voltammetry (CV) as well as electrochemical impedance spectroscopy (EIS). During galvanostatic cycling, cells are charged or discharged with a constant current within predetermined voltage limits and the

change in cell voltage is followed as a function of time (or charge). This method gives information on the specific capacity of an active material, its rate capability and cycle life behavior. The CV experiments, in turn, provide additional information on the electrochemical reactions. In this method, the cell voltage is scanned linearly between two vertex values, and the induced current is measured. The current peak maxima, peak widths, peak separations and their evolution with cycling give information on the kinetics of the electrochemical reactions and the stabilities of the materials. On the other hand, EIS can detect changes in the internal resistances of the cells caused by e.g. charge/discharge cycling, and thus it is a commonly used non-destructive method in aging studies. In this method, an alternating voltage (current) impulse is applied on the cell and the current (voltage) response is recorded as a function of the frequency of the stimulus. Due to the differing time scales of the various processes within the cells, EIS allows the different reaction steps, such as mass transport, electronic conduction and charge transfer, to be separated.

The electrochemical tests were mostly performed in laboratory-scale test cells in either a two-electrode or a three-electrode set-up (Figure 4). Both half-cells and full cells were studied. The term “half-cell” refers to cells that use Li metal as the counter electrode. They are useful for evaluating the performance of only one electrode material at a time, as the process that takes place on the Li metal electrode occurs at a constant potential. However, due to the Li plating and stripping reaction on the Li counter electrode, large amounts of SEI are expected to form during prolonged cycling. The electrolyte decomposition species formed on the Li counter electrode can diffuse to the working electrode.^{46,47} Moreover, the increasing impedance of the SEI on Li metal and drying of the electrolyte limit the cycle life of half-cells. Another weakness of the half-cell measurements is that the Li counter electrode is practically an unlimited source of Li ions (as opposed to common positive electrode materials in full cells), and therefore half-cell measurements can mask the detrimental effects of Li-consuming side reactions, if present, on the working electrode. Therefore, long-term cycle-life measurements were conducted in full cells rather than half-cells in Publications II and IV, whereas three-electrode half-cells with excess electrolyte and a Li reference electrode were used in Publication III to mitigate the effects of the impedance increase of the counter electrode.

Due to the high and non-constant impedance of the Li counter electrode, the EIS measurements in Publications I–III were conducted in the three-electrode set-up, except for the full-cell impedance measurements in Publications I and II, which were conducted in two-electrode set-up. In the three-electrode cells (EL-CELL, ECC-Ref), a piece of metallic Li acted as the reference electrode, and it was in contact with the electrolyte at the edge of the separator (Figure 4c, d). The reference electrode set-ups are known to sometimes produce artifacts in EIS measurements, and therefore the three-electrode EIS measurements in this work were used only for qualitative analyses. Moreover, any cells showing clear artifacts in the EIS response, such as inductive loops,⁴⁸ were disregarded. The use of the problematic reference electrode could be avoided by performing the EIS measurements in symmetrical cells with two identical electrodes. However,

such cells do not allow the easy monitoring of the evolution of the EIS response of a single electrode during cycling nor the varying of the SOC, and were thus not used in the present work.

Figure 4. Cell set-ups used in the electrochemical characterizations. (a) Two-electrode 2016 coin cell (Publications I and II) with some of the cell components shown in the background, (b) schematic of the two-electrode set-up, (c) EL-CELL three-electrode cell and (d) schematic of the three-electrode set-up. In Publications III and IV, the EL-CELL cell set-ups were utilized also without the reference electrode.

2.3 Material Characterization

Several materials characterization methods were used in conjunction with the electrochemical techniques to understand the electrode material properties that affect the performance. The morphologies of the particles and electrodes have major effects on the performance of the cells. Therefore, scanning electron microscopy (SEM) was applied to study the particle sizes, morphologies and cycling-induced changes in Publications I–III. On the other hand, the aging of Li-ion battery electrodes is often seen as changes in the compositions of the electrodes and in the crystal structures of the materials. Accordingly, the elemental compositions of electrodes were estimated with energy dispersive X-ray spectroscopy (EDX) in Publications I and III. However, a significant drawback of EDX in Li-ion battery research is its inability to detect light elements including Li. Therefore, inductively coupled plasma optical emission spectroscopy (ICP-OES), which is more sensitive to Li and can give quantitative information on the composition, was used in Publications I and II. However, neither EDX nor ICP-OES can detect the chemical environments or oxidation states of the elements. Therefore, Raman spectroscopy (Publications I–III) as well as X-ray photoelectron spectroscopy (XPS, Publication III) were used for analyzing the surface chemical compositions before and after electrochemical cycling. XPS shows the advantage of being able to directly detect Li. In addition, X-ray diffraction (XRD) was employed to study the bulk crystalline structures and phase purities of the electrode materials (Publication II) and to probe structural changes caused by aging (Publication I). Moreover, the lithiation degrees of LiFePO_4 electrodes in Publication I were analyzed by XRD. The drawback of the method

is that it can only detect crystalline phases and the X-ray scattering from light elements like Li is weak, which adds uncertainty to the analysis of the data.

2.4 *Post-Mortem* Analysis of Commercial Cells

The state-of-health of a commercial battery cell is usually evaluated based on the electrochemical characteristics measured for full cells. Generally, the galvanostatically measured capacity remaining in the cell and cell resistance are used as parameters for the evaluation of the internal condition of the cell. For more sophisticated analysis of the internal changes caused by aging, non-destructive methods such as EIS, incremental capacity analysis and differential voltage analysis have been used. However, these analyses contain contributions from both the positive and negative electrodes, and it is often difficult to distinguish them from each other. Moreover, electrochemical analyses of full cells produce values that represent the average over the whole cell, whereas it has been shown that aging is often non-uniform especially in larger cells.^{49–51,I}

The electrochemical measurements of full cells can be used to distinguish impedance increase, loss of cyclable Li or loss of active materials from the electrodes, but they are usually not able to reveal the mechanism causing the changes. Furthermore, some non-destructive methods to detect Li deposits on graphite negative electrodes have recently been reported, such as in-situ neutron diffraction,⁵² observation of mixed potentials during voltage relaxation after charging⁵³ and detection of high-voltage plateaus during discharging.⁵⁴ However, they often cannot detect irreversibly plated Li or require expensive special equipment not readily available. Therefore, cell disassembling and *post-mortem* analysis is an important tool in the research on the causes of cell degradation. In a *post-mortem* analysis, the cell is carefully disassembled under inert atmosphere and the cell components are separated from each other to enable the analysis of each component individually.

In general, *post-mortem* analyses are complicated by the air and moisture sensitivity of lithiated graphite, metallic Li and electrolyte salt residues.⁵⁵ Moreover, some of the SEI components on graphite electrodes are unstable in air.⁵⁵ This has forced many research groups to develop specialized systems to prevent air exposure or find ways to take the air exposure into account in the analysis of the results. The air sensitivity of especially cycled positive electrodes after cycling can be reduced by rinsing the electrodes with DMC or other common electrolyte solvents. The rinsing removes the electrolyte salt residues that otherwise interfere with the materials characterizations and form corrosive HF with the moisture in air. However, the DMC rinsing is known to dissolve also some of the components of the passivating layers,^{56,57} which should be taken into account in the analysis.

In Publication I, a *post-mortem* analysis was performed on commercial cycle-aged graphite/LiFePO₄ cells. The electrode samples collected from the commercial cells were characterized using electrochemical half-cell testing, SEM, EDX, ICP-OES, Raman spectroscopy and XRD. The half-cell tests were used to identify losses of active material from the positive and negative electrodes separately

and to determine the amount of Li inventory loss. Moreover, the changes in the electrode impedances were analyzed. In general, half-cell measurements of electrodes collected from aged commercial cells are complicated by the sample preparation: half-cell measurements in standard test cells require one-sided electrodes, while the electrodes in commercial cells are usually double-sided. Therefore, the coating on one side of the electrode must be removed e.g. by dissolving it in NMP, which has to be performed extremely carefully in order to avoid damaging the samples. Moreover, sometimes the deteriorated mechanical properties of the aged electrodes have been reported to cause coating delamination from the current collector during cell disassembling.^{49,58} In Publication I, care was taken not to damage the electrodes during the sample preparation and the materials characterization methods were employed to support and explain the results of the electrochemical tests. Raman spectroscopy, XRD and morphology analysis with SEM were used to understand the changes in the electrochemical properties of the electrodes. Moreover, the loss of cyclable Li determined electrochemically was confirmed from the relative amounts of the LiFePO_4 and FePO_4 phases in the LiFePO_4 electrodes analyzed through Rietveld refinement of the XRD data. In the materials characterization in Publication I, the air sensitivity of the samples was taken into account by measuring the Raman spectra in a specially built airtight container with a glass window to prevent air exposure. Moreover, the consequences of the reactions with air were considered in the analysis of the SEM and XRD data for which the air exposure was unavoidable at the time of the experiments.

3. Aging of Li-Ion Battery Cells

The performance of Li-ion batteries degrades over time, which is known as aging. Aging is seen as a decrease of the reversible capacity and an increase of the cell resistance, and it occurs during both operation (cycle aging) and storage (calendar aging). In small consumer electronics, where the innovation cycles are short, the aging of Li-ion batteries is not of major importance. However, in larger systems like EVs and stationary energy storage, the durability of the batteries has significant environmental and economic impacts. Therefore, there is considerable interest to improve the lifetime and cyclability of Li-ion batteries.

Traditionally, it has been considered that a battery has reached the end of its useful life when the usable capacity decreases below 80% of the initial value. This threshold value has been chosen to guarantee safe operation throughout the use of the cells. However, with the high initial cost of the batteries in large-scale applications, there has been a push to decrease the threshold to lower values. Moreover, there is an interest to reuse end-of-life batteries from EV applications in e.g. back-up power, where the performance requirements are less strict. Such “second life” applications require that the safety of the aged cells can be ensured.

In order to improve the durability of Li-ion batteries and to understand the effects of aging on their safety, knowledge of the aging mechanisms taking place inside the cells is needed. Often this knowledge is acquired through *post-mortem* analyses of aged cells, in which the cells are dismantled and each cell component is analyzed separately. In contrast to most non-destructive methods, a *post-mortem* analysis allows the contributions from the two electrodes to be separated from each other and any non-uniformities in the aging to be detected.

This chapter discusses the main aging mechanisms of current Li-ion batteries. Like the energy content of the cells, the aging mechanisms are largely determined by the materials used in the cells. Therefore, the most prevalent degradation processes of common electrode materials are reviewed first. Due to the vast number of different electrode materials under development, this chapter focuses on those that are currently in widespread commercial use. The operating conditions of the cells affect the aging, and thus their impacts are discussed, as well. Aging at elevated temperatures is briefly described but the emphasis of the chapter is on the effects of low-temperature operation, as the performance at cold temperatures has been identified as a major drawback of current Li-ion batteries. The next chapter (Chapter 4) then discusses doping of positive electrode materials as a method to suppress the aging.

3.1 Aging Mechanisms in Li-ion Cells

The aging of Li-ion cells is caused by a complicated interplay of different physical and chemical mechanisms.⁵⁹ Typically, side reactions at the electrode/electrolyte interfaces, structural degradation of the active materials as well as degradation of the non-active components (electrolyte, separators, binder materials or current collectors) are regarded as the most common aging mechanisms.^{59–62} Furthermore, the performance deterioration is affected by the operating conditions of the cells, such as cycling/storage temperature, average SOC, depth of discharge, applied current density and the voltage limits.^{59,60}

The effects of the aging mechanisms in the cells can be divided into three separate degradation modes: (i) loss of Li inventory, (ii) loss of active material from the electrodes, and (iii) impedance increase.^{59,63} In the following, the most important mechanisms leading to these degradation modes on each of the electrodes are reviewed.

3.1.1 Negative Electrode Materials

The typical cycle lives of graphite-based cells range from 1000 to more than 2000 full charge-discharge cycles, depending on e.g. the usage temperature, the voltage range of cycling and the positive electrode material.^{64–66} Usually, the SEI on the surface of the graphite electrode is considered the main origin of the performance decline of the cell.^{60,65–68} Ideally, SEI is formed only during the first lithiation-delithiation cycle of a graphite electrode. However, in reality, minor SEI reformation and growth occur throughout the lifetime of a graphite-based cell. Li insertion into graphite induces a volume change (approximately 10% change in the graphene layer spacing from pristine graphite to LiC_6),⁶⁹ and as a consequence, small cracks form in the SEI during cell usage. This exposes new parts of the graphite surface to the electrolyte, triggering the formation of more SEI. Moreover, changes in the SEI composition and morphology take place, especially at elevated temperatures.^{49,59,66,70} The reformation reactions of the passivating layer consume electrolyte and active Li ions, leading to capacity fade and increases in the cell impedance.⁵⁹ With prolonged cycling, the SEI can penetrate into the pores of the electrode and the separator, resulting in diffusion limitations and a decrease of the accessible surface area of the negative electrode.⁵⁹ Furthermore, the SEI growth is accompanied by the release of gaseous electrolyte decomposition products, which can create bubbles, making parts of the cell inactive.⁶⁵

In addition to the SEI growth, mechanical changes of the graphite electrodes occur during cycling. The volume changes during lithiation and delithiation can damage especially the defect sites within graphite particles.⁵⁹ Large concentration gradients promoted by high current densities or low temperatures accelerate the damage,^{71,1} which can eventually lead to fracturing of the particles.^{51,72} Moreover, the stacking of graphene sheets in graphite changes during lithiation, which can contribute to the stresses in the material.^{9,59} Another detrimental mechanical effect is solvent co-intercalation with Li, which can take place at small

scale in spite of the SEI.⁹ The subsequent reduction of the solvents inside graphite particles produces gas, causing graphite exfoliation and cracking.^{9,15,59} The mechanical damages can eventually lead to loss of active material due to the associated deterioration of electrical contacts.

Another significant aging mechanism on graphite electrodes is the deposition of metallic Li.^{59,73} The operating potential of Li_xC_6 compounds (around 0.1–0.2 V vs. Li^+/Li) is close to the reduction potential of Li. Consequently, instead of intercalating into the graphite lattice, Li may be reduced on the surface of graphite as metallic deposits during cell charging if the graphite electrode polarizes beyond 0 V vs. Li^+/Li .^{54,59,74} Such a situation could be caused by charging at a low temperature, which decreases the diffusion rate of Li in the graphite lattice, or by charging at a high current density.⁷³ High SOC and especially overcharging also promote Li deposition.⁷³ Moreover, the aging of the cells in itself can lead to conditions favoring Li deposition over intercalation: continuous electrolyte decomposition during prolonged cycling can cause cell drying and gas formation, which create areas of high polarization within the cell.^{65,73} Local Li deposits can form in such areas even at high temperatures.^{49,65}

Li deposition accelerates capacity and power fade by two different mechanisms. First, if the metallic Li loses electrical contact to the graphite electrode, it cannot be stripped during the subsequent discharging, and it corresponds directly to a loss of cyclable Li. Second, the Li deposits will grow their own SEI, consuming more electrolyte and Li ions from the cell and increasing impedance.^{54,59} The reversibility of the Li deposition is affected by the morphology of the metallic Li, and recent studies with neutron diffraction have shown that considerable amounts of the deposited Li is intercalated into the graphite structure during relaxation periods after the charging step.^{52,75} Li deposited at a low temperature or high current density tends to have a low specific surface area, and thus it experiences less parasitic reactions with the electrolyte. On the other hand, dendritic lithium deposited at higher temperatures or low currents has a higher surface area and is thus more prone to excessive SEI formation.^{73,74} Therefore, it can lose electrical contact to the graphite electrode rather easily, creating electrochemically inactive “dead” Li.^{50,54,74,76} The dendritic depositions are also more problematic for the safety of the cells, as they may penetrate the separator, causing an internal short circuit.^{54,59,74} However, all metallic Li inside the cells presents a significant safety risk, as it lowers the onset temperature of self-heating during a thermal runaway event.^{17,18}

The addition of small amounts (<5 wt-%) of Si into the graphite electrodes in some commercial cells gives rise to additional aging mechanisms. The large volume changes of Si are problematic, and the presence of Si causes new side reactions with the electrolyte.⁷⁷ The native oxide layer on the surface of Si particles has been shown to react with Li and trace amounts of HF impurities in the electrolyte, leading to the irreversible formation of Li-silicates (mainly Li_4SiO_4) and fluorinated SiO_xF_y .^{78,79}

By replacing graphite with $\text{Li}_4\text{Ti}_5\text{O}_{12}$, much of the degradation on the negative electrode side can be circumvented. Indeed, cycle lives of several thousands of cycles have been reported for $\text{Li}_4\text{Ti}_5\text{O}_{12}$ -based cells.^{80,81} $\text{Li}_4\text{Ti}_5\text{O}_{12}$ benefits from a

negligible volume change during Li insertion/extraction, which prevents the mechanical damage to the particles and electrodes. The high redox potential of $\text{Li}_4\text{Ti}_5\text{O}_{12}$ (1.55 V vs. Li^+/Li) also prevents the risk of Li depositing on the electrode surface and the related aging mechanisms. In addition, $\text{Li}_4\text{Ti}_5\text{O}_{12}$ is thermodynamically stable in contact with the commonly used organic electrolytes, and thus no SEI is expected to form on its surface.¹⁹ However, it has been demonstrated that $\text{Li}_4\text{Ti}_5\text{O}_{12}$ still undergoes side reactions with the electrolyte, which can produce significant amounts of gas inside the cells during prolonged cycling.^{82–85} The origin and extent of the surface reactivity of $\text{Li}_4\text{Ti}_5\text{O}_{12}$ towards the electrolyte are a controversial issue within the scientific community. Some reports suggest that the gas formation is caused by water impurities in the electrolyte, thus highlighting the importance of careful drying of the cell components before assembling.^{86,87} More recent studies have indicated the formation of surface layers on $\text{Li}_4\text{Ti}_5\text{O}_{12}$ after the electrolyte salt decomposes on the electrode surface, followed by solvent decomposition at lower potentials.^{83,84}

3.1.2 Positive Electrode Materials

On the positive electrode side, surface reactivity with the electrolyte, structural changes and microcracking are the most commonly reported aging mechanisms.^{59,88} Similarly to graphite, side reactions with the electrolyte may lead to the formation of a cathode electrolyte interface (CEI) layer, especially at high potentials.^{16,89} However, the CEI differs from the SEI on graphite electrodes in the sense that it is thinner and usually does not fully passivate the surface from further reactions with the electrolyte.^{89,90} Moreover, the composition and thickness of the CEI depend on the positive electrode material and its operating potential window, with higher potentials generally leading to thicker surface films.⁸⁹ For example, the CEI formation on LiFePO_4 , which has a relatively low Li intercalation potential, is considered minor compared to the transition metal oxides.^{16,89,90}

Cracking of the particles after prolonged cycling, which is sometimes referred to as “electrochemical milling” or “grinding”, is also reported for many of the positive electrode materials.⁵⁹ Cracking has been reported for LiFePO_4 ,^{91,92} and LiMO_2 ($M=\text{Co}, \text{Ni}, \text{Mn}$, etc.) transition metal oxides,^{88,93} and it is attributed to high levels of strain on grain boundaries and defects,⁹¹ and anisotropic stresses in constrained particles of polycrystalline aggregates.⁹³ Volume changes occur in LiFePO_4 and LiMO_2 during lithiation and delithiation (6.8% difference in volume between LiFePO_4 and FePO_4 ,⁴² and ~2% difference between LiCoO_2 and $\text{Li}_{0.5}\text{CoO}_2$ ⁹⁴) which contribute to the diffusion-induced stresses. The cracking is promoted by high charge cut-off voltages and high current densities,⁸⁸ whereas recent studies have shown that it can be impeded through the preparation of single-crystalline electrode material particles.^{95,96}

Transition-metal dissolution is another important degradation mechanism for many of the positive electrode materials.^{40,49,97} LiMn_2O_4 is especially well-known to suffer from Mn dissolution due to the disproportionation reaction of Mn^{3+} to form Mn^{4+} and soluble Mn^{2+} .⁴⁰ Moreover, Co dissolution from LiCoO_2

can occur if the electrodes are cycled to potentials above 4.2 V vs. Li^+/Li (corresponding to the removal of >50% of the Li).⁹⁷ Fe dissolution from LiFePO_4 has also been reported as a result of prolonged cycling,⁴⁹ and it is attributed to HF impurities inevitably present in LiPF_6 -based electrolytes.⁹⁸ The transition-metal dissolution is promoted by high temperatures, and it can be suppressed by coating the particles with e.g. carbon.⁹⁰ The transition-metal dissolution degrades the positive electrode materials, thereby reducing the capacity. However, more critical to the aging of the Li-ion cells is that the dissolved transition metal ions migrate to the graphite negative electrode and reduce on the graphite surface. Thus, they are incorporated into the SEI, where they increase the electrical conductivity and thereby accelerate the growth of the layer, leading to loss of cyclable Li and resistance increase.^{59,99}

For the layered transition metal oxides, structural changes of the material during cycling are also a common aging mechanism.⁶² For example, spinel-phase formation has been reported especially on the surfaces of LiMO_2 particles.^{93,100} The phase transitions are promoted by high extent of delithiation, and they can lead to the release of O_2 from the structure.^{88,101} Structural changes can occur in LiMn_2O_4 , as well, especially at low and high states of charge.⁵⁹ In contrast, irreversible formation of new phases is not expected for LiFePO_4 .

3.1.3 Other Cell Components

In addition to the changes in the active electrode materials, aging can affect the electrochemically inactive components in the cell. Aging of the electrolyte can be caused by excessive side reactions on the electrode surfaces. As side reactions on both electrodes consume electrolyte, Li-ion cells can eventually dry out during prolonged cycling, which causes the ohmic resistance of the cell to increase.⁶⁵ Moreover, excessive SEI growth can lead to clogging of the separator pores, causing diffusion limitations within the cell. The volume changes of the active materials, in turn, can lead to the degradation of the composite electrode itself. This can be aggravated by degradation of the binder, which may lead to mechanical instability of the electrodes.⁵⁹ Contact losses (electrical or mechanical) between the particles or between the particles and the current collector also lead to capacity loss and higher cell resistance. Corrosion of the metallic current collectors is possible, as well, especially during overdischarge events.⁵⁹

3.2 Temperature Effects on Aging Mechanisms

The effects of elevated temperatures on the aging of Li-ion cells have been studied widely, and hot environments are known to be problematic during both battery operation and storage. High temperatures promote the reaction kinetics of the Li intercalation/deintercalation but they also increase the rate of the parasitic side reactions, thereby accelerating the aging rate.⁶⁷ They are especially harmful to the stability of the SEI on graphite electrodes, which starts to decompose around 60–80 °C.⁷⁰ Moreover, the organic SEI components (e.g. Li-alkyl carbonates) are transformed into more stable inorganic products (e.g. LiF , Li_2CO_3) at high temperature, which reduces the ionic conductivity of the SEI,

thus increasing cell impedance.^{59,70} Transition-metal dissolution from the positive electrode is also accelerated at high temperature, promoting the growth of more SEI.

In contrast, low cell temperatures slow down the reactions at the electrode-electrolyte interfaces, thereby also slowing the growth of the passivating layers, transition-metal dissolution and related phase changes. Low temperatures are especially problematic during the charging of graphite-based cells, because they promote the Li deposition on graphite negative electrodes: the hindered kinetics of the Li intercalation reaction and slow Li diffusion within the graphite lattice can cause Li deposition to become favorable over Li intercalation into graphite.⁷³ Accordingly, Li deposition on graphite is considered the main aging mechanism of Li-ion cells cycled in cold environments. Contrary to graphite-based cells, low-temperature operation is not expected to give rise to additional aging mechanisms in cells with $\text{Li}_4\text{Ti}_5\text{O}_{12}$ negative electrodes due to the high operating potential and low volume changes of $\text{Li}_4\text{Ti}_5\text{O}_{12}$.¹⁰²

In the present work (Publication I), the aging mechanisms of commercial graphite/ LiFePO_4 cells (cylindrical, 2.3 Ah) cycle aged at three different temperatures of $-18\text{ }^\circ\text{C}$, $0\text{ }^\circ\text{C}$ and room temperature (RT) were compared. Moreover, a cell calendar aged for the same period of time as the length of the cycle aging tests was studied as a reference. The cycle aging results, which are not a part of the present thesis, have been published in a preceding article.⁶⁴ During the aging, the cells were cycled using a load profile simulating battery usage in an EV (highest charging current pulse rate 2C and highest discharge rate 4C), in order to obtain results that are relevant for EV applications.⁶⁴ The task performed in this work was the investigation of the cycling-induced degradation in the cells through a *post-mortem* analysis.

$0\text{ }^\circ\text{C}$ is often regarded as the threshold temperature below which the probability of Li plating increases significantly during charging. However, the tendency for Li plating depends strongly on the cell design (e.g. capacity ratio of the positive and negative electrodes), and the properties of the graphite electrode (e.g. surface area and particle size) and can therefore occur at higher temperatures, as well.⁶⁷ The cycle-aging performance of the cells studied in this work showed that the reduction in temperature from room temperature to $0\text{ }^\circ\text{C}$ caused about a 10% decrease in cycle life, from 2071 equivalent full cycles to 1850 cycles.⁶⁴ In contrast, cycling at $-18\text{ }^\circ\text{C}$ caused a dramatic 90% decrease in cycle life to only 185 cycles.⁶⁴ When the cells were disassembled, the graphite electrodes of cells cycled at $-18\text{ }^\circ\text{C}$ were observed to be completely covered by a uniform layer of metallic Li, demonstrating that the electrodes were polarized well beyond the reduction potential of Li during the cycling and that Li plating was the cause of the high rate of aging. On the other hand, only minor Li deposits were observed on the graphite electrodes disassembled from cells aged at $0\text{ }^\circ\text{C}$, in line with the relatively good cycle aging performance of the cells.

Electrochemical analysis of the graphite/ LiFePO_4 full cells prior to disassembling revealed that the cycling-induced aging was seen mainly as capacity fade, whereas the impedance increase was small. To investigate the causes of the capacity fade, electrochemical half-cell testing of positive and negative electrode

samples recovered from the aged full cells was conducted (Figure 5). The analysis revealed that significant loss of active material had not taken place during the full-cell cycling on either of the electrodes in any of the cells. XRD analysis further supported the conclusion, as no changes of the bulk structures of the electrode materials were found. However, minor loss of graphite active material was observed, especially for the cell cycled at 0 °C (capacity loss of 9% or less), but it was not considered high enough to decrease the cell capacity. This is because the graphite negative electrode was oversized compared to the positive electrode, which is a normal practice designed to limit Li deposition in commercial cells.

Figure 5. Half-cell testing of graphite and LiFePO₄ electrodes recovered from commercial cylindrical 2.3 Ah graphite/LiFePO₄ cells cycle aged at different temperatures (Publication I). The end-of-life condition was 80% of initial room temperature capacity remaining at 1C. The rate capability performance of the graphite electrodes collected from (a) outer part of the electrode jellyroll; (b) inner part of the electrode jellyroll, and LiFePO₄ electrodes recovered from (c) outer part of the electrode jellyroll; (d) inner part of the electrode jellyroll.

Analysis of the lithiation degrees of the LiFePO₄ positive electrodes^a (Figure 6) showed that the capacity loss was caused by loss of cyclable Li at all temperatures. It was attributed to SEI growth on graphite at room temperature and 0 °C, and to the Li deposition at -18 °C and 0 °C. SEI thickening and Li deposition both contributed on the graphite electrode cycled at 0 °C.

The degradation within relatively large commercial cells is often non-uniform throughout the electrode stacks or jellyrolls.^{49–51,74} In the present work, the loss of active Li was higher in the outer parts of the electrode jellyroll in all of the cells. However, this was partly attributed to cell-design effects, as some local Li deposits were found in all of the cells near the current collecting tabs, and the

^a The cells were completely discharged prior to analysis, ensuring that all of the cyclable Li was intercalated into the LiFePO₄ electrodes.

deposits increased towards the outer surface of the cell. However, non-uniformities in the aging of the different parts of the cells was considered likely, too. The graphite electrodes were visually uneven and the (non-local) Li deposits on the graphite electrodes of the cells cycled at 0 °C and –18 °C appeared more severe in the outer parts of the electrode jellyrolls. Moreover, the loss of graphite active material from the cell cycled at 0 °C was more severe towards the core of the electrode jellyroll. The non-uniform aging was considered to result from variations in the current density and potential distribution within the cells. Temperature and pressure gradients are known to occur within cylindrical cells due to the decreasing winding radius of the jellyroll towards the core and the limited heat-transfer rate of the cells.^{50,74}

Figure 6. Lithiation degrees of LiFePO₄ electrodes recovered from commercial cylindrical 2.3 Ah graphite/LiFePO₄ cells cycle aged at different temperatures (Publication I). The lithiation degrees were determined from half-cell measurements for the inner and outer parts of the electrode jellyroll and from XRD data for the middle of the jellyroll. Inner part refers to a location close to the cell core and outer part to an area close to the outer surface of the cell within the electrode jellyroll.

Low-temperature cycling can also promote large concentration gradients within the active material particles. The migration of Li ions within the electrolyte is usually considered fast compared to the diffusion within the solid matrix of the electrode materials. Low temperatures decrease both the conductivity of the electrolyte and the Li diffusion rate within the active material. Therefore, significant concentration gradients between the surface and bulk of the active material particles can form during cycling at low temperatures. As the lithium insertion/extraction causes a volume change in many of the active materials, the concentration gradients cause diffusion-induced stress within the particles and can eventually lead to fracturing of the particles.^{71,103} For example, in a study by Takahashi et al.⁷² graphite particle cracking was detected by SEM after 100 cycles at a temperature of –10 °C and a high current rate of 10C.

In the present work, Raman analysis of the graphite electrodes disassembled from the cycle-aged graphite/LiFePO₄ cells, shown in Figure 7, showed a slightly increased amount of disordered carbon for the electrodes cycled at –18 °C. The ratio of the integrated D (1330 cm^{–1}) and G (1580 cm^{–1}) band intensities (I_D/I_G) increased from 0.39 for the reference sample to 0.56 for the –18 °C sample. The

disordering of the graphite surfaces was attributed to the mechanical damage caused by the diffusion-induced stress promoted by low cycling temperature. Moreover, it was hypothesized that the Li plating may also have contributed to the damage, as it has been shown to take place not only on the graphite particle surfaces but also within the pores inside the graphite particles.¹⁰⁴ XRD analysis, however, indicated that the bulk structure of the graphite did not change significantly with low-temperature cycling, and thus the damage was concluded to occur mainly on the surfaces of the particles and along the grain boundaries.

Figure 7. Raman spectra of graphite electrodes recovered from commercial cylindrical 2.3 Ah graphite/LiFePO₄ cells cycle aged at different temperatures (Publication I). The three extra bands seen in the spectrum of the $-18\text{ }^{\circ}\text{C}$ sample are ascribed to Li₂CO₃ (1090 and 1480 cm⁻¹)^{105,106} and Li₂C₂ or Li-acetylide (Li-C≡C-X) species (1850 cm⁻¹).^{107–110} The presence of Li₂CO₃ is attributed to the SEI on the metallic Li deposits, whereas the origin of the Li-acetylide/carbide species has been debated in the literature. Recent articles^{107,109} have identified it as a component of the SEI on Li metal, while earlier studies¹¹⁰ ascribed its presence to decomposition products of carbonate species formed due to local laser heating during the Raman measurement.

The increased disordering of the graphite electrodes aged at $-18\text{ }^{\circ}\text{C}$ was accompanied by a surprising improvement of the rate capability performance of the electrodes in half-cell testing (Figure 5a, b). This was attributed to the cracking of the graphite particles. Surface cracking and the introduction of defects increase the amount of sites for Li intercalation into the graphite lattice.^{111,112} Li intercalation into graphite is known to occur mainly through the edge planes and defect sites instead of the basal planes.^{9,111,112} It should be noted, however, that the performance improvement detected in half-cell testing was not detected in the electrochemical characterization of the full cells. This could be affected by the sample preparation, as DMC rinsing may have removed some of the SEI present during full-cell testing. Moreover, the rate capability performance of the full cells was not tested prior to disassembling.

At the positive electrode side, low-temperature operation is generally considered to suppress the aging due to the lowered rate of side reactions. However, some studies have indicated that low-temperature operation could indirectly promote the aging of transition metal oxides.^{113,114} This has been attributed to the harmful effect of the lowered lithiation degree of the positive electrode

caused by Li plating on the graphite negative electrode.¹¹³ However, other studies with LiMO_2 positive electrodes found no evidence of such effects.⁶⁷ In the present study, no indications of aging were detected on the LiFePO_4 positive electrodes apart from the lowered degree of lithiation, which was caused by side reactions on the graphite negative electrode. None of the common aging mechanisms of particle cracking, Fe dissolution, excessive CEI formation or structural changes took place on the LiFePO_4 electrodes. Accordingly, the study confirmed that the graphite electrode was the source of aging in the graphite/ LiFePO_4 cells.

Finally, it should be mentioned that the true usage conditions of Li-ion batteries are more complicated than those created in laboratory tests. The test are often designed to accelerate the aging rate through e.g. large depth of discharge or high temperatures. Real-life batteries are exposed to temperature variations, vibration and external pressure, and spend a large portion of the time idle. However, the laboratory tests give valuable information about the effects of various usage parameters, and the information from the tests can be utilized in modeling the aging response in real-life applications.

4. Doping of Layered Transition Metal Oxides

As shown in Chapter 3, the graphite negative electrode is the electrode limiting the lifetime of graphite/LiFePO₄ cells. However, in spite of its exceptional stability and safety, LiFePO₄ is presently being phased out in EV applications due to its low energy density.¹¹⁵ The currently preferred positive electrode materials are based on the layered transition metal oxides (LiMO₂, *M*=Co, Ni, Mn, etc.). When these materials are used in the cells, the aging scenario changes, and the degradation on the positive electrode can become the factor limiting the useful life of the cells. Intensive research efforts have been deployed to improve the stability and the electrochemical performance of the transition metal oxides through modifications of the structure. The studied methods include optimization of the particle size and morphology, as well as modifications of the chemical compositions of the materials. The chemical modifications can be further divided into three categories: (i) doping, (ii) chemical gradient compositions and core-shell structures, and (iii) coatings.⁸⁸ Sometimes more than one of the methods are combined in one product.

Doping and substitutions of the transition metals with other cations are the most extensively studied approaches to improve the structural stability of the transition metal oxides. The development of the widely used Li(Ni,Co,Mn)O₂ and Li(Ni,Co,Al)O₂ materials are examples of successful adoption of the substitutions. However, the dopants and substituents are often electrochemically inactive, and thus they can decrease the reversible capacity of the doped materials. Therefore, core-shell structures and concentration gradient compounds as well as coatings, such as Al₂O₃, have been developed to improve the durability without compromising the capacity. The downside of the coatings and chemical gradient compositions is that they complicate the otherwise rather simple (solid-state) synthesis process of the transition metal oxides. Thus, they are not as widely used as the doping strategy. In addition, single-crystal materials have recently shown exceptional stabilities.^{95,116} However, the large primary particle size of these materials leads to slightly smaller specific capacity and lower rate capability compared to the more conventional polycrystalline materials.

This chapter discusses cation doping of layered transition metal oxides, mainly LiCoO₂, as a method to improve the cycling stability of the materials. Even though LiCoO₂ is not widely used in large applications, it serves as a good

model compound to study the effects of doping on the stability of layered transition metal oxides due to its simpler structure compared to the substituted oxides.

4.1 Cation Doping of LiCoO₂

LiCoO₂ has a highly ordered structure (space group $R\bar{3}m$) in which Li and Co occupy alternating layers between O layers (see also Figure 3 in Chapter 1). The Co in the structure exists in the trivalent form, oxidizing to Co⁴⁺ during Li extraction. During delithiation, Li_xCoO₂ also undergoes a sequence of phase transitions. The first is an insulator-metal transition, which leads to the formation of a two-phase region at potentials around 3.9 V vs. Li⁺/Li ($0.75 \leq x \leq 0.93$).⁹⁴ A second transition, an order-disorder transition of the Li ions, occurs after further delithiation at around $x=0.5$ in Li_xCoO₂ at potentials of 4.0–4.2 V vs. Li⁺/Li.⁹⁴ Both of these transitions are reversible and take place during normal operation of the material within the traditionally used potential window up to 4.3 V vs. Li⁺/Li.

Lately, research on LiCoO₂ has concentrated on enabling higher charging potentials. The upper cutoff potential of LiCoO₂ has been increased from the initial value of 4.2 V vs. Li⁺/Li, which roughly corresponds to extraction of half of the Li in the structure ($\sim 140 \text{ mAh g}^{-1}$), to a maximum of 4.5 V vs. Li⁺/Li, corresponding to the extraction of 0.7 Li per formula unit ($\sim 190 \text{ mAh g}^{-1}$).^{117,118} The upper potential limit of the structural stability is considered inherently determined by the energies of the Co 3d and the O 2p bands: the extraction of Li beyond a certain level leads to not only the oxidation of Co³⁺ to Co⁴⁺ but will also involve the O 2p band.^{28,101,119} This results in partly irreversible phase changes in the material accompanied by a rapid decrease of the *c*-axis parameter caused by a decrease of the repulsion between adjacent CoO₂ layers.^{28,97,101} This can induce mechanical stress leading to the formation of cracks and the release of oxygen from the structure.^{28,97,101} Doping has been suggested as a method to suppress these high-potential phase changes and to inhibit the resistance increase during cycling.^{117,118}

Doping LiCoO₂ with various cations, such as Mg,^{117,120} Al,^{121,122} Mn¹¹⁷ and Ti,^{120,123} has proven to be a successful approach to improve the electrochemical and thermal stability. The effects of the different dopants depend on the valence and size of the cations.^{88,118} Generally, divalent dopants can occupy both the transition metal site and the Li site in the layered structure.^{88,124} When incorporated on the Li site, the electrochemically inactive dopants are considered to act as sort of “pillars”, stabilizing the structure against collapsing from the removal of large amounts of Li.^{88,118} Moreover, divalent dopants such as Mg²⁺ have been shown to improve the electronic conductivity and suppress the phase transitions in Li_xCo_{1-y}Mg_yO₂.^{125–127} Trivalent and tetravalent dopant cations, in turn, usually occupy the transition metal sites and can increase the lattice spacings and reduce the band gap, increasing the electrical conductivity.^{88,124} In addition to the cationic substitutions, anion doping with e.g. F, Cl and S on the oxygen site has been studied, but to a much lesser degree compared to the cation doping.⁸⁸

The drawback of doping with inactive cations is that they usually decrease the reversible capacity of transition metal oxides, because they “lock in” some of the otherwise cyclable Li ions. Moreover, the substitution of divalent cations such as Mg^{2+} for Co^{3+} in LiCoO_2 adds inactive cations and causes either a corresponding amount of the initial Co^{3+} to be oxidized to Co^{4+} or the formation of oxygen deficiency.^{117,128} To maintain the charge balance of the Co sites, an equivalent amount of a tetravalent cation, such as Ti^{4+} or Mn^{4+} , has been co-doped with Mg^{2+} in some studies.^{117,120,129}

Another method suggested to suppress the phase transitions in LiCoO_2 is the preparation of Li overstoichiometric ($\text{Li}/\text{Co} > 1$) materials.¹³⁰ The extra Li ions in the structure occupy the Co site and the electroneutrality of the system is fulfilled by oxygen vacancies.¹³¹ As the extra Li sits on the Co site similarly to other cationic dopants, the Li-excess materials can be considered Li-doped LiCoO_2 . Even at relatively low amounts of Li excess ($\text{Li}/\text{Co} \approx 1.08$), the potential features related to the two-phase domain and order-disorder transitions occurring in LiCoO_2 below 4.3 V vs. Li^+/Li are suppressed.^{130–132} Moreover, recent studies by Duffiet *et al.*¹³⁰ have shown that the excess Li affects the phase transitions also at higher potentials. Li-doping has also been shown to increase the conductivity of LiCoO_2 , albeit to a smaller extent than e.g. Mg doping.¹²⁵ However, the sloping potential profile of Li-excess LiCoO_2 at the end of discharge (lithiation) can lower the measured specific capacity due to the potential cut-off value being met earlier.¹³¹ Compared to the other doping strategies, Li overstoichiometry is a relatively unexplored area within LiCoO_2 research.

4.2 Comparison of Doping and Variation of Li/Co Ratio

In Publication II, the electrochemical performance and cycling stability of LiCoO_2 materials modified through either Li overstoichiometry ($\text{Li}/\text{Co} > 1$) or Mg and Ti co-doping were compared to stoichiometric LiCoO_2 . The materials were prepared using the same Co_3O_4 precursor and the same solid-state synthesis process in order to ensure the comparability. The Li/Co ratios were determined by ICP-OES for the stoichiometric ($\text{Li}/\text{Co}=0.965$), over-lithiated ($\text{Li}/\text{Co}=1.003$) and Mg-Ti doped materials ($\text{Li}/\text{Co}=0.977$), which are hereafter referred to as $\text{LiCoO}_2(\text{S})$, $\text{LiCoO}_2(\text{R})$ and $\text{LiCoO}_2(\text{D})$, respectively. The amounts of Li excess and dopants (0.5 mol-% of Mg and 0.2 mol-% Ti) used in the present work were relatively low compared to earlier reports^{117,125,127,130,131} in which Li/Co ratios up to 1.08 and doping levels of 1–6 mol-% have been investigated.

4.2.1 Electrochemical Performance

The Li/Co ratio and the Mg-Ti doping were found to have a clear effect on the electrochemical characteristics of the LiCoO_2 materials. The cyclic voltammograms of the stoichiometric, Li-rich and Mg-Ti doped LiCoO_2 are shown in Figure 8. A pair of peaks at 3.9 V vs. Li^+/Li , related to the insulator-metal transition, and potential features at 4.05 and 4.20 V vs. Li^+/Li caused by the Li order-disorder transitions around $x=0.5$ in Li_xCoO_2 were seen for all of the materials. These features are characteristic of stoichiometric LiCoO_2 . However, the high-

potential features were clearly suppressed in the Li-overstoichiometric material, as expected for a Li-excess Li_xCoO_2 .^{130,131} The Mg-Ti doping also somewhat suppressed the peaks in the Li extraction scan, in line with previous works, which have shown that Mg,¹²⁷ Mg-Mn,¹¹⁷ Ti¹²⁰ and Mg-Ti¹²⁰ doping is expected to diminish the phase transitions. The largest difference in the materials electrochemical responses was the rather wide lithium insertion peak at 3.9 V vs. Li^+/Li for $\text{LiCoO}_2(\text{S})$ and $\text{LiCoO}_2(\text{R})$ compared to $\text{LiCoO}_2(\text{D})$. The behavior was assigned to the Li-overstoichiometry in $\text{LiCoO}_2(\text{R})$ as well as to increasing resistance caused by either structural damage or electrolyte oxidation on the surface of LiCoO_2 during the high-potential operation or both. The Mg-Ti doping was shown to clearly prevent the behavior.

Figure 8. Cyclic voltammograms of the stoichiometric $\text{LiCoO}_2(\text{S})$, Li-overstoichiometric $\text{LiCoO}_2(\text{R})$ and Mg-Ti doped $\text{LiCoO}_2(\text{D})$ materials measured in half-cells using a scan rate of 0.02 mV s^{-1} (Publication II).

The synthesis modifications affected the reversible capacities measured for the LiCoO_2 variants, as well. In a potential range of 3.0–4.5 V vs. Li^+/Li , the stoichiometric and overlithiated materials showed similar specific capacities ($193\text{--}195 \text{ mAh g}^{-1}$), whereas the Mg-Ti doped material showed a slightly higher capacity (204 mAh g^{-1}). The result was surprising, as most studies in the literature have reported a decrease in capacity with doping.^{117,128,129} Moreover, the amount of doping was too low to improve the specific capacity through decreasing the molecular weight of the compound. Accordingly, the improvement was attributed to a better electrical and ionic conductivity of the Mg-Ti doped LiCoO_2 , as the Mg-Ti doping also significantly improved the rate capability performance of the material (see Publication II). Indeed, electron energy loss spectroscopy of the pristine LiCoO_2 powders showed that the Co in the doped $\text{LiCoO}_2(\text{D})$ had a slightly lower valence than the Co^{3+} in stoichiometric LiCoO_2 . The reduction of part of the Co^{3+} to Co^{2+} was attributed to the Ti^{4+} doping on the Co site, and it was considered to increase the electronic conductivity of the material due to an increased number of charge carriers. The Mg doping, on the other hand, was considered likely to be located on both Li and Co sites, therefore not affecting the Co valence. Furthermore, the Li diffusion coefficients estimated for the LiCoO_2 variants suggested that the Li diffusion was faster in the Mg-Ti doped

material, which was attributed to a slightly smaller crystallite size with the doping.

4.2.2 Cycling Stability

The synthesis modifications were also shown to affect the cycling stability of the LiCoO_2 materials. The relative capacity fade measured in pouch-type full cells against a graphite negative electrode and the cell impedance spectra at different cycle numbers are plotted in Figure 9. Two different voltage windows were explored during the cycling to gain information on the effects of the LiCoO_2 potential window on the long-term stability of the material. The Mg-Ti doping of the LiCoO_2 positive electrode clearly improved the full-cell cycling stability in both of the studied voltage windows. On the other hand, the Li excess in the positive electrode had a markedly negative effect on the durability of the cells when cycled at voltages below 4.2 V (corresponding to a potential of 4.3 V vs. Li^+/Li on the positive electrode). However, the Li excess slightly improved the cycling stability when the upper cut-off voltage was increased to 4.4 V, especially if the cells were cycled beyond 20% capacity fade.

Figure 9. Cycling performance of the $\text{LiCoO}_2(\text{S})$, $\text{LiCoO}_2(\text{R})$ and $\text{LiCoO}_2(\text{D})$ materials measured in full cells with a graphite negative electrode at a C-rate of 0.5C (Publication II). The relative capacity drop of the full cells cycled in a voltage range of (a) 3.0–4.2 V and (c) 3.0–4.4 V. The higher capacities seen after every 50 cycles result from one cycle performed at 0.1C. The evolution of the impedance spectra of the graphite/ LiCoO_2 full cells at a SOC of 50% cycled in the voltage range of (b) 3.0–4.2 V and (d) 3.0–4.4 V.

The evolution of the EIS spectra during cycling depended strongly on the LiCoO_2 material used in the cells. The impedance spectra after formation (inset in Figure 9d) were similar for all of the cells and consisted of two semi-circles and a diffusion tail. The higher frequency semi-circle has previously been assigned to

passivating layers (SEI and CEI), whereas the semi-circle at lower frequencies can be attributed to charge-transfer reactions on both of the electrodes.^{133,134} Cycling in both of the studied voltage windows caused a significant increase in the size of the lower frequency semi-circle, while the higher frequency feature underwent a smaller increase. As expected, the impedance increase was faster when the graphite/LiCoO₂ cells were cycled to higher voltages. The increase of the high-frequency semi-circle was similar for all of the cells, and it was attributed to interfacial reactions with the electrolyte, especially SEI growth. However, contribution from electrolyte oxidation on the LiCoO₂ electrodes (CEI growth) was also possible especially when the cells were cycled to higher voltages. The increase of the lower frequency semi-circle was strongly dependent on the positive electrode material, being most severe for the cells with Li-overstoichiometric LiCoO₂, whereas the Mg-Ti doping was seen to suppress the increase. However, if the cells were cycled beyond 80% remaining capacity, the Li excess was seen to diminish the impedance increase in comparison to the stoichiometric LiCoO₂ (see Publication II for further details).

By comparing the frequency ranges and evolution of the full-cell EIS spectra to the impedance response of the LiCoO₂ electrodes measured in three-electrode cells, most of the increase in charge-transfer resistance could be assigned to changes on the LiCoO₂ electrodes. Moreover, it should be noted that the changes on the LiCoO₂ electrodes can cause changes in the EIS response of the graphite negative electrodes, as well, for example through Co dissolution and subsequent reduction in the SEI of the graphite electrodes. The Mg-Ti doping of LiCoO₂ clearly improved the cycling stability of the full cells by suppressing the impedance increase through stabilizing the LiCoO₂ electrodes against cycling-induced changes. Moreover, the slightly smaller primary particle size of the Mg-Ti doped LiCoO₂ appeared not to have a negative effect on the cycling stability of the material, even though particle cracking related to the high strain on grain boundaries in polycrystalline materials has been linked to accelerated aging rates.^{135,136} On the other hand, the adverse effect of the Li overstoichiometry was attributed to a more disordered structure with slightly poorer crystallinity compared to stoichiometric compounds. The mechanism of the stabilizing effect of Li excess in long-term cycling at high-voltages could not be definitively resolved within the present work.

5. Conducting Polymers as Electrode Materials

Transition metal oxides are currently the most popular positive electrode materials in Li-ion batteries due to their superior energy density. However, they are expensive and their production requires critical raw-material resources. Moreover, Co and Ni are toxic, and the mining methods of Co have occasionally raised ethical concerns. The increasing demand and production of Li-ion batteries has aggravated these concerns, and therefore research to find positive electrode materials free of transition metals is intense. Especially, materials that are based on organic compounds are sought after.

Intrinsically conducting polymers are organic materials that have been studied as potential electrode materials for both Li-ion batteries and electrochemical capacitors. Their benefits include that they are free of transition metals, show rather high specific capacity and facile kinetics. However, the commercial use of conducting polymers is restricted by their poor cycling stability in organic electrolytes. The poor stability arises from volume changes during electrochemical reactions as well as poor reversibility at high potentials. However, several methods have been developed to improve the durability of conducting polymers, such as using carbonaceous supports and thermal treatments. To enable the further development of these conducting polymer materials for use in electrochemical energy storage devices, a better understanding of the degradation mechanisms of the materials is still needed.

This chapter discusses the use of conducting polymers as electrode materials in Li-ion cells. After introducing the concept of intrinsically conducting polymers, their application in electrochemical energy storage systems is discussed, and the most common approaches to mitigate the stability problems are outlined. The emphasis of the chapter is on polyaniline, which is recognized as one of the most promising conducting polymers for application in Li-ion cells. Numerous articles have been published regarding the synthesis and use of conducting polymers and their composites in energy storage devices based on aqueous electrolytes. These studies have been reviewed elsewhere,^{137–141} and the primary focus of this chapter is on the non-aqueous systems.

5.1 Conducting Polymers in Electrochemical Energy Storage

The discovery of the first intrinsically conducting polymer, polypyrrole, was reported by Donald E. Weiss *et al.* in 1963.^{142–144} Later, in the end of the 1970s,

Alan J. Heeger, Alan G. MacDiarmid and Hideki Shirakawa studied and developed conducting polymers further, for which they received the Nobel Prize in Chemistry in 2000. As the name implies, intrinsically conducting polymers are defined as organic polymers that conduct electricity due to a conjugated π system of their backbone. In the presence of a suitable oxidant or at sufficiently high potentials, electrons can be removed from the π system to form holes in a process known as p-doping. This increases the mobility of the remaining electrons and makes the polymer conductive. To maintain electroneutrality, the polymer takes up ions from the electrolyte.^{145,146} Electrons can also be added to an unfilled band to produce an n-doped conducting polymer. However, n-type materials are uncommon in practice.¹⁴⁵

Intrinsically conducting polymers have been studied for both supercapacitor and Li-ion battery applications to be used as active materials or to replace the binder-conductive carbon combination normally used in the preparation of the composite electrodes.¹⁴⁷ In supercapacitor applications, they are often referred to as “pseudocapacitive” materials. The term “pseudocapacitance” refers to materials that undergo fast reversible faradaic reactions at or near their surface and show a current-potential response resembling that of a capacitive process (i.e. a rectangular shape of the cyclic voltammogram). The behavior occurs due to a finite amount of active material or surface area available for the electrochemical charge-transfer reaction. However, pronounced redox peaks are usually seen in the CV response of conducting polymers, which makes the use of the term “pseudocapacitive” often inappropriate for them.

The most commonly studied conducting polymers for electrochemical energy storage devices are polyaniline (PANI), polypyrrole, polythiophene and its derivatives. From these, PANI is often considered the most promising due to its relatively simple synthesis, good stability in ambient conditions and most importantly its high specific capacity (theoretical value up to 294 mAh g⁻¹).^{137,140} When conducting polymers are utilized as electrode active materials or additives, it must be taken into account, however, that the materials are conductive and electrochemically active only in a rather narrow potential window: for example, the potential window for p-doping of PANI is roughly 2.8–4.3 V vs. Li⁺/Li, whereas n-doping occurs at potentials beyond the stability window of common organic electrolytes.^{145,148,III} Therefore, PANI is generally suitable as conductive additive or active material only for positive electrodes.

The electrochemical reactions of the polymer backbone (i.e. p- or n-doping) are accompanied by significant volume changes because the size of the counter ions is often rather large. Furthermore, it has been shown that solvent molecules are also absorbed and released by the polymer during doping and dedoping processes.¹⁴⁹ These volume changes lead to poor cycling stability which has hindered the use of conducting polymers in commercial applications. Moreover, charge trapping and poor reversibility of the redox reactions at high potentials have been reported.^{150,151} A further hindrance to the commercial adoption of conducting polymers is their poor solubility in most solvents, which makes their processing difficult. In the following, these issues are described in more detail for PANI.

5.2 Polyaniline as Electrode Material in Li-ion Cells

Three oxidation states are generally identified for PANI: fully reduced leucoemeraldine, half-oxidized emeraldine and fully oxidized pernigraniline (Figure 10).^{146,152–156} The imine (=N–) nitrogen atoms of the emeraldine and pernigraniline base forms and the amine (–N–) nitrogens of the leucoemeraldine base form can be protonated in the presence of a suitable protonic acid to yield the corresponding salt forms.^{153,156} The protonation of emeraldine base creates the emeraldine salt form, which is the only one of the PANI forms that shows high electronic conductivity. In contrast to other conducting polymers, the number of electrons associated with the PANI chain does not change during the protonic acid doping.¹⁵²

Figure 10. The oxidation states and redox states of polyaniline. The reaction pathway desired in organic electrolytes is shown in bold.

In aprotic organic electrolytes, the PANI electrochemical reactions are desired to follow a pathway that does not involve protons: PANI should reversibly switch between the leucoemeraldine base, emeraldine salt and pernigraniline salt states (shown in bold in Figure 10). Four electrons are transferred per repeating unit in the full transition from leucoemeraldine to pernigraniline, corresponding to a theoretical specific capacity of 294 mAh g^{-1} (not taking into account the mass of the counter ions). As stated earlier, the excess charge created by the redox reactions on the polymer backbone is compensated by the absorption and release of anions from the electrolyte. Accordingly, it is the anion that transfers the charge across the polymer-solution interface. The term “dual-ion cell” has been proposed¹⁵⁷ to describe cells utilizing this type of mechanism on the positive electrode to differentiate from cells, where the electrolyte serves primarily as a Li-ion transfer medium and the anions do not participate in the overall cell reaction. In dual-ion cells, there is a risk of significant increase of the electrolyte resistance at the charged state. Therefore, they require the use of highly concentrated electrolytes or an excess of electrolyte, which decreases the cell-level energy density. It is also worth noticing that if PANI is to be used as the positive electrode in a Li-ion cell, the negative electrode of the full cell needs

to be pre-lithiated or consist of metallic Li, because PANI does not contain Li ions. Pre-lithiation techniques for the negative electrodes are discussed in Section 6.2.

The dopant has a significant influence on the properties of PANI. For example, emeraldine salt doped with HCl shows good environmental stability and high conductivity but lacks processability due to insolubility in most solvents.¹⁵⁸ On the other hand, doping with protonic acids having a bulky group, such as camphorsulfonic acid or dodecylbenzenesulfonic acid, has been shown to increase the processability and provide good electronic conductivity.¹⁵⁹ Ryu *et al.*^{158,160,161} have studied the effects of the dopant ion on the performance of PANI in Li-ion battery and supercapacitor applications and reported that the highest capacities were obtained with dimethyl sulfate doping. Moreover, it has been shown that PANI can be (pseudo)doped with Li salts. However, Li doping is inhomogeneous and the electronic properties of Li-doped PANI are not as good as those of the protonic-acid doped polymer.^{160,162–165}

5.3 Stability of Polyaniline in Organic Electrolytes

Like the other conducting polymers, PANI shows poor cycling stability due to the volume changes during the doping and dedoping. PANI also shows an additional degradation mechanism at high potentials: full oxidation of the polymer generally leads to degradation because the pernigraniline form is unstable.^{153,156} In aqueous electrolytes, hydrolysis of pernigraniline base takes place.^{166–168} In organic electrolytes, the desired product of the full oxidation is pernigraniline salt. However, formation of pernigraniline base has been reported, which is irreversible in organic systems due to the lack of protons in the electrolyte.^{154,169} In early works, these problems were circumvented by restricting the potential range of the polymer to values below the emeraldine-pernigraniline transition (<3.5–4.0 V vs. Li^+/Li). However, this limits the specific capacity of the electrodes to half of the theoretical value.

Stabilization of PANI-based electrodes in neutral or slightly alkaline aqueous solutions has been of interest in the field of biosensors for decades (i.e. the prevention of acid dedoping). For example Bartlett *et al.*¹⁷⁰ have shown that this can be accomplished through immobilization of sulfonate groups within PANI by incorporating sulfonate polymers as the counter ions. More recently, Tarver *et al.*^{171,172} have shown that a similar approach, template synthesis of polymer-acid-doped PANI, allows the pernigraniline base state of PANI to be reversibly accessed in mildly acidic and neutral aqueous solutions. Inspired by the results of Tarver *et al.*, the group of Lutkenhaus^{154,173} has shown that also the pernigraniline salt form in organic electrolytes can be stabilized through the synthesis of a PANI-polyacid complex. In addition to the sulfonate-based polyacids, complexation with weak polyacids having carboxylic acid functional groups has been shown to improve the stability.¹⁷³ The drawback is, however, that the polyacids are usually not electrochemically active, and therefore they reduce the specific capacity of the resulting electrodes.

Another common approach to improve the cycle life of conducting polymers has been to form composites with metal oxides or carbonaceous materials.¹³⁹ Generally, the motivation for the conducting polymer-metal oxide composites is to increase the specific capacity of the system, whereas the carbonaceous supports are more effective in enhancing the durability. The supports stabilize the electrodes against mechanical failure and often improve the electrolyte percolation into the bulk of the electrodes.^{145,150,III} Moreover, carbon-based support materials enhance the conductivity of the composites and can contribute to the charge storage through their double-layer capacitance.^{145,174} Especially carbon nanotubes stand out among the various support materials due to the rigid backbone and conducting network that they can provide to the composites. Recent studies^{174–176,III} have combined the polyacid method with the carbon support approach by synthesizing PANI-containing electrodes with carbon supports having oxygen-containing functional groups.

Finally, the most recent approach suggested to improve the stability of PANI is heat treatment.^{177,178} Heating at a moderate temperature around 150 °C induces cross-linking of the PANI chains,¹⁷⁹ which reduces the solubility of the polymer in organic solvents^{180,181} and affects its mechanical properties.^{176,182,183} However, heat-treatment can cause several other changes in the polymer, such as dedoping, oxidation, chain scission and changes of the crystal structure,¹⁸⁴ and the reports in the literature have been contradictory on the effects of these changes on the electrochemical properties of PANI-based materials. Some studies have reported a decrease of the conductivity,^{182,184,185} whereas others have indicated increased conductivity after thermal treatments.^{177,186} The outcome of the thermal treatment is obviously affected by the temperature, but the treatment atmosphere and time as well as the dopant in PANI affect it, too. It has been shown that HCl dopant evaporates at lower temperatures compared to more bulky acids, and hence PANI-HCl is more susceptible to decreases in conductivity.^{185,187} On the other hand, heat treatments in air are more detrimental to the electrochemical response of PANI than treatments under N₂ due to the oxidation of the polymer in air.¹⁸² Furthermore, composites of PANI with other conducting materials, such as carbons, are expected to be less susceptible to decreases in electrochemical performance.¹⁸⁸

5.4 Composites of Polyaniline and Carbon Nanotubes

In the present work, the effects of an acid-functionalized carbon nanotube support and heat treatments on the electrochemical stability of PANI were studied in Publication III. The aim was to investigate not only the cycle-life effects but also the aging mechanisms of the PANI-based materials through analysis of cycled electrodes recovered from half-cells. In the existing literature on the topic, the formation of pernigraniline base and large volume changes in PANI are usually cited as the causes of performance degradation. However, the situation is likely more complicated than that with other side reactions taking place in the cells. Moreover, previous reports on the aging mechanisms of PANI in organic systems have relied on UV-vis measurements of thin-film electrodes on glass

substrates, whereas more extensive investigations have been lacking. Therefore, a *post-mortem* analysis of the cycled cells was performed to expand on the previously existing works.

In Publication III, a composite of PANI and acid-treated MWNTs (a-MWNTs) was prepared from chemically synthesized PANI (emeraldine salt) through ultrasonic-assisted mixing of aqueous colloids of PANI and a-MWNTs.¹⁸⁹ Both PANI and MWNTs were obtained from commercial sources, and the MWNTs were acid treated in-house to introduce oxygen-containing functional groups (mainly carboxylic groups) on the sidewalls of the nanotubes. The samples were then heat treated under vacuum at moderate temperatures of 120–180 °C to induce cross-linking of the PANI phase.

5.4.1 Electrochemical Performance

When evaluating the suitability of a method to stabilize PANI, it is important to take into account any adverse effects it might have on the other electrochemical characteristics of the electrodes. Figure 11 presents the cyclic voltammograms of pristine and heat-treated PANI/a-MWNT composites and pristine PANI in 1 M LiClO₄ in propylene carbonate. Two pairs of peaks arising from the redox reactions of PANI were seen for all the materials. The first pair of peaks, observed between 2.6 and 3.6 V, was assigned to the transition from leucoemeraldine base to emeraldine salt in the anodic scan, and vice versa in the cathodic direction.^{152–154} The second pair of peaks at 3.6–4.3 V was attributed to the redox reaction between emeraldine salt and the pernigraniline form of PANI.^{152–154} The attribution of the plateau region between the two pairs of peaks, in turn, is still under debate in the scientific community.¹⁹⁰ It is generally attributed either to capacitive processes¹⁹⁰ or to faradaic charge transfer due to a higher formal potential of the electrochemical reactions at a higher oxidation state of PANI.¹⁹¹

Figure 11. Cyclic voltammograms of pristine and heat-treated PANI/a-MWNT composites measured in half-cells (Publication III). (a) CVs measured at a scan rate of 1 mV s⁻¹ for pristine PANI, pristine PANI/a-MWNT and PANI/a-MWNT heat treated at 165 °C. (b) The discharge capacities determined by integrating the cathodic current in the CVs of pristine PANI and PANI/a-MWNT samples as well as PANI/a-MWNT heat treated at 150–180 °C.

The presence of the a-MWNTs in the composite clearly improved the electrochemical accessibility of PANI and facilitated the PANI electrochemical reactions in the pristine composite. The CVs of pristine PANI/a-MWNT (mass ratio 3/2) showed a smaller peak separation in comparison to pure PANI and similar

specific capacity of 120–130 mAh g⁻¹. As the capacity of a-MWNTs in the studied voltage window was small (45 mAh g⁻¹), this demonstrated an improved utilization of the PANI in the composite. The effect was attributed to the improved conductivity of the composites, especially at potentials where PANI was not in the conductive emeraldine salt form (i.e. close to the vertex potentials). Furthermore, part of the improvement in the electrochemical accessibility was ascribed to improved electrolyte percolation into the electrodes, as the density of the PANI/a-MWNT composite electrodes was lower compared to PANI electrodes.

On the other hand, heat treatments of the PANI/a-MWNT composites at temperatures of 165 °C or higher were found to cause hindrance to the kinetics of the PANI redox reactions, seen as clearly suppressed peaks in the CVs. In turn, heat treatments at lower temperatures had only minor effects on the electrochemical characteristics. The hindrance was attributed to the cross-linking of the polymer phase, which could slow down the diffusion of counter ions within the polymer. This was supported by the ohmic resistances, as measured by EIS, which were similar before and after thermal treatment. Moreover, XPS analysis confirmed that evaporation of the dopants had not taken place during the heat treatments.

All of the materials except the PANI/a-MWNT composites heat treated at a minimum of 165 °C showed a surprising cycling behavior, in which most of the capacity drop occurred during open circuit phases between galvanostatic or CV cycling (Figure 11b). Similar behavior was seen also for pure PANI electrodes heat treated above 165 °C (not shown). The reason for the behavior could not be fully resolved in the present work. However, the most likely explanations were suggested to be a lower release rate of low molecular weight polymer or polymer oxidation products to the electrolyte and a lower rate of dedoping during galvanostatic cycling. Moreover, the electrodes were kept at 3.1 V vs. Li⁺/Li during the open circuit periods, and thus the charge density on the polymer backbone was smaller compared to higher potentials (see Figure 10). Therefore, the electrostatic interactions between the a-MWNTs and PANI and within the polymer were smaller, and relaxation processes could also have taken place within the samples. In a study of PANI/poly(styrenesulfonate), Bartlett *et al.*¹⁷⁰ similarly observed that the electroactivity of the composite decreased markedly if the films were left in an aqueous solution of neutral pH at open circuit. They also assigned the behavior to relaxation through polymer chain reorganization within the composite films.

5.4.2 Cycling Stability and Degradation Mechanisms

The stabilizing effect induced by the heat treatments on the PANI/a-MWNT composites was learned to be quickly lost during prolonged cycling. As depicted in Figure 12, both pristine and heat-treated PANI/a-MWNT composites showed similar performance in prolonged cycling. Therefore, based on the present study, heat treatments were not effective in improving the long-term cycling stability of PANI or PANI/a-MWNT composites in organic electrolyte. The heat treatment was merely able to postpone the degradation but not change the aging mechanisms. This is in contrast to studies by Wang *et al.*^{177,178} conducted in

aqueous electrolyte, which suggested that thermal crosslinking is an effective method to improve the durability of PANI. However, the degradation mechanisms are different in the different electrolytes as described in Section 5.3. In addition, the larger size of the organic solvents absorbed and released during the cycling can aggravate the volume changes and thus promote mechanical damage. Furthermore, the modest improvement in the initial cycle stability brought by the heat treatment was accompanied by hindered kinetics, which counteracts any benefits of the heat treatments. On the other hand, the a-MWNTs improved the cycling stability of the composites much more pronouncedly. After 200 charge-discharge cycles, the PANI/a-MWNT composites showed a capacity retention of 80% compared to 70% for the PANI electrodes.

Figure 12. Galvanostatic cycling ($2.5\text{--}4.3\text{ V vs. Li}^+/\text{Li}$, 1 A g^{-1}) of pristine PANI, pristine PANI/a-MWNT and PANI/a-MWNT heat treated at $165\text{ }^\circ\text{C}$ (Publication III). (a) The specific discharge capacity and (b) the energy efficiency and the coulombic efficiency recorded during the stability test.

Analysis of the cycled electrodes recovered from the half-cells showed that the stability improvement brought by the a-MWNT support was caused by improved mechanical stability and the ability of the a-MWNTs to retain the conductivity of the composite throughout the cycling. SEM images of non-heat-treated PANI/a-MWNT composite and pure PANI, before and after electrochemical cycling, are presented in Figure 13. Pure PANI electrodes showed drastic changes in morphology and a decrease in conductivity after cycling, whereas both of the changes were prevented by the presence of the a-MWNTs. The pure PANI electrodes showed also a decrease in the amount of dopants after cycling, and therefore the increased resistivity of pure PANI was attributed to the irreversible formation of insulating pernigraniline base during the cycling.^{154,169}

The cycling-induced degradation of the PANI/a-MWNT composites was more subtle. Analysis with Raman spectroscopy and XPS suggested that the PANI/a-MWNT composites also experienced changes of the microstructure. The volume changes in the polymer caused the a-MWNTs to be embedded deeper into the polymer matrix during cycling. Moreover, oxidation products of both the electrolyte solvent and the LiClO_4 salt were found on the surface of the PANI/a-MWNT electrodes after electrochemical cycling. Slight dedoping of the polymer was also found, which was likely associated to the formation of pernigraniline base in the composites, as well. Thus, the mechanism of the stability improvement by the a-MWNTs, in addition to the improved mechanical durability, was

the mitigation of the effects of the formation of pernigraniline base (decreased conductivity) rather than the prevention of the transition altogether.

Figure 13. SEM images of electrodes prepared from (a, c) PANI/a-MWNT composite and (b, d) pure PANI (a, b) before and (c, d) after cycling (Publication III).

To conclude, the present work strengthens the earlier reports of formation of pernigraniline base instead of pernigraniline salt as a major aging mechanism in PANI and PANI-based composites in organic systems, when the electrodes are cycled beyond potentials where the emeraldine-pernigraniline transformation takes place. Moreover, morphology changes in PANI were shown to be a major cause of aging. The addition of a carbon nanotube support was shown to effectively prevent these changes and to suppress the negative effect of pernigraniline base on the conductivity of PANI-based electrodes. In contrast, heat treatments, which have been suggested as an effective method to improve the stability of PANI in aqueous electrolytes,^{177,178} were shown to be ineffective in enhancing the stability in organic systems and as a further drawback caused hindrance to the kinetics of the electrochemical reactions of PANI. Moreover, the study highlighted the importance of testing the calendar aging stability of novel materials. As the stability of PANI-based materials are often tested only by cycling at a high current or potential sweep rate, any problems in open circuit stability might easily be overlooked.

6. Li-Ion Capacitors

As can be concluded from the previous chapters, most of the aging mechanisms in Li-ion batteries are inherent to the electrode materials and often result from side reactions accompanying the Li-insertion main reaction. Therefore, the most fundamental method to improve the stability is to change the reaction mechanisms in the cells.

Electrochemical double-layer capacitors (EDLCs), also known as “supercapacitors” and “ultracapacitors”, are another electrochemical energy-storage technology, which utilizes the formation of the electrical double layer to store charge instead of faradaic reactions. Their main difference to Li-ion batteries in terms of performance is their significantly higher specific power ($>10 \text{ kW kg}^{-1}$) and their almost unlimited cycle life of up to 1 000 000 full charge-discharge cycles.^{150,192} However, their main drawback is a low specific energy ($<10 \text{ Wh kg}^{-1}$)¹⁹² compared to Li-ion batteries ($<250 \text{ Wh kg}^{-1}$)⁷, which makes them unsuitable for many of the desired applications.¹⁵⁰

Finding a technology that could combine the benefits of EDLCs’ high power and excellent cycling stability with Li-ion batteries’ high specific energy would be the solution to the drawbacks of both technologies. Recently, Li-ion capacitors have been developed in an attempt to accomplish this. They combine a Li-ion battery electrode and an EDLC-type electrode in one cell, and thus present an intermediate between the two technologies. In comparison to Li-ion batteries, the energy storage mechanism on one of the electrodes is changed from the faradaic intercalation reaction to a purely capacitive process. As the capacitive process occurs only on the surface of the electrode, many of the complications of faradaic processes, such as activation overpotentials and volume changes, can be avoided on the capacitive electrode, theoretically reducing the cell overpotentials and decreasing the degradation rate. Some commercial products have already emerged, which have demonstrated specific energies up to $\sim 20 \text{ Wh kg}^{-1}$ and specific power values of $\sim 10 \text{ kW kg}^{-1}$.^{193,194} However, further development is still needed, especially in terms of the specific energy. In this chapter, the operating mechanism and electrode material choices for Li-ion capacitors are discussed.

6.1 Principles of Li-Ion Capacitors

EDLCs store energy through the formation of an electrical double layer (Figure 14) at the interface between a high-surface-area carbon electrode and the electrolyte solution. Because there is no charge transfer through the electrode-electrolyte interface, there are no activation overpotentials and the charge-storage mechanism is fast. However, as the double-layer formation occurs only on the surface of the carbon, the capacity of the electrodes is low, which leads to the low specific energy of an EDLC.

Figure 14. A schematic illustration of the electrical double layer at the electrode-electrolyte interface.¹⁹⁵ The solution side of the double layer is thought to consist of several layers. The layer closest to the electrode surface at distance x_1 is the inner Helmholtz plane (IHP), which contains solvent molecules and specifically adsorbed (unsolvated) ions. Solvated ions, on the other hand, can approach the electrode surface only to a distance x_2 , which is called the outer Helmholtz plane (OHP). The diffuse layer extends from the OHP to the bulk of the solution. On the electrode side, the charge resides in a very thin layer at the surface due to the high conductivity of the electrode.

The amount of energy stored in an EDLC is proportional to the capacitance, C , and the square of the operating voltage, U^2 , according to the equation

$$E = \frac{1}{2} C U^2. \quad (2)$$

Thus, there are two approaches to increase the energy density of an EDLC: (i) by increasing the charge-storage capacity of the porous carbon electrodes *e.g.* by increasing the surface area or (ii) by increasing the operating voltage of the device. From the two approaches, increasing the operating voltage is more effective due to the second-power dependence. Li-ion capacitors can be considered to utilize both of these approaches. By replacing one of the high-surface-area carbon electrodes with a “battery-like” electrode that undergoes faradaic reactions occurring at a rather constant potential, the average operating voltage can be increased. On the other hand, also the charge-storage capacity of that electrode is significantly increased due to the participation of the electrode bulk.

A Li-ion capacitor is usually constructed using the battery-type material as the negative electrode and the capacitive material as the positive electrode, as it al-

lows highest cell voltages. However, there is an inherent mismatch in the kinetics and the capacities of the two energy storage mechanisms employed on the two electrodes of the cell. The faradaic reaction on the battery-type electrode is sluggish compared to the formation of the double layer on the capacitive electrode. Therefore, the power performance of a Li-ion capacitor is limited by the kinetics of the Li-intercalation reaction, whereas the capacity is restricted by the capacitive electrode. Furthermore, the cycle life of the device is determined by the battery component due to the volume changes, phase transitions and side reactions associated with the Li intercalation.

Often, the performance mismatch of the electrodes is mitigated by using an excess of the intercalation material. This decreases the current density and narrows the state-of-charge window on the battery-type electrode, thereby diminishing the effects of the sluggish kinetics and the volume changes.^{196–198} However, using an excess of one of the electrode materials adds dead weight to the cells and thus decreases the specific energy and power. Consequently, to optimize the performance of the cells, materials with better matching properties, i.e. materials that show fast redox reactions and higher specific capacitance, are desirable.

6.2 Faradaic Materials for Li-Ion Capacitors

As stated in the previous section, the faradaic electrode of a Li-ion capacitor is most often the negative electrode. The ideal negative electrode material for a Li-ion capacitor presents facile kinetics for Li intercalation/deintercalation as well as a long cycle life. Moreover, the operating potential should preferably be constant and high enough not to induce SEI formation but low enough to produce high cell voltages. To date, finding a negative electrode material that could fulfill all of the requirements has proven difficult.

$\text{Li}_4\text{Ti}_5\text{O}_{12}$ has been one of the most popular negative electrode materials for Li-ion capacitors since the introduction of the technology by Amatucci *et al.*¹⁹⁹ in 2001. It is well suited for the application for the same reasons it is used in high-power batteries. There is no risk of Li deposition, and due to its negligible volume change during Li insertion/extraction and a lack of SEI formation, a long cycle life can be expected for $\text{Li}_4\text{Ti}_5\text{O}_{12}$ -based cells. Moreover, as the choice of the electrolyte is not limited by its SEI-forming ability, electrolytes with high conductivities can be used with $\text{Li}_4\text{Ti}_5\text{O}_{12}$.²⁰⁰ However, due to the high operating potential of $\text{Li}_4\text{Ti}_5\text{O}_{12}$, the maximum cell voltage of the Li-ion capacitor is around 2.8 V when paired with activated carbon,^{201,202} which leads to modest specific energy values that are not much higher compared to traditional EDLCs.

Like in Li-ion batteries, carbonaceous materials such as graphite, hard carbons and soft carbons are also common choices for the negative electrode of a Li-ion capacitor. They provide higher cell voltages around 3.8–4.0 V (vs. activated carbon)²⁰² and thus a significantly higher specific energy than $\text{Li}_4\text{Ti}_5\text{O}_{12}$. For example, JM Energy reports a specific energy value of 24 Wh kg⁻¹ for their laminate cells using a carbonaceous negative electrode.¹⁹³ However, the disadvantage of most of the carbons is their tendency to form a resistive SEI on their

surface, which is more of a problem for a high-power Li-ion capacitor than for a battery. Moreover, the risk of Li deposition during high-rate charging exists.

A further drawback of the SEI formation on carbonaceous electrodes is that carbon must be pre-lithiated prior to utilization as the negative electrode in a Li-ion capacitor. The pre-lithiation is conducted to compensate for the loss of Li ions from the electrolyte into the SEI and to control the potential of the negative electrode to the desired range. For example, the operating potential of graphite can be controlled to values around 0.1 V vs. Li^+/Li through pre-lithiation and cell balancing, as opposed to ~ 3 V vs. Li^+/Li for pristine graphite before lithiation.

Several ways to pre-lithiate the negative electrode have been studied.²⁰³ The proposed methods can be roughly divided into two groups: (i) pretreatment of the negative electrode before cell assembling and (ii) *in-situ* methods. A few examples of the first group include pre-lithiation through applying direct electrical contact between the negative electrode and a metallic Li foil^{204,205} or using stabilized Li powder.^{206–208} The second group of methods is based on using a sacrificial Li source in the cells, e.g. an auxiliary Li electrode or additives that irreversibly release Li during the formation of the cells. For example, the addition of a Li metal oxide ($\text{Li}_x\text{M}_y\text{O}_z$, $M = \text{Co}, \text{Cu}, \text{Fe}, \text{Ni}$, etc.)^{194,203,209} or an organic Li salt (e.g. $\text{Li}_2\text{C}_4\text{O}_4$)^{203,210} into one of the composite electrodes to act as a Li-ion source has been investigated recently. Currently, the only method used in industrial scale is an electrochemical process based on the use of a sacrificial Li metal foil.^{203,211–213}

Finally, the pre-lithiation can be avoided altogether if the cell is constructed so that the intercalation material is the positive electrode, because the typical positive electrode materials are lithiated in their pristine state. For example, Krause *et al.*²¹⁴ prepared a Li-ion capacitor using LiFePO_4 as the positive electrode and carbon black as the negative electrode. This configuration also avoids the risk of Li deposition during charging at high currents. However, high-surface-area carbon electrodes cannot be polarized in the cathodic direction beyond approximately 1.0–1.5 V vs. Li^+/Li to prevent irreversible insertion of Li and excessive SEI formation.^{198,214–216} Hence, the cell voltage and the specific energy of this cell configuration are generally lower than the values for the opposite setup.

6.3 Capacitive Materials for Li-ion Capacitors

The formation of the electrical double layer takes place on the electrode-electrolyte interface, and thus the capacitance of an electrode is proportional to the surface area of the interface. Accordingly, an ideal capacitive material should have a high specific surface area, which is readily accessible to the electrolyte. Moreover, the ideal capacitive material is chemically inert in the electrolyte and has high electrical conductivity, which enables the use of high currents. High-surface-area carbons, typically used in EDLCs, offer all of these properties and are thus the most common capacitive electrode materials.

In addition to the surface area, the specific capacitance of the carbonaceous materials is affected by the total pore volume, the pore size and the pore-size distribution. Recent studies have indicated a sharp increase in the specific capacitance for carbons that have pore sizes smaller than the size of the solvated ions in the electrolyte, approaching the crystallographic diameter of the ions.^{217,218} This increase has been explained by a distortion of the ion solvation shell, allowing closer approach of the ions to the electrode surface, thereby increasing the capacitance according to equation

$$C = \frac{\varepsilon_r \varepsilon_0 A}{d}, \quad (3)$$

where ε_r is the relative dielectric constant of the electrolyte, ε_0 the dielectric constant of vacuum, d is the separation between the carbon surface and the electrolyte ions (the thickness of the double layer) and A is the surface area of the interface. Furthermore, the specific capacitance tends to reach a plateau, when the surface area determined according to Brunauer-Emmett-Teller (BET) theory increases beyond values around $1600 \text{ m}^2 \text{ g}^{-1}$.^{219,220} The behavior has been explained by space constrictions for charge accommodation inside the pore walls, and it suggests that the use of extremely high-surface-area carbons is not beneficial for the capacitance of the cells.^{219,220}

The most frequently reported high-surface-area carbon material used in Li-ion capacitors and EDLCs is activated carbon. It can be produced from various precursors (e.g. coal, pitch and biomass such as coconut shells), and the surface area is rather easily enhanced through chemical and physical activation methods, which increase the porosity in the bulk of the particles.¹⁴⁵ Moreover, it is inexpensive and has a good conductivity. The drawback of activated carbons is their relatively wide pore-size distribution.¹⁴⁵ Other materials studied in the literature include, for example, carbon blacks²¹⁴, conducting polymers,²²¹ graphene,^{222,223} carbon nanotubes^{224,225} and composite materials combining both capacitive and faradaic materials in one electrode.²²⁶

6.4 Cells with Carbide-Derived Carbon as Positive Electrode

Nanoporous carbide-derived carbons (CDCs) have been studied as electrode materials for EDLCs due to their unique synthesis process that allows careful control of their properties, most importantly the porosity and the conductivity.²¹⁷ CDCs are obtained by the extraction of a metal from its carbide at high temperature, usually through chlorination ($M = \text{Si}, \text{Ti}, \text{Zr}$, etc.):

The pore-size distribution of CDCs is narrow, and it can be controlled during the synthesis through the selection of the carbide precursor and the process temperature.²²⁷ Therefore, it is possible to tailor the pores of CDC to match the size of the electrolyte ions. For example, Chmiola *et al.*²¹⁸ have shown that 0.7–

0.8 nm is the optimal CDC pore size for high capacitance in a commonly used organic electrolyte of $(\text{CH}_3\text{CH}_2)_4\text{NBF}_4$ in acetonitrile solvent.

In Publication IV of the present work, Li-ion capacitors using nanoporous CDC as the positive electrode material were investigated. As the size of the PF_6^- ions used in the electrolyte in this work was similar to the size of the BF_4^- ions (both have diameters ~ 0.5 nm),²²⁸ a roughly similar pore size to the work of Chmiola *et al.*²¹⁸ was used. CDC with a BET surface area of $1460 \text{ m}^2 \text{ g}^{-1}$ was combined in Li-ion capacitor cells with two different negative electrode materials, $\text{Li}_4\text{Ti}_5\text{O}_{12}$ and graphite, to compare the performance of the two cell chemistries. In most of the experiments, the graphite and $\text{Li}_4\text{Ti}_5\text{O}_{12}$ electrodes were pre-lithiated before assembling the cells, but a brief series of measurements with non-pre-lithiated $\text{Li}_4\text{Ti}_5\text{O}_{12}$ was conducted, as well.

The specific capacitance of CDC in the LiPF_6 -containing Li-ion battery electrolyte was 120 F g^{-1} , which was in line with values reported in common electrolytes used in EDLCs.²²⁹ The CDC capacitance was found to be larger at higher potentials, which was related to a change in the ion forming the electrical double layer. The potential of zero charge of CDC was around 3.1 V vs. Li^+/Li . Thus, above 3.1 V vs. Li^+/Li , adsorption and desorption of PF_6^- anions took place on the CDC electrode, whereas below the potential of zero charge, Li^+ cations adsorbed and desorbed on the CDC surface during the charging and discharging of the Li-ion capacitor cells. The lower capacitance below 3.1 V vs. Li^+/Li was attributed to stronger solvation of the Li^+ ions compared to the anions.^{230–232}

The electrochemical characteristics and the cycling stability of the graphite/CDC and $\text{Li}_4\text{Ti}_5\text{O}_{12}$ /CDC cells are shown in Figure 15. As described in Sections 6.1 and 6.2, the cell balancing and negative electrode preparation differed from typical Li-ion battery cells. In both of the Li-ion capacitors, the negative electrodes were significantly oversized in capacity compared to the positive electrode to limit the SOC windows of the negative electrodes and to compensate for the slower kinetics of the battery-type electrodes. The SOC range of graphite was limited within the stage-3–stage-2 plateau at 22–50% SOC (0.1 V vs. Li^+/Li), where the stress developed in graphite due to lithiation and delithiation remains at a constant value.²³³ A similar cell balancing was used for $\text{Li}_4\text{Ti}_5\text{O}_{12}$ electrodes, which were pre-lithiated to a SOC of 50% (1.55 V vs. Li^+/Li). Accordingly, the CDC capacity corresponded to roughly 20% of the negative electrode capacity in both of the cells, which has been shown to offer the best compromise between specific energy and power capability for both of the cell types.^{196,198}

Figure 15. The electrochemical performance of Li-ion capacitors prepared from (a-c) pre-lithiated graphite and (d-f) pre-lithiated $\text{Li}_4\text{Ti}_5\text{O}_{12}$ (Publication IV). (a,d) The potential profiles of graphite and $\text{Li}_4\text{Ti}_5\text{O}_{12}$, respectively, measured in a half-cell at 0.02C. The graphite electrodes in the Li-ion capacitors were pre-lithiated to a SOC of 37.5% and the $\text{Li}_4\text{Ti}_5\text{O}_{12}$ electrodes to a SOC of 50%; (b,e) The potentials of the positive and negative electrodes measured against a Li^+/Li reference and the cell voltage; (c,f) The cycle life performance of graphite/CDC and $\text{Li}_4\text{Ti}_5\text{O}_{12}/\text{CDC}$ cells.

The negative electrode material affected the utilization of the CDC positive electrode, and hence the cell performance, in two ways. First, the potential of the negative electrode determined the usable potential window on the positive electrode. In contrast to an EDLC, where the carbonaceous electrodes are usually polarized in only one direction, either above or below the potential of zero charge, in a Li-ion capacitor, the potential of the capacitive electrode can swing in both directions around the potential of zero charge. When pre-lithiated graphite was used as the negative electrode, the CDC electrode could be cycled in a 2 V potential window of 2.1–4.1 V vs. Li^+/Li (corresponding to cell voltage window of 2.0–4.0 V). This translated to a maximum specific energy of 89 Wh kg^{-1} on an active material basis. On the other hand, due to the higher operating potential of $\text{Li}_4\text{Ti}_5\text{O}_{12}$, the cell voltage would be very low ($<1.5 \text{ V}$) if the lower range of the CDC potential window was utilized during cycling. Thus, only the positive side of the CDC potential window (3.1–4.1 V vs. Li^+/Li) was utilized

in the $\text{Li}_4\text{Ti}_5\text{O}_{12}/\text{CDC}$ cell (1.55–2.55 V). Accordingly, the specific energy of 30 Wh kg^{-1} obtained for the $\text{Li}_4\text{Ti}_5\text{O}_{12}/\text{CDC}$ cell was clearly lower compared to the graphite cells.

The other way that the negative electrode material affected the utilization of the CDC electrode was through the polarization of the electrode. Due to the lack of activation overpotentials, the polarization of the positive electrode was negligible compared to the negative electrode in the Li-ion capacitors (Figure 15b, e). However, if the negative electrode shows a large polarization in the cell voltage window, the potential swing of the CDC electrode is correspondingly narrower. This leads to a smaller capacity, because the capacity of the CDC electrode is directly proportional to its potential swing. From the two tested negative electrode materials, graphite showed a clearly larger polarization despite the oversizing, leading to a narrowing of the CDC potential range and a decrease in the utilization of the capacitance of the CDC especially at higher currents.

Both of the cell chemistries showed excellent cycling stabilities with 2–3% loss in specific energy over 1000 charge-discharge cycles, which is a low rate of aging compared to most Li-ion battery chemistries, especially in laboratory-scale test cells. The good cycle life was attributed to the narrow SOC range on the negative electrode and to the suppressed aging on the positive electrode. Even though the potential of the graphite electrode was seen to be slightly below 0 V vs. Li^+/Li at the end of the charging steps during the cycling, Li deposition did not occur in the cells due to the hindering effect of the relatively low SOC of the graphite electrode.

6.5 Effects of Pre-lithiating $\text{Li}_4\text{Ti}_5\text{O}_{12}$

The pre-lithiation of the negative electrode is often time-consuming and it complicates the manufacturing process of Li-ion capacitors. Thus, omitting the pre-lithiation step is desirable from the industrial perspective. In Publication IV, it was shown that pre-lithiation can be omitted when $\text{Li}_4\text{Ti}_5\text{O}_{12}$ is used as the negative electrode, but it changes the cell voltage profile significantly (Figure 16a). Without pre-lithiation, the cell voltage showed a sudden drop at low SOC (below 1.9 V), which was caused by the $\text{Li}_4\text{Ti}_5\text{O}_{12}$ electrode that now operated partly outside of the two-phase region. The high voltage swing of the $\text{Li}_4\text{Ti}_5\text{O}_{12}$ electrode caused under-utilization of the CDC electrode. This decreased the specific energy to 23 Wh kg^{-1} if the mass of the $\text{Li}_4\text{Ti}_5\text{O}_{12}$ electrode was kept the same as in the pre-lithiated cell.

Omitting the pre-lithiation also had a minor effect on the cycle life of the device (Figure 16b). The non-pre-lithiated $\text{Li}_4\text{Ti}_5\text{O}_{12}/\text{CDC}$ cell showed an 8% decrease in specific energy after 1000 charge-discharge cycles in comparison to 3% for the pre-lithiated cell. As described in Section 3.1.1, it has been shown that even $\text{Li}_4\text{Ti}_5\text{O}_{12}$ shows some reactivity with the electrolyte.^{82–85} As pre-lithiation provides a reserve of active Li, it provides a buffer against any Li-consuming side reactions taking place in the cell.

Figure 16. The electrochemical performance of a Li-ion capacitor prepared from non-pre-lithiated $\text{Li}_4\text{Ti}_5\text{O}_{12}$ (Publication IV). (a) The cell voltage profile and (b) the cycle life performance of the $\text{Li}_4\text{Ti}_5\text{O}_{12}/\text{CDC}$ cell.

Subsequent publications^{234,235} have considered the effect of pre-lithiation on the performance of $\text{Li}_4\text{Ti}_5\text{O}_{12}$ -based Li-ion capacitors more rigorously and developed mathematical models to determine the optimal level of Li pre-loading. However, the practical applicability of pre-lithiated $\text{Li}_4\text{Ti}_5\text{O}_{12}$ in commercial devices depends on the development of a safe and cost-effective pre-lithiation process, which has been identified as the prime bottleneck for the technology. Due to the ability of Li pre-loading to improve the energy densities of other Li-ion cell types, as well, there is a strong interest to develop an industrially relevant process to accomplish the pre-lithiation.

7. Conclusions

In this thesis, the degradation mechanisms of Li-ion battery electrode materials were studied from a broad perspective ranging from commercial materials to novel organic alternatives. Moreover, methods to mitigate the aging through modifications of the materials and alternative cell designs were considered.

Based on a *post-mortem* analysis of commercial graphite/LiFePO₄ battery cells charge-discharge cycled at different temperatures, cell aging was observed to arise mainly from side reactions at the graphite negative electrode. Passivating layer growth on graphite dominated at room temperature, whereas severe metallic Li deposition occurred at lower temperatures. In addition to these well-known aging mechanisms, low-temperature cycling (−18 °C) was found to promote the formation of surface and intergranular cracks in the graphite particles. Even though the cracking might initially improve the high-power performance of the cells due to increased amount of sites for Li intercalation into graphite, it is expected to promote further passivating layer growth and deterioration of the electrical contacts within the electrode, therefore accelerating cell aging in prolonged cycling. Moreover, it was shown that it is difficult to distinguish these aging mechanisms, especially the Li deposition, from electrochemical measurements of full cells without disassembling them. This should be taken into account in considering the second-life use of Li-ion cells, as undetected Li plating can be a significant safety hazard.

In addition to the aging of the negative electrode, the degradation of the positive electrode can contribute to the performance decline. In the present work, the olivine-structured LiFePO₄ was shown to be very stable during cycling, with no indications of deterioration after 2000 charge-discharge cycles at room temperature. However, the currently most popular positive electrodes, layered transition metal oxides, are known to suffer from significant degradation especially during high-voltage cycling. In Publication II, even relatively low amounts of Mg and Ti co-doping (<1 mol-%) were observed to effectively increase the cycling stability of the layered transition metal oxide LiCoO₂. The durability improvement was shown to be related to the inhibition of cell impedance increase, likely caused by the improved structural stability and better electrical and ionic conductivity of the doped LiCoO₂. Moreover, slight Li overstoichiometry was shown to be detrimental to the durability of LiCoO₂ when cycling up to relatively low potentials (≤ 4.3 V vs. Li⁺/Li), but it appeared beneficial to the cycling performance at higher potentials (≤ 4.5 V vs. Li⁺/Li). Thus, to gain further improvements in the high-potential cycling stability of LiCoO₂, the combined effect of

Mg-Ti co-doping and Li excess should be studied. A rather large Li excess (Li to transition metal ratios up to ~ 1.2) combined with careful temperature control in the synthesis have been shown to be the keys to producing single-crystalline (Ni-rich) transition metal oxide particles, which have shown improved cycling stability.^{95,116,236} In relation to this, the effect of the grain size of the doped LiCoO_2 should be studied further in an effort to improve its lifetime. It should also be noted that these modifications are industrially viable, as they do not add new process steps to the solid-state synthesis of the transition metal oxides.

With the currently increasing demand for large-scale Li-ion batteries, cheaper and more environmentally friendly alternatives to the transition metal oxides are also needed. Especially, the introduction of electrode materials based on organic compounds could reduce the environmental burden of battery production. Conducting polymers are an example of organic compounds considered as a replacement, but their utilization is restricted by their poor stability in Li-ion battery applications. In an effort towards finding ways to mitigate this, the preparation of conducting polymer-carbon nanotube composites and their degradation mechanisms were investigated in Publication III. The carbon nanotube support network was shown to improve the cycling stability of polyaniline, which is one of the most commonly used conducting polymers. The improvement arose from the inhibition of mechanical changes during cycling as well as the suppression of degradation due to the irreversible formation of pernigraniline base, if not by preventing the formation altogether but by suppressing its effects on the electrochemical performance. While the carbon nanotube support provided clear stability enhancement, further development is still needed to obtain materials stable enough for commercial products. For example, the dopants have major effects on the properties of conducting polymers, and thus their effects on the stability in organic electrolytes should be studied further. Improved utilization of the functional groups on the sidewalls of the nanotubes as the dopant in the polymer could be advantageous. Moreover, Publication III demonstrated that, regarding the methodology used to study novel materials, both the cycling stability and the calendar aging stability should be tested in order to fully assess the viability of a material.

Alternative cell designs were also briefly considered. As most of the aging processes in Li-ion batteries result from side reactions accompanying the Li-insertion main reaction, replacing one of the Li-intercalation electrodes with an electrode showing a capacitive charge-storage mechanism should theoretically reduce the aging rate. Such a substitution creates a cell known as a Li-ion capacitor.¹⁹⁹ In the present work, carbide-derived carbon was shown to be a viable option as the capacitive electrode, and cells with both graphite and $\text{Li}_4\text{Ti}_5\text{O}_{12}$ as the intercalation electrode showed good cycling stability, albeit with a lower specific energy compared to Li-ion batteries. However, the optimization of the pore size of the carbide-derived carbon for LiPF_6 electrolytes could offer some improvements in specific energy. It was also shown that pre-lithiation of the intercalation electrode not only improves the initial performance of the Li-ion capacitors but also improves the cycling stability by introducing a reserve of active Li ions, counteracting the effects of any Li-consuming side reactions taking place during

cycling. However, as pre-lithiation is a time consuming procedure that complicates the manufacturing process of the cells, its viability in commercial devices depends on the development of safe and cost-effective pre-lithiation methods.

From the studies of the various electrode materials in this thesis, some general trends could be seen. It was shown that regardless of the electrode material, the key mechanisms that need to be tackled are the side reactions at the electrode-electrolyte interfaces and the volume changes of the electrode materials. Moreover, the importance of maintaining a high electrical conductivity within the electrodes was demonstrated. To address these issues from the electrode material perspective, several different approaches must likely be combined. These strategies include modifications of the active material structures, morphologies and crystallite sizes as well as coatings to stabilize the interfaces. In addition to these, electrolyte additives and careful design of the cells and cell management systems will be needed. Especially, the role of electrolyte additives and advanced electrolytes (e.g. HF-free electrolytes, ionic liquids, solid electrolytes) in stabilizing the interfaces on both the positive and the negative electrode is likely to be high particularly in combination with high-potential positive electrode materials. In the future, modeling approaches are also needed to deepen the understanding of the chemical and mechanical processes leading to electrode material degradation.

References

- 1 M. S. Whittingham, *Proc. IEEE*, 2012, **100**, 1518–1534.
- 2 The Royal Swedish Academy of Sciences, Scientific Background on the Nobel Prize in Chemistry 2019, <https://www.nobelprize.org/prizes/chemistry/2019/advanced-information>, (accessed 27 November 2019).
- 3 U.S. Department of Energy Vehicle Technologies Office, Batteries 2018 Annual Progress Report, https://www.energy.gov/sites/prod/files/2019/04/f62/VTO_2018_APR_BATTERIES_041519_compliant.pdf, (accessed 2 December 2019).
- 4 E. C. Evarts, *Nature*, 2015, **526**, S93–S95.
- 5 D. Linden and T. B. Reddy, Eds., *Handbook of Batteries*, McGraw-Hill, New York, 3rd edn., 2002.
- 6 T. Placke, R. Kloepsch, S. Dühnen and M. Winter, *J. Solid State Electrochem.*, 2017, **21**, 1939–1964.
- 7 Panasonic, Specifications for NCR18650BF, https://b2b-api.panasonic.eu/file_stream/pids/fileversion/3446, (accessed 25 November 2019).
- 8 M. Li, J. Lu, Z. Chen and K. Amine, *Adv. Mater.*, 2018, **30**, 1800561.
- 9 M. Winter, J. O. Besenhard, M. E. Spahr and P. Novák, *Adv. Mater.*, 1998, **10**, 725–763.
- 10 J. R. Dahn, *Phys. Rev. B*, 1991, **44**, 9170–9177.
- 11 E. Pohjalainen, S. Räsänen, M. Jokinen, K. Yliniemi, D. A. Worsley, J. Kuusivaara, J. Juurikivi, R. Ekqvist, T. Kallio and M. Karppinen, *J. Power Sources*, 2013, **226**, 134–139.
- 12 S. Schweidler, L. De Biasi, A. Schiele, P. Hartmann, T. Brezesinski and J. Janek, *J. Phys. Chem. C*, 2018, **122**, 8829–8835.
- 13 D. Aurbach, Y. Ein-Eli, O. Chusid, Y. Carmeli, M. Babai and H. Yamin, *J. Electrochem. Soc.*, 1994, **141**, 603–611.
- 14 D. Aurbach, Y. Ein-Eli, B. Markovsky, A. Zaban, S. Luski, Y. Carmeli and H. Yamin, *J. Electrochem. Soc.*, 1995, **142**, 2882–2890.
- 15 D. Aurbach, B. Markovsky, I. Weissman, E. Levi and Y. Ein-Eli, *Electrochim. Acta*, 1999, **45**, 67–86.
- 16 S. Malmgren, K. Ciosek, M. Hahlin, T. Gustafsson, M. Gorgoi, H. Rensmo and K. Edström, *Electrochim. Acta*, 2013, **97**, 23–32.
- 17 M. Börner, A. Friesen, M. Grütze, Y. P. Stenzel, G. Brunklaus, J. Haetge, S. Nowak, F. M. Schappacher and M. Winter, *J. Power Sources*, 2017, **342**, 382–392.
- 18 M. Fleischhammer, T. Waldmann, G. Bisle, B.-I. Hogg and M. Wohlfahrt-Mehrens, *J. Power Sources*, 2015, **274**, 432–439.
- 19 T. Ohzuku, A. Ueda and N. Yamamoto, *J. Electrochem. Soc.*, 1995, **142**, 1431–1435.
- 20 S. Scharner, W. Weppner and P. Schmid-Beurmann, *J. Electrochem. Soc.*, 1999, **146**, 857–861.
- 21 K. Kanamura, T. Umegaki, H. Naito, Z. Takehara and T. Yao, *J. Appl. Electrochem.*, 2001, **31**, 73–78.
- 22 X. Zeng, M. Li, D. Abd El-Hady, W. Alshitari, A. S. Al-Bogami, J. Lu and K. Amine, *Adv. Energy Mater.*, 2019, **9**, 1900161.
- 23 N. Nitta, F. Wu, J. T. Lee and G. Yushin, *Mater. Today*, 2015, **18**, 252–264.
- 24 G. E. Blomgren, *J. Electrochem. Soc.*, 2017, **164**, A5019–A5025.
- 25 P. Poizot, S. Laruelle, S. Grugeon, L. Dupont and J. Tarascon, *Nature*, 2000, **407**, 496–499.

- 26 K. Mizushima, P. C. Jones, P. J. Wiseman and J. B. Goodenough, *Mater. Res. Bull.*, 1980, **15**, 783–789.
- 27 J. N. Reimers and J. R. Dahn, *J. Electrochem. Soc.*, 1992, **139**, 2091–2097.
- 28 S. Venkatraman, Y. Shin and A. Manthiram, *Electrochem. Solid-State Lett.*, 2003, **6**, 8–12.
- 29 D. Doughty and E. P. Roth, *Electrochem. Soc. Interface*, 2012, **21**, 37–44.
- 30 M. S. Islam and C. A. J. Fisher, *Chem. Soc. Rev.*, 2014, **43**, 185–204.
- 31 D. D. MacNeil, Z. Lu and J. R. Dahn, *J. Electrochem. Soc.*, 2002, **149**, A1332–A1336.
- 32 K. K. Lee, W. S. Yoon, K. B. Kim, K. Y. Lee and S. T. Hong, *J. Power Sources*, 2001, **97–98**, 308–312.
- 33 Y. Wang, J. Jiang and J. R. Dahn, *Electrochem. commun.*, 2007, **9**, 2534–2540.
- 34 B. J. Hwang, Y. W. Tsai, D. Carlier and G. Ceder, *Chem. Mater.*, 2003, **15**, 3676–3682.
- 35 T. Ohzuku and Y. Makimura, *Chem. Lett.*, 2001, **30**, 642–643.
- 36 Z. W. Lebens-Higgins, N. V. Faenza, M. D. Radin, H. Liu, S. Sallis, J. Rana, J. Vinkeviciute, P. J. Reeves, M. J. Zuba, F. Badway, N. Pereira, K. W. Chapman, T. L. Lee, T. Wu, C. P. Grey, B. C. Melot, A. Van Der Ven, G. G. Amatucci, W. Yang and L. F. J. Piper, *Mater. Horizons*, 2019, **6**, 2112–2123.
- 37 Z. Lu, D. D. MacNeil and J. R. Dahn, *Electrochem. Solid-State Lett.*, 2001, **4**, A191–A194.
- 38 C. S. Johnson, J. S. Kim, C. Lefief, N. Li, J. T. Vaughey and M. M. Thackeray, *Electrochem. commun.*, 2004, **6**, 1085–1091.
- 39 M. M. Thackeray, W. I. F. David, P. G. Bruce and J. B. Goodenough, *Mater. Res. Bull.*, 1983, **18**, 461–472.
- 40 M. M. Thackeray, *Prog. Solid State Chem.*, 1997, **25**, 1–71.
- 41 R. J. Gummow, A. De Kock and M. M. Thackeray, *Solid State Ionics*, 1994, **69**, 59–67.
- 42 A. K. Padhi, K. S. Nanjundaswamy and J. B. Goodenough, *J. Electrochem. Soc.*, 1997, **144**, 1188–1194.
- 43 T. Marks, S. Trussler, A. J. Smith, D. Xiong and J. R. Dahn, *J. Electrochem. Soc.*, 2011, **158**, A51–A57.
- 44 D. Aurbach, K. Gamolsky, B. Markovsky, Y. Gofer, M. Schmidt and U. Heider, *Electrochim. Acta*, 2002, **47**, 1423–1439.
- 45 A. L. Michan, B. S. Parimalam, M. Leskes, R. N. Kerber, T. Yoon, C. P. Grey and B. L. Lucht, *Chem. Mater.*, 2016, **28**, 8149–8159.
- 46 E. Björklund, D. Brandell, M. Hahlin, K. Edström and R. Younesi, *J. Electrochem. Soc.*, 2017, **164**, A3054–A3059.
- 47 H. Lee, H.-S. Lim, X. Ren, L. Yu, M. H. Engelhard, K. S. Han, J. Lee, H.-T. Kim, J. Xiao, J. Liu, W. Xu and J.-G. Zhang, *ACS Energy Lett.*, 2018, **3**, 2921–2930.
- 48 C. Bünzli, H. Kaiser and P. Novák, *J. Electrochem. Soc.*, 2015, **162**, A218–A222.
- 49 M. Klett, R. Eriksson, J. Groot, P. Svens, K. Ciosek Högström, R. Wreland Lindström, H. Berg, T. Gustafson, G. Lindbergh and K. Edström, *J. Power Sources*, 2014, **257**, 126–137.
- 50 N. Ghanbari, T. Waldmann, M. Kasper, P. Axmann and M. Wohlfahrt-Mehrens, *J. Phys. Chem. C*, 2016, **120**, 22225–22234.
- 51 R. Scipioni, P. S. Jørgensen, D. I. Stroe, R. Younesi, S. B. Simonsen, P. Norby, J. Hjelm and S. H. Jensen, *Electrochim. Acta*, 2018, **284**, 454–468.
- 52 V. Zinth, C. Von Lüders, M. Hofmann, J. Hattendorff, I. Buchberger, S. Erhard, J. Rebelo-Kornmeier, A. Jossen and R. Gilles, *J. Power Sources*, 2014, **271**, 152–159.
- 53 S. Schindler, M. Bauer, M. Petzl and M. A. Danzer, *J. Power Sources*, 2016, **304**, 170–180.
- 54 M. Petzl and M. A. Danzer, *J. Power Sources*, 2014, **254**, 80–87.
- 55 S. Malmgren, K. Ciosek, R. Lindblad, S. Plogmaker, J. Kühn, H. Rensmo, K. Edström and M. Hahlin, *Electrochim. Acta*, 2013, **105**, 83–91.
- 56 T. Waldmann, A. Iturrondobeitia, M. Kasper, N. Ghanbari, F. Aguesse, E. Bekaert, L. Daniel, S. Genies, I. J. Gordon, M. W. Lölle, E. De Vito and M.

- Wohlfahrt-Mehrens, *J. Electrochem. Soc.*, 2016, **163**, A2149–A2164.
- 57 D. P. Abraham, J. L. Knuth, D. W. Dees, I. Bloom and J. P. Christophersen, *J. Power Sources*, 2007, **170**, 465–475.
- 58 T. Waldmann, S. Gorse, T. Samtleben, G. Schneider, V. Knoblauch and M. Wohlfahrt-Mehrens, *J. Electrochem. Soc.*, 2014, **161**, A1742–A1747.
- 59 J. Vetter, P. Novák, M. R. Wagner, C. Veit, K. C. Möller, J. O. Besenhard, M. Winter, M. Wohlfahrt-Mehrens, C. Vogler and A. Hammouch, *J. Power Sources*, 2005, **147**, 269–281.
- 60 M. Broussely, P. Biensan, F. Bonhomme, P. Blanchard, S. Herreyre, K. Nechev and R. J. Staniewicz, *J. Power Sources*, 2005, **146**, 90–96.
- 61 P. Arora, R. E. White and M. Doyle, *J. Electrochem. Soc.*, 1998, **145**, 3647–3667.
- 62 M. Wohlfahrt-Mehrens, C. Vogler and J. Garche, *J. Power Sources*, 2004, **127**, 58–64.
- 63 C. R. Birkel, M. R. Roberts, E. McTurk, P. G. Bruce and D. A. Howey, *J. Power Sources*, 2017, **341**, 373–386.
- 64 N. Omar, M. A. Monem, Y. Firouz, J. Salminen, J. Smekens, O. Hegazy, H. Gaulous, G. Mulder, P. Van den Bossche, T. Coosemans and J. Van Mierlo, *Appl. Energy*, 2014, **113**, 1575–1585.
- 65 K. Jalkanen, J. Karppinen, L. Skogström, T. Laurila, M. Nisula and K. Vuorilehto, *Appl. Energy*, 2015, **154**, 160–172.
- 66 A. Friesen, X. Mönnighoff, M. Börner, J. Haetge, F. M. Schappacher and M. Winter, *J. Power Sources*, 2017, **342**, 88–97.
- 67 T. Waldmann, M. Wilka, M. Kasper, M. Fleischhammer and M. Wohlfahrt-Mehrens, *J. Power Sources*, 2014, **262**, 129–135.
- 68 M. Dubarry, N. Qin and P. Brooker, *Curr. Opin. Electrochem.*, 2018, **9**, 106–113.
- 69 A. H. Whitehead, K. Edström, N. Rao and J. R. Owen, *J. Power Sources*, 1996, **63**, 41–45.
- 70 M. N. Richard and J. R. Dahn, *J. Electrochem. Soc.*, 1999, **146**, 2068–2077.
- 71 K. Zhao, M. Pharr, J. J. Vlassak and Z. Suo, *J. Appl. Phys.*, 2010, **108**, 073517.
- 72 K. Takahashi and V. Srinivasan, *J. Electrochem. Soc.*, 2015, **162**, A635–A645.
- 73 T. Waldmann, B. I. Hogg and M. Wohlfahrt-Mehrens, *J. Power Sources*, 2018, **384**, 107–124.
- 74 M. Petzl, M. Kasper and M. A. Danzer, *J. Power Sources*, 2014, **275**, 799–807.
- 75 C. von Lüders, V. Zinth, S. V. Erhard, P. J. Osswald, M. Hofmann, R. Gilles and A. Jossen, *J. Power Sources*, 2017, **342**, 17–23.
- 76 C. Brissot, M. Rosso, J. N. Chazalviel and S. Lascaud, *J. Power Sources*, 1999, **81**, 925–929.
- 77 N. P. Wagner, K. Asheim, F. Vullum-Bruer and A. M. Svensson, *J. Power Sources*, 2019, **437**, 226884.
- 78 B. Philippe, R. Dedryvère, M. Gorgoi, H. Rensmo, D. Gonbeau and K. Edström, *Chem. Mater.*, 2013, **25**, 394–404.
- 79 K. Richter, T. Waldmann, M. Kasper, C. Pfeifer, M. Memm, P. Axmann and M. Wohlfahrt-Mehrens, *J. Phys. Chem. C*, 2019, **123**, 18795–18803.
- 80 S. Liu, M. Winter, M. Lewerenz, J. Becker, D. U. Sauer, Z. Ma and J. Jiang, *Energy*, 2019, **173**, 1041–1053.
- 81 Altairnano, Altairnano 70 Amp Hour Cell Specifications, <https://altairnano.com/products/70-amp-hour-cell/>, (accessed 25 June 2020).
- 82 I. Belharouak, G. M. Koenig, T. Tan, H. Yumoto, N. Ota and K. Amine, *J. Electrochem. Soc.*, 2012, **159**, A1165–A1170.
- 83 T. Nordh, R. Younesi, D. Brandell and K. Edström, *J. Power Sources*, 2015, **294**, 173–179.
- 84 C. J. Jafta, C. A. Bridges, Y. Bai, L. Geng, B. P. Thapaliya, H. M. Meyer III, R. Essehli, W. T. Heller and I. Belharouak, *ChemSusChem*, 2020, **13**, 3654–3661.
- 85 D. Leanza, C. A. F. Vaz, I. Czekaj, P. Novák and M. El Kazzi, *J. Mater. Chem. A*, 2018, **6**, 3534–3542.
- 86 R. Bernhard, S. Meini and H. A. Gasteiger, *J. Electrochem. Soc.*, 2014, **161**, A497–A505.
- 87 C. R. Fell, L. Sun, P. B. Hallac, B. Metz and B. Sisk, *J. Electrochem. Soc.*, 2015,

- 162**, A1916–A1920.
- 88 S. Sharifi-Asl, J. Lu, K. Amine and R. Shahbazian-Yassar, *Adv. Energy Mater.*, 2019, **9**, 1900551.
- 89 K. Edström, T. Gustafsson and J. O. Thomas, *Electrochim. Acta*, 2004, **50**, 397–403.
- 90 N. Dupré, J. F. Martin, J. Degryse, V. Fernandez, P. Soudan and D. Guyomard, *J. Power Sources*, 2010, **195**, 7415–7425.
- 91 D. Wang, X. Wu, Z. Wang and L. Chen, *J. Power Sources*, 2005, **140**, 125–128.
- 92 H. Gabrisch, J. Wilcox and M. M. Doeff, *Electrochem. Solid-State Lett.*, 2008, **11**, A25–A29.
- 93 H. Wang, Y.-I. Jang, B. Huang, D. R. Sadoway and Y.-M. Chiang, *J. Electrochem. Soc.*, 1999, **146**, 473–480.
- 94 J. N. Reimers and J. R. Dahn, *J. Electrochem. Soc.*, 1992, **139**, 2091–2097.
- 95 J. E. Harlow, X. Ma, J. Li, E. Logan, Y. Liu, N. Zhang, L. Ma, S. L. Glazier, M. M. E. Cormier, M. Genovese, S. Buteau, A. Cameron, J. E. Stark and J. R. Dahn, *J. Electrochem. Soc.*, 2019, **166**, A3031–A3044.
- 96 Y. Liu, J. Harlow and J. R. Dahn, *J. Electrochem. Soc.*, 2020, **167**, 020512.
- 97 G. G. Amatucci, J. M. Tarascon and L. C. Klein, *Solid State Ionics*, 1996, **83**, 167–173.
- 98 M. Koltypin, D. Aurbach, L. Nazar and B. Ellis, *J. Power Sources*, 2007, **174**, 1241–1250.
- 99 K. Amine, J. Liu and I. Belharouak, *Electrochem. commun.*, 2005, **7**, 669–673.
- 100 H. Gabrisch, R. Yazami and B. Fultz, *J. Electrochem. Soc.*, 2004, **151**, A891–A897.
- 101 R. Hausbrand, G. Cherkashinin, H. Ehrenberg, M. Gröting, K. Albe, C. Hess and W. Jaegermann, *Mater. Sci. Eng. B Adv. Funct. Solid-State Mater.*, 2015, **192**, 3–25.
- 102 E. Pohjalainen, T. Rauhala, M. Valkeapää, J. Kallioinen and T. Kallio, *J. Phys. Chem. C*, 2015, **119**, 2277–2283.
- 103 J. Christensen and J. Newman, *J. Solid State Electrochem.*, 2006, **10**, 293–319.
- 104 D. Burow, K. Sergeeva, S. Calles, K. Schorb, A. Börger, C. Roth and P. Heitjans, *J. Power Sources*, 2016, **307**, 806–814.
- 105 N. Koura, S. Kohara, K. Takeuchi, S. Takahashi, L. A. Curtiss, M. Grimsditch and M. L. Saboungi, *J. Mol. Struct.*, 1996, **382**, 163–169.
- 106 M. H. Brooker and J. B. Bates, *J. Chem. Phys.*, 1971, **54**, 4788–4796.
- 107 M.-T. Fonseca Rodrigues, V. A. Maroni, D. J. Gosztola, K. P. C. Yao, K. Kalaga, I. A. Shkrob and D. P. Abraham, *ACS Appl. Energy Mater.*, 2019, **2**, 873–881.
- 108 S. Tang, Y. Gu, J. Yi, Z. Zeng, S. Y. Ding, J. W. Yan, D. Y. Wu, B. Ren, Z. Q. Tian and B. W. Mao, *J. Raman Spectrosc.*, 2016, **47**, 1017–1023.
- 109 R. Schmitz, R. Ansgar Müller, R. Wilhelm Schmitz, C. Schreiner, M. Kunze, A. Lex-Balducci, S. Passerini and M. Winter, *J. Power Sources*, 2013, **233**, 110–114.
- 110 C. Naudin, J. L. Bruneel, M. Chami, B. Desbat, J. Grondin, J. C. Lasségues and L. Servant, *J. Power Sources*, 2003, **124**, 518–525.
- 111 T. Tran and K. Kinoshita, *J. Electroanal. Chem.*, 1995, **386**, 221–224.
- 112 F. Yao, F. Güneş, H. Q. Ta, S. M. Lee, S. J. Chae, K. Y. Sheem, C. S. Cojocaru, S. S. Xie and Y. H. Lee, *J. Am. Chem. Soc.*, 2012, **134**, 8646–8654.
- 113 Y. Li, K. Qian, Y.-B. He, Y. V. Kaneti, D. Liu, D. Luo, H. Li, B. Li and F. Kang, *J. Power Sources*, 2017, **342**, 24–30.
- 114 Y. Wu, P. Keil, S. F. Schuster and A. Jossen, *J. Electrochem. Soc.*, 2017, **164**, A1438–A1445.
- 115 International Energy Agency, Global EV Outlook 2019 - Scaling-up the transition to electric mobility, <https://www.iea.org/reports/global-ev-outlook-2019>, (accessed 27 November 2019).
- 116 J. Li, A. R. Cameron, H. Li, S. Glazier, D. Xiong, M. Chatzidakis, J. Allen, G. A. Botton and J. R. Dahn, *J. Electrochem. Soc.*, 2017, **164**, A1534–A1544.
- 117 A. Liu, J. Li, R. Shunmugasundaram and J. R. Dahn, *J. Electrochem. Soc.*, 2017, **164**, A1655–A1664.
- 118 Y. Lyu, X. Wu, K. Wang, Z. Feng, T. Cheng, Y. Liu, M. Wang, R. Chen, L. Xu, J.

- Zhou, Y. Lu and B. Guo, *Adv. Energy Mater.*, 2020, 2000982.
- 119 J. B. Goodenough and K. S. Park, *J. Am. Chem. Soc.*, 2013, **135**, 1167–1176.
- 120 M. Zhang, M. Tan, H. Zhao, S. Liu, X. Shu, Y. Hu, J. Liu, Q. Ran, H. Li and X. Liu, *Appl. Surf. Sci.*, 2018, **458**, 111–118.
- 121 W. Luo and J. R. Dahn, *Electrochim. Acta*, 2009, **54**, 4655–4661.
- 122 F. Zhou, W. Luo, X. Zhao and J. R. Dahn, *J. Electrochem. Soc.*, 2009, **156**, A917–A920.
- 123 S. Kim, S. Choi, K. Lee, G. J. Yang, S. S. Lee and Y. Kim, *Phys. Chem. Chem. Phys.*, 2017, **19**, 4104–4113.
- 124 K. Hoang, *Phys. Rev. Mater.*, 2017, **1**, 075403.
- 125 M. Carewska, S. Scaccia, F. Croce, S. Arumugam, Y. Wang and S. Greenbaum, *Solid State Ionics*, 1997, **93**, 227–237.
- 126 H. Tukamoto and A. R. West, *J. Electrochem. Soc.*, 1997, **144**, 3164–3168.
- 127 S. Levasseur, M. Ménétrier and C. Delmas, *J. Power Sources*, 2002, **112**, 419–427.
- 128 W. Luo, X. Li and J. R. Dahn, *J. Electrochem. Soc.*, 2010, **157**, A782–A790.
- 129 W. Luo, X. Li and J. R. Dahn, *J. Electrochem. Soc.*, 2010, **157**, A993–A1001.
- 130 M. Duffiet, M. Blangero, P. E. Cabelguen, C. Delmas and D. Carlier, *J. Phys. Chem. Lett.*, 2018, **9**, 5334–5338.
- 131 S. Levasseur, M. Ménétrier, Y. Shao-Horn, L. Gautier, A. Audemer, G. Demazeau, A. Largeteau and C. Delmas, *Chem. Mater.*, 2003, **15**, 348–354.
- 132 S. Levasseur, M. Ménétrier, E. Suard and C. Delmas, *Solid State Ionics*, 2000, **128**, 11–24.
- 133 P. Shafiei Sabet and D. U. Sauer, *J. Power Sources*, 2019, **425**, 121–129.
- 134 M. Dollé, F. Orsini, A. S. Gozdz and J.-M. Tarascon, *J. Electrochem. Soc.*, 2001, **148**, A851–A857.
- 135 D. J. Miller, C. Proff, J. G. Wen, D. P. Abraham and J. Bareño, *Adv. Energy Mater.*, 2013, **3**, 1098–1103.
- 136 P. Yan, J. Zheng, M. Gu, J. Xiao, J. G. Zhang and C. M. Wang, *Nat. Commun.*, 2017, **8**, 14101.
- 137 G. A. Snook, P. Kao and A. S. Best, *J. Power Sources*, 2011, **196**, 1–12.
- 138 A. Eftekhari, L. Li and Y. Yang, *J. Power Sources*, 2017, **347**, 86–107.
- 139 Q. Meng, K. Cai, Y. Chen and L. Chen, *Nano Energy*, 2017, **36**, 268–285.
- 140 Z. Wang, M. Zhu, Z. Pei, Q. Xue, H. Li, Y. Huang and C. Zhi, *Mater. Sci. Eng. R Reports*, 2020, **139**, 100520.
- 141 P. Liu, J. Yan, Z. Guang, Y. Huang, X. Li and W. Huang, *J. Power Sources*, 2019, **424**, 108–130.
- 142 R. McNeill, R. Siudak, J. H. Wardlaw and D. E. Weiss, *Aust. J. Chem.*, 1963, **16**, 1056–1075.
- 143 B. A. Bolto and D. E. Weiss, *Aust. J. Chem.*, 1963, **16**, 1076–1089.
- 144 B. A. Bolto, R. McNeill and D. E. Weiss, *Aust. J. Chem.*, 1963, **16**, 1090–1103.
- 145 T. Pandolfo, V. Ruiz, S. Sivakkumar and J. Nerkar, in *Supercapacitors: Materials, Systems, and Applications*, eds. F. Béguin and E. Frackowiak, Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim, 1st edn., 2013, pp. 69–109.
- 146 A. G. MacDiarmid, *Angew. Chemie - Int. Ed.*, 2001, **40**, 2581–2590.
- 147 R. Holze and Y. P. Wu, *Electrochim. Acta*, 2014, **122**, 93–107.
- 148 O. A. Kozarenko, V. S. Dyadyun, M. S. Papakin, O. Y. Posudievsky, V. G. Koshechko and V. D. Pokhodenko, *Electrochim. Acta*, 2015, **184**, 111–116.
- 149 J. Desilvestro, W. Scheifele and O. Haas, *J. Electrochem. Soc.*, 1992, **139**, 2727–2736.
- 150 Z. Lin, E. Goikolea, A. Balducci, K. Naoi, P. L. Taberna, M. Salanne, G. Yushin and P. Simon, *Mater. Today*, 2018, **21**, 419–436.
- 151 E. Frackowiak, in *Supercapacitors: Materials, Systems, and Applications*, eds. F. Béguin and E. Frackowiak, Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim, First Ed., 2013, pp. 207–237.
- 152 A. G. MacDiarmid, J. C. Chiang, A. F. Richter and A. J. Epstein, *Synth. Met.*, 1987, **18**, 285–290.
- 153 E. Song and J.-W. Choi, *Nanomaterials*, 2013, **3**, 498–523.
- 154 J.-W. Jeon, Y. Ma, J. F. Mike, L. Shao, P. B. Balbuena and J. L. Lutkenhaus, *Phys. Chem. Chem. Phys.*, 2013, **15**, 9654–9662.

- 155 R. Mažeikienė, V. Tomkute, Z. Kuodis, G. Niaura and A. Malinauskas, *Vib. Spectrosc.*, 2007, **44**, 201–208.
- 156 W. A. Marmisollé and O. Azzaroni, *Nanoscale*, 2016, **8**, 9890–9918.
- 157 T. Placke, O. Fromm, S. F. Lux, P. Bieker, S. Rothermel, H. W. Meyer, S. Passerini and M. Winter, *J. Electrochem. Soc.*, 2012, **159**, 1755–1765.
- 158 K. S. Ryu, S. K. Jeong, J. Joo and K. M. Kim, *J. Phys. Chem. B*, 2007, **111**, 731–739.
- 159 Y. Cao, P. Smith and A. J. Heeger, *Synth. Met.*, 1992, **48**, 91–97.
- 160 K. S. Ryu, K. M. Kim, S.-G. Kang, J. Joo and S. H. Chang, *J. Power Sources*, 2000, **88**, 197–201.
- 161 K. S. Ryu, K. M. Kim, S.-G. Kang, G. J. Lee, J. Joo and S. H. Chang, *Synth. Met.*, 2000, **110**, 213–217.
- 162 A. Saprigin, R. S. Kohlman, S. M. Long, K. R. Brennenman, A. J. Epstein, M. Angelopoulos, Y.-H. Liao, W. Zheng and A. G. MacDiarmid, *Synth. Met.*, 1997, **84**, 767–768.
- 163 A. V. Saprigin, K. R. Brennenman, W. P. Lee, S. M. Long, R. S. Kohlman and A. J. Epstein, *Synth. Met.*, 1999, **100**, 55–59.
- 164 J. Joo, H. G. Song, C. K. Jeong, J. S. Baeck, J. K. Lee and K. S. Ryu, *Synth. Met.*, 1999, **98**, 215–220.
- 165 J. H. Jung, B. H. Kim, B. W. Moon, J. Joo, S. H. Chang and K. S. Ryu, *Phys. Rev. B*, 2001, **64**, 035101.
- 166 A. Watanabe, K. Mori, Y. Iwasaki, Y. Nakamura and S. Niizuma, *Macromolecules*, 1987, **20**, 1793–1796.
- 167 D. E. Stilwell and S.-M. Park, *J. Electrochem. Soc.*, 1988, **135**, 2497–2502.
- 168 J. Deng, T. Wang, J. Guo and P. Liu, *Prog. Nat. Sci. Mater. Int.*, 2017, **27**, 257–260.
- 169 L. Shao, J.-W. Jeon and J. L. Lutkenhaus, *Chem. Mater.*, 2012, **24**, 181–189.
- 170 P. N. Bartlett and J. H. Wang, *J. Chem. Soc. - Faraday Trans.*, 1996, **92**, 4137–4143.
- 171 J. Tarver, J. E. Yoo, T. J. Dennes, J. Schwartz and Y.-L. Loo, *Chem. Mater.*, 2009, **21**, 280–286.
- 172 J. Tarver, J. E. Yoo and Y. L. Loo, *Chem. Mater.*, 2010, **22**, 2333–2340.
- 173 J.-W. Jeon, S. R. Kwon, F. Li and J. L. Lutkenhaus, *ACS Appl. Mater. Interfaces*, 2015, **7**, 24150–24158.
- 174 J.-W. Jeon, S. R. Kwon and J. L. Lutkenhaus, *J. Mater. Chem. A*, 2015, **3**, 3757–3767.
- 175 M. N. Hyder, S. W. Lee, F. Ç. Cebeci, D. J. Schmidt, Y. Shao-Horn and P. T. Hammond, *ACS Nano*, 2011, **5**, 8552–8561.
- 176 M. N. Hyder, R. Kaviani, Z. Sultana, K. Saetia, P.-Y. Chen, S. W. Lee, Y. Shao-Horn and P. T. Hammond, *Chem. Mater.*, 2014, **26**, 5310–5318.
- 177 X. Wang, D. Liu, J. Deng, X. Duan, J. Guo and P. Liu, *RSC Adv.*, 2015, **5**, 78545–78552.
- 178 D. Liu, H. Wang, P. Du and P. Liu, *Carbon*, 2017, **122**, 761–774.
- 179 M. M. Nobrega, C. H. B. Silva, V. R. L. Constantino and M. L. A. Temperini, *J. Phys. Chem. B*, 2012, **116**, 14191–14200.
- 180 R. Mathew, B. R. Mattes and M. P. Espe, *Synth. Met.*, 2002, **131**, 141–147.
- 181 J. A. Conklin, S.-C. Huang, S.-M. Huang, T. Wen and R. B. Kaner, *Macromolecules*, 1995, **28**, 6522–6527.
- 182 R. Ansari, W. E. Price and G. G. Wallace, *Polymer (Guildf.)*, 1996, **37**, 917–923.
- 183 S.-A. Chen and H.-T. Lee, *Macromolecules*, 1993, **26**, 3254–3261.
- 184 S. Bhadra and D. Khastgir, *Polym. Degrad. Stab.*, 2008, **93**, 1094–1099.
- 185 T. Chen, C. Dong, X. Li and J. Gao, *Polym. Degrad. Stab.*, 2009, **94**, 1788–1794.
- 186 A. Kobayashi, H. Ishikawa, K. Amano, M. Satoh and E. Hasegawa, *J. Appl. Phys.*, 1993, **74**, 296–299.
- 187 J. Prokeš and J. Stejskal, *Polym. Degrad. Stab.*, 2004, **86**, 187–195.
- 188 A. López Cabezas, Y. Feng, L.-R. Zheng and Z.-B. Zhang, *Carbon*, 2013, **59**, 270–277.
- 189 F. Davodi, M. Tavakkoli, J. Lahtinen and T. Kallio, *J. Catal.*, 2017, **353**, 19–27.
- 190 J. Scotto, W. A. Marmisollé and D. Posadas, *J. Solid State Electrochem.*, 2019,

- 23**, 1947–1965.
- 191 K. Roßberg, G. Paasch, L. Dunsch and S. Ludwig, *J. Electroanal. Chem.*, 1998, **443**, 49–62.
- 192 Maxwell Technologies, Ultracapacitor Overview, https://www.maxwell.com/images/documents/Ultracapacitors_Overview_Flyer_3000615-2EN.pdf, (accessed 25 November 2019).
- 193 JM Energy Corporation, Specifications for ULTIMO Laminate Cell, <https://www.jmenergy.co.jp/en/product/cell/>, (accessed 30 January 2020).
- 194 P. Han, G. Xu, X. Han, J. Zhao, X. Zhou and G. Cui, *Adv. Energy Mater.*, 2018, **8**, 1–30.
- 195 A. J. Bard and L. R. Faulkner, *Electrochemical methods: Fundamentals and applications*, John Wiley & Sons, 2nd edn., 2001.
- 196 S. Dsoke, B. Fuchs, E. Gucciardi and M. Wohlfahrt-Mehrens, *J. Power Sources*, 2015, **282**, 385–393.
- 197 D. Cericola and R. Kötz, *Electrochim. Acta*, 2012, **72**, 1–17.
- 198 V. Khomenko, E. Raymundo-Piñero and F. Béguin, *J. Power Sources*, 2008, **177**, 643–651.
- 199 G. G. Amatucci, F. Badway, A. Du Pasquier and T. Zheng, *J. Electrochem. Soc.*, 2001, **148**, A930–A939.
- 200 I. Plitz, A. Du Pasquier, F. Badway, J. Gural, N. Pereira, A. Gmitter and G. G. Amatucci, *Appl. Phys. A Mater. Sci. Process.*, 2006, **82**, 615–626.
- 201 A. Du Pasquier, I. Plitz, J. Gural, S. Menocal and G. Amatucci, *J. Power Sources*, 2003, **113**, 62–71.
- 202 K. Naoi, S. Ishimoto, J. Miyamoto and W. Naoi, *Energy Environ. Sci.*, 2012, **5**, 9363–9373.
- 203 F. Holtstiege, P. Bärman, R. Nölle, M. Winter and T. Placke, *Batteries*, 2018, **4**, 4.
- 204 M. Kim, F. Xu, J. H. Lee, C. Jung, S. M. Hong, Q. M. Zhang and C. M. Koo, *J. Mater. Chem. A*, 2014, **2**, 10029–10033.
- 205 M. Valvo, A. Liivat, H. Eriksson, C. W. Tai and K. Edström, *ChemSusChem*, 2017, **10**, 2431–2448.
- 206 W. J. Cao and J. P. Zheng, *J. Power Sources*, 2012, **213**, 180–185.
- 207 W. J. Cao, Y. Li, B. Fitch, J. Shih, T. Doung and J. P. Zheng, *J. Power Sources*, 2014, **268**, 841–847.
- 208 W. J. Cao, M. Greenleaf, Y. X. Li, D. Adams, M. Hagen, T. Doung and J. P. Zheng, *J. Power Sources*, 2015, **280**, 600–605.
- 209 S. S. Zhang, *J. Power Sources*, 2017, **343**, 322–328.
- 210 D. Shanmukaraj, S. Grugeon, S. Laruelle, G. Douglade, J. M. Tarascon and M. Armand, *Electrochem. commun.*, 2010, **12**, 1344–1347.
- 211 T. Watanabe, T. Tsuda, N. Ando, S. Nakamura, N. Hayashi, N. Soma, T. Gunji, T. Ohsaka and F. Matsumoto, *Electrochim. Acta*, 2019, **324**, 134848.
- 212 T. Tsuda, N. Ando, N. Mitsuhashi, T. Tanabe, K. Itagaki, N. Soma, S. Nakamura, N. Hayashi and F. Matsumoto, *ECS Trans.*, 2017, **77**, 1897–1903.
- 213 US 6461769 B1, 2002.
- 214 A. Krause, P. Kossyrev, M. Oljaca, S. Passerini, M. Winter and A. Balducci, *J. Power Sources*, 2011, **196**, 8836–8842.
- 215 M. Schroeder, M. Winter, S. Passerini and A. Balducci, *J. Power Sources*, 2013, **238**, 388–394.
- 216 M. Schroeder, S. Menne, J. Ségalini, D. Saurel, M. Casas-Cabanas, S. Passerini, M. Winter and A. Balducci, *J. Power Sources*, 2014, **266**, 250–258.
- 217 J. Chmiola, G. Yushin, Y. Gogotsi, C. Portet, P. Simon and P. L. Taberna, *Science*, 2006, **313**, 1760–1763.
- 218 J. Chmiola, C. Largeot, P.-L. Taberna, P. Simon and Y. Gogotsi, *Angew. Chemie - Int. Ed.*, 2008, **47**, 3392–3395.
- 219 M. Käärik, U. Maran, M. Arulepp, A. Perkson and J. Leis, *ACS Appl. Energy Mater.*, 2018, **1**, 4016–4024.
- 220 O. Barbieri, M. Hahn, A. Herzog and R. Kötz, *Carbon*, 2005, **43**, 1303–1310.
- 221 A. Du Pasquier, A. Laforgue and P. Simon, *J. Power Sources*, 2004, **125**, 95–102.
- 222 M. D. Stoller, S. Murali, N. Quarles, Y. Zhu, J. R. Potts, X. Zhu, H.-W. Ha and

- R. S. Ruoff, *Phys. Chem. Chem. Phys.*, 2012, **14**, 3388–3391.
- 223 V. Aravindan, D. Mhamane, W. C. Ling, S. Ogale and S. Madhavi,
ChemSusChem, 2013, **6**, 2240–2244.
- 224 Q. Wang, Z. Wen and J. Li, *Adv. Funct. Mater.*, 2006, **16**, 2141–2146.
- 225 S. W. Lee, N. Yabuuchi, B. M. Gallant, S. Chen, B.-S. Kim, P. T. Hammond and
Y. Shao-Horn, *Nat. Nanotechnol.*, 2010, **5**, 531–537.
- 226 D. Cericola, P. Novák, A. Wokaun and R. Kötz, *J. Power Sources*, 2011, **196**,
10305–10313.
- 227 S. Urbonaitė, J. M. Juárez-Galán, J. Leis, F. Rodríguez-Reinoso and G.
Svensson, *Microporous Mesoporous Mater.*, 2008, **113**, 14–21.
- 228 M. Ue, *J. Electrochem. Soc.*, 1994, **141**, 3336–3342.
- 229 L. Permann, M. Lätt, J. Leis and M. Arulepp, *Electrochim. Acta*, 2006, **51**,
1274–1281.
- 230 K. Xu, *Chem. Rev.*, 2004, **104**, 4303–4417.
- 231 Y. Kameda, Y. Umehayashi, M. Takeuchi, M. A. Wahab, S. Fukuda, S.-I.
Ishiguro, M. Sasaki, Y. Amo and T. Usuki, *J. Phys. Chem. B*, 2007, **111**, 6104–
6109.
- 232 M. T. Ong, O. Verners, E. W. Draeger, A. C. T. Van Duin, V. Lordi and J. E.
Pask, *J. Phys. Chem. B*, 2015, **119**, 1535–1545.
- 233 V. A. Sethuraman, N. Van Winkle, D. P. Abraham, A. F. Bower and P. R.
Guduru, *J. Power Sources*, 2012, **206**, 334–342.
- 234 N. Xu, X. Sun, F. Zhao, X. Jin, X. Zhang, K. Wang, K. Huang and Y. Ma,
Electrochim. Acta, 2017, **236**, 443–450.
- 235 G. Madabattula, B. Wu, M. Marinescu and G. Offer, *J. Electrochem. Soc.*, 2020,
167, 013527.
- 236 H. Li, J. Li, X. Ma and J. R. Dahn, *J. Electrochem. Soc.*, 2018, **165**, A1038–
A1045.

Efficient energy storage is a prerequisite for increasing the share of renewables in energy production. It is also needed for reducing the use of fossil fuels in transportation.

Rechargeable batteries can convert electrical energy directly into chemical energy stored within the chemical compounds in the device. When needed, this energy can easily be released with high efficiency and short response time.

The performance of all batteries degrades over time and use. It has severe implications on the economic feasibility and environmental impacts of the technology. An understanding of the degradation mechanisms is the key enabler of the development of more durable devices.

This thesis examines the degradation mechanisms of the electrode materials used in lithium-ion batteries. A set of cases, which includes both commercially available materials and novel alternatives, is investigated. Strategies to mitigate the degradation are also considered.

ISBN 978-952-64-0117-1 (printed)

ISBN 978-952-64-0118-8 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University
School of Chemical Engineering
Department of Chemistry and Materials Science
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**