Ex situ and *in situ* characterization of Direct Alcohol Fuel Cell anode materials

Annukka Santasalo-Aarnio

Ex situ and *in situ* characterization of
Direct Alcohol Fuel Cell anode
materials

Annukka Santasalo-Aarnio

A doctoral dissertation completed for the degree of Doctor of Science in Technology to be defended, with the permission of the Aalto University School of Chemical Technology, at a public examination and debate in the lecture hall Ke2 (Komppa Auditorium) at the Aalto University School of Chemical (Espoo, Finland) Technology on 14th December 2012 at 12.

**Aalto University
School of Chemical Technology
Department of Chemistry
Research Group of Physical Chemistry**

Supervising professor

Professor Kyösti Kontturi

Thesis advisor

Dr. Tanja Kallio

Preliminary examiners

Professor Enrique Herrero, University of Alicante, Spain

Dr. Pertti Kauranen, VTT, Finland

Opponent

Associate Professor Carina Lagergren, Kungliga Tekniska högskolan (KTH), Sweden

Aalto University publication series

DOCTORAL DISSERTATIONS 167/2012

© Annukka Santasalo-Aarnio

ISBN 978-952-60-4907-6 (printed)

ISBN 978-952-60-4908-3 (pdf)

ISSN-L 1799-4934

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-60-4908-3>

Unigrafia Oy

Helsinki 2012

Finland

441 697
Printed matter

Author

Annukka Santasalo-Aarnio

Name of the doctoral dissertation

Ex situ and *in situ* characterization of Direct Alcohol Fuel Cell anode materials

Publisher School of Chemical Technology

Unit Department of Chemistry

Series Aalto University publication series DOCTORAL DISSERTATIONS 167/2012

Field of research Physical Chemistry

Manuscript submitted 17 August 2012

Date of the defence 14 December 2012

Permission to publish granted (date) 30 October 2012

Language English

☐ **Monograph**

☒ **Article dissertation (summary + original articles)**

Abstract

With direct alcohol fuel cells (DAFC) the chemical energy of the reactants can be directly converted to electrical energy that can be used for instance in portable applications, independent of the electrical network. Liquid fuels such as organic alcohols are interesting for customer applications because they are more facile to use and relatively safe when compared with gaseous hydrogen. However, the obstacles to commercialization are the expensive cell components, catalysts and electrolyte membrane, as well as the limited lifetime of current systems due material decomposition. In order to make this technology commercially viable new cost effective and more durable materials must be introduced and this thesis highlights the *ex situ* and *in situ* methods for studying these materials in DAFC related conditions.

The first part introduces methods to detect anode reaction products *ex situ*. The results indicate that at DAFC anode related potentials formic acid, formaldehyde and carbon dioxide are detected for methanol, acetaldehyde and acetic acid for ethanol and only acetone for isopropanol. In addition, HPLC analyses revealed that in alkaline media Pt based catalyst would be more preferable than Pd for methanol and ethanol oxidation, however, for isopropanol oxidation Pd shows increased performance. Moreover, the surface structure sensitivity of these reactions is studied with Pt single crystal electrodes and results imply that a strong effect on onset potential and activity exists: the Pt(111) surface being the most active for isopropanol and Pt(100) for methanol and ethanol oxidation.

The second part discusses the properties, preparation and performance of nanoparticle catalyst. A Pd catalyst prepared with ALD method showed increased activity for ethanol and isopropanol oxidation due to the evenly distributed catalyst on the carbon support. Moreover, the effect of various nanocarbon supports was studied and they showed high activity and durability in *ex situ* experiments, however, this activity was lost in the *in situ* tests implying that the MEA preparation needs to be optimized individually as each support material possesses different polarities. The third part introduces proton and anion exchange membrane DAFCs and shows the effect of catalyst, carbon support, anode fuel and the membrane material to the cell performance and durability. It can be concluded that in DAFCs exist also various phenomena that cannot be observed with solely *ex situ* techniques.

The results reported in this thesis are relevant to the fundamental understanding of the DAFC phenomena occurring on the electrodes and in the MEA and highlight the importance of both *ex situ* and *in situ* experiments.

Keywords DAFC, alcohol oxidation, catalysis, nanoparticles, electrochemistry

ISBN (printed) 978-952-60-4907-6

ISBN (pdf) 978-952-60-4908-3

ISSN-L 1799-4934

ISSN (printed) 1799-4934

ISSN (pdf) 1799-4942

Location of publisher Espoo

Location of printing Helsinki

Year 2012

Pages 148

urn <http://urn.fi/URN:ISBN:978-952-60-4908-3>

Tekijä

Annukka Santasalo-Aarnio

Väitöskirjan nimi

Suora-alkoholipolttokennojen anodimateriaalien tutkiminen

Julkaisija Kemian tekniikan korkeakoulu**Yksikkö** Kemian laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 167/2012**Tutkimusala** Fysikaalinen kemia**Käsitteilyajankohdan pvm** 17.08.2012**Väitöspäivä** 14.12.2012**Julkaisuluvan myöntämispäivä** 30.10.2012**Kieli** Englanti☐ **Monografia**☒ **Yhdistelmäväitöskirja (yhteenveto-osa + erillisartikkelit)****Tiivistelmä**

Suora-alkoholipolttokennoilla (SAPK) lähtöaineiden kemiallinen energia muunnetaan suoraan sähköenergiaksi, jota voidaan hyödyntää pienten, kannettavien sovellusten energianlähteenä. Näiden virtalähteiden etuja ovat korkea tehotehous ja riippumattomuus verkkovirrasta. Nestemäiset polttoaineet, kuten alkoholit, ovat kiinnostavia polttoaineita kuluttajasovelluksiin, koska ne ovat turvallisempia ja helpompia käyttää kuin kaasumaiset polttoaineet. Kuitenkin esteenä tämän tyyppisten kennojen kaupallistamiselle ovat kalliit komponentit (katalyyttimateriaalit ja elektrolyytinä toimiva membraani) sekä komponenttien rajoitettu kestävyys. Kuluttajasovelluksia varten on kehitettävä uusia, halvempia ja kestävämpiä materiaaleja. Tämä väitöskirja esittelee SAPK-olosuhteita jäljitteleviä sähkökemiallisia analyysimenetelmiä, joilla voidaan arvioida uusien materiaalien sopivuutta tähän sovellukseen.

Aluksi työssä tarkastellaan alkoholireaktioiden tuotteita Pt- ja Pd-elektrodeilla. Analyysi osoittaa, että pääreaktiotuotteina metanolilla on formaldehydi, muurahashappo ja hiilidioksidi, etanolilla asetdehydi ja etikkahappo sekä isopropanolilla aseton. HPLC-analyysi osoitti lisäksi, että emäksisessä ympäristössä metanolin ja etanolin hapettumisessa Pt-pohjaiset sekä isopropanolin hapettumiseen Pd-pohjaiset katalyytit ovat tehokkaita. Työssä tarkastellaan myös katalyytin pintarakenteen vaikutusta alkoholien hapettumiseen yksikide-elektrodeilla. Tuloksista nähdään, että kidepinta vaikuttaa selkeästi alkoholin hapettumisen alkamiseen sekä aktiivisuuteen ja näihin vaikuttaa pinnan lisäksi elektrolyytin pH. Kaikkein aktiivisin Pt-pinta isopropanolin hapettumiseen oli Pt(111) kun taas metanolille ja etanolille Pt(100)-pinta oli aktiivisin.

Toinen osa työstä käsittelee polttokennossa käytettävien nanopartikkelikatalyyttien ominaisuuksia, valmistusta ja suorituskykyä alkoholin hapettumisessa. ALD-menetelmällä valmistetun katalyytin jakautuminen pinnalle oli erittäin tasaista, joka johti kohonneeseen aktiivisuuteen alkoholin hapettumisessa. Tämän lisäksi katalyyttien kantajamateriaalit vaikuttavat elektrodin kestävyteen ja työssä todettiin membraanielektrodyhteenliittymän optimoinnin vaikuttavan sekä kennon suorituskykyyn että kestävyteen. Sähkökemiallisilla mittauksilla voidaan tutkia ainoastaan elektrodin reaktioita, joten jos kaikki SAPK:ssa tapahtuvat ilmiöt halutaan ymmärtää, on myös polttokennokokeita suoritettava: työssä on tutkittu sekä happamien että emäksisten SAPK-jen suorituskykyä sekä stabiilisuutta.

Väitöskirjan tulokset korostavat elektrodin rakenteen optimoinnin tärkeyttä ja osoittavat, että pelkillä sähkökemiallisilla mittauksilla uusien materiaalien arviointi on haastavaa.

Avainsanat SAPK, alkoholin hapetus, katalyyysi, nanopartikkelit, sähkökemian**ISBN (painettu)** 978-952-60-4907-6**ISBN (pdf)** 978-952-60-4908-3**ISSN-L** 1799-4934**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Espoo**Painopaikka** Helsinki**Vuosi** 2012**Sivumäärä** 148**urn** <http://urn.fi/URN:ISBN:978-952-60-4908-3>

Preface

The work presented in this thesis has been carried out in three locations: the main part is done at the Department of Chemistry in Aalto University between 2007 and 2012. The experimental parts for the Publication II and I have been performed in the Instituto de Electroquímica at University of Alicante, Spain in 2008, and in the Leiden Institute of Chemistry, University of Leiden, Netherlands in 2010, respectively.

First of all I would like to thank Prof. Kyösti Kontturi for providing me the opportunity to do my PhD with a fuel cell related topic and to thank both Kyösti and Dr. Annu Kontturi for the good working environment at fyke; this is a kind of work place person can just dream about. My biggest gratitude belongs to my supervisor Dr. Tanja Kallio for her guidance and encouragement along this process. I would also like to thank Prof. Juan Feliu for welcoming me to his group in Alicante and express my sincere appreciation to my supervisors Dr. Francisco Vidal-Inglésias and Dr. José Solla-Gúllon for introducing me into the world of SCEs and electrochemical experiments. In addition, I would like to thank Mr. António Berná for performing the FTIR experiments and send un abrazo for all my coworkers in Spain. This trip was financially made possible by Finnish Cultural Found and Insinöörien matkarahasto.

I further thank Prof. Mark Koper for accepting me to work with his group in Leiden and sharing his expertise in electrocatalysis. I owe special gratitude for Mr. Youngkook Kwon for introducing me into the HPLC systems and my colleagues in Leiden for welcoming me with an open heart. Furthermore, I would like to thank Prof. Elisabeth Ahlberg for encouraging me to participate to ELCAT training courses, that have provided the theoretical background to my work, as well as all the participants of ELCAT for welcoming me and providing new ideas at the late night student workshops. Finnish Foundation for Technology Promotion enabled my participation to the ELCAT training courses and my visit to Leiden University.

I would like to thank also other collaborators at Aalto University: Dr. Victoria Ruiz, Ms. Maryam Borghei and Prof. Esko Kauppinen from the Nanomaterial Group as well as Ms. Emma Sairanen and Dr. Sanna Airaksinen from the Industrial Chemistry Research Group. I personally think that collaboration has significantly improved the quality of the research and I was privileged to have the opportunity to work with you. A contribution to my work have also been performed summer and part time workers who have with their endless question made me validate all experimental choices made. Thanks to Ivan, Fiona, Barbara, Laura, Taina, Eero, Timo and especially to Ms. Kirsi Jalkanen with who we have been optimizing the RDE experiments.

To all my coworkers at the research group of Physical Chemistry and Electrochemistry I want to give my sincere gratitude: there has never been time when I would have not been helped with technical or theoretical problems. My biggest thanks go to the fuel cell group Mr. Petri Kanninen, Lic.Sc. (Tech.) Pekka Peljo, Dr. Ville Saarinen and Mr. Sami Tuomi for endless help and guidance. Also a big hug to Dr. Kirsi Yliniemi, Dr. Ben Wilson, Mr. David Lloyd, Ms. Maija Huuppola, Lic.Sc. (Tech.) Nguyet Doan, Ms. Elina Pohjalainen and Mr. Tuomas Vainikka as well as to my faithful roommate Dr. Outi Toikkanen for her endless support with all the matters in life. Especial thank is addressed to Petri, Pekka, Ben and Emma for proofreading my thesis, to David and Ben for proofreading my research papers as well as to Prof. Kari Laasonen for the fruitful discussions of the topics related to my thesis.

Finally, I would like to thank my parents who have always supported me, my brother and all my friends for providing me relaxing counterbalance to my work life. My sincere appreciation belongs to my husband Matti who has patiently listened all problems I encountered during this thesis process. I would also like to thank my daughter Kaisla for showing me every day what is important in life.

Espoo, August 17th, 2012

Annukka Santasalo-Aarnio

Contents

List of Publications	i
Author's contribution	ii
List of Abbreviations	iii
List of Symbols	v
1 Introduction	1
1.1 Fuel cell	3
1.2 Scope of this Thesis	4
2 Experimental approaches	5
2.1 Electrochemistry	5
2.1.1 Electrochemical cell	5
2.1.2 Preparation of well-ordered SCE	7
2.1.3 Nanoparticle electrode preparation	8
2.1.4 Electrochemically active surface area	9
2.2 Direct Alcohol Fuel Cell	12
3 Electrocatalysis of alcohol oxidation	15
3.1 Reaction mechanisms	17
3.1.1 Adsorption	17
3.1.2 Methanol	19
3.1.3 Ethanol	21
3.1.4 Isopropanol	23
3.2 Detection of reaction products	25
3.2.1 HPLC method	26
3.2.2 FTIR method	30
4 Single crystal electrodes	33

4.1	Characterization of SCEs	37
4.2	Alcohol oxidation on SCEs	39
5	Carbon supported nanoparticle electrodes	41
5.1	Properties of nanoparticles	42
5.2	Support materials	44
5.3	Catalyst preparation.....	48
5.4	Bimetallic nanoparticles	50
5.5	Alcohol oxidation on nanoparticles.....	53
6	Direct Alcohol Fuel Cell	57
6.1	Acidic DAFC.....	58
6.2	Alkaline DAFC.....	60
6.3	Crossover	62
6.4	Alcohol oxidation in DAFCs.....	63
6.4.1	Effect of carbon support.....	66
6.5	Comparison to electrochemical results.....	69
7	Conclusions.....	71
7.1	Reliability	73
7.2	Recommendation for further work	74
	References.....	75

List of Publications

This thesis consists of an overview and of the following publications which are referred in the text by their Roman numerals.

- I A. Santasalo-Aarnio, Y. Kwon, E. Ahlberg, K. Kontturi, T. Kallio and M.T.M. Koper, Comparison of methanol, ethanol and iso-propanol oxidation on Pt and Pd electrodes in alkaline media studied by HPLC, *Electrochem. Commun.* **13** (2011) 466-469.
- II A. Santasalo, F.J. Vidal-Iglesias, J. Solla-Gullón, A. Berná, T. Kallio and J. M. Feliu, Electrooxidation of methanol and 2-propanol mixtures at platinum single crystal electrodes, *Electrochim. Acta* **54** (2009) 6576-6583.
- III E. Rikkinen, A. Santasalo-Aarnio, S. Airaksinen, M. Borghei, V. Viitanen, J. Sainio, E.I. Kauppinen, T. Kallio and A.O.I. Krause, Atomic Layer Deposition Preparation of Pd Nanoparticles on a Porous Carbon Support for Alcohol Oxidation, *J. Phys. Chem. C* **115** (2011) 23067-23073.
- IV A. Santasalo-Aarnio, M. Borghei, I.V. Anoshkin, A.G. Nasibulin, E.I. Kauppinen, V. Ruiz and T. Kallio, Durability of different carbon nanomaterial supports with PtRu catalyst in a direct methanol fuel cell, *Int. J. Hydr. Ene.* **37** (2012) 3415-3424.
- V A. Santasalo-Aarnio, S. Tuomi, K. Jalkanen, K. Kontturi and T. Kallio, The correlation of electrochemical and fuel cell results for alcohol oxidation in acidic and alkaline media, *Electrochim. Acta*, In Press., <http://dx.doi.org/10.1016/j.electacta.2012.09.100>.

Author's contribution

Publication I	The experiments were performed as a co-operation of the first and second author. A. Santasalo-Aarnio had a major role in writing the manuscript.
Publication II	The research plan for this manuscript was defined together with co-authors. The author carried out the experimental work excluding the FTIR measurements. The results were interpreted and the manuscript prepared together with co-authors.
Publication III	The author carried out the electrochemical characterization of the new catalyst material. She had a major role in interpretation of the results and writing the manuscript.
Publication IV	The research plan for this manuscript was defined together with co-authors. All the electrochemical characterization and fuel cell measurements are performed by the author. The author had an active role in interpretation of the results and writing the manuscript.
Publication V	The author defined the research plan and carried out all of the measurements except the fuel cell measurements with alkaline membrane. The author interpreted the results and wrote the manuscript.

Espoo 17th August 2012

Prof. Kyösti Kontturi

List of Abbreviations

AEM	anion exchange membrane
AES	atomic emission spectroscopy
AFC	alkaline fuel cell
ALD	atomic layer deposition
CE	counter electrode
CNT	carbon nanotube
DAA	diacetone alcohol
DAFC	direct alcohol fuel cell
DEMS	direct electrochemical mass spectrometry
DFT	density functional theory
EASA	electrochemically active surface area
EDS	energy-dispersive X-ray spectroscopy
FAA-2	anion exchange membrane (FumaTech)
fcc	face-centered cubic
FRC	fraction collector
FTIR	Fourier transform infrared spectroscopy
FWCNT	few-walled carbon nanotube
GNF	graphitized carbon nanofiber
hkl	Miller indices
HPLC	high performance liquid chromatography
IR	infrared
MEA	membrane electrode assembly
MWCNT	multi-walled carbon nanotube
Nafion [®]	Sulphonated tetrafluorethylene copolymer (Du Pont)
OCV	open circuit voltage
ORR	oxygen reduction reaction
PEFC	polymer electrolyte fuel cell
PEM	proton exchange membrane
PVBTA	poly(vinylbenzyl trimethyl ammonium chloride)
PZC	potential of zero charge

RE	reference electrode
RHE	reversible hydrogen electrode
SCE	single crystal electrode
SEM	scanning electron microscopy
SERS	surface enhanced Raman spectroscopy
SWCNT	single-walled carbon nanotube
TEM	transmission electron microscopy
UPD	underpotential deposition
WE	working electrode
XPS	X-ray photoelectron spectroscopy
XRD	X-ray diffraction

List of Symbols

A	area (cm^2)
c	concentration (mol dm^{-3})
D	ratio of the FTIR single beam spectra
E	fuel cell voltage (V)
F	Faraday constant, ($96485.31 \text{ C mol}^{-1}$)
i	current (A)
j	current density (A cm^{-2})
n	number of electrons
Q_H	charge (C) or charge density (C cm^{-2})
R	resistance (Ω)
R_g	molar gas constant ($8.314510 \text{ J (mol}^*\text{K)}^{-1}$)
S	single beam spectra from the FTIR
T	temperature (K)
W	power density (W cm^{-2})

Greek

α	transfer coefficient of an electrochemical reaction
η	overpotential (V)

Subscripts and superscripts

0	initial or standard value
act	activation
ads	adsorbed
b	bulk
con	concentration
h	hydrogen
me	measured

<i>mono</i>	monolayer
<i>ohm</i>	ohmic
PdO	palladium oxide
<i>ref</i>	reference
<i>s</i>	surface
<i>sol</i>	solution
<i>upd</i>	underpotential deposited

1 Introduction

Polymer electrolyte fuel cells (PEFC) using liquid fuels are promising electrochemical power generators, especially for portable applications such as laptops or cell phones, due to their high energy densities in comparison to batteries and independency of the electrical network. In this thesis PEFCs that utilize liquid alcohols as fuels for an anode and oxygen (or air) for a cathode are studied and this cell type is called a direct alcohol fuel cell (DAFC). These cells are not commercially viable until the cost of the total system is significantly reduced and the lifetime extended.

One of the expensive materials in the cell is the precious noble metal catalysts such as Pt or Pd that is required to oxidise organic alcohols on the anode at low temperatures and even on these noble metal catalysts the reaction are slow. Reaction rates can be increased by introducing another metal to the catalyst to form bimetallic catalyst and this added metal can also non-noble which reduces the cost of the total system. In order to find the best catalyst for each fuel in each media a screening of a wide range of possible individual and bimetallic catalysts must be performed. Though, the DAFC tests require large amount of the studied material and are time consuming due to the complex membrane electrode assembly (MEA) preparation and therefore, other methods to study the activity of electrode materials are needed.

Electrochemistry offers rapid methods to test developed materials in experiments where only a small sample amount is required, moreover, in a three electrode cell the electrode reactions can be studied separately (in the fuel cell it is problematic to separate response from anode and cathode reactions from each other). In addition, the same setup can be utilized to explore the effect of the catalyst material, bimetallic catalyst, support material and ionomer in acidic and alkaline media by the change of electrode material or electrolyte. Nevertheless, these experiments must be performed in such manner that the results obtained apply also in a DAFC. In this thesis the effect of nanoparticle preparation (**Publication III**) and bimetallic catalysts (**Publication V**) as well as carbon

supports (**Publication IV**) are studied with an electrochemical system in order to obtain insight prior to DAFC tests.

Alcohol oxidation reactions can proceed via various paths leading to preferred or unwanted reaction intermediates and products and it is vital to understand which circumstances favour a certain route. In DAFC experiments it is impossible to single factors and more controlled systems must be used. For instance, to identify the effect of the surface structure for these reactions single crystal electrodes (SCE) can be utilized (**Publication II**). In addition, by solely electrochemical methods only limited reaction products or intermediates can be detected and these methods can be combined with spectroscopic or chromatographic methods to obtain the product distribution as a function of the cell potential (**Publications I and II**).

Another key issue for commercial fuel cell applications is the durability of the cell components: if the power produced by the DAFC decreases more than 20 % from the initial value in a month it is defined as not commercially viable. Unfortunately, the DAFC is a corrosive environment and materials that withstand these conditions are limited. The current materials used in fuel cells, especially membranes and carbon supports, are vulnerable to corrosion and they should be replaced with more long-lasting materials. Nanocarbon supports have been introduced as more durable catalyst supports for PEFCs [1,2] and in **Publication IV** various carbon support materials are tested for their activity and durability in both an electrochemical and a fuel cell environment.

Overall, to commercialize this technology cheaper, durable and more efficient materials for DAFCs must be introduced. The objective of this thesis is to show how different model electrodes are utilized to understand the phenomena occurring on a DAFC anode and making a contribution to the development of electrochemical methods to study anode materials for DAFCs in fuel cell related conditions.

1.1 Fuel cell

A fuel cell is a device that converts the chemical energy of the reactants to electricity and product molecules. The first fuel cell was introduced by Sir William Grove already in 1839 [3], however, its applications remained limited due to the rapid development of combustion engines. In the first fuel cell, hydrogen and oxygen were fed to separate closed containers, having sulphuric acid as electrolyte and Pt shred as electrodes, and the products obtained were electricity and water. At present, various types of fuel cells for different applications have been developed and they are classified by their electrolyte material.

This thesis concentrates on DAFCs having a solid, ion conducting membrane that can be either proton exchanging (acidic, PEM) or anion exchanging (alkaline, AEM). This electrolyte provides a channel for produced ions to cross from one electrode to the other and at the same time prevent electron and reactant transport. Together with the two electrodes (consisting of metal nanoparticle often on a support material and conductive ionomer) they form a membrane electrode assembly (MEA). In Figure 1 a schematic of a methanol fuelled DAFC with Nafion[®] PEM is presented.

Figure 1. Methanol and oxygen fuelled DAFC with a proton conductive membrane electrolyte. In addition, the reactions occurring on the electrodes and in the cell are presented. (Unpublished)

The alcohol-water mixture is fed to the anode electrode where the alcohol reacts with water producing carbon dioxide, protons and electrons. The ion conductive membranes are electrical insulators and therefore electrons flow from the anode to the cathode through outer circuit and this movement of electrons or electricity can be utilized or stored. The protons are transported through the membrane material to the cathode where they encounter an oxygen stream and cycled electrons to form water molecules.

1.2 Scope of this Thesis

As discussed in the previous pages, to commercialize DAFCs more efficient and still cost efficient electrode materials must be introduced. In this thesis, detailed methods to test new electrode materials in fuel cell related circumstances has been described and the focus is on the methodology rather than in material science. This work focuses on the phenomena occurring at the anode and therefore the phenomena in the membrane and at the cathode are not discussed in detail.

In this thesis methanol, ethanol and isopropanol have been selected as alcohols due to their interesting behavior seen in previous work [4,5]: methanol has the highest performance, isopropanol has the possibility to produce high open circuit voltages (OCV) and ethanol produces the largest current density of all fuels having more than one carbon atom. All these alcohols have been studied only in Publications I and V, however, the focus in Publication III and IV is on ethanol and methanol oxidation, respectively. In Publication II methanol, isopropanol and their mixtures have been investigated, but the alcohol mixtures are excluded from this thesis to narrow the scope.

2 Experimental approaches

2.1 Electrochemistry

2.1.1 Electrochemical cell

The electrochemical activity of fuel cell anode materials can be studied *ex situ* in a three electrode electrochemical cell (Figure 2). The alcohol oxidation occurs on the working electrode (WE) surface and a balancing reduction reaction takes place at the counter electrode (CE). The reference electrode (RE) is located in a separate container being in contact with the cell via a Lugging capillary which tip is placed as close to the WE surface as possible to minimize ohmic drop. The rate and direction of the reaction taking place at the WE is controlled with a potentiostat by varying the potential between the WE and the RE. Any current that flows will pass only through the WE and CE, leaving the reference potential at the RE unperturbed.

Figure 2. Schematic diagram of three electrode electrochemical cell with a glassy carbon planar working electrode (WE), a plate counter electrode (CE) and a reference electrode (RE). (Unpublished)

For the CE a Pt sheet or wire having a large surface area is selected to ensure that the reactions occurring on this electrode would not limit the current. The selection of the RE is dictated by the electrolyte solution: in acidic medium a reversible hydrogen electrode (RHE) or a saturated calomel electrode ($E = 0.2412$ V vs. RHE) and in alkaline medium a RHE or a mercury oxide electrode ($E = 0.64$ V vs. RHE) is used. Nevertheless, in this thesis all the potentials from the electrochemical cell have been presented versus RHE at pH 1 in order to facilitate the interpretation of the results. In addition, three different types of WE are introduced in this work: planar Pt and Pd electrodes, Pt single crystal electrodes (SCE, in section 2.1.2) and nanoparticles on a glassy carbon electrode (in section 0).

In fuel cell related electrochemical experiments sulphuric acid (H_2SO_4) is commonly used as an electrolyte because it dissociates to sulphate ions resembling the active sulphononic acid groups in the Nafion[®] PEM. Though, in the solid membrane sulphate ions are attached to the polymer chains and thus have a different mobility when comparing to the dissolved ions. It has been reported that the presence of sulphate ions in the electrolyte leads to changes in voltammetric profiles as a result of ion adsorption on the electrode surface [6,7]. Therefore, 0.1 M perchloric acid ($HClO_4$) that dissociates only to form weakly adsorbing perchlorate ions has been chosen as a supporting electrolyte in acidic medium. In alkaline medium 0.1 M NaOH or 0.5 M KOH electrolyte is used and these solutions are freshly prepared to avoid gradual dissolution of glass [8] that had been observed to cause changes in voltammetric profiles [9].

During all the experiments the surface potential of the working electrode is controlled to avoid unwanted anion adsorption. The electrolyte is deaerated prior to the experiments by purging with Ar or N_2 gas. This procedure is performed in order to remove the oxygen from the electrolyte that would cause a shift in the voltammogram [10]. Prior to the experiments, the electrode surface is cleaned electrochemically except for the SCE electrodes that are cleaned by annealing (Section 2.1.2). The cleaning in the electrochemical cell is performed by cycling to high potentials (planar Pt and Pd electrode) or with the CO adsorption/oxidation method (nanoparticle electrodes). After

the measurements in the pure electrolyte, the electrolyte is changed to one containing the same supporting electrolyte and studied alcohol. To prevent the changes in the concentration, the gas inlet is first directed into a bubbler bottle containing the same solution as the cell and subsequently the alcohol solution saturated gas is directed into the experimental cell (this is not done in the case of the HPLC measurements because the experimental time is short, Publication I).

Cyclic voltammetry and chronoamperometry are the electrochemical methods used for studying the alcohol oxidation and catalyst poisoning. From the cyclic voltammogram of alcohol oxidation two important issues can be observed: firstly, the onset potential of alcohol oxidation can be determined with the anodic sweep as the potential where notable current starts to flow. Secondly, the maximum normalized current (or current peak) and the potential where it is obtained are a point of interest because with higher current more power can be obtained from the fuel cell. The chronoamperometric experiments are applied in order to obtain more information of the catalyst poisoning by the reaction intermediates that are presented in Section 3.1. Overall, a good catalyst for alcohol oxidation would be one with low onset potential, high normalized current at as low potential as possible and could maintain the normalized current at constant potential during the extended experiments.

2.1.2 Preparation of well-ordered SCE

Well-ordered single crystal electrodes (SCE) used in Publication II are prepared by cutting a metal bead with laser at a specific angle so their surface is constructed with atoms of only one orientation. The well-ordered low-index surface must be atomically flat meaning that they have only large terraces and should possess as few surface defects as possible. A detailed procedure of this preparation process was first published by Clavilier *et al.* [11]. Prior to every set of experiments the SCE is flame annealed with a Bunsen burner to burn away impurities and to reorder the surface atoms [12]. With this high temperature treatment, the thermal movement of the metal atoms will progressively

order the disordered parts of the surface. Moreover, at high temperature both oxidation and thermodesorption of different impurities occurs resulting in a clean electrode surface. However, when the electrode is cooling down (especially around 100 °C) the ambient impurities of air commence to oxidise on the surface due to the high catalytic activity of the clean Pt surface. This can be avoided by cooling the crystal in a reducing atmosphere like a H₂ stream. When the crystal is cooled down it is dipped into ultrapure water in equilibrium with H₂/Ar atmosphere and the surface becomes protected by a water droplet [13]. As the crystal originated from a metal bead it also has reactive edges with mixed atom orientation and if these imperfections are in contact with the electrolyte they would interfere the measurements. Therefore the crystal is dipped into the electrolyte and then pulled upwards as shown in Figure 3 to form a meniscus. This procedure also ensures that the reactive surface area is exactly the same as the geometric area of the crystal surface, and therefore, all the currents obtained with the SCE experiments can be normalized with the geometric area of the electrode.

Figure 3. Formation of a meniscus with a single crystal electrode. (Unpublished)

2.1.3 Nanoparticle electrode preparation

To prepare a nanoparticle electrode for electrochemical experiments that would resemble a fuel cell anode, the similar catalyst ink utilized for the DAFC anode is prepared and dried on a glassy carbon working electrode. The catalyst powders are dispersed in solvent (ethanol or 1-methyl-2-pyrrolidione), then mixed with a magnetic stirrer and sonicated with an ultrasonic bath. Ionomers which are dispersed polymers resembling the corresponding membrane material are added to the dispersion. For acidic

ink Nafion[®] dispersion and for alkaline ink fumion[®] FAA-2 or poly(vinylbenzyl trimethyl ammonium chloride) (PVBTA) dispersions are used in Publication III and V, respectively.

2.1.4 Electrochemically active surface area

In order to evaluate the activity of the catalyst material, the currents obtained from the electrochemical experiments must be normalized with the catalytically active surface area on the catalyst. For planar electrodes and SCEs this corresponds to geometric surface area that is in contact with the electrolyte, however, with nanoparticle catalyst on a porous support the determination is more difficult because the idea of the catalyst is that the active surface area is far larger compared to the geometric area. Therefore a concept of electrochemically active surface area (EASA) has been introduced defining the three dimensional catalyst surface area where the reactants can adsorb and oxidize.

EASA determination of electrodes having only one metal are relatively straight forward and is well described for each metal [14]. Firstly, in the special case of Pt electrode the EASA can be determined through the hydrogen adsorption from the electrolyte onto the Pt surface. The charge needed for underpotential deposition (UPD) of hydrogen (Q_H) can be obtained by integrating the surface area of hydrogen adsorption region in a cyclic voltammogram where the effect of the double layer capacitance has been subtracted [15]. For this method it is commonly assumed that the adsorption process of H_{UPD} on Pt surface is a 1:1 (*i.e.* a hydrogen atom will adsorb on each Pt sites) [14] and that the charge required for adsorption on polycrystalline Pt to form a monolayer is $Q_{H,mono} = 210 \mu C cm^2$. This value is estimated with the assumption that the density of the atoms is $1.31 \times 10^{15} cm^{-2}$ [15,16] pertaining to the (100) face of the Pt electrode [17]. Overall, the electrochemical surface area can be determined with the equation

$$A = \frac{Q_H}{Q_{H,mono}} \quad (1)$$

and this method has been used for EASA determination for planar Pt electrodes in Publication I. Nevertheless, it is good to keep in mind that the properties of nanoparticles differ from bulk metals and this method has found to provide decreased EASA for small nanoparticles < 3.5 nm [18].

Another technique to determine EASA of a Pt surface is utilization of a well-controlled probe molecule having relatively standard adsorption on the Pt surface sites over a wide potential area. Carbon monoxide (CO) can be used for this purpose because it is a strong adsorbent which also displaces other adsorbed species from the surface site and therefore can be used for the EASA determination as well as cleaning the electrode surface [19-21]. Firstly, the electrolyte is saturated with CO gas which is rapidly adsorbed on the Pt surface. Secondly, stripping experiments are performed from which the charge required for the adsorbed CO to oxidize to CO_2 can be estimated by integrating the CO oxidation peak (black scan in Figure 4) where the base curve (red scan) in pure electrolyte has been subtracted.

Figure 4. CO stripping curves for Pt (A) and PtRu (B) nanoparticles in 0.1 M HClO_4 electrolyte with 10 mV s^{-1} scan rate. Black and red scans refer to oxidation of adsorbed CO monolayer and pure electrode surface, respectively. (Unpublished data)

Whereas Pd electrode exhibits an indefinable hydrogen adsorption region, as seen in Figure 5, and therefore the hydrogen adsorption method cannot be accurately used for the EASA determination. Instead, reduction of PdO_x is commonly utilized [14,22-25]. In this method oxygen is assumed to chemisorb onto the catalyst surface with 1:1 process [26] prior to O_2 evolution. When PdO_x is formed but the oxygen evolution had not yet started a cathodic sweep is performed where the reduction of this oxide can be

observed as a peak at 0.68 V (Figure 5). By integrating this peak, the charge needed for the PdO_x reduction Q_{PdO} is obtained

$$A = \frac{Q_{\text{PdO}}}{Q_{\text{PdO},\text{mono}}} \quad (2)$$

where $Q_{\text{PdO},\text{mono}} = 405 \mu\text{C cm}^{-2}$ [27] and corresponds to the value for the monolayer reduction of PdO_x . In Publications I and III determination of the EASA of both planar and nanoparticle Pd electrodes have been performed with this method.

Figure 5. Cyclic voltammogram of ALD prepared Vulcan supported Pd nanoparticles in 0.1 M NaOH electrolyte with 20 mV s^{-1} scan rate. (Unpublished data)

The determination EASA of a bimetallic catalyst is more complex: as can be seen from Figure 4 the potential region of CO stripping is well-defined on the Pt electrode, however, on a PtRu electrode the upper potential limit where the all CO would be totally oxidized cannot be defined. Moreover, CO oxidation on Ru surface occurs at lower potential and therefore, the CO stripping potential and peak width vary with the element composition [28] making the EASA determination challenging. For this bimetallic catalyst neither hydrogen adsorption, due to the low onset potential of RuO formation overlapping the hydrogen adsorption/desorption region, nor metal oxygen reduction, due to limited upper potential of the anodic sweep that hinders the metal oxide formation (Figure 4B), can be used. Therefore, in publications IV and V the currents in the electrochemical cell have been normalized by the amount of the catalyst.

2.2 Direct Alcohol Fuel Cell

The fuel cell used in the DAFC experiments is a single cell with serpentine flow channels by Fuel Cell Technologies. The active surface area of the cell is 7.29 cm^2 which is selected because it is large enough to produce relative currents, but also small enough that small catalyst samples can be tested. Figure 6 presents the cell with all the other components: membrane electrode assembly (MEA), two Teflon[®] gaskets which ensure that no leakages from the cell occurs and two gas diffusion layers of carbon cloth having 10 and 60 wt% Teflon[®] dispersion on the surface for anode and cathode, respectively. On the cathode thicker Teflon[®] coating is used to increase the hydrophobicity of the gas diffusion layer that hinders the cathode flooding.

Figure 6. Single cell fuel cell, carbon cloths, Nafion-PtRu MEA and white Teflon gaskets. (Unpublished)

A proton exchange membrane (PEM) Nafion[®] by Dupont or anion exchange membrane (AEM) fumapem[®] FAA-2 from FumaTech company are used as electrolytes. For PEFC with hydrogen fuel a Nafion[®] 112 membrane is often used, however, in DAFCs the alcohol-water mixture can permeate the membrane to the cathode reacting on the cathode catalyst to poisoning species and causing mixed potentials. In addition, the excess of liquids (methanol and water) on the cathode hinders the gas diffusion [29]. To

decrease the methanol permeability from anode to cathode a thicker membrane material can be selected: in the case of the Nafion[®] membranes the lowest methanol crossover is obtained with the thickest Nafion[®] 117 membrane (178 μm), however, the highest power densities in DAFC are obtained with the Nafion[®] 115 membrane (127 μm) [30] and therefore the latter has been selected as an electrolyte in acidic DAFCs (Publications IV and V). The thickness of the FAA-2 membrane in water is considerably lower (25 μm) in comparison to Nafion 115, however, the methanol permeability is decreased [31].

Fuel cell electrodes consist of the similar inks previously described for the nanoparticle catalyst electrode (Section 2.1.3): metal nanoparticle catalyst on carbon support, ionomer dispersion and solvent. The ionomer is used in order to increase the ionic conductivity of the electrode [32 - 34] and improving the adhesion between the membrane material and the electrode layer. In the acidic MEAs Nafion[®] dispersion is used and the optimum ionomer-carbon ratio depends on the carbon support of the catalyst particles: for carbon black (Vulcan) the optimized value for anodes is between 25-40 wt% [35-38] and in our experiments the aim is for 30 wt% ionomer. As for the less porous nano carbon supports (CNT and GNF) only limited optimization has been performed, however, in preliminary studies it has been found that higher (over 50 wt%) would be more beneficial [39,40]. Nevertheless, the MEA preparation in Publication IV revealed that with nanostructured carbon support the ionomer-carbon ratios are more difficult to control. At the cathode side the amount of ionomer is crucial because an excess would decrease the porosity of the catalyst layer resulting in an increase in oxygen mass transport resistance and poorer cell performance [32] and therefore, the aim for the ionomer on the cathode was lower (20 wt%). For the FAA-2 membrane anion exchange ionomer PVBTA is used in a similar fashion as in electrochemical inks outlined in Section 0 and the same ionomer-carbon ratio as for the Nafion MEAs is targeted in order to obtain comparable results. Nevertheless, these ratios are not optimized for an alkaline DAFC but were used to obtain comparable results with the Nafion cells and further optimization of the MEA preparation could increase the power densities significantly.

The catalyst inks are sprayed directly on both sides of the membrane material, to obtain thin-film catalyst layers that minimize the transport limitations within the layers [41], and are dried at 80 °C for 2 h. Subsequently, the MEAs are hot pressed in order to obtain well compressed electrodes to increase the conductivity of the MEA reducing ohmic losses [42]. The heat pressing procedure has been shown to have no significant effect on the morphology of the Pt nanocatalyst [43] nor particle size at low pressing times [44]. In contrast, the improved performance of the cell is attributed to the microstructure of the cathode facilitating the reactant diffusion through this electrode [43]. The conditions for the hot pressing are 130 °C for 120 s under a force of 50 kN for the Nafion MEAs and 80 °C for 120 s under a force of 50 kN for the FAA-2 MEA.

The fuel cell is assembled by sandwiching anode end plate, Teflon gasket, MEA, another gasket and cathode endplate. The cell is sealed with 8 screws and tightened with a 10 Nm torque. All the currents and powers obtained from the DAFC are normalized with the cell area of 7.29 cm². The fuel cell test station includes: anode fuel container (1), temperature control units for the cell and gas pipes (2), liquid fuel pump (3), the cell (4), gas flow control unit (5), gas humidifier (6) and anode outlet (7) which are outlined in Figure 7.

Figure 7. The single cell test station. (Unpublished)

3 Electrocatalysis of alcohol oxidation

Electrocatalysis is defined as the effect of an electrode material on the reaction rate occurring on an electrode surface. In the case of alcohol oxidation this means the influence of an electrode material on the adsorption and oxidation rate of an alcohol molecule. When an electrochemical setup is used, the reaction rate on the WE can be controlled by the electric potential thereby affecting the electrodes affinity to electrons. The electrocatalysis on a Pt electrode is described in detail in previous work [45].

For each reaction there is a thermodynamic standard potential where the reaction takes place under standard conditions which is defined by the thermodynamic properties of the reactants and products. In the case of ethanol oxidation to CO_2 the total reaction is:

In reality the alcohol oxidation reaction commence at higher potential (around 0.35 V in Figure 8) due to reaction overpotential (η) that is defined as the difference between the applied potential and the thermodynamic standard potential:

$$\eta = E - E^0 \quad (3)$$

Figure 8. Electrooxidation of 0.5 M methanol and isopropanol on a polycrystalline Pt electrode in 0.1 M HClO_4 (A) and 0.5 M NaOH (B) (Publication II). In addition, electrooxidation of 0.5 M ethanol in acidic medium is also shown (Unpublished). Scan rate 20 mV s^{-1} , third scans are presented.

The total overpotential can be defined as a sum of activation overpotential (η_{act}), ohmic overpotential (η_{ohm}) and mass transport overpotential (η_{conc}).

$$\eta = \eta_{act} + \eta_{ohm} + \eta_{conc} \quad (4)$$

At low current densities the alcohol oxidation is limited mostly by activation overpotential that is due to the sluggish electron transfer in the cell reactions and is defined as:

$$\eta_{act} = \frac{R_g T}{\alpha n F} \ln \frac{i}{i_0} \quad (5)$$

According to *Ohm's law* there are always resistive losses when current is drawn from the cell and this is called as ohmic overpotential:

$$\eta_{ohm} = iR \quad (6)$$

This overpotential term is not so relevant in electrochemical cell where the total cell resistant is low due to well conductive liquid electrolyte, however, it has high impact in solid electrolyte with lower conductivity utilized in fuel cells (Section 6.0). The concentration overpotential is defined as

$$\eta_{con} = \frac{R_g T}{\alpha n F} \ln \frac{c^s}{c^b} \quad (7)$$

and becomes dominant at high current densities where the surface concentration (c^s) significantly decreases when compared to the bulk concentration (c^b). Nevertheless, with electrochemical experiments a concept of electrode reaction onset potential is often used describing the potential where the initiation of significant current can be observed even though this value is difficult to define accurately.

In addition, Figure 8 underlines the importance of the electrolyte pH for alcohol oxidation: the onset potential of alcohol oxidation and maximum current densities vary with the pH. For instance, the activity of methanol oxidation increases in alkaline medium whereas, conversely, the activity of isopropanol oxidation decreases. In this chapter the reaction mechanisms of the studied alcohols are discussed in detail, moreover, spectroscopic methods to detect alcohol oxidation reaction products and intermediates as a function of the electrode potential are presented.

3.1 Reaction mechanisms

Alcohol oxidations reactions are very complex and are not entirely understood even though they have been intensively studied for decades. Modern spectroscopic methods have given a boost to these studies, however, there are still some reaction intermediates that are very difficult to detect due to either low quantities or fast reactions to other intermediates.

3.1.1 Adsorption

Alcohol oxidation occurs at various steps; yet, the first step for all molecules is the same: the molecule adsorbs on the electrode surface and forms a bond with the electrode (chemical adsorption):

When an electrode is placed into an aqueous electrolyte the electrode surface is covered by water molecules, its dissociated products like H_{ads} , OH_{ads} or even adsorbed oxygen depending on the electrode potential and the solution pH [47]. For each electrode material there is a potential of zero charge (PZC) correlating directly to the work function of that material and therefore the value differs with each metal. For SCE electrodes the PZC can be determined with accuracy, however, for polycrystalline

electrodes the values depend on electrolyte and density of different surface sites: for instance values between 0.18-0.31 V have been reported [48,49] for polycrystalline Pt. As reported for Pt(111) surfaces [50], at potentials lower than the PZC value the water molecules adsorb with positively charged atoms (hydrogen) down and only weak hydrogen bonds between molecules are formed (Figure 9). When the PZC is reached the water molecules rotate and at higher potentials the molecules are oriented with the negatively charged oxygen atom down. In this state the water molecules can create hydrogen bonds with other water molecules in the bulk covering the electrode with an ice-like net structure. The optimal moment for large alcohol molecules to displace the solvent molecules on the electrode surface is the PZC when water is not strongly attached to the surface.

Figure 9. The orientation of water molecules on a Pt(111) surface depending on the electrode potential. The potential of zero charge for Pt(111) is 0.35 V [50]. (Image from [45])

By increasing pH, the potential window - where water is stable - shifts to more negative potential by 59 mV per pH unit, as a consequence of the Nernst equation also changing the work function of the metal electrode subsequently causing changes to the adsorption strengths [51] and leading to a change in voltammograms as seen in Figure 8. Furthermore, some of the reaction intermediates of alcohol oxidation can act as an acid or base and therefore changes in the electrolyte pH will also result in changes to the product distributions [52,53]. Another advantage of alkaline medium is that in acidic medium corrosion and catalytic activity limits the choice of metal electrode to noble metals, in contrast, in alkaline medium also other than noble metals can be considered [54-56] reducing the cost of the cell and thus making alkaline DAFCs as a focus of interest in future research.

3.1.2 Methanol

Methanol is the simplest organic alcohol that has been widely used in DAFCs because it has no C-C bond that is difficult to cleave at low temperatures. Nevertheless, methanol is toxic, easily flammable and has a low boiling point (65 °C). In addition - as will be discussed in Section 6.3 - as a small, polar molecule it has larger level of crossover in comparison to larger alcohols. Even though methanol is the simplest alcohol its oxidation is very complex [57], however, the main steps are summarized in Figure 10.

Figure 10. Schematic of the methanol oxidation mechanism on Pt electrodes. (Unpublished)

In electrochemical environment the first step, after molecule adsorption on the electrode, is the rupture of the C-H bond in the methanol molecule [58]

With this step protons are formed which can be observed in Figure 8 as an increased current between 0.4-0.6 V potential at both media. After this the dehydrogenation continues and adsorbed formaldehyde is formed (reaction 1 in Figure 10):

As suggested early by Breiter [59] and confirmed with spectroscopic experiments [60-62] after the methanol dehydrogenation to formaldehyde two parallel reactions routes to form CO_2 are possible: via COOH_{ads} or CO_{ads} type of intermediates (reaction 2 and 3). In more detail: dehydrogenation can continue further from formaldehyde until an adsorbed CO molecule is formed (reaction 3) and two more electrons are produced:

Nevertheless, after this the reaction route is blocked until water can adsorb onto the electrode surface providing the required oxygen species (reaction vi and vii):

In a parallel path formaldehyde can be oxidized to formic acid (reaction 2), however, this reaction step also requires an external oxygen molecule:

Finally, the formic acid can desorb from the electrode surface back to the solution or be oxidized further to CO_2 (reaction 5):

Overall, methanol oxidation to CO_2 depends on the external oxygen provided by the adsorbed water. This step cannot occur until at the electrode potential where water can dissociate is attained, which for the Pt electrode is $> 0.4 \text{ V}$ [60,63] indicating that at lower potentials the electrode surface is blocked by an intermediate. For this reason another metal, on which the water dissociation occurs at a lower potential, is added to pure Pt to form bimetallic catalyst that will be further addressed in Section 5.1.

In alkaline medium the reaction routes and product distribution alter due to the change in the work function of the electrode material: the main products on a polycrystalline Pt electrode [64] are formate (formic acid in alkaline medium dissociates rapidly to formate ion HCOO^-) and bicarbonate (HCO_3^-) in the low potential region (> 0.2 V) as well as CO_2 above a potential of 0.7 V. On Pt(111) electrode [65] the main products are formate and CO_2 . According to DFT calculation the electrocatalytic activity of Pd on alcohol oxidation is strongly depended on pH [66] and at high pH solutions Pd could be an alternative for Pt. Nevertheless, the fundamental understanding of alcohol oxidation on Pd surface at high pH electrolyte has not been fully obtained but is a focus in Publication I and III.

3.1.3 Ethanol

Ethanol is an interesting fuel for DAFCs because it can be produced from renewable sources by fermentation. In addition, as a larger molecule when compared to methanol it has a higher boiling point (78 °C), higher theoretical energy density as well as lower crossover rate through both acidic and alkaline membranes [5,67,68]. Nevertheless, this molecule has the thermodynamically stable C-C bond that is difficult to cleave at low temperatures. Similarly as with methanol the first step of ethanol oxidation is the adsorption of the ethanol molecule on the catalyst surface followed by two parallel paths (reaction 1 and 3) [46,69] presented in the Figure 11.

Figure 11. Schematic of the ethanol oxidation mechanism. (Unpublished)

Firstly, ethanol oxidation can occur by the same route as methanol oxidation to form aldehyde and then the corresponding acid (reaction 1 and 2 in Figure 11). Nevertheless, acetic acid is a very stable molecule at DAFC anode related potentials [70,71] and has a tendency to rather dissolve into the solution than oxidize further, as a consequence, it can be considered as an end product of ethanol oxidation. This reaction path produces only 4 electrons and it has been suggested that most of the current observed in ethanol oxidation in acidic medium would be due this reaction implying that acetic acid is the main oxidation product [72,73].

The other parallel pathway requires the cleavage of the C-C bond from either an ethanol or acetaldehyde molecule (reaction 3 and 4) and it has been found that this is more likely to occur from the acetaldehyde molecule than directly from ethanol because the reaction 4 is faster [73]. The molecule with two carbon atoms will break to form two separate molecules: the first initially having one oxygen atom (CO_{ads}) and the other having only carbon and hydrogen atoms (CH_x). The latter molecule slowly transforms to CO_{ads} already at < 0.4 V potentials [73,74]. When external oxygen from water dissociation (reaction v) is available both of these fragments undergo further oxidation to CO_2 (reaction 5).

In the case of alkaline medium, the same reaction mechanism applies, however, the increase in pH will change the reaction product distribution: with spectroscopic experiments it has been found that on a Pt surface the main ethanol oxidation product is acetate [75] (acetic acid in alkaline medium dissociates rapidly to acetate ion CH_3HCOO^-). Similarly as in acidic medium the C-C cleavage most probably occurs via an acetaldehyde molecule where the α -hydrogen atom (in the CH_3 group) is slightly acidic causing deprotonation of acetaldehyde in high pH electrolytes. When the charge is delocalized at the one end of the molecule, the C-C bond becomes less shielded and is easier to break. Combining more facile C-C bond cleavage and the fact that CH_x [52] and CO_{ads} [76,77] can be adsorbed at lower potential in alkaline medium it could be deduced that selectivity towards C-C bond rupture pathway is enhanced.

3.1.4 Isopropanol

Isopropanol (2-propanol) is a molecule with three carbon atoms and hydroxyl group at the middlemost carbon atom affecting the configuration of the molecule and alters the molecules adsorption and oxidation properties. In addition, isopropanol is also the largest molecule in this study and therefore possesses the lowest crossover rate through acidic and alkaline membranes [5,67] as well as the highest boiling point (83 °C) and energy density. It has been shown previously that 1-propanol (where the hydroxyl group is attached to the end carbon atom) behaves like other primary alcohols (methanol and ethanol) in DAFC studies [5] whereas isopropanol behavior differs from that trend and is therefore selected as a part of this work. Though, with the larger amount of atoms in the molecule also the reaction mechanism is more complex and it has been presented in detail by Pastor *et al.* [78], however, in Figure 12 a simplified version is outlined.

Figure 12. Schematic of the isopropanol oxidation mechanism. (Unpublished)

The first step after the adsorption on the electrode surface is the dehydrogenation from the central carbon (reaction 1 in Figure 12). Subsequently, there are three different paths to follow: firstly, further dehydrogenation to acetone (reaction 2) that is quite stable molecule and can be desorbed from the electrode surface in the presence of isopropanol into the bulk solution with competitive adsorption displacement [78]:

or be further oxidized to CO_2 (reaction 6) with external oxygen from the water dissociation. Another option is that the first dehydrogenation product $\text{CH}_3 - \text{CHO} - \text{CH}_{3,\text{ads}}$ can further react from the central carbon via reaction 3 to $\text{CH}_3 - \text{C} - \text{CH}_{3,\text{ads}}$ and this product can either oxidize to CO_2 (reaction 5) or be converted to propane (reaction 4) which is released to the electrolyte [78]. Nevertheless, the most important fact is that in contrast to the primary alcohols no adsorbed CO is detected [79,80]. Even though small amounts of CO_2 have been observed [78] it has been formed without the CO_{ads} intermediate that is considered to be a strong catalyst poison at low potentials. The product distribution implies that the middlemost carbon atom is the reactive center of all the reactions that occur on a Pt electrode. Overall, it is clear that on a pure Pt surface the main reaction product is acetone due to the fast isopropanol dehydrogenation and slow reaction rate of other products [81-83].

To further understand the role of acetone in isopropanol oxidation, a cyclic voltammetry on Pt nanoparticle surfaces with 1 M acetone has been performed (Figure 13) to observe if acetone could further oxidized at this potential region as suggested by the mechanistic study with FTIR analysis in acidic medium [78]. As shown in Figure 13 only a small indication of acetone oxidation can be observed above potential of 0.4 V and therefore acetone can be considered as the main product of isopropanol oxidation in this medium.

Figure 13. Electrooxidation of 1 M acetone on commercial Pt/C in 0.1 M HClO_4 with 20 mV s^{-1} scan rate. (Unpublished)

In alkaline medium, no specific reaction mechanism studies with spectroscopic methods have been performed, however, electrochemical methods imply that in this medium isopropanol dehydrogenation to acetone would occur through strongly adsorbed intermediates poisoning the catalyst surface [84]. Similarly as in acidic medium (Figure 13), in alkaline medium the activity of acetone oxidation on a Pt electrode is low [85] and is limited to the high potential region irrelevant for DAFC anode. In Publication II (and also Figure 8) lower isopropanol oxidation currents in alkaline medium on Pt electrode has been observed indicating that even though oxidation of primary alcohols is enhanced in alkaline medium on Pt electrode this is not the case with the secondary alcohol isopropanol. On the contrary, isopropanol oxidation on other catalyst materials, such as Au promoted Pd, have shown considerably higher currents in alkaline medium with comparison to the Pt [86] implying that the rate of isopropanol oxidation can be increased by the choice of the electrode material.

3.2 Detection of reaction products

To understand the reaction processes behind the alcohol oxidation it is crucial to verify the reaction intermediates and products at each potential. Unfortunately, with solely electrochemical methods these cannot be observed, but additional methods that can be combined with electrochemical ones to obtain product distribution as a function of potential have been developed. Most commonly used are spectroscopic methods: direct electrochemical mass spectrometry (DEMS) [87,88] that is limited to the detection of the volatile substances produced on the electrode, Fourier transform infrared spectroscopy (FTIR) [89-91] which can detect the adsorbed reaction intermediates and products on the electrode with infrared light and surface enhanced Raman spectroscopy (SERS) [92] that employs visible light rather than infrared and can therefore be used to measure molecular vibrations at low wavelengths. In addition, also chromatographic methods with a direct connection to the electrochemical cell can be applied: one example is the high performance liquid chromatograph (HPLC) that has a sample collection system in the vicinity of the electrode surface. With this method only liquid

reaction products can be detected, however, these are often the most interesting ones especially for the oxidation reactions of large organic molecules. In next two chapters HPLC (Publication I) and FTIR (Publication II) are presented in more detail.

3.2.1 HPLC method

The high performance liquid chromatography (HPLC) can be used for the detection of liquid reaction products and its advantages are a cheap, facile system and straightforward product analysis when compared to more complex spectroscopic methods. The limiting factor is that only liquid reaction products can be detected and therefore existence of CO or CO₂ molecules cannot be confirmed. Nevertheless, in the case of alcohol molecules (especially with various carbon atoms) intermediate aldehydes, ketones and acids play an important role. The limitation of the early HPLC studies was that the samples were taken from the electrolyte of the electrochemical cell [93,94] or from fuel cell anode output [95] which requires high concentration of these products for detection and the concentration of the products could be presented as a function of time. Since then these systems have been developed further and now HPLC can be combined with an electrochemical cell allowing the sample taken from the vicinity of the WE and the results can therefore be presented as a function of WE potential.

This kind of system was used in Publication I and is described in detailed elsewhere [96]. In short: as can be seen in Figure 14 an electrochemical cell with planar Pt or Pd electrode is mounted with an aqueous electrolyte consisting KOH electrolyte and the studied alcohol. The HPLC sample collection tip is placed in vicinity of the WE surface and pumping is applied to gather small samples close to the electrode surface. A very slow potential sweep is performed in order to precisely control the product distribution at the selected potential. Prior to the experiments, the probable reaction products are analyzed in alkaline medium with the same HPLC system to determine peaks at the retention times correlating with each product.

Figure 14. Schematic diagram of the on-line sample collection with fraction collector (FRC) equipped with an in-house designed micro-sized sample collecting tip for rapid sample collection close to the electrode surface during voltammetry, with subsequent analysis with a HPLC system. (Publication I)

As is well-known from organic chemistry, aldehydes and ketones with α carbons (without attached oxygen atoms) are reactive in alkaline medium and tend to form aldol condensation products [97]. Prior to the experiments all these products are analyzed in solutions with added base to see if this reaction occurs: formaldehyde does not possess α carbon and no additional peaks are observed, acetaldehyde has α carbon, but no aldol condensation product is detected. As acetone possesses two α carbons, during the HPLC analysis a small additional peak is observed while analyzing a solution of 1 mM acetone and 0.1 M KOH. In this process the α carbon of one acetone molecule reacts with the oxygen atom in the other acetone molecule and in the presence of base forms diacetone alcohol (DAA) according to the reaction:

This same product has been also observed during the experiments and could be excluded from the analysis because it is not a reaction product alcohol oxidation. As discussed earlier, in alkaline medium acids produced are immediately deprotonated. The HPLC system cannot detect ions and therefore, acidiceluent has been used in the analysis to ensure detection of carboxylic acids, nevertheless, in Figure 15 the products are classified with the species originating from the electrode surfaces. With primary

fuels corresponding aldehydes or carboxylic acids are detected, however, the Pd electrode shows increased selectivity towards acid formation due to the faster reaction rate from aldehydes to acids. For isopropanol oxidation the only detected liquid product on the electrode was acetone which correlates well with the findings of other electrochemical experiments (Figure 13) and the spectroscopic findings presented in Section 3.1.4.

Figure 15. Potential sweeps and formed products of 1 M alcohol oxidation on the Pt (A) and Pd (B) electrodes in 0.5 M KOH electrolyte with 1 mV s⁻¹ sweep rate. The black lines represent the potential sweep with sample collection and the red ones without. (Publication I)

Publication I presents the results from the combined voltammetry and HPLC analysis (which are also seen in Figure 15) for both planar electrodes. For each experiment, firstly a potential sweep without sample collection (red line) was performed, subsequently, the same potential sweep with the same scan rate was performed with sample collection (black line). This was done in order to observe the effect of sample collection on the electrode reaction: if the current density was higher in the presence of the sample collection, it could mean that some poisoning species exist on or near the

electrode surface which are removed during the sample collection [96]. In contrast, when current density increases without sample collection the removed molecules have most likely been active reaction intermediates that could have still reacted further. With this in mind, it can be clearly seen from Figure 15 that surface poisons exist on a Pt electrode for methanol and a Pd electrode for ethanol oxidation which is most likely to be CO_{ads} that has been observed with spectroscopic methods [89,91]. In the case of ethanol this fluctuation in current could also be due to diffusion limitations that are addressed in Section 5.5. For the other cases investigated here CO_{ads} would not seem to have a strong role.

From Figure 15 it can be also seen that one electrode materials offers a more preferable route for alcohol oxidation: in the case of methanol current densities and product amounts on Pt are higher compared to Pd indicating that Pt is more active at catalyzing methanol oxidation in this medium and if a bimetallic catalyst is desired it would be preferable to be Pt based. As for ethanol oxidation, the current densities and reaction product amounts are similar on both electrodes with the exception that the Pd electrode would seem to be more selective towards acetate formation. Organic acids in alkaline DAFCs are not preferred products because they cause changes in the membrane pH. As was discussed in Section 3.1.3, the C-C bond is easier to break from acetaldehyde and therefore, also in the case of ethanol Pt based bimetallic catalysts would be preferable.

Isopropanol oxidation to acetone on a Pt electrode (Figure 15A) would seem to occur at three different stages: first at 0.25-0.5 V, second directly after at 0.5-0.9 V and the third at 1 – 1.4 V. In addition, no surface poisoning by intermediates was observed with the HPLC implying that acetone does not strongly adsorb on a Pt surface in alkaline medium. This is in contrast to the mechanism suggested by Markiewicz *et al.* [84], however, further spectroscopic experiments are required to confirm these findings. On the contrary, on a Pd electrode acetone formation would seem to occur smoothly. Even though higher current densities were obtained in comparison to Pt (also observed by Liu *et al.* [98]), lower amount of acetone is produced indicating that other reaction products

not detectable with HPLC might be produced and additional methods are required for their confirmation.

3.2.2 FTIR method

In situ Fourier transform infrared spectroscopy (FTIR) can be combined with an electrochemical set-up to detect adsorbed species on the electrode surface as a function of the WE potential. To achieve this, an especial spectroelectrochemical cell having a prismatic CaF_2 window must be used, where the IR beam can be directed at the electrode surface (Figure 16). A WE (a planar electrode or a SCE) is placed close to the IR window so that in the between there is only a thin electrolyte layer (1-10 μm) which enables the adsorption and desorption of the reactants and products and minimizes the adsorption of IR light by the solvent.

Figure 16. Schematic representation of the thin layer configuration for *in situ* IR experiments (not in scale). (Unpublished)

All the spectrums are calculated as the ratio of two single beam spectra S_{me} and S_{ref} corresponding to the measurement potential and at reference potential (0.10 V), where the studied reaction does not occur, respectively.

$$D = -\log \left(\frac{S_{me}}{S_{ref}} \right) \quad (8)$$

The negative and positive bands observed on the calculated spectra indicate depletion of reactant and formation of products, respectively. For each IR active stretch there is a “fingerprint” wavenumber indicating the presence of that functional group on the electrode surface. Thus, the larger molecules are studied, the more IR active parts there are and the interpretation of the results becomes more demanding, however, in the case of isopropanol the restriction of the oxidation to acetone facilitates the interpretation. In Publication II the oxidation of isopropanol has been studied with FTIR on a Pt(111) electrode in 0.1 M HClO₄ and the spectra are presented in Figure 17.

Figure 17. FTIR spectra collected in 0.5 M isopropanol solution on a Pt(111) electrode surface in 0.1 M HClO₄. The bands circled refer to isopropanol consumption (blue), CO₂ formation (red) and acetone formation (green). (Publication II)

The consumed isopropanol can be seen as a negative band at 2900 cm⁻¹ (blue circle) in Figure 17. In addition, negative bands at 1700, 1428, 1369 and 1240 cm⁻¹ (green circles) are observed in the low potential region >0.3 V and corresponding to different vibrations in an acetone molecule. The presence of this product at the low potential explains the low onset potential of isopropanol oxidation observed on polycrystalline electrodes in Figure 8A. The CO₂ formation (red circle at 2345 cm⁻¹) is visible only at 0.9 V implying that at this potential isopropanol can be totally oxidized, however, this

high potential is not relevant for a DAFC anode implying that acetone is the only product of isopropanol oxidation in acidic DAFC with Pt electrode. Though, the most interesting observation is that no linearly or bridge bonded CO is observed at any potential as has been reported also by other groups [78,99,100].

4 Single crystal electrodes

To understand alcohol oxidation on the DAFC electrodes, the effect of the surface composition to adsorption and oxidation of the reactant molecules is needed. Though, electrode reactions in the DAFCs takes place on the three phase boundary including the liquid or gaseous reactants, metal particles with a mixture of surface sites as well as ionomer increasing the complexity of the system and making it impossible to evaluate the effect of an individual component. Therefore, single crystal electrodes (SCE) having known surface structure can be used to estimate the effect of surface structure to alcohol oxidation in electrochemical cell even though these electrodes cannot be used directly in a DAFC.

The surface of a SCE is made atomically flat by laser beam as described in Section 2.1.2 and all the atoms on the surface possess only one crystal orientation. For many noble metal catalysts such as Pt and Pd the crystal lattice is face centred cubic (fcc) indicating that the atoms are at the centre of the lateral surfaces and at the corners of the unit cell (Figure 18). The surfaces of the SCE are characterised by Miller indices (hkl) that represent the reciprocal of the intercepts of the plane defined by the x -, y - and z -axes.

Figure 18. Face centred cubic (fcc) crystal lattice. (Unpublished)

For fcc systems, there are three ways to arrange the surface atoms to obtain minimum surface energy, called low-index planes, and in the case of the fcc lattice are (100),

(111) and (110) representing atomically flat surfaces with square, hexagonal and rectangular arrangement of the surface atoms (Figure 19), respectively. The proper preparation and cleaning of the SCEs is crucial to obtain perfectly oriented surfaces, otherwise, the advantage of having a known surface structure is lost.

Figure 19. Low-index planes (100), (111) and (110) of fcc systems. (Unpublished)

The most common surface defects are adatoms, islands, vacancies, holes and monoatomically high steps (Figure 20) and these surfaces represent more closely to nanoparticle surfaces than low-index SCEs. It is possible to prepare an SCE electrode with controlled surface defects, called stepped single crystal surfaces, and their properties and activity for alcohol oxidation is presented in previous study [45]. To understand which phenomena exist already on low-index electrode and which are caused by surface defects, adsorption and oxidation mechanisms are often first studied on low-index SCEs.

Figure 20. Most commonly found surface defects on a regular electrode surface. (Unpublished)

Alcohol oxidation reactions are complex and parallel reaction paths, which are often surface sensitive, exist. Some reaction routes are more desirable and the information of which surface morphologies catalyze preferred routes is significant. For instance, ethanol oxidation occurs through the dual path mechanism presented in Figure 11 (Section 3.1.3) and Figure 21 represents the same schematic with the additional information of which paths are most favorable of each low-index Pt surfaces determined by Colmati *et al.* [69]. According to these authors on Pt(111) terraces ethanol oxidation occurs via acetaldehyde to acetic acid and only a small CO₂ fragment is observed. In the case of Pt(110) surface very little acetic acid is produced, but instead the C-C bond cleavage occurs at a high rate (both from ethanol and acetaldehyde) at wide potential range. As for Pt(100), at the low potential region (0.3 - 0.4 V) the intensity of the CO band increases showing that C-C cleavage takes place. Only at clearly increased potentials (from 0.65 V) the formed CO layer is oxidized and simultaneously, acetic acid formation initiates on this surface site.

Figure 21. Schematic of ethanol oxidation mechanism on low-index Pt SCEs. (Unpublished)

In addition, it is also possible to modify SCE surfaces with adatoms of another metal [101-104] and these electrodes are of special interest because they resemble bimetallic nanoparticles that will be discussed in Section 5.4. For instance addition of Ru atoms on

Pt(332) surface revealed that Ru has only an active role in the oxidation of CO_{ads} to CO_2 , but has no role in enhancement of $-\text{CH}_3$ transformation to CO nor C-C bond cleavage [101]. This information helps to shed light on the role of the added metal to the bimetallic catalyst.

As alcohol oxidation is enhanced at certain surface sites, it would be preferable that nanoparticles would have an increased density of those surface atoms. Currently, it is possible to increase the amount of specifically oriented surface atoms on nanoparticle surfaces with the synthesis method that was first introduced by El-Sayed *et al.* in 1996 [105]. This also changes the shape of these particles: cubic nanoparticles are essentially covered by (100), octahedron by (111) and rhombic dodecahedron by (110) sites. Since then various groups have reported methods to obtain shape controlled Pt [106-108] and Pd [109] nanoparticles and they are especially interesting for fuel cells applications because increased performance can be obtained without increasing the catalyst loading which would also facilitate the MEA preparation by diminishing the thickness of the required electrode layer.

Nevertheless, for commercial applications the stability of these particles is of the high importance. Susut *et al.* [110] cycled both cubic and octahedral/tetrahedral particles between -0.25 and 1.2 V for 1000 scans in electrochemical cell and found only small changes in the voltammograms recorded in pure electrolyte, however, with methanol addition the voltammograms were more affected. Moreover, TEM images confirmed that with large 9-10 nm cubic particles severe agglomeration did occur, instead octahedral/tetrahedral particles were rather well-preserved. This confirms that particles with different shape and size have different stabilities and methods to increase the stability in fuel cell conditions are required.

4.1 Characterization of SCEs

Every single crystal surface has its own “fingerprint” cyclic voltammetry depending on the potential at which the protons and anions of the solutions are adsorbed and desorbed on/from the surface (Figure 22). The voltammograms of different Pt low-index planes in 0.1 M HClO₄ acid and 0.1 M NaOH are presented in Figure 22A and B, respectively. For all electrodes the upper limit of the anodic sweep is selected as 0.9 V in order to avoid the surface oxidation and in the special cases of Pt(100) and Pt(110) electrodes in acidic electrolyte the upper limit is decreased to 0.5 V to inhibit small rearrangements of the crystal structure [111].

Figure 22. Voltammetric profiles for Pt low-index planes in 0.1 M HClO₄ (A) and 0.1 M NaOH (B), with 50 mV s⁻¹ scan rate, third scans are shown. (Unpublished)

The voltammograms in HClO₄ electrolyte (Figure 22A) resemble ones obtained previously for samples cooled down in air [112] and in a H₂ atmosphere [113,114]. On Pt(110) proton adsorption starts at very low potentials and there are two main peaks

(0.14 V and 0.25 V vs. RHE) corresponding to the Pt(110) terraces and Pt(110) steps. On Pt(100) the main peak is observed at 0.35 V referring to the Pt(100) terraces, however, there is also a small shoulder at 0.30 V. Finally, for Pt(111) the hydrogen adsorption is observed as a plateau from 0.05 V to 0.35 V and a sharp peak at a potential of 0.8 V corresponds to OH adsorption on the (111) oriented surface sites [114]. If additional peaks appear in the voltammogram it is normally due to the unsuccessful annealing and cooling process of the SCE or impurities in the electrolyte (contamination). Examples of surface defects formed without flame treatment are outlined by Clavilier *et al.* [115].

In alkaline medium (Figure 22B) the adsorption processes on Pt(100) can be divided into three different zones: the first zone is at $0.05 < E < 0.4$ V where one peak (0.29 V) that is related to hydrogen adsorption/desorption phenomena is observed. The second zone is described by three individual peaks at 0.39 V, 0.47 V and 0.57 V; Tripkovic *et al.* suggested that these peaks are associated with OH adsorption on the surface [116]. The last zone above 0.7 V, where increased current density is observed, refers to oxide layer formation. For the Pt(110) surface only one large peak at 0.27 V with a shoulder at 0.29 V is observed correlating hydrogen adsorption to this surface site [112,117]. At higher potentials another peak has been reported between 0.7 – 0.8 V [112,117], however, in our case this peak is very small (0.73 V) and this difference is most likely due to different surface cleaning method. In the case of Pt(111) a smooth flat curve with a small shoulder is seen at 0.26 V in the hydrogen adsorption/desorption region and the OH adsorption peak is observed at 0.77 V as was also seen in acidic medium (Figure 22A). These findings correlate well with ones reported earlier [112,118,119] implying that Pt(111) is not that sensitive to surface annealing and cooling as the other two crystals.

4.2 Alcohol oxidation on SCEs

It is well known that specific surface configurations promote or inhibit different reaction rates as has been seen with ethanol oxidation in Figure 21. In Publication II the oxidation behavior of methanol and isopropanol on low-index SCEs are studied with acidic and alkaline electrolyte (Figure 23). In addition, to the data presented in Publication II ethanol oxidation on these SCEs in acidic medium is added to Figure 23.

Figure 23. Electrooxidation 0.5 M methanol and isopropanol on Pt(100), Pt(110) and Pt(111) in 0.1 M HClO_4 (A) and in 0.1 M NaOH (B). (Publication II) In addition, for acidic medium also ethanol electrooxidation is presented. (Unpublished) Scan rate 20 mV s^{-1} , third scans are shown.

From Figure 23 it can be seen that in acidic medium both primary alcohols methanol and ethanol behave similarly: on Pt(100) the onset potential of alcohol oxidation initiates at a considerably high potential (0.7 V) and the current density obtained is between 4-6 mA cm^{-2} . Similar high onset potentials have been reported earlier on Pt(100) for methanol [60,113,120,121] and ethanol [69]. However, isopropanol has a

different behavior: the onset potential is somewhat lower and the current density obtained is 3-4 times higher when compared to the other studied alcohols. On the Pt(110) surface the onset potential of all alcohols has shifted towards less positive potentials and the current density maximum for the anodic direction is between 2-4 mA cm⁻². Thus, the current density values for reversed scans are higher indicating that the oxidation of reaction intermediates occurs. On the Pt(111) surface the onset of isopropanol oxidation is similar to the Pt(110) surface, however, the current density obtained is 8 times higher. Nevertheless, this surface is strongly poisoned by reaction intermediates, resulting as 40 % decreasing in the current density between the first and third scan (Figure 4 in Publication II). For methanol and ethanol oxidation the onset potential is similar to that observed on Pt(110), but the current densities are more modest. Overall, it was concluded in Publication II and notable from Figure 23 that the activity of methanol and ethanol oxidation decreases in the order Pt(100) > Pt(110) > Pt(111) whereas for isopropanol the most active surface site is Pt(111) followed by Pt(100) and finally Pt(110).

In alkaline medium, methanol oxidation shows a lower onset potential around 0.5 V on Pt(100) and Pt(110) surfaces and the current density is also low (1.5 – 6 mA cm²). In contrast, on the Pt(111) surface onset potential shifts to more positive potentials but a considerably high current density of 25 mA cm² is obtained. This confirms that the most active surface site for methanol oxidation is Pt(111) [65] and that the high current densities observed on the polycrystalline electrode in Figure 8 is mainly contribution of this site. For isopropanol oxidation the onset potential on Pt(100) and Pt(110) sites is remarkably low between 0.25 – 0.35 V, however, the current densities obtained are modest. For Pt(111) site the onset potential is also shifted to more positive values and the current density is only half what is produced in acidic medium. This confirms the observations made with the polycrystalline electrode (Figure 8) that isopropanol oxidation on Pt electrode is not enhanced in alkaline medium that was the case with methanol and ethanol. Moreover, the increased performances with the Pd catalyst observed in Publication I suggest that Pd based catalyst would be more interesting for isopropanol oxidation in alkaline medium.

5 Carbon supported nanoparticle electrodes

In DAFCs power produced increases by the size of the electrodes, however, for portable applications one of the most critical issues is the size of the total system. If pure metal plates are used as electrodes in DAFCs the EASA would be the close to the geometric area. When supported nanoparticles are used the equivalent EASA from the same geometric area can be 20-30 times higher, thus, the size of the cell would remain the same and therefore nanoparticle catalyst are used in current DAFC applications.

Clusters of metallic particles are generally considered as nanoparticles if their diameter is below 100 nm and their chemistry is considered to have been initiated by Faraday in his work in the mid-1800s [122]. These particles belong to the size range where they possess different properties compared to both molecules and bulk metals, however, the most interesting properties are observed with clusters having a diameter under 10 nm [123]. The nanoparticles can be protected from agglomeration with surfactants, however, that would also inhibit the adsorption of the alcohol molecules and therefore, in fuel cell applications the nanoparticles are usually attached onto conductive support materials which are reviewed in Section 5.2.

Even though supported nanoparticle catalysts can provide higher powers required for commercialization, there are several new challenges that need to be resolved before fuel cells using these materials are commercially viable: the particle size distribution must be controlled and agglomeration of these particles inhibited, a preparation process with good reproducibility and constant quality of the catalyst must be developed and finally the thickness and morphology of the electrode layer with both liquid and gas flow must be optimized. In this chapter the preparation and the properties of individual and bimetallic nanoparticles as well as their support materials are discussed and the alcohol oxidation reactions on these nanoparticle catalysts are presented.

5.1 Properties of nanoparticles

As discussed in the previous section the properties of nanoparticle catalysts deviate from those of bulk metals and become dependent on particle size. The electronic properties of metal particles, especially in the size range from 2-10 nm, are interesting for fuel cell related reactions such as methanol oxidation [124-126] and the oxygen reduction reaction (ORR) [126,127]. Decreasing the particle diameter increases the binding energy of adsorbents such as H, CO and OH [128] causing changes in oxidation processes on the catalyst. Particularly, with very small particles (< 5 nm) the binding energy becomes very strong inhibiting especially alcohol oxidation and therefore, the optimum particle size for DAFC anode reactions is higher in comparison to the cathode reaction (ORR) whose optimum diameter is around 3 nm [129].

As most of the nanoparticle properties depend on the particle size, the durability of these clusters is the key issue for electrocatalysis: due to their high specific surface energy nanoparticles inherently have a strong driving force for assembling themselves into larger agglomerates to reduce the overall surface energy [130] *i.e.* small clusters merge forming larger ones (Figure 24), furthermore, the smaller the particles the more rapid the agglomeration proceeds [131]. Three different mechanisms for nanoparticle agglomeration on a carbon support have been proposed [132]: 1) the Ostwald ripening process where small particles dissolve in the ionomer phase and redeposit on the surface of larger particles, 2) with random cluster-cluster collisions that is followed by liquid-like coalescence of these particles or 3) the growth can occur at the atomic scale by minimization of the clusters' Gibbs free energy. The catalyst agglomeration has also been observed in the extended fuel cell tests [133]. These agglomerates can remain on the support surface - reducing the EASA of the catalyst - or the agglomerates can be detached by the fuel flow in DAFC. Consequently, the performance of the fuel cell decreases not only because of the lower EASA but also because the electrode reactions are more active on small particles (<10 nm). Nevertheless, the agglomeration can be impeded by the selection of a catalyst support having stronger interactions with the attached nanoparticles which is discussed further in the next section.

Figure 24. Schematic representation of Pt nanoparticle agglomeration on and detachment from the support material surface. (Unpublished)

A voltammogram of Pt nanoparticles and a polycrystalline Pt electrode are presented in acidic and alkaline electrolytes (Figure 25). This electrochemical behavior of cleaned nanoparticles resemble only partly the polycrystalline electrode, however, the peak shapes in the hydrogen adsorption/desorption region and surface oxidation region are strongly affected by the shape [106] and size of the nanoparticles [18]. By decreasing Pt particle size the PtO_x reduction peak shifts to more negative potentials and the hydrogen adsorption peaks attenuate independent of the electrolyte pH as can also be seen in Figure 25. It should be noted that in Figure 25 the potential range for nanoparticle electrodes is wider resulting as thicker PtO_x layer and enlarged oxide reduction peak.

Figure 25. The cyclic voltammetry of Pt nanoparticles and a polycrystalline Pt electrode in 0.1 M HClO_4 (A) and 0.1 M NaOH (B) with 20 mV s^{-1} scan rate. The nanoparticles have been normalized with the catalyst mass (refer to left y-axis) and the polycrystalline with geometric area (refer to right y-axis). The potential range is wider for nanoparticle experiments increasing the thickness of PtO_x layer and, subsequently, enlarging the PtO_x reduction peak. (Unpublished)

5.2 Support materials

To stabilize the metal nanoparticles and prevent their immediate agglomeration a porous catalyst support is used as a platform for nanoparticle growth. These porous materials enable the high dispersion of metal particles onto their surface that is particularly important with expensive noble metal catalysts like Pt and Pd. The most widely used supports for fuel cell electrodes are carbon based materials and conductive oxides such as ITO, TiO₂, WO_x, IrO₂ and SnO₂ [134]. The required properties for the catalyst supports are: high surface area (to obtain high EASA), corrosion resistance and a stable surface where the nanoparticles can be attached with strong bonds to inhibit the particle agglomeration.

Carbon based catalyst support materials are commonly used for fuel cell applications due to their high surface area, low cost and high conductivity. Carbon black (commercial product Vulcan) is an amorphous carbon consisting of spherical pieces of graphite possessing a high percentage of 20-40 nm diameter mesopores (Figure 26a), which provide a high accessible surface area for nanoparticles and ionomer as well as facile transport of reactants and products [135]. Nevertheless, carbon black is not very tolerant of the demanding physical and chemical circumstances in the fuel cell and is under these conditions oxidized [136]

resulting in a decrease in the DAFC performance. In addition, this oxidation process can also lead to changes in the hydrophobicity of the support surface impeding reactant flow to the electrode [138].

Recently, various types of nanocarbon supports have been introduced to replace carbon black due to their increased tolerance for carbon corrosion in *ex situ* measurements [138-140] that could increase the lifetime of the catalyst in DAFCs, however, durability studies in fuel cells are still very limited [2]. Moreover, because the metal nanoparticles

are bound to the surface of the support material an interaction effect between them is likely to occur [135]: the support material can modify the electronic character of the metal particles affecting the reaction characteristics and could also modify the geometric shape of the catalyst particles.

The most commonly used are carbon nanotubes (CNT) which consist of individual layers of graphene sheets wrapped into the shape of a cylinder (Figure 26c). If these cylinders consist of only one graphene layer they are called single-walled carbon nanotubes (SWCNT) or if there are various concentric and parallel cylinders they are called few-walled (FWCNT) or multi-walled carbon nanotubes (MWCNT). The length of the nanotubes is typically 50-100 μm and the diameter is 0.3-5.0 nm and 1.4-100 nm for SWCNT and MWCNT [141], respectively. These nanotubes are normally pre-treated in acid to introduce surface functional groups such as carboxylic acids on the nanotube surface [142] enhancing the nanoparticle deposition.

Figure 26. TEM images of PtRu nanoparticles on Vulcan (a), GNF (b) and FWCNT (c) supports. The lower the molecular weight of the atom the darker it can be observed in the images: the low molecular weight carbon is seen as gray and in comparison metals clusters (Pt and Ru) are seen as white spots. (Publication IV)

The outcome of the pre-treatment procedures (in 2 M HNO_3 and 1 M H_2SO_4 at 120 $^\circ\text{C}$) for the electrochemical performance is presented in Figure 27. From Figure 27 it can be seen that after 2 h treatment there is a clear increase in current density obtained throughout the potential window whereas after 4 h the performance has declined. Furthermore, there is an addition peak at 0.55 V appearing after 2 h treatment possibly

due to the electroactive surface groups on the carbon nanotubes surface [136] which are created by this procedure. Nevertheless, the chronoamperometric experiments (Figure 27B) in methanol solution showed that the highest current density is obtained with catalyst that had the 4 h acid treatment and therefore that treatment was selected as the procedure for CNT activation in Publication IV and subsequently, the deposition of the metals has been performed by the reduction method.

Figure 27. Effect of the catalyst support pretreatment on 30 wt% PtRu/FWCNT for the voltammetric profile (A) and 1 M methanol oxidation in chronoamperometric experiment at 0.7 V (B), in 0.1 M HClO₄ electrolyte with 20 mV s⁻¹ scan rate. (Unpublished)

Another widely investigated nanocarbon materials are graphitized carbon nanofibers (GNF) (Figure 26b) that consist of multiple layer by layer placed parallel graphene sheets aligned in definite directions such as platelet or ribbon and the diameter of these fibers is 2-100 nm with length of 5-100 μ m [135]. Due to their graphitic nature these structures have high electronic conductivity, thermal oxidation resistance [143,144] and high mesoporous content that can enhance the mass transfer through the catalyst layer [145]. Even with low catalyst loading high performance have been obtained for methanol oxidation with this support in comparison to Vulcan [146] and the platelet type PtRu/GNF has shown superior performance for methanol DAFC [147]. The GNF materials used in Publication IV had increased diameter (150 nm) and small length of 10 μ m and therefore they formed very thick structure having lower porosity than GNFs in general. Accordingly, also the GNFs in Publication IV were acid treated (for 6 h) prior to catalyst deposition to form surface functional groups for anchoring the nanoparticles.

MWCNT have been intensively studied over the last decade and in Publication IV the aim is to study PtRu/FWCNT because to the best of our knowledge no previous study of their activity for methanol oxidation had been performed. In this same study also commercial, parallel GNF materials were selected to evaluate the effect of various carbon supports in the same publication: the voltammetric profiles for these materials compared to the PtRu on carbon black (Vulcan) support are presented in Figure 28.

Figure 28. Cyclic voltammograms of PtRu catalyst material on different carbon supports in 0.1 M HClO_4 with 20 mV s^{-1} scan rate. (Publication IV)

Publication IV shows that the PtRu nanocatalyst applied on different supports in acidic electrolyte resemble (Figure 28), thus, the H_{UPD} peak on PtRu catalyst shifts to more positive potentials with PtRu/GNF catalyst in comparison with PtRu/Vulcan as has also been observed with Pt/GNF catalyst [148,149] implying that GNF might modify the electronic properties of the catalyst due to stronger interaction between the support and the catalyst. For PtRu on CNT support neither here nor previously [150] has reported any shift. Furthermore, with PtRu/FWCNT an additional feature appears in the oxide formation region (0.55 V) that is observed also in Figure 27 and is related to the acid treatment reported previously by other groups [150-152]. This feature have been reported only on CNTs and not on GNFs even though they have both been acid treated, indicating that different surface groups are formed on each support.

5.3 Catalyst preparation

In order to control the size and distribution of the metal nanoparticles on the support material, the nanoparticle preparation must be performed carefully and the resulting catalyst material must be characterized with various methods to ensure successful preparation. The most common method used to prepare metal nanoparticle catalyst on supports for fuel cell electrodes is a reduction method where the metal salts and the support material are mixed in a beaker. Subsequently, a reduction agent, for instance sodium borohydrate (NaBH_4) [153-155] or glycerol [156-158], is added drop wise to the solution to reduce the metal particles directly on the catalyst support. This traditional method has a disadvantage that it is difficult to scale up without losing the control of catalyst particle size and distribution.

Another method, which could be also scaled up to industrial scale, is atomic layer deposition (ALD) where metal nanocatalysts can be formed on planar or porous substrates [159]. In general, the advantages of ALD method are the facile scale up and highly dispersed homogeneous surface that can be obtained due to the self-limiting nature of the ALD process [160]. However, during the catalyst preparation process in Publication III (Pd on Vulcan support) a uniform monolayer was not obtained; instead Pd nanoclusters were formed. The tentative explanation for this behavior is proposed to be due to challenge to form a continuous ALD film on a hydrophobic support such as graphene. However, on Vulcan support there are e.g. OH-groups that are hydrophilic and can operate as seeds for nanoparticle growth and therefore it is most likely that the Pd atoms attach only to these seeds and form nanoclusters whereas the other parts of the carbon support remain untouched leading to evenly distributed metal nanoparticles on the support. This growth mode is called as the Island (or Vollmer-Weber) growth mode and is a typical outcome if the atoms are more strongly bond to each other than to the hydrophobic substrate material [161].

Nevertheless, as the monolayer is not obtained the catalyst structure is more difficult to control and thus the method requires further optimization. Overall, if the proposed

mechanism is confirmed this method could become very important in the DAFC catalyst preparation due to similar or increased activity with decreased metal loadings in comparison to commercial nanoparticle catalysts reported previously [162,163] and in Publication III. As an example ethanol oxidation on an ALD prepared Pd/C and commercial Pd/C catalysts is shown in Figure 29 where it can be noted that not only lower onset potential but significantly increased current density already at the lower potentials is obtain when the currents are normalized with the catalyst loadings.

Figure 29. The activity of ALD prepared (ALD) and commercial (Com) Pd catalyst on Vulcan support for 1 M ethanol oxidation in 0.1 M NaOH with 20 mV s⁻¹ scan rate and 1800 rpm rotation of the WE. (Publication III)

The essential step following the catalyst preparation is the physical characterization of the material to ensure that the preparation process has been successful and that an evenly distributed catalyst material is obtained. Typically, first a method to obtain the atomic composition is applied: the catalyst powder can be studied with atomic emission spectroscopy (AES), X-ray diffraction (XRD) or X-ray photoelectron spectroscopy (XPS) in order to obtain the metal loadings (AES) and oxidation states of the metal components (XPS and XRD). Nevertheless, these methods do not provide any information of the metal distribution on the support material and therefore additional microscopy methods are used: scanning electron microscopy (SEM) or transmission electron microscopy (TEM) can be applied for imaging the metal catalyst particles on the carbon based support because the atomic weight of the latter component is lower with comparison to metal atoms. In these images normally the heavier component is seen with a darker color. An example of TEM images can be seen in Figure 26 for the

PtRu catalyst on carbon supports. SEM can be equipped with energy-dispersive spectroscopy (EDS) that can analyze the elements on the SEM sample surface and an example of this technique can be seen in Figure 30 for the ALD prepared Pd/C catalyst.

Figure 30. ALD prepared Pd/C catalyst. SEM image of the catalyst surface (a) and the element analysis by EDS: distribution of carbon (b) and Pd (c) on the surface. (Publication III)

5.4 Bimetallic nanoparticles

Oxidation of organic alcohols is complex because these molecules have several chemical bonds between different atoms that need to be broken for the total oxidation and some of the reaction intermediates are very stable (for instance acetone, acetic acid and CO_{ads}). To find an individual metal that would not only catalyze all C-H, C-O and C-C bond cleavage but would also do this at low temperature and potential is challenging and therefore, a bimetallic catalyst is often utilized. The additional metal should form oxygen containing surface species at lower potentials to further enhance the oxidation of intermediates which require adsorbed oxygen to be oxidized further. Nevertheless, not all metals that fulfill these criteria can be used due to possible negative effects such as inhibition of alcohol adsorption or low stability in fuel cell conditions. Sn, Re, Ru, Ge, Rh and Mo among others, have been reported to have a positive effect on the oxidation of an organic alcohols in acidic medium [164- 170] and in this medium there is a general consensus that for methanol oxidation PtRu - proposed by Petrii *et al.* [164] – and for ethanol oxidation PtSn [171] are the most active catalyst.

The effect of oxygen donating metals is explained by the bi-functional mechanism first proposed by Watanabe *et al.* [165]. This theory explains that the increase in performance is due to the separate roles of the individual metals: on the Pt surface methanol is adsorbed and oxidized to CO_{ads} whereas on the Ru surface water will dissociate (reaction v) already at potential that is 0.08-0.14 V lower in comparison to Pt [63] enabling the CO_{ads} oxidation (reaction vi) at lower potentials:

In Figure 31 the formation of PtO_x layer can be seen in both media after the double layer capacitance above 0.4 V. On the contrary, the formation of RuO_x layer initiates already in the hydrogen adsorption region (< 0.4 V) implying that water dissociation will occur at a lower potential in comparison to a Pt surface.

Figure 31. Cyclic voltammogram of commercial Pt/C and PtRu/C nanoparticles in 0.1 M HClO₄ electrolyte (A) and in 0.1 M NaOH (B) with 20 mV s⁻¹ scan rate. (Unpublished)

In addition, it has been proposed that the added metal could also have a ligand (electronic) effect on the noble metal [172,173]: the bond between Pt and CO_{ads} is very strong inhibiting the further reaction of the adsorbed molecule, however, when Ru (or Sn) is added to Pt catalyst the energy of the Pt-CO_{ads} bond is decreased and the reaction rate increases. Current knowledge suggests that at least both of these mechanisms apply [174-176] indicating that only bimetallic catalysts could increase the reaction rate of alcohol oxidation at low temperatures.

The differences in the voltammogram features for a PtRu catalyst in comparison to pure Pt nanoparticles depends on the Ru content in the catalyst: if the Ru content is less than 50 wt% the features resemble pure Pt nanocatalyst, however, in the opposite case more Ru like behavior is exhibited [177-179]. When there is 20 wt% or more Ru in the catalyst the adsorption of protons to Pt(100) surface is suppressed [177] indicated by the fact that only one hydrogen adsorption peak (on the Pt(110) sites) is observed. This is also the case in our commercial PtRu catalyst (40 wt% of Pt, 20 wt% of Ru and 40 wt% of carbon) and consequently, only one adsorption peak is observed in Figure 31A. Moreover, with the SCE electrodes (Figure 22) it can be easily seen that the OH adsorption initiates around 0.55 V and 0.40 V on a Pt surface in acidic and alkaline media, respectively. Adsorption on Ru sites would seem to commence at lower potential in both media (already before the double layer regions) on PtRu nanoparticles (Figure 31), however, this is difficult to confirm with purely electrochemical methods and would benefit from combined spectroscopic techniques.

Nevertheless, preparing nanoparticle catalyst with two or several different metals is a great challenge: the material needs to be prepared so that both metals are evenly distributed on the support surface because it is vital that the different materials are located in the vicinity of each other. With DFT calculations it has been determined that the distance between adsorbed alcohol molecule on Pt site and adsorbed hydroxyl on Ru site cannot be larger than 4.5 Å because the molecules would only repel each other and no reaction would occur [180]. It is also good to keep in mind that this mobility of the adsorbed species on the surface depends on the surface structure [181] and can considerably limit the reaction rate. Moreover, if a well distributed bimetallic catalyst is obtained there still remains the issue of what will happen over time. As has been discussed in Section 5.1 small nanoparticles have a tendency to agglomerate to decrease the total surface energy indicating that even though Pt and Ru metal atoms would be originally located in favorable places in fuel cell conditions they agglomerate and the initial performance can be lost. Therefore, a good electrocatalyst material for DAFC applications should include a corrosion resistant support, with evenly distributed nanoparticles that are as strongly attached to the support material as possible.

5.5 Alcohol oxidation on nanoparticles

Alcohol oxidation on nanoparticle catalysts have been studied *ex situ* with electrochemical methods (cyclic voltammetry and chronoamperometry) in order to define the effect of support material, preparation method and bimetallic catalyst on these reactions. Firstly, in Publication III the effect of catalyst particle preparation that has a major role in electrocatalysis is investigated (Figure 32) by comparing the activity of ethanol and isopropanol oxidation on a commercial and an ALD prepared Pd catalyst.

Figure 32. 1M Ethanol and isopropanol oxidation on ALD prepared and commercial Pd/C catalyst in 0.1 M NaOH with 10 mV s^{-1} scan rate. The black dashed lines correspond to still WE and red solid lines to WE that was rotated with 1800 rpm. (Publication III).

In addition, the effect of rotating the WE (0 and 1800 rpm, respectively) is studied to mimic the circumstances on the DAFC anode where the fuel solution is constantly flowing through the catalyst layer hindering the diffusion limitations. The results in Figure 32 highlight that if the WE is not rotated some mass transfer limitations in

alcohol oxidation will be observed, particularly, for the commercial catalyst. The curves recorded without rotation diverge from the ones with rotation at 0.6 V potential and in without rotating the oxidation peak current is obtained due to limited diffusion of alcohol to (or a reaction product from) the electrode surface. This implies that the catalyst poisoning observed for ethanol oxidation on Pd catalyst with the HPLC above 0.8 V in Publication I and in Figure 15 is probably due to diffusion limitations and not catalyst poisoning as stated in Publication I. In the case of the fuel cell cathode reaction (ORR) the observed limiting current increases along with increased rotation rate, however, alcohol oxidation reactions are slow and only slight enhancement at higher rotation rates has been observed. For the ALD catalyst the shape of the curves remains independent of the rotation speed but the normalized currents increase considerably implying that the transport of reactants in the vicinity of the electrode surface has a major impact. For ethanol and isopropanol oxidation the intermediate products like acetic acid and acetone, respectively, are formed and desorption of these molecules from the catalyst surface could cause the diffusion limitations.

As stated in Publication II the oxidation of both alcohols is considerably enhanced on the ALD prepared Pd/C catalyst in comparison to the commercial (Figure 32), which can be explained by the increase of EASA per catalyst mass. Also other groups have reported increased EASA values for ALD prepared catalyst [162,163] indicating that the ALD preparation method could provide a well distributed catalyst having a higher metal surface area. Moreover, in chronoamperometric experiments (Figure 7 in Publication III) it can be observed that the normalized current of isopropanol oxidation on the Pd/C (ALD) catalyst is decreases rapidly due to surface poisoning by oxidation reaction products, however, this effect is not observed with the commercial catalyst nor with the planar Pd in Publication I. This implies that the oxidation mechanism on ALD prepared catalyst is different and confirmation of the reaction products would be beneficial.

The effect of bimetallic nanoparticles on alcohol oxidation is discussed in Publication V in both acidic and alkaline media (Figure 33) and can be summarized in two important points: firstly, for primary fuels (MeOH and EtOH) the introduction of Ru into the

metal catalyst reduces significantly the onset potential of alcohol oxidation and increases the normalized current in both media. Increased performance for both alcohols with the bimetallic catalyst possessing small amount of Ru has been reported previously [182], nevertheless, when the amount of Ru is increased a decrease in performance has been observed [182,183] indicating that there is optimum content of PtRu catalyst that has only been optimized for acidic medium. Similar behavior on PtRu catalyst has been reported with another primary fuel (1-propanol [184]), however, for the secondary alcohol isopropanol, this phenomenon applies only in acidic medium (Figure 33C).

Figure 33. 1 M methanol (A), ethanol (B) and isopropanol (C) oxidation on Pt/C and PtRu/C catalyst in 0.1 M HClO₄ and 0.5 M KOH electrolytes with 10 mV s⁻¹ scan rate and 1800 rpm rotation of the WE. (Publication V)

In general, the enhanced activity on PtRu catalyst for primary fuels is probably due to the bi-functional mechanism and the ligand effect discussed in the previous section and the results in Figure 33 emphasize the importance of bimetallic catalyst materials for alcohol oxidation. Furthermore, it is notable that this phenomenon is also seen in alkaline medium where the formation of a PtO_x layer initiates at less positive potentials (Figure 31) and from that fact it could be assumed that the bimetallic catalyst would not

further enhance the alcohol oxidation, however, this is not the case and Ru has a vital role also in alkaline medium. Secondly, the alcohol oxidation is enhanced in alkaline medium when compared to the same alcohol and electrode in acidic medium highlights the interest of alkaline DAFCs. Though, there is one exception to this trend: isopropanol oxidation on a PtRu catalyst that produces already high normalized currents at low potentials in acidic medium, but in alkaline medium the activity is clearly lower. Implying that in this medium isopropanol dehydrogenation could occur through strongly adsorbed intermediates as suggested by Markiewicz *et al.* [84], however, some additional spectroscopic experiments are needed to confirm this hypothesis.

In Publication IV the effect of the support material for methanol oxidation on a PtRu catalyst has been evaluated and it can be concluded that both catalyst on carbon nanosupports show increased mass activity in comparison to PtRu/Vulcan (Figure 34).

Figure 34. 1 M Methanol oxidation on PtRu catalyst on various carbon supports, in 0.1 M HClO₄ electrolyte. (A) Cyclic voltammogram with 10 mV s^{-1} and 1800 rpm rotation and (B) chronoamperometric experiment at 0.7 V potential. (Publication IV)

On nanocarbon supports the onset potential and maximum normalized current are increased and durability improved as reported earlier [185]. PtRu/GNF produces the highest current density with cyclic voltammetry (Figure 34A) [186], however, as seen with the chronoamperometric curves (Figure 34B) this catalyst is poisoned by methanol oxidation intermediates. In contrast, on PtRu/FWCNT methanol oxidation provides lower maximum normalized current, though, is more stable in longer experiments, which for fuel cell conditions is extremely important. The results indicate that PtRu on nanocarbon supports is interesting for further DAFCs studies.

6 Direct Alcohol Fuel Cell

As introduced in Section 1.1 DAFCs are a special group of PEFCs utilizing organic alcohols as anode fuels and the schematic representation of this cell with a PEM and methanol fuel is presented in Figure 1. The ethanol oxidation reaction (i) presented in Section 3 apply also for anode reactions in the acidic DAFC while the corresponding reaction at the cathode is ORR:

Accordingly, the theoretical fuel cell voltage is the potential difference between the cathode and the anode that for ethanol DAFC is 1.145 V. The equilibrium voltage of DAFC, also called open circuit voltage (OCV), is the cell voltage when no current is drawn from the cell. This voltage is significantly lower in comparison to the theoretical voltage: for ethanol fuelled Nafion cell it is around 0.54 V (Figure 35) implying that more than half of the theoretical value (0.605 V) is lost due fuel crossover to the cathode and electrode surface phenomena on the anode and the cathode. As discussed in Section 3 the anode reaction does not occur at the thermodynamic potential but the onset of the reaction is shifted to higher potentials due to activation overpotential (defined in equation 5). This is caused by kinetic issues of both the DAFC electrodes which are higher for alcohol oxidation reaction in comparison to ORR and therefore the anode overpotential has major contribution.

The electrolyte in a fuel cell is not a liquid, as in electrochemical cell, but instead a solid polymer membrane having higher resistance and the total resistance R represents the sum of electronic, ionic and contact resistances of the cell from which the ionic

resistance of the membrane material is dominant. When current is drawn a clear decrease of the potential in the polarization curve is observed in Figure 35 with all fuel concentrations due to this ohmic overpotential. At high current densities the electrode reactions become more rapid and the diffusion of reactant to the electrode surface become rate determining. These losses are called concentration overpotential that have been defined in equation 7 and can be clearly seen in Figure 35 with the most concentrate fuel (10 M) where the diffusion of water to the anode becomes rate limiting.

Figure 35. Polarization curves of ethanol oxidation in the Nafion membrane DAFC with PtRu/C as anode and Pt/C as cathode catalyst, both with loadings of 1 mg cm^{-2} . Various concentrations of ethanol and pure oxygen gas are fed to the anode and cathode, respectively, and cell temperature 30°C . (Unpublished)

6.1 Acidic DAFC

Since the development of PEFCs challenges with gaseous fuels have been encountered: they required either synthesis on site or transportation and storage, both increasing the engineering complexity and cost of the system [187]. Therefore, a similar system that would utilize liquid fuel became highly desirable. The utilization of methanol as a direct fuel initiated in the 1960s by Shell Research in the UK and Exxon-Alstom in France, however, the cells still utilized liquid electrolytes [188]. The first direct methanol fuel cell (DMFC) with PEM electrolyte was developed during the 1980s, however, the optimization of the new MEA structures was demanding and various designs was

suggested. Nafion[®] membranes are the most commonly used PEM in DAFCs due to its dominant durability and conductivity properties.

During the last decade methanol has been the most studied fuel for DAFCs [for instance: 30,187,189- 194] because it possesses no C-C bonds and is therefore easier to oxidize in comparison to molecules with various carbon atoms. This is also the first low temperature fuel cell type that is extensively used by private and industrial customers with 8000 DMFC systems (since 2009) sold by SFC Smart Fuel Cell [195]. The DMFC components are highly optimized: the search for the optimal catalyst material for the DMFC has been a topic for hundreds of studies and concluding that PtRu is the best material for the anode and Pt for the cathode. Since, the increased performances have been introduced by the development of new catalyst support materials and further cell design. Nevertheless, challenges still remain: low power in comparison to hydrogen fuelled PEFC, methanol crossover (discussed further in Section 6.3) and durability of the MEA components that is essential for consumer products.

Formic acid fuel cells [196,197] have an advantage that in water solutions formic acid forms a formate anion that repels the negatively charged groups of PEM resulting in negligible crossover [198]. Accordingly, concentrated anode fuels (5-20 mol dm⁻³) can be used reducing the amount of water required and the overall weight of the system. These systems are used in military applications where silent and light power sources are required, however, formic acid oxidation produces only two electrons (instead of 6 from methanol) resulting in lower performance which can be improved by increasing catalyst loading that adds to the cells cost. In addition, sufficient power densities are obtained only with concentrated solutions causing corrosion issues [196] and therefore requiring corrosion resistant materials further increasing the cost of these systems.

Ethanol has also been widely studied as a fuel for direct ethanol fuel cells (DEFC) [for instance: 95,171, 199] due to the possible production from renewable sources, nevertheless, more challenges are faced due to the strong C-C bond. With PEM cells the highest activity has been obtained with PtSn as an anode catalyst and Pt for cathode

[171]. As a larger molecule, in comparison to methanol, ethanol possesses lower crossover through the Nafion membrane [5] reducing the power losses at the cathode, however, the Nafion membrane swells more in ethanol than in methanol solutions [200]. Also other liquid organic compounds have been tested for DAFCs: 1-propanol [5], isopropanol (2-propanol) [5, 201 - 203], ethylene glycol (with two OH-groups) [5, 204] and glycerol (with three OH-groups) [5] have been studied as fuels for DAFCs, however, they have received little interest due to low performance.

6.2 Alkaline DAFC

Alkaline fuel cell (AFC) is a low temperature fuel cell type that has a liquid alkaline electrolyte between the electrodes and utilizes oxygen or air and hydrogen as fuels. These cells have been used in the space program (Apollo Space Shuttle) since the 1960s and their advantages are the highest performance of all low temperature fuel cells and the possibility to use cheaper catalyst materials such as Ni, Ag or metal oxides [205] along with noble metals. The disadvantage of these systems is that they are intolerant for CO₂ that forms carbonates with the cations (K⁺ or Na⁺) in the electrolyte and therefore AFCs have only limited use in non-terrestrial applications. Nevertheless, the high performance and possibility to use cheap electrode materials are interesting and therefore, PEFC with anion exchange membranes (AEM) have been developed during the last decade. With this system the advantages of the alkaline cell can be obtained, thus, CO₂ tolerance is increased because no free cations exist in the electrolyte.

A schematic of a DAFC with AEM and methanol fuel is shown in Figure 36 that is analogous with the schematic presented in Figure 1 (with PEM) and the same reactants can be fed to the cell: alcohol-water solution to the anode and oxygen (air) to the cathode. In addition, the total reaction for both cell types remains the same, however, the electrode reactions differ: now water produces hydroxyl ions at the cathode, ions are transported through the membrane to anode where they are consumed in alcohol oxidation reaction. In an acidic cell the water is produced at the cathode causing

occasionally flooding of that electrode therefore hindering the diffusion of gases, in contrast, in an alkaline DAFC the water is produced at the anode, which is already saturated with the fuel solution. As a result, flooding in alkaline DAFCs is observed only at intermediate current densities or if the cathode gas flow is hindered [206].

Figure 36. Methanol fuelled DAFC with an anion exchange membrane electrolyte. (Publication V)

The first alkaline DAFCs fuelled with alcohols were introduced at the beginning of the century by Inaba *et al.* [207] and Scott *et al.* [208] with Tokuyama[®] and Morgane[®] membranes, respectively, followed by various other groups. These two experiments and most of those published since had a flow of alcohol-alkaline (KOH or NaOH) solution to the anode in order to increase the ion conductivity of the cell. This turns the alkaline DAFC to a type of AFC and similar challenges with the CO_2 tolerance are faced. In AFCs this phenomenon can be controlled by eliminating CO_2 from the cell by feeding pure oxygen to the cathode, however, in the case of alkaline DAFC with alcohol fuel CO_2 cannot be avoided because it is a reaction product of the anode reaction. In addition, by adding KOH or NaOH into the anode fuel cations (K^+ or Na^+) are introduced that can form solid metal carbonates accumulating over time in the cell and blocking the electrode layers [209]. It should be also kept in mind that a liquid with a high pH has a corrosive effect on all components: for instance a decrease in an AEM ion-exchange capacity is observed when the membrane is immersed in a NaOH solution for several days [133] indicating that the durability of that kind of cell is questionable.

With alkaline DAFC various liquid fuels have been introduced: methanol [210-213], ethanol [133,210,214-215], formate [216], ethylene glycol [217,218] and glycerol [210,219] being the most reported. Nevertheless, only few groups have reported studies with alcohol-water anode fuels [31,68,220-224] obtaining lower current densities in comparison to DAFCs with alcohol-alkaline anode fuels. In Publication V with water-alcohol mixtures are used as anode fuels to avoid carbonate formation in the cell.

6.3 Crossover

Ion conductive polymer membranes consist of two different parts: hydrophobic polymer back bones as well as hydrophilic end groups and in moist environment they are organized so that the backbones are wrapped inside and the hydrophilic groups form channels where ions and water molecules can be transported. Organic alcohols are polar particles with a small size and can therefore be transported through these same channels, called as alcohol crossover. This phenomenon is strongly influenced by the cell temperature and a clear increase in values is observed with elevated temperatures for both acidic and alkaline membranes [225,226]. This is unfortunate because also the electrode reactions are enhanced at higher temperatures and therefore the cells are often operated at as high temperature as possible. In addition, alcohol concentration affects permeability and therefore the highest DAFC performance is obtained with 1-2 mol dm⁻³ alcohols [200,227], however, utilizing diluted fuels is problematic because a vast amount of water, that is not required for electrode reactions but for alcohol dilutions, has to be transported along resulting as increase in DAFC size and weight.

At the cathode the transported alcohol molecule can adsorb on the catalyst and due to increased cathode potential reacts forming electrons which are directly consumed with the ORR. The latter reaction will occur with the same rate as the methanol oxidation on the cathode, resulting as depolarization of the electrode, that is, decrease in the cathode potential and in the cell voltage [205]. Moreover, CO_{ads} can be formed on the cathode surface sites preventing ORR and further lowering the DAFC performance [189].

One method to hinder the alcohol crossover is to select larger alcohols as fuel components because their permeability is decreased especially at the low temperatures as observed for both PEMs [5,200,225] and AEMs [67,68]. Another method is to select thicker membrane materials for DAFCs (for instance Nafion 115 or 117) in comparison to PEFC with gaseous fuels (Nafion 112). Thus disadvantage of the thicker membrane is increase in the cell ohmic overpotential according to Equation 6 and the thicker membrane material also causes challenges to the stack assembly making it more prone to leakage. Finally, it should be pointed out that even though AEMs are often thinner in comparison to PEMs the alcohol permeability rates measured *ex situ* are an order of magnitude smaller [67,68,228] due to dissimilar structure of the membrane materials. Moreover, in acidic DAFCs the protons are transported from anode to cathode (Figure 1), that is the same direction as the alcohol crossover, whereas for alkaline DAFC the ion movement occurs in the opposite direction, against alcohol crossover (Figure 36), implying that in the latter case the alcohol permeability might be further diminished.

6.4 Alcohol oxidation in DAFCs

In Publication V the effect of bimetallic catalyst and membrane material for alcohol oxidation is studied by preparing two MEAs (Pt/C or PtRu/C for anode catalyst) with each membrane material (Nafion[®] 115 or FAA-2). In Publication V the polarization curves of each fuel are presented for a Nafion (Figure 37) and FAA-2 (Figure 38) DAFC with 1 M alcohol. As additional data corresponding chronoamperometric measurements at 0.2 V voltage are presented in Figure 37 and 38 for Nafion and FAA-2 cells, respectively. The polarization curves initiate from the OCV value obtained after stabilization overnight and the current from the cell is followed as a function of decreased cell voltage. The OCV values depend on operating temperature, selected catalyst, electrode layer structure and alcohol crossover.

Figure 37. Polarization curves (Publication V) for Pt/C (A) and PtRu/C (B) as well as chronoamperometric experiments at 0.2 V potential (Unpublished) for Pt/C (C) and PtRu/C (D) catalyst (loadings 1.2-1.7 mg cm⁻²) DAFCs with the Nafion 115 -membrane. Cathode catalyst is Pt/C (2-2.5 mg cm⁻²), 1 M methanol and pure oxygen gas are fed to the anode and cathode, respectively, and cell temperature 30 °C.

In Publication V the OCV values for the Pt/Nafion cell are between 0.40 – 0.55 V (Figure 37A), isopropanol produces the highest OCV, however, the highest current density is clearly obtained with methanol that is due to the total oxidation of this fuel. These findings are in agreement with the observations reported earlier [95,199,203], however, comparison of fuel cell data between different publications is onerous due to varying catalyst loading, MEA preparation and experimental conditions. The chronoamperometric curves (Figure 37 C) show that the current density for Pt/Nafion cell with ethanol and methanol is quite stable, however, the latter cell shows small fluctuation especially after 2000 s that is most likely caused by instability of the MEA structure. In contrast, for isopropanol a constant declined is observed indicating surface poisoning by reaction intermediates.

Publication V implies that with all alcohols the OCVs and the maximum current densities are increased when bimetallic PtRu is used as an anode catalyst (Figure 37B) instead of pure Pt, indicating that the surface processes on these catalysts differ. For primary fuels the OCV of the PtRu catalyst cell is 0.53 V whereas for isopropanol a significantly higher value (0.85 V) is obtained - which has been reported previously [201,202] - and is due to efficient deprotonation of isopropanol to acetone at low potential (observed with FTIR in Publication II and electrochemical experiments in Publication V). Nevertheless, as can be seen in the polarization curve in Publication V isopropanol oxidation declines rapidly at 0.65 V (Figure 37B) because the reaction from isopropanol to acetone is fast and thus diffusion limitations at that potential are faced, however, this behavior can be seen as a constant decrease in chronoamperometric current in Figure 37D.

Figure 38. Polarization curves (Publication V) for Pt/C (A) and PtRu/C (B) as well as chronoamperometric experiments at 0.2 V potential (Unpublished) for Pt/C (C) and PtRu/C (D) catalyst (loadings 1.2-1.7 mg cm^{-2}) DAFCs with the FAA-2 -membrane. Cathode catalyst is Pt/C (2-2.5 mg cm^{-2}), 1 M methanol and pure oxygen gas are fed to the anode and cathode, respectively, and cell temperature 30 °C.

In general, all current densities obtained with the FAA-2 cell (Figure 38) are significantly lower than the ones obtained with the Nafion cell (Figure 37), however, it should be kept in mind that the ion conductivity of FAA-2 is still a decade lower in comparison to Nafion[®] [31] and that the MEA preparation method has not been optimized for FAA-2 MEAs which could in future increase these current density values. Furthermore, if an alkaline solution is added to the anode fuel, significantly increased current densities would be obtained, but the cell would encounter similar problems to the AFC discussed in Section 6.2. Nevertheless, the OCV values for the alkaline DAFC in Publication V are similar or in most cases increased in comparison to the Nafion cell. This might be due to enhanced electrode reactions that have been observed *ex situ* (Figure 33), and lower crossover rate [31], however, to confirm these phenomena more detailed measurements further experiments are required. The current densities obtained with the PtRu/FAA-2 cells are at least twice as high as for the Pt/FAA-2 cells implying that Ru has also a significant role in alcohol oxidation within alkaline DAFCs.

As can be seen from the chronoamperometric measurements (Figure 38) the current densities from the FAA-2 cells are modest and with the primary fuels no severe catalyst poisoning is observed as was the case with the Nafion cell (Figure 37). Publication V confirms that isopropanol oxidation in an alkaline DAFC is more complex: in the Pt/FAA-2 cell it possesses very poor performance, thus, the current density would seem to increase during the 2 h experiment whereas in the PtRu/FAA-2 cell a very high OCV and the highest current density is observed. In contrast with the chronoamperometric experiments there is a clear decrease in isopropanol oxidation current indicating surface poisoning by intermediate products.

6.4.1 Effect of carbon support

The effect of the catalyst support material on fuel cell performance and stability is studied in publication IV and MEAs with Nafion membrane, PtRu catalyst on various carbon supports for the anode and Pt/C for the cathode have been prepared. The support materials are the same used in the electrochemical experiments in Figure 28:

PtRu/Vulcan, PtRu/FWCNT and PtRu/GNF. The MEA preparation was more challenging than expected due to the different polarities of the nanocarbon supports resulting as high variation in electrode inks densities. Nevertheless, the aim of Publication IV was to compare different nanocarbon supports with similar loadings and optimization of the PtRu/GNF catalyst electrodes is outlined elsewhere [40]. In Publication IV, the polarization and chronoamperometric measurements for different MEAs have been shown (Figure 39A and B). In addition, the power densities of the cells (W) can be calculated from the current density-voltage data according to:

$$W = j \cdot E \quad (9)$$

where j is current density and E cell voltage. These curves are presented in Figure 39C.

Figure 39. Polarization curves (A) (Publication IV), chronoamperometric curves for 6 days at 0.4 V (B) (Publication IV) and power densities curves (C) (Unpublished) for PtRu catalyst on various carbon supports as anode catalyst (loadings 1 mg cm⁻²). Cathode catalyst is Pt/C (2 mg cm⁻²), membrane material Nafion 115, 1 M methanol and pure oxygen gas are fed to the anode and cathode, respectively, and cell temperature is 70 °C.

Figure 39 shows that in the DAFCs PtRu/Vulcan catalyst shows the highest performance and the peak power density is obtained above 0.2 V. Nevertheless, in Figure 39B it can be seen that the performance of the PtRu/Vulcan MEA is decreasing over time and after 6 days of operation 14 % of the original current density at 0.05 V is lost. Further post-characterization of the MEA by SEM (Figure 6 in Publication IV) and catalyst by TEM (Figure 1 in Publication IV) after the 6 days of operation revealed that the three dimensional net structure of the anode catalyst layer in the PtRu/Vulcan MEA had collapsed, the anode electrode had swollen in the diluted (1 M) methanol solution increasing the electrode layer thickness by 3.5 times and, moreover, the catalyst particle size had increased from 3.3 to 4.5 nm. From an application point of view these phenomena are very alarming and these kinds of decrease cannot be tolerated in customer applications emphasizing the urgent need for new more durable support materials.

For the PtRu/GNF MEA surprisingly high current and power densities (Figure 39A and C) have been obtained in Publication IV even though the anode layer thickness was initially 8 times higher in comparison to the PtRu/Vulcan MEA. Moreover, the performance remained fairly stable during the 6 day experiments (Figure 39B) due to maintained porous net structure throughout the experiments (Figure 6 in Publication IV), that facilitated the reactant flow to the catalyst particles. These results confirm that GNF support material is especially of interest for further studies. The PtRu/FWCNT performance in the fuel cell experiments was poor even on the first measurement day (Figure 39A and C) even though the SEM images (Figure 6 in Publication IV) showed that a good porous structure offering channels for reactant flow was obtained. As was the case of the Vulcan support, also PtRu/FWCNT structure collapsed after 6 days of operation explaining the dramatic decrease in the maximum current density (35 %) during the experiment. There still remains an open question: could these FWCNT be somehow pretreated so that the durability in fuel cell conditions would be prolonged?

6.5 Comparison to electrochemical results

There is a vast amount of studies done with DAFC anode materials in electrochemical cells as well as with single cell DAFCs, however, there is very little work that combines these two different research areas. Moreover, a part of electrochemical experiments are performed in conditions unrealistic for fuel cell applications. The aim of this thesis is to emphasize methods where electrochemical experiments are performed under fuel cell related conditions in order to obtain practical results from these *ex situ* measurements. In this section the result obtained from the electrochemical cell and DAFC are compared.

Even though the OCV of the DAFC does not correspond directly to the onset potential of alcohol oxidation in electrochemical cell, similar catalyst surface phenomena, such as reactant adsorption, occur explaining the difference observed in these values when, for instance, anode catalyst or electrolyte pH is varied. This can be seen in Publication V where the use of the bimetallic catalyst shifts the onset potential towards less positive value in electrochemical cell (Figure 33) as well as increases the OCV in DAFCs (Figure 37) while other variables remain constant. In addition, the increase in the electrolyte pH resulted as similar response for primary fuels.

In Publication I catalyst poisoning in the electrochemical experiments in alkaline medium for methanol on a Pt and ethanol on a Pd surface has been observed by HPLC. On the contrary, with chronoamperometry in DAFCs presented in Figures 36 and 37 the most significant decrease in current is observed with isopropanol. When the performance decrease over time with these experiments are evaluated caution must be applied, because in an electrochemical cell they are mostly due to catalyst poisoning by reaction intermediates, thus, in DAFCs various different mechanisms can be co-effecting: possible causes are catalyst poisoning, component degradations, increased alcohol crossover as well as limited reactant or product diffusion (that can be the case if the anode fuel feed is too slow or anode reaction fast). Particularly, the catalyst poisoning observed with the HPLC in Publication I for methanol oxidation on Pt in

alkaline medium, but no severe drop with Pt/FAA-2 cell was observed (Figure 37C) implying that catalyst poisoning is not the primary cause of losses in the case of this DAFC.

The study into the effect of catalyst support on methanol oxidation in Publication IV showed that the maximum normalized current is obtained from the cyclic voltammogram (Figure 34A) and chronoamperometric measurements (Figure 34B) with PtRu/FWCNT and PtRu/GNF, respectively, implying that high performance with these catalyst materials could be obtained in fuel cells. Conversely, the highest performance is obtained with PtRu/Vulcan (Figure 39) which is due to the optimized MEA preparation for this material. In addition, in the electrochemical cell the PtRu/FWCNT catalyst showed a high tolerance for catalyst poisoning, but in the DAFC poor performance and durability has been observed. Publication IV confirms that even though this catalyst is resistant to catalyst poisoning with methanol oxidation intermediates it is vulnerable to structural collapse under DAFC conditions. These findings highlight that both electrochemical and fuel cell experiments - in the case of new anode materials - are important for understanding the different mechanism occurring both on catalyst surfaces and in electrode layers. In addition, with these experiments it is evident that especially as new support materials have different hydrophobicity, the development of MEA preparation process individually for each support is essential.

7 Conclusions

This thesis reports newly developed methods to study DAFC anode materials electrochemically in fuel cell related conditions in order to make *in* and *ex situ* results more comparable. The results highlight that in an DAFC it is complicated to separate different phenomena that occur on the anode and therefore, electrochemical methods where individual mechanisms can be evaluated are needed. In this work, various methods to study *ex situ* the effect of electrode surface structure, nanoparticle preparation, bimetallic catalyst, catalyst support materials as well as electrolyte pH on alcohol oxidation are presented.

The surface structure sensitivity of the alcohol oxidation is studied with Pt SCE and it is found that these reactions are enhanced or inhibited on different surface sites. For isopropanol oxidation Pt(111) surface sites are the most active, however, for methanol and ethanol Pt(100) and Pt(111) sites would produce high current densities in acidic and alkaline media, respectively. Nevertheless, these currents are observed only at high overpotential implying that a combination of the two most active surface sites would be more beneficial. After discovering on which surface sites unwanted intermediates are formed, their density on shape controlled nanoparticles can be limited and the utilization of these particles in DAFCs could result as an increase in power density without increase in the catalyst loading.

Pd catalyst has not been intensively studied for alcohol oxidation due to its poor performance in acidic medium, but in alkaline medium it has shown to be an active electrocatalyst. After the introduction of AEM search for bimetallic catalyst that would catalyze alcohol oxidation in alkaline medium has commenced, however, it is vital to determine the optimal noble base metal for each bimetallic catalyst. With the HPLC experiments it was found that in alkaline medium Pd is more selective for organic acid formation than Pt. For methanol oxidation higher performance is obtained with Pt catalyst in alkaline medium and therefore it is the preferred candidate for bimetallic

catalyst. For ethanol oxidation the spectroscopic experiments, in literature, have implied that the C-C bond would be more facile to cleave from acetaldehyde than from ethanol and therefore acetaldehyde is wanted as intermediate indicating that Pt should be chosen as base metal for bimetallic catalyst. With isopropanol no corresponding acid was formed on either Pt or Pd but with the latter the current density was clearly increased suggesting that Pd based bimetallic catalysts could be more effective for isopropanol oxidation.

The efficient oxidation of organic alcohols can be obtained only if the nanoparticle catalyst is a certain size, well attached and evenly distributed onto the support. Industrial methods to prepare catalyst in large scale can decrease the material costs: with ALD prepared Pd/C catalyst well distributed nanoclusters on carbon support is obtained and they show high performance for alcohol oxidation. Moreover, it can be concluded that introduction of bimetallic catalyst enhanced the alcohol oxidation in both *ex situ* and *in situ* experiments. This behavior has been observed also in alkaline medium where the formation of adsorbed OH on Pt surface has been shifted to less positive potentials possibly reducing the effect of the bi-functional mechanism, however, ligand effect and probably some other mechanisms still apply.

For commercial DAFC the durability of the cell materials is essential, and therefore the biggest obstacle to commercialization is the fast degradation of the components and electrode structures. The study of different carbon supports emphasizes the durability issues in fuel cell environments when from the electrochemical experiments only information on the reaction onset potential, maximum normalized current and catalyst poisoning are obtained. Nevertheless, often in DAFCs the most essential issues lowering the cell performance are related to MEA preparation or component degradation and therefore it is vital to study these materials also *in situ*.

To sum up, both *ex situ* and *in situ* experiments are required to understand the mechanisms on the DAFC anode.

7.1 Reliability

With all experimental work some error exists in the data and in this Section the accuracy of the different experiments is evaluated. The more controlled system, the more facile is to obtain accurate data and in the case of more complex systems the sources of the largest error is pointed out. With well controlled systems such as SCE (Publication II) the fingerprint cyclic voltammograms are well defined, the peaks sharp and therefore, even low concentration of impurities or surface defects are facially noted. In addition, these experiments can be quickly repeated and therefore these experiments are the most accurate ones in this work. For the reaction product detection in Publication I large planar electrodes have been used in order to produce high amounts of reaction intermediates and products which are needed for accurate detection. Moreover, the experiments have been performed with very slow sweep rate to ensure that the slow reaction has sufficient time to occur.

With the nanoparticle electrodes, a more complex system is introduced including: catalyst particles, supports with different hydrophobicity and ionomer. The current produced cannot be normalized with the geometric area, accordingly, for monometallic catalyst (Publication III) the EASA defined in Section 2.1.4 can utilized, however, for bimetallic catalyst (Publication IV and V) they are not well enough defined. Instead, the catalyst loading of a 5 μl drop is known and the currents can be normalized with that, however, not all catalyst on the electrode is in contact with the reactants. The CO adsorption/desorption offers a possibility to compare each electrode and give an estimation on how much active catalyst there is on the electrode which is then taken into account in normalizing the currents. The other method to increase the reliability of the experiments is repetition of the experiments which is more time consuming than with simple systems, though, only way to confirm the trends.

The most demanding case are the fuel cell experiments (Publication IV and V) that are even far more complex than the electrochemical ones and each MEA is hand prepared individual with different thickness at different parts of the electrode due to spray-

preparation technique. Luckily, we have new screen printing equipment that will increase the reducibility of the MEAs in the future. With the *in situ* experiments the reliability is obtained by repeating the experiment with various MEAs. Overall, the focus of this work has been in comparison of materials and therefore, the aim has not been to find optimum condition but instead have standard conditions for the measurements.

7.2 Recommendation for further work

In this work some of the materials that performed well in electrochemical experiments had poor durability in DAFC conditions. While performance advantages are often intensively discussed they have low importance for commercial applications if the activity is rapidly lost. In future work the focus of DAFC anode material design should be on material durability and performance should be evaluated as a function of operation time. Therefore it would be interesting to continue testing various anode materials for their durability and performance behavior over time in DAFCs with a similar post-characterization procedure as introduced in Publication IV.

The shape controlled nanoparticles, which have more controlled surface sites, could enhance the DAFC performance without increasing the catalyst loading. The main focus of that study could be in determining of the durability of these particles during the MEA preparation process and fuel cell operation. Other interesting fields of study could be the improvement of the ALD catalyst preparation method as well as the preparation of well distributed bimetallic catalyst with ALD and the study of their durability *ex situ* and *in situ*. Moreover, the reaction mechanism studies of bimetallic nanoparticles could be performed, for instance with a HPLC, and this could provide information on the effect of different nanoparticle preparation methods on enhanced activity which is difficult to attain with purely electrochemical methods.

References

1. Y. Shao, G. Yin, J. Zhang, Y. Gao, *Electrochim. Acta* **51** (2006) 5853-5857.
2. E. Yli-Rantala, A. Pasanen, P. Kauranen, V. Ruiz, M. Borghei, E. Kauppinen, A. Oyarce, G. Lindbergh, C. Lagergren, M. Darab, S. Sunde, M. Thomassen, S. Ma-Andersen, E. Skou, *Fuel Cells* **11** (2011) 715-725.
3. W.R. Grove, *Phil. Mag. S.* **14** (1839) 127-130.
4. A. Santasalo, Use of liquid fuels in a polymer electrolyte fuel cell, Master's thesis, Helsinki University of Technology, Espoo 2007, 91 p.
5. A. Santasalo, T. Kallio, K. Kontturi, *Platinum Met. Rev.* **53** (2009) 59-66.
6. E.P.M. Leiva, M.C. Giordano, *J. Electroanal. Chem.* **158** (1983) 115-130.
7. H. Wang, H. Baltruschat, *J. Phys. Chem. C* **111** (2007) 7038-7048.
8. W. Sheng, H.A. Gasteiger, Y. Shao-Horn, *J. Electrochem. Soc.* **157** (2010) B1529-B1536.
9. D. Strmcnik, K. Kodama, D. van der Vliet, J. Greeley, V.R. Stamenkovic, N.M. Markovic, *Nature Chem.* **1** (2009) 466-472
10. F. Seland, R. Tunold, D.A. Harrington, *Electrochim. Acta* **55** (2010) 3384-3391.
11. J. Clavilier, D. Armand, S.G. Sun, M. Petit, *J. Electroanal. Chem.*, **205** (1986) 267-277.
12. J. Clavilier, K. El Achi, M. Petit, A. Rodes, M.A. Zamakhchari, *J. Electroanal. Chem.*, **295** (1990) 333-356.
13. A. Rodes, M. A. Zamakhchari, K. El Achi, J. Clavilier, *J. Electroanal. Chem.* **305** (1991) 115-129.
14. S. Trasatti, O.A. Petrii, *J. Electroanal. Chem.* **327** (1992) 353-376.
15. T. Biegler, D.A.J. Rand, R. Woods, *J. Electroanal. Chem.* **29** (1971) 269-277.
16. J. Bett, K. Kinoshita, K. Routsis, P. Stonehart, *J. Catal.* **29** (1073) 160-168.
17. M. Hayes, A.T. Kuhn, *Appl. Surf. Sci.* **6** (1980) 1-14.
18. F. Maillard, S. Pronkin, E.R. Savinova, Influence of size on the electrocatalytic activities of supported metal nanoparticles in fuel cell-related reactions, in: *Handbook of fuel cells*, W. Vielstich (Ed.), Vol 5, John Wiley & Sons Ltd, Chichester 2009, p. 95.
19. D. Chen, Q. Tao, L.W. Liao, S.X. Liu, Y.X. Chen, S. Ye, *Electrocatal.* **2** (2011) 207-219.
20. K.J.J. Mayrhofer, D. Strmcnik, B.B. Blizanac, V. Stamenkovic, M. Arenz, N.M. Markovic, *Electrochim. Acta* **53** (2007) 3181-3188.
21. T.J. Schmidt, H.A. Gasteiger, G.D. Stäb, P.M. Urban, D.M. Kolb, R.J. Behm, *J. Electrochem. Soc.* **145** (1998) 2354-3187.
22. R. Pattabiram, *Appl. Catal. A* **153** (1997) 1-8.
23. R.M. Mobidebi, T. Masombuka, M.K. Mathe, *Int. J. Hydr. Ene.* **36** (2011) 4664-4672.
24. Y. Zhao, X. Yang, J. Tian, F. Wang, L. Zhan, *Int. J. Hydr. Ene.* **35** (2010) 3249-3257.

25. M.M. Ottakam Thotiyl, T. Ravi Kumar, S. Sampath, *J. Phys. Chem. C* **114** (2010) 17934-17941.
26. A.A. Michri, A.G. Pshchenicknikov, R. Kh. Brushtein, *Electrochimica* **8** (1972) 364-366.
27. T. Chierchie, C. Mayer, W.J. Lorenz, *J. Electroanal. Chem.* **135** (1982) 211-220.
28. B. Du, S.A. Rabb, C. Zangmeister, Y. Tong, *Phys. Chem. Chem. Phys.* **11** (2009) 8231-8239.
29. M.P. Hogarth, T.R. Ralph, *Platinum Met. Rev.* **46** (2002) 146-164.
30. C. Coutanceau, R.K. Koffi, J.-M. Leger, K. Marestin, R. Mercier, C. Nayoze, P. Capron, *J. Power Sources* **160** (2006) 334-339.
31. A. Santasalo-Aarnio, S. Hietala, T. Rauhala, T. Kallio, *J. Power Sources* **196** (2011) 6153-6159.
32. X. Zhao, W. Li, Y. Fu, A. Manthiram, *Int. J. Hydr. Ene.* **37** (2012) 9845-9852.
33. X. Zhao, X. Fan, S. Wang, S. Yang, B. Yi, Q. Xin, G. Sun, *Int. J. Hydr. Ene.* **30** (2005) 1003-1010.
34. S.C. Thomas, X. Ren, S. Gottesfeld, *J. Electrochem. Soc.* **146** (1999) 4354-4359.
35. J.-H. Kim, H.-Y. Ha, I.H. Oh, S.-A. Hong, H.N. Kim, H.-I. Lee, *Electrochim. Acta* **50** (2004) 801-806.
36. B. Krishnamurthy, S. Deepalochani, K.S. Dhathathreyan, *Fuel Cells* **8** (2008) 404-409.
37. L. Birry, C. Bock, X. Xue, R. McMillan, B. MacDougall, *J. Appl. Electrochem.* **39** (2009) 347-360.
38. C. Wannek, S. Nehr, M. Vahlenkamp, J. Mergel, D. Stolten, *J. Appl. Electrochem.* **40** (2010) 29-38.
39. K.-T. Jeng, C.-C. Chien, N.-Y. Hsu, W.-M. Huang, S.-D. Chiou, S.-H. Lin, *J. Power Sources* **164** (2007) 33-41.
40. P. Kanninen, M. Borghei, V. Ruiz, E.I. Kauppinen, T. Kallio, *Int. J. Hydr. Ene.* In Press.
41. S. Gottesfeld, T.A. Zawodzinski, Polymer electrolyte fuel cells, in *Advances in Electrochemical Science and Engineering*, R.C. Alkire, H. Gerischer, D.M. Kolb, C.W. Tobias (Eds.), Vol 5, Wiley-VCH, New York 1997, p. 240.
42. E.A. Ticianelli, C.R. Derouin, A. Redondo, S. Srinivasan, *J. Electrochem. Soc.* **135** (1988) 2209-2214.
43. C.Y. Chen, C.S. Tsao, *Int. J. Hydr. Ene.* **31** (2006) 391-398.
44. Z.X. Liang, T.S. Zhao, C. Xu, J.B. Xu, *Electrochim. Acta* **53** (2007) 897-902.
45. A. Santasalo, *Electrocatalysis of organic molecules on platinum catalyst surfaces: from the fundamentals to the polymer electrolyte fuel cell applications*, Licentiate's thesis, Helsinki University of Technology, Espoo 2009, 55 p.
46. C. Lamy, E.M. Belgsir, J.-M. Leger, *J. Appl. Electrochem.* **31** (2001) 799-809.
47. C. Lamy, *Electrochim. Acta* **29** (1984) 1581-1588.
48. S. Trasatti, Electrode potential and double layer, in *Handbook of fuel cells*, W. Vielstich (Ed.), Vol 2, John Wiley & Sons Ltd, Chichester 2003, p. 75.
49. Q.-S. Chen, J. Solla-Gullon, S.-G. Sun, J.M. Feliu, *Electrochim. Acta* **55** (2010) 7982-7994.
50. T. Iwasita, X. Xia, *J. Electroanal. Chem.* **411** (1996) 95-102.
51. S.A. Wasileski, M.T.M Koper, M.J. Weaver, *J. Phys. Chem. B* **105** (2001) 3518-3530.

52. S.C.S. Lai, M.T.M. Koper, *Phys. Chem. Chem. Phys.* **44** (2009) 10446-10456.
53. V. Rao, Hariyanto, C. Cramers, U. Stimming, *Fuel Cells* **7** (2007) 417-423.
54. M. Zhiani, H.A. Gasteiger, M. Piana, S. Catanorchi, *Int. J. Hydr. Ene.* **36** (2011) 5110-5116.
55. J.-W. Kim, S.-M. Park, *J. Electrochem. Soc.* **150** (2003) E560-E566.
56. M.A. Abdel Rahim, R.M. Abdel Hameed, M.W. Khalil, *J. Power Sources* **135** (2004) 42-51.
57. J.L. Cohen, D.J. Volpe, H.D. Abruña, *Phys. Chem. Chem. Phys.* **9** (2007) 49-77.
58. K. Franaszczuk, E. Herrero, P. Zelenay, A. Wieckowski, J. Wang, R.I. Masel, *J. Phys. Chem.* **96** (1992) 8509-8516.
59. M. Breiter, *Electrochim. Acta* **12** (1967) 1213-1218.
60. T. Iwasita, *Electrochim. Acta* **47** (2002) 3663-3674.
61. A. Kabbabi, R. Fayre, R. Durand, B. Beden, F. Hahn, J.-M. Leger, C. Lamy, *J. Electroanal. Chem.* **444** (1998) 41-53.
62. T.H.M. Housmans, A.H. Wonders, M.T.M. Koper, *J. Phys. Chem. B* **110** (2006) 10021-10031.
63. P.S. Kauranen, E. Skou, J. Munk, *J. Electroanal. Chem.* **404** (1996) 1-13.
64. P.A. Christensen, D. Linares-Moya, *J. Phys. Chem. C* **114** (2010) 1094-1101.
65. E. Morallon, A. Rodes, J.L. Vazquez, J.M. Perez, *J. Electroanal. Chem.* **391** (1995) 149-157.
66. G. Cui, S. Song, P.K. Shen, A. Kowal, C. Bianchini, *J. Phys. Chem. C* **113** (2009) 15639-15642.
67. A. Santasalo-Aarnio, P. Peljo, E. Asperg, K. Kontturi, T. Kallio, *ECS Trans.* **33** (2010) 1701-1714.
68. J.R. Varcoe, R.C.T. Slade, E.L.H. Yee, S.D. Poynton, D.J. Driscoll, *J. Power Sources* **173** (2007) 194-199.
69. F. Colmati, G. Tremiliosi-Filho, E.R. Gonzalez, A. Berna, E. Herrero, J.M. Feliu, *Faraday Discuss.* **140** (2009) 379-397.
70. A. Wieckowski, J. Sobrowski, P. Zelenay, K. Franaszczuk, *Electrochim. Acta* **26** (1981) 1111-1119.
71. A. Rodes, E. Pastor, T. Iwasita, *J. Electroanal. Chem.* **376** (1994) 109-118.
72. H. Wang, Z. Jusys, R.J. Behm, *J. Phys. Chem. B* **108** (2004) 19413-19424.
73. S.C.S. Lai, M.T.M. Koper, *Faraday Discuss.* **140** (2008) 339-416.
74. U. Schmiemann, U. Muller, H. Baltruschat, *Electrochim. Acta* **40** (1995) 99-107.
75. Z.-Y. Zhou, Q. Wang, J.-L. Lin, N. Tian, S.-G. Sun, *Electrochim. Acta* **55** (2010) 7995-7999.
76. G. Garcia, M.T.M. Koper, *Phys. Chem. Chem. Phys.* **10** (2008) 3802-3811.
77. R.B. Kutz, B. Braunschweig, P. Mukherjee, D.D. Dlott, A. Wieckowski, *J. Phys. Chem. Lett.* **2** (2011) 2236-2240.
78. E. Pastor, S. Gonzalez, A.J. Arvia, *J. Electroanal. Chem.* **395** (1995) 233-242.
79. E. Pastor, S. Wasmus, T. Iwasita, M.C. Arevalo, S. Gonzales, A.J. Arvia, *J. Electroanal. Chem.* **350** (1993) 97-116.
80. I.A. Rodrigues, J.P.I. De Souza, E. Pastor, F.C. Nart, *Langmuir* **13** (1997) 6829-6835.

81. S.-G. Sun, Y. Lin, *J. Electroanal. Chem.* **375** (1994) 401-404.
82. R.G.C.S. Reis, C.A. Martins, G.A. Camara, *Electrocatal.* **1** (2010) 116-121.
83. I.A. Rodriques, F.C. Nart, *J. Electroanal. Chem.* **590** (2006) 145-151.
84. M.E.P. Markiewicz, D.M. Herbert, S.H. Bergens, *J. Power Sources* **161** (2006) 761-767.
85. M.E.P. Markiewicz, S.H. Bergens, *J. Power Sources* **185** (2008) 222-225.
86. C. Xu, Z. Tian, Z. Chen, S.P. Jiang, *Electrochem. Commun.* **10** (2008) 246-249.
87. D. Bayer, S. Berenger, M. Joos, C. Cremers, J. Tübke, *Int. J. Hydr. Ene.* **35** (2010) 12660-12667.
88. H. Wang, Z. Jusys, R.J. Behm, *J. Power Sources* **154** (2006) 351-359.
89. Z.-Y. Zhou, N. Tian, Y.-J. Chen, S.-P. Chen, S.-G. Sun, *J. Electroanal. Chem.* **573** (2004) 111-119.
90. S.C.S. Lai, S.E.F. Kleijn, F.T.Z. Öztürk, V.C. van Rees Vellinga, J. Koning, P. Rodriguez, M.T.M. Koper, *Catal. Today* **154** (2010) 92-104.
91. X. Fang, L. Wang, P.K. Shen, G. Cui, C. Bianchini, *J. Power Sources* **195** (2010) 1375-1378.
92. S.C.S. Lai, M.T.M. Koper, *Phys. Chem. Chem. Phys.* **11** (2009) 10446-10456.
93. E.M. Belgsir, H. Huser, J.-M. Leger, C. Lamy, *J. Electroanal. Chem.* **225** (1987) 281-286.
94. E.M. Belgsir, E. Bouhier, H. Essis-Yei, K.B. Kokoh, B. Beden, H. Huser, J.-M. Leger, C. Lamy, *Electrochim. Acta* **36** (1991) 1157- 1164.
95. S. Rousseau, C. Coutanceau, C. Lamy, J.-M. Leger, *J. Power Sources* **158** (2006) 18-24.
96. Y. Kwon, M.T.M. Koper, *Anal. Chem.* **82** (2010) 5420-5424.
97. J. McMurray, in: *Organic Chemistry*, Brooks/Cole, Monterrey, 1984, pp. 850-853.
98. J. Liu, J. Ye, C. Xu, S.P. Jiang, Y. Tong, *J. Power Sources* **177** (2008) 67-70.
99. S.-G. Sun, Y. Lin, *Electrochim. Acta* **41** (1996) 693-700.
100. L.W.H. Leung, M. Weaver, *Langmuir* **6** (1990) 323-333.
101. J. Souza-Garcia, E. Herrero, J.M. Feliu, *Chem. Phys. Chem.* **11** (2010) 1391-1394
102. Q.-S. Chen, A. Berna, V. Climent, S.-G. Sun, J.M. Feliu, *Phys. Chem. Chem. Phys.* **12** (2010) 11407-11416
103. Q.-W. Zheng, C.-J. Fan, C.-H. Zhen, Z.-Y. Zhou, S.-G. Sun, *Electrochim. Acta* **53** (2008) 6081-6088.
104. C.M. Sanchez-Sanchez, J. Souza-Garcia, E. Herrero, A. Aldaz, *J. Electroanal. Chem.* **668** (2012) 51-59.
105. T.S. Ahmadi, Z. L. Wang, T.C. Green, A. Henglein, M.A. El-Sayed, *Science* **272** (1996) 1924-1926.
106. J. Solla-Gullon, F.J. Vidal-Iglesias, A. Lopez-Cudero, E. Garnier, J.M. Feliu, A. Aldaz, *Phys. Chem. Chem. Phys.* **10** (2008) 3689-3698.
107. C. Susut, G.B. Chapman, G. Samjeske, M. Osawac, Y.Y. Tong, *Phys. Chem. Chem. Phys.* **10** (2008) 3712-3721.
108. H. Yang, L. Dai, D. Xu, J. Fang, S. Zou, *Electrochim. Acta* **55** (2010) 8000-8004.

109. Y.-W. Lee, A.-R. Ko, S.-B. Han, H.-S. Kim, D.-Y. Kim, S.-J. Kim, K.-W. Park, *Chem. Commun.* **46** (2010) 9241-9243.
110. C. Susut, T.D. Nguyen, G.B. Chapman, Y.Y. Tong, *Electrochim. Acta* **53** (2008) 6135-6142.
111. R. Gómez, J. Clavilier, *J. Electroanal. Chem.* **354** (1993) 189-208.
112. M.-C. Morin, C. Lamy, J.-L. Vazquez, A. Aldaz, J.-M. Léger, *J. Electroanal. Chem.* **283** (1990) 287-302.
113. E. Herrero, K. Franaszczuk, A. Wieckowski, *J. Phys. Chem.* **98** (1994) 5074-5083.
114. R. Subbaraman, D. Strmcnik, V. Stamenkovic, N.M. Markovic, *J. Phys. Chem. C* **114** (2010) 8414-8422.
115. J. Clavilier, "Flame-Annealing and Cleaning Technique", Interfacial Electrochemistry, A. Wieckowski (Ed.), Marcel Dekker, New York 1999, p. 231-248.
116. A.V. Tripkovic, K.Dj. Popovic, J.D. Momcilovic, D.M. Drazic, *J. Electroanal. Chem.* **448** (1998) 173-181.
117. A.V. Tripkovic, K.Dj. Popovic, J.D. Momcilovic, D.M. Drazic, *Electrochim. Acta* **44** (1998) 1135-1145.
118. E. Herrero, Q.-S. Chen, J. Hernandez, S.-G. Sun, J. M. Feliu, *Phys. Chem. Chem. Phys.* **13** (2011) 16762-16771.
119. A.V. Tripkovic, K.Dj. Popovic, J.D. Momcilovic, D.M. Drazic, *J. Electroanal. Chem.* **418** (1996) 9-20.
120. X.H. Xia, T. Iwasita, F. Ge, W. Vielstich, *Electrochim. Acta* **41** (1996) 711-718.
121. T.H.M. Housmans, A.H. Wonders, M.T.M. Koper, *J. Phys. Chem. B* **110** (2006) 10021-10031.
122. M. Faraday, *Philosophical Transactions of the Royal Society*, London, 1857.
123. R.W. Murray, *Chem. Rev.* **108** (2008) 2688-2720.
124. S. Park, Y. Xie, M. J. Weaver, *Langmuir* **18** (2002) 5792-5798.
125. T. Frelink, W. Visscher, J.A.R. van Veen, *J. Electroanal. Chem.* **382** (1995) 65-72.
126. A. Kabbabi, F. Gloaguen, F. Andolfatto, R. Durand, *J. Electroanal. Chem.* **373** (1994) 251-254.
127. K. Kinoshita, *J. Electrochem. Soc.* **137** (1990) 845-848.
128. S. Mukerjee, J. McBreen, *J. Electroanal. Chem.* **448** (1998) 163-171.
129. K. Kinoshita, *J. Electrochem. Soc.* **137** (1990) 845-848.
130. G.X. Wang, L. Yang, J.Z. Wang, H.K. Liu, S.X. Dou, *J. Nanosci. Nanotechnol.* **5** (2005) 1135-1140.
131. J. Xie, D.L. Wood, K.L. More, P. Atanassov, R.L. Borup, *J. Electrochem. Soc.* **152** (2005) A1011-A1020.
132. J. Wu, X.Z. Yuan, J.J. Martin, H. Wang, J. Zhang, J. Shen, S. Wu, W. Merida, *J. Power Sources* **184** (2008) 104-119.
133. Y.S. Li, T.S. Zhao, *Int. J. Hydr. Ene.* **37** (2012) 4413-4421.

134. Y. Shao, J. Liu, Y. Wang, Y. Lin, *J. Mater. Chem.* **19** (2009) 46-59.
135. E. Antolini, *Appl. Catal. B* **88** (2009) 1-24.
136. J. Wang, G. Yin, Y. Shao, S. Zhang, Z. Wang, Y. Gao, *J. Power Sources* **171** (2007) 331-339.
137. B.J. Eastwood, P.A. Christensen, R.D. Armstrong, N.R. Bates, *J. Solid State Electrochem.* **3** (1999) 179-186.
138. X. Wang, W. Li, Z. Chen, M. Waje, Y. Yan, *J. Power Sources* **158** (2006) 154-159.
139. T. Maiyalagan, B. Viswanathan, U.V. Varadaraju, *Electrochem. Commun.* **7** (2005) 905-912.
140. Y. Shao, G. Yin, Y. Gao, *J. Power Sources* **171** (2007) 558-566.
141. E.G. Rakov, Chemistry of Carbon Nanotubes, in: *Carbon Nanomaterials*, Y. Gogotsi (Ed.), CRC Press, Taylor and Francis Group, Boca Raton, Florida 2006, p. 77-147.
142. H. Luo, Z. Shi, N. Li, Z. Gu, Q. Zhuang, *Anal. Chem.* **73** (2001) 915-920.
143. M. Endo, Y. Kim, T. Hayashi, K. Nishimura, T. Matusita, K. Miyashita, M. Dresselhaus, *Carbon* **39** (2001) 1287-1297.
144. P. Serp, M. Corrias, P. Kalck, *Appl. Catal. A* **253** (2003) 337-358.
145. L. Calvillo, M. Gangeri, S. Perathoner, G. Centi, R. Moliner, M.J. Lazaro, *J. Power Sources* **192** (2009) 144-150.
146. C.A. Bessel, K. Laubernds, N.M. Rodriguez, R.T.K. Baker, *J. Phys. Chem. B* **105** (2001) 1115-1118.
147. M. Tsuji, M. Kubokawa, R. Yano, N. Miyamae, T. Tsuji, M.-S. Jun, S. Hong, S. Lim, S.-H. Yoon, I. Mochida, *Langmuir* **23** (2007) 387-390.
148. M.S. Mamat, S.A. Grigoriev, K.A. Dzhus, D.M. Grant, G.S. Walker, *Int. J. Hydr. Ene.* **35** (2010) 7580-7587.
149. S.A. Grigoriev, M.S. Mamat, K.A. Dzhus, G.S. Walker, P. Millet, *Int. J. Hydr. Ene.* **36** (2011) 4143-4147.
150. L. Li, Y. Xing, *J. Phys. Chem. C* **111** (2007) 2803-2808.
151. M.S. Saha, R. Li, X. Sun, *J. Power Sources* **177** (2008) 314-322.
152. Y. Lin, X. Cui, *Langmuir* **21** (2005) 11474-11479.
153. L. Demarconnay, S. Brimaud, C. Coutanceau, J.-M. Leger, *J. Electroanal. Chem.* **601** (2007) 169-180.
154. T. Maiyalagan, Alaje, O. Taiwo, K. Scott, *J. Phys. Chem. C* **116** (2012) 2630-2638.
155. L. La-Torre-Riveros, E. Abel-Tatis, A.E. Mendez-Torres, D.A. Tryk, M. Prelas, C.R. Cabrera, *J. Nanopart. Res.* **13** (2011) 2997-3009.
156. A.O. Neto, R.R. Dias, M.M. Tusi, M. Linardi, E.V. Spinace, *J. Power Sources* **166** (2007) 87-91.
157. B. Fang, N.K. Chaudhari, M.-S. Kim, J.H. Kim, J.-S. Yu, *J. Am. Chem. Soc.* **131** (2009) 15330-15338.

158. W.J. Zhou, W.Z. Li, S.Q. Song, Z.H. Zhou, L.H. Jiang, G.Q. Sun, Q. Xin, K. Poulitanitis, S. Kontou, P. Tsiakaras, *J. Power Sources* **131** (2004) 217-223.
159. M. Ritala, M. Leskelä, *Handbook of Thin Film Materials*, H.S. Nalwa (Ed.), Vol. 1, Academic Press, San Diego, 2002.
160. R.L. Puurunen, *J. Appl. Phys.* **97** (2005) 121301-1 – 121301-52.
161. K. Oura, V.G. Lifshits, A.A. Saranin, A.V. Zotov, M. Katayama, *Surface Science*, Springer, New York, 2003, p.357.
162. H. Kim, S.H. Moon, *Carbon* **49** (2011) 1491-1501.
163. T. Shu, S.-J. Liao, C.-T. Hsieh, A.K. Roy, Y.-Y. Liu, D.-Y. Tzou, W.-Y. Chen, *Electrochim. Acta* **75** (2012) 101-107.
164. O.A. Petrii, B.I. Podlovchenko, A.N. Frumkin, H. Lal, *J. Electroanal. Chem.* **10** (1965) 253-269.
165. M. Watanabe, M. Motoo, *J. Electroanal. Chem.* **60** (1975) 267-273.
166. K.J. Cathro, *J. Electrochem. Soc.* **116** (1969) 1608-1611.
167. M.M.P. Janssen, J. Moolhuysen, *J. Catal.* **46** (1977) 289-296.
168. S.A. Campbell, R. Parsons, *Farad. Trans.* **88** (1992) 833-841.
169. H. Kita, H. Nakajima, K. Shimazu, *J. Electroanal. Chem.* **248** (1988) 181-191.
170. J.P.I. de Souza, S.L. Queiroz, K. Bergamaski, E.R. Gonzalez, F.C. Nart, *J. Phys. Chem. B* **106** (2002) 9825-9830.
171. S. Song, P. Tsiakaras, *Appl. Catal. B: Environ.* **63** (2006) 187-193.
172. T. Iwasita, F.C. Nart, W. Vielstich, *Ber. Bunsenges. Phys. Chem.* **94** (1990) 1030-1034.
173. M.M.P. Janssen, J. Moolhuysen, *J. Catal.* **46** (1977) 289-296.
174. T. Frelink, W. Visscher, J.A.R. van Veen, *Surf. Sci.* **335** (1995) 353-360.
175. T. Frelink, W. Visscher, J.A.R. van Veen, *Langmuir* **12** (1996) 3702-3708.
176. P. Waszczuk, G.-Q. Lu, A. Wieckowski, C. Lu, C. Rice, R.I. Masel, *Electrochim. Acta* **47** (2002) 3637-3652.
177. H. Gasteiger, N. Markovic, P. Ross, E. Cairns, *J. Phys. Chem.* **98** (1994) 617-625.
178. D. Chu, S. Gilman, *J. Electrochem. Soc.* **143** (1996) 1685-1690.
179. D. Cao, S. Bergens, *Electrochim. Acta* **48** (2003) 4021-4031.
180. L. Zhuang, J. Jin, H.D. Abruña, *J. Am. Chem. Soc.* **129** (2007) 11033-11035.
181. M.T.M. Koper, J.J. Lukkien, A.P.J. Jansen, R.A. van Santen, *J. Phys. Chem. B* **103** (1999) 5522-5529.
182. S. Selda, S. Fatih, G. Gökagac, *Phys. Chem. Chem. Phys.* **13** (2011) 6784-6792.
183. A.V. Tripkovic K.D. Popovic, B.N. Grgur, B. Blizanac, P.N. Ross, N.M. Markovic, *Electrochim. Acta* **47** (2002) 3707-3714.
184. P. Katikawong, T. Ratana, W. Veerasai, *J. Chem. Sci.* **121** (2009) 329-337.

185. G. Giriskumar, T.D. Hall, K. Vinodgopal, P.V. Kamat, *J. Phys. Chem. B* **110** (2006) 107-114.
186. I.-S. Park, K.-W. Park, J.-H. Choi, C.R. Park, Y.-E. Sung, *Carbon* **45** (2007) 28-33.
187. A. Hamnett, Direct methanol fuel cells (DMFC), in: *Handbook of fuel cells*, W. Vielstich (Ed.), Vol 1, John Wiley & Sons Ltd, Chichester 2003, p. 305.
188. B.D. McNicol, D.A.J. Rand, K.R. Williams, *J. Power Sources* **83** (1999) 15-31.
189. Z. Qi, A. Kaufman, *J. Power Sources* **110** (2002) 177-185.
190. S.H. Seo, C.S. Lee, *Energy & Fuels* **22** (2008) 1212-1219.
191. C. Suo, X. Liu, X. Tang, Y. Zhang, B. Zhang, P. Zhang, *Electrochem. Commun.* **10** (2008) 1606-1609.
192. C. Cremers, M. Scholz, W. Seliger, A. Racz, W. Knechtel, J. Rittmayr, F. Grafwallner, H. Peller, U. Stimming, *Fuel Cells* **7** (2007) 21-31.
193. S.C. Thomas, X. Ren, S. Gottesfeld, P. Zelenay, *Electrochim. Acta* **47** (2002) 3741-3748.
194. P. Zelenay, *ECS Trans.* **1** (2006) 483-495.
195. J. Müller, Field experience with portable DMFC products, in: *Handbook of fuel cells*, W. Vielstich (Ed.), Vol 6, John Wiley & Sons Ltd, Chichester 2009, p. 916.
196. M. Weber, J.-T. Wang, S. Wasmus, R.F. Savinell, *J. Electrochem. Soc.* **143** (1996) 158-160.
197. C. Rice, S. Ha, R.I. Masel, P. Waszczuk, A. Wieckowski, T. Barnard, *J. Power Sources* **111** (2002) 83-89.
198. Y. Rhee, S.Y. Ha, R.I. Masel, *J. Power Sources* **117** (2003) 35-38.
199. N. Nakagawa, Y. Kaneda, M. Wagatsuma, T. Tsujiguchi, *J. Power Sources* **199** (2012) 103-109.
200. S. Song, W. Zhou, Z. Liang, R. Cai, G. Sun, Q. Xin, V. Stergiopoulos, P. Tsiakaras, *Appl. Catal. B: Environ.* **55** (2005) 65-72.
201. Z. Qi, A. Kaufman, *J. Power Sources* **112** (2002) 121-129.
202. D. Cao, S.H. Bergens, *J. Power Sources* **124** (2003) 12-17.
203. T. Kobayashi, J. Otomo, C.-j. Wen, H. Takahashi, *J. Power Sources* **124** (2003) 34-39.
204. V. Livshits, E. Peled, *J. Power Sources* **161** (2006) 1187-1191.
205. F. Barbir, *PEM fuel cells theory and practice*, Elsevier, Burlington, 2005, pp. 433.
206. Y.S. Li, T.S. Zhao, R. Chen, *J. Power Sources* **196** (2011) 133-139.
207. Z. Ogumi, K. Matsuoka, S. Chiba, M. Matsuoka, Y. Iriyama, T. Abe, M. Inaba, *Electrochemistry* **70** (2002) 980-983.
208. E.H. Yu, K. Scott, *Electrochem. Commun.* **6** (2004) 361-365.
209. J.R. Varcoe, R.C.T. Slade, *Fuel Cells* **5** (2005) 187-200.
210. V. Bambagioni, C. Bianchini, A. Marchionni, J. Filippi, F. Vizza, J. Teddy, P. Serp, M. Zhiani, *J. Power Sources* **190** (2009) 241-251.

211. G.K.S. Prakash, F.C. Krause, F.A. Viva, S.R. Narayanan, G.A. Olah, *J. Power Sources* **196** (2011) 7967–7972.
212. J. Kim, T. Momma, T. Osaka, *J. Power Sources* **189** (2009) 999–1002.
213. J.-H. Kim, H.-K. Kim, K.-T. Hwang, Jai-Young Lee, *Int. J. Hydr. Ene.* **35** (2010) 768–773.
214. S.Y. Shen, T.S. Zhao, Q.X. Wu, *Int. J. Hydr. Ene.* **37** (2012) 575–582.
215. N. Fujiwara, Z. Siroma, S.-i. Yamazaki, T. Ioroi, H. Senoh, K. Yasuda, *J. Power Sources* **185** (2008) 621–626.
216. A.M. Bartrom, J.L. Haan *J. Power Sources* **214** (2012) 68–74.
217. L. An, T.S. Zhao, S.Y. Shen, Q.X. Wu, R. Chen, *Int. J. Hydr. Ene.* **35** (2010) 4329–4335.
218. C. Cremers, A. Niedergesaess, F. Jung, D. Mueller, J. Tuebke, *ECS Trans.* **41** (2011) 1987–1996.
219. S.R. Ragsdale, C.B. Ashfield, *ECS Trans.* **16** (2008) 1847–1854.
220. J.R. Varcoe, R.C.T. Slade, *Electrochem. Commun.* **8** (2006) 839–843.
221. J.R. Varcoe, R.C.T. Slade, E.L.H. Yee, S.D. Poynton, D.J. Driscoll, D.C. Apperley, *Chem. Matter.* **19** (2007) 2686–2693.
222. H. Bunazawa, Y. Yamazaki, *J. Power Sources* **182** (2008) 48–51.
223. H. Bunazawa, Y. Yamazaki, *J. Power Sources* **190** (2009) 210–215.
224. C.-C. Yang, S.-S. Chiu, S.-C. Kuo, T.-H. Liou, *J. Power Sources* **199** (2012) 37–45.
225. Y.H. Chu, Y.G. Shul, *Fuel Cells* **12** (2012) 109–115.
226. Y. Zhang, J. Fang, Y. Wu, H. Xu, X. Chi, W. Li, Y. Yang, G. Yan, Y. Zhuang, *J. Colloid. Interface Sci.* **381** (2012) 59–66.
227. S. Song, W. Zhou, J. Tian, R. Cai, G. Sun, Q. Xin, S. Kontou, P. Tsiakaras, *J. Power Sources* **145** (2005) 266–271.
228. H. Jung, K. Fujii, T. Tamakia, H. Ohashia, T. Ito, T. Yamaguchi, *J. Memb. Sci.* **373** (2011) 107–111.

Direct alcohol fuel cell (DAFC) can produce power for electronics with high energy efficiency independently of the electric net. The obstacles to this technology are the high cost and low durability of current electrode materials and therefore there is an urgent need for alternative catalysts and their supports. The amount of these experimental materials is often limited, however, even with small samples electrochemical methods can be applied providing information of catalyst activity and durability. The results show that nanoparticle preparation, bimetallic catalyst, catalyst support, alcohol fuel as well as membrane electrode assembly preparation has an effect on the performance and durability of the cell. This thesis presents new methodology to study experimental materials *ex situ* offering fast and reliable way to study suitability of electrode materials for commercial applications.

ISBN 978-952-60-4907-6
ISBN 978-952-60-4908-3 (pdf)
ISSN-L 1799-4934
ISSN 1799-4934
ISSN 1799-4942 (pdf)

Aalto University
School of Chemical Technology
Department of Chemistry
www.aalto.fi

BUSINESS +
ECONOMY

ART +
DESIGN +
ARCHITECTURE

SCIENCE +
TECHNOLOGY

CROSSOVER

DOCTORAL
DISSERTATIONS