The influence of interacting small defects on the fatigue limit of steels

Mari Åman

The influence of interacting small defects on the fatigue limit of steels

Vuorovaikuttavien pienten vikojen vaikutus terästen väsymisrajaan

Mari Åman

A doctoral dissertation completed for the degree of Doctor of Science (Technology) to be defended, with the permission of the Aalto University School of Engineering, at a public examination held remotely via Zoom (<https://aalto.zoom.us/j/64095547925>) on 17th December 2020 at 12.

Aalto University
School of Engineering
Department of Mechanical Engineering

Supervising professor

Prof. Heikki Remes, Aalto University, Finland

Thesis advisors

Prof. Hisao Matsunaga, Kyushu University, Japan

Prof. Gary Marquis, Aalto University, Finland

Preliminary examiners

Dr. Bernd Schönbauer, University of Natural Resources and Life Sciences, Austria

Prof. Stefano Beretta, Politecnico di Milano, Italy

Opponent

Prof. Stefano Beretta, Politecnico di Milano, Italy

Aalto University publication series

DOCTORAL DISSERTATIONS 217/2020

© 2020 Mari Åman

ISBN 978-952-64-0199-7 (printed)

ISBN 978-952-64-0200-0 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

<http://urn.fi/URN:ISBN:978-952-64-0200-0>

Unigrafia Oy

Helsinki 2020

Finland

Printed matter
4041-0619

Author
Mari Åman

Name of the doctoral dissertation
The influence of interacting small defects on the fatigue limit of steels

Publisher School of Engineering

Unit Department of Mechanical Engineering

Series Aalto University publication series DOCTORAL DISSERTATIONS 217/2020

Field of research Mechanical Engineering

Manuscript submitted 1 August 2020 **Date of the defence** 17 December 2020

Permission for public defence granted (date) 13 October 2020 **Language** English

☐ **Monograph** ☒ **Article dissertation** ☐ **Essay dissertation**

Abstract

Metallic engineering components possess numerous small natural defects, which can potentially become sites for fatigue crack initiation. Although the influence of a single small crack on the fatigue strength is well studied, knowledge of the behavior of interacting defects is more limited. Current design rules and standards for the interaction effect, such as British standard BS 7910, are based on material-independent criteria. Consequently, this thesis examines experimentally the effect of the material on defect interaction. In addition, this work introduces an efficient finite element-based method for stress intensity factor (SIF) evaluation of interacting arbitrarily shaped 3D cracks.

In experimental investigations, fully-reversed tension-compression fatigue tests were performed using different steel grades. Small artificial defects were manufactured onto the specimen surface with an accurately determined distance between them. Fatigue limits were determined by the non-propagating condition of cracks that had emanated from artificial defects. The size of natural non-propagating cracks (NPC's) varies among different materials. Thus, the influence of the material's effect is determined on both NPC characteristics and defect interaction on the fatigue limit.

In order to evaluate SIF's of arbitrarily shaped 3D cracks, this thesis develops the Stress Component Division Method (SCDM), which utilizes the theory of elasticity, the superposition principle, and stress component division. The key point of the SCDM is that it separates the total stress in an element into two components, singular and non-singular terms, the former of which is associated with the SIF.

This study showed that the behavior of interacting defects varied greatly among different steels. In low strength steel, the defects coalesced at the fatigue limit regardless of the spacing between them, whereas defects never coalesced at the fatigue limit in high strength steel regardless of the spacing between the defects. In case of moderate strength steels, the interaction phenomena were more complicated and the coalescence at the fatigue limit depended on the materials hardness, the relative size of NPC's, microstructure and the spacing between original defects. The numerical SIF solutions for arbitrarily shaped 3D cracks computed by SCDM are in good agreement with the known numerical solutions even when a coarse mesh is employed.

It was concluded that, by itself, the commonly used material-independent interaction criterion is insufficient in the evaluation of fatigue strength for interacting crack problems in different steel grades. The experimental results presented here provide new information and guidance to improve the interaction criteria in real engineering structures. It was also shown that in addition to the aspect ratio of the defects and the spacing between defects, the defect shape must also be considered in SIF evaluation of interacting defects.

Keywords small crack, interaction effect, defect interaction, fatigue limit, non-propagating crack

ISBN (printed) 978-952-64-0199-7 **ISBN (pdf)** 978-952-64-0200-0

ISSN (printed) 1799-4934 **ISSN (pdf)** 1799-4942

Location of publisher Helsinki **Location of printing** Helsinki **Year** 2020

Pages 116 **urn** <http://urn.fi/URN:ISBN:978-952-64-0200-0>

Tekijä
Mari Åman**Väitöskirjan nimi**

Vuorovaikuttavien pienten vikojen vaikutus terästen väsymisrajaan

Julkaisija Insinööritieteiden korkeakoulu**Yksikkö** Konetekniikan laitos**Sarja** Aalto University publication series DOCTORAL DISSERTATIONS 217/2020**Tutkimusala** Konetekniikka**Käsikirjoituksen pvm** 01.08.2020**Väitöspäivä** 17.12.2020**Väittelyluvan myöntämispäivä** 13.10.2020**Kieli** Englanti☐ **Monografia**☒ **Artikkeliväitöskirja**☐ **Esseeväitöskirja****Tiivistelmä**

Teräskomponentit sisältävät erilaisia materiaalivikoja, joista väsymissäröt tyypillisesti ydintyvät. Vaikka pienten vikojen vaikutusta terästen väsymislujuuteen on kattavasti tutkittu, useamman vian yhteisvaikutuksen tutkimus on ollut huomattavasti rajallisempaa. Nykyiset väsymiskriittisten osien suunnitteluohjeistukset perustuvat standardeihin, joiden kriteerit eivät huomioi materiaalin vaikutusta. Esimerkki tällaisesta standardista on BS 7910. Tässä väitöskirjatyössä tutkitaan kokeellisesti materiaalin vaikutusta vikojen vuorovaikutukseen. Lisäksi työssä esitellään tehokas elementtimenetelmään perustuva numeerinen menetelmä vuorovaikuttavien 3D-säröjen jännitysintensiteettikertoimien (SIF) määrittämiseen.

Kokeellisessa tutkimusosassa eri lujuusluokan teräksiä testattiin käyttäen väsytykskoikeissa vaihtojännitystä keskijännityksen ollessa nolla. Koekappaleiden pintaan työstettiin pienet keinotekoiset viat, joiden välinen etäisyys määriteltiin tarkasti. Väsymisraja määriteltiin pysähtyvien säröjen perusteella, eli säröjen, jotka ydintyvät, mutta eivät jatka kasvamistaan murtumaan asti. Pysähtyvien säröjen luontainen koko vaihtelee eri materiaaleissa. Materiaalin vaikutusta tutkittiinkin sekä pysähtyvien säröjen ominaisuuksien että vikojen vuorovaikutuksen näkökulmasta. Työn teoreettisessa osassa kehitetään Stress Component Division Method (SCDM), jossa hyödynnetään elastisuusteoriaa, superpositioperiaattia sekä jännityskomponenttien erittelyä. SCDM:n avulla kokonaisjännitys särön kärjen elementissä voidaan jakaa singulaariseen ja ei-singulaariseen komponenttiin, joista ensimmäinen vastaa SIF:a.

Tässä työssä havaittiin, että vikojen vuorovaikutuksessa oli huomattavia eroja eri materiaaleissa. Matalan lujuusluokan teräksessä säröt yhdistyivät väsymisrajalla huolimatta alkuvikojen välisestä etäisyydestä, kun taas korkealujassa teräksessä viat eivät yhdistyneet riippumatta etäisyydestä. Keskiluissa teräksissä vikojen vuorovaikutus oli monimutkaisempi ilmiö, ja säröjen yhdistymiseen vaikuttivat mm. materiaalin kovuus, suhteellinen pysähtyvän särön koko, mikrorakenne ja alkuvikojen välinen etäisyys. Numeerisesti SCDM:llä määritetyt 3D-säröjen jännitysintensiteettikertoimet vastasivat erinomaisesti tunnettuja vastaavia ratkaisuja, vaikka käytetty elementtikoko oli suhteellisen suuri.

Tämän työn tulosten perusteella voidaan päätellä, että yleisesti käytetyt, analyttiset ja materiaalista riippumattomat vuorovaikutuskriteerit ovat sellaisenaan riittämättömiä kuvaamaan vikojen vuorovaikutusta väsymisrajaan erilaisissa teräksissä. Työn kokeelliset tulokset tarjoavat paitsi uutta tietoa vikojen vuorovaikutuksesta todellisissa komponenteissa, myös suosituksia vuorovaikutuskriteerien parantamiseksi. Työssä osoitettiin myös, että vuorovaikuttavien vikojen jännitysintensiteettikertoimen täsmällisessä määrittämisessä tulisi vikojen mittojen suhteen ja vikojen välisen etäisyyden lisäksi huomioida myös vian todellinen geometria.

Avainsanat pienet säröt, vikojen vuorovaikutus, vuorovaikutustekijä, väsymisraja, pysähtyvät säröt**ISBN (painettu)** 978-952-64-0199-7**ISBN (pdf)** 978-952-64-0200-0**ISSN (painettu)** 1799-4934**ISSN (pdf)** 1799-4942**Julkaisupaikka** Helsinki**Painopaikka** Helsinki**Vuosi** 2020**Sivumäärä** 116**urn** <http://urn.fi/URN:ISBN:978-952-64-0200-0>

Preface

“Why don’t you come to Japan to extend your research?” was the question asked by Professor Emeritus Yukitaka Murakami in 2014. Consequently, the short visit eventually turned into almost four years’ research project. This thesis is the outcome of this project, which was jointly carried out in Fatigue and Fracture laboratory of Kyushu University’s Department of Mechanical Engineering and in the Marine Technology group of Aalto University’s Department of Mechanical Engineering. The research work was funded by Aalto University School of Engineering, Finnish Academy Project 298762 and Heikki ja Hilma Honkasen säätiö. All the financial support is gratefully acknowledged. I want to express my gratitude to my supervising Professor Heikki Remes and thesis advisors Professor Hisao Matsunaga and Professor Gary Marquis for their enthusiasm, encouragement and support. First of all, I want to thank Professor Matsunaga for accepting me into his lab, his endless support not only in the lab but also outside of the lab, guidance and introduction into extremely high-quality experimental research. In addition, I want to thank smart students and friendly staff of Kyushu University for their hospitality and willingness to help. In particular, I want to express my gratitude to Japanese co-authors Saburo Okazaki and Kentaro Wada, who have tirelessly helped with the experiments. Very special thanks are in order to Professor Emeritus Yukitaka Murakami for his patient guidance, invaluable advice, counselling, wisdom, insights and friendship. I wish to thank the preliminary examiners Doctor Bernd Schönbauer and Professor Stefano Beretta for their efforts and contributions. I want to thank Professor Beretta for acting also as my opponent. I want to express my gratitude also to my Aalto colleagues and group members, especially to my co-author Kennie Berntsson for his excellent contribution in the analysis. Moreover, I want to thank Pasquale Gallo and Adeyinka Abass for their support, helpful discussions and encouragement. Moreover, I want to thank Pauli Lehto for assistance with layout finalization and supporting attitude. Finally, I want to thank all my friends and especially my dear son Axel for their patience and support.

Espoo, 13th of November 2020

Mari Åman

Contents

List of Abbreviations and Symbols.....	xi
List of Publications.....	xiii
Original features	xv
Author's Contribution	xvii
1. Introduction.....	1
1.1 Fatigue assessment	1
1.2 Small fatigue cracks	2
1.3 Fatigue limit prediction, the $\sqrt{area}$ parameter model.....	4
1.4 Defect interaction.....	5
2. Scope of work.....	7
2.1 Research objectives.....	7
2.2 Limitations.....	8
3. Experimental and numerical methods	9
3.1 Experimental procedure	9
3.1.1 Materials and specimen preparation	9
3.1.2 Introduction of artificial defects	11
3.1.3 Fatigue testing.....	13
3.1.4 Results analysis procedure.....	13
3.2 Stress Component Division Method	14
3.2.1 Modeling principles and theoretical background	14
3.2.2 Numerical modeling by FEM	15
4. Results	19
4.1 Crack initiation and growth in finite life regime	19
4.1.1 Medium carbon steel S45C.....	19
4.1.2 Pure iron SUY1	23
4.1.3 Bearing steel SUJ2	23
4.2 Fatigue limit for interacting defects.....	24

4.3	Non-propagating cracks at the fatigue limit.....	26
4.3.1	Medium carbon steel S45C	26
4.3.2	Pure iron SUY1.....	28
4.3.3	Bearing steel SUJ2	30
4.4	SIF's for interacting arbitrarily shaped 3D cracks	31
4.4.1	Validation of the SCDM	31
4.4.2	Defect shape effect on interaction factor	32
4.4.3	Interacting asymmetric cracks.....	33
4.4.4	Interacting mixed crack geometries	34
4.4.5	Conversion to the $\sqrt{area}$ parameter model.....	36
5.	Discussion	39
5.1	The role of non-propagating crack characteristics.....	39
5.2	Defect interaction in different materials	40
5.2.1	Small crack or large crack?	42
5.2.2	Crack or notch?	44
5.2.3	The effect of local microstructure on crack behaviour	45
5.3	Numerical modeling of defect interaction.....	47
6.	Conclusions	49
	References	53
	Publications	59

List of Abbreviations and Symbols

BFM	Body force method
EDM	Electric discharge machining
FEM	Finite element method
HV	Vickers hardness
K-T	Kitagawa-Takahashi
LEFM	Linear-elastic fracture mechanics
NPC	Non-propagating crack
SIF	Stress intensity factor
a_i	half-length of crack i
a_{NPC}	Half-length of a non-propagating crack
$area$	The area of the defect projected to the plane perpendicular to the maximum principal stress
$area_{eff}$	The effective area of the defect projected to the plane perpendicular to the maximum principal stress
d	Distance between cracks
d_i	Diameter of defect i
h_i	Depth of defect i
s	Spacing between the defects
s_{cr}	Critical spacing between the defects
F	Dimensionless stress intensity factor
I_i	Point on defect i that is closest to the adjacent defect
K_{A1}	Stress intensity factor at point A of crack 1

K_{Ao}	Stress intensity factor at point A of a single crack
K_{max}	Maximum stress intensity factor
$K_{I, max}$	Maximum Mode I stress intensity factor
N	Number of cycles
N_{co}	Number of cycles to coalescence
N_f	Number of cycles to failure
O_i	Point on defect i that is furthest to the adjacent defect
R	Stress ratio
ε	Distance parameter
γ	Interaction factor
σ_a	Stress amplitude
σ_o	Remote stress
σ_w	Fatigue limit
$\sigma_{w, exp}$	Experimentally-determined fatigue limit
$\sigma_{w, pred}$	Predicted fatigue limit
$\Delta K_{eff, th}$	Effective threshold stress intensity factor range
$\Delta K_{o, th}$	Intrinsic threshold stress intensity factor range
ΔK_{th}	Threshold stress intensity factor range
$\Delta K_{th, lc}$	Threshold stress intensity factor range for a long crack

List of Publications

This thesis is based on the three original publications that are referred to in the text as I–III. These publications are reproduced with the permission of the publishers.

Publication I: Åman, M., Okazaki, S., Matsunaga, H., Marquis, G. B. & Remes, H. (2017). Interaction effect of adjacent small defects on the fatigue limit of a medium carbon steel. *Fatigue and fracture of engineering materials and structures*, 40: 130– 144. DOI 10.1111/ffe.12482.

Publication II: Åman, M., Wada, K., Matsunaga, H., Remes, H. & Marquis, G. (2020). The influence of interacting small defects on the fatigue limits of a pure iron and a bearing steel. *International journal of fatigue*, vol. 135, 105560. DOI 10.1016/j.ijfatigue.2020.105560.

Publication III: Åman, M., Berntsson K., & Marquis, G. (2020). An efficient stress intensity factor evaluation method for interacting arbitrarily shaped 3D cracks. *Theoretical and Applied Fracture Mechanics*, 109, 102767. DOI <https://doi.org/10.1016/j.tafmec.2020.102767>.

Original features

Steels contain various natural defects that could act as crack initiation sites and reduce the fatigue strength. Defect tolerance is one of the major challenges in fatigue assessment. Phenomena related to the influence of a single defect on the fatigue strength are extensively examined and well understood. However, if multiple defects are located in close proximity, they may begin to interact and act together as a larger single defect. Therefore, it is very important to evaluate under which conditions such interaction occurs in order to determine the effective defect size. This thesis studies experimentally and theoretically the defect interaction and its influence on the fatigue limit in different steel grades. Particular attention is paid to the non-propagating crack characteristics. In addition, an effective numerical method to evaluate the stress intensity factors for interacting arbitrarily shaped 3D cracks is proposed. The features believed to be original are:

1. The current interaction criteria is based on linear-elastic stress analyses that are independent of the material properties (e.g., strength level and microstructure). This research showed that the behavior of interacting defects varied greatly among different steels. Therefore, the analytical interaction criteria alone are insufficient to evaluate fatigue strength, thus, it is suggested that the effect of the material properties should be taken into consideration in practical applications.
2. The analytical interaction criteria includes so-called “analytical critical distance” in interaction. The experimental results revealed that the analytical critical distance criteria hold only for moderate strength steels. The real critical distance was found to be significantly smaller than the analytical critical distance in high-strength steels with the reverse holding true for low-strength steels.
3. The dual-phase microstructure in moderate-strength medium carbon steel had a strong effect on crack initiation and non-propagating crack location and length. The large pearlite structures near the artificial defects could completely prevent crack initiation. When less pearlite existed between the artificial defects, the cracks coalesced easily and the coalescence typically resulted in failure when the distance between cracks was equal to the analytical critical distance. Since the local microstructure is difficult to control precisely, it

complicates the defect interaction problem in steels having complex microstructure.

4. The experimental results imply that the non-propagating crack size of a material, which is related to the hardness, determines the severity of defect interaction. The maximum size of non-propagating cracks in a material is not easy to determine, as there is large scatter and possibly other influencing factors in addition to *HV*.

5. A new Finite Element based method for the analysis of interacting 3D cracks was developed. This method differs from the traditional numerical analysis in that it requires no fine mesh, special elements or extrapolations. The key to the method is to divide the total stress in an element into two components; singular and non-singular terms. The former is associated with the stress intensity factor and the latter is the stress induced by the neighboring crack. Such stress division is not possible by traditional means.

6. Various novel numerical solutions for interacting 3D cracks are presented. These solutions will be useful for the standardization of such complicated defect configurations.

Author's Contribution

Publication I: Interaction effect of adjacent small defects on the fatigue limit of a medium carbon steel

The author performed all the experiments including the specimen preparation, artificial defect introduction as well as the data analyses of the experimental results. The author prepared the manuscript including writing, figures and tables.

Publication II: The influence of interacting small defects on the fatigue limits of a pure iron and a bearing steel

The author performed all the experiments including the specimen preparation, artificial defect introduction as well as the data analysis of the experimental results. The author completed a literature survey on the non-propagating crack size as a function of Vickers hardness. The author prepared the manuscript including writing, figures and tables.

Publication III: An efficient stress intensity factor evaluation method for interacting arbitrarily shaped 3D cracks

The author developed a method for the evaluation of interacting 3D crack analysis. The author contributed to the model design and analyzed the numerical results. The author prepared the manuscript including writing, figures and tables.

1. Introduction

1.1 Fatigue assessment

Modern steel structures and vehicles, such as ships, should have excellent energy efficiency, without the loss of load carrying capacity, in order to meet the sustainable development goals. Thus, industries require developed lightweight structures in addition to more advanced materials with high cleanliness. Components subject to repetitive loads are prone to fatigue failure. Such a failure is caused by the initiation and growth of small fatigue cracks which eventually result in the complete failure of the component. Small cracks initiate from natural discontinuities and defects in the material, such as non-metallic inclusions [1-4], casting defects [1, 5-7], surface roughness [1, 8-10] and welds [11-13]. Recently the significant reduction in the fatigue strength of additively manufactured (AM) materials have highlighted the importance of defect tolerance in fatigue critical components [14-19]. Fig. 1.1 shows examples of complex shaped defects that acted as fracture origins in AM materials [14].

Figure 1.1. Defects at the fracture origins of AM specimens. [14].

Fatigue strength assessment commonly utilizes $S-N$ curves [20]. As shown in Fig. 1.2 it describes a relationship between the alternating stress and the number of cycles to failure. The stress corresponding to an abrupt change in the slope is the fatigue limit, which can be determined accurately for most steels. The specimens tested at the fatigue limit show no signs of failure even after the application of more than 10 million cycles. In practice, the fatigue limit is determined from the non-propagation condition of cracks that have emanated from small defects. Hence, even if a small defect acts as a crack initiation site, but the crack becomes non-propagating at the fatigue limit, the final state is still regarded as a crack. Consequently, small defects can be considered to be

mechanically equivalent to small cracks [1]. This is very important because it allows us to approach the small crack problem from a fracture mechanics viewpoint, i.e. relevant use of stress intensity factor (SIF), regardless of the actual shape of the original defect. It is worth noticing that small cracks are also termed short cracks in technical literature; see e.g. [21]. For the sake of consistency and clarity, the small crack terminology is used thorough this work.

A non-propagating crack (NPC) appears only at the very narrow stress range at and just below the fatigue limit. The plain specimen fatigue limit can be estimated as $1.6HV$, which is valid for $HV < 400$ [1]. The NPC size tends to decrease with increasing hardness although there is large scatter. In addition, it has been suggested that defect orientation [22], stress ratio [23, 24] and microstructure [1] can influence the size and location of non-propagating cracks. However, notwithstanding other factors, a non-propagating crack usually tends to appear as a result of plasticity-induced crack-closure [25]. Thus, HV , which reflects a materials resistance to plastic deformation, can be one of the material properties most relevant in the description of non-propagating crack characteristics.

Figure 1.2. Schematic S-N curve typical for steels.

1.2 Small fatigue cracks

Traditional notch effect theories, based on the theory of elasticity, stress concentration factors and stress gradients, are applicable to notches having root radius larger than 1 mm [1]. However, as notch size decreases these theories are no longer valid, because the notch depth becomes of the same order as the fatigue-damaged zone at the notch root. A similar phenomenon occurs in the case of small cracks. Typically, the fatigue limit is associated with the threshold stress intensity factor range, ΔK_{th} , which is stated to be a material constant for a constant stress ratio, R . This is correct for the cases where linear-elastic fracture mechanics (LEFM) is valid, i.e. for so-called long cracks. LEFM assumes that the similitude concept holds. Similitude means that if the SIF's of cracks are the same, their crack growth rate and plastic zones are equal, and the small-scale yielding condition holds. The small-scale yielding condition means that the plastic zone size is small compared to the crack size. Since the SIF is a function of stress and crack length, similitude is no longer valid for very small cracks, because the small-scale yielding condition is not satisfied. This causes

the decrease in ΔK_{th} for small cracks as crack length decreases. Thus, small cracks have size-dependent ΔK_{th} [1], see Fig. 1.3. This decrease in ΔK_{th} was pointed out by Frost et al. in [26], Kitagawa and Takahashi [27], and Kobayashi and Nakazawa [28]. The relationship between crack size and threshold stress range is commonly described by the Kitagawa-Takahashi (K-T) diagram [27], see Fig. 1.4. The first linear part is associated with the plain specimen fatigue limit. The second linear part is the region where LEFM applies. The non-linear small crack region is between these two linear parts. A proper K-T diagram should report two important crack sizes. The maximum size of non-critical crack size a_1 and the transition size for small and long cracks a_2 . Both must be determined experimentally, since they are influenced by the material properties, stress ratio, loading type and so on [1].

Alternatively, information in the K-T diagram can be presented using threshold stress intensity factor range, ΔK_{th} , on the vertical axis, see Fig. 1.5. This representation was introduced by Tanaka [29, 30] and is called the cyclic R-curve. The cyclic R-curve suggests that the ΔK_{th} consists of two components; an intrinsic $\Delta K_{0, th}$ that is associated with the crack initiation limit and a crack opening component ΔK_{op} which is related to crack closure effect. [31].

Figure 1.3. The threshold stress intensity factor range is constant for long cracks but has size-dependency in the small crack region.

Figure 1.4. Schematic K-T diagram.

Figure 1.5. Schematic cyclic R-curve.

1.3 Fatigue limit prediction, the $\sqrt{area}$ parameter model

When LEFM is applicable, the fatigue limit can be determined based on the constant ΔK_{th} . Since LEFM is not valid in small crack region, assuming $\Delta K_{th} = \text{constant}$ would lead to a critical error in the fatigue limit evaluation. Murakami & Endo have established a widely used model, the $\sqrt{area}$ parameter model, for the fatigue limit evaluation of small cracks [32]. The model conveniently requires only two variables: Vickers hardness, HV , which reflects the materials resistance against plastic deformation and the $\sqrt{area}$ of a defect projected normal to the maximum principal stress. The equation for this model has the form

$$\sigma_w = C \frac{(HV + 120)}{(\sqrt{area})^{1/6}} \quad (1)$$

where C is 1.43 for a surface defect, 1.41 for a defect in touch with the surface and 1.56 for an internal defect. The σ_w is the predicted fatigue limit in [MPa], HV is the Vickers hardness of the matrix and $\sqrt{area}$ is the square root of the projected area of the defect on the plane normal to the maximum principal stress in [μm]. The model is straightforward to use when the *area* of a defect is known. However, if multiple cracks behave together as a larger single defect, then the actual effective area is more difficult to determine.

1.4 Defect interaction

Structural steels contain various material irregularities and natural defects, which cause local stress concentrations and from which fatigue cracks tend to initiate. Two defects in close proximity to each other may affect local stress distributions, and thus, begin to interact. Typical fracture mechanics models are applicable only for a single crack. Although the defect interaction problem has been a general concern among fatigue researchers for decades, it is not well understood or systematically examined. Perhaps the reasons for this relate to the necessity for extremely complicated analyses and time-consuming and costly experimental research. Although closed form solutions for SIF's for 3D cracks are very limited [33, 34], several solutions have been obtained by means of various numerical techniques, such as the Finite Element Method (FEM) [35, 36], the Body Force Method (BFM) [37-40], the Boundary Element Method [41], Kachanov's approximation method [42, 43], Eshelby's equivalent inclusion method [44, 45] and Lagrangian finite difference method [46]. Among these methods, FEM is the most popular. The main challenges in FEM are that the whole domain must be divided into elements, a very fine mesh must be introduced at the regions near the cracks and, often, special singular elements must be used. Such requirements increase the CPU time enormously or the accuracy remains unclear if coarse mesh is used. It is easy to see that SIF's for complex shaped cracks are even more difficult to obtain, and the complexity increases yet further when interacting cracks are involved. Other numerical techniques also have their difficulties, since they often require extremely complicated mathematical formulation, the treatment of singular integrals is troublesome, and the analysis code must be self-created. On the other hand, once suitable code is created the analysis, using for example BFM, is very fast and accurate. However, the generalization of such codes for interacting and arbitrarily shaped 3D cracks is extremely difficult.

2. Scope of work

2.1 Research objectives

Current design rules for defect interaction rely on a British standard [47], which provides analytical interaction criteria for steels based on the crack length, depth and proximity; see Fig. 2.1. The criteria in the standard are based on the elastic stress analyses. Since such analyses require only two material parameters, Young's modulus E and Poisson's ratio ν that are nearly constants for all steels, the criteria in the standard can be considered material-independent. Although the influence of defects on the fatigue strength in different materials is comprehensively studied, the applicability of the standard's interaction criteria to various materials and defect shape configurations has not been systematically investigated.

Schematic flaws	Criteria for interaction	Effective dimensions after interaction
i) Coplanar surface flaws	$s \leq 2c_1$ for a_1/c_1 or $a_2/c_2 > 1$ $s \leq \max. \{0.5a_1, 0.5a_2\}$ for a_1/c_1 and $a_2/c_2 < 1$ $(c_1 < c_2)$	$a = \max. \{a_1, a_2\}$ $2c = 2c_1 + 2c_2 + s$

Figure 2.1. Interaction criteria for interacting surface defects in British standard [47].

Therefore, in order to examine the defect interaction phenomena in engineering materials, the first part of this thesis will provide an insight into the material's effect in interaction phenomena. The experiments were carried out using specimens having two small artificial surface defects close to each other. Three different materials with four different hardness's were used to examine the materials effect on interaction in terms of HV . The HV is considered to be the most relevant material parameter, since it reflects a material's resistance against plastic deformation, and it has a linear correlation with fatigue limit as described in the previous chapter. In addition, the interaction criteria in the standard is size-independent, i.e. it uses only the relative dimensions of cracks and the spacing between the cracks. Since small crack behavior differs from that of long cracks, this work investigates whether the criteria in the standard is valid for small cracks. In the second part of this thesis an efficient numerical method to evaluate the SIF's accurately for interacting 3D surface cracks is introduced.

Since fracture mechanics-based design criteria are often based on critical SIF values, it is important to be able to compute SIF's accurately – and efficiently.

2.2 Limitations

Due to the lack of prior experimental investigation on the influence of defect interaction on the fatigue limit, the simplest possible problems are selected for this work. These simple problems would act as excellent references for further, more advanced, detailed and specific investigations of defect interaction problems. In addition, simple problems reduce the number of variables that can potentially introduce ambiguities and uncertainties into the results, which might make them difficult to understand and explain precisely with the limited experimental data available. For these reasons, the interaction between just two adjacent defects is examined in this thesis. Moreover, the round shape of the fatigue specimen used would cause discrepancies between analytical assumptions made, if the roundness of the specimen began to affect the interaction effect of several adjacent defects. In addition, only surface defects are examined in this work. This is because the desired surface defect configurations can be introduced with existing equipment, their behaviour can be monitored during the test and crack sizes can be measured accurately. Surface defects are also the defects most detrimental to fatigue strength and are thus the most relevant type of defect to investigate. Stress ratio $R = -1$ is applied throughout this work. Defects that can be considered equivalent to small cracks were used, in order to simulate the real fatigue problem with natural material defects. In the second part of the work, where an efficient numerical method is developed, the simplified crack shapes are used in order to validate the model. This numerical study ignores the material plasticity effect, and thus, numerical investigations of the combined effect of crack shape and material is left for future work.

3. Experimental and numerical methods

3.1 Experimental procedure

3.1.1 Materials and specimen preparation

The objective of this work is to examine defect interaction in materials of varying strength levels, the materials were thus selected based on their hardness, *HV*. Three materials with *HV* between 110 and 710 were used; a medium carbon steel JIS-S45C, a bearing steel JIS-SUJ2 and a pure iron JIS-SUY1. The materials are hereafter identified without the prefix “JIS” (Japanese Industrial Standard). The chemical compositions and mechanical properties of each material are presented in Tables 1 and 2, respectively. The *HV*’s were determined as the average of ten measurements at 9.8 N. The scatter of the ten *HV* measurements was $\pm 15\%$. Microstructures of all materials are shown in Fig. 3.1. Materials are introduced in more detail below.

The medium carbon steel S45C is a widely used common structural steel and its fatigue properties are well known. Therefore, S45C was examined in Publication I. Before machining, the original S45C steel bars were annealed at 865°C for 30 minutes followed by air cooling. Before the introduction of drilled holes, the manufactured specimens were electropolished in order to remove a work-affected layer with residual stresses. A special feature of S45C steel is that it has a dual-phase microstructure, which may have an influence on the NPC location and characteristics.

A bearing steel SUJ2 and a pure iron SUY1 are materials with uniform microstructure that were examined in Publication II. As SUY1 has large variation in grain size, its effect was also indirectly examined in Publication II. Since the *HV* of the as-received SUY1 (*HV*=165) was close to the *HV* of a previously examined S45C (*HV* = 186), some SUY1 specimens were annealed to obtain a lower *HV*. The resulting *HV* was 110. In order to distinguish the differently heat-treated SUY1 specimens, annealed SUY1 specimens are hereafter named as A-SUY1 and non-annealed ones as NA-SUY1. The as-received NA-SUY1 was cold rolled and no heat treatments were applied. A-SUY1 specimens were annealed at 600°C for one hour, followed by furnace-cooling at room temperature. The gage-section surface was mirror-polished with a diamond paste in the case of SUY1. SUJ2 has a very fine martensitic microstructure. Initially, the SUJ2 was heat-treated at 840°C for one hour in a

deoxidizing gas, and subsequently oil-quenched and tempered at 240°C for two hours to obtain an HV of 710. The gage-section surface was electro-polished for SUJ2.

Figure 3.1. Microstructure of (a) S45C, (b) NA-SUY1, (c) A-SUY1 and (d) SUJ2.

Table 1. Chemical compositions of materials used (mass-%).

Material		Chemical composition (mass-%)						
S45C	C	Si	Mn	P	S	Fe		
	0.43	0.22	0.78	0.014	0.004	balanced		
SUY1	C	Si	Mn	P	S	Cu	Ni	Cr
	0.004	< 0.01	0.25	0.01	0.004	0.01	0.02	0.02
SUJ2	C	Si	Mn	Cr	Ti	O		
	1.00	0.26	0.36	1.44	0.002	0.0006		

Table 2. Mechanical properties of materials used. $\sigma_{0.2}$ is 0.2% proof stress, σ_y is yield stress, σ_b is tensile strength and HV is Vickers hardness.

Material	$\sigma_{0.2}$ or σ_y (MPa)	σ_b (MPa)	Reduction of area (%)	HV
S45C	339	620	54	186
NA-SUY1	350	420	unknown	165
A-SUY1	260	313	71	110
SUJ2	2131	2323	3	710

Figure 3.3. Configuration of artificial defects: (a) drilled holes and (b) sharp notches. Axial directions are indicated by red marks.

3.1.3 Fatigue testing

Fatigue tests were performed using servo-hydraulic testing machines under fully-reversed, tension–compression loading (stress ratio, $R = -1$), at test frequencies of 10–20 Hz. Each fatigue limit was defined as the maximum stress amplitude at which a specimen ceased to fail after 10^7 cycles. Each specimen was used only once at the constant stress amplitude. The first stress amplitude of each test series was chosen so that the specimen is assumed to fail. Fatigue limits were determined by testing at stress steps of 5–20 MPa. An example of stress step selection is as follows. The S45C specimen having drilled hole configuration $(d_1, d_2, s) = (100, 100, 50)$ μm failed at 180 MPa and runout at 170 MPa without non-propagating cracks. At 175 MPa, the existence of non-propagating cracks was confirmed and 175 MPa was determined to be the fatigue limit. Fatigue tests were periodically interrupted in order to observe crack initiation and growth by the plastic replica method.

In a tension-compression fatigue test, bending misalignment of the specimen can easily lead to under-estimation of the fatigue life and fatigue limit. To avoid this difficulty, four strain gages were applied to the smooth section near the gripping fixture and the alignment was carefully adjusted in each fatigue test.

3.1.4 Results analysis procedure

The fracture surfaces of failed specimens were inspected in order to detect the fracture origin. The fracture origins were at the artificial defects, as desired. Non-failed specimens were removed carefully from the testing machine, washed with acetone to remove debris and the non-propagating cracks were inspected by plastic replica and optical microscope. Then the shapes of non-propagating cracks were obtained by breaking the specimens. Some non-failed S45C specimens were heat treated (400°C for 6 hours) to obtain a darker oxide layer on the free surfaces in order to examine the 3D shapes of non-propagating cracks. After heat treatment, specimens were broken using stress ratio $R = 0.1$. A positive stress ratio was used in order to avoid contact with the initial fracture surfaces. In some cases, the oxide layer was not very clear and thus in later tests another method [48] was successfully applied in order to create marker bands. In addition, a large breaking stress amplitude was applied to ensure the marker lines become clearer on the fracture surface. SUY1 specimens were broken by impact loading at -196°C , at which the steel breaks in a brittle manner due to low-temperature embrittlement. Unfortunately, some specimens broke from locations other than the non-propagating crack plane and therefore the shapes of those non-propagating cracks are not shown. SUJ2 specimens were not broken since they contained no non-propagating cracks and because they are very difficult to break controllably.

3.2 Stress Component Division Method

3.2.1 Modeling principles and theoretical background

In order to study the influence of crack shape on crack interaction this work introduced the Finite Element -based method for interacting arbitrarily shaped 3D cracks in solids in Publication III. This method is named as the *Stress Component Division Method*, SCDM. It provides an efficient tool for SIF analysis using common commercially available FEM software, such as ABAQUS, and a relatively coarse mesh. Considering linear-elastic problems, SCDM utilizes the superposition principle shown in Fig. 3.4. Although the SIF's for problems in Fig. 3.4 (a) and (c) are the same, the stress distributions are different, as illustrated in Fig. 3.5. The total stress in a crack tip element can be divided into two components, a singular term and a non-singular term both of which are included, for example, in a constant stress element. The singular term is associated with the SIF whereas the non-singular term is obtained based on the stress which already exists at the same element by assuming that the crack does not exist. In FEM, the non-singular term is dominant and interferes with the accurate determination of SIF based on the singular term. Thus, the key of the SCDM is to extract the non-singular term from the total stress, after which only the singular term remains. With the help of SCDM, this work presents interaction factors for various surface crack geometries and configurations. Moreover, the conversion of size-independent SIF solutions to the small crack model, the $\sqrt{area}$ parameter model [32], is introduced. This work was motivated by the previous study, where a similar method was successfully applied to 2D cracks by Murakami [49]. In his work, Murakami established the original SCDM principle. However, since only single cracks were analyzed, it was necessary to calibrate the reference term (the denominator in Eq. 2) using various mesh sizes. In the end, analyzing interacting cracks using SCDM is not laborious because no calibration is needed. In other words, in an interaction problem, one can directly compare the FEM results of a two-crack problem and a single-crack problem. This will be explained in next chapter.

Figure 3.4. Superposition principle.

Figure 3.5. Stress distributions for problems in Fig. 3.4 (a) and (c).

3.2.2 Numerical modeling by FEM

By comparing the two stress components with those of a basic single crack for which an exact SIF is known, the interaction factor is obtained. In the case of a single crack, the non-singular stress is equivalent to the remote stress. However, in the interacting crack problem, the neighboring crack contributes to the non-singular stress field. In the problem of two cracks, first the non-singular term at the tip of an imaginary crack is calculated by solving the problem with only one crack (Cases B and C in Fig. 3.6). Secondly, the problem with two cracks is solved to obtain the total stress at the crack tip element (Case A in Fig. 3.6). Finally, the non-singular term is subtracted from the total stress, after which only the singular term remains. In practice, the equation for SIF of A1 point can be written as

$$K_{A1} = \frac{(A_{\text{tip}} - A_{\text{i,tip}})}{(A_{0,\text{tip}} - \sigma_0)} K_{A0}, \quad (2)$$

where K_{A1} is the stress intensity factor at point A1, K_{A0} is the stress intensity factor of a single crack, σ_0 is the remote stress and other notations refer to stresses at the centroids of crack tip elements as illustrated in Fig. 3.6. SIF at point B2 is obtained in a similar manner. From Eq. 2 the interaction factor is determined as

$$\gamma = \frac{(A_{\text{tip}} - A_{\text{i,tip}})}{(A_{0,\text{tip}} - \sigma_0)}. \quad (3)$$

Since the ratio of stresses is used, the possible error in the obtained stresses will vanish. This allows the convenient use of relatively coarse mesh.

The SIF solutions for non-elliptical cracks can be obtained when the SIF for similar elliptical crack and the stresses at the crack tip elements are known. For instance, the SIF for a single rectangular crack (Fig. 3.6) can be obtained as $K_{\text{rectangle}} = A_{0,\text{tip, rectangle}} * K_{\text{ellipse}} / A_{0,\text{tip, ellipse}}$. Using the known solution $K_{\text{ellipse}} = 0.730\sigma_\infty\sqrt{\pi a}$ [37], we obtain $K_{\text{rectangle}} = 0.809\sigma_\infty\sqrt{\pi a}$ at A1 point.

Figure 3.6. Notations for Equation 2.

Traditionally, the stresses at the crack tip are obtained by using very fine meshes and singular elements. Since the exact stresses at the crack tip are unbounded, the SIF is obtained by extrapolating the results with different meshes until reasonable accuracy is obtained. Such analyses tend to be troublesome in interaction problems, because the two cracks *simultaneously* influence the stress distributions in the vicinity of other cracks. Consequently, using traditional methods, it is impossible to separate the stress distribution caused by a crack itself and the magnification of the stress distribution caused by a neighboring crack.

The above-mentioned challenges relating to the used element size was overcome in the proposed method since the ratio of stresses is obtained from equal element sizes. Thus, the element sizes and types need to be kept constant thorough this investigation in order to maintain the consistency of the results. The smaller crack, having surface length of $2a$, is kept as the reference dimension. The smallest mesh in the vicinity of the cracks was $0.05a$ and the mesh size smoothly increased towards the exterior of the solid. This element size was able to model deformation and stress with sufficient accuracy based on the sensitive analysis carried out with different element sizes. It is worth noticing that SCDM does not require stress convergence analysis since it utilizes the ratio of the stresses of two different geometry configurations using the same fixed element size. The element used was an 8-node brick C3D8R, which was found to be the most convenient based on numerical analysis with different element types. Elements having fewer degrees of freedom than C3D8R sometimes gave unrealistic stress values at the crack tip elements, whereas more advanced elements, with larger number of integration points, increased the CPU time significantly without improving accuracy. An example of a model is shown in Fig. 3.7.

Figure 3.7. An example of an FEM model.

Since this thesis focuses on steels, a Young's modulus of $E = 210$ GPa, suitable for steels, was used. All the FE analyses used Poisson's ratio $\nu = 0.0$. The reason for this is given below. Within the context of 3D linear-elasticity, the nature of a singularity close to a free surface at the tip of a surface crack depends on the value of the Poisson's ratio. However, experiments [50, 51] suggest that this may not be very significant compared with, for example, the differences in the state of stress, *i.e.* plane stress or plane strain. In practice, a through-crack is often regarded to be under either a plane stress or plane strain condition, depending on the thickness of the plate, although a three-dimensional problem in linear-elasticity is involved, where the state of stress is near plane strain in the interior and plane stress close to the free surface. In fact, the changes in the nature of a singularity close to the free surface introduced by the Poisson's ratio effect for plane stress problems is generally ignored in practice [38]. Therefore, it is acceptable to ignore the Poisson effect close to the free boundary and present numerical results for zero Poisson's ratio only. In addition, the usual definition of the SIF does not apply if Poisson's ratio is non-zero; see the detailed analysis by Murakami & Ishida [52]. Moreover, the BFM solutions [37-39] used for comparison in this work also use $\nu = 0.0$.

According to, for example, Åman [37] and Murakami & Nemat-Nasser [38], the location of $K_{\max}$ depends on the aspect ratio of a crack. When aspect ratio, *i.e.* the ratio of crack depth and half of the cracks surface length, is 1.0, the $K_{\max}$ is never located at the deepest point of the crack [37, 38]. Since the cracks used in this study had aspect ratios of 1.0, the SIF's at the cracks deepest points are not reported. In addition, the interaction factors are often very small at the deepest points [37, 38], and therefore the SIF's at the surface points of interacting cracks are more relevant to investigate.

4. Results

4.1 Crack initiation and growth in finite life regime

The cracks emanated from the artificial defects. At the stress amplitudes that were higher than the fatigue limit, the cracks coalesced forming a larger single crack. The number of cycles to coalescence is defined as the coalescence life, N_{co} . The growth before and soon after coalescence was typically irregular. After the coalesced crack acquired a stable elliptical shape, it continued its propagation in a smoother manner until the specimen failed. The detailed crack initiation and growth observation is done only for selected examples of S45C steel, while fatigue strength analysis is presented for all material and defect configurations.

4.1.1 Medium carbon steel S45C

S - N data for S45C are shown in Figs. 4.1 (a) and (b). In the finite life regime, the fatigue test results demonstrated a clear tendency. When spacing between the defects was either $s = d_2$ or $s = 1.5d_2$ (i.e. when the interaction effect was negligibly small), the finite life was always shorter for the case $s = 1.5d_2$ than for $s = d_2$ at the same stress amplitude. In addition, the difference in life was almost constant at all stress levels, whether $s = d_2$ or $s = 1.5d_2$. These phenomena may appear to be strange, but can be explained by the significant stepwise jumps in stress intensity factors with respect to the original spacing between the defects. Simply put, as defects lie further away from each other at the start, they form a larger crack after coalescence, resulting in a decrease in the remaining life. However, early coalescence did not necessarily signify shorter life as is shown in Fig. 4.2. For instance, the lives of cases $s = 0.5d_2$ and $s = 1.5d_2$ are nearly the same, but the cracks coalesced after a small number of cycles when $s = 0.5d_2$. Illustrative crack growth behaviors in dual-phase S45C steel are presented in Fig. 4.3. In the case of $s = 1.5d_2$ (Fig. 4.3 (a)), the interaction effect should be negligible. However, soon after outer point O_1 initiation a crack initiated from inner point I_1 and grew rapidly towards the other defect. The failed specimen was etched for observation of the microstructure in the vicinity of the defects to determine the reason for crack initiation and the somewhat aggressive growth from point I_1 . The discovery of a large ferrite grain adjacent to point I_1 explains the crack behavior, since cracks propagate more easily into ferrite grains than into pearlite structures. Another example is shown in Fig. 4.3 (b). In this case, where $s = d_2$, analytically, any interaction effect should be still negligible.

(a)

(b)

Figure 4.1. S - N data for S45C (a) $d_1 = d_2$, (b) $d_1 = 2d_2$.

Figure 4.2. Influence of spacing between the defects on the coalescence and crack coalescence life.

However, cracks initiated from points O_1 and O_2 and grew during many cycles, while crack lengths of $94 \mu\text{m}$ and $157 \mu\text{m}$ were observed. A crack finally initiated from point I_2 after 8.4×10^5 cycles. The two cracks soon coalesced ($N_{co} = 8.6 \times 10^5$) and the specimen eventually failed ($N_f = 1.26 \times 10^6$). Thus, considering these facts, it can be concluded that the interaction effect was indeed negligible and that the critical distance concept applies. Conversely when $s < d_2$, first cracks never initiated from points O_1 or O_2 . The fatigue limit (190 MPa) for the case $s = 1.5d_2$ was 10 MPa higher than the fatigue limit for a similar single defect (180 MPa), which failed at 190 MPa after 4.0×10^6 cycles. The fatigue limit for $s = d_1 = d_2 = 100 \mu\text{m}$ was equal to that for a similar single defect.

With defects of different sizes, crack behavior was not as clear. In these cases, the cracks initially tended to grow near the sub-surface, especially at points between the defects. This means that nothing was observed on the surface between the defects until the cracks had already coalesced. However, the coalescence life, N_{co} , was relatively long when $s \geq d_2$ and consequently, the interaction effect was not strong. Nevertheless, when $s = 0.5d_2$, defects of different sizes coalesced after a small number of cycles, which indicates strong interaction. The fatigue limit was 170 MPa regardless of the spacing between the defects when $d_1 = 2d_2$.

Figure 4.3. Crack growth examples (a) $(d_1, d_2, s) = (100, 100, 150) \mu\text{m}$, $\sigma_a = 200 \text{ MPa}$, (b) $(d_1, d_2, s) = (100, 100, 100) \mu\text{m}$, $\sigma_a = 190 \text{ MPa}$.

4.1.2 Pure iron SUY1

Figure 4.4 shows the S - N diagrams for SUY1 with uniform microstructure. Regarding the NA-SUY1 samples, the fatigue limit at the analytical critical distance ($s = d_2$) was the same as that of a single defect (160 MPa). When $s = 0.5d_2$, the fatigue limit decreased to 140 MPa, due to crack coalescence. Moreover, when $s = 1.5d_2$, the fatigue limit was marginally lower than that of a single defect (150 MPa). This is most probably due to a normal scatter, which typically results from differences in local microstructure. The local microstructure causes scatter not only in the fatigue limit but also in the fatigue life. For example, in Fig. 4.4 (a), the life of a single-hole specimen is shorter than that of a specimen with two holes under the same loading condition. On the other hand, the fatigue limit of A-SUY1 was 140 MPa regardless of the spacing between the defects, see Fig. 4.4 (b).

Figure 4.4. S - N data for (a) non-annealed SUY1 and (b) annealed SUY1.

4.1.3 Bearing steel SUJ2

In addition to drilled holes, sharp notches were also investigated in the case of bearing steel SUJ2 with fine martensitic microstructure. The fatigue limit of SUJ2 was greatly dependent on the defect shape, see Fig. 4.5. With regard to the drilled holes, the fatigue limit was 500 MPa, whereas in the presence of sharp notches, the fatigue limit was only 380 MPa ($s = 0.5d_2$ in both cases). It should be noted that the fatigue limit of SUJ2 was determined to be the crack initiation limit, controlled by the stress concentration of the defect.

Figure 4.5. S-N data for SUJ2.

4.2 Fatigue limit for interacting defects

The summary of predicted and experimentally obtained fatigue limits are shown in Table 3. Figure 4.6 shows the fatigue limits normalized by prediction values. It is shown that the $\sqrt{area}$ parameter model [28] can predict fatigue limits, even in the framework of interaction problems. Throughout this research, the effective prediction area was determined according to an assumption of the analytical critical distance in all cases. I.e., if $s < d_2$, the combined area of defects and the spacing between them is considered as $area_{eff}$, otherwise, only the area of the larger defect is used in the evaluation. A visual comparison between predicted and measured fatigue limits is presented in Figure 4.6. The results suggest that the $\sqrt{area}$ parameter model can apparently also predict the SUJ2 drilled-hole fatigue limit, that is, the crack initiation limit. However, since the $\sqrt{area}$ parameter model is based on fracture mechanics, it may be just pure coincidence that it can also predict the crack-initiation limit of a drilled hole. In fact, since a drilled hole behaved precisely like a blunt notch in SUJ2, it would have been more appropriate to use some of the well-established, fatigue-notch methods. The SUJ2 results are discussed in further detail later.

Figure 4.6. Comparison of the predicted and experimental fatigue limits.

Table 3. Summarized experimental results. Notations are shown in Fig. 3.3.

Material	Defect type (Fig. 3.3)	(d_1, d_2, s) [μm] (Fig. 3.3)	Schematic $area_{\text{eff}}$	$\sqrt{area}$ [μm]	$\sigma_{w,\text{pred}}$ [MPa]	$\sigma_{w,\text{exp}}$ [MPa]
$d_i = h_i$						
Annealed SUY1 ($HV = 110$)	Drilled hole	(200, 200, 200)	A	177	139	140
	Drilled hole	(200, 200, 300)	A	177	139	140
Non-annealed SUY1 ($HV = 165$)	Drilled hole	(200, -, -)	A	177	172	160
	Drilled hole	(200, 200, 100)	B	350	153	140
	Drilled hole	(200, 200, 200)	A	177	172	160
	Drilled hole	(200, 200, 300)	A	177	172	150
S45C ($HV = 186$)	Drilled hole	(100, -, -)	A	89	206	180
	Drilled hole	(100, 100, 50)	B	140	192	175
	Drilled hole	(100, 100, 100)	A	89	206	180
	Drilled hole	(100, 100, 150)	A	89	206	190
	Drilled hole	(200, 100, 50)	D	223	177	170
	Drilled hole	(200, 100, 100)	C	177	184	170
	Drilled hole	(200, 100, 150)	C	177	184	170
SUJ2 ($HV = 710$)	Drilled hole	(100, 100, 50)	B	140	562	500
	Sharp notch	(100, 100, 50)	B	140	562	380

4.3 Non-propagating cracks at the fatigue limit

4.3.1 Medium carbon steel S45C

Examples of the non-propagating cracks observed in S45C are illustrated in Fig. 4.7. The lengths of non-propagating cracks measured from the hole edges varied between 20 μm and 140 μm . In some cases, several hole pairs were drilled onto the surface of the same specimen, see Fig. 4.7 (a). When comparing the obtained non-propagating cracks in Fig. 4.7 (a), it is interesting to note that large pearlite bands completely prevented crack initiation and coalescence, as shown in Fig. 4.7 (a-4), even though there was clear evidence of the strong interaction effect when $s < d_2$. Therefore, in order to draw the correct conclusions, it is important to understand the scatter observed, even in a single specimen. Another interesting finding is that the crack in Fig. 4.7 (a-2) propagated into pearlite instead of ferrite after coalescence. This phenomenon is unlikely because when the crack attained a stable, semi-elliptical shape, the stress concentration was approximately equal at points O_1 and O_2 , but threshold conditions were much higher at O_1 due to the pearlite texture. It is possible that, after coalescence, the crack grew into the interior of the specimen and later propagated from the inside out towards the surface.

Three of the hole pairs in Fig. 4.7 (a) were clearly coalesced and behaved as larger single cracks at the fatigue limit. According to Fig. 4.7 (b), it is clear that the cracks behaved individually, whereas in Fig. 4.7 (c), the defects behaved jointly as a larger single crack. When the interaction effect was negligibly small, i.e., when $s \geq d_2$, cracks behaved as if they were isolated at the fatigue limit. However, when $s = 0.5d_2$, cracks coalesced after a small number of cycles, continued to grow as a single crack at some extent and became non-propagating at the fatigue limit. Figure 4.8 shows that the crack had stopped its propagation within the pearlite structure. Had this particular pearlite structure not existed, the crack closure in ferrite may not have been able to keep the crack non-propagating. In addition, had the pearlite structure been more closely located to the defects, the crack may have been able to penetrate through the pearlite, as a result of insufficient crack closure. On the other hand, had this large pearlite structure been located further away and the crack able to penetrate through ferrites, crack length may have become large enough to exceed threshold conditions, even in the pearlite structure, resulting in crack propagation to failure.

Figure 4.7. Non-propagating cracks: (a) $(d_1, d_2, s) = (100, 100, 50) \mu\text{m}$, (b) $(d_1, d_2, s) = (200, 100, 150) \mu\text{m}$, (c) $(d_1, d_2, s) = (200, 100, 50) \mu\text{m}$.

Figure 4.8 Crack initiation and non-propagation condition. $(d_1, d_2, s) = (200, 100, 50) \mu\text{m}$, $\sigma_a = \sigma_w = 170 \text{ MPa}$.

4.3.2 Pure iron SUY1

Despite heat treatment, the non-propagation of cracks was evident at the fatigue limit of SUY1, as illustrated in Fig. 4.9 (a-f). The non-propagating cracks in A-SUY1 ($HV=110$) were approximately 1-mm-long and artificial defects coalesced despite the spacing ($s = d_2$ or $1.5d_2$). Furthermore, with respect to A-SUY1, the fatigue limit was the same (140 MPa) regardless of the spacing between defects. Experiments with smaller spacings were not considered relevant, since the interaction was already confirmed to occur at the critical distance $s = d_2$ and even when $s = 1.5d_2$.

Regarding NA-SUY1 ($HV=165$), the defects behaved as individual cracks without coalescence at the fatigue limit when the spacing between defects was greater than the critical distance, *i.e.*, when $s > d_2$, whereas at $s \leq d_2$, the defects behaved together as a single larger crack, with non-propagating cracks coalescing at the fatigue limit. It is noteworthy that cracks emanating from NA-SUY1 ($HV=165$) grew transgranularly, while in A-SUY1 ($HV=110$), the cracks essentially grew along grain boundaries, see Fig. 4.9.

Figure 4.9. (Continued on next page).

Figure 4.9. Non-propagating cracks: (a) NA-SUY1, single defect; (b) NA-SUY1, $s = 1.5d_2$; (c) NA-SUY1, $s = d_2$; (d) NA-SUY1, $s = 0.5d_2$; (e) A-SUY1, $s = 1.5d_2$; (f) A-SUY1, $s = d_2$.

4.3.3 Bearing steel SUJ2

In contrast, in the context of bearing steel SUJ2 ($HV=710$), no non-propagating cracks were observed at the fatigue limit in all cases, see Fig. 4.10. Therefore, the crack initiation limit was also considered to be the fatigue limit. Interaction did not occur even at $s = 0.5d_2$, implying that the real critical distance for SUJ2 is considerably smaller. The author therefore elected not to investigate larger spacings.

Figure 4.10. (a) SUJ2, $s = 0.5d_2$, drilled holes; (b) SUJ2, $s = 0.5d_2$, sharp notches. The surfaces of SUJ2 specimens were electro-polished after the tests to confirm the absence of cracks.

4.4 SIF's for interacting arbitrarily shaped 3D cracks

In order to investigate analytically the effect of crack shape on the interaction effect, the FE-based SCDM was developed in this thesis. The numerical solutions for interacting 3D cracks are presented in this chapter. Three basic crack shapes with different configurations are used; elliptical, triangular and rectangular cracks. The SCDM is first validated by comparing the computed SIF's with known numerical solutions.

4.4.1 Validation of the SCDM

Before applying new numerical techniques to general problems, it is necessary to validate the models by comparing the numerical results with existing solutions. Figures 4.11 and 4.12 show the validation of some selected problems, for which SIF's are known. BFM solutions are from a previous work that focused on semi-elliptical cracks [37]. The results are in excellent agreement with the known numerical solutions. The differences with known numerical BFM solutions are typically less than 2%. Larger differences occurred in the case of triangular cracks, which is most probably due to the variation in $K_{\max}$ location. The obtained dimensionless SIF's, i.e. F -values, are shown in Table 4. F is determined as

$$F = K / \sigma_0 \sqrt{\pi a} \quad (4)$$

It is noted that the maximum SIF's of a triangular cracks are not at the surface points. Triangular cracks will be discussed in more detail later.

Figure 4.11. Interaction factors for similar rectangular, triangular and elliptical cracks. BFM values are from [37].

Figure 4.12. Interaction factors for uneven size elliptical cracks and comparison with BFM values [37].

Table 4. Dimensionless stress intensity factors for single cracks.

Crack Shape	F (current study)	F (ref)	Difference
Ellipse (Surface point)	0.730 [37]	0.732 [38]	0.2 %
Rectangle (Surface point)	0.809	0.793 [39]	2 %
Triangle (Surface point)	0.536	0.493 [39]	8%
Triangle ($K_{\max}$ point)	0.714	0.618* [39]	13%

*) In [39] it is assumed that the $K_{\max}$ location is at the midpoint of the triangular crack front. In this study, the $K_{\max}$ location is not at exactly the same point, which explains the differences in the obtained F -values.

4.4.2 Defect shape effect on interaction factor

Figure 4.13 shows interaction factors for uneven size rectangular, triangular and elliptical surface cracks. The interaction factors at B2 points are always larger than those at A1 points, because the larger crack has more influence on the stress field near the smaller crack. It should be noted that the magnitude of the interaction factor does not necessarily mean larger SIF, because SIF is also a function of crack length. Therefore, attention should be paid to the larger crack. Figure 4.15 shows the interaction factors at $K_{\max}$ points of triangular surface cracks. In the case cracks of the same size, the interaction factor at MA1 (= MB2) does not exceed 1.05 regardless of the distance between the cracks. The location of $K_{\max}$ element was found to change depending on the distance between the cracks. When $\varepsilon = 1.0$, the $K_{\max}$ element was the 7th element from the surface. With smaller distances, the $K_{\max}$ location moved closer to the surface, see Fig. 4.14. In the case of uneven size triangular cracks, the interaction factor at MA1 point was barely larger than 1.0, whereas the interaction factor at MB2 increased smoothly when the distance decreased.

Figure 4.13. Interaction factors for uneven size surface cracks.

Figure 4.14. Interaction factors of same and uneven size triangular surface cracks.

4.4.3 Interacting asymmetric cracks

Figures 4.15 and 4.16 show the interaction factors for asymmetric triangular surface cracks with the same aspect ratio. In Fig. 4.15, the interaction factor at A1 point increases smoothly when the distance between the cracks decrease, in a manner very similar to the case of symmetric triangular cracks, see Fig. 4.11. Conversely, Fig. 4.16 shows that the interaction factors, at every point investigated, are very close to 1.0 even when the distance between the cracks is very small.

Figure 4.15. Interaction factors for skewed triangular surface cracks.

Figure 4.16. Interaction factors for skewed triangular surface cracks.

4.4.4 Interacting mixed crack geometries

Figure 4.17 shows interaction factors for elliptical and rectangular surface cracks. The interaction factors of an elliptical crack are slightly higher than those of a rectangular crack. This is logical, because the ellipse has a smoother crack front than the rectangle and thus, the effect of the ellipse on the rectangle is smaller than that of the rectangle on the ellipse. Figure 4.18 shows the interaction factors for rectangular and triangular cracks. Although the $K_{\max}$ of a triangular crack is located at MB2 point, the interaction factor of B2 point is always higher than that of MB2 point. This also seems natural, because B2 point is closer to the rectangular crack and is therefore more affected by the disturbances in the stress field, due to the rectangular crack. Figure 4.19 shows the interaction factors for elliptical and triangular cracks. After comparing Figs. 4.18 and 4.19, their similarity becomes evident. Considering, for example the triangular cracks, it seems that the actual shape of neighboring cracks does not greatly influence the interaction factors. Such a result may be useful, because it allows modeling simplifications of more complex shaped cracks.

Figure 4.17. Interaction factors for elliptical and rectangular surface cracks.

Figure 4.18. Interaction factors for rectangular and triangular surface cracks.

Figure 4.19. Interaction factors for elliptical and triangular surface cracks.

4.4.5 Conversion to the $\sqrt{area}$ parameter model

All the SCDM results are size-independent. They use the most generic form of stress intensity factor: $K = F\sigma_0\sqrt{\pi a}$. However, considering the unique phenomenon of small crack initiation and their well-known size-dependent threshold SIF range, as discussed previously, LEFM methods cannot be applied to small-crack problems. Therefore, a conversion of size-independent solutions to the $\sqrt{area}$ parameter model [32] is provided here.

According to Murakami & Endo [32], the $K_{\max}$ of a small surface crack can be expressed by the following equation, regardless of the actual shape of the defect:

$$K_{\max} = 0.65\sigma_0\sqrt{\pi\sqrt{area}}, \quad (5)$$

where $area$ is the area of a crack projected to the plane perpendicular to the maximum principal stress in [m²]. In order to convert the F -values of three basic cracks used in this study to the $\sqrt{area}$ parameter model, we must make their areas equal, see Fig. 4.20. Then, we solve for F^* the following form of equations:

$$F\sigma_0\sqrt{\pi a} = F^*\sigma_0\sqrt{\pi\sqrt{area}}. \quad (6)$$

The computed values are shown in Table 5. The maximum difference is 9%, which is likely a result of somewhat ambiguous $K_{\max}$ location of triangular cracks. The differences in other problems are less than 5%. It should be noted that the Eq. 5 is semi-empirical, and its accuracy has been stated to be within 10% [32]. With these considerations in mind, we can say that the results presented here coincide very well with the $\sqrt{area}$ parameter model.

Figure 4.20. Equal areas of three basic cracks of this study.

Table 5. Dimensionless stress intensity factors and comparison with the $\sqrt{area}$ parameter model.

Crack Shape	F (current study)	F (ref)	Difference in F	F^* (current study)	F^* [32]	Difference in F^*
Ellipse	0.730	0.732				
(Surface point)	[37]	[38]	0.2 %	0.652	0.65	0.3%
Rectangle		0.793				
(Surface point)	0.809	[39]	2 %	0.680	0.65	4.4%
Triangle		0.618				
($K_{\max}$ point)	0.714	[39]	13%	0.714	0.65	9 %

5. Discussion

5.1 The role of non-propagating crack characteristics

This work revealed that the non-propagating crack characteristics had a great impact on defect interaction. The material-independent analytical interaction models are based on variations in elastic stress distributions and an increase in stress intensity factors due to the existence of neighboring defects. In view of the experimental findings presented in this study, it is clear that the analytical interaction criteria must be treated with caution in practical applications. This is because the behavior of interacting small defects at the fatigue limit varies between materials due to differences in the characteristics of non-propagating cracks. For example, it has been suggested that defect orientation [22], stress ratio [23, 24] and microstructure [1] can influence the size and location of non-propagating cracks. However, notwithstanding other factors, a non-propagating crack usually tends to appear as a result of plasticity-induced crack-closure [25]. Thus, HV , which reflects materials resistance to plastic deformation, can be one of the most relevant material properties in the description of non-propagating crack characteristics.

To illustrate this phenomenon, several datasets taken from the literature [22, 53-61] have been plotted in Fig. 5.1. All data were tested at $R = -1$. Figure 5.1 reveals that the size of a non-propagating crack tends to diminish with an increase in hardness, although a large scatter exists. Moreover, it is evident that a non-propagating crack seldom exists when $HV > 400$. During the course of this study, non-propagating cracks were also not observed at the fatigue limit in SUJ2 ($HV=710$). Since experimental data are limited and not every material can be tested individually, it is very difficult to provide the exact values of HV and/or non-propagating crack size for which certain interaction criteria are always applicable. This greatly complicates the defect interaction problem. However, regarding the experimental results presented here, it is possible to consider the

extreme cases of very low and very high HV , as well as intermediate HV cases separately.

Figure 5.1. Relative size of non-propagating crack as a function of HV . [22, 53-61].

5.2 Defect interaction in different materials

In order to examine the defect interaction in different materials, several materials having artificial small defects were tested. To investigate the minimum size of the detrimental defect in SUY1, which behaves as a fracture origin instead of the persistent slip bands in large grains, grain sizes were inspected based on the statistics of extremes [62] in a manner similar to that recorded in the literature [1]. Grain size analysis was undertaken for NA-SUY1. It was not repeated for A-SUY1 since grain size was not influenced by annealing, see Fig 3.1. The results of the grain size analysis are documented in Fig. 5.2. As shown in Fig. 3.1, the average grain size of SUY1 was approximately 60 μm , while the largest grain size was approximately 200 μm , as shown in Fig. 5.2. The result implied that a defect smaller than 200 μm would not be expected to become a fracture origin. Under fatigue loading, the fracture origin in low- and moderate-strength materials is typically the largest grain on the surface. The persistent slip bands create cumulative dislocations within a grain, eventually penetrate the entire grain and become a crack [1]. Therefore, larger grains would naturally result in larger naturally occurring cracks and defects smaller than the largest grain would not become fracture origins [1]. Consequently, drilled holes of 200 μm were employed during the SUY1 experiments. It should be noted that the absolute size of defects does not influence the analytical interaction criteria,

since the interaction (or not) of cracks is determined by the ratio, s/d_2 , (*i.e.*, if $s/d_2 > 1$, the interaction effect is negligible).

Figure 5.2. Grain size analysis of non-annealed SUY1 based on statistics of extremes.

In the context of the softest material tested, A-SUY1 ($HV=110$), the non-propagating cracks are of particular interest, on display in Figs. 4.9 (e) and (f). The total length of coalesced non-propagating cracks, regardless of the spacing between defects, was approximately 1 mm, *i.e.*, five times larger than the initial defect size. According to analytical interaction criteria, the defects should be acknowledged to be individual if the spacing between them is larger than the diameter of the smaller defect, *i.e.*, when $s > d_2$. Since the defects definitely behaved in the manner of a larger single defect, even when $s = 1.5d_2$, the analytical interaction criteria apparently does not apply to materials with non-propagating cracks as long as those observed for A-SUY1. It is interesting to note that the fatigue limit was the same (140 MPa) regardless of the spacing between defects and despite crack coalescence. Nevertheless, if the spacing between defects were to increase beyond a certain value, crack coalescence might begin to decrease the fatigue limit, as the newly-formed coalesced crack may exceed the material's crack-propagation threshold simply due to its size. From a fatigue limit viewpoint, this implies that the real critical distance of such a material is in fact longer than the analytical one.

Conversely in the high-strength bearing steel SUJ2 ($HV=710$), unlike in every other material tested, the interacting defects behaved clearly as individual defects, even when the spacing between them was smaller than the analytical critical distance. No defect interaction was observed for $s = 0.5d_2$, which is significantly smaller than the proposed analytical critical distance, $s = d_2$. If the spacing between the defects had been further decreased, it could be expected

that the stress in the region between the defects would reach the crack initiation limit and the defects would have coalesced. As referenced in Fig. 5.1, since non-propagating cracks seldom exist when $HV > 400$, the fatigue limit of such higher-strength steels is determined more or less by crack initiation. Consequently, the real critical distance for high-strength steels correlates with the crack-initiation threshold.

In future work it may be important to determine the threshold condition for crack initiation and to estimate the real critical distance in materials exhibiting non-propagating cracks larger than the initial defect size. In addition, the interaction effect under diverse loading conditions is of interest, as well as an interaction study considering problems including different configurations of defect shape, orientation and location.

5.2.1 Small crack or large crack?

The evaluation of fatigue crack growth and its threshold via linear elastic fracture mechanics (LEFM) postulates that the small-scale yielding condition holds. This requires that the plastic zone size is sufficiently small compared to the crack size and remains constant under a constant stress intensity. In such a regime, ΔK_{th} becomes independent of crack size. On the other hand, when the defect is small and applied stress level is high, the plastic zone is no longer small compared to the crack size. In such a regime, the crack-tip yielding satisfies the large-scale yielding condition, where ΔK_{th} is decreased with a decrease in crack size. The $\sqrt{area}$ parameter model targets the latter case. Specifically, this model is applicable to the small crack, but not to the large crack.

As exhibited in Fig. 4.6, the fatigue limit of the SUJ2 that had a drilled hole was in good agreement with the prediction by the $\sqrt{area}$ parameter model (*i.e.*, $\sigma_{w,exp}/\sigma_{w,pred} = 0.89$). Conversely, the fatigue limit of the sharp-notched SUJ2 was well below the predicted value (*i.e.*, $\sigma_{w,exp}/\sigma_{w,pred} = 0.68$). This phenomenon can be understood as follows. Fig. 5.3 depicts the ΔK_{th} for various materials as a function of the defect/crack size [I, II, 57, 63-67]. As pointed out by Chapetti [68], the small/large crack-transition size is more or less dependent on HV , *i.e.*, the higher the HV , the smaller the transition size. According to Fig. 5.3, the transition point of $\sqrt{area}$ is approximately 50 μm for SUJ2, which is smaller than the size of the defects used in the present tests. Therefore, the $\sqrt{area}$ parameter model overestimates the crack growth threshold in the large crack regime (dashed lines in Fig. 5.3). In addition, in the present experiments, the fatigue limits of the drill-holed and sharp-notched specimens were both determined from crack initiation that is controlled by the stress concentration of the defect. As a result, the fatigue limit of a drill-holed specimen is higher than that of a sharp-notched specimen.

Figure 5.3. ΔK_{th} for various materials. $\Delta K_{th,lc}$ is associated with long cracks [I, II, 57, 63-67].

In the small crack regime, the ΔK_{th} is straightforward to estimate using the $\sqrt{area}$ parameter model [32]:

$$\Delta K_{th} = 3.3 \times 10^{-3} (HV + 120) (\sqrt{area})^{1/3}, \quad (7)$$

where HV is Vickers hardness in $[kgf/mm^2]$ and $\sqrt{area}$ is the area of the initial defect projected to the plane perpendicular to the maximum principal stress in $[\mu m]$. It should be noted that the $area$ is the area of the initial defect, i.e. it does not include the NPC size. This is important, because the NPC size can be determined after the test, whereas the fatigue limit and ΔK_{th} should be assessed before the test. However, if experimental results are available, the ΔK_{th} can be determined using equation

$$\Delta K_{th} = 0.65 \Delta \sigma_w \sqrt{\pi \sqrt{area}}, \quad (8)$$

where $\Delta \sigma_w$ is the stress amplitude at the fatigue limit in $[MPa]$ and $\sqrt{area}$ is in $[m]$ [32].

Another method to determine ΔK_{th} is by means of the cyclic R-curve, which can be conveniently constructed by using a single specimen [31]. The ΔK_{th} consists of two components, the intrinsic $\Delta K_{o,th}$ that is associated with the crack initiation limit and the ΔK_{op} , which is related to the crack closure effect. Although the cyclic R-curve has potential for assessing small crack problems, it needs further development before it can be applied to 3D cracks and interaction problem. For example, the SIF of a 3D crack is more difficult to determine than that of a 2D edge crack, which has been used in the cyclic R-curve development. As a 3D crack grows, only the crack growth along the surface can be measured, but cracks grow also towards the specimen interior. Whereas a single 3D crack usually grows maintaining a stable semi-elliptical shape, interacting small cracks may produce a shape that varies significantly from the semi-elliptical shape. In comparison with the $\sqrt{area}$ used in abscissa in Fig. 5.3, the cyclic R-

curve uses crack extension, Δa , instead. Therefore, the ΔK_{th} should be also presented in terms of crack length, a . Moreover, the ΔK_{th} based approach may be complicated in the interaction problems when multiple NPC's with varying sizes and thus with varying SIF's are present in the *same* specimen, see e.g. Fig. 4.7 (a), but on the other hand, the specimen should have a unique ΔK_{th} [1]. However, it would be interesting future work to develop the cyclic R-curve to consider also 3D cracks and interacting cracks.

5.2.2 Crack or notch?

As expounded by Nisitani [69] and shown in Fig. 5.4, the critical notch-root radius, ρ_0 , is a material-dependent parameter that determines whether a defect behaves like a blunt notch or as a crack. If the notch root radius ρ is smaller than ρ_0 , two fatigue limits, one for crack initiation and the other for crack propagation, can be distinguished. In a variety of materials, the ρ_0 typically measures about 0.4-0.5 mm, but can decrease to less than 0.1 mm as tensile strength increases [69]. The experimental results imply that the ρ_0 of SUJ2 ($\sigma_{0.2} = 2131$ MPa) is likely to be so small that the crack initiation and propagation limits become indistinguishable and that the fatigue limit was determined from crack initiation. The values of ρ_0 may also vary depending on the notch size for small defects, *i.e.*, length or depth of the notch [69]. In fact, Schönbauer [66] performed ultrasonic fatigue tests of stainless steels (UTS = 878-1030 MPa) and established the ρ_0 to be between 25-100 μm . The author is not aware of any method reliably to predict ρ_0 other than experimentally, especially for the defects smaller than 1 mm. In cases where the notch root radius in a component is larger than ρ_0 , notch-based methods to assess fatigue strength are preferred rather than fracture mechanics-based approach. However, in practice, as was pointed out by Murakami [1], the defects generally include locally higher stress concentrations and therefore fracture mechanics-based evaluation can provide a reasonable prediction in many instances.

Figure 5.4. Crack initiation and propagation limits versus the inverse of notch root radius [69].

In the moderate-strength steels NA-SUY1 ($HV=165$) and S45C ($HV=186$), the analytical critical distance criteria seem to hold well when compared with the two afore-mentioned extreme cases. However, the dual-phase microstructure

tends to exhibit larger scatter in non-propagating crack size and location(s), leading to larger scatter in fatigue limit. For a material with such a complex microstructure, the selection of conservative criteria is recommended, *i.e.*, the interaction should be assumed to occur even when $s = d_2$.

5.2.3 The effect of local microstructure on crack behaviour

Major studies have been undertaken in the past about the manner in which small cracks behave in inhomogeneous microstructures, e.g., in ferritic-pearlitic structures [70-74]. However, discussions about microstructural effects gain greater importance with regard to crack interaction, because of their undisputed effect on crack closure, where cracks penetrate different microstructures and produce the various characteristics of non-propagating cracks. In this study, detailed observation of crack growth and non-propagation behaviors demonstrate that the interaction between two defects is influenced not only by stress concentrations/intensities, but also by the microstructural nature of ferrite and pearlite structures. The influences of stress concentration and the stress intensity factor after crack initiation are naturally the mechanical basis for the interaction of two defects. However, the existence of pearlite or ferrite at the edges of drilled holes also has a definite influence on crack initiation and crack growth behavior through the pearlite. Thus, the details of crack behavior can be more fully understood from precise observation of the microstructure. It must also be noted that a pearlite structure cannot be the absolute resistance to crack propagation. A detailed discussion about the factors influencing threshold properties has been offered by Murakami [75]. If $\Delta K_{\text{eff,th}}$ exceeds the ΔK_{th} for pearlite, a crack continues to grow, as proven by the observations in this study. Although the $\Delta K_{\text{eff,th}}$ values are different locally, in ferrite or pearlite, depending on where the crack front exists, propagation or non-propagation of the crack always occurs due to competition between *the local effective stress intensity factor range* and *the local effective threshold stress intensity factor range*.

Evidence of such crack penetration can be seen in pearlite, followed by non-propagation in ferrite and, in some other cases, non-propagation in pearlite. If the ΔK_{th} is defined for an individual pair of holes, different threshold values may be defined for four pairs of two holes in one material, since the sizes of the non-propagating cracks observed at the fatigue limit (same stress amplitude) all varied at the four hole pairs, see Fig. 4.7 (a). Moreover, no cracks were observed at some of the hole pairs in Fig. 4.7 (a) indicating a stress intensity factor of zero. However, such an approach is not appropriate from the viewpoint of fatigue strength prediction. In these cases, failure or non-failure and propagation or non-propagation occur within a narrow stress amplitude range, specifically, within ± 10 MPa [1]. If the threshold stress intensity factor is calculated based on the individual crack after fatigue testing, the values naturally contain a scatter, even for one specimen. Furthermore, this calculation cannot be performed before fatigue testing.

Confusion has arisen from the unique crack behavior observed, influenced by a scatter of microstructure, with respect to the definition of a small crack as being either microstructurally small or mechanically small. This topic has been explored in detail by Murakami [1], in terms of the fatigue crack behavior in the annealed 0.46% C carbon steel specimen containing 12 small holes with diameters of 40 or 50 μm . The holes were drilled onto the specimen surface at four equidistant points on three circumferences, each equally spaced in the axial direction. Non-propagating cracks were not always observed. There were holes without cracks, as well as holes with either one or two non-propagating cracks on the periphery of the holes. The same phenomenon was observed during the experiments for this research. Therefore, in order to predict the fatigue limit or fatigue threshold for materials containing defects which may interact, the precise phenomenon related to crack growth behavior must be understood.

The specific results of the current study will serve as a good example for understanding both the fatigue phenomenon and fatigue strength prediction, particularly where small defects are concerned. Considering the aforementioned observations, the local dual-phase microstructure should be regarded as a critical factor in the understanding of crack interaction problems. According to analysis, stress intensity factors increase exponentially as the space between cracks decreases. This means that once a crack initiates from points I_1 or I_2 , stress intensity factors at these points increase significantly. However, crack initiation from points O_1 or O_2 may not be so crucial because as the crack grows, the shape of the crack also changes, and stress intensity factors vary along the crack front. Hence, it may be possible to develop sufficient crack closure before the cracks become so large that they begin to interact. It was revealed that in the case of 0.45% C steel, the scatter of microstructure, i.e., of ferrite and pearlite, influences the scatter of local fatigue strength and, ultimately, the fatigue limit. The nature of the interaction between two defects in this microstructure is influenced primarily by the distance between the pearlite structures, as produced by the rolling process during steelmaking. It was shown that if the interaction effect was negligible ($s \geq d_2$), pearlites on the hole periphery can prevent the local cracks from initiating at the fatigue limit. On the other hand, if the interaction effect was enhanced ($s < d_2$), defects coalesced at the fatigue limit and behaved as a larger single defect from the outset, regardless of the local microstructure between the defects.

In Publication I it was shown that if $d_1=2d_2$, only the larger defect would control the fatigue limit, regardless of the existence of the smaller defect and of the spacing between the defects. It is as yet unclear whether this applies to any material and what the boundary conditions actually are for the size effect in interaction. If it were possible to generate a general rule for the size effect in interaction, which allowed us to ignore the smaller defects, it would simplify the interaction problem significantly.

5.3 Numerical modeling of defect interaction

In order to compute SIF's of arbitrarily shaped interacting 3D cracks accurately, the numerical FE-based method was developed. The proposed SCDM is convenient in the evaluation of arbitrarily shaped interacting 3D cracks. The major advantages of SCDM are that it requires no fine meshes, singular elements or accurate determination of the stresses in the vicinity of cracks. In addition, modern FE software can be used, which allows the utilization of the versatility of FEM. SCDM uses the ratio of stresses, see Eq. 2, which makes it very insensitive to mesh details, errors in the absolute stress values at the crack tips or Poisson's ratio effect. The method also makes it easy to compare complex shaped cracks with simpler shapes. Such comparison gives justification to convenient modeling simplifications.

As shown in Fig. 2.1, the interaction criteria in the standard BS 7910:2013 + A1:2015 [47] considers only the aspect ratios of the defects instead of their actual shapes. Although the complex shaped surface cracks typically reach semi-elliptical shape after crack initiation and continue growing maintaining the semi-elliptical shape, in some problems it is important to evaluate the SIF of the original crack shape precisely. The fatigue limit of SUJ2, which was determined from the crack initiation, serves as an excellent example.

If one considers, for example, the cases shown in Figures 4.15 and 4.16, the aspect ratios of both crack configurations are equal, but the interaction factors differ significantly, especially when the distance between cracks is relatively small. In Fig. 4.15, the interaction factors are nearly the same as the corresponding interaction factors of a symmetric triangular crack. However, Fig. 4.16 shows that the interaction factors, at every points investigated, are very close to 1.0 even when the distance between the cracks is very small. According to the standard [47], the problems in Figs. 4.15 and 4.16 are equivalent since the aspect ratios of cracks are the same. However, if the crack initiation must be taken into consideration, it is recommended to evaluate the SIF's precisely by considering the actual crack shape configurations.

6. Conclusions

In this work, the defect interaction was examined experimentally and analytically. In experimental investigations, two defects were introduced onto the surface of a medium carbon steel S45C, a pure iron SUY1 and a bearing steel SUJ2 specimen in order to investigate defect interaction in different materials and its influence on the fatigue limit. In addition, the FE-based method was developed in order to accurately evaluate the SIF's of arbitrarily shaped interacting 3D cracks. The key point of the method is to divide the stress at an element into two components, singular and non-singular terms, which is not possible with traditional FEM procedures. The main findings of this work are as presented below:

- The characteristics of non-propagating cracks significantly affect crack coalescence and consequently, the behavior of interacting cracks, thereby rendering the interaction phenomena complicated. Non-propagating crack size tends to decrease with the increased hardness of a material, although there is a large scatter. The analytical critical distance applies only for moderate HV materials. In practice, it appears that the critical distance is smaller than the analytical distance in high-strength steels ($HV > 400$) and *vice versa*, for low-strength steels.
- Defects coalesced at the fatigue limit in annealed SUY1 ($HV=110$), regardless of the spacing between them. Non-propagating cracks were approximately five times larger than the initial defect size. The fatigue limit and non-propagating crack sizes were independent of the spacing between the defects.
- Since no non-propagating cracks were observed in SUJ2 ($HV=710$), the fatigue limit was determined from crack initiation. Neither defect type, drilled holes or sharp notches, interacted at the fatigue limit even when the spacing between the defects was less than the analytical critical distance.
- Regarding S45C ($HV=186$); in the cases where $d_1 = 2d_2$, fatigue limits were identical, regardless of the spacing between the defects. Thus, only the larger crack determines the fatigue limit.

- Local microstructure causes scatter in the results insofar as crack initiation and crack closure development are concerned. The scatter band is within $\pm 10\text{MPa}$ in the case of 0.45% C steel. Hence, defects can be treated as single defects when $s > d_2$. Otherwise, it is conservative to consider multiple defects as one larger single defect in fatigue limit evaluations. Naturally, the degree of homogeneity of the microstructure is considered to be relative to the size of the defects.
- Murakami's $\sqrt{area}$ parameter model also accurately predicted the fatigue limits of interacting small defects. The only exception involved the bearing steel SUJ2, the fatigue limit of which was identified as the crack initiation limit. Thus, the fracture mechanics-based $\sqrt{area}$ parameter model was not applicable. The $\sqrt{area}$ was determined based on the analytical interaction criteria.
- The proposed new FE-based method is applicable to interacting 3D crack problems. The key point of the method is to divide the stress at an element into two components, singular and non-singular terms, which is not possible with traditional FEM procedures. The singular term is associated with the SIF whereas the non-singular term is obtained based on the stress which already exists at the same element by assuming that the crack does not exist.
- The numerical results obtained by the developed method SCDM are in excellent agreement with known numerical solutions. The differences with known solutions are typically in the order of 0.2-5%. The new method does not require special elements or fine meshes, because it uses the ratio of SIF's. Therefore, if an error exists in an element, it will be divided by the same error.
- The numerical results could be especially useful in defect tolerance problems of AM materials, since AM defects often have very complex shapes. As the natural defects in materials are typically considered equivalent to small cracks, the simple conversion of size-independent solutions for a small crack model, the $\sqrt{area}$ parameter model, is also presented in this work.

For future work, the interaction effect under diverse loading conditions is of interest, as well as interaction studies considering problems including different defect shapes, orientations and location configurations. Other work of interest would be to determine the threshold condition for crack initiation and to estimate the real critical distance in materials exhibiting non-propagating cracks larger than the initial defect size. In addition, In Publication I it was shown that if $d_1=2d_2$, only the larger defect would control the fatigue limit,

regardless of the existence of the smaller defect and of the spacing between the defects. Notwithstanding this, it is as yet unclear whether this applies to any material and what the boundary conditions for the size effect in interactions actually are. It would be interesting to apply SCDM to real crack geometries. In addition, experimental validation of the SIF's for complex shaped cracks will be important. Moreover, numerical analyses considering more than two cracks and also parallel, non-adjacent and other crack configurations would be interesting topics of future research.

References

- [1] Murakami, Y. (2019). Metal fatigue: effects of small defects and nonmetallic inclusions. Academic Press.
- [2] Murakami, Y., Kodama, S., & Konuma, S. (1989). Quantitative evaluation of effects of non-metallic inclusions on fatigue strength of high strength steels. I: Basic fatigue mechanism and evaluation of correlation between the fatigue fracture stress and the size and location of non-metallic inclusions. *International Journal of Fatigue*, 11(5), 291-298. DOI 10.1016/0142-1123(89)90054-6.
- [3] Karr, U., Schuller, R., Fitzka, M., Schönbauer, B., Tran, D., Pennings, B., & Mayer, H. (2017). Influence of inclusion type on the very high cycle fatigue properties of 18Ni maraging steel. *Journal of Materials Science*, 52(10), 5954-5967.
- [4] Matsunaga, H., Sun, C., Hong, Y., & Murakami, Y. (2015). Dominant factors for very-high-cycle fatigue of high-strength steels and a new design method for components. *Fatigue & Fracture of Engineering Materials & Structures*, 38(11), 1274-1284. DOI 10.1111/ffe.12331.
- [5] Endo, M., & Yanase, K. (2014). Effects of small defects, matrix structures and loading conditions on the fatigue strength of ductile cast irons. *Theoretical and Applied Fracture Mechanics*, 69, 34-43. DOI 10.1016/j.tafmec.2013.12.005.
- [6] Léopold, G., Nadot, Y., Billaudeau, T., & Mendez, J. (2015). Influence of artificial and casting defects on fatigue strength of moulded components in Ti-6Al-4V alloy. *Fatigue & Fracture of Engineering Materials & Structures*, 38(9), 1026-1041. DOI 10.1111/ffe.12326.
- [7] Serrano-Munoz, I., Buffiere, J. Y., Verdu, C., Gaillard, Y., Mu, P., & Nadot, Y. (2016). Influence of surface and internal casting defects on the fatigue behaviour of A357-T6 cast aluminium alloy. *International Journal of Fatigue*, 82, 361-370. DOI 10.1016/j.ijfatigue.2015.07.032.
- [8] Takahashi, K., & Murakami, Y. (1999). Quantitative evaluation of effect of surface roughness on fatigue strength. *Engineering Against Fatigue*, 693-703.
- [9] Murakami, Y., Tsutsumi K., & Fujishima, M. (1996). Quantitative evaluation of effect of surface roughness on fatigue strength. *Trans. Jpn. SOC. Mech. Eng. Ser. A*, 63597, 1124-1131.
- [10] Kawamoto, M., Nishioka, K., Inui, T., & Tsuchiya, F. (1955). The influence of surface roughness of specimens on fatigue strength under rotating-beam test. *J Soc Mater Sci Jpn*, 4, 42-48.

- [11] Madia, M., Schork, B., Bernhard, J., & Kaffenberger, M. (2017). Multiple crack initiation and propagation in weldments under fatigue loading. *Procedia Structural Integrity*, 7, 423-430. DOI 10.1016/j.prostr.2017.11.108.
- [12] Otegui, J. L., Kerr, H. W., Burns, D. J., & Mohaupt, U. H. (1989). Fatigue crack initiation from defects at weld toes in steel. *International Journal of Pressure Vessels and Piping*, 38(5), 385-417. DOI 10.1016/0308-0161(89)90048-3.
- [13] Leitner, M., Murakami, Y., Farajian, M., Remes, H., & Stoschka, M. (2018). Fatigue Strength Assessment of Welded Mild Steel Joints Containing Bulk Imperfections. *Metals*, 8(5), 306. DOI 10.3390/met8050306.
- [14] Yamashita, Y., Murakami, T., Mihara, R., Okada, M., & Murakami, Y. (2018). Defect analysis and fatigue design basis for Ni-based superalloy 718 manufactured by selective laser melting. *International Journal of Fatigue*, 117, 485-495. DOI 10.1016/j.ijfatigue.2018.08.002.
- [15] Gao, W., Zhang, Y., Ramanujan, D., Ramani, K., Chen, Y., Williams, C.B., Wang, C.C., Shin, Y.C., Zhang, S. & Zavattieri, P.D. (2015). The status, challenges, and future of additive manufacturing in engineering. *Computer-Aided Design*, 69, 65-89. DOI 10.1016/j.cad.2015.04.001.
- [16] Molaei, R., & Fatemi, A. (2018). Fatigue design with additive manufactured metals: issues to consider and perspective for future research. *Procedia Engineering*, 213, 5-16. DOI 10.1016/j.proeng.2018.02.002.
- [17] Spierings, A. B., Starr, T. L., & Wegener, K. (2013). Fatigue performance of additive manufactured metallic parts. *Rapid Prototyping Journal*, 19(2), 88-94. DOI 10.1108/13552541311302932.
- [18] Beretta, S., & Romano, S. (2017). A comparison of fatigue strength sensitivity to defects for materials manufactured by AM or traditional processes. *International Journal of Fatigue*, 94, 178-191. DOI 10.1016/j.ijfatigue.2016.06.020.
- [19] Masuo, H., Tanaka, Y., Morokoshi, S., Yagura, H., Uchida, T., Yamamoto, Y., & Murakami, Y. (2018). Influence of defects, surface roughness and HIP on the fatigue strength of Ti-6Al-4V manufactured by additive manufacturing. *International Journal of Fatigue*, 117, 163-179. DOI 10.1016/j.ijfatigue.2018.07.020.
- [20] Wöhler, A. (1870). Über die Festigkeitsversuche mit Eisen und Stahl. *Zeitschrift für Bauwesen*, 20, 73-106.
- [21] Zerbst, U., Vormwald, M., Pippan, R., Gänser, H-P., Sarrazin-Baudoux, C., & Madia, M. (2016). About the fatigue crack propagation threshold of metals as a design criterion – A review. *Engineering Fracture Mechanics*, 153, 190-243. DOI 10.1016/j.engfracmech.2015.12.002.
- [22] Lorenzino, P., Okazaki, S., Matsunaga, H., & Murakami, Y. (2015). Effect of small defect orientation on fatigue limit of carbon steels. *Fatigue & Fracture of Engineering Materials & Structures*, 38(9), 1076-1086. DOI:10.1111/ffe.12321.
- [23] Kondo, Y., Sakae, C., Kubota, M., & Kudou, T. (2003). The effect of material hardness and mean stress on the fatigue limit of steels containing small defects. *Fatigue & Fracture of Engineering Materials & Structures*, 26(8), 675-682. DOI 10.1046/j.1460-2695.2003.00656.x.

- [24] Wada, K., Abass, A., Okazaki, S., Fukushima, Y., Matsunaga, H., & Tsuzaki, K. (2017). Fatigue Crack Threshold of Bearing Steel at a Very Low Stress Ratio. *Procedia Structural Integrity*, 7, 391-398. DOI 10.1016/j.prostr.2017.11.104.
- [25] Elber, W. (1971). The significance of fatigue crack closure. In *Damage tolerance in aircraft structures*. ASTM International.
- [26] N.E. Frost, N.E., Pook L.P., & and Denton, K. (1971). A fracture mechanics analysis of fatigue crack growth data for various materials. *Engineering fracture mechanics*, 3, 109-126.
- [27] Kitagawa, H., & Takahashi, S. (1979). Fracture mechanics approach to very small fatigue crack growth and to the threshold condition. *Trans. Jpn. SOC. Mech. Eng. A*, 45 (399), 1289-1303.
- [28] Kobayashi, H., & Nakazawa, H. (1972). A stress criterion for fatigue crack propagation in metals. *Proc. 1st Int. Conf. Mech. Behav. Mater*, Kyoto, 11, 199-208.
- [29] Tanaka, K., & Nakai, Y. (1983). Propagation and non-propagation of short fatigue cracks at a sharp notch. *Fatigue & Fracture of Engineering Materials & Structures*, 6, 315-327. DOI 10.1111/j.1460-2695.1983.tb00347.x
- [30] Tanaka, K., & Akiniwa, Y. (1988). Resistance-curve method for predicting propagation threshold of short fatigue cracks at notches. *Engineering Fracture Mechanics*, 30 (6), 863-876. DOI 10.1016/0013-7944(88)90146-4.
- [31] Maierhofer, J., Kolitsch, S., Pippan, R., Gänser, H-P., Madia, M., & Zerbst, U. (2018). The cyclic R-curve – Determination, problems, limitations and application. *Engineering Fracture Mechanics*, 198, 45-64. DOI 10.1016/j.engfracmech.2017.09.032.
- [32] Murakami, Y. & Endo, M. (1983). Quantitative evaluation of fatigue strength of metals containing various small defects or cracks. *Engineering Fracture Mechanics*, 17(1), 1-15. DOI 10.1016/0013-7944(83)90018-8.
- [33] Kassir, M., & Sih, G. C. (1975). Three-dimensional crack problems: A new selection of crack solutions in three-dimensional elasticity (Book), Leiden, Noordhoff, International Publishing, Mechanics of Fracture, vol. 2.
- [34] Sneddon I.N. (1946). The distribution of stress in the neighbourhood of a crack in an elastic solid. *Proceedings of Royal Society of London, A* 187, 229-260.
- [35] Gupta, P., Pereira, J.P., Kim, D.J., Duarte, C.A. & Eason, T. (2012). Analysis of three-dimensional fracture mechanics problems: A non-intrusive approach using a generalized finite element method. *Engineering Fracture Mechanics*, 90, 41-64.
- [36] Silva, R. C. C., Guerreiro, J. N. C., & Loula, A. F. D. (2007). A study of pipe interacting corrosion defects using the FEM and neural networks. *Advances in Engineering Software*, 38(11-12), 868-875. DOI 10.1016/j.advengsoft.2006.08.047.
- [37] Åman, M. (2015). Interacting three-dimensional surface cracks under tensile loading, Master's Thesis, available: <https://aaltodoc.aalto.fi/handle/123456789/16692> (last accessed date 11 November 2019).

- [38] Murakami, Y., & Nemat-Nasser, S. (1982). Interacting dissimilar semi-elliptical surface flaws under tension and bending. *Engineering Fracture Mechanics*, 16(3), 373-386. DOI 10.1016/0013-7944(82)90115-1.
- [39] Murakami, Y., & Nemat-Nasser, S. (1983). Growth and stability of interacting surface flaws of arbitrary shape. *Engineering Fracture Mechanics*, 17(3), 193-210. DOI 10.1016/0013-7944(83)90027-9.
- [40] Noda, N. A., Kobayashi, K., & Oohashi, T. (2001). Variation of the stress intensity factor along the crack front of interacting semi-elliptical surface cracks. *Archive of Applied Mechanics*, 71(1), 43-52. DOI 10.1007/s004190000113.
- [41] Denda, M. & Dong, Y. (1997). Complex variable approach to the BEM for multiple crack problems. *Computer methods in applied mechanics and engineering*, 141, 247-264.
- [42] Kachanov, M. (1987). Elastic solids with many cracks: a simple method of analysis. *International Journal of Solids and Structures*, 23, 23-43.
- [43] Lekesiz, N., Katsube, N., Rokhlin, S.I. & Seghi, R.R. (2013). The stress intensity factors for a periodic array of interacting coplanar penny-shaped cracks. *International journal of solids and structures*, 50, 186-200.
- [44] Xiao, Z., Lim, M. & Liew, K. (1994). Stress intensity factors for two coplanar pennyshaped cracks under uniaxial tension. *International journal of engineering science*, 32, 303-311.
- [45] Shodja, H., Rad, I. & Soheilifard, R. (2003). Interacting cracks and ellipsoidal inhomogeneities by the equivalent inclusion method. *Journal of the Mechanics and Physics of Solids*, 51, 945-960.
- [46] Chen, Y. (1975). Numerical computation of dynamic stress intensity factors by a Lagrangian finite-difference method (the HEMP code). *Engineering Fracture Mechanics*, 7, 653-660.
- [47] Standard, B. (2015). BS 7910: 2013+ A1: 2015 Guide to methods for assessing the acceptability of flaws in metallic structures. *London, UK: BSI Stand Publ.*
- [48] Schijve J. (2015). The application of small overloads for fractography of small fatigue cracks initiated under constant-amplitude loading, *International Journal of Fatigue* 70, 63–72.
- [49] Murakami, Y. (1976). A simple procedure for the accurate determination of stress intensity factors by finite element method, *Engineering Fracture Mechanics*, Volume 8, Issue 4, 643-655.
- [50] Nisitani H. & Morimitsu T. (1976). Estimation of crack propagation property by the rotating-bending fatigue test of specimens with a small hole. *Journal of the Japan Society of Mechanical Engineers JSME*, 42. 325-334.
- [51] Kawano H., Endo T. & Murakami Y. (1980). Propagation of cracks emanating from microhole of 40 μm diameter, *Prelim. Proc. Japan, Journal of the Japan Society of Mechanical Engineers JSME* No 800-11. 179-181

- [52] Murakami Y. & Ishida M. (1985). Analysis of stress intensity factors for arbitrarily shaped surface crack and stress distribution near surface. *Trans. JSME*, Ser. A, Vol. 51, No. 464.
- [53] Murakami, Y., Fukuda, S., & Endo, T. (1978). Effect of Micro-hole on Fatigue Strength [1st Report, Effect of Micro-hole (Dia.: 40, 50, 80, 100 and 200 μm) on the Fatigue Strength of 0.13% and 0.46% Carbon Steels]. *Trans. Jpn. Soc. Mech. Eng. Ser. I*, 44(388), 4003-4013.
- [54] Murakami, Y., & Endo, T. (1981). The effects of small defects on the fatigue strength of hard steels. *Materials, Experimentation and Design in Fatigue*, 431-440.
- [55] Yamada, K., Kim, M. G., & Kunio, T. (1986). Tolerant microflaw sizes and non-propagating crack behaviour. In *EGF1*.
- [56] Murakami, Y., & Toriyama, T. (1992). Application of the $\sqrt{\text{area}}$ parameter model to fatigue strength evaluation of steels containing various artificial defects (holes, cracks and complex defects), *Proc. 21th Fatigue Symp., SOC. Mater. Sci. Jpn.*, pp. 127-130.
- [57] Schönbauer, B. M., Yanase, K., & Endo, M. (2017). The influence of various types of small defects on the fatigue limit of precipitation-hardened 17-4PH stainless steel. *Theoretical and Applied Fracture Mechanics*, 87, 35-49. DOI 10.1016/j.tafmec.2016.10.003.
- [58] Habib, K., Koyama, M., Tsuchiyama, T., & Noguchi, H. (2017). Fatigue crack non-propagation assisted by nitrogen-enhanced dislocation planarity in austenitic stainless steels. *International Journal of Fatigue*, 104, 158-170. DOI 10.1016/j.ijfatigue.2017.07.019.
- [59] Schönbauer, B. M., Perlega, A., Karr, U. P., Gandy, D., & Stanzl-Tschegg, S. E. (2015). Pit-to-crack transition under cyclic loading in 12% Cr steam turbine blade steel. *International Journal of Fatigue*, 76, 19-32. DOI 10.1016/j.ijfatigue.2014.10.010.
- [60] Li, B., Koyama, M., Sakurada, E., Yoshimura, N., Ushioda, K., & Noguchi, H. (2016). Potential resistance to transgranular fatigue crack growth of Fe-C alloy with a supersaturated carbon clarified through FIB micro-notching technique. *International Journal of Fatigue*, 87, 1-5. DOI 10.1016/j.ijfatigue.2016.01.003.
- [61] Matsunaga, H., Murakami, Y., Kubota, M., & Lee, J. H. (2003). Fatigue strength of Ti-6Al-4V alloys containing small artificial defects. *Journal of the Society of Materials Science, Japan*, 52(12Appendix), 263-269.
- [62] Gumbel, E. J. (2012). *Statistics of Extremes*. Courier Corporation.
- [63] Nisitani, H., & Endo, M. (1985). Fatigue strength of carbon steel specimen having an extremely shallow notch (discussion based on successive observation). *Trans. Japan Soc. Mech. Eng.*, 51(464), 1008-1016.
- [64] Nisitani, H., & Endo, M. (1985). Unifying treatment of notch effects in fatigue. *Trans. Jpn. Soc. Mech. Eng. Ser. I*, 51, 784-789.
- [65] Nisitani, H., & Endo, M. (1988). Unified treatment of deep and shallow notches in rotating bending fatigue. In *Basic Questions in Fatigue: Volume I*. ASTM International.

- [66] Schönbauer, B. M., & Mayer, H. (2019). Effect of small defects on the fatigue strength of martensitic stainless steels. *International Journal of Fatigue* 127, 362-375. DOI doi.org/10.1016/j.ijfatigue.2019.06.021.
- [67] Wada, K. (2015). Effects of small defect size and stress ratio on fatigue limit of bearing steel SUJ2 (in Japanese), Bachelor Thesis, Kyushu University, Japan.
- [68] Chapetti, M. D., Tagawa, T., & Miyata, T. (2003). Ultra-long cycle fatigue of high-strength carbon steels Part II: Estimation of fatigue limit for failure from internal inclusions. *Materials Science and Engineering: A*, 356(1-2), 236-244. DOI 10.1016/S0921-5093(03)00136-9.
- [69] Nisitani, H. (1968). Size effects of branch point and fatigue limit of carbon steel in rotary bending tests. *Transactions of the Japan Society of Mechanical Engineers A*, 34(259), 371-382.
- [70] Goto, M (1994). Statistical investigation of the behaviour of small cracks and fatigue life in carbon steels with different ferrite grain sizes. *Fatigue & Fracture of Engineering Materials & Structures*, 17, 635-649. DOI:10.1111/j.1460-2695.1994.tb00262.x.
- [71] Goto, M., Yanagawa, Y., & Nisitani, H. (1990). Property in the Initiation and Statistical Propagation of Microcracks of a Heat-Treated 0.45% C Steel. *JSME*, Series 1, Vol. 33 (2), 235-242.
- [72] Marx, M., Schaefer, W., & Welsch M.T. (2012). The microstructure as crack initiation point and barrier against fatigue damaging. *International Journal of Fatigue*, 41, 57–63.
- [73] De Los Rios, E.R., Mohamed, H.J., & Miller, K.J. (1985). A micro-mechanics analysis of short fatigue crack growth. *Fatigue & Fracture of Engineering Materials & Structures*, 8, 49–63.
- [74] Graig, D., Ellyin, F., & Kujawski, D. (1995). The behaviour of small corner cracks in a ferritic/ pearlitic steel: experiments and analysis. *Fatigue & Fracture of Engineering Materials & Structures*, 18, 861–873.
- [75] Murakami, Y. (2012). Material defects as the basis of fatigue design. *International Journal of Fatigue*, 41, 2–10

Defects and their interaction often significantly reduce the fatigue strength of the machine components. The accurate determination of stress intensity factors of 3D cracks is complicated. The complexity increases when multiple cracks are in close proximity, since the cracks disturb the stress fields between them. Consequently, the single crack models are not directly applicable in crack interaction problems. This thesis will provide an accurate finite element based tool for interacting 3D crack analyses. Interaction effect was examined also experimentally in order to investigate the material's effect in interaction phenomena. It was revealed that the interaction effect varied greatly among different steels. As a conclusion, analytical and material-independent interaction criteria alone are insufficient in the fatigue strength evaluation of interacting crack problems. This thesis provides knowledge and guidance to improve the interaction criteria in real engineering structures.

ISBN 978-952-64-0199-7 (printed)

ISBN 978-952-64-0200-0 (pdf)

ISSN 1799-4934 (printed)

ISSN 1799-4942 (pdf)

Aalto University
School of Engineering
Department of Mechanical Engineering
www.aalto.fi

**BUSINESS +
ECONOMY**

**ART +
DESIGN +
ARCHITECTURE**

**SCIENCE +
TECHNOLOGY**

CROSSOVER

**DOCTORAL
DISSERTATIONS**